0.92853

ANL-91/39

Materials and Components
Technology Division
Materials and Components
Technology Division
Materials and Components
Technology Division
Materials and Components
Technology Division
**Materials and Components
Technology Division**
**Materials and Components
Technology Division**
**Materials and Components
Technology Division**
Materials and Components
Technology Division
Materials and Components
Technology Division
Materials and Components
Technology Division
Materials and Components
Technology Division
Materials and Components
Technology Division
Materials and Components
Technology Division
Materials and Components
Technology Division
Materials and Components
Technology Division
Materials and Components
Technology Division
Materials and Components
Technology Division

Three-Dimensional Nuclear Magnetic Resonance Imaging of Green-State Ceramics

by S. L. Dieckman, N. Gopalsami, P. Rizo,
J. M. Ford, A. C. Raptis, W. A. Ellingson,
D. M. Tracey, and V. K. Pujari

Argonne National Laboratory, Argonne, Illinois 60439
operated by The University of Chicago
for the United States Department of Energy under Contract W-31-109-Eng-38

Materials and Components
Technology Division
Materials and Components
Technology Division
Materials and Components
Technology Division
Materials and Components
Technology Division

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

Argonne National Laboratory, with facilities in the states of Illinois and Idaho, is owned by the United States government, and operated by The University of Chicago under the provisions of a contract with the Department of Energy.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Reproduced from the best available copy.

Available to DOE and DOE contractors from the
Office of Scientific and Technical Information
P.O. Box 62
Oak Ridge, TN 37831
Prices available from (615) 576-8401

Available to the public from the
National Technical Information Service
U.S. Department of Commerce
5285 Port Royal Road
Springfield, VA 22161

Distribution Categories:
Heat Engines
(UC-111);
Ceramics/Advanced Materials
(UC-332)

Argonne National Laboratory
9700 South Cass Avenue, Argonne Illinois 60439

ANL--91/39

DE93 000930

ANL-91/39

**THREE-DIMENSIONAL NUCLEAR MAGNETIC RESONANCE IMAGING OF
GREEN-STATE CERAMICS**

by

S. L. Dieckman, N. Gopalsami, P. Rizo,* J. M. Ford,
A. C. Raptis, W. A. Ellingson, D. M. Tracey,**
and V. K. Pujari**

Materials and Components Technology Division

September 1991

Work sponsored by

U.S. DEPARTMENT OF ENERGY
Assistant Secretary for Conservation and Renewable Energy
CTAHE Project,
Subcontract 86X-SB182C

Under subcontract from Norton Company

*L.E.T.I./Département Systèmes, C.E.A./C.E.N.G. 85X Avenue des
Martyrs 38041 Grenoble Cedex, France.

**Norton Company, Northboro, MA.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED ^{2D}

Contents

Abstract.....	1
1 Introduction.....	2
1.1 Objective.....	2
1.2 Background.....	2
2 Fundamentals of NMR.....	4
2.1 Principles of NMR.....	4
2.2 Principles of NMR Imaging.....	8
3 Technical Approach.....	9
3.1 Principles of 3-D Back-Projection Imaging.....	10
3.2 Imaging Sampling Requirements.....	11
3.3 NMR Imaging System.....	15
3.3.1 Imaging Probe Design	15
3.3.2 RF Resonator Design.....	16
3.3.3 Three-Dimensional NMR Imaging Pulse Sequence.....	19
3.3.4 NMR Acquisition, Reconstruction, and Display Software	19
3.4 Sample Preparation.....	20
4 Results.....	22
4.1 Spectroscopic Measurements.....	22
4.2 Imaging Results	24
4.2.1 Moderate-Resolution Imaging.....	24
4.2.2 Limited-RF-Field-of-View Imaging.....	25
4.2.3 Concentration Phantom Studies	26
4.2.4 Spatial Sampling Experiments.....	27
5 Discussion	29
5.1 Experimental Difficulties and Limitations	30
5.2 Apparatus and Technique Improvements.....	31
6 Conclusions.....	33
Acknowledgments	33
References.....	34

Figures

1	Flow diagram of typical ceramic injection-molding process.....	3
2	Diagram of NMR experiment	6
3	Schematic drawing of a modern NMR spectrometer	6
4	Plot of relaxation rates vs. molecular correlation time.....	8
5	Diagram of frequency-encoding spatial position by application of gradient vectors.....	10
6	Definition of 3-D Radon transform, and decomposition of integral over a sphere	12
7	Diagram of required data sampling.....	12
8	Plot of log (of number of projections) vs. sample radius and resolution.....	14
9	Contour plot of $\text{Log}(N_{3-D})$ as a function of radius and resolution	14
10	Block diagram of ANL's NMR imaging system.....	16
11	Schematic drawing of ANL's imaging probe.....	17
12	Sketch of RF resonator and lumped-parameter approximation of tuning tank circuit employed for this study...	18
13	Sketch of 3-D back-projection NMR imaging pulse sequence.....	20
14	Flow diagram of computer reconstruction codes: Radon_3d, and RMN2.....	21
15	Optical photo of green-state as-injected tensile specimen and 3-mm diameter concentration standards supplied by Norton Ceramics	22
16	Proton NMR spectra of organic additives acquired under static and "magic" angle spinning conditions.....	23
17	Surface-rendered image and 2-D slice of a 3-D proton NMR image of as-injected Si_3N_4 tensile specimen	25
18	Simulation of the B field produced from the short resonator employed for limited RF-field-of-view imaging.....	26
19	Drawing of concentration phantom constructed from imaged tensile specimen and four concentration standards	27

20	Two-dimensional thin "slices" obtained from a 3-D NMR image of a concentration phantom	28
21	Plot of gray-scale intensity vs. organic additive concentration acquired from the image presented in Fig. 16	28
22	Two-dimensional thin-section "slices" obtained from 3-D NMR images of the concentration phantom acquired with 1600 and 400 projections.....	29
23	Sampling procedure employed in 3-D back-projection NMR imaging.....	32

Tables

1	Characteristics of resonators constructed for tensile specimen imaging.....	18
2	Experimentally determined T_1 values for various specimens used in this study.....	24

THREE-DIMENSIONAL NUCLEAR MAGNETIC RESONANCE IMAGING OF GREEN-STATE CERAMICS

**S. L. Dieckman, N. Gopalsami, P. Rizo, J. M. Ford,
A. C. Raptis, W. A. Ellingson, D. M. Tracey,
and V. K. Pujari**

ABSTRACT

The objective of this work is the development of nuclear magnetic resonance imaging techniques and technology applicable to the nondestructive characterization of green-state ceramics. To this end, a three-dimensional (3-D) NMR imaging technique has been developed, based on a back-projection acquisition protocol in combination with image reconstruction techniques that are based on 3-D Radon transform inversion. The method incorporates the experimental flexibility to overcome many of the difficulties associated with imaging of solid and semisolid broad-line materials, and also provides contiguously sampled data in three dimensions. This technique has been evaluated as a nondestructive characterization method for determining the spatial distribution of organic additives in green-state injection-molded cylindrical Si_3N_4 tensile specimens. The technique has been evaluated on the basis of providing moderate image resolution over large sample volumes, high resolution over smaller specimen volumes, and sensitivity to variations in the concentration of organics. Resolution of 200 μm has been obtained with excellent sensitivity to concentration. A detailed account of the 3-D imaging results obtained from the study, a discussion of the difficulties and limitations of the imaging technique, and suggestions for technique and system improvements are included.

1 Introduction

1.1 Objective

The objective of this work is to evaluate the utility of three-dimensional (3-D) nuclear magnetic resonance (NMR) imaging technology for applications of nondestructive evaluation (NDE) of green-state ceramics. Specifically, the goal of the work reported here was to evaluate the potential of 3-D back-projection NMR imaging in mapping distributions of organic additives in cylindrically shaped green-state, as-injected Si_3N_4 tensile specimens. The evaluation of this technique is based on its ability to provide moderate resolution over reasonable specimen volumes and higher resolution over smaller specimen volumes, and on its sensitivity to variations in organic concentrations throughout the specimen.

1.2 Background

Process development in the mass production of high-performance structural ceramics and ceramic composites requires a detailed understanding of the macro and microstructural characteristics of the ceramic materials in relation to the processing conditions. The origin, nature, and effect of flaws (such as voids, cracks, inclusions, and density variations) must be understood to ensure the continuing technological development of advanced processing techniques. One such technique is injection molding, shown schematically in Fig. 1. Nondestructive evaluation methods such as NMR spectroscopy and imaging can play a key role in continued development of such processing techniques by providing detailed diagnostic measurements on selected specimens before, during, and after various processing stages. In this study, NMR imaging techniques were applied to determine binder distribution in as-injected ceramic specimens.

NMR imaging is sensitive to the local chemical environments in molecules. Moreover, the technique has the unique capability of spatially measuring the chemical and physical properties of a sample independently. In general, NMR techniques can provide a wealth of information relating to molecular structure and bonding, intra- and inter-molecular interactions, molecular mobility, and molecular diffusion. In addition, and perhaps most

Fig. 1. Flow diagram of typical ceramic injection-molding process

important for this work, NMR has the unique ability to quantitate molecular species and, when operating in the imaging mode, the quantitative measurements can be made with regard to spatial orientation within the sample.

Nuclear magnetic resonance imaging is a nondestructive and noninvasive evaluation technique. The basis of NMR is well understood and has been a valuable tool in spectroscopic characterization of materials for some time.¹⁻⁴ In addition, because it is noninvasive and uses no ionizing radiation, NMR imaging has become a standard, or perhaps the preferred, imaging methodology for medical diagnosis.⁵⁻⁸ However, while the use of NMR imaging in medicine has progressed rapidly, its application to materials characterization has been slow to develop. This is mainly due to the experimental difficulties presented by the intrinsic NMR spectroscopic properties, i.e., the broad linewidths, that are characteristic of many solids.

Recently, applications of two-dimensional (2-D) NMR imaging have been demonstrated on various materials, including polymers, rubbers, rocket propellants, porous media, and coals.⁹⁻¹⁴ Also,¹⁵⁻¹⁹ the utility of NMR imaging for mapping organic distributions in green-state ceramics and ceramic composites has been demonstrated at Argonne National Laboratory (ANL) and elsewhere. However, whereas these initial applications have demonstrated the potential of the technique overall, application to NDE requires an imaging methodology designed to provide data over 3-D spatial dimensions.

In this report, we describe a 3-D NMR method that is based on a back-projection protocol in combination with image reconstruction techniques based on 3-D Radon transform inversion. The method incorporates the experimental flexibility to overcome the difficulties presented by broad-line materials, and provides contiguously sampled data throughout the specimen. We have recently demonstrated this technique, along with X-ray computed tomography (CT) for dual-modality imaging of cold-pressed ceramic composites.¹⁹ Application of this technique to NDE of organic distributions in long cylindrically shaped green-state ceramic specimens was investigated in this work. The technique has been evaluated on the basis of providing moderate image resolution over large specimen volumes, high resolution over smaller specimen volumes, and sensitivity to variations in organic concentration throughout the specimen. Below, we present background material and a description of the 3-D imaging technique, along with its application to NDE of green-state, as-injected ceramic tensile specimens. Additionally, we discuss the difficulties and limitations of the technique, and suggest further technique and system improvements.

2 Fundamentals of NMR

2.1 Principles of NMR

Nuclei with either an odd atomic number or an odd mass number contain a nuclear magnetic moment or a simple magnetic moment. When a sample containing such nuclei is placed in a homogeneous static magnetic field ($\mathbf{B}_0$), the nuclei align (according to Maxwell-Boltzmann statistics) along

the direction of the magnetic field (along the z axis by definition) and precess (spin) as shown in Fig. 2a. The precession rate (ω) is given by $\omega = \gamma B_0$, where γ is the nuclear gyromagnetic ratio (a constant for given nuclei).

Once aligned along the z axis, the net nuclear magnetic vector component can be perturbed (tipped away from z) by application of additional magnetic fields (Fig. 2b). This is typically performed in modern NMR experiments by application of short RF pulses at or near the precession rate in a direction normal to B_0 (see schematic drawing of typical modern NMR spectrometer, Fig. 3). After the perturbation, the net xy vector component of the magnetization can be measured as a function of time by the same transceiver coil.

The signal obtained from the experiment is generally an exponentially damped sinusoid, known as a free induction decay (FID), Fig. 2d. Because of its low level (microvolts), the signal is averaged as the experiment is repeated. The time domain signal can be transformed to a frequency domain by application of a Fourier transform, producing a spectrum of the frequency and phase components of the signal. As discussed in the following sections, the spectrum typically is highly dependent on the materials and experimental conditions.

Additional factors governing the NMR experiment, and thus the resultant NMR signal, are the intrinsic nuclear relaxation rates. The two main relaxation phenomena that dominate both spectroscopy and imaging experiments are spin-lattice and spin-spin relaxation. These relaxation phenomena can often be described by first-order kinetics (singularly decaying exponentials), with characteristic rate constants T_1 and T_2 for the spin-lattice and spin-spin relaxations, respectively. Physically, T_1 is the rate of alignment of the net spin magnetization vector back along z (the direction of the main magnetic field B_0), whereas T_2 is the rate at which the net magnetization vector dephases (incoherently) in the xy plane (Fig. 2c). These relaxation rates essentially define the appropriate experimental conditions, and in many cases dominate the experimental response function (the spectrum).

Initial alignment and relaxation of the macroscopic magnetization back along z occur at rate T_1 . Thus, magnetization along M_z at time t after an RF perturbation pulse tips the net vector component into the xy plane can be described as

Fig. 2. *Diagram of NMR experiment: (A) alignment of the nuclei with the static magnetic field, (B) perturbation of the resultant net magnetization vector, (C) dephasing of the signal, (D) resultant signal obtained at the receiver coil*

Fig. 3. *Schematic drawing of a modern NMR spectrometer*

$$M_z = M_0 [1 - \exp(-t / T_1)], \quad (1)$$

where M_0 is the total nuclear spin density. Given that the NMR experiment is sensitive only to the projection of the net magnetization vector on to the xy plane, and that the magnetization must be aligned along z before the experiment can be performed, T_1 limits the speed at which the experiment can be signal averaged.

In proton NMR of solid and semisolid materials, the spin-spin relaxation rate (T_2) typically dominates the spectral response. The line-shape, typically a Lorentzian or Gaussian response function, is directly related to T_2 . In the case of the Lorentzian function, the spectral full-width-half-maximum (FWHM) peak width Δf relates to T_2 as

$$\Delta f = 1 / (\pi * T_2). \quad (2)$$

A similar expression can be derived for a Gaussian response. Note that the dephasing caused by T_2 is completely incoherent; thus, once the magnetization is dephased, the signal is lost and cannot be recovered.

Relaxation rates generally vary, depending upon the molecular mobility, or more precisely, on the molecular correlation time of the molecule in the material (see Fig. 4). Small molecules in solution, which are undergoing rapid isotropic tumbling, generally have long T_1 and T_2 rates, whereas molecules in true solids have long correlation times and thus long T_1 , but extremely short T_2 , rates. Molecules in semisolids, including those in waxy and soft polymeric materials, have intermediate correlation times and correspondingly moderate T_1 and T_2 rates. Multicomponent materials generally have multiple correlation times and thus multiple relaxation rates for both T_1 and T_2 . This may also be true for T_1 and T_2 rates from different nuclei within the same molecule. Thus, NMR experiments are often dominated by a mixture of relaxation rates.

Fig. 4. Plot of relaxation rates vs. molecular correlation time

2.2 Principles of NMR Imaging

The basis of NMR imaging has a long history, with contributions from many research groups (see discussions in Ref. 5-8). The preeminent paper that initially described the basis of the technique was published by Lauterbur in 1973.²¹ This paper discussed the principle of frequency encoding of the spatial dimension using magnetic-field gradients. Although many significant advances have been made recently (see Ref. 5-13), the work of Lauterbur²¹ essentially formed the basis of present day imaging.

If a specimen is placed in a nonhomogeneous magnetic field, given that the precession frequency is proportional to the applied field at that point (i.e. $\omega = \gamma B_0$), the nuclei from different sections of the sample precess at different rates. If the magnet field is made inhomogeneous in a linearly varying manner, for example by application of a static magnetic field gradient vector $\mathbf{G}_r$, the precession rate for the plane normal to the vector at a given point ($\mathbf{r}$) can simply be expressed as

$$\omega(r) = \gamma[\mathbf{B}_0 + \mathbf{G}_r(r)]. \quad (3)$$

A resultant point in the frequency spectrum is the linear planar integral of the 2-D space normal to the gradient vector (see Fig. 5). The spectrum obtained is thus a projection of the nuclear spin density in the plane normal to the vector. Acquisition of a series of projections in a plane about the object can be used to reconstruct a 2-D image in a fashion directly analogous to X-ray CT.

However, application of NMR imaging to solids presents a significant technological challenge due to the intrinsic spectroscopic properties (i.e., the relaxation rates) of materials in the solid or semisolid state. Both the T_1 's and/or the T_2 's may prohibit the experiment. For example, because a large data matrix is often necessary to adequately encode the 3-D space (see discussions below), significantly long T_1 's lead to prohibitively long acquisition times. Additionally, the short T_2 's common for solids and semisolids lead to wide spectral linewidths and impose significant resolution and experimental difficulties for imaging. A detailed discussion of these effects is given in the following sections.

3 Technical Approach

Based on previous experience¹⁵⁻²⁰ and initial measurements of spectral linewidths of the organic additives in ceramic materials (see Results section), the requirements for the NMR imaging technique and system were determined. Proton spectral linewidths of approximately 1 kHz indicated that from the viewpoint of NMR, the organic additives can be considered soft solids. The linewidths are considerably wider (by ~3 orders of magnitude) than typical solutions, but still considerably narrower (by a factor of 20-40) than true rigid solids. This suggested that the appropriate method of imaging is 3-D back projection in combination with large magnetic field gradients and wide spectral bandwidths.

Fig. 5. *Diagram of frequency-encoding spatial position by application of gradient vectors. The projection obtained is the planar integral of the 2-D space normal to gradient vector*

3.1 Principles of 3-D Back-Projection Imaging

In a conventional 2-D NMR back-projection tomographic experiment, a linear magnetic field gradient is applied in a plane at numerous projection angles. As discussed above, for each angle, the Fourier transform of the data represents a planar integral of the proton density normal to the gradient vector. Similarly, in the 3-D back-projection experiment, it has been demonstrated that by varying the gradient vector to sample the entire 3-D space, one obtains a 3-D Radon transform of the proton density.^{22,23} If $Rf(P)$ is the Radon transform of the object function $f(M)$, where P and M are discrete points in the Radon and object space, respectively (Fig. 6A), the value of the 3-D Radon transform in P is defined by the equation

$$Rf(P) = \int_{(OP \cdot OM)=0} f(M) dM \quad (4)$$

The inversion of this transform can be obtained by double differentiation and back projection. Marr et al.²⁴ have shown that the fastest way to invert the Radon transform is to use two sets of back projections, one along the

meridian planes and the other along planes of constant latitude. The inversion can then be written as:

$$f(M) = \frac{1}{4\pi} \int_{\theta=0}^{\theta=\pi} \int_{\phi=0}^{\phi=\pi} \frac{\partial^2 Rf}{\partial \rho^2} (\rho(M, \theta, \phi), \theta, \phi) \sin \theta d\phi d\theta \quad (5)$$

where ρ, θ, ϕ are the classical parameters of spherical coordinates, and $\rho(M, \theta, \phi) = OM \cdot \mathbf{n}$, where O is the origin and $\mathbf{n}$ is the unit vector in the direction (θ, ϕ) (Fig. 6b). The reconstruction algorithm of the 3-D Radon transform inversion was implemented as proposed by Grangeat et al.²⁵

3.2 Image Sampling Requirements

As discussed above, the 3-D object space is sampled by applying gradient vectors and collecting FIDs in numerous directions about a spherical sample space. This is done by rotating the vector about Euler angles θ and ϕ (see diagram in Fig. 6a). As in other tomographic techniques, appropriate choice of the increment of θ and ϕ , as well as the number of points across the specimen, is necessary to avoid critical undersampling and the associated artifacts in the resultant image. The requirements for sampling the 3-D space can be determined using the Central Slice Theorem, which states that the parallel-line projection of the 3-D Fourier transform of the object space is the 1-D Fourier transform of the 2-D projection of the object normal to the projection.²⁶ If the object is to be sampled discretely at $\Delta\rho$ and reconstructed on a Cartesian grid, the minimum number of projections (N) incremented by $\Delta\theta$ angles can be determined as a function of the object radius (R), and the desired resolution (Δx), see Fig. 7, for the minimal sampling condition $R\Delta\theta \leq \Delta x$, and $\Delta\rho \leq \Delta x/2$. Thus, for a 2-D back-projection acquisition, the minimal number of projections needed to provide sufficient sampling at the surface is $N_{2-D} = R2\pi/\Delta x$.

The specific 3-D data acquisition protocol implemented at ANL samples the spherical space around the object by varying the magnetic field gradient vector as illustrated in Fig. 6a. For a given ϕ , θ is incremented from 0 to $\pi/2$ radians as individual projections are acquired. Then, ϕ is incremented and the process is repeated until $\phi = 2\pi$ radians. With the sampling conditions described above, an expression for the number of total

Fig. 6. (A) Definition of 3-D Radon transform. Value of 3-D Radon transform in P is the integral of points M in the plane defined by OP MP . (B) Decomposition of integral over a sphere in two series of back-projections

Fig. 7. Diagram of required data sampling, given a specimen of radius R , and a desired resolution of Δx

projections required to adequately encode the 3-D space N_{3-D} (the product of the number of ϕ 's times the number of θ 's) can be reduced to

$$N_{3-D} = R^2 \pi^2 / \Delta x^2. \quad (6)$$

Thus, the required sampling is proportional to the surface area of the spherical sample space and inversely proportional to the resolution.

Equation 6 allows direct calculation of the required sampling when the maximum 3-D radius and desired resolution are given. For example, given a sample of radius 5 mm (a diameter of 10 mm) and desired image resolution of 100 μ m lower, the total number of projections required is 24,649. If lower resolution can be tolerated in the resultant images, the number of projections becomes much more reasonable. For 200- μ m resolution, the number of projections required is only 6,168. In practice, these numbers can be reduced because of significant filtering in the reconstruction algorithm.

While a discrete calculation of the sampling requirements is useful, graphical presentation of the information provided by Eq. 6 is also quite appealing. A plot of $\log(N_{3-D})$ vs. radius and resolution is shown in Fig. 8. The plotted surface represents a portion of a hyperbolic-paraboloid which increases exponentially with increasing resolution and radius. Although the sampling requirements can be obtained from this plot, in practice, it is convenient to calculate the maximum number of projections possible for the experimental time allotted on the basis of the signal-to-noise ratio and T_1 relaxation rates. Once this is obtained, a contour plot showing lines of equivalent N_{3-D} vs. radius and resolution as presented in Fig. 9 can be used to determine the maximum resolution obtainable in the allotted time for a specimen of given radius.

The frequency space must also be sampled appropriately to avoid artifacts and provide the desired resolution in the resulting image. Such sampling is done by acquiring data with appropriate spectral bandwidth and the appropriate gradient strength. The required gradient (G_x) strength necessary to resolve two points separated by a distance Δx is

$$G_x = \Delta f / (\gamma \Delta x). \quad (7)$$

Fig. 8. Plot of log (of number of projections) vs. sample radius and resolution

Fig. 9. Contour plot of $\log(N_{3-D})$ as a function of radius and resolution

where Δf is the FWHM peak width (with application of gradients) and γ is the gyromagnetic ratio as described above. The bandwidth (ΔB) necessary to accurately sample the frequency space with the above gradient is

$$\Delta B \geq 1.5 \cdot \gamma G_x D, \quad (8)$$

where D is the maximal sample diameter. A factor of at least 1.5 is required in practice, due to difficulties in specimen centering and the need for the data to span the object. For example, given a desired resolution of 100 μm , a FWHM peak width of 1000 Hz, and a 10-mm sample diameter, the required gradient strength and bandwidth are 23.5 G/cm and $\sim 1.5 \times 10^5$ Hz, respectively.

3.3 NMR Imaging System

A block diagram of the NMR imaging system used in this study is shown in Fig. 10. The system consisted of a Bruker CXP-100 NMR spectrometer fitted with a home-built imaging accessory that is described in detail elsewhere.⁵ The accessory, designed specifically for examining solid materials, consists of a versatile home-built IBM/PC-based pulse sequencer, three (X,Y,Z) audio-range 1-kW-gradient amplifiers, an RF shaping unit, and a home-built, singly tuned imaging probe capable of operating at 1-kW RF levels.

3.3.1 Imaging Probe Design

The imaging probe is designed to be used in an 89-mm vertical bore, 2.35 T superconducting magnet, in conjunction with a Bruker CXP 100 spectrometer, as shown in Fig. 11. The probe, which can accommodate samples up to 28 mm in diameter, includes RF coils for excitation and detection of the nuclear signals, and a set of gradient coils to create orthogonal gradient fields with respect to the spatial coordinates. To improve the filling factor of the RF coil and allow for different sample shapes, various RF coils and resonating structures can be inserted in the probe. The probe also contains forced-air-cooled gradient coils capable of operating with duty cycles in excess of 20% while producing a highly linear magnetic field gradient of 58 G/cm over a spherical space 30 mm in diameter.

Fig. 10. Block diagram of ANL's NMR imaging system

3.3.2 RF Resonator Design

The RF resonator design chosen for this application was a simple strip-line resonator circuit, as illustrated in Fig. 12a. The resonator provides high B_1 homogeneity, low self-inductance and a high quality factor. Additionally, the design provides vertical sample access (along the bore of the superconducting magnet) which is a necessity for imaging of materials with geometries similar to tensile specimens. Three resonators of varying design were constructed and are described in Table 1. The separate designs offered differences in filling factor, and provided different lengths of homogeneous RF field. The resonators were tuned to the proton resonance frequency at 2.35 T (100.135 MHz) and matched to 50 Ω by addition of a standard series-parallel tank circuit (Fig. 12b). Each of the three designs produced a quality factor (Q) of ≈ 320 .

Fig. 11. Schematic drawing of ANL's imaging probe

Fig. 12. Sketch of (A) RF resonator and (B) lumped-parameter approximation of tuning tank circuit employed for this study

Table 1: Characteristics of resonators constructed for tensile specimen imaging

Resonator	A (mm)	B (mm)	C (mm)	Quality Factor (Q)
A	25	30	5	312
B	25	25	5	320
C	25	10	5	308

3.3.3 Three-Dimensional NMR Imaging Pulse Sequence

A sketch of the 3-D back-projection NMR imaging pulse sequence used in this study is shown in Fig. 13. After a synchronization trigger, the gradients are ramped up to their calculated values. The gradients are allowed to stabilize to eliminate possible eddy currents before application of the RF pulse. RF pulse widths of 2 μ s were employed to excite the broad sweep width of 150 kHz. A postpulse delay of 2.5 μ s was used with receiver blanking to help eliminate RF pulse breakthrough to the receiver and to minimize the effects of coil ringdown.

3.3.4 NMR Acquisition, Reconstruction, and Display Software

Reconstruction of the series of 1-D frequency domain FID acquired at various gradient vectors into a 3-D image required two separate and distinct steps. Step one involves the conversion of the time domain FIDS into the appropriately phased frequency domain projections. Step two involved the reconstruction of the series of 1-D frequency domain projections by 3-D Radon transform inversion. This was accomplished with two computer codes, Radon_3d and RMN2. Radon_3d, designed and developed at ANL, features various time and frequency domain processing options, as well as FFT and phasing routines (see Fig. 14a). Initially, RMN2 was developed as a 3-D X-ray cone beam reconstruction algorithm;²⁵ at ANL it was converted for reconstruction of NMR data. A flowchart of the main sections of the code is presented in Fig. 14b.

Thin 2-D sections (or slices) of the 3-D reconstructed images were displayed and photographed from an Apple Macintosh II computer using the shareware image-processing program, Image (available from National Institute of Health, Bethesda, MD). The 3-D surface images were rendered, displayed, and photographed from either an Ardent/Titian or Stellar workstation using a commercial image production package entitled Application Visualization System (AVS, available from Stardent Computer Inc., Newton, MA).

Fig. 13. Sketch of 3-D back-projection NMR imaging pulse sequence

3.4 Sample Preparation

Concentration phantoms and tensile specimens used in this study were produced at the Norton Company's Advanced Ceramics Division. The concentration phantoms consisted of four 3-mm extruded rods, delivered in as-extruded condition (see Fig. 15). They were prepared by high-shear mixing (compounding) of Si_3N_4 + 4 wt.% Y_2O_3 powder (0.7- μm average particle size) with polyolefin-based binder at 125°C. The four phantoms were produced with binder/powder proportions of 86/14, 64/16, 82/18, and 80/20 by weight.

The net-shape formed (NSF) button-head tensile bar (Fig. 15) was received in as-injection-molded conditions with a 84/16 powder-to-binder ratio by weight. Premolded procedures included the above compounding step, cooldown to ambient conditions, and pelletizing at 100°C prior to feeding into the molding unit.

Fig. 14. Flow diagram of computer reconstruction codes: (A) Radon_3d, and (B) RMN2

Fig. 15. Optical photo of green-state as-injected tensile specimen and 3-mm diameter concentration standards supplied by Norton Ceramics

4 Results

4.1 Spectroscopic Measurements

Measurement of molecular properties such as chemical shifts, linewidths, and rate constants is necessary to determine the correct experimental techniques and conditions to be applied during imaging. For example, the spectral linewidth must be measured to determine the appropriate magnetic field gradient strength necessary to achieve a given spatial resolution in the final image. Additionally, in previous studies, we have noted heavy dependence of T_1 relaxation rates upon absolute concentrations of organic additives in Si_3N_4 /organic additive mixtures. Because the relaxation rates can determine the amount of signal observed under a given set of experimental conditions, it is imperative that the relationship of relaxation rate to organic additive concentration be studied.

Proton (^1H) spectra of pure binder were acquired as a function of "magic" angle spinning speed (see Fig. 16). Only an aliphatic resonance at 2.3 parts per million was observed for the material. This indicated that the material is highly aliphatic, containing only saturated carbons and no

Fig. 16. Proton NMR spectra of organic additives acquired under (A) static and (B) "magic" angle spinning conditions at 3.5 kHz

aromatic or acetic hydrogens. Peak widths of 850 Hz were obtained for the static material. The relatively narrow peak width obtained for the static experiment, and the increased narrowing with increased spinning at 5 kHz, indicated that the organic is semisolid on the NMR timescale.

Proton spin-lattice (T_1) relaxation was also measured on the pure organic materials and on the organic/ceramic mixture as a function of organic/ceramic ratio, see Table 2. The T_1 values obtained for all the mixtures were moderate, indicating that little difficulty would be encountered with quick RF pulsing and that selective saturation of the organics based upon concentration-induced T_1 differences would not occur.

Table 2. Experimentally determined T_1 values for various specimens used in this study

Sample (weight percent organic)	Spin-Lattice Relaxation Times (T_1)
14%	114 ms
16%	112 ms
18%	140 ms
20%	140 ms
Tensile Specimen	114 ms

4.2 Imaging Results

4.2.1 Moderate-Resolution Imaging

Initial imaging experiments were performed on the button end of the green-state as-injection-molded tensile specimen described above. The image data were collected using the 30-mm RF resonator insert (see [A] in Table 1) at ambient conditions. Three-dimensional sampling of the space was accomplished by using 128 complex data points along ρ , and a total of 1600 projections (20 θ angles over $\pi/2$ radians $\times$ 80 ϕ angles over 2π radians). A gradient strength of 25 G/cm and a sweep width of 100 kHz were used. One hundred twenty-eight averages were acquired by using an approximate 90° pulse and a recycle delay time of 0.25 s. A spatial resolution of $500_x \times 500_y \times 500_z \mu\text{m}^3$ was achieved, as calculated from the spectral FWHM linewidth. With these parameters, 18 h were required for data acquisition.

The 3-D surface-rendered image, along with a narrow 2-D "slice" of the 3-D reconstructed tensile specimen image, is presented in Fig. 17. The tapered point near the top of the 3-D image in Fig. 17 results from the sample's placement in the RF resonator, or more precisely, from its extension beyond the resonator boundary. Surface modeling and the slight shape distortion present in the image are the result of a phasing error associated with the receiver board.

Fig. 17. (A) Surface-rendered image and (B) 2-D slice of 3-D proton NMR image of as-injected Si₃N₄ tensile specimen

4.2.2 Limited RF-Field-of-View Imaging

Imaging experiments aimed at obtaining high resolution on small sections of a long "infinite" cylindrical as-injected Si₃N₄ tensile specimen were attempted. The approach included an attempt to limit the RF field of view in conjunction with the application of higher gradient strengths. The RF field of view was limited by the use of the smallest RF resonator (see resonator C in Table 1), which had a 1-cm RF "window" (Fig. 12). It was reasoned that the resonator would produce a homogeneous B_1 field over the window, and thus provide a significantly smaller field of view than the 3- or 2.5-cm "window" resonators used in the above imaging study. The smaller field of view could conceivably provide a three-fold increase in resolution using the same spectral bandwidth. Although the signal-to-noise ratio provided by the smaller coil was excellent because of an increased filling factor, the reconstructed images were flawed. Further investigation indicated that few data were obtained from the center of the samples.

To establish the exact nature of the difficulties encountered when using resonator C (see Table 1), electromagnetic field simulations were performed with a high-frequency, finite-element modeling package MAFIA.²⁷ The package simulates both the electric and magnetic fields of the structure for the lowest n th resonant modes. Simulations indicated that a homogeneous B_1 field should be produced by the lowest frequency

resonant mode, however, the next higher mode has a B_1 null in the center of the resonator, see Figs. 18a and 18b, respectively. The second mode would produce the experimentally observed null in the data set. Although it is possible that the resonator was tuned using the second resonant mode, it is felt that this is highly unlikely. Further investigation is necessary to establish the exact nature of the difficulties encountered during experiments performed with this resonator.

4.2.3 Concentration Phantom Studies

To establish the chemical sensitivity of the 3-D imaging method to the concentration of organics, images of concentration phantoms were constructed. A phantom, shown in Fig. 19, was constructed from a slice of the above-imaged tensile specimen and the four concentration standards described in Section 3.4. Three-dimensional NMR imaging data were acquired on specimens using 256 complex data points and a total of 1600 projections (20 θ angles over $\pi/2$ radians $\times$ 80 ϕ angles over 2π radians). A gradient strength of 25 G/cm and a sweep width of 300 kHz were used. Forty averages were acquired with an $\sim 40^\circ$ pulse and a recycle delay time of 0.25 s. A spectroscopic resolution of $200_x \times 200_y \times 200_z \mu\text{m}^3$ was achieved. Twelve hours were required for data acquisition when these parameters were used.

Fig. 18. *Simulation of the B field produced from the short resonator employed for limited RF-field-of-view imaging*

Fig. 19. *Drawing of concentration phantom constructed from imaged tensile specimen and four concentration standards*

A 2-D slice, extracted from the reconstructed 3-D image of the concentration phantom, is presented in Fig. 20 as a function of gray-scale stretching. The figure shows the disappearance of the lower concentration sections of the phantom as the gray-scale threshold is increased from Figs. 20a-20c.

Average intensities and associated standard deviations were measured from the above 2-D concentration phantom slice. These intensities were plotted as a function of organic percentage (wt.%), along with the tensile specimen with 16% organic additives (Fig. 21). Density differences among the concentration standards were not corrected. The corresponding intensities were obtained by manual selection of an area of interest from the appropriate section of the phantom. The plot shows the expected linear dependence of intensity on concentration of organics. Error bars for the concentration standards are larger than expected because of edge rounding due to filtering in the 3-D reconstruction algorithm.

4.2.4 Spatial Sampling Experiments

In an effort to determine the effect of critical undersampling in the spatial domain on the resultant 3-D image quality, experiments were conducted with varying sampling frequency. The concentration phantom described in Section 4.2.3 (Concentration Phantom Studies) was also employed for this study. A narrow "slice" obtained from the 3-D reconstructed image of the sample with 1600 (20 θ 's over $\pi/2$ and 80 ϕ 's

Fig. 20. Two-dimensional thin "slices" obtained from a 3-D NMR image of a concentration phantom. The images are displayed with increasing contrast enhancement from (A) to (C)

Fig. 21. Plot of gray-scale intensity vs. organic additive concentration acquired from the image presented in Fig. 16

over 2π radians) and 400 (10 θ 's over $\pi/2$ and 40 ϕ 's over 2π radians) total projections is shown in Figs. 22a and 22b, respectively. Both images were contrast-enhanced so that the reconstruction artifacts would be clearly visible in the resultant photos. The radial artifacts are significantly more intense in the grossly under-sampled image, Fig. 22b. Although a 2-D slice is presented, the artifacts extend radially from the image center in three dimensions. Clearly, artifacts of this nature will reduce the accuracy of the technique and should be avoided by sufficient spatial sampling.

5 Discussion

The three-dimensional back-projection technique implemented in this work has proven to be the only NMR imaging technique able to obtain images that are contiguously sampled in three spatial dimensions. In addition, we have demonstrated that this technique can uniquely provide

Fig. 22. Two-dimensional thin-section "slices" obtained from 3-D NMR images of the concentration phantom acquired with (A) 1600 and (B) 400 projections

3-D discrimination of proton spin density in materials with short T_2 relaxation rates, i.e., solids and semisolids. This work has demonstrated the application of this technique to imaging of semisolid organic additives in cylindrical "infinite" lengths of as-injected Si_3N_4 tensile specimens.

5.1 Experimental Difficulties and Limitations

The main difficulties and limitations encountered in imaging "infinite"- length components, stem from two sources: (1) the sampling conditions and associated experimental time necessary to encode the 3-D space, and (2) the difficulties encountered with exciting and detecting signals when bandwidths are extremely wide.

To satisfy correct sampling conditions requires acquisition of a large number of projections, as discussed in Section 3.2 and demonstrated experimentally in Section 4.2.4. This poses a significant restriction in obtaining high-resolution images on rather large specimens. However, these restrictions are not unique to 3-D NMR, but are also common to other forms of tomography, i.e. X-ray, PET, and nuclear imaging. In the worst case, the restrictions demand significant increases in experimental time, data storage requirements, and image reconstruction time.

The number of projections to be acquired in a "reasonable" period is proportional to the signal-to-noise ratio in the FID, and inversely proportional to the T_1 relaxation rate of the specimen. Increased signal-to-noise in the projection will reduce the required number of averages, and thus the signal averaging time. Shorter T_1 's will permit faster pulse repetition and thus result in quicker averaging per projection, see Section 2.1. In general, these factors will ultimately dictate the feasibility of obtaining a given resolution on a desired specimen. In the specific experiments performed in this study, T_1 was relatively short; thus, it was not a contributing factor. The time needed to obtain the required signal-to-noise ratio in the projections, was, however, a limiting factor. Discussions on improving signal fidelity and thus reducing acquisition times are presented below.

The combination of wide spectral peak widths of the organic binder, the application of high-power gradients necessary to obtain the desired resolution, and reasonably large object sizes lead to bandwidths of 300 kHz and image-projection widths of 200 kHz. The large projection widths imply

quick-decaying FIDs, as discussed in Section 2.1. Acquisition of data spread over these spectral widths presents stringent constraints on acquisition parameters, as well as rather significant demands on the electronics.

The quick decay of the signal, on the order of a few microseconds for the experimental conditions used in this study, dictates the acquisition delay requirements. A short postpulse delay (see Fig. 13) of less than 2 μ s generally distorts the projection by capturing RF-pulse breakthrough, preamp saturation, and RF coil ringdown. A long postpulse delay in excess of 5 μ s generally decreases the signal amplitude and thus the signal-to-noise ratio, and more importantly, often causes nonlinear phase distortions. Distortions caused by these errors can generally not be corrected because they require a priori knowledge of the proton distribution within the specimen. In practice, a postpulse delay length is chosen that is a compromise between the two types of errors.

5.2 Apparatus and Technique Improvements

Experimental acquisition time can be reduced by implementing improvements in the experimental apparatus that lead to increased signal-to-noise ratio and thus to reduced signal averaging requirements. In ANL's current imaging system, the apparatus can be improved to provide significant enhancement in experimental sensitivity, signal fidelity, spatial resolution, speed of data acquisition, and reduction in overall image artifacts. The system improvements to be implemented should include higher static magnetic field strengths, a shielded magnet, quieter preamps, quicker data capture and save, better RF coil designs, adjustable filters, cooled coils, bigger data and computer sizes, and quicker shielded-gradient sets.

Significant reduction in the experimental noise level could also be achieved by application of RF shielding to the magnet and receiver sections. Because ANL is located near Chicago and imaging is at 100.135 MHz, the experimental frequency is directly in the center of a very busy FM radio band. No fewer than five major FM radio stations are located within 1.0 MHz of our operating frequency. Although the FM stations are incoherent (not phase-locked to the NMR spectrometer), limited signal averaging, coupled with the wide spectral bandwidths (300 kHz) employed during the imaging experiment, leads to significant noise in the FIDs and in the resultant projections. Additional RF shielding, as routinely employed for clinical use,

would significantly improve the overall signal fidelity and thus the signal-to-noise in the resultant image.

The experimental time could also be reduced by changes in the sampling protocol. The current sampling method is performed by acquiring projections at equal increments of θ and ϕ . This results in uneven sampling of the surface, because the surface area of the spherical polygon is bound by the lune defined by $\Delta\phi$ and the planar meridian lines defined by $\Delta\theta$ (see Fig. 23). Because the Nyquist sampling condition is based upon the minimal sampling on the surface (i.e., at the equator), oversampling at the poles is unnecessary and quite time consuming. A more appropriate method of sampling with identical frequency response around the sphere should be implemented. One such method could place the gradient vectors in positions similar to those of dimples on a golf ball. Implementation of such a protocol may reduce the experimental time by perhaps 30-40%.

Fig. 23. Sampling procedure employed in 3-D back-projection NMR imaging showing lower sampling rate near the equator, at gradient vector G_3 , and higher sampling frequency near the poles at gradient vector G_1

6 Conclusions

- 3-D NMR imaging of as-injected green-state Si_3N_4 ceramics is possible with 3-D back-projection data acquisition and reconstruction based on 3-D Radon transform inversion.
- Maximal spatial resolution obtainable is dependent on the maximum dimension of the specimen in any of the acquisition vectors, the relaxation T_1 and T_2 rates, and the allotted experimental acquisition time.
- Resolution of 200 μm has been achieved with 3-D back-projection on green-state as-injected Si_3N_4 tensile specimens. Significantly higher spatial resolution can be achieved, provided that the sample dimensions are limited.
- Chemical sensitivity experiments performed with calibrated concentration phantoms confirm the quantitative nature of the NMR technique.
- High-resolution imaging of long "infinite" cylindrically shaped specimens will be possible if the designs of the RF coil or resonator are improved.

Acknowledgments

The authors thank L.E.T.I./DSYS for providing the 3-D Radon inversion reconstruction algorithm. We are also pleased to acknowledge that the financial support for this work was provided by the U.S. Department of Energy, Assistant Secretary for Conservation and Renewable Energy, Office of Transportation Systems, as part of the Ceramic Technology for Advanced Heat Engines Project, Subcontract 86X-SB182C, under subcontract from Norton Company.

References

1. Farrar, T. C., and Becker, E. D., *Pulsed Fourier Transform NMR*, Academic Press, New York, 1971.
2. Harris, R. K., *Nuclear Magnetic Resonance Spectroscopy: A Physicochemical View*, Pitman, Marshfield, MA, 1983.
3. Schlichter, G. P., *Principles of Magnetic Resonance*, 2nd Ed., Springer-Verlag, New York, 1978.
4. Fukushima, E., and Roeder, B. W., *Experimental Pulse NMR: A Nuts and Bolts Approach*, Addison-Wesley, London, 1982.
5. *Practical NMR Imaging*, ed. Foster, M. A., and Hutchinson, J. M. S., IRL Press, Oxford, U.K., 1987.
6. Morris, P. G., *Nuclear Magnetic Resonance Imaging in Medicine and Biology*, Clarendon Press, Oxford, U.K., 1986.
7. *NMR Imaging in Biomedicine*, eds. Mansfield, P., and Morris, P. G., Academic Press, New York, 1982.
8. Chen, C.-N., and Hoult, D. I., *Biomedical Magnetic Resonance Technology*, Adam Hilger, New York, 1989.
9. Sinton, S. W., Iwamiya, J. H., Ewing, B., and Drobny, G. P., *Nuclear Magnetic Resonance Imaging of Solid Rocket Fuel*, *Spectroscopy*, **6**, 42 (1991).
10. Miller, J. B., and Garroway, A. N., *J. Magn. Reson.*, **85**, 255 (1989).
11. Rommel, E., Hafner S., and Kimmich R., *J. Magn. Reson.*, **86**, 264 (1990).
12. Subhendra, N., Sarkar E., Wooten W., and Komoroski R. A., *NMR Imaging of Water in Model Porous Materials*, *Appl. Spectros.*, **45** (4), 619 (1991).
13. Hayashi, K., and Kawashima K., *NMR Imaging of Advanced Ceramics During Slip Casting Process*, *J. Phys. D.*, **21**, 1037 (1988).
14. Dieckman, S. L., Gopalsami N., and Botto R. E., *Microscopic NMR Imaging of Coal*, *Energy and Fuels*, **4**, 417 (1990).
15. Garrido, L., Ackerman J. L., and Ellingson W. A., *Polymeric Binder Distribution Maps in Green Ceramics by ^1H NMR Imaging*, *J. Magn. Reson.*, **83**, 340 (1990).
16. Garrido, L., Ackerman, J. L., Ellingson, W. A., and Weyand, J. D., *Determination of Binder Distribution in Green-State Ceramics by NMR Imaging*, *Ceram. Eng. Sci. Proc.*, **9**, 1465 (1988).

17. Gopalsami, N., Foster, G. A., Dieckman, S. L., Ellingson, W. A., and Botto, R. E., *Proc. Rev. Prog. in QNDE, Development of NMR Imaging Probes for Advanced Ceramics*, ed. by Thompson, D. O., and Climenti, D. E., Plenum Press, New York (1990).
18. Gopalsami, N., Dieckman, S. L., Ellingson, W. A., Botto, R. E., Wong, P. S., Yeh, H. C., and Pollinger, J. P., *Nuclear Magnetic Resonance Imaging of Green-state Ceramics*, ANL-90/27, Argonne National Laboratory (1990).
19. Gopalsami, N., Dieckman, S. L., Ellingson, W. A., Botto, R. E., and Yeh, H., *Quantitative MRI Measurement of Binder Distributions in Green-State Ceramics*, *Proc. Rev. Prog. in QNDE*, ed. Thompson, D. O., and Climenti, D. E., Plenum Press, New York (1991).
20. Dieckman, S. L., Rizo, P., Gopalsami, N., and Botto, R. E., *Three-dimensional Nuclear Magnetic Resonance and X-ray Microtomographic Imaging of Composite Materials*, *Materials Research Society Proceedings*, in press (1991).
21. Lauterbur, P. C., *Image Formation by Induced Local Interactions: Examples Employing Nuclear Magnetic Resonance*, *Nature*, **242**, 190-191. (1973).
22. Lauterbur, P. C., and Lai, C.-M., *IEEE Trans.*, **27**, 1227 (1980).
23. Lai, C.-M., and Lauterbur, P. C., *A Gradient Control Device for Complete Three-Dimensional Nuclear Magnetic Resonance Zeugmatographic Imaging*, *J. Phys. E*, **13**, 747 (1980).
24. Marr, R. B., Chen, C., and Lauterbur, P. C., *Aspects of Computerized Tomography*, ed. Herman, G. T., and Natterer, F., Springer-Verlag, New York, 1980.
25. Grangeat P., Hatchadourian, G., Le Masson, P., and Sire, P., *Logiciel Radon, Notice Descriptive Des Algorithmes Et Des Programmes*, Version 2.1 du 13-04-1990, LETI/DSYS/SETI/90-180 PS, Grenoble (le 11 Mai, 1990).
26. Kak, A. C., and Slaney, M., *Principles of Computerized Tomographic Imaging*, IEEE Press, 1987.
27. Ebeling, F., Klatt, R., Krawczyk, F., Lawinsky, E., Wipf, S. G., Weiland, T., Barts, T., Browman, M. J., Cooper, R. K., Rodenz, G., and Steffen, B., *MAFIA Users Guide: The MAFIA Collaboration*, University of California, 1989.

Distribution for ANL-91/39**Internal:**

R. E. Botto	D. S. Kupperman	R. A. Valentin
S. L. Dieckman (20)	C. A. Malefy (2)	R. W. Weeks
W. A. Ellingson	A. C. Raptis	ANL Patent Dept.
J. Ford	S. H. Sheen	ANL Contract Files
N. Gopalsami	L. Stock	TIS Files
N. Heeg	C. E. Till	

External:

DOE-OSTI, for distribution per UC-111 and UC-332 (329)

ANL Libraries (3)

DOE-CH

Manager

D. T. Goldman

F. Herbaty

A. L. Taboas

Materials and Components Technology Division Review Committee:

H. Berger, Industrial Quality Inc., Gaithersburg, MD

H. Birnbaum, University of Illinois at Urbana-Champaign, Urbana

R. Buchanan, University of Illinois at Urbana-Champaign, Urbana

M. S. Dresselhaus, Massachusetts Institute of Technology, Cambridge, MA

R. A. Greenkorn, Purdue University, West Lafayette, IN

B. Jones, University of Illinois at Urbana-Champaign, Urbana

C.-Y. Li, Cornell University, Ithaca, NY

R. E. Smith, Electric Power Research Institute, Charlotte, NC

S. D. Hartline, Norton Company, Northboro, MA

E. E. Hoffman, USDOE-Oak Ridge Operations, Oak Ridge, TN

D. Ray Johnson, Oak Ridge National Laboratory

R. R. Judkins, Oak Ridge National Laboratory

R. M. Peters, ALCOA Technical Center, PA

J. R. Pollinger, Allied Signal Aerospace Co., Torrance, CA

J. N. Ponzarino, Norton Company, Northboro, MA

V. Pujari, Norton Company, Northboro, MA

P. Rizo, L.E.T.I./Department Systems, C.E.A./C.E.N.G., France

D. Tracey, Norton Company, Northboro, MA

H. C. Yeh, Allied Signal Aerospace Co., Torrance, CA

END

**DATE
FILMED**

10 / 27 / 92