Keywords:

*Electron Microscopy
Al-Li Alloys
Control Rods
Powder Metallurgy*

Retention:

Permanent

TRANSMISSION ELECTRON MICROSCOPY OF AL-LI CONTROL ROD PINS (U)

M. H. Tosten

**SAVANNAH RIVER TECHNOLOGY CENTER
Equipment & Materials Technology Department
Materials Technology Section**

ISSUED: September, 1992

D. Thomas Rindlin

Authorized Derivative Classifier

**Westinghouse Savannah River Company
Savannah River Site
Aiken, SC 29808**

SAFETY • RESPONSIBILITY • SECURITY

SRS

MASTER

SAVANNAH RIVER SITE

WSRC-TR-92-434 (U)

THIS PAGE INTENTIONALLY LEFT BLANK

CONTENTS

	PAGE
EXECUTIVE SUMMARY	1
INTRODUCTION	1
BACKGROUND	2
EXPERIMENTAL	3
RESULTS AND DISCUSSION	4
<i>Cast Pins</i>	4
<i>Powder Metallurgy Pins</i>	6
CONCLUSIONS	8
ACKNOWLEDGEMENTS	8
REFERENCES	9

LIST OF FIGURES

	PAGE
1. General Microstructure — Lot 1287K Pin. (a) Region containing small, randomly oriented α grains. (b) SADP from the area shown in (a). The ring (at arrows) near the transmitted beam (T) originates from the Li_2O phase.....	10
2. General Microstructure — Lot 1287K Pin. (a) Interface between a large α grain and a polycrystalline region. (b) SADP from the large grain in (a). The diffuse spots (e.g., those marked with arrows) originate from δ' the phase.....	11
3. X-ray Spectra — 1287K Pin. (a) Spectrum from a polycrystalline region. Note the presence of Ga and O. (b) Spectrum from a large α grain. The Cu peaks in these spectra are artifacts produced by the TEM.....	12
4. General Microstructure — Lot 1278K Pin. Two large α grains separated by a polycrystalline region. The small, circular regions in this image are β precipitates.....	13
5. δ' Microstructure — Lot 1278K Pin. CDF image which shows the δ' distribution from a region of this material. Arrows mark the positions of low angle grain boundaries.....	14
6. δ' Microstructure - Lot 1278K Pin. Low magnification CDF image which shows δ' PFZs in the vicinity of a high angle grain boundary and matrix β particles. (The dark, circular areas are β particles and associated PFZs.).....	15
7. A bright field micrograph which shows the micro-crystalline region remaining following dissolution of a β particle. See text for discussion.....	16
8. A CDF Image which shows a "ring" of β precipitate(s) frequently found surrounding the microcrystalline regions.....	17
9. An image from the powder metallurgy pin. The large, bright area is the primary hole produced during thinning while the many bright spots are holes where second phase particles were selectively removed from the foil.....	18

LIST OF FIGURES *(Continued)*

	PAGE
10. General Microstructure — Powder Metallurgy Pin. An image of the "lacy network of α grains that remained at the edge of the large hole (see Figure 9) after electrolytic thinning (jet-polishing).....	19
11. General Microstructure — Powder Metallurgy Pin. An image that illustrates the grain structure of this material. The rod-shaped particles (e.g., at arrows) are aluminum carbides (Al_4C_3).....	20
12. δ' Microstructure — Heat Treated Powder Metallurgy Pin. A δ' CDF from a small α grain. The diameter of the δ' in this area is less than 2 nm.....	21

APPROVALS

M. H. Tosten Date: 10/13/92
M. H. Tosten, AUTHOR
Materials Compatibility & Joining Technology Group
MATERIALS TECHNOLOGY SECTION

H. B. Peacock Date: 10-14-92
H. B. Peacock, Jr., CUSTOMER
Fabrication Technology & Operations Support Group
MATERIALS TECHNOLOGY SECTION

P. A. Kestlin Date: 10/21/92
P. A. Kestlin, TECHNICAL REVIEWER
Materials Compatibility & Joining Technology Group
MATERIALS TECHNOLOGY SECTION

D. T. Rankin Date: 10/13/92
D. T. Rankin, MANAGER
Materials Compatibility & Joining Technology Group
MATERIALS TECHNOLOGY SECTION

T. L. Capeletti Date: 10/14/92
T. L. Capeletti, MANAGER
MATERIALS TECHNOLOGY SECTION

EXECUTIVE SUMMARY

Transmission electron microscopy was employed to characterize the microstructures of both cast and mechanically alloyed powder Al-Li control rod pins. The results indicated that microstructural differences existed between the ingot and powder metallurgy materials. In general, the cast specimens contained large, dendritic α grains separated by regions of much smaller α grains and AlLi (β) particles. The grain interiors, except in the immediate vicinity of the β particles, contained a high number density of Al_3Li (δ') precipitates. Several specimens also contained a widely distributed and unidentified Si-rich phase. In contrast, the microstructure of powder metallurgy samples consisted of small, randomly oriented α grains containing a dispersion of rod-like Al_4C_3 (aluminum carbide) particles - confirmed by both TEM and X-ray diffraction. No TEM evidence was found for the presence of the δ' or β phases in the as-received powder material, although the β phase was identified with X-ray diffraction. The δ' phase was observed in the powder metallurgy pin after the material was given a solutionizing heat treatment. This observation suggests that Li may have been segregated to other phases, most likely either the β or LiAlO_2 phases, that subsequently dissolved during the "solution treatment" freeing-up Li to form δ' . The possibility exists that the microstructural differences between these two materials could be decreased by further heat treatments or thermo-mechanical processing. However, without further experimentation, it is unknown which material (microstructure) is better suited for control rod pin applications.

INTRODUCTION

Various components of the SRS nuclear reactors are manufactured from binary Al-Li alloys including the control rod pins. These pins comprise the core of control rods that are used to "control" the neutron flux and maintain the reactor at a specified power level. To date, these pins have been fabricated via conventional ingot metallurgy processes, i.e., alloying molten Al with Li, casting, extrusion, etc. Recently, however, the 300-Area has requested a study to determine the feasibility of using powder metallurgy practices to prepare Al-Li reactor components. In support of this program, a transmission electron microscopy (TEM) study was

conducted to characterize the microstructure of 3.1 wt.% Al-Li control rod pins prepared from both conventional ingot metallurgy and powder metallurgy processes.

BACKGROUND

The principle phases present in binary Al-Li alloys with Li concentrations greater than ~1 wt.% and less than ~20 wt.% are α (Al-Li, solid solution), $\beta^\dagger$ (AlLi, equilibrium intermetallic), and δ' (Al₃Li, metastable ordered phase) [1-6]. Alloys aged (heat treated) in the α/β phase field but above the metastable δ' solvus will contain only the α and β phases. The β phase forms predominantly on grain boundaries but can precipitate within the grain interiors after long aging times. At temperatures below the δ' solvus a mixture of α , β , and δ' phases can exist. The δ' forms by homogeneous nucleation as 1-2 nm diameter spheres within the grains. Although the amount of δ' can be controlled (the more β already present, the less Li available for the δ'), the formation of δ' during quenching is nearly impossible to suppress. Aging at elevated temperatures but below the δ' solvus will result in δ' coarsening along with a concomitant dissolution of other δ' precipitates to supply Li to the equilibrium β particles. The mechanical properties of the binary alloys are determined by the number density and size of the δ' precipitates as well as the amount of β precipitation that occurs on the grain boundaries, e.g., [7,8].

TEM methods can be used to identify the presence of second phase precipitates, like the β and δ' phases. The two most commonly used methods are electron diffraction analysis (selected area or convergent beam) and centered-dark field microscopy. The first of these techniques is possible because second phase particles typically have a different lattice parameter, crystal structure, and/or chemical composition than the matrix - the α solid solution in this case. Reflections in the diffraction patterns arise from the elastic scattering of electrons from lattice planes. Since the spacing of these second phase lattice planes is usually different from the matrix, extra reflections can be present in the diffraction patterns.

[†] The β phase is generally referred to as δ in the open literature.

The δ' phase has an ordered, face-centered cubic structure with Li atoms located on the cube corners and Al atoms on the cube faces. The lattice parameters of this phase is nearly identical to that of the α matrix; but, because the electron scattering factors differ for Li and Al, reflections appear in diffraction patterns at positions where α reflections are not allowed[†]. The β phase is also cubic but has an NaCl structure and a much larger lattice parameter than either the α or δ' phases. Reflections from this phase are therefore easily identifiable when β is present in the thin foil. In most cases, however, due to its highly reactive nature, β particles are preferentially dissolved during jet-polishing and do not exist in the final, polished specimen.

The centered-dark field phase identification technique is used in conjunction with diffraction analysis. With this technique, images of second phase particles are formed in the TEM using electrons diffracted from the second phases. As a result, images show only the second phase particles and not the matrix. This technique essentially isolates the precipitates revealing not only their location within the material but also their morphology. Both of these techniques were used in this study.

EXPERIMENTAL

TEM specimens were prepared from two cast control rod pins and one powder metallurgy pin. Each of these pins had a total average Li content of ~3.1 wt.%. The cast pins originated from two lots, 1287K and 1278K. They were manufactured in M-Area following standard procedures which included a high temperature soak above the δ' solvus and an extrusion reduction of ~60:1. Powder metallurgy pins were prepared by a much different process. Al powder was mechanically alloyed in a ball mill with a cast Al - 20 wt.% Li master alloy. The alloyed powder was hot pressed and then double extruded resulting in a total extrusion reduction of nearly 172:1.

All TEM specimens were taken from thin slices cut perpendicular to the extrusion axis (transverse orientation) of the pins. Specimen

[†] The α phase is face-centered cubic; therefore, only reflections from lattice planes where hkl are all even or all odd are visible in a diffraction pattern. The δ' phase diffracts electrons like a simple cubic structure and all reflections are allowed.

disks were punched from these slices and subsequently ground to $\sim 0.1 \mu\text{m}$ (0.004 in.) in thickness. Final thinning to produce electron transparent regions was performed either electrolytically or by ion-milling. Electrolytic thinning was accomplished using a twin-jet electropolisher. The electrolyte employed consisted of 25 vol% nitric acid and 75 vol% methanol. Jet-polishing was performed using a potential of 11 volts with the solution cooled to -15°C . After thinning, the foils were rinsed for approximately 60 seconds in a steady stream of ethanol. Ion-milled specimens were thinned with argon plasma in a Gatan Model 600 Dual Ion Mill using a gun voltage of 6 kV. All specimens were examined in a Philips EM400T operating at 120 kV. X-ray microanalysis was performed using a Kevex energy dispersive microanalysis system equipped with a Quantum light element detector.

RESULTS AND DISCUSSION

Cast Pins

The microstructure of the first cast pin examined (Lot 1287K) was very inhomogeneous. Most regions contained $0.2 - 5 \mu\text{m}$ sized, randomly oriented α grains adjacent to much larger α grains (size unknown). A bright field micrograph (Figure 1a) shows a region of the small α grains. Figure 1b is the corresponding selected area diffraction pattern (SADP) from this region. All of the discrete reflections in this pattern originated from the α phase. In many cases these reflections appeared to be arranged as discontinuous rings about the transmitted beam (labeled T). This "ring effect" was a result of the random arrangement of the small α grains and the diffraction of electrons from lattice planes of equal d-value. (The continuous ring located at the center of the pattern (at arrows) did not originate from the α phase but instead from a surface oxide, most likely the Li_2O phase.) An image of the interface between a polycrystalline region and a much larger α grain is shown in Figure 2a. An SADP from the large grain (Figure 2b) revealed that this grain was indeed a single crystal as evidenced by the absence of extra α reflections.

X-ray spectra from the polycrystalline and single crystal regions are shown in Figures 3a and 3b, respectively. Close examination of these spectra showed that the polycrystalline region contained

small amounts (<1 wt.%) of Ga† and significantly more O than the large α grain. This observation was typical for all polycrystalline regions examined in the 1287K pin. (It should be noted that the X-ray technique is not sensitive enough to detect Li because of its low atomic number.) The polycrystalline regions also contained a large number of Si-rich precipitates. The composition and structure of these precipitates was not determined.

Considerable effort was needed to show that the δ' phase was present in this material. (Because of the low solubility of Li in Al at room temperature [9,10] and the rapid nucleation kinetics, δ' will precipitate irrespective of quench rate [4] or prior heat treatment [11]). Weak δ' reflections (arrowed in Figure 2b) were observed in SADPs from some α grains but not from others. Centered-dark field (CDF) images formed from these reflections were quite poor; however, they did reveal that the δ' was present but inhomogeneously distributed from region to region. The diameter of these precipitates measured less than 3 nm.

The second of the cast pins (Lot 1278K) examined yielded much more information than the first. A low magnification image from this specimen is shown in Figure 4. Similar to the 1287K pin, the microstructure of this pin was very inhomogeneous. It consisted of large, dendrite-like α grains separated by regions containing small, randomly oriented α grains and β precipitates. The β phase was also observed in the large α grains but to a much lesser extent. This microstructure had the appearance of an unrefined, as-cast microstructure, i.e., large α dendrites and interdendritic regions consisting of much smaller α grains and β particles. The observation of many β particles in the interdendritic regions suggests that during solidification excess Li was transported to these regions. No evidence of Ga or excess O segregation to the polycrystalline regions of this material was observed.

Figure 5 is a δ' CDF image from a region of this material. The δ' in this image ranges in size from <1 to 20 nm in diameter except for larger, irregularly shaped δ' precipitates found on the low angle grain boundaries. In general, size and number density of the δ' in

† Ga is often found as a trace element in bauxite but its presence in the Al-Li pins has never been reported.

this region was typical of the Lot 1278K specimen. The spatial distribution of δ' throughout this specimen was also similar to that shown in Figure 5 except in the immediate vicinity of β precipitates and high angle grain boundaries (primary nucleations site for β). In these regions significant δ' precipitate-free zones (PFZs) were observed (Figure 6). PFZs readily develop in Al-Li alloys at elevated temperatures because the metastable δ' phase dissolves to supply Li to the growing β precipitates, e.g., [4]. The δ' microstructure of this pin closely resembled that of other Al-Li alloys that have been studied at SRS [12].

Close examination of many of the regions where individual β particles once existed revealed that these areas actually contained a number of very small Al-rich grains (Figure 7). These regions were characteristically thinner than the surrounding matrix and usually consisted of ~10-20 Al-rich grains measuring 100-200 nm in diameter. (This phenomenon has also been observed in Al-Li-Cu-Zr and Al-Li-Zr alloys [11]). It is suspected that these regions developed during the jet-polishing step of the specimen preparation procedure when Li, because of its highly reactive nature, was selectively removed from the β particles. The strains associated with this large change in partial molar volume actually caused the remnants of the β particles to "recrystallize" leaving behind an area of microcrystalline Al-rich grains. Evidence for this mechanism includes the absence of δ' reflections in the diffraction patterns from these regions and the observation of a "ring" of β surrounding many of the microcrystalline regions (Figure 8).

Powder Metallurgy Pin

The mechanically alloyed Al-Li specimens were very difficult to thin via jet-polishing. The resulting electron transparent areas were limited to a "lacy" network of material at the edges of the foils. Figure 9 is a low magnification micrograph of a thin foil of this material. The area imaged in this photograph represents ~1/3 of the total area exposed to the electrolyte. As can be seen, there is a large hole (at arrow) in this region surrounded by a great number of smaller holes across the whole area of the micrograph. These holes represent regions where second phase particles were selectively removed from the specimen. A higher magnification micrograph (Figure 10) also shows the small holes and remaining

network of thinned material. The grain structure of the network (Figure 11) consisted of small α grains and subgrains measuring 0.1 - 0.8 μm in diameter. Convergent beam electron diffraction (CBED) analysis could not detect the presence of the δ' phase within the α grains. Patterns were recorded from many different regions and in no case were δ' reflections observed. All regions did, however, contain a significant number density of small rod-shaped precipitates (e.g., at arrows in Figure 11). X-ray diffraction and CBED techniques identified this phase as Al_4C_3 (aluminum carbide). X-ray diffraction also identified the presence of the β phase, however, this phase was not observed with TEM.

On several occasions particles were found protruding into the holes in the α grains. Electron diffraction analysis showed these particles to be LiAlO_2 . Although this phase was identified in the region of the holes, it was unclear whether these oxide particles were actually the particles attacked by the polishing solution to produce the holes. In an attempt to retain the dissolved particles for analysis, several thin foils were prepared by ion-milling. The foils generated using this method were of low quality, producing similar holes as those in the electrolytically thinned material. In the latter case however, a significantly higher number of the second phase particles were retained at the edges of the holes. Those particles analyzed using CBED analysis were also identified as LiAlO_2 .

To further characterize the powder specimens, a section of the material was heat treated at 550°C for 45 minutes and then cold water quenched. (This is a heat treatment typically used to solution treat Al-Li alloys, i.e., dissolve the β and δ' particles and re-precipitate δ' on the quench.) The heat treated alloy was examined in the TEM. Results showed that the grain size and Al_4C_3 distribution was similar to the as-received material. However, in this instance, weak δ' superlattice reflections were observed from several grains (Figure 12). The δ' particle size was very small (<2 nm in diameter), typical of δ' that forms during quenching from elevated temperatures. This result suggests that the Li in the as-received material was segregated to regions other than those observed in the TEM (possibly the LiAlO_2 or β phases). During the solution treatment Li was then placed back into solid solution subsequently precipitating as δ' upon cooling to ambient temperatures.

CONCLUSIONS

The results of this study have shown that the grain structures and phase distribution of the cast and powder pins were quite different. The cast pins had an inhomogeneous grain structure consisting of large α dendrites separated by regions of 0.2 - 5 μm α grains, β particles and an unidentified Si-rich phase. The powder pin, on the other hand, had a homogeneous distribution of randomly oriented 0.1 - 0.8 μm α grains containing a dispersion of Al_4C_3 particles. The δ' distribution in both types of material was also quite different. In general, the cast material had a δ' microstructure similar to conventional Al-Li alloys but the powder metallurgy specimen, prior to heat treatment, showed no signs of δ' at all. Additionally, unlike the cast material, the β phase was not observed in the powder pin even though x-ray diffraction confirmed its presence. The absence of δ' in the as-received powder metallurgy pin and its precipitation following a solution treatment can be explained if Li was segregated to other second phase particles in the material. The precipitation of δ' also suggests that heat treatments or thermo-mechanical processing may help decrease the microstructural differences between these materials. The significance of the microstructural variations (e.g., grain structure, the distribution of the δ' and other second phases, etc.), as they apply to the functionality of the control rod pins, is unknown. Further research, including in-situ irradiation experiments, is necessary before this can be determined.

ACKNOWLEDGEMENTS

The author wishes to acknowledge C. N. Foreman and J. C. Marra for their able assistance during the course of this research program. Additionally, the author would like to acknowledge A. R. Jurgensen for the X-ray diffraction results presented in this paper.

REFERENCES

1. J. M. Silcock, J. Inst. Met., Vol. 88, 1959-60, pp. 357-64.
2. M. Tatmura, T. Mori and T Nakamura, J. Japan Inst. of Metals, Vol. 34, 1970, pp. 919-25.
3. B. Noble and G. E. Thompson, Met. Sci. J., Vol. 5, 1971, pp. 114-20.
4. D. B. Williams and J. W. Edington, Metal Sci., Vol. 9, 1975, pp. 529-32.
5. D. B. Williams, in Aluminum-Lithium Alloys, Proc. First Int. Conf. on Al-Li Alloys, T. H. Sanders, Jr. and E. A. Starke, Jr., eds., TMS-AIME, Warrendale, PA, 1981, pp. 89-100.
6. D. Venables, L. Christodoulou and J. R. Pickens, Scripta Met., Vol. 17, 1983, pp. 1263-68.
7. A. K. Vasudevan and S. Suresh, Mater. Sci. and Eng., Vol. 72, 1985, pp. 37-49.
8. S. Suresh, A. K. Vasudevan, M. H. Tosten and P. R. Howell, Acta Metall., Vol. 35, 1987, pp. 25-46.
9. L. P. Costas and R. P. Marshall, Trans. Met. Soc. AIME, Vol. 224, 1962, pp. 970-74.
10. E. D. Levine and E. J. Rapperport, Trans. Met. Soc. AIME, Vol. 227, 1963, pp. 1204-08.
11. M. H. Tosten, "*Microstructural Development in Al-Li-Cu-Zr Alloys*", Ph.D. Thesis, The Pennsylvania State University (1988).
12. M. H. Tosten, Unpublished research.

Figure 1. General microstructure - Lot 1287K pin. (a) Region containing small, randomly oriented α grains. (b) SADP from the area shown in (a). The ring (at arrows) near the transmitted beam (T) originates from the Li_2O phase.

Figure 2. General microstructure - Lot 1287K pin. (a) Interface between a large α grain and a polycrystalline region. (b) SADP from the large grain in (a). The diffuse spots (e.g., those marked with arrows) originate from δ' the phase.

Figure 3. X-ray spectra - 1287K pin. (a) Spectrum from a polycrystalline region. Note the presence of Ga and O. (b) Spectrum from a large α grain. The Cu peaks in these spectra are artifacts produced by the TEM.

Figure 4. General microstructure - Lot 1278K pin. Two large α grains separated by a polycrystalline region. The small, circular regions in this image are β precipitates.

NPN

Figure 5. δ' microstructure - Lot 1278K pin. CDF image which shows the δ' distribution from a region of this material. Arrows mark the positions of low angle grain boundaries.

Figure 6. δ' microstructure - Lot 1278K pin. Low magnification CDF image which shows δ' PFZs in the vicinity of a high angle grain boundary and matrix β particles. (The dark, circular areas are β particles and associated PFZs.)

NPN

Figure 7. A bright field micrograph which shows the microcrystalline region remaining following dissolution of a β particle. See text for discussion.

Figure 8. A CDF image which shows a "ring" of β precipitate(s) frequently found surrounding the microcrystalline regions.

Figure 9. An image from the powder metallurgy pin. The large, bright area is the primary hole produced during thinning while the many bright spots are holes where second phase particles were selectively removed from the foil.

NPN

Figure 10. General microstructure - powder metallurgy pin. An image of the "lacy" network of α grains that remained at the edge of the large hole (see Figure 9) after electrolytic thinning (jet-polishing).

Figure 11. General microstructure - powder metallurgy pin. An image that illustrates the grain structure of this material. The rod-shaped particles (e.g., at arrows) are aluminum carbides (Al_4C_3).

NFM

Figure 12. δ' microstructure - heat treated powder metallurgy pin. A δ' CDF from a small α grain. The diameter of the δ' in this area is less than 2 nm.

THIS PAGE INTENTIONALLY LEFT BLANK

END

**DATE
FILMED**

9 / 1 / 93