DISCLAIMER

DOE/PC/91923-X

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DOE/PC/91293--2

DE92 018759

DIRECT CATALYTIC DECOMPOSITION OF NITRIC OXIDE

Maria Flytzani-Stephanopoulos
Adel F. Sarofim
Yanping Zhang

Quarterly Technical Progress Report No. 2
January-March 1992

Prepared for:
U.S. Department of Energy
Pittsburgh Energy Technology Center
Pittsburgh, Pennsylvania
Technical Project Officer - Dr. K. Das (DOE/METC)
Grant No. DE-FG22-91PC91923

by
Massachusetts Institute of Technology
Department of Chemical Engineering
Cambridge, Massachusetts

"US/DOE Patent Clearance is not required prior to the publication of this document."

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

Project Title: DIRECT CATALYTIC DECOMPOSITION OF NITRIC OXIDE

Abstract

This project will investigate a suitable catalyst system for the direct NO decomposition, for post-combustion NO_x control. The proposed process will not use a reductant, such as ammonia in case of Selective Catalytic Reduction (SCR) process for catalytic reduction of NO_x to nitrogen.

This is a simplified process basically involving passing the flue gas through a catalytic converter, thus avoiding problems generally associated with the commercial Selective Catalytic Reduction (SCR) process, namely high operating cost, ammonia slip, and potential N₂O emissions. A brief description of the proposed work is as follows:

Catalysts will be prepared by incorporating metal cations into zeolite supports according to ion exchange procedures widely used in preparation of metal/zeolite catalysts. Zeolites will be modified to improve catalytic activity, by blocking ion exchange sites in the small pores of zeolites with promoter cations of high valence. The catalysts of primary interest include copper (Cu), palladium (Pd), platinum (Pt), silver (Ag), and nickel (Ni) exchanged zeolites. Additional tests will be conducted for the promoter/Cu-exchanged zeolites, particularly the catalyst system Mg/Cu-ZSM-5 for NO conversion to nitrogen at typical flue gas O₂ and NO levels and over the temperature range of 723-873 K. Effects of zeolite modification, copper exchange level and catalyst preparation conditions on the catalyst activity will be studied in a packed-bed microreactor. Temperature-programmed desorption (TPD) and reduction (TPR) experiments will be carried out in a thermogravimetric analyzer and a single-particle electrodynamic balance (EDB). Kinetic studies of NO and O₂ interactions with catalysts as well as catalyst structural investigations are planned. These would provide new ways for improving the Cu-ZSM-5 system, which is presently the most promising catalyst for direct NO decomposition in oxygen-containing exhaust gas streams.

Progress Summary

Construction of Packed-Bed Microreactor System

During this quarter, a fully equipped packed-bed microreactor set-up was constructed to carry out the NO-decomposition tests with the ion-exchanged ZSM-5 catalyst samples prepared during the last quarter and this quarter. Figure 1 shows a schematic of the system consisting of a fixed-bed flow reactor made from 1/2 inch diameter quartz tube; a temperature-programmed furnace electrically heated and controlled by a temperature controller (Tetrahedron: Model Wizard); three mass flow controllers used to measure mass flow rates of He, He+NO and O₂; a NO-NO_x analyzer (Thermo Electron: Model 14A), which can measure NO and NO_x concentrations ranging from 0.001 ppm to 2,500 ppm; a gas chromatograph (Hewlett Packard: Model 5890) with a thermal conductivity

detector, using a 13-X molecular sieve to monitor oxygen and nitrogen levels in the exit gas; high purity gases (He, NO/He, and O₂) were purchased from Matheson and Airco. Six thermocouples were inserted through the steel cover and the ceramic wall of the furnace to monitor the temperature along the reactor; two of them are also used as sensors to feed back temperature signals to the temperature controller.

The analytical equipment (NO_x chemiluminescence analyzer and gas chromatograph) was calibrated with standard gas mixtures. The mass flow controllers were also calibrated with various gases, in preparation for testing. As shown in Figure 1, two more thermocouples were placed in the catalyst bed through both ends of the reactor to measure the bed temperature directly.

Catalyst Synthesis

Six catalyst samples were prepared this quarter by incorporating metal cations into the ZSM-5 zeolite substrates according to well-established ion-exchange procedures used in preparation of metal/zeolite catalysts. The procedure used in our laboratory is as follows: The zeolite was washed with dilute NaNO₃ solution, ion-exchanged in aqueous copper (II) acetate/magnesium nitrate solution, washed with deionized water, and dried at 383 K overnight. To obtain zeolites with high extents of ion exchange, the parent zeolite underwent several ion-exchange treatments. For example, *ca.* 5 grams of the ZSM-5 zeolite was ion-exchanged in 300 ml of copper (II) acetate solution with a concentration of 8 mmol dm⁻³ overnight, and separated from the solution by filtration. The obtained wet cake of light blue color was again ion-exchanged in new copper ion solution. After the desired repetition of the ion exchange treatment, the sample was washed with deionized water to remove coating materials on its surface and dried at 383 K overnight. It has been reported [1] that three or more ion exchange treatments result in high copper loading.

The preparation conditions for the six catalysts are shown in Table 1. Catalyst 1 was heat-treated in different ways; one batch was heated in He at 500°C for 2 hours, another in air at 500°C for 2 hours, to see the effect of heat pretreatment on the catalyst activity. Catalyst samples 1 and 3 were copper ion-exchanged once and three times, respectively, to examine the effect of exchange level on the catalytic activity. The starting Na⁺-ion exchange zeolite used in preparation of catalysts 3 to 6 was same, but the copper ion-exchange procedures were different. Catalyst 3 was only Cu-exchanged. Catalyst samples 4-6 were prepared by combination of Cu²⁺ with promoter, Mg²⁺, ions. The Cu²⁺/Mg²⁺-exchanged ZSM-5 samples were prepared in three ways corresponding respectively to catalysts 4, 5, and 6: (1) Cu²⁺-exchange followed by the promoter cation (Mg²⁺) exchange; (2) simultaneous ion-exchange of Cu²⁺ and the promoter cation, Mg²⁺; (3) exchange of the promoter cation, Mg²⁺, followed by Cu²⁺-exchange.

Experimental Procedure

A known weight of the ion-exchanged ZSM-5 catalyst was put in the packed-bed reactor to a length of about 2 cm. The reactor was heated to the desired temperature in helium. The reactant gas stream passed through the bed material after the desired reaction temperature was reached. The NO/NO_x levels were measured upstream and downstream of the reactor. An inlet gas mixture with 2,000 ppm of NO in He was used in the tests reported here. The contact times defined here as a catalyst weight velocity in g·catalyst/volumetric flow rate of gas mixture (STP) were 0.75 g·catalyst/s/ml and 2 g·catalyst/s/ml.

Results and Discussion

This quarter, three of the catalysts shown in Table 1, namely catalysts 1, 2, and 4, were studied at various temperatures in the above NO-He gas mixture.

The catalytic activity of each catalyst sample for the direct NO decomposition was measured as a function of time-on-stream, and reaction temperature. Figures 2, 3, and 4 show the NO conversion with time-on-stream over catalyst 1 at 475, 525 and 575°C. Figures 5, 6, and 7 show the NO conversion over catalyst 4 at different reaction temperatures. We started the runs over catalyst 1 at 475°C, and over catalyst 4 at 500°C. It can be seen in Figures 2 and 5 that the NO conversions were initially very high (about 100%), and gradually reached a stable, lower conversion after catalyst was on stream for about 2 hours. This may be due to loss of active catalyst sites by oxygen chemisorption. Figures 3, 4, and 6, 7 show the NO conversions over catalysts 1 and 4 respectively at various temperatures. Based on the NO and NO_x signals measured by the NO/NO_x chemiluminescent analyzer, during the first two hours there was no NO₂ produced under the conditions of Figures 2 and 5. When these catalysts were reacted further or at different temperatures the (NO_x-NO)/(inlet NO) was typically less than about 7%. Thus, for all the data reported here, the NO conversion is assumed to be to nitrogen and oxygen. More refined measurements of N₂, O₂, NO₂ will be performed in further experiments by complementing the NO/NO_x analyzer with a gas chromatograph.

Figures 8 and 9 show the variation of NO decomposition over catalysts 1 and 4 with reaction temperature. The catalytic activity of catalyst 4 is higher than that of catalyst 1.

During these experiments, the reaction temperature was automatically changed into the next desired one after a run was finished. For catalyst 4, the reactor was restarted from room temperature to 350, 400 and 450°C to perform tests after the continual runs were finished at 500, 525, 575, and 450°C. It was noteworthy that, when the temperature was again set to 450°C after the experiments at 350 and 400°C, the degree of NO conversion was the same as the degree of NO conversion at the first 450°C run. These results have shown that no deterioration of the effectiveness of the catalysts was found at different temperatures for over 15 hours.

Figure 10 shows NO conversion over Na/Cu-ZSM-5 and Ni/Cu-ZSM-5 with temperature [2]. Compared to Figure 9, it appears that catalyst 4, Mg/Cu-ZSM, used in our experiments, is of higher catalytic activity. Additional work is necessary to examine whether these catalysts differ on both the level of exchanged Cu ions and promoter type.

For catalysts 1 (calcined in air) and 2 (with the Mobil ZSM-5 substrate) we did not see any NO decomposition activity at 500°C.

Plans for Next Quarter

Continued testing of the catalysts prepared this quarter will be performed in the next reporting period to examine in more detail the effect of Cu^{2+} -exchange level and the promoting effect of Mg^{2+} on the catalytic reactivity of Cu/ZSM-5. The effect of contact time will be examined by varying gas flow rates and catalyst amounts. Titration of acid sites in the ion-exchanged ZSM-5 is planned to determine whether copper ions are in the zeolite framework. The results of these tests will provide us with potential new approaches to catalyst preparation. The gas chromatograph will be calibrated and used for N_2 , O_2 , and perhaps N_2O measurement complementing the information obtained by NO/ NO_x analyzer.

References

1. Iwamoto, M., Yahiro, H., Mine, Y., and Kagawa, S., Chemistry Letters, pp. 213-216, 1989.
2. Kagawa, S., Ogawa, H., Furukawa, H., and Teraoka, Y., Chemistry Letters, pp. 407-410, 1991.

Table 1 Summary of Catalyst Preparation Conditions

<u>Catalyst Number</u>	<u>Parent Zeolite</u>	<u>Pre-Ion Exchanges</u>	<u>Ion Exchanges</u>	<u>Heat Pre-Treatment</u>
1	a	NaNO ₃ Solution	Copper acetate once	in H ₂ , and air at 500°C for 2 hours, respectively
2	b	NaNO ₃ Solution	Copper acetate once	in H ₂ , and air at 500°C for 2 hours, respectively
3	a	NaNO ₃ Solution	Copper acetate three times	Not done yet
4	a	NaNO ₃ , then Mg(NO ₃) ₂ solution	Copper acetate three times	in He at 500°C for 2 hours
5	a	NaNO ₃ Solution	Mg(NO ₃) ₂ and Copper Acetate	Not done yet
6	a	NaNO ₃ , then copper acetate solution	Mg(NO ₃) Solution	Not done yet

Parent Zeolites: a: Davison, low Si/Al HZSM-5
 b: Mobil, HZSM-5 (MZ-354)

Fig. 1: Schematic of Reactor System

Fig. 2. NO decomposition over Catalyst 1 at 475° C with 2,000 ppm of NO concentration and 0.75 g/cm³/s of catalyst weight velocity.

Fig. 3. NO decomposition over Catalyst 1 at 525° C with 2,000 ppm of NO concentration and 0.75 g/cm³/s of catalyst weight velocity.

Fig. 4. NO decomposition over Catalyst 1 at 575° C with 2,000 ppm of NO concentration and 0.758 g/cm³/s of catalyst weight velocity.

Fig. 5. NO decomposition over Catalyst 4 at 500° C with 2,000 ppm of NO concentration and 2 g/cm³/s of catalyst weight velocity.

Fig. 6. NO decomposition over Catalyst 4 at 525° C with 2,000 ppm of NO concentration and 0.75 g/cm³/s of catalyst weight velocity.

Fig. 7. NO decomposition over Catalyst 4 at 575° C with 2,000 ppm of NO concentration and 2 g/cm³/s of catalyst weight velocity.

Fig. 8. NO conversion over Catalyst 1 with 2,000 ppm of NO concentration and $0.7 \text{ g/cm}^3/\text{s}$ of catalyst weight velocity.

Fig. 9. NO conversion over Catalyst 4 with 2,000 ppm of NO concentration and $2 \text{ g/cm}^3/\text{s}$ of catalyst weight velocity.

Fig. 10. NO decomposition over Na(21)-Cu(83)-Z2 ($\triangle$, ∇) and Ni(60)-Cu(75)-Z2 ($\blacktriangle$, $\blacktriangledown$).
 $W/F=1.9 \text{ g}\cdot\text{s}\cdot\text{cm}^{-3}$, $P_{NO}=0.48 \text{ vol\%}$.

(Kagawa, etc, Chemistry Letters, pp. 407 - 410, 1991)

END

**DATE
FILMED
9/16/92**