**THE STUDY OF STRUCTURE - PROCESSING -
PROPERTY RELATIONS IN COPPER OXIDE BASED
HIGH T_c SUPERCONDUCTORS**

Progress Report

July 1992 - June 1993

A. I. Kingon

Department of Materials Science and Engineering

North Carolina State University

Raleigh, North Carolina 27695

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

June 1993

RECEIVED

JUN 14 1993

OSTI

**PREPARED FOR THE U.S. DEPARTMENT OF ENERGY
UNDER GRANT NUMBER DE-FG05-88ER-45359**

MASTER

Summary

Our objective is the investigation of the critical current limiting processes in bulk superconductors. Since the grain boundaries play a key role here, we focus on the electrical characterization of single grain boundaries. Electrical contact to thin polished sections is established with thermosonic wire bonding. Laser cutting is used to isolate a single grain boundary. Results on $\text{YBa}_2\text{Cu}_3\text{O}_x$ showed that two different types of grain boundaries are present. Most grain boundaries showed current voltage characteristics typical for flux pinning effect and no or little change in low magnetic fields. However, Josephson effect could also be found in some grain boundaries exhibiting a remarkable decrease of I_c in low magnetic fields. Both types could be found in the same sample. Additionally we are working on $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_x$ thick films grown on silver foil or MgO substrates. The film showed metallic behaviour and $T_c=80\text{K}$. Preliminary results showed that the grain boundaries are of the flux pinning type.

Summary of Progress (Year 2 only)

Contacts: Processes for reliable and low resistivity contacts to the thin polished oxide superconductor samples were developed. Direct wire bonding to the superconductor had turned out not to be feasible, so a pattern of gold pads on the surface was necessary. First a gold layer was sputtered onto the surface of the superconductor. A pattern of square pads (100 by 100 μm^2) was developed on the gold layer using photolithography. Subsequent argon ion etching left a pattern of gold pads on the superconductor. However, the adhesion of the pads to the surface was very low. Annealing the sample at 450-600 $^{\circ}\text{C}$ for 5-10 hours was employed to improve adhesion properties and minimize the interface resistance. After mounting the sample in a chip carrier, gold wires were attached to the sample using thermosonic wire bonding. The contact resistivity achieved with this method was $20\mu\Omega\text{cm}^2$ ($T=77\text{K}$). The wires made only a minor contribution to the overall resistance at low temperature.

Electrical Characterization of $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$: The electrical properties of the grain boundaries were measured with the four terminal technique. The $R(T)$ characteristics showed metallic behaviour and a steep superconducting - normal transition with $T_c=91\text{K}$. Most of the grain boundaries showed current voltage characteristics typical for flux pinning behaviour. These samples also showed little or no change in their current voltage characteristics in applied magnetic fields up to 8mT. However, some grain boundaries were found that exhibited current voltage characteristics typical for Josephson junctions. They also showed a remarkable drop of I_c in fields of 0.1mT. The change from flux pinning to Josephson junction behaviour was not correlated to different sample preparation or sintering conditions. Both types of current voltage characteristics could be found in the same sample at opposite sides of the same grain. Our present measurement setup allows us to apply magnetic fields up to 8mT, which is sufficient for investigating Josephson junctions.

However, the flux pinning junctions didn't show any effect on these low fields. We are currently planning to acquire a superconducting magnet with a maximum field of 2-3T to overcome this problem.

Bi₂Sr₂CaCu₂O_x thick films: Superconducting tapes of Bi₂Sr₂CaCu₂O_x were made using the doctor blade technique. Bi₂Sr₂CaCu₂O_x powder was mixed with organic solvents and cast to form green tapes with a thickness of approximately 50-70μm. Small pieces of the tape were then placed on silver foil or single crystalline MgO substrates and sintered at 840-900 °C. It was noted that the silver plays an important role in the formation of the superconductor, so a 0.5μm thick silver layer had to be sputtered onto the MgO substrates. The superconducting phase formed large grains with sizes up to several 100 μm. The a-b planes of the grains were in general parallel to the surface of the MgO substrate. The superconducting properties of the thick films were checked using four terminal resistance measurement and ac-susceptibility and confirmed a metallic behaviour with T_c=80K. Preliminary results showed that the grain boundaries are of the flux pinning type and show little or no change in low magnetic fields. The superconducting magnet will be employed here for further investigation.

Research Objectives for the Next Year (Year 3)

Our main objective for the next year will be the continuation of the electrical characterization of single isolated grain boundaries, which will include measurements at high magnetic fields. We are planning to extend our research to samples with grain sizes considerably smaller than these of melt textured grown $\text{YBa}_2\text{Cu}_3\text{O}_x$. New techniques for contacts to this kind of samples have to be developed. The results will be compared to the measurements performed on the thick film $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_x$.

Additionally we are planning to perform structural analysis of grain boundaries. TEM will be employed to investigate the chemical composition of the interface layer between the grains. It is also important to check for stacking faults, dislocations etc. in the vicinity of the grain boundary. Electron channelling will be used to determine the angle of misorientation between the grains.

List of Students

<u>Name</u>	<u>Degree</u>	<u>Expected completion</u>
C. Sarma	Ph.D.	June 1994
R. Velasquez	M.S.	May 1993

Publications, Theses (Year 2 only)

a. Theses

Ricardo Velasquez, M.S., "Processing and Phase Equilibria of $\text{Pb}_2\text{Sr}_2(\text{Y}_{1-x}\text{Ca}_x)\text{Cu}_3\text{O}_{8+\delta}$ superconductors ($x=0.4-0.6$)", Department of Materials Science and Engineering, NCSU, 1993

b. Publications

"Grain Growth Kinetics and Microstructure in the High T_c $\text{GdBa}_2\text{Cu}_3\text{O}_{7-\delta}$ Superconductor", M. W. Shin, T. M. Hare, A. I. Kingon, and C. C. Koch, J. Mater. Res., 7[12], 3194-3201 (1992).

"Effects of Excess CuO on Grain Growth Kinetics, Sintering, and Microstructure in the $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$ Superconductor", M. W. Shin, A. I. Kingon, T. M. Hare, and C. C. Koch, Materials Letters, 15 [1,2] 13-18 (1992)

"Techniques for the Isolation and the Electrical Characterization of Individual Grain Boundaries in Polycrystalline Superconductors", G. Schindler, C. Sarma, D. G. Haase, C. C. Koch, and A. I. Kingon, submitted to CRYOGENICS, June 1993

Reprints + Preprint removed

END

DATE
FILMED

7 / 15 / 93