DOE/PC/89757--5

DE92 040019

DOE | PC

DE-AC22-89PC89757-5

THERMODYNAMICS AND SURFACE STRUCTURE OF COALS

Quarterly Report for the Period
October 1, 1990 to December 31, 1990

John W. Larsen, Deanna M. Quay,
James E. Roberts, and Patrick C. Wernett

Department of Chemistry
Lehigh University
Bethlehem, Pa. 18015

PREPARED FOR THE UNITED STATES DEPARTMENT OF ENERGY
Under Contract DE-AC22-89PC89757

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

SCOPE AND OBJECTIVES OF WORK

Scope. An understanding of the surface structure and chemistry of coals is necessary to understand and intelligently optimize processes dominated by surface interactions. In applications such as coal cleaning and coal slurries, the interactions occurring at the coal surface are critical. In all chemical reactions of solid coal, the reagent must first encounter the coal surface. How much of the surface is open to a molecule and the interactions occurring on contact with the coal surface are important, often crucial parameters. Our present scientific understanding of the coal surface and its interactions with solvents are rudimentary and inadequate to support the development of new processes and to allow full understanding of the technology which has already been developed, largely on a trial-and-error basis.

Objectives. The objectives of this work are to investigate the surface structure and surface interaction thermodynamics of a variety of coals and treated coals in order to develop an understanding of the coal surface and how it changes. The surface structure of coals will be analyzed by:

1) deposition of NMR relaxation agents to provide spectra of those atoms near the surface which yield direct information about the structure of the surface groups.

2) using ^{129}Xe NMR as a probe to determine pore size

distributions and the surface polarity of coals.

3) Measuring the dependence of surface area on adsorbate size for a variety of coals.

Thermodynamic studies of coals will be studied by:

4) inverse gas chromatography to obtain full desorption isotherms of coals.

5) to use classical calorimetric studies of coal surface-adsorbate interactions to generate a thermodynamic data base.

Present Work. Our work this quarter has been a BET gas adsorption and fractal analysis of Argonne: Lewiston-Stockton (85.5% C, dmmf); Blind Canyon (81.3% C, dmmf); and Wyodak-Anderson (76.0% C, dmmf) coals.

Background. The surface area and pore structure of coals are among their most important physical properties. They are well studied and good reviews are available.¹⁻⁴ We have presently determined the BET surface areas of the full series of Argonne coals using CO₂, N₂, ethane, and an homologous series of cyclic aliphatic hydrocarbons. We present here our data on three Argonne bituminous coals. Our adsorption data are inconsistent with the generally accepted interconnected bottle-necked pore model for

coals first proposed by Bond⁸. The adsorption data suggest that most coal pores are closed to the external surface and to reach them an adsorbate must diffuse through solid coal rather than through an interconnected pore network. The CO₂ BET surface areas for the Argonne coals are much larger than those obtained using the hydrocarbon gases, even though CO₂ is of similar size to cyclopropane and similar size and shape to ethane. We believe the much larger CO₂ surface areas are due to the solubility of CO₂ in coals^{5,6} (however see reference 7 for a conflicting view). This solubility allows CO₂ to penetrate into pores that are inaccessible from the external surface to insoluble molecules.

Experimental. We measured the surface areas of the Argonne coals using standard multipoint volumetric BET techniques^{3,9}, a series of aliphatic alkanes, N₂, and CO₂. All samples were dried by evacuation at 10⁻⁶ torr overnight on a Micromeritics Digisorb 2500 stainless steel adsorption apparatus. Twenty four hours equilibration time was allowed for the first adsorption point and six hours equilibration time was used for each subsequent point when using the cyclic hydrocarbon gases. Six hours equilibration time between adsorption points was used for all the other gases except N₂.¹⁰ The equilibrium time for N₂ was determined by the Digisorb 2500 automated N₂ surface area computer program. The data and measurement conditions for Argonne: Lewiston-Stockton, Blind Canyon, and Wyodak-Anderson coals are presented in figures 1-3 respectively.

Discussion. The coal surface areas obtained using CO₂, ethane and cyclopropane, all of similar cross sectional area, cannot be rationalized using a constricted pore model. Ethane (cylindrical) and cyclopropane (planar) have different shapes and slit like or cylindrical pores would discriminate between them. Both report much lower BET surface areas than CO₂, which is similar in shape to ethane (both cylindrical) and similar in area to both cyclopropane and ethane. Diffusion through constricted openings cannot be solely responsible for the differences in surface areas.

A fractal analysis of the adsorption data was performed. The fractal dimensionality of a surface can be determined by plotting the log of the adsorbate cross-sectional area against the log of the number of moles adsorbed for monolayer coverage (obtained directly from the BET equation). This approach was developed by Avnir and Pfeiffer (see Equation 1).¹¹⁻¹⁵

$$\log N = (-D/2) \log \sigma + \text{Const.} \quad (1)$$

here, N is the number of moles of the adsorbate required for monolayer surface coverage per gram adsorbent, σ is the cross-sectional area of the adsorbate, and D is the fractal dimensionality of the adsorbent surface. Figures 1-3 demonstrate the application of this analysis to Lewiston-Stockton (LS), Blind Canyon (BC), and Wyodak-Anderson (WA) coals respectively. Fractal dimensionalities of 15 for LS, 14 for BC, and 11 for WA were calculated based on the data for cyclic hydrocarbons. All of these are impossible values from a fractal standpoint. The observed surface areas are not controlled by a coal surface property.

We believe the steep dependence of the coal surface areas on adsorbate size is due to sharply different diffusion rates of the adsorbates through solid coal to reach the pores. The extraordinarily steep dependence of the measured surface area on adsorbate size is similar to molecular size dependence of diffusion rates through glassy polymers.¹⁶ The hydrocarbons reach only a small portion of the pores, that portion dependent on their diffusion rates. Those diffusion rates fall very rapidly as molecular size increases as expected for diffusion through a glassy polymer. Because of slow diffusion, adsorption equilibrium was not reached with the hydrocarbon adsorbates. All of the coals are glassy polymers under these conditions.^{17,18} CO_2 is soluble in coals, diffuses rapidly reaching closed pores, and so will report a large total pore surface area. These surface areas will be slightly overestimated due to the solubility of CO_2 in coals, but this effect is thought to be small (although this may be becoming controversial).^{1,5-7} Very small molecules like helium can diffuse reasonably rapidly through coals, resulting in accurate helium densities and valid pore volumes determined from them. Apparently, CO_2 is sufficiently polar to have an efficient interaction-based diffusion mechanism. To verify slow diffusion, ethane uptake was followed, in this laboratory, for 130 hours at -76°C on an Argonne Illinois No. 6 coal. Adsorption was continuous during this time and equilibrium had not been reached when the experiment was terminated.

The only other explanation of these data is that coal surface

areas are not being measured, just the solubility of the probe molecules in the coals. This argument is controverted by recent neutron diffraction studies of coal pores and by the agreement between CO₂ coal surface areas and those obtained from low-angle X-ray scattering experiments.^{19,20} Disagreement between the CO₂ and X-ray surface areas of two brown coals have also been reported.²¹

We propose that most pores in coals are closed. They cannot be reached by diffusion through a pore network but can only be reached by diffusion through solid coal. CO₂ gives accurate total surface areas because it dissolves in and rapidly diffuses through solid coals, reaching all the pores. This surface area is irrelevant to materials which are only slightly soluble or insoluble in coals for these can only reach a small portion of the pores. Thus, the diffusion rate controls the determined pore size. For the large molecules involved in direct liquefaction and most organic reactions, the effective surface areas of these coals are very small, only a few m²/g.

The consequences of this structure model for coal processing and reaction are significant. These coals cannot be considered high (hundreds of m²/g) surface area materials which are easily accessible. They are low surface area solids only slightly permeable to hydrocarbons. The advantages of fine grinding are obvious. Using solvents which will cause coal to become rubbery rather than glassy will enhance diffusion and thus reactivity.

Figure 1. BET Tilling Experiment on Argonne
 Lewiston-Stockton Coal
 81% C, 5.5% H, 11% O, 0.6% S, 20% ash (daf)

Figure 2. BET Tilling Experiment on Argonne
Blind Canyon Coal
79% C, 6.0% H, 13% O, 0.5% S, 5% ash (daf)

Figure 3. BET Tilling Experiment on Argonne
 Wyodak-Anderson Coal
 74% C, 5.1% H, 19% O, 0.5% S, 8% ash (daf)

REFERENCES

1. Marsh, H. Carbon 1987, 25, 49-58.
2. Mahajan, O. P. In Coal Structure; Meyers, R. A., Ed.; Academic Press: New York, 1982.
3. Mahajan, O. P.; Walker, P. L., Jr. In Analytical Methods for Coal and Coal Products; Karr, C., Jr., Ed., Academic Press: New York 1979; Vol. 1.
4. Sharkey, A. G., Jr.; McCartney, J. T. In Chemistry of Coal Utilization, Second Supplementary Volume; Elliott, M. A., Ed., Wiley: New York, 1981.
5. Reucroft, P. J.; Patel, H. Fuel 1986, 65, 816-820.
6. Reucroft, P. J.; Sethuraman, A. R. Energy Fuels 1987, 1, 72-75.
7. Stacy, W. O.; Jones, J. C. Fuel 1986, 65, 1171-1173.
8. Bond, R. L. Nature (London) 1956, 178, 104-105. Bond, R. L.; Spencer, D. H. T. Brennst. - Chem. 1956, 37, 233-234.
9. Brunauer, S.; Emmett, P. H.; Teller, E. J. Am. Chem. Soc. 1938, 60, 309-319.
10. Larsen, J. W.; Wernett, P. C. Energy Fuels 1988, 2, 719-720. The N₂ surface areas for all the Argonne coals were determined using the Micromeritics Digisorb 2500 automated 5-point BET N₂ adsorption program.
11. Pfeifer, P.; Avnir, D. J. Chem. Phys. 1983, 79, 3558-3565.
12. Avnir, D.; Farin, D.; Pfeifer, P. J. Chem. Phys. 1983, 79, 3566-3571.
13. Avnir, D.; Farin, D.; Pfeifer, D. Nature (London) 1984, 308, 261-263.
14. Farin, D.; Volpert, A.; Avnir, D. J. Am. Chem. Soc. 1985, 107, 3368-3370.
15. Farin, D.; Peleg, S.; Yavin, D.; Avnir, D. Langmuir 1985, 1, 399-407.

16. Van Krevelen, D. W. Properties of Polymers; Elsevier: New York, 1976, pp 403-425.

17. Brenner, D. Fuel 1985, 64, 167-173.

18. Lucht, L. M.; Larson, J. M.; Peppas, N. A. Energy Fuels 1987, 1, 56-68.

19. Spitzer, Z.; Ulicky, L. Fuel 1977, 55, 212-224.

20. Winans, R. E.; Thiyagarajan, P. Energy Fuels 1988, 2, 355-358.

END

**DATE
FILMED**

10 / 20 / 92