MTR

Proj. 22130.6.3
DOE/MC/22130-T13

DOE/MC/22130---T13

DE92 017785

LOW COST HYDROGEN/NOVEL MEMBRANE TECHNOLOGY
FOR HYDROGEN SEPARATION FROM SYNTHESIS GAS,
PHASE I

Contract Number: DE-AC21-85MC22130

A Quarterly Technical Progress Report
for the Period ending September 30, 1986

Contributors to this Report

R.W. Baker
I. Pinnau
J.G. Wijmans

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

Membrane Technology and Research, Inc.
1030 Hamilton Court • Menlo Park, California 94025 • (415) 328-2228

MASTER

Table of Contents

I. INTRODUCTION AND SUMMARY

II. PROGRESS THIS QUARTER

Task 3.1(1) Microporous Membranes
Task 3.1(2) Poly(etherimide) Membranes
Task 3.2 Construct Modules

III. PLANS FOR THE NEXT QUARTER

I. INTRODUCTION AND SUMMARY

This is the fourth quarterly technical progress report from Membrane Technology and Research, Inc. to the U.S. Department of Energy under contract number DE-AC21-85MC22130. This report covers the period 1 July - 30 September 1986. It further summarizes the development of polymer membranes useful in the separation of hydrogen from coal-derived synthesis gas during period 1 October 1985 - 30 September 1986.

During the last year we developed several high performance membranes for the separation of hydrogen from nitrogen and carbon monoxide. The heat resistant resins poly(methyl pentene) (TPX®, Mitsui Petrochemical Industries, New York, NY) and poly(etherimide) (Ultem®, General Electric, Pittsfield, MA) have been selected as polymers with outstanding properties for membrane preparation.

The properties of membranes prepared from these polymers are given in Table I. TPX is an example of a moderately selective and highly permeable membrane; the poly(etherimide) membranes are more selective but have lower fluxes. We believe these membranes will cover the range of properties required in our hydrogen separation program and we will concentrate the bulk of our future work on these membranes. A few experiments with palladium/silver membranes are also planned, as described in the Test Plan.

Table I. Separation Properties of Different Membranes for Hydrogen/Nitrogen Separation

PSf - Polysulfone
TPX® - Poly(methyl pentene)
PDMS - Polydimethylsiloxane
PEI - Poly(etherimide)
PA - Polyamide

<u>Source</u>	<u>Membrane structure</u>	<u>Selective layer</u>	<u>Configuration</u>	<u>Normalized flux (P/l)</u>		<u>Selectivity α H₂/N₂</u>
				(cm ³ (STP)/cm ² sec.cmHg) Nitrogen	Hydrogen	
MTR	PSf-PDMS-TPX	TPX®	flat sheet	1.7x10 ⁻⁵	2.2x10 ⁻⁴	13
MTR	PA-PEI-PDMS	PEI	flat sheet	1.9x10 ⁻⁷	3.0x10 ⁻⁵	160
GKSS*	PEI-PDMS	PEI	flat sheet	5.0x10 ⁻⁷	7.0x10 ⁻⁵	140
MTR	PEI-PDMS	PEI	hollow fiber	2.0x10 ⁻⁷	3.3x10 ⁻⁵	163

*purchased from GKSS Research Center, Geesthacht, West Germany

The preparation of our membranes can be briefly summarized as follows. TPX membranes have been prepared by making a three-layer composite structure shown in Figure 1a. In these membranes, the strength, seal function and permselectivity are performed by the different elements of the composite. The first, (bottom) layer is a microporous, tough support membrane made of polysulfone. It has no permselective properties and acts only to provide mechanical strength for the system. The second layer is a thin sealing layer of polydimethylsiloxane, which provides a smooth, defect-free surface on which the third, ultrathin permselective TPX layer can be cast. MTR has already prepared these membranes continuously and reproducibility is not a problem.

Two different types of poly(etherimide) membranes have been prepared at MTR: three-layer flat sheet and two-layer hollow-fiber composite membranes. Figure 1b shows the cross section of a poly(etherimide) three-layer composite membrane. This membrane consists of a microporous poly(amide) support coated with an ultrathin, selective layer of poly(etherimide). Since it is very difficult to prepare a defect-free poly(etherimide) layer of less than one micron, a thin highly permeable polydimethylsiloxane top layer is applied to prevent gas flow through remaining defects of the poly(amide)/poly(etherimide) membrane. This layer further protects the sensitive poly(etherimide) layer during the rolling process for the preparation of spiral-wound modules.

MTR has recently developed poly(etherimide) two-layer composite hollow-fiber membranes. Hollow fiber membranes have some major advantages over flat sheet membranes; in particular, no mechanical force acts on the selective layer during the module preparation. This is desirable because the delicate permselective layer of flat sheet composite membranes is easily damaged during the preparation of spiral-wound modules. The cross section of a hollow-fiber composite membrane is shown schematically in Figure 1d. The membrane consists of a thin, selective skin layer backed by a porous substructure. The skin layer is coated with polydimethylsiloxane to plug any defect in the selective layer.

In addition to these membranes prepared at MTR, flat sheet poly(etherimide) membranes were purchased from GKSS Research Center, Geesthacht, West Germany. These membranes are made by the Loeb-Sourirajan precipitation method, which yields integral-asymmetric membranes. As shown in Figure 1c, the membranes are comprised of a thin, selective skin layer (about 0.1 to 0.2 micron) and a 100-200 micron thick porous substructure which provides the membranes' strength. A polydimethylsiloxane top layer serves to plug defects of the skin and protect the membranes during the rolling process.

Figure 1 (a): TPX three-layer composite membrane (flat sheet)

Figure 1 (b): Polyetherimide three-layer composite membrane (flat sheet)

Figure 1 (c): Polyetherimide two-layer composite membrane (flat sheet)

Figure 1 (d): Polyetherimide two layer-composite membrane (hollow fiber)

II. PROGRESS THIS QUARTERTask 3.1.(1) Microporous Membranes

During the last quarter we continued to focus our work on solvent resistant microporous support membranes made from amorphous polyamide (Trogamid® T). The support membrane is cast on non-woven paper or web material. We investigated the influence of different web materials on the performance of the membrane. The properties of a number of membranes cast on different support materials are listed in Table II. The criteria that were used to determine the optimum web material were:

- high nitrogen flux through the microporous membrane,
- uniform and smooth surface of the microporous membrane, and
- no shrinkage of the microporous membrane.

The best web material for the preparation of Trogamid membranes is polyamide fabric Fabriquilt® #122 (Fabriquilt, Inc., North Kansas City, MO).

Table II. Influence of Different Support Materials on Microporous Trogamid® Membranes

Support material	Trade name	Nitrogen flux P/l (cm ³ (STP)/cm ² sec.cmHg)	Surface properties	Shrinkage
Polyester non-woven paper	Pellon® style T62360	6 x 10 ⁻²	non-uniform rough	no
Nylon web	Fabriquilt® # 122	4 x 10 ⁻²	uniform smooth	no
Nylon web	Fabriquilt® # 175	2 x 10 ⁻²	uniform smooth	no

The membranes listed in Table I were continuously cast on the support materials using a casting solution consisting of 15 wt% Trogamid T, 70 wt% acetic acid and 75 wt% dimethyl formamide. The casting thickness was 178 microns and the casting speed was 3 meters/minute. The membranes were quenched in a water bath at 160C. After precipitation the membranes were washed for 24 hours and dried at room temperature.

Task 3.1(2) Poly(etherimide) Membranes

The Trogamid support membranes cast onto Fabriquilt #122 were coated three times with a 0.5 wt% solution of poly(etherimide) (Uitem 6000) in methylene chloride. However, these composite membranes were not defect-free. Some typical data is shown in Table III. The hydrogen/nitrogen selectivities are all less than 10, well below the value of greater than 100 expected for a defect-free membrane. Therefore, a thin, very permeable sealing layer (TPX or polydimethylsiloxane) was applied to these membranes to plug the remaining membrane defects.

The thin sealing layer also protects the sensitive layer of poly(etherimide) during the winding process. Continuously prepared Trogamid/poly(etherimide)/TPX composite membranes were tested with pure gases at room temperature. The performance of membrane samples was encouraging, with an average hydrogen flux of 2 to $3 \times 10^{-5} \text{ cm}^3(\text{STP})/\text{cm}^2\text{sec.cmHg}$ and a hydrogen/nitrogen selectivity of at least 100. Some typical results are listed in Table IV.

Table III. Performance of Trogamid®-Poly(etherimide) Composite Membranes

Normalized flux (P/l) ($\text{cm}^3(\text{STP})/\text{cm}^2\text{sec.cmHg}$)		Selectivity $\alpha \text{ H}_2/\text{N}_2$
Nitrogen	Hydrogen	
9.4×10^{-6}	6×10^{-5}	6.4
1.1×10^{-5}	7×10^{-5}	6.4
1.2×10^{-5}	8×10^{-5}	6.7

Table IV. Performance of TPX®-Coated Trogamid®-Poly(etherimide) Composite Membranes

Normalized flux (P/l) ($\text{cm}^3(\text{STP})/\text{cm}^2\text{sec.cmHg}$)		Selectivity $\alpha \text{ H}_2/\text{N}_2$
Nitrogen	Hydrogen	
1.9×10^{-7}	2.5×10^{-5}	132
1.4×10^{-7}	2.5×10^{-5}	179
2.3×10^{-7}	2.9×10^{-5}	126

Task 3.2 Construct Modules

The Trogamid/poly(etherimide)/TPX membrane above was rolled into a spiral-wound module with an effective area of 700 cm². The permeation tests were carried out with hydrogen and nitrogen at different feed pressures at 200°C. As can be seen from Table V, the module selectivity was considerably less than the selectivity obtained with small samples of the same membrane. The decrease of the hydrogen/nitrogen selectivity with increased feed pressure is probably due to membrane defects that occurred during the rolling process or small leaks along the glue lines at the edges of the membrane envelope.

Table V. Performance of a TPX®-Coated Trogamid® -Poly(etherimide) Spiral-Wound Module

p (psi)	Normalized flux (P/l) (cm ³ (STP)/cm ² sec.cmHg)		α H ₂ /N ₂ (-)
	Nitrogen	Hydrogen	
10	4.2x10 ⁻⁷	2.2x10 ⁻⁵	52
20	1.8x10 ⁻⁶	2.2 x10 ⁻⁵	12

III. PLANS FOR THE NEXT QUARTER

The separation properties of various poly(etherimide) membranes is very encouraging and comparable to those of the best membranes reported in the literature. The membrane performance for each membrane type will be evaluated with gas mixtures. The influence of major feed gas parameters, (i.e. feed gas composition, feed pressure and temperature) on the membrane performance will be determined.

Further, we will concentrate on improving the performance of the Trogamid/poly(etherimide)/TPX spiral-wound modules. Their potential value as separation systems will be assessed. A few experimental modules of poly(etherimide) membranes in hollow-fiber form have been prepared at MTR using internal research and development funds. These modules have a surprisingly high performance and a few preliminary tests with pure and mixed gases will be performed with these modules also.

END

**DATE
FILMED
9/01/92**