TOPICAL REPORT

ENHANCED DURABILITY AND REACTIVITY FOR
ZINC FERRITE DESULFURIZATION SORBENT

VOLUME 2

SINGLE PARTICLE KINETIC STUDIES OF SULFIDATION AND
REGENERATION REACTIONS OF CANDIDATE ZINC FERRITE SORBENTS

By

A. Silaban

D. P. Harrison

Louisiana State University

Department of Chemical Engineering

Baton Rouge, Louisiana 70803

DOE/MC/23172--T7-Vol.2

DE92 017544

Subcontractor to

AMAX Research & Development Center

5950 McIntyre Street

Golden, Colorado 80430

DOE Contract No. DE-AC21-86MC23172

May 2, 1989

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

APPROVED FOR RELEASE OR
PUBLICATION - OR PATENT GROUP
BY *QCB* DATE *7/28/92*

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

TOPICAL REPORT

ENHANCED DURABILITY AND REACTIVITY FOR
ZINC FERRITE DESULFURIZATION SORBENT

VOLUME 2

SINGLE PARTICLE KINETIC STUDIES OF SULFIDATION AND
REGENERATION REACTIONS OF CANDIDATE ZINC FERRITE SORBENTS

By
A. Silaban
D. P. Harrison
Louisiana State University
Department of Chemical Engineering
Baton Rouge, Louisiana 70803

Subcontractor to
AMAX Research & Development Center
5950 McIntyre Street
Golden, Colorado 80430

DOE Contract No. DE-AC21-86MC23172

May 2, 1989

ACKNOWLEDGEMENT

This research was supported by subcontract from AMAX Research & Development Center under prime Contract Number DE-AC21-86MC23172 from the U. S. Department of Energy, Morgantown Energy Technology Center. The authors would like to thank Dr. Mahesh Jha and Mr. Mark Berggren of AMAX and Mr. Suresh Jain of METC for their assistance and cooperation during the period of the research.

EXECUTIVE SUMMARY

This report describes the results of research entitled "Single Particle Kinetic Studies of Sulfidation and Regeneration Reactions of Candidate Zinc Ferrite Sorbents", performed by the Department of Chemical Engineering of Louisiana State University as a subcontractor to AMAX Research & Development Center, prime contractor to the U. S. Department of Energy, Morgantown Energy Technology Center under Contract Number DE-AC21-86MC23172 entitled "Enhanced Durability and Reactivity for Zinc Ferrite Desulfurization Sorbent".

The sulfidation and regeneration kinetics of approximately 35 formulations of zinc ferrite sorbent supplied by AMAX were tested in a single pellet electrobalance reactor. A typical 1-1/2-cycle test consisted of first-cycle reduction, first-cycle sulfidation, first-cycle regeneration, second-cycle reduction, and second-cycle sulfidation. Standard sulfidation conditions were chosen to be 1,022°F (550°C) using a simulated coal-gas composition containing 2.7 volume percent H₂S. Standard regeneration conditions chosen were 1,292°F (700°C) in a gas composed of 4 percent O₂, 66 percent N₂, and 30 percent H₂O (all volume percent). The reduction portion of the cycle was carried out at 1,022°F (550°C) using the H₂S-free sulfidation gas. The artificially high H₂S concentration during sulfidation was chosen to increase the global reaction rate so that a complete sulfidation test could be completed in approximately 3 hours. In addition to the single pellet tests conducted at standard conditions, selected formulations were tested using lower regeneration temperatures of 1,202 and 1,112°F (650 and 600°C).

Formulation variables considered by AMAX in preparing the zinc ferrite sorbents included:

- ZnO-to-Fe₂O₃ stoichiometric ratio (0.8:1.0 and 1.0:1.0).
- Fe₂O₃ grade (Mobay pigment grade and UCI catalyst grade).
- Binder (weight percent bentonite and weight percent methocel or starch).
- Shape (cylindrical extrudes and spherical pellets).
- Induration conditions (time and temperature).

AMAX prepared approximately 120 formulations representing various combinations of the above variables. The resultant sorbents were screened on the basis of crush strength and specific surface area in order to select the formulations to be tested by LSU.

The single pellet kinetic results were analyzed to develop a reactivity index and reactivity maintenance index for each

formulation. These indices permit direct comparison of the effect of the individual formulation variables and when coupled with the results from multiple cycle integral fixed-bed reactor studies being performed by AMAX, should identify the formulation variables most effective in improving the reactivity and stability of zinc ferrite sorbent.

Induration conditions were found to be the most important formulation variables. Sorbents indurated at the most severe conditions (highest temperature and longest time) exhibited lower values of both reactivity and reactivity maintenance indices. This result implies that the optimum induration conditions must be based upon a compromise between sorbent crush strength which increases with increasing induration severity and the kinetic properties which are adversely affected by induration severity.

Other formulation variables are of lesser importance. The $\text{ZnO}:\text{Fe}_2\text{O}_3$ ratio has no significant effect on either reactivity or reactivity maintenance. The catalyst grade of Fe_2O_3 produces sorbents having marginally greater reactivity, but sorbents formulated with pigment-grade Fe_2O_3 have higher values of the reactivity maintenance index. A single sorbent produced from Ruthner grade Fe_2O_3 showed high values of both reactivity and reactivity maintenance. Additional formulations using Ruthner grade Fe_2O_3 should be prepared and tested. Ruthner grade Fe_2O_3 is produced during recovery of acid from steel pickling liquors. The effect of inorganic binder (bentonite) concentration is somewhat contradictory. For spherical pellets, bentonite concentration had no measurable effect on the reactivity index, but high bentonite concentration (10 percent) produced pellets having higher reactivity maintenance values. For extrudes, there was essentially no effect of bentonite concentration on either reactivity or reactivity maintenance. The organic binder (starch for pellets and methocel for extrudes) had no measurable effect on pellet or extrude reactivity but did improve reactivity maintenance for both pellets and extrudes.

A series of supplementary tests showed that reactivity maintenance improved when the regeneration temperature was lowered from the standard $1,292^\circ\text{F}$ (700°C). The values of $\text{RM}(t)$ increased by approximately 10 percent when regeneration was carried out at $1,202^\circ\text{F}$ (650°C). Further increases in $\text{RM}(t)$ were associated with $1,112^\circ\text{F}$ (600°C) regeneration, but significant amounts of zinc sulfate were formed at this temperature. No appreciable zinc sulfate was formed during regeneration at either $1,202$ or $1,292^\circ\text{F}$ (650 or 700°C).

Comparison of the single particle kinetic results with the multi-cycle fixed-bed test results of AMAX indicated the potential value of single particle testing for screening sorbent formulations. Sorbent P-11A was found to be the best pellet sorbent tested by AMAX; this same result is predicted

from the single particle tests. Similarly, base sorbent T-2465 should, on the basis of the single particle tests, have exhibited the best performance of all extrude sorbents tested, based strictly on reactivity and considering strength. AMAX results have confirmed the superiority of T-2465.

TABLE OF CONTENTS

	<u>Page</u>
I. HIGH TEMPERATURE DESULFURIZATION	1
INTRODUCTION	1
OBJECTIVES OF THE AMAX STUDY	1
OBJECTIVES OF THE LSU STUDY	2
II. THE SORBENT FORMULATION PROGRAM OF AMAX	3
SORBENT FORMULATION VARIABLES	3
ZnO/Fe ₂ O ₃ Ratio	3
Iron Oxide Grade	3
Binders	3
Shape	4
Induration Conditions	4
SUMMARY OF SORBENTS AND THEIR PROPERTIES	4
III. EXPERIMENTAL APPARATUS, PROCEDURE AND MATERIALS	9
ZINC FERRITE CHEMISTRY	9
SINGLE PELLET REACTOR	10
STANDARD REACTION CONDITIONS	14
TEST SORBENTS	15
REACTIVITY AND REACTIVITY MAINTENANCE INDICES	17
IV. RESULTS OF SPHERICAL PELLET TESTS	19
INTRODUCTION	19
REPRODUCIBILITY	21
REACTIVITY AND REACTIVITY MAINTENANCE RESULTS	25
REACTIVITY ANALYSIS	27
ZnO:Fe ₂ O ₃ Ratio	30
Fe ₂ O ₃ Grade	32
Inorganic Binder	33
Organic Binder	34
Induration Conditions	34
Summary of the Effect Sorbent Formulation Parameters	35
Structural Properties	35
REACTIVITY MAINTENANCE ANALYSIS	37
ZnO:Fe ₂ O ₃ Ratio	38
Fe ₂ O ₃ Grade	40
Inorganic Binder	40
Organic Binder	41
Induration Conditions	42
Summary of Sorbent Formulation Parameters	42
Structural Properties	43

TABLE OF CONTENTS
(Continued)

	<u>Page</u>
V. RESULTS OF CYLINDRICAL EXTRUDE TESTS	45
INTRODUCTION	45
REPRODUCIBILITY	47
REACTIVITY AND REACTIVITY MAINTENANCE RESULTS	47
REACTIVITY ANALYSIS	52
ZnO:Fe ₂ O ₃ Ratio	52
Fe ₂ O ₃ Grade	55
Inorganic Binder	56
Organic Binder	56
Induration Conditions	57
Summary of Sorbent Formulation Parameters	60
Structural Properties	61
REACTIVITY MAINTENANCE ANALYSIS	63
ZnO:Fe ₂ O ₃ Ratio	63
Fe ₂ O ₃ Grade	63
Inorganic Binder	65
Organic Binder	66
Induration Conditions	66
Summary of the Effect of Sorbent Formulation Parameters	68
Structural Properties	68
VI. SUPPLEMENTAL STUDIES	70
REGENERATION TEMPERATURE	70
COMPARISON WITH FIXED-BED RESULTS	76
VII. SUMMARY AND CONCLUSIONS	81
NOMENCLATURE	84
REFERENCES	85

LIST OF TABLES

	<u>Page</u>
Table II-1. Zinc Ferrite Spherical Pellet Characteristics	5
Table II-2. Zinc Ferrite Cylindrical Extrude Characteristics	7
Table III-1. Standard Reaction Test Conditions	14
Table III-2. Sorbents Selected for Single Pellet Testing	16
Table IV-1. Summary of Spherical Pellet Test Conditions	20
Table IV-2. Reproducibility Comparisons for Base Sorbent 1094-59	22
Table IV-3. Reproducibility Comparisons for Test Sorbent P-21	24
Table IV-4. Summary of R(20) and RM(20) Results for Spherical Test Sorbents	26
Table IV-5. Comparison of Pellet Reactivity	31
Table IV-6. Comparison of Pellet Reactivity Maintenance	39
Table V-1. Summary of Cylindrical Extrude Test Conditions	46
Table V-2. Reproducibility Comparisons for Sorbent E-16	48
Table V-3. Summary of R(30) and RM(30) Results for Cylindrical Extrude Sorbents	49
Table V-4. Comparison of Extrude Reactivity	54
Table V-5. Comparison of Extrude Reactivity Maintenance	64
Table VI-1. The Effect of Regeneration Temperature on Reactivity Maintenance	76
Table VI-2. R(t) and RM(t) Values of Sorbents Tested in the AMAX Bench-Scale Reactor	80
Table VII-1. Summary of the Effect of Formulation Variables on R(t) and RM(t)	82

LIST OF FIGURES

	<u>Page</u>
Figure III-1. Electrobalance schematic.	11
Figure III-2. Gas feed manifold.	12
Figure III-3. Typical TGA response for 1-1/2 cycle test.	13
Figure IV-1. Time-conversion results for pellets exhibiting maximum and minimum reactivity.	28
Figure IV-2. Comparison of first and second cycle sulfidation results for pellets exhibiting maximum and minimum reactivity maintenance.	29
Figure IV-3. The effect of surface area on pellet R(20).	36
Figure IV-4. The effect of porosity on pellet R(20). .	37
Figure IV-5. The effect of surface area on pellet RM(20).	44
Figure IV-6. The effect of porosity on pellet RM(20).	44
Figure V-1. Time-conversion results for extrudes exhibiting maximum and minimum reactivity.	51
Figure V-2. Comparison of first and second cycle sulfidation results for extrudes exhibiting maximum and minimum reactivity maintenance.	53
Figure V-3. The effect of induration conditions on extrude R(30).	59
Figure V-4. The effect of surface area on extrude R(30).	61
Figure V-5. The effect of porosity on extrude R(30).	62
Figure V-6. The effect of surface area on extrude RM(30).	69
Figure V-7. The effect of porosity on extrude RM(30).	69

LIST OF FIGURES
(Continued)

	<u>Page</u>
Figure VI-1. Regeneration results for sorbent P-21 as a function of temperature.	71
Figure VI-2. Regeneration results for sorbent E-2 as a function of temperature.	72
Figure VI-3. Second sulfidation cycle kinetics for sorbent P-21 as a function of regeneration temperature.	74
Figure VI-4. Second sulfidation cycle kinetics for sorbent E-2 as a function of regeneration temperature.	75
Figure VI-5. Breakthrough capacity as a function of cycle number, AMAX results for pellet sorbents.	78
Figure VI-6. Breakthrough capacity as a function of cycle number, AMAX results for extrude sorbents.	79

CHAPTER I. HIGH TEMPERATURE DESULFURIZATION

INTRODUCTION

Improved technology for high-temperature desulfurization of coal-derived gases is an important component of DOE's program for coupling coal gasification with advanced power generation systems such as integrated gasification combined cycles (IGCC) and molten carbonate fuel cells (MCFC).

The mixed metal oxide zinc ferrite (ZnFe_2O_4) is presently considered a prime candidate sorbent for high temperature H_2S removal. It is known that ZnFe_2O_4 will react rapidly and to completion, H_2S concentrations below 5 ppm (volume) may be achieved prior to breakthrough from a fixed-bed reactor, and sulfided sorbent may be regenerated and resulfided without major reactivity losses. While regeneration and resulfidation are known to be possible, questions concerning the long-term durability of zinc ferrite, a key factor in the economics of any high temperature desulfurization process, remain.

Some of the early tests using ZnFe_2O_4 indicated relatively poor reactivity maintenance. However, sorbent stability was not a major concern at that time. More recently, it has been found that sorbent stability can be improved by varying formulation conditions and by the addition of small amounts of an inorganic binder (bentonite) to ZnFe_2O_4 . For example, in a previous study by AMAX (Jha, 1986), a particular ZnFe_2O_4 formulation (designated 1094-49) was subjected to 43 complete sulfidation/regeneration cycles. Sorbent sulfur capacity at H_2S breakthrough was decreased only by approximately 1/3, from 15.8 to 10.2 lb S/100 lb fresh sorbent over the 43 cycles.

OBJECTIVES OF THE AMAX STUDY

The overall objective of the present AMAX study is to identify and investigate methods for improving the reactivity and durability of the zinc ferrite sorbent to be used in IGCC and MCFC applications. The sorbent should possess a strong porous structure to permit rapid diffusion of H_2S into the pores and sufficient surface area to permit rapid reaction. A sorbent possessing the desired durability characteristics will maintain its mechanical strength, as well as porous structure and surface area, through numerous sulfidation/regeneration cycles.

The improved reactivity and durability are to be attained by systematically varying sorbent formulation conditions and evaluating the effect of each change on selected sorbent structural parameters such as crush strength and specific surface area, single pellet reactivity through two sulfidation and one regeneration cycles, and, ultimately, by comparing

sorbent performance through 10 complete cycles in a small fixed-bed reactor.

The test program calls for a pyramidal approach with a large number of formulations to be prepared and characterized in terms of crush strength and surface area. On the basis of these results, a sub-set of formulations is to be tested for 1-1/2 cycles in the single pellet reactor. Finally, only the most promising formulations are to be fully evaluated by running 10 cycles in the fixed-bed reactor.

OBJECTIVES OF THE LSU STUDY

LSU, under subcontract to AMAX, is to perform the single pellet kinetic studies using the sub-set of formulations chosen from the large number originally prepared. The kinetic studies are to be performed under standard conditions so that results from different formulations may be directly compared. Selection of the smaller number of sorbents to be subjected to multiple cycle testing in the fixed-bed reactor will be based, in part, on the single pellet test results.

CHAPTER II. THE SORBENT FORMULATION PROJECT OF AMAX

Because the LSU single pellet kinetic program is an integral portion of the broader AMAX test program, a more complete understanding of the AMAX effort, particularly with respect to sorbent formulation variables, is necessary.

SORBENT FORMULATION VARIABLES

The first step in the AMAX program of enhanced reactivity and durability was the preparation of a large number of sorbent samples in which five formulation parameters were varied.

ZnO/Fe₂O₃ Ratio

The majority of previous studies have used a sorbent formulated from stoichiometric equivalents of ZnO and Fe₂O₃ to produce ZnFe₂O₄. Higher proportions of zinc, including pure ZnO, have exhibited poorer performance, which has been attributed to the tendency of ZnO to be reduced to volatile metallic zinc at the higher temperatures of interest.

In this study, sorbents have been prepared containing both stoichiometric equivalents (1.0 ZnO:1.0 Fe₂O₃) and excess iron (0.8 ZnO:1.0 Fe₂O₃). In addition to potentially producing a more stable sorbent, raw material costs may be somewhat reduced by increasing the proportion of potentially less expensive Fe₂O₃. Overall sorbent capacity is not significantly altered by the change in proportions, since the capacity of each component is almost equal. ZnO has a theoretical capacity of 393 g S per kg sorbent, while the capacity of Fe₂O₃ is 401 g S per kg sorbent.

Iron Oxide Grade

Previous AMAX tests (Jha, 1986) indicated that satisfactory sorbent performance could be achieved using both pigment-grade (Mobay Chemical) and catalyst-grade (United Catalysts, Inc.) Fe₂O₃. The raw materials differ in particle size, specific surface area, and, importantly, price. One of the test program objectives is to compare the performance of sorbents prepared using both grades of Fe₂O₃.

Binders

Both organic (primarily methocel) and inorganic (primarily bentonite) binders have been used in previous zinc ferrite formulations. Organic binders serve as an extrusion aid and create pellet porosity and surface area when they are burned away during sorbent induration. While sorbents containing an organic binder tend to exhibit high initial reactivity, they also tend to disintegrate and exhibit poor durability in repeated cyclic testing. The addition of inorganic binders

such as bentonite (or other clays) is thought to produce a stronger pellet with increased durability during multiple cycle operation. In the present program, sorbents containing up to 2 weight percent organic binder (methocel or starch) and up to 10 weight percent inorganic binder (bentonite) have been prepared.

Shape

While the majority of past studies have used cylindrical extrudes, spherical pellets have also been considered. The spherical pellets are thought to provide better handling properties and more uniform gas flow patterns. Also, stresses caused by temperature variation and sulfidation/regeneration chemistry effects are believed to be more severe in the cylindrical shape. Both sorbent shapes have been prepared for evaluation in the current test program.

Induration Conditions

Both cylindrical extrudes and spherical pellets must be indurated at high temperature in order to impart the proper combination of pellet strength and structure. As a general rule, more severe induration conditions increase pellet strength but reduce surface area and porosity. Induration temperature and time have been varied between 1,500 and 1,900°F (815 and 1,040°C) and 0.25 and 4 hours, respectively, in this program.

SUMMARY OF SORBENTS AND THEIR PROPERTIES

A summary of all sorbent formulations prepared by AMAX in the current test program is presented in Table II-1 (for spherical pellets) and Table II-2 (for extrudes). One base sorbent of each shape was chosen from previous test programs to serve as a reference. Reactivity and durability characteristics of the newly prepared sorbents are to be compared to the corresponding values of the reference sorbent.

The reference sorbent for spherical pellets is AMAX 1094-59. This sorbent, which is equivalent to AMAX 1094-49 developed in the previous study (Jha, 1986), was prepared with stoichiometric quantities of ZnO and pigment-grade Fe₂O₃. This formulation contained 5 weight percent bentonite and 2 weight percent starch. The pellets were indurated for 3 hours at 1,825°F.

UCI T-2465 was chosen as the reference extrude sorbent. This sorbent has exhibited good reactivity and durability in bench-scale tests (Grindley, 1987) and was selected for use in the larger-scale process demonstration unit operated by KRW (Smith, 1987). This sorbent was formulated using stoichiometric proportions of ZnO and catalyst-grade Fe₂O₃ and

Table II-1. Zinc Ferrite Spherical Pellet Characteristics

Sorbent Sample Number	Pellet Formulation					Physical Properties							
						Induration Conditions		Bulk Density, kg/l	Crush Strength, lb		Loss on Attrition, %	BET Surface Area, m ² /g	TGA Testing
	Run No.	Fe ₂ O ₃ Grade	ZnO/ Fe ₂ O ₃	% Bentonite	% Starch	Temp., °F	Time, Hours		x	s			
1094-59	Base	Pigment	1.0	5	2	1,825	3.00	1.014	5.1	2.9	54.5	1.01	*
P1	2	Pigment	0.8	2	0	1,500	0.25	0.876	4.6	1.8	65.1		
P2						1,500	4.00	0.912	3.8	1.5	76.7		
P3						1,700	2.00	0.916	4.8	1.5	60.2		
P4						1,700	2.00	0.860	5.7	2.8	54.0		
P5						1,900	0.25	0.952	6.6	3.7	51.5	3.95	*
P6						1,900	4.00	1.529	40.3	10.7	10.2	1.28	*
P6A						1,900	4.00	1.488	22.0	8.2	11.0	1.68	
P7	3	Catalyst	1.0	2	0	1,500	0.25	0.999	9.3	4.4	42.8		
P8						1,500	4.00	0.952	6.8	2.9	40.7		
P9						1,700	2.00	1.013	10.0	4.8	33.7		
P10						1,700	2.00	1.048	10.1	4.1	31.6	2.43	*
P11						1,900	0.25	1.036	10.5	4.1	32.4	2.47	*
P11A						1,900	0.25	1.141	16.6	6.0	19.5	2.63	
P12						1,900	4.00	1.273	21.5	10.2	24.5	1.38	*
P13	5	Catalyst	0.8	2	2	1,500	0.25	1.028	14.5	3.3	16.2		
P14						1,500	4.00	1.034	17.6	5.5	18.7		
P15						1,700	2.00	1.075	18.2	5.5	13.8		
P16						1,900	0.25	1.196	27.3	5.4	10.7	1.55	*
P17						1,900	4.00	1.339	32.8	5.3	8.4	1.43	*
P18	19	Catalyst	1.0	10	0	1,500	0.25	0.956	10.2	1.8	36.5		
P19						1,500	4.00	0.955	11.3	2.5	33.5		
P20						1,700	2.00	0.952	11.6	2.6	32.0		
P21						1,900	0.25	0.955	12.3	3.4	29.7	2.46	*
P22						1,900	4.00	1.132	20.8	6.6	22.8	2.10	*
P23	21	Catalyst	0.8	10	2	1,500	0.25	0.914	5.7	2.3	42.4		
P24						1,500	4.00	0.902	7.1	2.5	39.0		
P25						1,700	2.00	0.922	10.4	1.9	35.0		
P26						1,900	0.25	0.956	15.0	3.5	25.5	2.05	*
P27						1,900	4.00	1.111	21.2	4.8	19.9	1.91	*
P27A						1,900	4.00	1.143	22.0	8.5	19.1	1.21	
P28	8	Pigment	1.0	2	2	1,500	0.25	0.900					
P29						1,500	4.00	0.918	3.7	1.4			
P30						1,700	2.00	0.906	3.9	0.8			
P31						1,900	0.25	0.972	6.5	3.0		2.57	*
P32						1,900	4.00	1.270	19.4	6.9			
P32A						1,900	4.00	1.276	20.5	6.4	25.1	0.77	*

Table II-1. Zinc Ferrite Spherical Pellet Characteristics
(Continued)

Sorbent Sample Number	Run No.	Pellet Formulation				Induration Conditions		Physical Properties				BET Surface Area, m ² /g	TGA Testing
		Fe ₂ O ₃ Grade	ZnO/ Fe ₂ O ₃	% Bentonite	% Starch	Temp., °F	Time, Hours	Bulk Density, kg/l	Crush Strength, lb		Loss on Attrition, %		
P33	10	Pigment	0.8	5	0	1,500	0.25	0.878					
P34						1,500	4.00	0.834	4.3	1.0			
P35						1,700	2.00	0.877	5.2	1.6			
P36						1,900	0.25	0.993	10.0	3.6	49.9		
P37						1,900	4.00	1.456	34.8	9.7	10.8		
P37A						1,900	4.00	1.279	22.1	6.6	9.3	1.76	*
P38	16	Pigment	1.0	5	2	1,500	0.25	0.926					
P39						1,500	4.00	0.940	4.4	2.0			
P40						1,700	2.00	0.928	3.9	1.7			
P41						1,900	0.25	1.020	9.1	3.4	29.5		
P42						1,900	4.00	1.383	31.2	5.9	14.6		
P42A						1,900	4.00	1.240	17.0	3.0	20.9	1.07	*
P43	11	Catalyst	1.0	5	0	1,500	0.25	0.930	5.8	1.6			
P44						1,500	4.00	0.939	5.1	1.9			
P45						1,700	2.00	0.979	6.9	3.0			
P46						1,900	0.25	0.988	6.8	3.0			
P47						1,900	4.00	1.234	17.7	4.1	22.0	1.40	*
P48	13	Catalyst	0.8	5	2	1,500	0.25	0.889	7.3	3.5			
P49						1,500	4.00	0.882	5.7	2.7			
P50						1,700	2.00	0.920	9.0	4.5			
P51						1,900	0.25	0.997	13.4	6.6	32.7	1.76	
P52						1,900	4.00	1.142	22.3	6.8	25.5	1.63	*
P53	18	Pigment	0.8	10	0	1,500	0.25	0.860	3.5	1.7			
P54						1,500	4.00	0.846	5.1	2.0			
P55						1,700	2.00	0.858	5.6	2.0			
P56						1,900	0.25	0.860	5.8	1.6			
P57						1,900	4.00	1.275	45.3	8.5	15.1	1.67	*
P58	24	Pigment	1.0	10	2	1,500	0.25	0.712	0.6	0.6			
P59						1,500	4.00	0.733	0.8	0.9			
P60						1,700	2.00	0.751	1.8	0.7	79.6		
P61						1,900	0.25	0.729	2.2	1.8	84.5		
P62						1,900	4.00	0.947	12.2	4.4	49.2	1.64	*

Notes: x = Average single pellet crush strength.

s = Standard deviation.

An "A" designation in the sorbent sample number indicates preparation of a larger sample for cyclic testing.

Table 11-2. Zinc Ferrite Cylindrical Extrude Characteristics

Sorbent Sample Number	Pellet Formulation					Induration Conditions		Physical Properties					BET Surface Area, m ² /g	TGA Testing
	Run No.	Fe ₂ O ₃ Grade	ZnO/ Fe ₂ O ₃	X Bentonite	X Methocel	Temp., Of	Time, Hours	Bulk Density, kg/l	Crush Strength, lb		Loss on Attrition, %			
									x	s				
T-2465	Base	Catalyst	1.0	2	0	1,550	2.00	1.306	30.2	6.3	11.2	3.30	*	
E1	1	Catalyst	0.8	2	0	1,500	0.25	1.199	29.4	7.0	9.8	5.12	*	
E2						1,500	4.00	1.120	42.5	8.5	7.7	4.39	*	
E2A						1,500	4.00							
E3						1,700	2.00	1.159	39.1	8.0	11.9			
E4						1,900	0.25	1.172	46.2	8.0	8.2	3.59		
E5						1,900	4.00	1.355	>50		5.7			
E6	4	Pigment	1.0	2	0	1,500	0.25	1.130	24.6	4.6	16.5			
E7						1,500	4.00	1.154	26.0	6.1	18.2	5.77	*	
E7A						1,500	4.00	1.250	24.4	7.1	12.5	5.62		
E8						1,700	2.00	1.147	24.2	6.3	14.1			
E9						1,900	0.25	1.354	46.8	11.7	6.6	2.74	*	
E10						1,900	4.00	1.501	>50		4.9			
E11	7	Catalyst	1.0	2	0.5	1,500	0.25	1.215	31.8	8.5	12.2	4.39	*	
E12						1,500	4.00	1.196	33.3	6.5	13.3	4.36	*	
E13						1,700	2.00	1.148	37.7	6.6	15.5	3.37	*	
E13A						1,700	2.00	1.260	33.2	7.2	14.6	4.06		
E14						1,900	0.25	1.272	>50		8.3			
E15						1,900	4.00	1.623	>50		6.8	1.42	*	
E16	9	Catalyst	0.8	5	0	1,500	0.25	1.269	>50		6.1	4.78	*	
E17						1,500	4.00	1.238	>50		9.4			
E18						1,700	2.00	1.231	>50		10.8			
E19						1,900	0.25	1.367	>50		8.5	2.51		
E20						1,900	4.00	1.743	>50		5.7			
E21	15	Catalyst	1.0	5	0.5	1,500	0.25	1.195	>50		9.9	4.62	*	
E22						1,500	4.00	1.207	36.8	7.6	11.7			
E23						1,700	2.00	1.220	>50		10.2			
E24						1,900	0.25	1.300	>50		7.4	2.93	*	
E24A						1,900	0.25	1.328	41.3	12.0	8.3	4.15		
E25						1,900	4.00	1.676	>50		5.3			
E26	16	Pigment	0.8	5	0.5	1,500	0.25	1.070	43.5	8.9	9.3			
E27						1,500	4.00	1.082	46.2	9.4	8.9			
E28						1,700	2.00	1.110	44.8	8.2	9.0			
E28A						1,700	2.00	1.115	29.7	7.3	10.7	4.99	*	
E29						1,900	0.25	1.254	>50		6.0			
E30						1,900	4.00	1.888	>50		3.9			
E31	6	Pigment	0.8	2	0.5	1,500	0.25	1.168	26.1	9.7	13.9	6.31	*	
E32						1,500	4.00	1.174	20.5	8.4	14.0			
E32A						1,500	4.00	1.191	27.9	7.1	15.4	6.33	*	
E33						1,700	2.00	1.123	25.8	8.0	12.5			
E34						1,900	0.25	1.234	38.2	11.3	9.0			
E35						1,900	4.00	1.686	>50		2.9	1.42	*	
E36	12	Pigment	1.0	5	0	1,500	0.25	1.092	39.8	12.0	6.9	5.76	*	
E37						1,500	4.00	1.138	40.7	7.4	6.7			
E38						1,700	2.00	1.174	44.7	9.6	5.7	4.12	*	
E39						1,900	0.25	1.314	50.9	8.0	3.3			
E40						1,900	4.00	2.039	>50		2.2	0.85		

Notes: x = Average single extrude crush strength.

s = Standard deviation.

An "A" designation in the sorbent sample number indicates preparation of a larger batch for cyclic testing.

contained 2 percent bentonite and no organic additive. The sorbent was indurated for 2 hours at 1,550°F.

The following procedure was used in the preparation and initial testing of sorbent samples. Approximately 20 pounds of a particular formulation (stoichiometric ratio, Fe_2O_3 grade, and binder composition) was originally prepared. A particular 20-pound batch is designated by the run number in the second column of Tables II-1 and II-2. Each batch was then divided into subsamples, with each subsample indurated for different temperature and time combinations. The subsample designations appear in the first column of Tables II-1 and II-2.

Subsamples containing the A designation represent freshly prepared larger batches to be tested in the AMAX bench-scale reactor. For example, in Table II-1, Run Number 2 represents a 20-pound batch of spherical pellets prepared from ZnO and pigment-grade Fe_2O_3 in the 0.8:1.0 ratio and containing a 2 percent bentonite additive. This batch was divided into six subsamples (P1 through P6), each of which was indurated at different conditions. On the basis of preliminary testing, subsample P6 was chosen for bench scale testing. Sample P6A, therefore, represents a new batch prepared using the same formulation variables and indurated at conditions equivalent to those of subsample P6.

The preliminary measurements conducted by AMAX consisted of bulk density, crush strength, and attrition determinations. In addition, the BET surface area of selected subsamples was measured. For a complete description of these measurements, the reader is referred to the appropriate AMAX report (Jha, 1986). By examining the data in Tables II-1 and II-2, one may conclude that, in general, the bulk density and crush strength increase as the severity of the induration increases, while the attrition loss and surface area decrease with increasing induration severity. All of these trends are as expected.

Those samples designated with the asterisk in the last column of Tables II-1 and II-2 were selected for single particle kinetic testing at LSU.

CHAPTER III. EXPERIMENTAL APPARATUS, PROCEDURE, AND MATERIALS

ZINC FERRITE CHEMISTRY

In a fixed-bed desulfurization reactor, that portion of the sorbent away from the reactor inlet will initially be exposed to sulfur-free reducing gas. At the temperature and pressure of interest, this reducing gas may cause the zinc ferrite to break up into the component oxides, and Fe_2O_3 may be reduced to Fe_3O_4 according to the following stoichiometry:

Reduction may be caused by H_2 , as shown, or by CO , in which case CO_2 would be formed. At sufficiently high temperature and reducing gas concentration, the Fe_3O_4 may be further reduced to FeO (or even Fe) according to:

Although considerably more stable than iron oxide, ZnO may, at sufficiently high temperatures, be reduced to volatile metallic zinc.

In general, it is desirable that reduction reactions beyond Equation III-1 be minimized. Not only is valuable H_2 and CO consumed, it has been shown that FeO may be considerably less reactive (Focht et al., 1986), and zinc losses through vaporization must obviously be minimized. One apparent advantage associated with bentonite addition is a retardation of the reduction reactions (Focht et al., 1986). As will be shown, this earlier observation has been confirmed in this present study.

If reduction conditions are controlled so that Fe_3O_4 is the stable form of iron, then the sulfidation stoichiometry can be written:

At the conditions of interest, iron will form nonstoichiometric sulfur compounds which may be represented by the general formula FeS_x , where $1.0 \leq x \leq 1.2$ (Tamhankar et al., 1981). Therefore, it is possible to achieve sulfur loadings which exceed the stoichiometry specified by Equation III-3.

Regeneration is carried out in a nitrogen-oxygen-steam atmosphere, and the primary reaction is direct oxidation:

Steam in the regeneration gas also reacts slowly with the sulfided solid, according to:

In the normal regeneration atmosphere in the presence of both oxygen and steam, the Fe_3O_4 will be further oxidized to Fe_2O_3 .

At sufficiently low temperature and/or high oxygen concentration, there is a tendency to form ZnSO_4 , presumably via one or both of the following reactions:

Once formed, the ZnSO_4 can be decomposed by heating to a higher temperature in air or inert gas or by reacting it with reducing gas without increasing the temperature.

Since each of the reacting species is present under normal regeneration conditions, all of the reactions may occur simultaneously, thus making the regeneration chemistry significantly more complex than sulfidation chemistry.

SINGLE PELLET REACTOR

The noncatalytic reaction between a gas and solid results in a change in solid mass. In this situation, sulfidation produces an increase in mass, while reduction and regeneration result in a mass decrease. As a result, gravimetric methods may be used to monitor the progress of the reaction with time. A thermogravimetric analyzer, modified to serve as a single pellet reactor, was used to study reaction kinetics. A schematic diagram of the apparatus is shown in Figure III-1. Key elements are a Cahn Model 2000 electrobalance, a temperature controlled furnace, and a manifold system to control the feed rates and composition of the gaseous components.

Figure III-1. Electrobalance schematic.

The gas manifold system for the reduction and sulfidation phases is shown in Figure III-2. All components, except steam, were obtained from high purity gas cylinders with flows regulated by needle valves and calibrated rotameters. Inert gas entered the reactor via two paths. In the upper path, a small flow of inert gas passed over the balance to ensure that none of the corrosive gases reached the mechanism. Additional inert plus all reactive gases were mixed just downstream of the rotameters and entered the reactor through the sidearm of the hangdown tube. The combined gases passed over the sorbent pellet, exited from the bottom of the hangdown tube, and were vented through a laboratory hood.

Steam was added to the gases from a distilled water reservoir maintained under slightly elevated nitrogen pressure to induce flow. The flow rate of liquid water was monitored using a needle valve and rotameter. At the point where water

mixed with the reactive gases, the line was heated to induce vaporization. The reactive gas feed line was heat traced from the point that water was added until it entered the reaction furnace.

Figure III-2. Gas feed manifold.

The solid mass change which accompanies the reactions was monitored by a strip chart recorder. A typical response for the standard 1-1/2 cycle test is shown in Figure III-3. W/W_0 , the normalized solid weight, is plotted as a function of time.

Once the sorbent pellet was in place and the balance properly calibrated, the reactor temperature was adjusted and the system purged with an inert gas. No weight change occurred during this period. The reaction phase begins with a reduction step in which H_2S -free sulfidation gas is introduced. All tests were performed at atmospheric pressure. If reduction occurs, it is quite rapid. The weight loss in the Figure III-3 example corresponds to the complete reduction of Fe_2O_3 to Fe_3O_4 , according Equation III-1. This reduction step

Figure III-3. Typical TGA response for 1-1/2-cycle test

corresponds to a 2.2 percent weight loss or a final value of $W/W_0 = 0.978$.

At the conclusion of reduction, H_2S was introduced and the sulfidation phase, which is accompanied by a weight gain, was initiated. Complete sulfidation, according to Equation III-3, will result in a final value of $W/W_0 = 1.133$. Sulfidation was followed by a purge period in which the simulated coal gas was replaced by inert nitrogen and the reactor temperature was adjusted to the level desired for regeneration. Regeneration began with the introduction of oxygen and steam. The sorbent weight, W/W_0 , after complete regeneration should be 1.0, according to Equation III-4. At this point, one cycle has been completed and the sorbent is ready for the second reduction/sulfidation cycle to begin.

STANDARD REACTION CONDITIONS

The primary objective of this study was to compare reactivity and reactivity maintenance as a function of formulation conditions. Hence, all reaction tests were carried out using standard gas compositions and temperatures shown in Table III-1.

Table III-1. Standard Reaction Test Conditions

<u>Reduction and Sulfidation</u>		
Temperature, °C	550	
Gas Composition, Volume %		
	<u>Reduction</u>	<u>Sulfidation</u>
H_2	10.9	10.6
H_2O	26.0	25.3
CO	16.8	16.3
CO_2	4.6	4.5
N_2	41.7	40.6
H_2S	0.0	2.7
<u>Regeneration</u>		
Temperature, °C	700	
Gas Composition, Volume %		
O_2	4.0	
H_2O	30.0	
N_2	66.0	

The reduction and sulfidation compositions were chosen to simulate the product from a partially water-quenched, air-blown, fluidized-bed gasifier. H_2S concentration was artificially high in order to speed the progress of the reaction. The same gas composition, except for a lower H_2S content of 1.0 percent (volume), was used by AMAX in the bench-scale portion of this research project.

The steam concentration in the regeneration gas was lower than that used by AMAX in the bench-scale studies (30 versus 80 volume percent) because of the unique configuration of the electrobalance reactor. The need to blanket the electrobalance mechanism in an inert, noncondensing gas prevents operation at such high steam levels. However, the 4 percent (volume) oxygen was equal to that used by AMAX. Previous single pellet kinetic tests at LSU (Focht et al., 1986) have shown that steam concentrations above 30 percent (volume) have little effect on the global regeneration kinetics.

The sulfidation and regeneration temperatures of 1,022 and 1,292°F (550 and 700°C), respectively, are approximately equal to those expected in a fixed-bed reactor. However, the highly exothermic nature of the regeneration reaction makes isothermal operation in a fixed-bed reactor impossible, and the actual temperature would be expected to vary between approximately 1,202 and 1,382°F (650 and 750°C). The small electrobalance reactor will operate more nearly in an isothermal manner, although single pellet temperature modeling accompanied by crude experimental measurements (Focht, 1988) has shown that significant temperature gradients may be generated between the solid pellet and bulk gas. Because of this uncertainty in regeneration temperature, a number of nonstandard regeneration tests using 1,202 and 1,112°F (650 and 600°C) regeneration temperatures were also conducted. Results of these tests are described in a separate chapter of this report.

TEST SORBENTS

Thirty-six test sorbents and two reference sorbents were subjected to the standard 1-1/2-cycle test. A summary of the test sorbents, their formulation conditions, and selected physical property data is presented in Table III-2.

All sorbents were tested at least once at standard conditions. Two or more runs at identical conditions were made using selected test sorbents in order to determine the degree of reproducibility which might be expected. Also, in some cases, multiple tests were carried out when results from the first test were unexpected or otherwise questioned.

Each test required a new sorbent pellet. To the extent possible, pellets of equal size were chosen to permit direct

Table III-2. Sorbents Selected for Single Pellet Testing

Designation	Fe ₂ O ₃ Grade ^a	ZnO/ Fe ₂ O ₃	% Bentonite	% Organic ^b	Induration		Bulk Density, kg/l	Crush Strength, lb ^c		Attrition Loss, %	BET Surface Area, m ² /g
					Time, Hours	Temperature, °F		x	s		
Spherical Pellets											
1094-59 (Reference)	P	1.0	5	2	3.00	1,825	1.014	5.1	2.9	54.5	1.01
P-5	P	0.8	2	0	0.25	1,900	0.952	6.6	3.7	51.5	3.95
P-6	P	0.8	2	0	4.00	1,900	1.529	40.3	10.7	10.2	1.28
P-10	C	1.0	2	0	2.00	1,700	1.048	10.1	4.1	31.6	2.43
P-11	C	1.0	2	0	0.25	1,900	1.036	10.5	4.1	32.4	2.47
P-12	C	1.0	2	0	4.00	1,900	1.273	21.5	10.2	24.5	1.38
P-16	C	0.8	2	2	0.25	1,900	1.196	27.3	5.4	10.7	1.55
P-17	C	0.8	2	2	4.00	1,900	1.339	32.8	5.3	8.4	1.43
P-21	C	1.0	10	0	0.25	1,900	0.955	12.3	3.4	29.7	2.46
P-22	C	1.0	10	0	4.00	1,900	1.132	20.8	6.6	22.8	2.10
P-26	C	0.8	10	2	0.25	1,900	0.956	15.0	3.5	25.5	2.05
P-27	C	0.8	10	2	4.00	1,900	1.111	21.2	4.8	19.9	1.91
P-31	P	1.0	2	2	0.25	1,900	0.972	6.5	3.0		2.57
P-32A	P	1.0	2	2	4.00	1,900	1.276	20.5	6.4	25.1	0.77
P-37A	P	0.8	5	0	4.00	1,900	1.279	22.1	6.6	9.3	1.76
P-42A	P	1.0	5	2	4.00	1,900	1.240	17.0	3.0	20.9	1.07
P-47	C	1.0	5	0	4.00	1,900	1.234	17.7	4.1	22.0	1.40
P-52	C	0.8	5	2	4.00	1,900	1.142	22.3	6.8	25.5	1.63
P-57	P	0.8	10	0	4.00	1,900	1.275	45.3	8.5	15.1	1.67
P-62	P	1.0	10	2	4.00	1,900	0.947	12.2	4.4	49.2	1.64
Cylindrical Extrudes											
T-2465 (Reference)	C	1.0	2	0	2.00	1,550	1.306	30.2	6.3	11.2	3.30
E-1	C	0.8	2	0	0.25	1,500	1.199	29.4	7.0	9.8	5.12
E-2	C	0.8	2	0	4.00	1,500	1.120	42.5	8.5	7.7	4.39
E-7	P	1.0	2	0	4.00	1,500	1.154	26.0	6.1	18.2	5.77
E-7A	R	1.0	5	0	4.00	1,500	0.770	35.0			2.59
E-9	P	1.0	2	0	0.25	1,900	1.354	46.8	11.7	6.6	2.74
E-11	C	1.0	2	0.5	0.25	1,500	1.215	31.8	8.5	12.2	4.39
E-12	C	1.0	2	0.5	4.00	1,500	1.196	33.3	6.5	13.3	4.36
E-13	C	1.0	2	0.5	2.00	1,700	1.148	37.7	6.6	15.5	3.37
E-15	C	1.0	2	0.5	4.00	1,900	1.623	>50		6.8	1.42
E-16	C	0.8	5	0	0.25	1,500	1.269	>50		6.1	4.78
E-21	C	1.0	5	0.5	0.25	1,500	1.195	=50		9.9	4.62
E-24	C	1.0	5	0.5	0.25	1,900	1.300	>50		7.4	2.93
E-28A	P	0.8	5	0.5	2.00	1,700	1.115	29.7	7.3	10.7	4.99
E-31	P	0.8	2	0.5	0.25	1,500	1.168	26.1	9.7	13.9	6.31
E-32A	P	0.8	2	0.5	4.00	1,500	1.191	27.9	7.1	15.4	6.33
E-35	P	0.8	2	0.5	4.00	1,900	1.686	>50		2.9	1.42
E-36	P	1.0	5	0	0.25	1,500	1.092	39.8	12.0	6.9	5.76
E-38	P	1.0	5	0	2.00	1,700	1.174	44.7	9.6	5.7	4.12

^a C = catalyst grade, P = pigment grade, R = Ruthner grade.

^b Starch used for spherical pellets, methocel used for cylindrical extrudes.

^c x = average value, s = standard deviation.

comparison between sorbents. For cylindrical extrudes, both the length and diameter were matched, while spherical pellets having an equal diameter were chosen. By selecting equal volume pellets, the initial mass varied, depending on pellet porosity.

REACTIVITY AND REACTIVITY MAINTENANCE INDICES

Comparisons of the reactivity and reactivity maintenance of the different sorbent formulations are based upon indices which are defined by the following equations:

$$R(t) = \frac{W_s(t)}{W_o} \quad (\text{III-8})$$

$$RM(t) = \frac{\left[\frac{W(t) - W_{R2}}{W_{th} - W_{R2}} \right]_2}{\left[\frac{W(t) - W_{R1}}{W_{th} - W_{R1}} \right]_1} \quad (\text{III-9})$$

$R(t)$ is simply the mass of sulfur sorbed by the sorbent at a designated time divided by the initial mass of the pellet. $RM(t)$ compares the weight increase at a particular time during sulfidation Cycle 2 to the weight gain at the same time during sulfidation Cycle 1. The complexity of Equation III-9 is due to the fact that different levels of reduction are sometimes attained in the two cycles. In such cases, the direct comparison of pellet weight in the two cycles may skew the result.

Selection of the appropriate time upon which to base the reactivity and reactivity maintenance calculations is an important consideration. As shown in Figure III-3, the sulfidation rate is typically quite fast initially and asymptotically approaches zero as the sorbent approaches complete sulfidation. Therefore, if the comparison time is too short, the rapid initial rate may cause substantial error in the index values. On the other hand, if the comparison time is too long, all sorbents will approach complete sulfidation. The reactivity index will only reflect sorbent capacity and the reactivity maintenance index will always approach 1.0, assuming that complete sulfidation in both cycles is possible. Therefore, the appropriate time for index calculations should be in the intermediate range, long enough to escape the uncertainty associated with the rapid initial reaction rate and short enough that the reaction does not approach completion.

For extrudes, the reference time has been chosen to be 30 minutes, and for pellets, the reference time is 20 minutes. At these reference times, the fractional sulfidation of typical pellets and extrudes is in the range of 0.4 to 0.7.

CHAPTER IV. RESULTS OF SPHERICAL PELLET TESTS

INTRODUCTION

Twenty-nine tests consisting of 1-1/2 cycles using standard gas compositions and temperatures were carried out using reference sorbent 1094-59 and 19 test sorbents. A summary of these tests is presented in Table IV-1. Six additional tests, marked with footnote a in the run number column, were carried out using a nonstandard regeneration temperature. Results of these runs are included in the reactivity analysis, since the first sulfidation cycle was carried out at standard conditions. Reactivity maintenance results for the nonstandard regeneration conditions are discussed separately.

To the extent possible, pellets were chosen to be of equal size, i.e., equal diameter. The mean $\pm$ standard deviation of the 35 entries from Table IV-1 is 0.554 ± 0.012 cm. Only 4 of the 35 lie outside the above range, the three pellets of sorbent P-6 and one of the P-21 pellets. In each case, the pellet diameter was below the 0.542 cm value. The selection of equal volume pellets permitted the pellet density to vary, depending upon formulation conditions, primarily induration time and temperature. Individual pellet densities varied from 1.66 g/cm^3 (P-5) to 2.42 g/cm^3 (P-6). In all cases, those pellets with densities equal to or greater than 2.0 were indurated at $1,900^\circ\text{F}$.

Surface area values were determined by AMAX and are based on a representative sample of each test sorbent. Therefore, surface area values do not vary from pellet to pellet. The porosity of individual pellets was calculated from the equation:

$$\epsilon = 1 - \frac{\rho_p}{\rho_{Th}} \quad (\text{IV-1})$$

Individual pellet densities were calculated from the mass and diameter in Table IV-1, and the theoretical density was calculated using a weighted average composition of the pellet, along with handbook densities of each of the components:

$$\frac{1}{\rho_{Th}} = \frac{1}{W_o} \sum_i \frac{W_i}{\rho_{Thi}} \quad (\text{IV-2})$$

Table IV-1. Summary of Spherical Pellet Test Conditions

<u>Sorbents</u>	<u>Run No.</u>	<u>Initial Sorbent Properties</u>				
		<u>Diameter, cm</u>	<u>Mass, mg</u>	<u>Pellet Density, g/cm³</u>	<u>Surface Area, m²/g</u>	<u>Calculated Porosity</u>
1094-59 (Reference)	12	0.560	165.0	1.79	1.01	0.64
	75 ^a	0.556	162.0	1.80		0.64
	82	0.558	161.0	1.77		0.65
	83	0.559	162.0	1.77		0.65
	88	0.556	162.6	1.81		0.64
P-5	18	0.575	165.5	1.66	3.95	0.68
P-6	45 ^a	0.519 ^b	177.0	2.42	1.28	0.53
	57	0.534 ^b	178.5	2.24		0.57
	93	0.538 ^b	181.5	2.23		0.57
P-10	34	0.548	156.5	1.82	2.43	0.65
P-11	19	0.557	162.5	1.80	2.47	0.66
	76	0.552	161.0	1.83		0.65
P-12	84	0.555	192.0	2.14	1.38	0.59
P-16	67	0.566	210.5	2.22	1.55	0.57
P-17	68	0.561	221.5	2.40	1.43	0.54
	95	0.559	215.0	2.35		0.55
P-21	33	0.511 ^b	121.0	1.73	2.46	0.63
	50 ^a	0.560	162.0	1.76		0.63
	58	0.560	164.7	1.79		0.62
	70	0.558	164.0	1.80		0.62
	89 ^a	0.559	163.3	1.79		0.62
P-22	96	0.557	174.8	1.93	2.10	0.59
P-26	98	0.557	154.5	1.71	2.05	0.64
P-27	51 ^a	0.559	166.0	1.81	1.91	0.61
	59	0.557	165.0	1.82		0.61
	87 ^a	0.555	165.5	1.85		0.61
P-31	97	0.554	166.5	1.87	2.57	0.64
P-32A	72	0.557	198.5	2.19	0.77	0.58
P-37A	71	0.553	206.0	2.33	1.76	0.54
	94	0.553	197.0	2.22		0.56
P-42A	69	0.555	185.0	2.07	1.07	0.59
P-47	100	0.557	203.5	2.25	1.40	0.55
P-52	101	0.557	181.0	2.00	1.63	0.60
P-57	99	0.557	202.5	2.24	1.67	0.53
P-62	102	0.555	157.0	1.75	1.64	0.63

^a Regeneration conducted at nonstandard temperature.

^b Pellet diameter outside the range of 0.554 ± 0.012 cm (mean $\pm$ standard deviation).

REPRODUCIBILITY

Before reactivity and reactivity maintenance results from different sorbent formulations can be compared, it is necessary to know the degree of reproducibility which may be expected from multiple tests at the same temperature and gas composition using different pellets from the same sorbent sample. As shown in the Table IV-1 summary, reference sorbent 1094-59 and test sorbent P-21 were both tested in five separate runs. The following discussion examines the reproducibility of these results.

Four of the five tests using the 1094-59 reference sorbent were carried out at standard conditions, while the fifth test (Run 75) used a lower regeneration temperature. First cycle sulfidation results should, however, be equivalent in each of the five tests. Detailed numerical results in the form of dimensionless pellet weight, W/W_0 , at selected reaction times are summarized in Table IV-2.

No weight loss was observed in any of the five first cycle reduction tests. This is counter to previous results from $ZnFe_2O_4$ pellets containing no bentonite binder (Focht, et al., 1986). In the previous study, a reduction temperature of $550^\circ C$ was sufficient to reduce Fe_2O_3 to Fe_3O_4 . Greater sorbent stability during the reduction step was observed throughout this work and is attributed to the presence of bentonite.

Comparison of W/W_0 values during the first sulfidation cycle indicates that the global kinetics of Run 12 was slightly faster and that runs 75, 82, 83, and 88 exhibited almost equal kinetics. For example, after 20 minutes sulfidation time, the sorbent weight gain for the five runs averaged 7.3 percent and ranged from a high of 7.9 percent (Run 12) to a low of 6.8 percent (Run 82). Near the end of the first sulfidation cycle (at 90 minutes), the total weight gain ranged from 11.5 percent (Run 75) to 11.9 percent (Run 83). Complete sulfidation was not achieved in any of the tests. With 5 percent inert bentonite, complete sulfidation of 1094-59 according to Equation III-3 would correspond to a final value of $W/W_0 = 1.127$.

Regeneration test results are also quite reproducible. After 20 minutes, the values of W/W_0 range from 1.032 (Run 83) to 1.035 (Run 85). Complete regeneration corresponding to $W/W_0 = 1.000$ was achieved only in Run 12. The small amount of "excess" weight at the end of the other regeneration runs may reflect small amounts of unregenerated sulfide, the formation of trace amounts of sulfate, or simply slight changes in electrobalance calibration during the approximately 6 hours required to complete one sulfidation/regeneration cycle.

Table IV-2. Reproducibility Comparisons
for Base Sorbent 1094-59

	Run				
	12	75	82	83	88
W ₀ , mg	165.0	162.0	161.0	162.0	162.6
Diameter, cm	0.560	0.556	0.558	0.559	0.556
	W/W ₀				
Time, Minutes					
Reduction					
0 (Start)	1.000	1.000	1.000	1.000	1.000
10	1.000	1.000	1.000	1.000	1.000
20	1.000	1.000	1.000	1.000	1.000
30	1.000	1.000	1.000	1.000	1.000
Sulfidation					
0 (Start)	1.000	1.000	1.000	1.000	1.000
10	1.052	1.044	1.043	1.047	1.046
20	1.079	1.071	1.068	1.072	1.073
30	1.094	1.086	1.084	1.088	1.089
40	1.105	1.097	1.096	1.099	1.098
50	1.109	1.104	1.103	1.105	1.105
70	1.115	1.111	1.112	1.114	1.111
90	1.118	1.115	1.118	1.119	1.116
110	1.119	--	1.120	1.120	1.117
Regeneration					
0 (Start)	1.113	--	1.118	1.117	1.116
10	1.061	--	1.056	1.056	1.061
20	1.033	--	1.034	1.032	1.035
30	1.018	--	1.021	1.019	1.020
40	1.009	--	1.012	1.015	1.010
60	1.000	--	1.003	1.004	1.004
80	--	--	1.003	1.004	1.002
Second Reduction					
0 (Start)	0.997	--	1.001	1.003	0.999
10	0.995	--	1.000	1.000	0.996
20	0.994	--	1.000	1.000	0.996
30	0.994	--	1.000	1.000	0.996
Second Sulfidation					
0 (Start)	0.994	--	1.000	1.000	0.996
10	1.046	--	1.056	1.052	1.052
20	1.071	--	1.079	1.077	1.076
30	1.085	--	1.093	1.093	1.092
40	1.097	--	1.104	1.102	1.101
50	1.103	--	1.111	1.108	1.107
70	1.112	--	1.118	1.117	1.114
90	1.115	--	1.122	1.121	1.117
110	--	--	1.124	1.123	1.119
Reactivity Index, R(20)	0.235	0.212	0.204	0.214	0.219
Reactivity Maintenance Index, RM(20)	0.96	--	1.14	1.05	1.07

The second reduction and sulfidation cycles were normally conducted on the second day. Overnight, the pellet was left in the balance at room temperature under nitrogen. Slight additional weight loss which was observed from the end of the regeneration cycle to the beginning of the second reduction cycle may be attributed to balance drift or aero-dynamic drag differences associated with temperature and gas composition.

Very small weight loss amounting to $0.001 \leq \Delta(W/W_0) \leq 0.003$ was observed during the second reduction. Once again, it is only possible to speculate on the cause. Any sulfur remaining after oxidative regeneration may be removed in the reducing gas. Alternately, it may be possible during the second cycle to reduce a small fraction of Fe_2O_3 to Fe_3O_4 .

W/W_0 values during the second sulfidation cycle are comparable to those observed in the first cycle. For example, after 20 minutes, the average value of W/W_0 (4 runs) was 1.076, compared to 1.073 for the five first cycle runs. The second cycle values are somewhat skewed to the low side because of the low initial values of W/W_0 in runs 12 and 88.

Calculated values of the reactivity and reactivity maintenance indices for each run at 20 minutes are presented at the end of Table IV-2. The five values of $R(20)$ vary between 0.204 and 0.235, with an average of 0.217. Only four values of the $RM(20)$ index may be compared, since the regeneration temperature in Run 75 was $1,112^\circ\text{F}$ (600°C). The four values of $RM(20)$ vary between 0.96 and 1.14, with an average of 1.06. Sorbent 1094-59 is a particularly stable sorbent. As will be seen, $RM(20)$ for most test sorbents is less than 1.0.

Similarly, detailed results for five runs using the P-21 test sorbent are summarized in Table IV-3. Sulfidation conditions were the same in all runs, but lower regeneration temperatures were used in runs 59 and 89. Consequently, regeneration results and reactivity maintenance values are not reported for these runs. It is also significant to note that the pellet used for Run 33 was considerably smaller than the remaining pellets. Small pellets lead to abnormally high values of $R(20)$ but should have no effect on $RM(20)$.

Slight weight loss was noted in each run during the first reduction period. This is in contrast to the previous results for base sorbent 1094-59. The stabilizing effect of bentonite is again evident, however, because all weight losses are considerably less than associated with the reduction of Fe_2O_3 to Fe_3O_4 .

With the exception of Run 33 using the small pellet, the sulfidation W/W_0 versus time results are quite reproducible. P-21 pellets react faster than 1094-59 and attain larger final

Table IV-3. Reproducibility Comparisons
for Test Sorbent P-21

	33	50	Run 58	70	89
W ₀ , mg	121.0	162.0	164.7	164.0	163.3
Diameter, cm	0.511	0.560	0.560	0.558	0.559
	<hr/> W/W ₀ <hr/>				
Time, Minutes					
Reduction					
0 (Start)	1.000	1.000	1.000	1.000	1.000
10	0.996	0.998	0.998	0.997	0.998
20	0.994	0.997	0.994	0.994	0.996
30	0.993	0.995	0.992	0.994	0.996
Sulfidation					
0 (Start)	0.993	0.995	0.992	0.994	0.996
10	1.074	1.066	1.069	1.067	1.066
20	1.103	1.093	1.096	1.095	1.093
30	1.116	1.108	1.111	1.110	1.107
40	1.124	1.117	1.121	1.119	1.118
50	1.126	1.125	1.125	1.125	1.124
70	1.129	1.130	1.132	1.131	1.130
Regeneration					
0 (Start)	1.126	--	1.126	1.128	--
10	1.066	--	1.063	1.065	--
20	1.037	--	1.038	1.040	--
30	1.022	--	1.023	1.026	--
40	1.012	--	1.014	1.015	--
60	1.004	--	1.004	1.006	--
80	1.004	--	--	1.003	--
Second Reduction					
0 (Start)	1.002	--	1.001	1.000	--
10	0.996	--	0.996	0.994	--
20	0.993	--	0.993	0.992	--
30	0.992	--	0.991	0.991	--
Second Sulfidation					
0 (Start)	0.992	--	0.991	0.991	--
10	1.064	--	1.056	1.055	--
20	1.091	--	1.084	1.082	--
30	1.107	--	1.098	1.098	--
40	1.120	--	1.108	1.108	--
50	1.124	--	1.115	1.116	--
70	1.128	--	1.123	1.124	--
90	1.130	--	--	--	--
110	--	--	--	--	--
Reactivity Index, R(20)	0.312	0.280	0.291	0.286	0.281
Reactivity Maintenance Index, RM(20)	0.87	--	0.88	0.88	--

values of W/W_0 . With 10 percent bentonite in P-21, the maximum value of W/W_0 according to stoichiometric Equation III-3 should be 1.120. This value is exceeded in all five runs. Similar "excess" sulfur loadings have been observed in other studies (Tamhankar et al., 1981; Focht et al., 1986) and have been attributed to the formation of nonstoichiometric iron sulfide, FeS_x , with $x > 1.0$.

Regeneration results for the three runs using the standard regeneration temperature are reasonable and reproducible. The final values of W/W_0 in each case are slightly above 1.000, perhaps indicating slight amounts of residual sulfide, trace amounts of zinc sulfate, or electrobalance drift.

Weight loss was again noted during the second reduction cycle, but final W/W_0 values were again above those corresponding to Fe_2O_3 reduction to Fe_3O_4 . Second cycle sulfidation results for the three runs are again quite reproducible, but the rate is noticeably slower in the second cycle. Final sulfidation weights are also slightly lower but again indicate "excess" sulfur.

Neglecting results from the small pellet (Run 33), the average value of $R(20)$ is 0.284, with a range from 0.280 to 0.291. This average is considerably higher than the 1094-59 average value of $R(20) = 0.217$. Reactivity maintenance values are also reproducible but lower than observed for 1094-59. The average value of $RM(20) = 0.88$ compared to $RM(20) = 1.06$ for the base sorbent.

REACTIVITY AND REACTIVITY MAINTENANCE RESULTS

Values of $R(20)$ and $RM(20)$ from all individual runs, along with average values for each sorbent, are reported in Table IV-4. Those runs marked by footnote a used a nonstandard regeneration temperature and $RM(20)$ values are omitted. As previously discussed, the pellet used in Run 33 (sorbent P-21) was smaller than normal. The larger than normal value of $R(20)$ associated with this run was omitted in determining the P-21 average. Finally, the value of $R(20)$ for Run 45 using sorbent P-6 is much smaller than the $R(20)$ values for the other P-6 sorbent runs. The Run 45 value was omitted in calculating the average value of $R(20)$ for sorbent P-6.

Average $R(20)$ values range from a low of 0.178 for sorbent P-37A to a high of 0.297 for sorbent P-10. $RM(20)$ values range from a low of 0.73 for sorbent P-37A to a high of 1.06 for base sorbent 1094-59. The base sorbent is the only one which does not exhibit decreased second cycle reactivity [$RM(20) < 1.0$]. It is interesting to note that sorbent P-37A exhibits the lowest values of both indices. This is counter to intuition since a high $R(20)$ value might be expected to produce a low $RM(20)$ value, and vice versa.

Table IV-4. Summary of R(20) and RM(20)
Results for Spherical Test Sorbents

<u>Sorbent</u>	<u>Run No.</u>	<u>R(20)</u>	<u>Average</u>	<u>RM(20)</u>	<u>Average</u>
1059-59 (Reference)	12	0.235		0.96	
	75 ^a	0.212		--	
	82	0.204		1.14	
	83	0.214		1.05	
	88	0.219	0.217	1.07	1.06
P-5	18	0.290	0.290	0.79	0.79
P-6	45 ^a	0.147 ^b		--	
	57	0.217		0.88	
	93	0.200	0.208	0.92	0.90
P-10	34	0.297	0.297	0.84	
P-11	19	0.293		0.87	
	76	0.271	0.282	0.82	0.84
P-12	84	0.257	0.257	0.82	0.82
P-16	67	0.206	0.206	0.83	0.83
P-17	68	0.188		0.79	
	95	0.206	0.197	0.77	0.78
P-21	33	0.312 ^b		0.85	
	50 ^a	0.280		--	
	58	0.291		0.88	
	70	0.286		0.88	
	89 ^a	0.281	0.285	--	0.88
P-22	96	0.253	0.253	0.89	0.89
P-26	98	0.289	0.289	0.90	0.90
P-27	51 ^a	0.259		--	
	59	0.279		0.88	
	87 ^a	0.232	0.256	--	0.88
P-31	97	0.275	0.275	0.90	0.90
P-32A	72	0.203	0.203	0.82	0.82
P-37A	71	0.158		0.73	
	94	0.199	0.178	0.73	0.73
P-42A	69	0.194	0.194	0.88	0.88
P-47	100	0.222	0.222	0.83	0.83
P-52	101	0.278	0.278	0.91	0.91
P-57	99	0.190	0.190	0.81	0.81
P-62	102	0.241	0.241	0.99	0.99

^a Nonstandard regeneration conditions.

^b Individual values omitted in calculated averages.

Complete W/W_0 versus time results are presented in Figure IV-1 for runs 34 (sorbent P-10) and 71 (sorbent P-37A). These individual runs exhibited maximum and minimum reactivities for the 34 individual tests. Results from each of the other tests would lie between these two curves. Sorbent P-10 was formulated from catalyst-grade iron oxide using a ZnO-to- Fe_2O_3 ratio of 1.0 to 1.0 and contained 2 percent bentonite and no organic binder. Induration conditions were 1,700°F for 2 hours. In contrast, sorbent P-37A contained pigment-grade iron oxide with a 0.8 to 1.0 ZnO-to- Fe_2O_3 ratio, 5 percent bentonite, and no organic binder. Induration conditions were at 1,900°F for 4 hours. While each of the formulation variables were different for the two sorbents, further analysis indicated that the different induration conditions were the most important factors in the reactivity difference.

The theoretical maximum values of $W/W_0 = 1.131$ (based upon 2 percent bentonite) for sorbent P-10 and $W/W_0 = 1.127$ (based upon 5 percent bentonite) for sorbent P-37A are shown on the figure. This maximum was reached in 55 minutes for sorbent P-10, but sulfidation was incomplete after 140 minutes using sorbent P-37A.

Figure IV-2 compares first and second cycle sulfidation results for runs 82 (base sorbent 1094-59) and 71 (sorbent P-37A). These two runs exhibited the highest and lowest values of $RM(20)$. The second cycle reactivity of 1094-59 actually increased, as seen in Figure IV-2 and as evidenced by the value of $RM(20) > 1.0$. In contrast, the second cycle reactivity for P-37A decreased significantly. Both sorbents contained 5 percent bentonite, leading to a theoretical maximum value of $W/W_0 = 1.127$, as indicated on the figure. Neither of the runs achieved complete sulfidation in either cycle, but the second cycle of Run 82 approached it closely.

Sorbents 1094-59 and P-37A have several formulation parameters in common. Both contain pigment-grade Fe_2O_3 and 5 percent bentonite. Sorbent 1094-59 also contained 0.2 percent Na_2CO_3 , 0.2 percent MoS_2 , and 1.5 percent kaolin. However, 1094-59 contains a 1.0-to-1.0 ratio of ZnO to Fe_2O_3 and originally contained a 2 percent organic binder, while P-37A contained excess Fe_2O_3 and no organic. Induration conditions were also different in that P-37A was indurated at 1,900°F for 4 hours, while 1094-59 was subjected to milder induration conditions of 1,825°F for 3 hours.

REACTIVITY ANALYSIS

In this section, pellet reactivity results in terms of the $R(20)$ index will be analyzed as a function of sorbent formulation variables and structural parameters in order to determine those characteristics needed to produce a highly reactive pellet. All of the pertinent data are summarized in

Figure IV-1. Time-conversion results for pellets exhibiting maximum and minimum reactivity.

Figure IV-2. Comparison of first and second cycle sulfidation results for pellets exhibiting maximum and minimum reactivity maintenance.

Table IV-5, with the sorbents arranged in order of decreasing reactivity. The sorbents are divided into three groups representing high, medium, and low reactivity. The dividing lines were based upon perceived gaps in the reactivity data. For example, there is a difference in RM(20) values of 0.018 between P-31, the last member of the high reactivity group, and P-12, the top member of the intermediate reactivity group. Differences within a group are smaller than the difference between groups.

The following evaluation is based upon two types of analysis. The first, referred to as an overall analysis, examines the reactivity rankings of Table IV-5 to determine which parameters consistently produce high reactivity pellets. The second analysis identifies sorbent subgroups in which only a single formulation parameter is varied. Reactivity rankings for this subgroup are then compared.

ZnO:Fe₂O₃ Ratio

The overall analysis shows no correlation between reactivity and the relative quantities of zinc and iron in the sorbent. Four of seven (57 percent) sorbents in the high reactivity category contain stoichiometric equivalents of ZnO and Fe₂O₃. Four of nine (44 percent) sorbents in the low reactivity group also contain stoichiometric equivalents. Neither of these percentages is significant, considering that 11 of 20 (55 percent) of the test sorbents were formulated with equal molar quantities of ZnO and Fe₂O₃.

No direct comparisons in which all formulation variables except the ZnO:Fe₂O₃ ratio are held constant are possible. However, nine 1-to-1 comparisons can be made if the effect of starch content is ignored. Arguments will be presented in a subsequent section leading to the conclusion that starch content, indeed, has no effect on pellet reactivity. For example, pellets P-5 and P-31 were both formulated using pigment-grade iron oxide, both contained 2 percent bentonite, and both were indurated at 1,900°F for 0.25 hour. P-5 contained 0.8 ZnO to 1.0 Fe₂O₃, while P-31 contained 1.0 ZnO to 1.0 Fe₂O₃. Both sorbents are in the high reactivity category. All sorbent pairs and the results of the direct comparisons are presented below.

In five of the nine cases, both members are in the same reactivity group. In three instances, the sorbent containing 1.0 ZnO:1.0 Fe₂O₃ is in a higher reactivity group, and in one case, the 0.8 ZnO:1.0 Fe₂O₃ sorbent is in the higher activity group. In conclusion, neither the overall nor direct comparison methods show any firm correlation between pellet reactivity and zinc-to-iron ratio.

Table IV-5. Comparison of Pellet Reactivity

<u>Sorbent</u>	<u>R(20)</u>	<u>ZnO:Fe₂O₃ Ratio</u>	<u>Fe₂O₃ Grade</u>	<u>% Bentonite</u>	<u>% Starch</u>	<u>Induration</u>		<u>Surface Area, m²/g</u>	<u>Pellet Porosity</u>
						<u>Temperature, Of</u>	<u>Time, Hours</u>		
P-10	0.297	1.0	C	2	0	1,700	2.00	2.43	0.65
P-5	0.290	0.8	P	2	0	1,900	0.25	3.95	0.68
P-26	0.289	0.8	C	10	2	1,900	0.25	2.05	0.64
P-21	0.285	1.0	C	10	0	1,900	0.25	2.46	0.62
P-11	0.282	1.0	C	2	0	1,900	0.25	2.63	0.66
P-52	0.278	0.8	C	5	2	1,900	4.00	1.63	0.60
P-31	0.275	1.0	P	2	2	1,900	0.25	2.57	0.64
P-12	0.257	1.0	C	2	0	1,900	4.00	1.38	0.59
P-27	0.257	0.8	C	10	2	1,900	4.00	1.91	0.61
P-22	0.253	1.0	C	10	0	1,900	4.00	2.10	0.59
P-62	0.241	1.0	P	10	2	1,900	4.00	1.64	0.63
P-47	0.222	1.0	C	5	0	1,900	4.00	1.40	0.55
1094-59	0.217	1.0	P	5	2	1,825	3.00	1.01	0.64
P-6	0.208	0.8	P	2	0	1,900	4.00	1.28	0.57
P-16	0.206	0.8	C	2	2	1,900	0.25	1.55	0.57
P-32A	0.203	1.0	P	2	2	1,900	4.00	0.77	0.58
P-17	0.197	0.8	C	2	2	1,900	4.00	1.43	0.54
P-42A	0.194	1.0	P	5	2	1,900	4.00	1.07	0.59
P-57	0.190	0.8	P	10	0	1,900	4.00	1.67	0.53
P-37A	0.179	0.8	P	5	0	1,900	4.00	1.76	0.55

	0.8 ZnO: 1.0 Fe ₂ O ₃	Reactivity Group	1.0 ZnO: 1.0 Fe ₂ O ₃	Reactivity Group
1.	P-5	High	P-31	High
2.	P-6	Low	P-32A	Low
3.	P-16	Low	P-11	High
4.	P-17	Low	P-12	Medium
5.	P-26	High	P-21	High
6.	P-27	Medium	P-22	Medium
7.	P-37A	Low	P-42A	Low
8.	P-52	High	P-47	Low
9.	P-57	Low	P-62	Medium

Fe₂O₃ Grade

The overall analysis suggests that catalyst-grade Fe₂O₃ produces more reactive pellets. Eleven of twenty (55 percent) sorbents contained catalyst-grade Fe₂O₃. Five of seven sorbents (71 percent) in the high reactivity group and only three of nine (33 percent) of the low reactivity group were formulated from the catalyst-grade raw material. Although not overwhelming, the percentage spreads do appear to be significant.

It is also necessary to accept the premise that starch content is unimportant if one-to-one comparisons of Fe₂O₃ grade are to be made. With this premise, eight direct comparisons are possible, and results are summarized below.

	Catalyst Fe ₂ O ₃	Reactivity Group	Pigment Fe ₂ O ₃	Reactivity Group
1.	P-16	Low	P-5	High
2.	P-17	Low	P-6	Low
3.	P-11	High	P-31	High
4.	P-12	Medium	P-32A	Low
5.	P-22	Medium	P-62	Medium
6.	P-27	Medium	P-57	Low
7.	P-52	High	P-37A	Low
8.	P-47	Low	P-42A	Low

The catalyst-grade oxide is in a higher reactivity group in three cases, in a lower reactivity group in one case, and the reactivity groups are equal in four cases. In conclusion, both the overall and direct comparison methods suggest that catalyst-grade Fe₂O₃ produces pellets having higher reactivity. However, the effect is small and other parameters may be more important.

Inorganic Binder

Three levels of bentonite addition to the zinc ferrite were tested, 2, 5, and 10 weight percent. This inorganic "glue" is believed to impart additional strength to the pellets, making them more resistant to crushing as well as to failure caused by temperature cycling and variations in chemical composition.

Results previously discussed have shown that bentonite stabilizes the zinc ferrite when exposed to the sulfur-free reducing gas. Eliminating or minimizing the reduction step should, therefore, reduce pellet stresses associated with variation in chemical composition. Elimination of the reduction step will also have process advantages in that H₂ and/or CO consumed by reduction will be conserved. However, even the minimum additions of bentonite (2 percent) were sufficient to achieve stabilization.

The overall results of bentonite addition on R(20) values are somewhat mixed. Nine of the test sorbents contained 2 percent bentonite. Four of these emerged in the high reactivity category of Table IV-5, one in the intermediate reactivity group, and four were in the low reactivity group. Six test sorbents contained 10 percent bentonite. Of this group, two are classified high reactivity, three are intermediate, and one is low reactivity. Of the five sorbents containing 5 percent bentonite, one is in the high reactivity group and the other four are in the low reactivity group.

A number of one-on-one comparisons of the effect of bentonite on R(20) values is possible. In the following summary, all formulation parameters (including starch content), except bentonite content, are constant:

Bentonite Comparison						
2%			5%		10%	
Sorbent	Reactivity Group		Sorbent	Reactivity Group	Sorbent	Reactivity Group
1. P-6	Low		P-37A	Low	P-57	Low
2. P-11	High		--	--	P-21	High
3. P-12	Medium		P-47	Low	P-22	Medium
4. P-16	Low		--	--	P-26	High
5. P-17	High		P-52	High	P-27	Medium
6. P-32A	Low		P-42A	Low	P-62	Medium

Once again, no fixed pattern emerges. Therefore, the stabilizing effect of bentonite relative to reduction is clear, but there is no effect on pellet reactivity.

Organic Binder

The organic binder (starch) burns away during induration, thereby helping to create the surface area and porosity necessary for rapid reaction. Only two levels of starch content, 0 and 2 percent, were tested and the reactivity results fail to show any effect.

Fifty percent of the pellets (ten) contained 2 percent starch, while the remainder contained no starch. Three of seven (42 percent) of the high reactivity pellets, two of four (50 percent) of the intermediate reactivity, and five of nine (56 percent) of the low reactivity pellets contained 2 percent bentonite. No one-on-one comparisons which isolate the starch content as the single variable are possible. We have concluded that the two starch levels produce no noticeable effect on reactivity, and as discussed, some of the previous analysis is based upon this conclusion.

Induration Conditions

The effect of induration conditions is somewhat complicated because of the two induration variables, temperature and time. Nevertheless, Table IV-5 indicates that high reactivity correlates with milder induration conditions. All but two of the twenty test sorbents were indurated at 1,900°F. Sorbent P-10, the only test sorbent indurated at the lowest temperature of 1,700°F, exhibited the single highest reactivity index. However, reference sorbent 1094-59, indurated at 1,825°F, fell into the low reactivity group.

The remaining 18 sorbents were indurated at 1,900°F for either 0.25 or 4 hours. In these cases, time becomes the sole measure of induration severity. Six of the eighteen (33 percent) were indurated for 0.25 hour. All but one of these sorbents emerged in the high reactivity category. Conversely, only one of the sorbents indurated for 4 hours was in the high reactivity group. Likewise, only one of the sorbents indurated for 0.25 hour emerged in the low reactivity group.

Several one-on-one comparisons in which all formulation variables, except induration time, are constant are summarized below:

<u>Induration Temperature/Time Comparison</u>				
<u>1,900°F/0.25 Hour</u>			<u>1,900°F/4.00 Hours</u>	
<u>Sorbent</u>	<u>Reactivity</u>		<u>Sorbent</u>	<u>Reactivity</u>
	<u>Group</u>			<u>Group</u>
1. P-5	High		P-6	Low
2. P-11	High		P-12	Medium
3. P-16	Low		P-17	Low
4. P-21	High		P-22	Medium
5. P-26	High		P-27	Medium
6. P-31	High		P-32A	Low

In five of the six cases, lower severity induration (shorter time) produces a pellet having higher reactivity. In the sixth case, the reactivity grouping of the two pellets is equal. In addition, sorbent P-10, which was indurated at 1,700°F for 2 hours, is otherwise the same as sorbents P-11 (1,900°F, 0.25 hour) and P-12 (1,900°F, 4 hours). P-10 was in the high reactivity group and, in fact, exhibited the highest R(20) value of all pellets tested. It seems clear that induration at 1,900°F for 4 hours has an adverse effect on pellet reactivity. Lower temperature induration also appears desirable, but the data are insufficient to permit a definite conclusion.

Summary of the Effect Sorbent Formulation Parameters

Induration severity appears to be the most important of the five formulation variables in determining first-cycle pellet reactivity. With only one exception, the seven sorbents in the high reactivity category were indurated at moderate conditions. Similarly, eleven of the thirteen test sorbents in the intermediate and low reactivity groups were indurated under the most severe conditions.

The grade of Fe_2O_3 used in pellet formulation also appears to be important but much less so than induration conditions. Catalyst-grade Fe_2O_3 produces pellets having higher R(20) values than can be attained from pigment-grade Fe_2O_3 . The other formulation variables ($\text{ZnO}:\text{Fe}_2\text{O}_3$ ratio, bentonite content, and starch content) appear to have no impact on reactivity. Any effect which might exist is masked by the more important effects of induration conditions and Fe_2O_3 grade.

Structural Properties

Sorbent structural properties, which are to a large extent determined by formulation conditions, also affect sorbent reactivity. If the global reaction rate is controlled by the intrinsic surface reaction, surface area should be the key structural parameter. Examination of Table IV-5 data confirms that surface area is, in a general sense, important. Six of the seven high reactivity sorbents have surface areas exceeding 2.0 m²/g, while twelve of the thirteen sorbents in the intermediate and low reactivity groups have surface areas below 2.0 m²/g. The R(20) index is plotted as a function of surface area in Figure IV-3. The straight line shown was determined by least squares fit of the data. However, the correlation is poor and examination of this figure fails to show any specific relation between reactivity and surface area, except for the general requirement for the surface area to exceed about 2.0 m²/g. Indeed, the R(20) values of sorbents in the low reactivity group appear to decrease with increasing surface area.

Figure IV-3. The effect of surface area on pellet R(20).

The surface area observations are consistent with previous studies (Focht et al., 1986) which suggest that the global sulfidation rate is controlled by the transport resistances, principally diffusion through the product layer. When pore diffusion controls, pellet porosity would be expected to be a more important structural parameter than surface area. Indeed, all seven of the sorbents in the high reactivity category have porosities equal to or greater than 0.6, and eleven of the thirteen sorbents in the intermediate and low reactivity categories have porosities below this value. One of the exceptions is reference sorbent 1094-59, which has a high porosity of 0.64 but is in the low reactivity group. It should also be noted that the surface area of 1094-59 is only 1.01 m²/g, well below the value of 2.0 m²/g needed for high reactivity.

Figure IV-4 shows that a rough correlation exists between R(20) and pellet porosity. Although there is considerable scatter in the data, there is an unmistakable trend toward higher reactivity with increasing porosity. The straight line in this figure was also determined by least squares fit of the

data, and the correlation coefficient for this line is somewhat higher than that of the straight line in Figure IV-3.

Figure IV-4. The effect of porosity on pellet R(20).

REACTIVITY MAINTENANCE ANALYSIS

In many respects, the ability of a sorbent to maintain its reactivity through numerous sulfidation and regeneration cycles is a more important property than initial reactivity. The 1-1/2-cycle tests conducted in this study provide only the first clues of the long-term behavior of the sorbent. More detailed studies involving numerous complete cycles under conditions more closely approximating those in a commercial reactor will be required. Such tests, however, are both expensive and time consuming, and a faster, less expensive screening test is needed.

This section of the report examines the ratio of the first and second cycle reactivities, expressed as RM(20), as a function of sorbent formulation and structural properties.

The organization is similar to that in the previous section in which the effect of these parameters on first-cycle reactivity was discussed.

All pertinent data are summarized in Table IV-6, with the sorbents arranged in order of decreasing RM(20). Once again the sorbents are divided into three groups representing high, intermediate, and low reactivity maintenance. The dividing lines are again arbitrary and are placed where logical gaps exist in the values of RM(20). Only two sorbents are placed in the high group, with eight in the intermediate, and ten in the low RM(20) group.

It should be noted that other methods of evaluating second cycle reactivity maintenance which lead to significantly different sorbent rankings can be defined. For example, the comparison could be based upon the amount of sulfur sorbed in the specified time period during the second cycle or upon the total sulfur sorbed in the first two cycles in the reactivity maintenance specified time. Both of these alternates would weigh the reactivity maintenance rankings in favor of sorbents which exhibit high first cycle reactivity.

In the final analysis, the optimum sorbent might well be one capable of sorbing the maximum amount of sulfur over a large number of cycles. Such data cannot be obtained from these short duration screening tests, and it is believed that the RM(20) analysis provides the best method for comparison.

ZnO:Fe₂O₃ Ratio

The overall analysis shows no correlation between reactivity maintenance and the proportions of zinc and iron oxides in the sorbents. Although both sorbents in the high category have a 1-to-1 ratio, five of the eight sorbents in the intermediate group contain 0.8 ZnO to 1.0 Fe₂O₃, and the ten sorbents in the low category are split equally between the two formulations.

In the earlier reactivity analysis, nine direct comparisons could be made after noting that the starch content (0 or 2 percent) had no apparent effect on reactivity. In terms of RM(20), however, it appears that starch content may be important. As a consequence, no one-on-one comparisons in which the ZnO:Fe₂O₃ ratio is the only formulation variable are possible. It is necessary, therefore, to rely on the overall analysis to conclude that the ZnO:Fe₂O₃ ratio has no effect on RM(20). Subsequent one-on-one comparisons of other formulation parameters will assume no effect of the ZnO:Fe₂O₃ ratio.

Table IV-6. Comparison of Pellet Reactivity Maintenance

Sorbent	R(20)	ZnO:Fe ₂ O ₃ Ratio	Fe ₂ O ₃ Grade	% Bentonite	% Starch	Induration		Surface Area, m ² /g	Pellet Porosity
						Temperature, Of	Time, Hours		
1094-59	1.06	1.0	P	5	2	1,825	3.00	1.01	0.64
P-62	0.99	1.0	P	10	2	1,900	4.00	1.64	0.63
P-52	0.91	0.8	C	5	2	1,900	4.00	1.63	0.60
P-6	0.90	0.8	P	2	0	1,900	4.00	1.28	0.57
P-26	0.90	0.8	C	10	2	1,900	0.25	2.05	0.64
P-31	0.90	1.0	P	2	2	1,900	0.25	2.57	0.64
P-22	0.89	1.0	C	10	2	1,900	4.00	2.10	0.59
P-27	0.88	0.8	C	10	2	1,900	4.00	1.91	0.61
P-42A	0.88	1.0	P	5	2	1,900	4.00	1.07	0.59
P-21	0.88	1.0	C	10	0	1,900	0.25	2.46	0.62
P-10	0.84	1.0	C	2	0	1,700	2.00	2.43	0.65
P-11	0.84	1.0	C	2	0	1,900	0.25	2.63	0.66
P-16	0.83	0.8	C	2	2	1,900	0.25	1.55	0.57
P-47	0.83	1.0	C	5	0	1,900	4.00	1.40	0.55
P-12	0.82	1.0	C	2	0	1,900	4.00	1.38	0.59
P-32A	0.82	1.0	P	2	2	1,900	4.00	0.77	0.58
P-57	0.81	0.8	P	10	0	1,900	4.00	1.67	0.53
P-5	0.79	0.8	P	2	0	1,900	0.25	3.95	0.68
P-17	0.78	0.8	C	2	2	1,900	4.00	1.43	0.54
P-37A	0.73	0.8	P	5	0	1,900	4.00	1.76	0.55

Fe₂O₃ Grade

Although both test sorbents in the high RM(20) group contain pigment-grade Fe₂O₃, only three of eight in the intermediate group contain pigment grade and four of ten in low RM(20) contain pigment-grade Fe₂O₃. This may indicate a slight advantage associated with pigment-grade Fe₂O₃.

Six one-on-one comparisons are possible (if one neglects the effect of the ZnO:Fe₂O₃ ratio):

	<u>Catalyst Grade</u>	<u>RM(20) Group</u>	<u>Pigment Grade</u>	<u>RM(20) Group</u>
1.	P-27	Medium	P-62	High
2.	P-52	Medium	P-42A	Medium
3.	P-16	Low	P-31	Medium
4.	P-11	Low	P-5	Low
5.	P-47	Low	P-37A	Low
6.	P-17	Low	P-32A	Low

In two of the six cases, the sorbent containing pigment-grade Fe₂O₃ is in a higher RM(20) group. In the remaining four cases, the grouping is equal, and no one-on-one comparisons show higher RM(20) associated with catalyst-grade Fe₂O₃.

These results suggest that pigment-grade Fe₂O₃ may provide a small improvement in terms of RM(20). Note that this result is opposite of the reactivity results where catalyst-grade Fe₂O₃ gave slightly higher values of R(20).

Inorganic Binder

The overall analysis suggests that reactivity maintenance improves with increased bentonite content. Nine of the twenty test sorbents contain 2 percent bentonite. Seven are assigned to the low RM(20) group and two are in the intermediate group. Five test sorbents contained 5 percent bentonite. Of these, one is in the high group, two are intermediate, and two in the low group. Six sorbents contained 10 percent bentonite. One of these is in the high RM(20) group, four are ranked intermediate, and only one is in the low group.

Six one-on-one comparisons are possible (again assuming no effect of the ZnO:Fe₂O₃ ratio) with results as follows:

Bentonite Comparison						
2%			5%		10%	
	<u>Sorbent</u>	<u>RM(20) Group</u>	<u>Sorbent</u>	<u>RM(20) Group</u>	<u>Sorbent</u>	<u>RM(20) Group</u>
1.	P-6	Medium	P-37A	Low	P-57	Low
2.	P-11	Low	--	--	P-21	Medium
3.	P-12	Low	P-48	Low	--	--
4.	P-16	Low	--	--	P-26	Medium
5.	P-17	Low	P-52	Medium	P-27	Medium
					P-22	Medium
6.	P-32A	Low	P-42A	Medium	P-62	High

These direct comparisons confirm the overall conclusions concerning the desirability of high bentonite content. In four of the six cases, there is a general trend to a higher RM(20) group with increased bentonite. In one case, there is no distinction and in one case, the low bentonite sorbent is in a higher RM(20) group.

Organic Binder

Unlike the R(20) results, there seems to be a definite correlation between starch content and reactivity maintenance. Eleven test sorbents were formulated with 2 percent starch, while nine contained no starch. Both sorbents in the high ranked group contained 2 percent starch, as did six of eight in the intermediate category. In contrast, seven of ten sorbents assigned to the low RM(20) category contained no starch.

Eight one-on-one comparisons are possible (assuming no effect of the $\text{ZnO}:\text{Fe}_2\text{O}_3$ ratio). These comparisons follow:

Starch Comparison				
0%			2%	
	<u>Sorbent</u>	<u>RM(20) Group</u>	<u>Sorbent</u>	<u>RM(20) Group</u>
1.	P-57	Low	P-62	High
2.	P-47	Low	P-52	Medium
3.	P-6	Medium	P-32A	Low
4.	P-21	Medium	P-26	Medium
5.	P-5	Low	P-31	Medium
6.	P-37A	Low	P-42A	Medium
7.	P-11	Low	P-16	Low
8.	P-12	Low	P-17	Low

Four of the eight comparisons result in a higher ranking being assigned to the sorbent containing 2 percent starch. Only one comparison produces a higher ranking for the sorbent containing

no starch, and the remaining three comparisons result in equal rankings. In summary, both methods of analysis suggest that including starch in the pellet formulation improves the reactivity maintenance.

Induration Conditions

All but two of the test sorbents were indurated at 1,900°F for either 0.25 or 4 hours. Therefore, the only possible comparison which can be made is the effect of induration time at a constant temperature. Surprisingly, neither the overall comparison nor the one-on-one comparisons show any correlation between time on RM(20).

On an overall basis, 12 test sorbents were indurated at 1,900°F for 4 hours. One of these sorbents is in the high RM(20) group, while five are in the intermediate group and six are in the low group. Six test sorbents were indurated at 1,900°F for 0.25 hour. These six are split equally among the intermediate and low categories.

Five one-on-one comparisons of the effect on induration time can be made (again assuming negligible effect of the ZnO:Fe₂O₃ ratio). These comparisons are summarized as follows:

<u>Induration Time Comparison</u>				
<u>0.25 Hour</u>			<u>4.0 Hours</u>	
		RM(20)		RM(20)
<u>Sorbent</u>		<u>Group</u>	<u>Sorbent</u>	<u>Group</u>
1. P-5		Low	P-6	Medium
2. P-26		Medium	P-27	Medium
3. P-31		Medium	P-32A	Low
4. P-11		Low	P-12	Low
5. P-16		Low	P-17	Low

One comparison favors 4 hours induration, one favors 0.25 hour, and three are equal.

Summary of Sorbent Formulation Parameters

The effect of sorbent formulation parameters on RM(20) is considerably different from the effect of these parameters on R(20). The binder content, both inorganic (bentonite) and organic (starch), appears to be important in determining RM(20). Larger quantities of both binders (within the levels studied) favor increased RM(20). In contrast, neither of the binder concentrations was found to be a significant factor in determining R(20).

Induration conditions appear to have no effect on RM(20) but exert a very important effect on R(20). This result is surprising, as one might expect induration conditions to exert an opposite effect on R(20) and RM(20). High R(20) values would be an expected result of mild induration, which was observed. However, no effect of induration severity on RM(20) was noted, while one would expect severe induration conditions to produce a more stable pellet capable of improved reactivity maintenance.

Fe₂O₃ grade appears to exert a weak effect on both R(20) and RM(20), but the effect is opposite. Increased R(20) values are favored by catalyst-grade Fe₂O₃, while increased RM(20) is associated with pigment grade. Only in the case of the ZnO:Fe₂O₃ ratio are the results completely consistent. The composition ratio appears to have no impact on either R(20) or RM(20).

Structural Properties

Neither surface area nor pellet porosity appears to correlate with RM(20), as shown by the plots in Figures IV-5 and IV-6. Linear regression was used to determine the "best-fit" straight line for each data set. In each case, the low correlation coefficient confirms the visual absence of correlation. No previous reactivity maintenance studies of this type have been performed; consequently, no comparisons with past results are possible.

Figure IV-5. The effect of surface area on pellet RM(20).

Figure IV-6. The effect of porosity on pellet RM(20).

CHAPTER V. RESULTS OF CYLINDRICAL EXTRUDE TESTS

INTRODUCTION

The organization of Chapter IV, which described spherical pellet test data and analysis of results, and this chapter, describing similar results for cylindrical extrudes, parallel one another.

Twenty-six tests consisting of 1-1/2 cycles using standard gas compositions and temperatures were conducted on reference sorbent T-2465 and 18 test sorbents. A summary of these tests is presented in Table V-1. Six additional tests marked with the footnote b in the run number column, were carried out using nonstandard regeneration temperatures. Results of these runs are included in the reactivity analysis, since first sulfidation cycle conditions were standard. Reactivity maintenance results for all tests using nonstandard regeneration temperatures (spherical pellets and cylindrical extrudes) are discussed in the following chapter.

Extrudes were chosen, to the extent possible, to have equal diameter and length. When necessary, extrudes longer than desired were carefully shortened prior to use. The mean $\pm$ standard deviation of the various dimensions are:

Diameter	0.476 ± 0.020 cm
Length	1.029 ± 0.035 cm
L/D	2.17 ± 0.13
Volume	0.185 ± 0.011 cm ³

Those sorbents having any dimension outside the mean $\pm$ standard deviation ranges above are noted by footnote a in the run number column of Table V-1. Finally, footnote c associated with Run 91 (sorbent E-16) indicates that only the first reduction and sulfidation cycle was completed.

The selection of extrudes having equal dimensions (and therefore equal volume) permitted the sorbent density to vary, depending upon formulation conditions, primarily induration time, and temperature. Pellet densities varied from 1.76 g/cm³ (E-7R) to 3.16 g/cm³ (E-35), with high pellet density generally associated with severe induration conditions. The range of pellet densities associated with the extrudes is greater than found for the spherical pellets (1.66 to 2.42 g/cm³). The greater range is believed to be due to the greater range of induration conditions associated with the test extrudes. Similarly, the range of extrude surface areas (1.42 to 6.33 m²/g) and porosities (0.39 to 0.65) is greater than for spherical pellets. In general, the extrude surface areas are

Table V-1. Summary of Cylindrical Extrude Test Conditions

Sorbent	Run No.	Diameter, cm	Length, cm	Mass, mg	Initial Sorbent Properties		
					Pellet Density, g/cm ³	Surface Area, m ² /g	Porosity
T-2465 (Reference)	15 ^a	0.535	0.871	360.0	1.84	3.30	0.65
E-1	114	0.473	1.040	392.0	2.15		0.59
E-2	108	0.475	1.040	404.5	2.19	5.12	0.58
	52 ^b	0.487	1.043	415.0	2.14	4.39	0.59
	55	0.486	1.043	409.6	2.12		0.59
	90 ^b	0.485	1.039	410.0	2.14		0.59
E-7	30	0.481	1.043	395.0	2.08	5.77	0.60
	49 ^b	0.482	1.043	398.0	2.09		0.60
E-7R	109 ^a	0.456	1.042	299.0	1.76	2.59	0.65
E-9	85	0.462	1.040	418.5	2.40	2.74	0.54
E-11	48 ^b	0.487	1.023	406.3	2.13	4.39	0.59
	54	0.487	1.022	401.5	2.11		0.60
E-12	110	0.474	1.041	401.8	2.19	4.36	0.58
E-13	44 ^b	0.481	0.998	400.0	2.21	3.37	0.58
	56	0.484	0.999	391.0	2.13		0.59
	62	0.483	0.996	386.0	2.12		0.59
E-15	86 ^a	0.434	1.042	474.5	3.08	1.42	0.41
E-16	74	0.476	1.042	451.5	2.43	4.78	0.51
	91 ^c	0.473	1.042	439.5	2.40		0.52
	92	0.477	1.042	429.5	2.31		0.54
	112	0.471	1.040	431.0	2.38		0.53
E-21	111	0.476	1.040	409.0	2.21	4.62	0.56
E-24	53 ^b	0.480	1.042	430.5	2.28	2.93	0.55
	60	0.473	1.041	433.8	2.37		0.53
	113	0.466	1.039	431.5	2.44		0.51
E-28A	73	0.471	1.043	390.4	2.15	4.99	0.57
E-31	103	0.478	1.042	389.0	2.08	6.31	0.60
E-32A	106	0.476	1.040	372.0	2.01	6.33	0.61
E-35	107 ^a	0.419	1.042	454.0	3.16	1.42	0.39
E-36	104	0.476	1.042	396.0	2.14	5.76	0.57
	115	0.473	1.038	398.7	2.19		0.56
E-38	105	0.471	1.040	421.0	2.32	4.12	0.54

^a Pellet size outside of desired range.^b Nonstandard regeneration temperature.^c First sulfidation cycle only.

larger and porosities are smaller. Extrude porosities were estimated, as described in Chapter IV.

REPRODUCIBILITY

Fewer reproducibility tests were carried out using extrude sorbents, but those which were conducted produced similar results to the pellet reproducibility tests. Table V-2 presents detailed time-dimensionless weight results for the four runs using test sorbent E-16. All of the tests used standard sulfidation conditions but one, Run 91 which used a nonstandard regeneration temperature. Therefore, only first cycle reduction and sulfidation results are presented for that run.

E-16 was reduced to a greater extent than either 1094-59 or P-21. The dimensionless weight at the end of the reduction cycle, which ranged from 0.981 to 0.991, corresponded to 40 to 86 percent reduction of Fe_2O_3 to Fe_3O_4 .

The sulfidation kinetics during Run 74 was somewhat slower than for runs 91, 92, and 112. The spread in the W/W_0 values for the four runs, which was initially 0.010, increased to 0.015 after 30 minutes and then decreased to 0.012 after the 200-minute duration of the test. The maximum final value of $W/W_0 = 1.106$ is considerably less than the theoretical maximum of 1.127 corresponding to complete sulfidation of zinc ferrite containing 5 percent bentonite.

Results for the three standard regeneration tests were similarly reproducible. The difference between the W/W_0 values gradually decreased as all tests approached $W/W_0 = 1.000$. Weight losses for the three tests during the second reduction cycle were almost equal. The second cycle sulfidation kinetics of runs 74 and 112 were similar and somewhat slower than for Run 92.

The reactivity and reactivity maintenance indices, based upon a reaction time of 30 minutes for extrudes, are presented at the end of Table V-2. The three values of $R(30)$ range from 0.131 to 0.159 with an average of 0.148. The three $RM(30)$ values range from 0.69 to 0.82 with an average of 0.75. The spread in the index values is similar to the spread observed for pellets. As will be shown later, the $R(30)$ and $RM(30)$ values for sorbent E-16 were among the lowest for any of the extrude sorbents tested.

REACTIVITY AND REACTIVITY MAINTENANCE RESULTS

Values of $R(30)$ and $RM(30)$ from individual runs, along with average values for each extrude sorbent, are reported in Table V-3. The footnotes in the run number column have the same meaning as in Table V-1. Footnote a indicates that the

Table V-2. Reproducibility Comparisons for Sorbent E-16

	Run			
	74	91	92	112
W ₀ , mg	451.5	439.5	429.5	431.0
Diameter, cm	0.476	0.473	0.477	0.471
Length, cm	1.042	1.042	1.042	1.040
Time, Minutes				
Reduction				
0 (Start)	1.000	1.000	1.000	1.000
10	0.983	0.985	0.993	0.986
20	0.982	0.984	0.992	0.984
30	0.981	0.984	0.991	0.984
Sulfidation				
0 (Start)	0.981	0.984	0.991	0.984
10	1.010	1.015	1.022	1.017
20	1.021	1.028	1.036	1.031
30	1.030	1.038	1.045	1.042
40	1.037	1.047	1.052	1.049
60	1.049	1.059	1.064	1.063
80	1.059	1.069	1.073	1.072
100	1.068	1.076	1.080	1.080
120	1.074	1.084	1.086	1.086
160	1.085	1.094	1.097	1.097
200	1.094	1.102	1.105	1.106
Regeneration				
0 (Start)	1.094	--	1.106	1.104
10	1.073	--	1.080	1.081
20	1.060	--	1.066	1.067
30	1.050	--	1.055	1.058
40	1.041	--	1.045	1.045
70	1.019	--	1.031	1.023
90	1.010	--	1.014	1.012
100	1.006	--	1.010	1.008
120	1.001	--	1.003	1.001
Second Reduction				
0 (Start)	1.000	--	1.001	1.000
10	0.992	--	0.994	0.991
20	0.992	--	0.993	0.991
30	0.992	--	0.992	0.990
Second Sulfidation				
0 (Start)	0.992	--	0.992	0.990
10	1.014	--	1.020	1.016
20	1.021	--	1.029	1.023
30	1.025	--	1.036	1.028
40	1.030	--	1.041	1.032
60	1.036	--	1.050	1.037
80	1.041	--	1.055	1.041
100	1.045	--	1.059	1.044
120	1.050	--	1.064	1.048
160	1.058	--	1.069	--
200	1.064	--	1.073	--
Reactivity Index, R(30)	0.131	0.148	0.155	0.159
Reactivity Maintenance Index, RM(30)	0.74	--	0.82	0.69

Table V-3. Summary of R(30) and RM(30)
Results for Cylindrical Extrude Sorbents

<u>Sorbent</u>	<u>Run No.</u>	<u>R(30)</u>	<u>Average</u>	<u>RM(30)</u>	<u>Average</u>
T-2465	15 ^a	0.224		0.89	
	114	0.233	0.228	0.89	0.89
E-1	108	0.207	0.207	0.83	0.83
E-2	52 ^b	0.210		--	
	55	0.215		0.84	
	90 ^b	0.202	0.209	--	0.84
E-7	30	0.182		0.81	
	49 ^b	0.183	0.182	--	0.81
E-7R	109 ^a	0.291	0.291	1.02	1.02
E-9	85	0.156	0.156	0.66	0.66
E-11	48 ^b	0.194		--	
	54	0.206	0.200	0.85	0.85
E-12	110	0.207	0.207	0.92	0.92
E-13	44 ^b	0.198		--	
	56	0.224		0.79	
	62	0.228	0.217	0.72	0.76
E-15	86 ^a	0.085	0.085	0.75	0.75
E-16	74	0.131		0.74	
	91 ^b	0.148		--	
	92	0.155		0.82	
	112	0.159	0.148	0.69	0.75
E-21	111	0.193	0.193	0.88	0.88
E-24	53 ^b	0.189		--	
	60	0.178		0.51	
	113	0.176	0.181	0.70	0.60
E-28A	73	0.166	0.166	0.80	0.80
E-31	103	0.192	0.192	0.89	0.89
E-32A	106	0.211	0.211	0.91	0.91
E-35	107 ^a	0.054	0.054	0.63	0.63
E-36	104	0.154		0.65	
	115	0.157	0.156	0.77	0.68
E-38	105	0.153	0.153	0.67	0.67

^a pellet size outside of desired range.

^b Nonstandard regeneration temperature.

individual extrude size was outside the range of the mean $\pm$ standard deviation of all extrudes. Footnote b indicates nonstandard regeneration conditions, and no RM(30) values are reported for these runs.

Individual R(30) values range from a high of 0.291 (Test 109) to a low of 0.054 (Test 107). RM(30) values range from a high of 1.02 (Test 109) to a low of 0.51 (test 60). Both sets of results represent a broader range of values than found for spherical pellets. The value of RM(30) = 1.02 for sorbent E-7R is the only case in which the extrude second cycle sulfidation activity did not decrease in comparison to the first cycle.

Test extrude E-7R, which produced the highest values of both R(30) and RM(30), represents a special formulation. A third grade of iron oxide, designated Ruthner, was used. Otherwise, the formulation conditions were the same as for test extrude E-7. Ruthner grade iron oxide is less expensive than the pigment and catalyst grades used in other formulations. Consequently, it represents an attractive option if the favorable R(30) and RM(30) values are translated to favorable results from fixed-bed tests.

Complete W/W_0 versus time results during first cycle sulfidation are presented in Figure V-1 for the individual runs exhibiting highest and lowest reactivity. Sorbent E-35 (Run 107) is totally unsuitable. Sulfidation stops completely after approximately 20 minutes, with the fractional conversion of less than 0.2. Such reaction "die-off" is generally associated with complete closure of pores at the exterior surface, thus preventing H_2S from diffusing to the interior of the pellet where it can come in contact with the oxide reactant. This behavior is common in flue gas treatment where SO_2 and oxygen react with the metal oxide to form the metal sulfate. The large difference in molar density between the oxide and sulfate molecules causes the pore closure (Borgwardt, 1972). It is less common in coal-derived gas desulfurization because the molar densities of the sulfide and oxide molecules are similar. A reduction in solid porosity is commonly observed (Focht et al., 1986), but it is not normally of sufficient magnitude to cause complete pore closure.

On the basis of an approximate theoretical analysis (Focht et al., 1986), it can be shown that for pure zinc ferrite, pore closure should occur when the initial sorbent porosity is less than 0.27. No sorbents had initial porosities this low, but the porosities of E-35 ($\epsilon_0 = 0.39$) and E-15 ($\epsilon_0 = 0.41$) were considerably lower than any of the other test sorbents, and these were the only sorbents which exhibited such abrupt reaction die-off at low sulfidation levels. It is obvious that sorbent porosities of about 0.4 are too low to permit complete sulfidation. In contrast, the most reactive extrude, E-7R,

Figure V-1. Time-conversion results for extrudes exhibiting maximum and minimum reactivity.

had a porosity of 0.65, the highest of all the extrudes tested.

Figure V-2 compares first and second cycle sulfidation results for runs 109 (sorbent E-7R) and 60 (sorbent E-24). These two runs exhibited the highest and lowest values of RM(30) of all of the extrudes tested. The second cycle reactivity of sorbent E-7R increased marginally, as evidenced by RM(30) = 1.02. Only E-7R among the extrudes and 1094-59 among the pellets showed improved second cycle reactivity. The decrease in second cycle reactivity associated with Run 60 (extrude E-24) is quite significant and more severe than observed with P-37A, the pellet having the lowest RM(30) value.

REACTIVITY ANALYSIS

In this section, extrude reactivity results are analyzed in terms of sorbent formulation variables and structural properties to determine the characteristics needed to produce a highly reactive extrude. The organization follows that of the previous chapter where the reactivity of spherical pellets was examined. The reactivity results are summarized in Table V-4, with the sorbents arranged in order of decreasing reactivity. In this case, the sorbents are divided into four groups representing high, medium high, medium low, and low reactivity. As in previous cases, the group divisions are based upon perceived gaps in the RM(30) values.

Only one sorbent, E-7R with RM(30) = 0.291, is in the high reactivity group. Eleven sorbents are in the medium high group, five are in the medium low group, and two are assigned to the low reactivity group. Note that there is a particularly large gap between RM(30) for E-7R and T-2465, the sorbent at the top of the medium high reactivity group. Similarly, there is a large gap between E-16, the bottom member of the medium low group, and both sorbents in the low reactivity category.

The following evaluation is based both upon an overall analysis of the Table V-4 data and direct comparisons of sorbents in which only a single formulation parameter is varied.

ZnO:Fe₂O₃ Ratio

Twelve of the nineteen extrude sorbents (63 percent) were formulated with a 1.0:1.0 ratio of ZnO to Fe₂O₃. Within statistical limits, the percentages in each reactivity group are similar. The single sorbent rated high reactivity contains stoichiometric equivalents of ZnO and Fe₂O₃, as do 7 of 11 sorbents (64 percent) in the medium high group and 3 of 5 sorbents (60 percent) in the low reactivity group. One of the two low reactivity sorbents contains ZnO and Fe₂O₃ in the

Figure V-2. Comparison of first and second cycle sulfidation results for extrudes exhibiting maximum and minimum reactivity maintenance.

Table V-4. Comparison of Extrude Reactivity

<u>Sorbent</u>	<u>R(30)</u>	<u>ZnO:Fe₂O₃ Ratio</u>	<u>Fe₂O₃ Grade</u>	<u>% Bentonite</u>	<u>% Methocel</u>	<u>Induration</u>		<u>Surface Area, m²/g</u>	<u>Porosity</u>
						<u>Temperature, Of</u>	<u>Time, Hours</u>		
E-7R	0.291	1.0	R	5	0	1,500	4.00	2.59	0.65
T-2465	0.228	1.0	C	2	0	1,550	2.00	3.30	0.62
E-13	0.217	1.0	C	2	0.5	1,700	2.00	3.37	0.59
E-32A	0.211	0.8	P	2	0.5	1,500	4.00	6.33	0.61
E-2	0.209	0.8	C	2	0	1,500	4.00	4.39	0.59
E-1	0.207	0.8	C	2	0	1,500	0.25	5.12	0.58
E-12	0.207	1.0	C	2	0.5	1,500	4.00	4.36	0.58
E-11	0.200	1.0	C	2	0.5	1,500	0.25	4.39	0.60
E-21	0.193	1.0	C	5	0.5	1,500	0.25	4.62	0.56
E-31	0.192	0.8	P	2	0.5	1,500	0.25	6.31	0.60
E-7	0.182	1.0	P	2	0	1,500	4.00	5.77	0.60
E-24	0.181	1.0	C	5	0.5	1,900	0.25	2.93	0.54
E-28A	0.166	0.8	P	5	0.5	1,700	2.00	4.99	0.57
E-9	0.156	1.0	P	2	0	1,900	0.25	2.74	0.54
E-36	0.156	1.0	P	5	0	1,500	0.25	5.76	0.57
E-16	0.154	0.8	C	5	0	1,500	0.25	4.78	0.53
E-38	0.153	1.0	P	5	0	1,700	2.00	4.12	0.54
E-15	0.085	1.0	C	2	0.5	1,900	4.00	1.42	0.41
E-35	0.054	0.8	P	2	0.5	1,900	4.00	1.42	0.39

1.0:1.0 ratio. These distributions do not suggest any reactivity correlation with the ZnO-to-Fe₂O₃ ratio. No direct comparisons in which all formulation parameters except the ZnO-to-Fe₂O₃ ratio are constant are possible. However, none of the data, including that for spherical pellets, suggests any correlation between reactivity and the ZnO-to-Fe₂O₃ ratio.

Fe₂O₃ Grade

All except one of the extrude sorbents were formulated using either catalyst or pigment grades of Fe₂O₃, as were all of the spherical pellet sorbents. The single exception was E-7R, which utilized an even less expensive grade of Fe₂O₃, designated Ruthner. Since E-7R exhibited the highest R(30) (and RM-30) value, Ruthner Fe₂O₃ looks quite attractive. However, additional sorbents containing this grade of Fe₂O₃ should be prepared and tested before definitive conclusions can be reached.

The remaining 18 test sorbents contained either catalyst-grade (10 to 56 percent) or pigment-grade (8 to 44 percent) Fe₂O₃, and the remaining analysis is devoted to a comparison of these two. The overall analysis suggests that catalyst-grade Fe₂O₃ produces higher reactivity. Eight of eleven sorbents (73 percent) in the medium high reactivity category and only one of five sorbents (20 percent) in the medium low category contain catalyst-grade Fe₂O₃. One of the two low reactivity extrudes contains catalyst-grade Fe₂O₃.

It is necessary to accept the premise that the ZnO:Fe₂O₃ ratio has no effect on reactivity in order to make direct comparisons of the effect of Fe₂O₃ grade. With this premise, four direct comparisons are possible, and results are summarized below:

	Catalyst <u>Fe₂O₃</u>	Reactivity <u>Group</u>	Pigment <u>Fe₂O₃</u>	Reactivity <u>Group</u>
1.	E-12	Medium High	E-32A	Medium High
2.	E-11	Medium High	E-31	Medium High
3.	E-16	Medium Low	E-36	Medium Low
4.	E-15	Low	E-35	Low

In each of the four cases, the reactivity group is the same, suggesting no effect. In conclusion, catalyst-grade Fe₂O₃ may produce slightly more reactive extrudes, but the advantage is, at best, small.

Inorganic Binder

Twelve of nineteen test sorbents (63 percent) contain 2 percent inert bentonite, while the remaining seven (37 percent) contain 5 percent. The highest reactivity sorbent, E-7R, contains 5 percent bentonite, while both of the low ranked sorbents contain 2 percent. While these results suggest that 5 percent bentonite should be used, examination of the remaining data in the medium high and medium low reactivity groups suggests the opposite. Nine of eleven sorbents (82 percent) in the medium high reactivity group and only one of five (20 percent) in the medium low reactivity group contains 2 percent bentonite. We conclude that the overall analysis shows no correlation between R(30) and bentonite content.

Two direct comparisons of the effect of bentonite content are possible (again assuming that the ratio of ZnO to Fe₂O₃ has no effect on reactivity):

	<u>2%</u> <u>Bentonite</u>	<u>Reactivity</u> <u>Group</u>	<u>5%</u> <u>Bentonite</u>	<u>Reactivity</u> <u>Group</u>
1.	E-1	Medium High	E-16	Medium Low
2.	E-11	Medium High	E-21	Medium High

One direct comparison indicates that 2 percent bentonite is preferred, while the other indicates no difference. In summary, although the results are somewhat confusing, it appears that the bentonite content is not a significant factor in determining extrude reactivity.

Organic Binder

Nine of nineteen test sorbents (47 percent) contain no methocel additive, while the remaining ten contain 0.5 weight percent methocel. The entire amount of organic is assumed to burn away during the extrude induration step. Examination of the high and low reactivity groups suggests that no methocel should be added, since E-7R contains no methocel and both extrudes in the low reactivity group do contain methocel. However, inclusion of the medium high and medium low reactivity results do not confirm this. The overall analysis shows no apparent correlation between methocel addition and reactivity.

Five direct comparisons of the effect of methocel addition are possible (assuming no effect of the ZnO:Fe₂O₃ ratio):

	<u>0%</u> <u>Methocel</u>	<u>Reactivity</u> <u>Group</u>	<u>0.5%</u> <u>Methocel</u>	<u>Reactivity</u> <u>Group</u>
1.	E-7	Medium High	E-32A	Medium High
2.	E-2	Medium High	E-12	Medium High
3.	E-1	Medium High	E-11	Medium High
4.	E-16	Medium Low	E-21	Medium High
5.	E-38	Medium Low	E-28A	Medium Low

In four cases, the reactivity groups are equal, and in one case, the sorbent containing 0.5 percent methocel is in a higher reactivity group. In conclusion, it appears that methocel addition (at the levels tested) has no effect on extrude reactivity.

Induration Conditions

While the same overall range of induration conditions was used for spherical pellets and extrudes, more of the extrudes were indurated at the low and moderate temperatures (1,500 and 1,700°F), in effect producing a greater number of induration conditions for evaluation. Five temperature-time combinations were studied. The overall analysis of the effect of induration conditions is summarized below:

<u>Reactivity</u> <u>Group</u>	<u>Sorbents</u> <u>In Group</u>	<u>Induration (Temperature, Time)</u>				
		<u>1,500°F,</u> <u>0.25 Hour</u>	<u>1,500°F,</u> <u>4 Hours</u>	<u>1,700°F,</u> <u>2 Hours</u>	<u>1,900°F,</u> <u>0.25 Hour</u>	<u>1,900°F,</u> <u>4 Hours</u>
High	1	0	1	0	0	0
Medium High	11	4	4	1	1	0
Medium Low	5	2	0	2	1	0
Low	2	0	0	0	0	2

From this table, it appears that the most severe induration conditions (1,900°F and 4 hours) are definitely to be avoided. However, this overall analysis does not show any clear advantage associated with any of the other four induration combinations.

A number of direct comparisons of the effect of induration time at constant temperature and induration temperature at constant time are possible. The comparisons below examine the effect of induration time at a constant temperature of 1,500°F. The effects of the ZnO:Fe₂O₃ ratio and methocel addition are assumed to be negligible.

	<u>0.25 Hour</u> <u>Induration</u>	<u>Reactivity</u> <u>Group</u>	<u>4 Hours</u> <u>Induration</u>	<u>Reactivity</u> <u>Group</u>
1.	E-31	Medium High	E-32A	Medium High
2.	E-1	Medium High	E-2	Medium High
3.	E-11	Medium High	E-12	Medium High
4.	E-31	Medium High	E-7	Medium High

Each comparison suggests no effect of induration time at 1,500°F. One direct comparison of induration time at 1,900°F, shown below, supports the previous conclusion that 4 hours induration at 1,900°F is too severe.

	<u>0.25 Hour</u> <u>Induration</u>	<u>Reactivity</u> <u>Group</u>	<u>4 Hours</u> <u>Induration</u>	<u>Reactivity</u> <u>Group</u>
1.	E-9	Medium Low	E-35	Low

The next set of comparisons examines the effect of 1,500 and 1,900°F induration temperature at constant induration time, again assuming that the effects of the ZnO:Fe₂O₃ ratio and methocel addition are negligible.

	<u>Induration</u> <u>Time, Hours</u>	<u>Induration,</u> <u>1,500°F</u>	<u>Reactivity</u> <u>Group</u>	<u>Induration,</u> <u>1,900°F</u>	<u>Reactivity</u> <u>Group</u>
1.	0.25	E-21	Medium High	E-24	Medium High
2.	0.25	E-31	Medium High	E-9	Medium Low
3.	4.00	E-32A	Medium High	E-35	Low
4.	4.00	E-12	Medium High	E-15	Low

Comparisons 3 and 4 again support the conclusion that induration times of 4 hours at 1,900°F should be avoided. Comparisons 1 and 2 lead to somewhat mixed conclusions but suggest that 1,900°F induration should be avoided even if the induration time is minimized.

Figure V-3 shows still another method of examining the effect of induration conditions on extrude reactivity. The five induration temperature-time combinations are represented by the X's on this figure. The numbers associated with each X represent the number of extrude samples corresponding to each induration condition (in parentheses) and the arithmetic average of the R(30) values for the samples. For example, six samples were indurated at 1,500°F for 0.25 hour and the average R(30) for the samples is 0.183. Such an analysis implicitly assumes that induration conditions are the only parameter which affects R(30). While this may be an oversimplification, the

Figure V-3. The effect of induration conditions on extrude R(30).

previous analysis does indicate that induration conditions are the most important single parameter.

From Figure V-3, the highest average $R(30)$ values are associated with $1,500^{\circ}\text{F}$ induration for 4 hours. Note that this group includes the E-7R result with $R(30) = 0.291$. However, even ignoring that number, the remaining four sorbents still produce the highest $R(30)$ average. This figure suggests that a still lower induration temperature and a longer induration time should be tested, perhaps $1,300$ or $1,400^{\circ}\text{F}$ and 5 or 6 hours. The $1,300^{\circ}\text{F}$ (704°C) temperature is essentially equal to the standard regeneration temperature of 700°C , and this should be the minimum induration temperature considered.

Summary of Sorbent Formulation Parameters

Induration severity appears to be the most important of the formulation parameters in determining extrude reactivity. The most severe induration conditions of $1,900^{\circ}\text{F}$ for 4 hours have an almost disastrous effect on reactivity. Although less certain, the data suggest that lower induration temperature ($< 1,500^{\circ}\text{F}$) and longer induration time (> 4 hours) should be tested.

The other formulation variables appear to be less important. No evidence of any correlation can be found between reactivity and either the $\text{ZnO}:\text{Fe}_2\text{O}_3$ ratio or the addition of up to 0.5 percent methocel to the mixture. The effect of either 2 or 5 percent bentonite addition is at most small. The grade Fe_2O_3 used may be important. Certainly sorbent E-7R, the only test sorbent containing Ruthner grade Fe_2O_3 , exhibited high reactivity. Additional tests of other sorbents containing Ruthner grade Fe_2O_3 are desirable. Otherwise, catalyst-grade Fe_2O_3 appears to be slightly better than pigment grade.

These conclusions agree quite well with the previous conclusions concerning spherical pellet reactivity. Induration time and temperature in both cases are the most important variables. Both data sets indicate that the most severe induration conditions ($1,900^{\circ}\text{F}$ for 4 hours) are to be avoided. Since most of the spherical pellets were indurated at $1,900^{\circ}\text{F}$ for either 0.25 or 4 hours, there was no strong evidence favoring a lower induration temperature. Extrude results, however, suggest that lower temperature and longer induration times should be tested. Both data sets also suggest that the other formulation variables either have no effect or that the effect is small compared to the more important effect of induration conditions. The only exception to this latter statement concerns extrude E-7R, formulated with Ruthner grade Fe_2O_3 . Additional tests with other sorbents containing this grade of Fe_2O_3 are needed to determine if the E-7R reactivity result is, indeed, general.

Structural Properties

The previous analysis of spherical pellet reactivity showed that specific surface area and pellet porosity were important parameters. Specific surface areas in excess of $2.0 \text{ m}^2/\text{g}$ generally resulted in high reactivity, while low reactivity was associated with sorbents having surface areas less than $2.0 \text{ m}^2/\text{g}$. Although the data scatter was considerable, a general trend of increasing pellet reactivity with increasing porosity was noted.

These conclusions also apply to the reactivity of the cylindrical extrudes. Figure V-4 shows extrude R(30) versus surface area. Seventeen of the extrude surface areas exceeded $2.0 \text{ m}^2/\text{g}$, and for these pellets, there is no correlation between R(30) and surface area. The least squares line shown in the figure has a slope only slightly different from zero. This straight line was determined by excluding the data from the two sorbents whose surface areas are less than $2.0 \text{ m}^2/\text{g}$ and from sorbent E-7R, formulated from the Ruthner grade of Fe_2O_3 , which produced the particularly high R(30) value.

Figure V-4. The effect of surface area on extrude R(30).

The correlation between extrude porosity and reactivity shown in Figure V-5 is stronger than observed for the spherical pellets. All data were included in the least squares line in this figure, which has a correlation coefficient of 0.93.

Figure V-5. The effect of porosity on extrude R(30).

Because the molar volume of the product sulfide is greater than that of the reactant oxide, the porosity should decrease as sulfidation proceeds. Such results have been measured (Focht et al., 1986) and correlated by assuming that a linear relationship exists between pellet porosity and fractional sulfidation. For pure zinc ferrite (neglecting the effect of the bentonite binder), it is estimated that a 35 percent solid volume increase would accompany the conversion of ZnFe_2O_4 to $(\text{ZnS} + 2\text{FeS})$. If the extrude particle volume remains constant, this solid volume increase can be accomplished only at the expense of decreasing porosity. Thus, if the initial porosity is too small, sulfidation can result in complete pore closure and reaction die-off prior to complete sulfidation. This behavior has been observed experimentally, at least in a qualitative sense. The two sorbents having the lowest initial porosity (E-15 and E-35) both experienced reaction die-off,

while pellets having the highest initial porosity reacted rapidly and to completion.

REACTIVITY MAINTENANCE ANALYSIS

This section of the report examines the ratio of extrude reactivities during the first and second sulfidation cycles, expressed as RM(30), as a function of formulation variables and structural properties. The data are summarized in Table V-5, with the sorbents arranged in order of decreasing RM(30). The sorbents are divided into three groups representing high, medium, and low reactivity maintenance. The group divisions are again arbitrary but are based upon perceived gaps in the RM(30) values. Six sorbents are placed in the high RM(30) group, eight are in the medium group, and five are placed in the low group. It is interesting to note that sorbents E-7R and E-24, which have the highest and lowest values of RM(30), respectively, also received the highest and lowest reactivity ranking for extrude sorbents.

As before, two types of analysis are reported. The overall analysis examines the correlation between RM(30) and the parameter of interest without considering the variation in other parameters. In the direct analysis, a one-on-one comparison of RM(30) values is made by selecting extrudes in which all formulation parameters are equal except the parameter of particular interest.

ZnO:Fe₂O₃ Ratio

Twelve of the nineteen extrudes (63 percent) contain ZnO and Fe₂O₃ in the stoichiometric 1.0-to-1.0 ratio, while the remaining seven contain 0.8 ZnO to 1.0 Fe₂O₃. Four of six sorbents (67 percent) in the high RM(30) group contain 1.0 to 1.0 ZnO to Fe₂O₃. Four of eight (50 percent) in the medium group and four of five (80 percent) of the low group also contain 1.0 to 1.0 ZnO to Fe₂O₃. These distributions within the groups do not differ sufficiently from the overall sample distribution to indicate any correlation between RM(30) and the ZnO:Fe₂O₃ ratio.

No direct comparison of the ZnO:Fe₂O₃ ratio holding all other formulation parameters constant is possible. However, the results of the overall analysis, coupled with the previous analysis concerning reactivity maintenance in spherical pellets, lead to the conclusion that there is no correlation between RM(30) and the ZnO:Fe₂O₃ ratio for the cylindrical extrudes.

Fe₂O₃ Grade

The single sorbent formulated using Ruthner grade Fe₂O₃, E-7R, produced the highest values of both R(30) and RM(30).

Table V-5. Comparison of Extrude Reactivity Maintenance

<u>Sorbent</u>	<u>R(30)</u>	<u>ZnO:Fe₂O₃ Ratio</u>	<u>Fe₂O₃ Grade</u>	<u>% Bentonite</u>	<u>% Methocel</u>	<u>Induration</u>		<u>Surface Area, m²/g</u>	<u>Porosity</u>
						<u>Temperature, Of</u>	<u>Time, Hours</u>		
E-7R	1.02	1.0	R	5	0	1,500	4.00	2.59	0.65
E-12	0.97	1.0	C	2	0.5	1,500	4.00	4.36	0.58
E-32A	0.91	0.8	P	2	0.5	1,500	4.00	6.33	0.61
T-2465	0.89	1.0	C	2	0	1,550	2.00	3.30	0.65
E-31	0.89	0.8	P	2	0.5	1,500	0.25	6.31	0.60
E-21	0.88	1.0	C	5	0.5	1,500	0.25	4.62	0.56
E-11	0.85	1.0	C	2	0.5	1,500	0.25	4.39	0.60
E-2	0.84	0.8	C	2	0	1,500	4.00	4.39	0.59
E-1	0.83	0.8	C	2	0	1,500	0.25	5.12	0.58
E-7	0.81	1.0	P	2	0	1,500	4.00	5.77	0.60
E-28A	0.80	0.8	P	5	0.5	1,700	2.00	4.99	0.57
E-13	0.76	1.0	C	2	0.5	1,700	2.00	3.37	0.59
E-16	0.75	0.8	C	5	0	1,500	0.25	4.78	0.52
E-15	0.75	1.0	C	2	0.5	1,900	4.00	1.42	0.41
E-36	0.68	1.0	P	5	0	1,500	0.25	4.12	0.57
E-38	0.67	1.0	P	5	0	1,700	2.00	4.12	0.54
E-9	0.66	1.0	P	2	0	1,900	0.25	2.74	0.54
E-35	0.63	0.8	P	2	0.5	1,900	4.00	1.42	0.39
E-24	0.60	1.0	C	5	0.5	1,900	0.25	2.93	0.54

While this single result is certainly favorable, more extensive testing of additional sorbents formulated from this grade Fe_2O_3 should be carried out.

Of the remaining eighteen extrude formulations, ten used catalyst-grade Fe_2O_3 (56 percent) and eight used pigment grade (44 percent). Extrudes having high RM(30) values can be formulated from both grades of Fe_2O_3 . Three of the sorbents in the high group contain catalyst grade and two contain pigment grade. Six of the eight sorbents in the medium RM(30) group contain catalyst grade, while only one of five sorbents in the low group contains catalyst-grade Fe_2O_3 . This overall analysis, while not conclusive, suggests a slight advantage associated with catalyst-grade Fe_2O_3 .

No direct comparisons in which all formulation variables are identical, except Fe_2O_3 grade, are possible. However, by assuming that the $\text{ZnO}:\text{Fe}_2\text{O}_3$ ratio (see earlier) is unimportant, a number of direct comparisons as shown below may be made:

	<u>Catalyst Grade</u>	<u>Reactivity Group</u>	<u>Pigment Grade</u>	<u>Reactivity Group</u>
1.	E-2	Medium	E-7	Medium
2.	E-12	High	E-32A	High
3.	E-11	Medium	E-31	High
4.	E-16	Medium	E-36	Low
5.	E-15	Medium	E-35	Low

In two of the above cases, the sorbent containing catalyst-grade Fe_2O_3 belongs to a higher RM(30) group. In one case, the pigment-grade Fe_2O_3 is in the higher group, and in two cases, the grouping is equal. In conclusion, it does appear that slightly improved RM(30) values may be obtained using catalyst-grade Fe_2O_3 .

Inorganic Binder

Sixty-three percent of the extrude sorbents contained 2 percent bentonite (12 of 19), while the remainder (7 of 19) contained 5 percent bentonite. Sorbents containing both levels of bentonite are spread throughout the RM(30) rankings in Table V-5. Four of six (67 percent) of the high group sorbents contain 2 percent bentonite. Six of eight (75 percent) of the medium group and two of five (40 percent) of the low group also contain 2 percent bentonite. No correlation between bentonite concentration and RM(30) is suggested by this overall analysis.

Only two comparisons in which bentonite concentration is the only formulation parameter varied are possible, and no additional comparisons are made possible by neglecting the

effect of the $\text{ZnO}:\text{Fe}_2\text{O}_3$ ratio. A summary of the two direct comparisons is shown below:

	<u>2% Bentonite</u>	<u>Reactivity Group</u>	<u>5% Bentonite</u>	<u>Reactivity Group</u>
1.	E-11	Medium	E-21	High
2.	E-1	Medium	E-16	Medium

One comparison favors the high bentonite concentration, while the other indicates no effect of bentonite. In summary, neither the overall nor direct analysis indicates a correlation between bentonite concentration and RM(30).

Organic Binder

Extrude sorbents were formulated either without methocel addition (9 of 19) or with 0.5 percent methocel added (10 of 19). Four of six (67 percent) sorbents in the high RM(30) group, four of eight (50 percent) in the medium group, and two of five (40 percent) in the low RM(30) group contained methocel.

No direct comparisons in which only methocel concentration is varied are possible. However, a number of comparisons can be made if one assumes that the $\text{ZnO}:\text{Fe}_2\text{O}_3$ ratio is not important in determining RM(30). These comparisons are:

	<u>0% Methocel</u>	<u>Reactivity Group</u>	<u>0.5% Methocel</u>	<u>Reactivity Group</u>
1.	E-2	Medium	E-12	High
2.	E-7	Medium	E-32A	High
3.	E-16	Medium	E-21	High
4.	E-1	Medium	E-11	Medium
5.	E-38	Low	E-28A	Medium

In three of the five cases, the sorbent containing 0.5 percent methocel is in the higher RM(30) group. The groups are the same in one case. This analysis indicates that the addition of methocel leads to improved reactivity maintenance. A similar conclusion was reached with respect to spherical pellets where sorbents containing 2 percent starch were found to have better reactivity maintenance than those containing no starch.

Induration Conditions

Five combinations of induration time and temperature were studied. These range in severity from 1,500°F for 0.25 hour to

1,900°F for 4 hours. The overall analysis strongly suggests that the lowest induration temperature of 1,500°F is preferred. All sorbents in the high RM(30) group, with the exception of reference sorbent T-2465, were indurated at 1,500°F. Also, with one exception, all sorbents in the low RM(30) group were indurated at either 1,700 or 1,900°F. Except for sorbent E-36 (indurated at 1,500°F for 0.25 hour), all of the Table V-5 data indicate that a decrease in RM(30) results from more severe induration.

Overall average values of RM(30) at each of the five induration conditions are shown below:

<u>Induration</u>		<u>Number of Sorbents</u>	<u>Average RM(30)</u>
<u>Temperature, °F</u>	<u>Time, Hours</u>		
1,500	0.25	6	0.81
1,500	4.00	5	0.90
1,700	2.00	3	0.74
1,900	0.25	2	0.63
1,900	4.00	2	0.69

Low induration temperatures and long induration times combine to produce higher values of RM(30). Note that analysis of the R(30) results for extrudes led to the same conclusions.

A number of one-on-one comparisons in which all formulation parameters, except induration conditions, were held constant also led to the same conclusions. The comparisons involve from two to four of the five induration conditions as shown below:

<u>Comparison</u>	<u>Induration</u>		<u>Sorbent</u>	<u>Reactivity Group</u>
	<u>Temperature, °F</u>	<u>Time, Hours</u>		
1	1,500	0.25	E-11	Medium
	1,500	4.00	E-12	High
	1,700	2.00	E-13	Medium
	1,900	4.00	E-15	Medium
2	1,500	0.25	E-31	High
	1,500	4.00	E-32A	High
	1,900	4.00	E-35	Low
3	1,500	0.25	E-21	High
	1,900	4.00	E-24	Low
4	1,500	0.25	E-1	Medium
	1,500	4.00	E-2	Medium
5	1,500	4.00	E-7	Medium
	1,900	0.25	E-9	Low
6	1,500	0.25	E-36	Low
	1,700	2.00	E-38	Low

Comparison 1 indicates that 1,500°F and 4 hours induration is preferable. Comparisons 2, 3, and 5 all indicate that induration at 1,900°F is to be avoided. Comparison 4 shows no significant effect of time with 1,500°F induration. Comparison 6 results in somewhat of an anomaly, since both sorbents are in the low RM(30) group, while the moderate induration conditions (particularly for sorbent E-36) suggest that higher RM(30) rankings should result.

Summary of the Effect of Sorbent Formulation Parameters

It is clear that induration conditions have a more significant effect on both R(30) and RM(30) than the other formulation parameters. Reactivity analysis indicates that the most severe induration conditions of 1,900°F and 4 hours should be avoided. Reactivity maintenance analysis confirms the above conclusion and further suggests that 1,900°F should be avoided altogether. Of the five sets of induration conditions studied, 1,500°F and 4 hours seems most favorable. Analysis also suggests that still lower induration temperatures, perhaps 1,300 or 1,400°F, and longer induration times should be investigated. The induration temperature should not be less than the maximum temperature expected in an operating reactor.

A single extrude sorbent formulated with Ruthner grade Fe₂O₃ produced the highest values of both R(30) and RM(30). Such results should be pursued and additional sorbents should be prepared using this raw material to determine if favorable results can be obtained at other bentonite concentrations, induration conditions, etc. Otherwise, it appears that catalyst-grade Fe₂O₃ may perform slightly better than pigment grade. This effect, however, is less important than the proper choice of induration conditions.

Surprisingly, the addition of 0.5 percent methocel seems to improve RM(30) performance while having no significant effect on R(30) values. A similar conclusion was reached from the spherical pellet analysis, and this effect deserves further study. Neither the ZnO:Fe₂O₃ ratio nor the addition of bentonite has a significant effect on either R(30) or RM(30).

Structural Properties

Neither surface area nor porosity appears to correlate with extrude RM(30) values. Experimental results, which are shown in Figures V-6 and V-7, are quite scattered. The best straight lines determined by least squares analysis are shown in both figures strictly for reference purposes. The correlation coefficients are too low to suggest any meaningful relationship. About all that can be said in both cases is that there appears to be a general tendency for RM(30) to increase with both surface area and porosity.

Figure V-6. The effect of surface area on extrude RM(30).

Figure V-7. The effect of porosity on extrude RM(30).

CHAPTER VI. SUPPLEMENTAL STUDIES

This chapter will address two topics which have been developed as supplements to the primary objectives of this study. The first concerns the effect of regeneration temperature on sulfidation kinetics in subsequent cycles. The second topic compares the single pellet screening results of this study to the integral fixed-bed reactor test results obtained by AMAX to show the extent to which the single pellet studies can be used to anticipate the performance of a particular sorbent on a larger scale and through numerous cycles.

REGENERATION TEMPERATURE

Previous zinc ferrite kinetic studies (Focht et al., 1986) have indicated that sorbent reactivity maintenance improved with lower regeneration temperature. This conclusion was based upon results from a particular zinc ferrite (designation UCI L-1442) which was formulated from stoichiometric equivalent quantities of ZnO and catalyst-grade Fe_2O_3 , with the original formulation containing methocel and no bentonite. The cylindrical extrudes were fired at $1,500^\circ\text{F}$ with the resultant sorbent having a surface area of $6.6 \text{ m}^2/\text{g}$ and a pore volume of $0.36 \text{ cm}^3/\text{g}$ (porosity ≈ 0.61). Regeneration temperatures of 550 ($1,022$), 650 ($1,202$), 750 ($1,382$), and 850°C ($1,562^\circ\text{F}$) were studied. The 850°C regeneration was totally unsatisfactory, and 750°C regeneration was found to result in diminished reactivity in subsequent sulfidation cycles. At 650°C , regeneration was complete and essentially no zinc sulfate was formed. Second sulfidation cycle reactivity was approximately equal to the reactivity observed in the first cycle. Sulfide oxidation at 550°C was complete, but appreciable quantities of zinc sulfate were formed. Subsequent removal of zinc sulfate by heating the sorbent to 650°C in an inert atmosphere or by direct introduction of a reducing gas at 550°C produced a regenerated sorbent which showed increased second cycle reactivity.

In this study, selected test sorbents were regenerated at temperatures of $1,112$ and $1,202^\circ\text{F}$ (600 and 650°C) to permit comparison with results obtained using the standard $1,292^\circ\text{F}$ (700°C) regeneration temperature. Each run consisted of the normal 1-1/2 cycle operation. Standard gas compositions and reduction and sulfidation temperatures were used throughout; only the regeneration temperature was changed.

Figures VI-1 and VI-2 show the dimensionless weight versus time results during regeneration of pellet sorbent P-21 and extrude sorbent E-2 as a function of regeneration temperature. In each case, the maximum regeneration rate was achieved at $1,292^\circ\text{F}$ (700°C), although the effect of temperature between $1,202$ and $1,292^\circ\text{F}$ (650 and 700°C) is relatively small. At both

Figure 6-1. Regeneration results for sorbent P-21 as a function of temperature.

Figure VI-2. Regeneration results for sorbent E-2 as a function of temperature.

1,202 and 1,382°F (650 and 750°C), complete regeneration with no zinc sulfate formation was achieved, as indicated by the final values of $W/W_0 \approx 1.0$.

At 1,112°F (600°C), appreciable sulfate was formed, as indicated by the constant W/W_0 values greater than 1.0 after 160 minutes for sorbent P-21 and after 180 minutes for sorbent E-2. Once constant weight was achieved at 1,112°F (600°C), oxygen was removed from the system and the temperature was increased to 1,202°F (650°C) in an inert atmosphere. The sulfate decomposed, producing completely regenerated zinc ferrite suitable for a second sulfidation cycle.

Therefore, strictly on the basis of regeneration kinetics, it appears that 1,292°F (700°C) regeneration is preferred and 1,112°F (600°C) regeneration should be avoided because of the sulfate formation problem. However, the ability of the sorbent to maintain reactivity during subsequent sulfidation cycles is of greater importance, and the following results show that lower regeneration temperatures result in better reactivity maintenance.

Figures VI-3 and VI-4 show the dimensionless weight versus time results for sorbents P-21 and E-2 during the second sulfidation cycle following regeneration at each of the three temperatures (600, 650, and 700°C).

Second cycle sulfidation reactivity differences for sorbent P-21 (Figure VI-3) are small, and at first glance, it appears that 1,202°F (650°C) regeneration temperature results in the highest second sulfidation cycle reactivity. However, there are small but important differences in the initial extrude weight, 0.985 for Run 89 versus 0.991 for Run 50, which, when properly accounted for, give a slight reactivity advantage to Run 89 with 1,112°F (600°C) regeneration. The second cycle sulfidation kinetics for Run 58 with 1,292°F (700°C) regeneration is marginally slower than either of the other two. The effect of regeneration temperature is more pronounced in Figure VI-4 for extrude sorbent E-2. In this case, the second sulfidation cycle kinetics for runs 90 and 52, using 1,112 and 1,202°F (600 and 650°C) regeneration, respectively, are reasonably close, and both are markedly superior to Run 55 using 1,292°F (700°C) regeneration.

These conclusions are confirmed by the values of the reactivity maintenance index. Table VI-1 presents the $RM(t)$ values for all of the special runs, as well as the previously reported values (from Tables IV-6 and V-5) for the same sorbents following 1,292°F (700°C) regeneration.

In all except one case (sorbent P-6), higher reactivity maintenance is associated with lower regeneration temperature. For sorbent P-6, the $RM(20)$ values are equal for 1,202 and

Figure VI-3. Second sulfidation cycle kinetics for sorbent P-21 as a function of regeneration temperature.

Figure VI-4. Second sulfidation cycle kinetics for sorbent E-2 as a function of regeneration temperature.

1,292°F (650 and 700°C) regeneration. The small but consistent improvements in RM(t) tend to confirm the previous results and reinforce the conclusion that regeneration temperature is one of the most important process parameters in high temperature desulfurization. Excessive regeneration temperature causes irreversible structural property changes which have an adverse effect on subsequent sulfidation kinetics.

Table VI-1. The Effect of Regeneration Temperature on Reactivity Maintenance

<u>Sorbent</u>	Reactivity Maintenance (RM(t*)) Following Regeneration at		
	<u>1,112°F (600°C)</u>	<u>1,202°F (650°C)</u>	<u>1,292°F (700°C)</u>
1094-59	1.12	--	1.06
P-6	--	0.90	0.90
P-21	0.93	0.90	0.88
P-27	0.93	0.91	0.88
E-2	1.00	0.93	0.84
E-7	--	0.89	0.81
E-11	--	0.99	0.85
E-13	--	0.81	0.76
E-24	--	0.76	0.60

* t = 20 minutes for pellet sorbents and
30 minutes for extrudes.

COMPARISON WITH FIXED-BED RESULTS

The single particle studies served two purposes. The first, and primary purpose, was to determine the correlation between formulation parameters and sorbent reactivity and reactivity maintenance. The second was to determine if the rapid and inexpensive single particle tests provide a reasonable prediction of sorbent performance in larger-scale and longer-term test results using fixed-bed reactors.

The second objective may be evaluated by comparing single pellet test results to bench scale results from the AMAX program. AMAX has completed the bench-scale evaluation of 11 test sorbents (6 extrudes and 5 pellets). Each evaluation consisted of ten complete sulfidation-regeneration cycles, with each sulfidation cycle terminated when the breakthrough H₂S concentration reach 200 ppmv. Sulfur capacity at breakthrough, expressed as grams of sulfur sorbed per 100 grams of fresh sorbent, provides a convenient means of comparing the performance of the test sorbents.

Figures VI-5 and VI-6 show the breakthrough capacity as a function of cycle number for the five spherical pellets (Figure VI-5) and six cylindrical extrudes (Figure VI-6) tested by AMAX. The expected data trend would be a gradual decrease in bed capacity with cycle number such as exhibited by sorbents P-6A and P-27A in Figure VI-5. Unexpected results such as the large apparent capacity increase for sorbent P-11A after cycle 2 (Figure VI-5) and the sudden capacity increases for sorbents E-13A and E-32A between cycles 9 and 10 (Figure VI-6) cannot be explained. However, by concentrating upon overall results instead of the details, it is possible to reach general conclusions concerning relative sorbent performance. For example, from Figure VI-5, the following sorbent rankings are fairly obvious:

$$P-11A > P-6A \approx P-27A > P-37A \approx 1094-59$$

The breakthrough capacity of P-11A is erratic but is always better than the other four pellet sorbents. The capacities of P-37A and 1094-59 show little deterioration with cycle number, but the capacities remain low throughout. The distinctions for the extrude samples are less clear, but similar logic leads to the following rankings:

$$T-2465 > E-13A > E-32A \approx E-24A \approx E-7A > E-28A$$

R(t) and RM(t) values for the same sorbents are summarized in Table VI-2. P-11A was the top ranked pellet in the AMAX tests; P-11 was the only pellet to receive a high reactivity ranking from single particle tests. This is consistent with the AMAX high sulfur loadings. However, because of P-11's low reactivity maintenance, the sulfur loading at breakthrough would be expected to decline rapidly as the number of cycles increased. Indeed, that behavior pattern was observed by AMAX from the fourth cycle onward. Also note that the RM(20) index of 0.84, although in the low group, is only marginally lower than pellets in the medium group.

Pellet P-27 was in the medium group for reactivity and reactivity maintenance. The analog, P-27A, behaved similarly in the AMAX tests. The first cycle sulfur loading was in the medium range and a gradual decrease in sulfur loading with cycle number was observed. Similarly 1094-59, with low reactivity and high reactivity maintenance, behaved as expected in the AMAX tests. The sulfur loading in the first cycle was low, but no significant decrease was noted throughout the ten-cycle test.

Figure VI-5. Breakthrough capacity as a function of cycle number, AMAX results for pellet sorbents.

Figure VI-6. Breakthrough capacity as a function of cycle number, AMAX results for extrude sorbents.

Table VI-2. R(t) and RM(t) Values of Sorbents
Tested in the AMAX Bench-Scale Reactor

<u>Pellets</u>	<u>R(20)</u>		<u>RM(20)</u>	
	<u>Index</u>	<u>Group</u>	<u>Index</u>	<u>Group</u>
P-11	0.282	High	0.84	Low
P-6	0.208	Low	0.90	Medium
P-27	0.256	Medium	0.88	Medium
P-37A	0.178	Low	0.73	Low
1094-59	0.217	Low	1.06	High

<u>Extrudes</u>	<u>R(30)</u>		<u>RM(30)</u>	
	<u>Index</u>	<u>Group</u>	<u>Index</u>	<u>Group</u>
T-2465	0.228	Medium High	0.89	High
E-13	0.217	Medium High	0.76	Medium
E-32A	0.211	Medium High	0.91	High
E-24	0.181	Medium High	0.60	Low
E-7	0.182	Medium High	0.81	Medium
E-28A	0.116	Low	0.80	Medium

Similar qualitative agreement between the two sets of test results was observed with the extrude samples. Five of the six extrude sorbents were in the medium-high reactivity group, with T-2465 having the highest index value. T-2465 was also in the high RM(30) group and was the top ranked extrude from the AMAX tests. E-28A was in the low R(30) and medium RM(30) groups. This combination was the lowest of any of the extrudes tested, and E-28A was the bottom ranked extrude in the AMAX tests.

Only sorbents E-32A and E-13 showed significant deviation between the two sets of test results. On the basis of E-32A's medium-high reactivity and high reactivity maintenance, its performance should have been better than E-13, which also had medium-high reactivity but only medium reactivity maintenance. Instead, the AMAX results indicate that E-13A is a better sorbent than E-32A.

In spite of this contradiction, it appears that results obtained from the single pellet screening tests are good predictors of multicycle bench-scale performance. Further development and confirmation of this result could be quite significant in providing a rapid and inexpensive method of sorbent screening.

CHAPTER VII. SUMMARY AND CONCLUSIONS

The sulfidation and regeneration kinetics of 35 zinc ferrite formulations have been tested in a single particle electrobalance reactor. The standard test consisted of two reduction and sulfidation cycles with one intervening regeneration cycle. Standard temperatures and gas compositions were used in all tests. A number of sorbent formulation parameters, including shape (spherical pellets or cylindrical extrudes), molar ratio of ZnO to Fe_2O_3 , grade of Fe_2O_3 used, addition of both inorganic (bentonite) and organic (starch or methocel) binders, and induration conditions (temperature and time), were varied in an effort to identify those parameters required to produce sorbents having high initial reactivity and the ability to withstand sulfidation and regeneration cycling without serious reactivity loss. In addition, the effect of sorbent structural properties, specific surface area and porosity, on reactivity and durability was examined.

A reactivity index, $R(t)$, and reactivity maintenance index, $RM(t)$, were developed to permit direct comparison of the performance of the formulations tested. Induration conditions were found to be the most important formulation parameter. Induration at the highest temperature ($1,900^\circ\text{F}$) and longest time (4 hours) reduced the reactivity of both pellets and extrudes and the reactivity maintenance of the extrudes. Moderate induration at a temperature approximately equivalent to the most severe temperature expected in actual use is recommended. However, no extrude was made at less than $1,500^\circ\text{F}$ during the present program.

A summary of the effect of each of the formulation variables on $R(t)$ and $RM(t)$ for pellets and extrudes is presented in Table VII-1. Other than the effect of induration conditions, the most interesting result was obtained with the single extrude test sorbent formulated from Ruthner grade Fe_2O_3 (E-7R). This sorbent exhibited the highest individual values of both $R(30)$ and $RM(30)$ of all the extrudes tested. This single test result is sufficiently interesting to justify additional work to determine if this is a general property. The catalyst and pigment grades of Fe_2O_3 , which were used in most of the formulations, showed little, if any, difference. Catalyst-grade Fe_2O_3 appeared to have a weak advantage with respect to pellet reactivity, while pigment grade appeared to produce pellets having slightly improved reactivity maintenance.

High bentonite contents (10 percent) had a moderately important effect on pellet reactivity maintenance but no noticeable effect on pellet reactivity or extrude reactivity and reactivity maintenance. While the importance of bentonite was less than might be expected on the basis of past studies, it should be recognized that all test sorbents contained at

least 2 percent bentonite. A greater effect might have been observed if sorbents containing no bentonite had been included in the test program.

Table VII-1. Summary of the Effect of Formulation Variable on R(t) and RM(t)

<u>Pellets</u>	<u>R(20)</u>	<u>RM(20)</u>
1. ZnO/Fe ₂ O ₃ Ratio (1.0:1.0 and 0.8:1.0)	No Effect	No Effect
2. Fe ₂ O ₃ Grade (Catalyst and Pigment)	Weak Effect (Catalyst)	Weak Effect (Pigment)
3. Bentonite (2, 5, and 10%)	No Effect	Moderate Effect (10%)
4. Starch (0 and 2%)	No Effect	Moderate Effect (2%)
5. Induration (1,700 to 1,900°F and 0.25 to 4 Hours)	Strong Effect Moderate Conditions	No Effect
<u>Extrudes</u>	<u>R(30)</u>	<u>RM(30)</u>
1. ZnO:Fe ₂ O ₃ Ratio (1.0:1.0 and 0.8:1.0)	No Effect	No Effect
2. Fe ₂ O ₃ Grade (Catalyst, Pigment, and Ruthner)	? Ruthner	? Ruthner
3. Bentonite (2 and 5%)	No Effect	No Effect
4. Methocel (0 and 0.5%)	No Effect	Moderate Effect (0.5%)
5. Induration (1,500 to 1,900°F and 0.25 to 4 Hours)	Strong Effect Moderate Conditions	Strong Effect Moderate Conditions

Surprisingly, the addition of the organic binder resulted in improved reactivity maintenance for both pellets and extrudes. No effect of the organic binder on pellet or extrude reactivity was observed. Similarly, no effect of the ZnO-to-Fe₂O₃ ratio on either reactivity or reactivity maintenance for pellets or extrudes could be detected.

Sorbent porosity was found to be important in determining pellet and extrude reactivity. In particular, extrudes having the lowest porosity ($\epsilon \approx 0.40$) experienced reaction die-off at low fractional sulfidation levels leaving large portions of the metal oxide unreacted. High porosities ($\epsilon \geq 0.60$) generally resulted in a highly reactive pellet capable of being completely sulfided. Sorbents having intermediate porosity ($\epsilon \approx 0.55$) were capable of being completed sulfided but at an appreciably lower rate. Surface area was much less important in determining reactivity. Sorbents whose surface area exceeded a critical value of approximately $2 \text{ m}^2/\text{g}$ showed little correlation between surface area and reactivity. Low reactivity sorbents almost always had surface areas below this critical value. Neither porosity nor surface area appeared to be of major importance with respect to reactivity maintenance.

In a series of special tests, the regeneration temperature was found to be important in determining sorbent reactivity maintenance. A standard regeneration temperature of $1,292^\circ\text{F}$ (700°C) was used in most tests. However, lower regeneration temperature of $1,112$ or $1,202^\circ\text{F}$ (600 or 650°C) always resulted in higher $\text{RM}(t)$ values. The $1,112^\circ\text{F}$ (600°C) regeneration is complicated by the presence of the side reaction to form zinc sulfate, but at $1,202$ and $1,292^\circ\text{F}$ (650 and 700°C), the direct oxidation reaction dominates with little, if any, sulfate being formed. These results confirm previous results which indicate that temperature control during regeneration is extremely important in determining sorbent durability.

Finally, the results of these 1-1/2 cycle single particle tests were compared to the bench-scale test results being conducted by AMAX. In general, it appears that the single pellet screening tests are an accurate predictor of sorbent performance through numerous cycles in a multiparticle fixed-bed reactor. In particular, pellet sorbent P-11A and extrude sorbed T-2465 have produced the best bench-scale results among the five pellets and six extrude formulations tested to date. The single particle screening test results suggest that the performance of these two formulations should be superior to the performance of the others tested. We recommend that multicycle (≈ 10 cycles) single pellet tests be carried out using these same sorbents, and that these more extensive single particle results be compared to the AMAX results.

NOMENCLATURE

- $R(t)$ - Reactivity index defined by Equation III-8, dimensionless.
- $RM(t)$ - Reactivity maintenance index defined by Equation III-9, dimensionless,
- W - Particle mass, m.
- W_0 - Initial value.
- $W(t)$ - As function of time.
- W_{R1} - Particle mass after first reduction cycle, m.
- W_{R2} - After second reduction cycle.
- $W_S(t)$ - Mass of sulfur in sorbent particle as function of time, m.
- W_{th} - Theoretical mass of fully sulfided particle, determined by stoichiometric Equation III-3, m.
- ϵ - Particle porosity, dimensionless.
- ρ - Particle density, $m/3$.
- ρ_{thi} - Theoretical (handbook) density of component i , $m/3$.
- ρ_{th} - Theoretical density of nonporous solid, $m/3$.

REFERENCES

- Borgwardt, R. H. and Harvey, R. D., 1972, Properties of Carbonate Rocks Related to SO₂ Reactivity, Env. Sci. Tech., 6, 350.
- Focht, G. D., 1988, High Temperature Coal-Gas Desulfurization: Kinetic Evaluation of a Zinc Ferrite Sorbent, Ph. D. Dissertation, Louisiana State University, May 1988.
- Focht, G. D., Sa, L. N., Ranade, P. V., and Harrison, D. P., 1986, Structural Property Changes in Metal Oxide Hot Coal Gas Desulfurization Sorbents, DOE/MC/21166-2163.
- Grindley, T., 1987, Sidestream Zinc Ferrite Regeneration Testing, Proceedings, 7th Annual Gasification and Gas Stream Cleanup Systems Review Meeting, DOE/MC-87/6079, Volume 2, page 567.
- Jha, M. C., Hepworth, M. T., and Baltich, L. K., 1986, Enhanced Sorbent Durability for Hot Coal Gas Desulfurization, DOE/MC/21168-2023.
- Smith, K. J., Haldipur, G. B., and Lucas, J. L., 1987, KRW Process Development Coal Gasification/Hot Gas Cleanup, Proceedings, 7th Annual Gasification and Gas Stream Cleanup Systems Review Meeting, DOE/METC-87/6079, Volume 2, page 668.
- Tamhankar, S. S., Hasatani, M., and Wen, C. Y., 1981, Kinetic Studies on the Reactions Involved in the Hot Gas Desulfurization Using a Regenerable Iron Oxide Sorbent-I., Chem. Eng. Sci., 36, 1181.

END DATE
8-27-92