DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

A NOVEL, INTEGRATED TREATMENT SYSTEM FOR COAL WASTEWATERS:

QUARTERLY REPORT:

FOR THE PERIOD March 2, 199²₇ - June 1, 1992.

PIs:

Prof. Henry Y. Wang
Department of Chemical Engineering
The University of Michigan
Ann Arbor, MI 48109-2136.

&

Dr. Keeran R. Srinivasan
Assoc. Research Scientist
Department of Chemical Engineering
The University of Michigan
Ann Arbor, MI 48109-2136.

Submitted To:

Pittsburgh Energy Technology Center
U. S. Department of Energy
Pittsburgh, PA.

ABSTRACT:

The aims of this study are to develop, characterize and optimize a novel treatment scheme that would be effective simultaneously against the toxic organics and heavy metals present in coal conversion wastewaters. To remove and recover heavy metals from wastewaters, four different types of surfactant-clay complexes have been prepared using hectorite or montmorillonite as the base clays. The adsorbent is prepared by first coating the clay surface, upto a monolayer, with a cationic surfactant, CBDA, to which an amine, (DT), or a carboxylic acid (Palmitic acid, PA) is anchored using hydrophobic effect to form a mixed bilayer. Such an arrangement is expected to locate the functional groups in metal adsorption at the solid-solution interface. Complexes based on hectorite are shown to adsorb Cu^{2+} ions more strongly than the ones based on montmorillonite. The rate of adsorption of Cu^{2+} ions is quite rapid and the adsorbed amount levels off in less than 2 hrs. The optimum pH for metal adsorption is around 6.5 and the amount of metal adsorbed declines sharply on the lower pH side of the pH optimum, suggesting that removal and recovery of adsorbed metal ions can be effected by a slight pH shift.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DOE/PC/91295--T3

DE92 018307

Received by OSTI
JUL 27 1992

INTRODUCTION:

In our previous reports (1,2), it was shown that a commercially-available, modified-clay (PC-1), supplied by Bentec Corporation (3), adsorbed Cd^{2+} from an aqueous solution buffered to pH 8.5. At pH 4.0, the adsorption of Cd^{2+} was weaker, but not totally absent. On the other hand, preliminary experiments with Cu^{2+} showed that adsorption of copper ions onto PC-1 was negligible at the high and the low pH. However, a clay-CBDA-DT complex developed and prepared in this lab bound Cu^{2+} very strongly (2), while at the same time this complex was equally effective with Cd^{2+} ions as well. Clay-CBDA-DT complex is formed by a two-step process; first the clay surface is hydrophobed by attaching CBDA moieties to its surface. Subsequent interaction of DT with clay-CBDA surface is expected to result in clay-CBDA-DT complex with the polar (amino) group of DT exposed to solid-liquid interface. Anchoring of DT to the surface is believed to occur through strong hydrophobic interaction between the hydrocarbon chains of DT and CBDA. These results have raised the following questions.

- (1) Can the pH at which Cu^{2+} and Cd^{2+} adsorb to modified-clay surfaces be lowered to a value of 5.0 or 6.0 so that complications arising from the possible metal hydrolysis be avoided or minimized?

It should be pointed out that all our metal adsorption experiments carried out so far have included pH controls to verify that metal hydrolysis occurred to a very minimal extent even at the highest pH used, probably because of low metal ion concentrations used (see Fig. 4 of this report).

- (2) Can DT be directly attached to clay surface to form a clay-DT complex? If so, how effective will this be?
- (3) Why is clay-CBDA-DT complex more effective than PC-1?

To answer question (1), clay-CBDA-Palmitic acid complex was prepared using a procedure similar to the one used for the preparation of clay-CBDA-DT complex. Using montmorillonite as the base clay, DT was directly attached to the clay surface. The above two schemes are explained diagrammatically in Figs 1 -2. Solid state organic carbon and amino group analyses were undertaken to help explain

The differences between PC-1 and the clay complexes prepared as a part of this study. These results are presented and discussed in this report.

I. Preparation of New Clay Complexes:

A. Hectorite-CBDA-Palmitic Acid (Hec-CBDA-PA):

As shown in Fig. 1, hectorite (base clay) was treated with CBDA, a cationic surfactant at a pH of 5.5 - 6.0. Sufficient quantity of CBDA was added to obtain a surfactant coverage of 23% by weight. At this pH, our previous work had shown that CBDA adsorbs "irreversibly" to clay surface and render the resultant clay surface essentially hydrophobic. The clay-CBDA complex was then reacted with palmitic acid, PA, an organic acid containing C15 chain attached to the terminal carboxyl group. A two-fold excess of PA was used. Since PA is virtually insoluble in water, a solution in isopropanol was prepared. Alternatively, palmitic acid was dispersed in 0.01 M NaOH. In both cases, the pH of the reaction medium was maintained at pH 8.5 so that the acid would be essentially in its carboxylate form, and the only mode of binding of PA to clay-CBDA surface was through a "mixed bilayer" formation as depicted in Fig. 1.

After 2 hr incubation at room temperature with constant agitation, solid-liquid separation was achieved by centrifugation. The resultant complex was washed with DI water adjusted to pH 8.5.

The expected mechanism of adsorption of a heavy metal ion to such a complex would be through a combination of electrostatic and a possible specific interaction with the deprotonated form of the acid, as shown in the bottom panel in Fig. 1.

B. Montmorillonite-Duomeen-T (Mont-DT):

Montmorillonite is a widely available smectite-type clay with a CEC of 77 meq/100g and DT was bound directly to the clay surface from an isopropanol solution of the amine surfactant. 5 g of clay (equivalent to 3.85 meq) was treated with 15.3 mmol of DT at a molar ratio of 1:4. The pH was maintained at 6.0 to protonate mainly the secondary amine function of the alkyl diamine. After 2 hrs of vigorous mixing, the complex (Mont-DT) was extensively washed and dried. The procedure is schematically presented in Fig. 2.

C. Montmorillonite-CBDA-DT (Mont-CBDA-DT):

The procedure was identical to the one used for the preparation of Hec-CBDA-DT complex as reported in our previous report. CBDA was added to yield a Mont-CBDA complex containing 20% by weight CBDA. The resultant complex was treated with a four-fold molar excess of DT and the Mont-CBDA-DT was washed extensively.

Fig. 1 Possible Mode of Formation of Clay-CBDA-PA Complex

I.

R = C14 - C18

● = (CH₂)₃

II.

III.

Fig. 2 A possible Mode of Formation of Clay-DT Complex and Metal Adsorption to the Complex

II. Characterization Studies:

The final and the intermediate clay complexes were analyzed for their organic carbon content by a solid state organic analyzer (Coulometrics Inc.) The carbon analyzer was calibrated using sucrose and succinic acid as standards. Blanks were subtracted to obtain corrected organic carbon values of the different clay complexes. The results are summarized in Table 1.

Table 1. Results of Organic Carbon (OC) Analysis:

Clay Complex	OC(Wt%)	Surfactant(Wt%)	mmoles/g
Hec-CBDA	18.0	21.6	0.6;
Hec-CBDA-PA	28.8	36.0	0.6 & 0.56•
Mont-CBDA	16.7	20.0	0.56
Mont-CBDA-DT	30.0	36.1	0.56 & 0.46•
MONT-DT	41.6	50.4	1.44
Hec-CBDA-DT	38.9	46.9	0.6 & 0.72•
PC-1	28.0	34.0	----

• The second entry denotes the mmoles/g of the surfactant forming the bilayer, i.e. PA or DT. The average MW of DT (according to Akzo Chemicals, Inc., the supplier) is 350 g/mole and its average organic carbon content is 82.5%. Similar values for isomerically pure CBDA cation and PA are 360 and 256.2 g/mole and 83.3 and 74.9% respectively.

The above table shows that molar ratios of CBDA and PA is quite close to unity. With Mont-CBDA-DT and Hec-CBDA-DT, these ratios are 1.2 and 0.83 respectively in the two cases. It should be noted that DT is a mixture of surfactant amines containing C14-C18 hydrocarbon chains and along with unsaturation in the hydrocarbon chain. Several different preparations of Hec-CBDA-DT yielded CBDA/DT ratios of 1.04 to 0.82. This spread may be explained by a possible "chromatographic" separation of surfactants upon binding to the organo-clay surface. The PIs have contacted Akzo Chemicals to obtain isomerically pure samples of DT. When these samples are received this problem can be addressed.

Finally, Mont-DT has the highest surfactant concentration and its DT concentration is double that of Hec-CBDA-DT. As shown later, the extra DT moieties on the surface are NOT effective in heavy metal adsorption.

A second method to characterize the clay complexes is the determination of surface amino groups using Ninhydrin assay. This is a spectrophotometric method which is based on the formation of a blue color by reaction of ninhydrin and compounds containing free amino groups (4,5). The procedure was to treat a known weight of clay complexes at pH 5.5 with ninhydrin reagent and determining the absorbance of the blue color at 570 nm. Calibration curves were obtained using glycine and ϵ -amino caproic acid as standards. Since solid samples were used hectorite was used to blank out errors that may be caused due to the possible turbidity of the sample.

The results are summarized in Table 2.

Table 2. Results of Ninhydrin assay for free amino groups:

Clay-Complex	Amino Groups (mmoles/g)
Hec-CBDA-DT	0.65 - 0.71
Mont-CBDA-DT	0.29 - 0.35
Mont-DT	0.67
PC-1	0.01

There is a good agreement between the mmoles of DT in Hec-CBDA-DT (Table 1) and mmoles of amino groups as measured by ninhydrin method since each DT has a single free amino group. The lower values of amino groups observed in the case Mont-CBDA-DT is in line the lower adsorbed amount of DT. In the case of Mont-DT, the observed amino groups is 50% of DT groups on a molar basis. The most likely explanation is that amino groups trapped in the interlayer space of the clay was not "accessed" by ninhydrin reagent. Longer reaction times and a lower sample concentrations will be attempted to resolve this issue.

The most interesting result is that PC-1, a commercial organo-clay, has no amino groups. It was mentioned in the Introduction preliminary data on Cu^{2+} adsorption onto PC-1 at the higher or the lower pH was negligible. On the other hand, PC-1 was shown to adsorb Cd^{2+} at higher pH (2). thus, amino group analysis shows that the presence of free amino groups on the surface is crucial to Cu^{2+} adsorption.

III. Kinetics of Cu^{2+} adsorption:

The rate of adsorption of Cu^{2+} to clay-surfactant complexes prepared previously and in this reporting period were carried out at pH 8.0 and 9.0. The rate measurements were done in a batch mode and solid-liquid separation was achieved by filtering the slurry through a 0.2 μm membrane. An adsorbent concentration of 2 mg/ml and an initial adsorbate concentration of 25 ppm were used. Control experiments at identical initial Cu^{2+} concentration were carried out to account for loss of metal ion from solution through possible hydrolysis and precipitation over the course of the experiment. Buffers were used to maintain the pH at the set point and the ionic strength was 0.02 M. The results are shown in Figs 3 and 4.

The results presented in these two figs show that the loss of Cu^{2+} ions through hydrolysis is negligible. Thus, any loss of Cu ions from solution is attributable to adsorption onto clay complexes. At both pH the adsorption process is seen to be quite rapid and levels off in less than 2 hrs. A significant depletion of Cu ions is observed only with Hec-CBDA-PA and Hec-CBDA-DT. The former containing a lower amount of surfactant adsorbs more Cu ions from solution. This would suggest that palmitic acid function is more effective because it provides for a favorable electrostatic and specific interaction between the clay-complex and the metal ion at both pH.

Secondly, Mont-DT and Hec-CBDA-DT have an identical number of surface amino groups as reported by the ninhydrin method. But, the latter is significantly more effective, especially at pH 9.0. The preliminary conclusions to be drawn is that the surface structure of the clay complex appears to be **crucial**. It is likely that the amino groups of Hec-CBDA-DT are more "accessible" than those of Mont-DT, or the former are more nucleophilic. The reason for the much higher potential of Hec-CBDA-DT is not clearly understood at this point and further studies will be undertaken to clarify this issue.

Mont-CBDA-DT appears to be the poorest of adsorbents at both pH even though it has half as many amino groups on the surface as Hec-CBDA-DT or Mont-DT. This is a further indication that the metal adsorption capability of clay complexes is closely related to the type of clay (hectorite vs montmorillonite), the amount of CBDA pre-saturation (a value of 20 and 21.6% respectively in the cases of montmorillonite and hectorite) and the orientation of DT at the interface.

It is clear that a number of clay complexes with a wide range of metal binding capacity has been prepared and a preliminary evaluation has been undertaken. The next logical step is the pH optimization which is considered in the next section.

Fig. 4 Rate of Adsorption of Cu ions at pH = 9.0

Fig. 3 Rate of Adsorption of Cu ions at pH = 8.0

Finally, it should be noted that the adsorbed amount is lower at pH 9.0 than at pH 8.0. If precipitation of Cu ions were a problem then an opposite trend in the amount of Cu ions removed from solution can be expected.

IV Optimization of pH Effect:

With the development of four different types of clay complexes it was felt necessary to determine the pH of maximal adsorption in each case. It should be remembered that Hec-CBDA-PA carries a net negative charge on its surface at pH above 5.0, the DT-containing complexes will have a higher isoelectric point (IEP). Therefore a range of pH from 3.0 to 9.0 was used to assess the pH effect. The depletion of Cu^{2+} from solution at the end of 120 minutes (selected from the data shown in Figs 3 and 4) was monitored in a batch mode. The mean value obtained from a set of triplicates is plotted against pH in Fig. 5

Fig. 5 Adsorption of Cu ion after 120 minutes:
pH Effect

The value of optimum pH is between 6.0 and 7.0 for all cases. On the low pH side the curves for the two hectorite complexes rises sharply indicating that the desorption can be easily effected by a shift in pH. These results on Cu^{2+} adsorption are in contrast to those obtained for Cd^{2+} adsorption onto PC-1, a commercial organo-clay. With Cd ions adsorption increased with pH upto a pH of 9.0. Thus, Cu and Cd ions may bind differently to modified clay surfaces.

V. Conclusions:

- (1) Four different types of clay complexes containing different surface functional groups have been prepared and characterized.
- (2) The rate adsorption of Cu^{2+} appears to be quite rapid and levels off in less than 2 hrs.
- (3) The pH optimum for Cu^{2+} adsorption is around 6.5 and the amount of adsorption declines sharply on the low pH side of the optimum.

VI References:

- (1) Henry Y. Wang and Keeran R. Srinivasan: I Quarterly Report, DOE/PETC, Dec. 1991.
- (2) Henry Y. Wang and Keeran R. Srinivasan: II Quarterly Report, DOE/PETC, March, 1992.
- (3) George Alther: Bentec, Inc., Ferndale, MI (Personal Communication).
- (4) S. Moore and W. H. Stein, J. Biol. Chem. 176, 367 (1948).
- (5) S. Blackburn, " Determination of Amino Acids by High-Voltage Paper Electrophoresis"
In Methods of Biochemical analysis Ed. (David Glick), Chap. 1, p1, Interscience Publishers, NY (1965).

END

**DATE
FILMED**

9 / 16 / 92