UNCLASSIFIED

STRUCTURAL DESIGN CRITERIA FOR REPLACEABLE GRAPHITE CORE ELEMENTS

~~ALL RIGHTS RESERVED. NO PART OF THIS DOCUMENT MAY BE REPRODUCED OR TRANSMITTED IN ANY FORM OR BY ANY MEANS, ELECTRONIC OR MECHANICAL, WITHOUT PERMISSION IN WRITING FROM THE U.S. DEPARTMENT OF ENERGY.~~
~~Representing Foreign Governments, Foreign Entities, or Foreign Organizations, or Divisions of U.S. Companies shall be approved by the Deputy Assistant Secretary for Research, Development and Technology, U.S. Department of Energy, before DOE approval is given to Federal Register, 10 CFR Part 910, and/or May 1974 Atomic Energy Act.~~

AUTHORS/CONTRACTORS

GENERAL ATOMICS

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

This document is

PUBLICLY RELEASABLE

H.A.

6/11/02

PER DAVID STEINMAN
GENERAL ATOMICS, CLASSIFICATION
OFFICER, MEMO DATED 01/22/01

**ISSUED BY GENERAL ATOMICS
FOR THE DEPARTMENT OF ENERGY
CONTRACT DE-AC03-89SF17885**

MASTER

SEPTEMBER 1989

UNCLASSIFIED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

UNCLASSIFIED

DOE-HTGR-88150
Revision 1

CAUTION

Do not publicly release this document.

This technical report is being transmitted in advance of DOE patent clearance and no further dissemination or publication shall be made of the report without prior approval of the DOE Patent Counsel.

This document will be returned upon request or when no longer needed, unless notification has been received that this document has been cleared for release or publication.

PATENT CLEARED
11/4/91

**STRUCTURAL DESIGN CRITERIA FOR
REPLACEABLE GRAPHITE CORE ELEMENTS**

Issued By:

General Atomics
P.O. Box 85608

San Diego, California 92138-5608

DOE CONTRACT DE-AC03-89SF17885

GA Project 6300

SEPTEMBER 1989

UNCLASSIFIED

ISSUE SUMMARY

TITLE	STRUCTURAL DESIGN CRITERIA FOR REPLACEABLE GRAPHITE CORE ELEMENTS	☐ R & D ☐ DV & S ☒ DESIGN	APPROVAL LEVEL <u>3</u>
-------	--	---	-------------------------

DISCIPLINE M	SYSTEM 11	DOC. TYPE RGE	PROJECT 6300	DOCUMENT NO. DOE-HTGR-88150	ISSUE NO./LTR. 0
-----------------	--------------	------------------	-----------------	--------------------------------	---------------------

QUALITY ASSURANCE LEVEL N/A	SAFETY CLASSIFICATION N/A	SEISMIC CATEGORY N/A	ELECTRICAL CLASSIFICATION N/A
--------------------------------	------------------------------	-------------------------	----------------------------------

ISSUE	DATE	PREPARED BY	APPROVAL				ISSUE DESCRIPTION/ CWBS NO.
			ENGINEERING	QA	FUNDING PROJECT	APPLICABLE PROJECT	
0	AUG 26 1988	N.D. Rickard <i>N.D. Rickard</i>	<i>R.E. Vollman</i> R.E. Vollman				Initial Issue (909729) 7052115004
1	SEP 29 1989	N.D. Rickard <i>N.D. Rickard</i>	<i>R.E. Vollman</i> R.E. Vollman <i>R.F. Turner</i> R.F. Turner	<i>G.P. Connors</i> G.P. Connors	<i>G.C. Bramblett</i> G.C. Bramblett		Update Criteria 7652115040 SLPP M/S 5211.5.05 DOE Change Class III

CONTINUE ON GA FORM 1485-1 *See List of Effective Pages for page count.	NEXT INDENTURED DOCUMENTS DOE-HTGR-86035
--	---

REDACTED SECTION

Representing Foreign Interests, Foreign Government, Foreign Corporation, Foreign Subsidiary, or Foreign Divisions of U.S. Companies, Shall Be Approved by the Associate Secretary for Reactor Systems Development and Technical Support, Department of Energy. Further, Foreign Party Release May Require DOE Approval, Federal Register Part 810, and/or May Be Subject to Section 7 of the Atomic Energy Act.

☐ **GA PROPRIETARY INFORMATION**

THIS DOCUMENT IS THE PROPERTY OF GENERAL ATOMICS. ANY TRANSMITTAL OF THIS DOCUMENT OUTSIDE GA WILL BE IN CONFIDENCE. EXCEPT WITH THE WRITTEN CONSENT OF GA, (1) THIS DOCUMENT MAY NOT BE COPIED IN WHOLE OR IN PART AND WILL BE RETURNED UPON REQUEST OR WHEN NO LONGER NEEDED BY RECIPIENT AND (2) INFORMATION CONTAINED HEREIN MAY NOT BE COMMUNICATED TO OTHERS AND MAY BE USED BY RECIPIENT ONLY FOR THE PURPOSE FOR WHICH IT WAS TRANSMITTED.

☒ **NO GA PROPRIETARY INFORMATION**

UNCLASSIFIED

LIST OF EFFECTIVE PAGES

<u>Page Number</u>	<u>Page Count</u>	<u>Revision</u>
i through iv	4	1
1-1	1	1
2-1 through 2-4	4	1
3-1 through 3-4	4	1
4-1 through 4-2	2	1
5-1 through 5-4	4	1
6-1	1	1
	<hr/>	
Total Pages	20	

CONTENTS

1. INTRODUCTION	1-1
1.1. Scope	1-1
1.2. Applicability	1-1
2. GENERAL DESIGN CRITERIA	2-1
2.1. Loading Criteria	2-1
2.2. Material Properties	2-3
2.3. Special Considerations.	2-3
2.3.1. Corrosion	2-3
2.3.2. Fracture Mechanics	2-4
3. DESIGN BY ANALYSIS.	3-1
3.1. Method of Analysis.	3-1
3.2. Analysis Input Data	3-2
3.3. Calculations of Strength	3-2
4. DESIGN BY TEST AND ANALYSIS	4-1
4.1. Design by Test.	4-1
4.2. Design by Combined Test and Analysis.	4-1
5. STRESS LIMITS	5-1
5.1. Fuel and Reflector Element Stress Limits	5-1
5.2. Dowel/Dowel-Socket Stress Limits.	5-1
5.3. Fatigue Stress Limits	5-2
6. REFERENCES	6-1

TABLES

1. Fuel and Reflector Element stress limits	5-3
2. Dowel/dowel-socket stress limits	5-4

1. INTRODUCTION

1.1. SCOPE

This document describes the structural criteria for the design of the replaceable graphite elements of the Modular High Temperature Gas-Cooled Reactor (MHTGR) core.

1.2. APPLICABILITY

These criteria are applicable to the design of the MHTGR fuel elements and replaceable reflector elements and are applicable only for the reactor configuration defined by the Reactor System Design Description (Ref. 1).

2. GENERAL DESIGN CRITERIA

The design of graphite elements governed by these criteria shall account for the brittle behavior of graphite, the low tensile strength relative to compressive strength, the effects of neutron irradiation and temperature in material behavior, and the process by which the graphite was manufactured. Failure due to stress shall be governed by the maximum principal stress theory commonly used for brittle materials.

The core graphite elements shall be designed by analysis or by a combination of test and analysis. Due to the wide range of possible thermal/irradiation loading conditions and the difficulty associated with simulating these conditions by test, design by analysis is required for thermal/irradiation loads. However, for mechanical loads such as seismic loads, it may be advantageous to verify the design by a combination of analysis and test results. The rules for design by analysis are presented in Section 3. The rules for design by test and analysis are presented in Section 4.

2.1. LOADING CRITERIA

Loads on MHTGR core graphite components are of three types: (1) mechanical, (2) differential thermal strains, and (3) differential irradiation induced dimensional change and shall be accounted for in the design.

Representative loads include but are not limited to the following:

- Core pressure drop from primary coolant flow
- Dead weight
- Weight of fuel pins
- Weight of shield structures
- Fuel handling motion
- Seismic motion from both the Operational Basis Earthquake (OBE) and the Safe Shutdown Earthquake (SSE)
- Flow induced vibration
- Acoustic vibrations
- Time dependent irradiation induced dimensional change caused by neutrons fluence
- Steady state temperature differences
- Transient temperature changes resulting from primary coolant flow
- Plant operational load change transients
- Scram transients
- Postulated accident conditions such as loss of coolant flow followed by a conduction cooldown

Specific loading conditions for each component shall be obtained from the appropriate component design specification. The loading conditions shall be assigned to service levels A, B, C, or D as prescribed in the appropriate component design specification.

The initial conditions considered for each event shall include any conditions that could exist at the time of the event assuming (1) the prior occurrence of any or all of the Service Level A or B events, and (2) the concurrent occurrence of any Service Level A event. The design shall be shown to withstand the load conditions and combinations thereof specified in the Core Component Design Specification (Ref. 5).

2.2. MATERIAL PROPERTIES

Mean values of material behavior data and failure data shall be used to show compliance with these criteria. Statistically significant quantities of data shall be used to know these mean values at a confidence level of 95%. The variability within a billet, from billet to billet, and from lot to lot shall be included in the statistical evaluation of material property data. The material property behavior to be used in evaluation of components to these criteria shall be obtained from the Graphite Design Handbook (Ref. 2).

2.3. SPECIAL CONSIDERATIONS

2.3.1. Corrosion

The effects of environmentally caused degradation shall be accounted for in the design. In particular the effects on material behavior and failure stress of graphite corrosion caused by moisture, carbon monoxide, and carbon dioxide shall be included in the design evaluations such that these criteria are met for the extremes of these effects.

2.3.2. Fracture Mechanics

When fracture mechanics principles are used to evaluate crack propagation the assumed initial flaw size shall be greater than the minimum that can be detected by NDE and/or implied by proof testing of the components.

3. DESIGN BY ANALYSIS

The following rules shall be used for design by analysis.

3.1. METHOD OF ANALYSIS

The time dependent strains induced by temperature, stress, and neutron irradiation shall be calculated in the stress analysis. These strains shall include thermal, irradiation, elastic, transient creep, and steady creep strains. The analysis shall include the effects of temperature on material properties, irradiation on material properties, the anisotropy of the material, and the systematic spatial variations of the graphite strength. In addition, the graphite strength shall be adjusted for grain size effects and volume effects as described in Section 3.3.

The design shall allow crack initiation and limited crack propagation for certain specified low frequency events as specified in Section 5.1. The extent of crack propagation shall be evaluated by performing a series of finite-element analyses in which the maximum stressed finite element is analytically cut and the analysis repeated until (1) the maximum stress is reduced below the maximum allowable stress, and (2) the crack terminates at an element surface (e.g., a fuel hole or coolant hole). To reduce the number of finite-element analyses cases when modeling crack propagation, several finite elements may be cut between each iteration. The crack shall not (1) cause a piece to separate from the element or (2) exceed the design limits for crack opening or crack length.

3.2. ANALYSIS INPUT DATA

The input used in the analysis shall be as follows:

1. Material Properties. Mean values of the material properties (e.g., Young's Modulus, irradiation creep moduli, thermal conductivity, etc.) shall be used in the analysis.
2. Dimensions. The analysis shall use nominal dimensions reduced to reflect the maximum removal of material due to graphite corrosion that would be expected to exist at the time of the event being analyzed (see Section 2.3.1).

3.3. CALCULATION OF STRENGTH

The maximum principal strength theory of failure shall be used in conjunction with the Weibull weakest link theory to account for volume effects on strength.

The systematic spatial variations of the graphite strength shall be accounted for as described in the Graphite Design Handbook (Section 4.5.3) of Ref. 2). In addition, the following equation (Ref. 3) shall be used to adjust the strength at a point in the graphite for volume and grain size effects:

$$SSR = SSR_s \frac{F_0}{F_1} \frac{V_1^{1/m}}{V_0},$$

where SSR = ratio of principal stress to mean graphite strength at a point adjusted for spatial, grain size, and volume effects,

SSR_s = SSR adjusted for spatial effects (Ref. 2),

F_1 = grain size factor,

$$= [(2/\pi)\cos^{-1}(h_0/h_1)] [(2/\pi)\cos^{-1}(h_0/h_2)],$$

h_0 = reference grain size = 0.0625 in.,

h_1 = crack surface width,

h_2 = crack surface length,

F_0 = reference grain size factor = 0.848,

V_0 = reference volume = 0.60 in.³,

$$V_1 = \int_{V_1} [f_1(V)]^m dV \text{ (Ref. 4, eq. 13),}$$

$f_1(V)$ = function which describes the actual stress distribution throughout the volume and is normalized to 1.0 at the location of SSR_s ,

m = Weibull parameter = 11.

The following rules govern the computation of V_1 :

1. In general, V_1 shall be evaluated for a single finite element.
2. Additional finite elements shall be included in the evaluation of V_1 if including these elements could cause the adjusted SSR to exceed the design limits.
3. The volume shall only include material that is subjected to tensile principal stresses. For example, in a finite element that is subjected to pure bending, only the half subjected to tension shall be included in the volume.
4. The function $f_1(V)$ can conservatively be assumed to be equal to 1.0 providing that SSR_s is the maximum SSR_s in the volume.

5. The maximum SSR_g in a volume may be approximated by the maximum SSR_g evaluated at the finite-element integration points.

The following rules govern the selection of h_1 and h_2 for the computation of F_1 :

1. In general, h_1 and h_2 shall be the dimensions of the potential failure surface assuming the complete ultimate failure of the surface (i.e., not just crack initiation, but crack propagation across the entire surface). For the example of a fuel element web, h_1 is the thickness of the web, and h_2 is the height of the fuel element.
2. The potential failure surface shall pass through the volume that is being evaluated.
3. The dimensions of the potential failure surface (h_1 and h_2) shall not include any previously cracked material. For example in a crack propagation analysis, h_1 and h_2 shall be the dimensions of the uncracked surface. Therefore, as the crack propagates, the area of the potential failure surface will become smaller.

4. DESIGN BY TEST AND ANALYSIS

Design by a combination of test and analysis is permitted for load combinations which have a maximum SSR < 0.60 since (1) a crack-propagation analysis is required if the maximum SSR is > 0.60 and (2) the design-by-test methodology is not applicable to crack-propagation analysis.

4.1. DESIGN-BY-TEST

A series of tests shall be conducted which measure the load required to initiate a crack. This load shall be designated the ultimate load. From these data, the mean and minimum ultimate loads shall be computed. The minimum ultimate load shall be the load that has 99% probability with 95% confidence that crack initiation will not occur.

The design-by-test SSR shall be computed as follows:

$$\text{SSR} = (\text{Applied Load}) / (\text{Allowable Ultimate Load}) \quad .$$

where the "allowable ultimate load" is the smaller of the mean ultimate load or $1.45 \times (\text{minimum ultimate load})$.

4.2. DESIGN BY COMBINED TEST AND ANALYSIS

The combined design-by-test-and-analysis SSR shall be computed by arithmetically adding the design-by-test SSR to the maximum design-by-analysis SSR without regard to the direction or location of the maximum stress. The combination of SSRs results in an upper bound to the actual SSR at a particular point. The combined upper bound SSR shall be less than or equal to the design limits of Section 5.1.

The design engineer may use other methods to combine the design-by-test and design-by-analysis results provided that an upper bound to the combined SSR is obtained. It shall be the responsibility of the design engineer to demonstrate that the resulting SSR is an upper bound to the maximum combined SSR.

5. STRESS LIMITS

The design of replaceable graphite elements in the core shall be such that the principal stress values, when expressed as stress-to-strength ratios (SSRs), will not exceed the stress limits of this section.

Stress-to-strength-ratio (SSR) is defined as the ratio of the principal stress to mean graphite strength.

5.1. FUEL AND REFLECTOR ELEMENT STRESS LIMITS

The graphite stress limits presented in Table 1 shall apply to stresses produced by all load combinations except load combinations which include loads acting on or reacted by the dowels (see Section 5.2). The design limits for Service Level A and B events must be met without allowing the element to crack. For Service Level C and D events, crack initiation and limited crack propagation are allowed. The crack-opening design limits only apply to fuel elements. Non-fuel elements shall meet the SSR design limits and the crack-length design limits.

5.2. DOWEL/DOWEL-SOCKET STRESS LIMITS

The dowel/dowel-socket stress limits presented in Table 2 shall apply to stresses produced by or partially produced by loads acting on the dowels or reacted by the dowels. SSRs shall be computed using the methodology described in Sections 3 and 4. Crack-propagation analysis is not permitted.

5.3. FATIGUE STRESS LIMITS

(To be included later)

TABLE 1
FUEL AND REFLECTOR ELEMENT STRESS LIMITS

Service Level	SSR	Crack Length (in.)	Crack Opening ^(a) (in.)
A	0.5	(b)	(b)
B	0.6	(b)	(b)
C	0.6	7.0(c)	0.020
D	0.6	(d)	0.025

(a) The design limits for crack opening apply only to fuel elements. Reflector elements are limited by notes (c) and (d) below.

(b) Crack initiation is not permitted.

(c) The sum of the lengths of all cracks in an element shall not exceed 7.0 in., and the element shall remain in one piece.

(d) The element shall remain in one piece.

TABLE 2
DOWEL/DOWEL-SOCKET
STRESS

Service Level	SSR
A	0.45
B	0.45
C	0.55
D	0.60

6. REFERENCES

1. "Reactor System Design Description," GA Document DOE-HTGR-86035, Rev. 2, April 1988.
2. Ho, F. H., "Graphite Design Handbook," GA Document DOE-HTGR-88111, Rev. 0, September 1988.
3. Ho, F. H., "A Modified Weibull Theory for the Strength of Granular Brittle Material," GA Report GA-A15228, May 1979.
4. Robinson, E. Y., "The Statistical Nature of Fracture," UCRL-50622, TID-4500, UC-25, Lawrence Radiation Laboratory, University of California, 1969.
5. "Core Component Design Specification," GA Document DOE-HTGR-88134, Rev. 0, October 1988.
6. "Overall Plant Design Specification Modular High Temperature Gas-Cooled Reactor," GA Document DOE-HTGR-86004, Rev. 7, August 1988.