UNCLASSIFIED

WAPD-PMM-262

Subject Category: REACTORS-POWER

LEGAL NOTICE

This report was prepared as an account of Government sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission:

A. Makes any warranty or representation, express or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or
B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method, or process disclosed in this report.

As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission to the extent that such employee or contractor prepares, handles or distributes, or provides access to, any information pursuant to his employment or contract with the Commission.

RESUME OF URANIUM ALLOY DATA-IX

By
E. F. Losco
Z. M. Shapiro

September 1, 1955

Price \$ 0.60

Available from the
Office of Technical Services
Department of Commerce
Washington 25, D. C.

UNITED STATES ATOMIC ENERGY COMMISSION
Technical Information Extension, Oak Ridge, Tennessee

UNCLASSIFIED

~~CONFIDENTIAL~~

This report has been reviewed under the Declassification Guide of 1955.

Work performed under Contract No. AT-11-1-Gen-14.

- LEGAL NOTICE

This report
United States, no

on account of Government sponsored work. Neither the
or any person acting on behalf of the Commission:

A. Makes any
accuracy, completeness,
use of any information,
fringe privately owned right

tation, express or implied, with respect to the ac-
information contained in this report, or that the
process disclosed in this report may not in-

B. Assumes any liability.
use of any information, apparatus

use of, or for damages resulting from the
disclosed in this report.

As used in the above, "person
employee or contractor of the Commiss.
prepares, handles or distributes, or provi
employment or contract with the Commission.

"the Commission" includes any em-
that such employee or contractor
information pursuant to his em-

This report has been reproduced from the best
available copy.

Printed in USA. Charge 60 cents. Available from the
Technical Information Extension, P. O. Box 1001, Oak Ridge,
Tennessee. Please direct to the same address inquiries cov-
ering the procurement of classified AEC reports.

~~CONFIDENTIAL~~

AEC, Oak Ridge, Tenn.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

Resume of Uranium Alloy Data - IX

E. F. Losco
Z. M. Shapiro

September 1, 1955

Compiled by:

S. Aronson	I. Cohen	H. G. Hoge
M. L. Bleiberg	H. W. Cooper	R. C. Koch
W. A. Bostrom	J. E. Eck	L. J. Jones
R. F. Boyle	J. D. Eichenberg	R. D. Leggett
M. W. Burkart	R. H. Fillnow	J. M. Markowitz
T. J. Burke	R. R. Fouse	T. R. Padden
F. M. Cain	J. Glatter	B. E. Schaner
J. C. Clayton	E. K. Halteman	R. A. Wolfe

INTRODUCTION

Following are the principal developments in the FWR uranium fuel program since the last panel meeting:

1. Irradiation behavior of uranium-molybdenum and uranium-niobium alloys.

Samples of uranium-molybdenum (9, 10.5, 12, and 13.5% Mo) and uranium-niobium (10% Nb) alloys exposed to pile irradiation in both the gamma-quenched and alpha-transformed conditions reverted to a condition intermediate between the untransformed and transformed states; that is, the gamma-quenched samples showed a slight tendency to transform, while the transformed samples showed a marked decrease in the amount of transformation. All the irradiations were conducted at temperatures far below those at which thermally-induced transformations would be expected. This behavior was also reported in case of the U-9 Mo alloy by Konobeevsky, Pravdyuk, and Kutaitsev (p 681, Effect of Irradiation on Structure and Properties of Fissionable Materials) at the Geneva Conference. These effects appear to be quite well-established based upon electrical resistivity, temperature coefficient of electrical resistivity, hardness, and metallography (the Russian investigators employed, in addition, X-ray diffraction techniques). In case of the U-Mo alloys where one of the products of transformation is the ordered epsilon phase, the results obtained are in harmony with experimental observations on other order-disorder systems, although it is indeed puzzling that alpha precipitated during a 2-week anneal at 525°C is apparently reabsorbed during the 6-week irradiation at a maximum estimated temperature of 300°C. However, in case of the U-Nb system, where no such ordered phase has been reported, this explanation is not available. The attention of the panel is directed to this phenomenon and its discussion at the next panel meeting requested.

CLASSIFICATION CANCELLED

DATE MAR 6 1957

For The Atomic Energy Commission

-1. R. Canale
Chief, Declassification Branch

2. Irradiation expansion of uranium and uranium-base alloys.

A number of uranium rods containing 0 and 2% zirconium and clad with a zirconium-2.5% tin alloy by coextrusion had been fabricated by Dr. A. R. Kaufmann (NMI, nee MIT) and exposed in the Chalk River reactor after a number of different heat treatments to a maximum of 8400 MWD/T. The results may be summarized as follows:

- a. Irrespective of heat treatment and alloy content, no appreciable growth was observed in any of the rods (growth is defined as directional deformation of the rods as contrasted with expansion defined as density decrease).
- b. Irrespective of heat treatment and alloy content the rods expand fairly uniformly at a rate of 0.4 to 0.5 volume percent per 1000 MWD/T burnup.
- c. Those rods irradiated in excess of 7000 MWD/T, again irrespective of heat treatment and composition, showed splitting of the cladding at a volume expansion of about 4%. While it cannot be unequivocally stated that the splitting did not occur as a result of corrosion of the uranium through clad or weld imperfections, it is the consensus of those who observed the splits that they are indeed irradiation-induced failures.

These observations may be compared with the reports by S. H. Paine and J. H. Kittel (p.745, Irradiation Effects in Uranium and Its Alloys) that at irradiations up to 1000 MWD/T, uranium decreases in density by 0.3-0.5% per 1000 MWD/T; with the observation reported herein that uranium alloys containing 9 to 13.5% Mo expand at irradiations up to 8000 MWD/T by less than 0.5% per 1000 MWD/T; and the further observation reported below that clad rods of uranium with 9 to 13.5% Mo irradiated to a nominal burnup of 40,000 MWD/T showed a volume expansion of 4% (or about 0.1% per 1000 MWD/T) and that one rod was split as a result of this irradiation. These results would appear to indicate that irradiation growth of uranium can be restrained by a suitable cladding, proper alloying, or heat treatment stresses induced in the cladding procedure. However, volume expansion of the uranium as a result of irradiation appears to be controllable to only a limited extent by alloying and may constitute the ultimate radiation damage limit to fuel elements clad with materials of low ductility or low irradiation-induced ductility.

3. Identification of the hydride phase in gamma-phase alloys.

Some progress has been made in tying down the nature of the hydride phase formed in gamma-phase alloys by corrosion, cathodic electrolytic treatment, or cathodic bombardment with hydrogen ions. It will be remembered that it was found to be impossible to cause absorption of hydrogen in gamma-phase uranium-molybdenum alloys by heating in molecular hydrogen. However, if the alloy is first hydrided by corrosion testing, absorption of molecular hydrogen can readily be achieved. It has thus been found possible to measure

equilibrium pressures over samples of hydrided uranium-molybdenum. That the pressures are indeed equilibrium pressures was confirmed by noting the pressure obtained both on heating from a lower temperature and cooling from a higher temperature. Equilibrium is attained in a surprisingly short time, less than 24 hours at temperatures as low as 153°C. The vapor pressures and heats of formation have thus far been measured for two samples containing 900 and 2000 ppm hydrogen initially. The heats of formation observed for each composition differed, that for the latter being 5650 cal/mol H_2 , for the former 3700 cal/mol, and for UH_3 formed from alpha uranium, 20,500 cal/mol. These results would tend to indicate that the phase is not simply UH_3 in equilibrium with gamma uranium (the free energy of transformation of alpha to gamma uranium is of the order of 2000 cal/mol), and further that the system is not behaving as a simple two-component system. It is tempting to consider that stress must be considered as a state variable in this system. An experiment is described below in which a single crystal of gamma uranium-12 Mo is completely transformed to the epsilon phase by exposure to water for only 3 days at 650°F, apparently as a result of stresses induced by hydride formation; heating at this temperature in the absence of water would not cause even incipient transformation in many months. Note that polycrystalline samples do not transform after such exposure to water evidently because of the restraint afforded by neighboring grains but rather harden quite markedly. Thus a marked stress field must surround each hydride platelet precipitate and it is conceivable that this stress must be considered as one of the variables describing the state of the hydride system.

4. Development of U_3Si

Development is proceeding on the application of the epsilonized U-3.8% silicon composition as a reactor fuel. While sample elements made by coextruding a Zircaloy-2 clad over an epsilonized U_3Si core have survived, when tested through a defect drilled through the clad into the alloy meat, for over 33 days in 650°F water as reported by NMI, similar samples from the same extrusion tested at Bettis have failed in less than 14 days of testing. This material appears therefore to be plagued by the same variability in core-clad bonding conditions and sensitivity to segregation effects as was encountered in case of the gamma-phase alloys. In order to minimize bonding effects, the use of an aluminum alloy bonding layer appears promising. During the course of a sub-contract with Sylvania Electric Products Co., it was found that of all materials tested as intermediate layers between U_3Si and zirconium, only aluminum showed no bond line deterioration. These results have been confirmed at Bettis. Elements are presently being tested which consist of an aluminum bonding layer between the Zircaloy clad and U_3Si meat.

Preliminary corrosion results have also indicated that the corrosion rate of U_3Si may be substantially decreased by the addition of 0.2 w/o or less of Mo, Cu, or Nb.

5. Development of UO_2 fuel

The UO_2 program is notable thus far for the remarkable insensitivity of the material to conditions of exposure. Thus, no external or internal (other than gross cracking) evidence of damage has been noted as a result of thermal cycling, both in- and out-of-pile, irradiation (up to 5000 MWD/T), exposure to

water of composition reasonably close to that of FWR, etc. An in-pile test at Chalk River of a clad fuel element containing 90-94% dense slugs exposed both to irradiation and to water through a defect in the slug is still in progress after almost 4 months and 4000 MWD/T exposure. No acceleration of release of fission products has been noted during the course of the test and the level of fission product release is quite low and consistent with the surface of UO_2 exposed and available to yield fission recoils into the water environment. Apparently the waterlogging failures and excessive fission product release noted in the two previous Chalk River Tests arose from use of low density, improperly sintered samples.

I. U-3.8 w/o Si Alloy Development

A preliminary investigation of the corrosion properties of defected fuel elements prepared by coextrusion of the epsilon phase U_3Si alloy clad with Zircaloy-2 was carried out at WAPD about 1-1/2 years ago. The information obtained at that time indicated that the core alloy, itself, was extremely promising from a corrosion standpoint, corroding from the surface (without internal hydride formation) at the rate of 1 to 2 mg/cm²/hr. Extruded Zircaloy-2 clad samples, however, were subject to severe bondline attack in 650°F water, failures occurring in 7 days or less. At that time little work was done to investigate the bond problem in detail, because of the more promising results obtained on other uranium alloys. Recently, however, it was shown by Nuclear Metals Incorporated that defected Zircaloy-clad U_3Si will survive 36-40 days in 650°F water. This represented much longer life than had been experienced in the past and presumably reflected improvements in cladding technique as well as melting and heat-treating practice. It was also found recently that the interposition of an aluminum barrier layer between Zircaloy-2 and U_3Si greatly retards bondline corrosion. Samples made in this way by hot pressing techniques by Sylvania Electric Products Co., under subcontract to Bettis, survived 38 days in 650°F water. In view of these encouraging data, it was felt that the bonding problem should be investigated more fully in a program involving direct bonding and the use of various barrier layer materials.

A. U-3.8 w/o Si Coextruded with Zircaloy-2 Cladding

Two fuel elements were fabricated from induction cast, pre-epsilonized (800°C for 7 days) and coextruded material supplied by NMI. These elements were defected with 0.040" diameter holes and submitted for test in 650°F water. One element failed in 0-14 days. The failure appeared to be due to bondline attack since the cladding bulged and cracked near one end of the element. This was verified by testing a clad bare-end sample from the same rod. Severe bondline attack was observed within 24 hours. The other element failed in 14-28 days by splitting of the cladding from the defect to one end cap. NMI reported lives of 36 and 40 days for two other elements made from the same extrusion. These also failed by bondline attack, the cladding bulging and cracking 2" away from the defects. Metallographic examination of a longitudinal section from this extrusion revealed residual alpha uranium stringers which are known to have very poor corrosion resistance. Since the stringers were concentrated for the most part near the center of the rod, they are not considered responsible for the observed failures.

Three duplex-melted (induction-melted followed by consumable arc-melted) ingots, prepared by WAPD, were epsilonized for 7 days at 800°C and co-extruded with Zircaloy-2 cladding. Duplex melting techniques were employed to minimize alloy segregation. Extrusion temperatures of 1550, 1600 and 1650°F were used to investigate the effect of temperature on core-clad interdiffusion. Preliminary shearing tests indicated strong core-clad bonds. Defected fuel elements, bare and bare-end samples were prepared for corrosion tests in 650°F water. Early results on bare samples from the 1600°F extrusion indicate a one day corrosion rate of -1.58 mg/cm²/hr and a four day rate of -0.81 mg/cm²/hr. This extrusion, therefore, appears to have normal corrosion properties despite

the presence of some widely dispersed residual alpha uranium observed metallographically in the ingot prior to extrusion. Metallography of the extrusions is not yet complete.

An attempt was made to bond stainless steel (Type 304) to U_3Si by co-extruding at 1600 and 1650°F. This was unsuccessful due to poor extrusion properties of stainless at these temperatures. It was intended to use these extrusions in a study of stainless-steel to U_3Si bonds and to determine the effect of a non-hydrogen getter on the corrosion properties of defected elements.

B. U-3.8 w/o Si Extruded with Metallic Barrier Layers

The possibility of employing metallic barrier layers between Zircaloy-2 and U_3Si is being investigated using extrusion techniques. The purpose of the barrier is to prevent the formation of poorly corrosion resistant inter-diffusion zones between cladding and core. Several different high melting point barriers, including Nb, Mo, V, Ni, Cr and U-Nb alloys applied as foil, tubing or electro-deposited layers, are being considered. Two extrusions have been prepared with Nb and one with Mo barriers (applied as foil). Shear tests on these extrusions indicate strong clad-to-barrier and barrier-to-core bonds.

Preliminary corrosion results on bare-end samples of one of the extrusions with a Nb barrier indicated rapid fuel attack, within 24 hours, making observations on the bond behavior difficult. Rapid failure of the fuel resulted from the presence of relatively large amounts of alpha uranium and delta phases observed in the microstructure of the ingot despite epsilonizing for 7 and 14 days prior to extrusion. This is discussed more fully in the following section. A metallographic examination of the extrusions is being made prior to submitting fuel element samples, heat-treated in various ways to develop interdiffusion layers, to 650°F corrosion tests.

C. Epsilonization of Duplex Melted U_3Si Ingots

It is desirable in the case of co-extruded clad fuel elements, to homogenize and epsilonize the cast ingot structure prior to extrusion to avoid the necessity of a post-extrusion heat-treatment which will result in the formation of diffusion layers of poor corrosion resistance. The epsilonization treatment employed by Bettis and NMI, to complete the peritectoid reaction of alpha plus delta to form epsilon as previously indicated, is 800°C for 7 days. The peritectoid reaction occurs at 930°C. The effectiveness of this treatment, which is based on relatively limited data, is being investigated by metallographic examination of epsilonized ingots and subsequently extruded rods, correlating the results obtained with short time corrosion tests on bare ingot and rod samples as well as with silicon analysis of the ingots. The most desirable and corrosion resistant phase is known to be the epsilon, U_3Si phase. The presence of residual alpha uranium, delta (U_2Si_2) or both of these phases adversely affects corrosion resistance and is an indication of incomplete epsilonization or deviations from the desired U-3.8 w/o Si composition. The presence of residual alpha in the previously mentioned NMI extrusion and some of the Bettis epsilonized ingots, coupled with their poor corrosion properties, emphasized the importance of the epsilonizing heat treatment.

Metallographic examination has been completed on 13 ingots epsilonized 7 days at 800°C. The results are shown in Table I, along with silicon analysis and corrosion results available so far. While the data are far from complete, it is apparent that none of the ingots have a complete epsilon structure. The presence of alpha plus delta in three ingots indicates that the heat-treatment was not effective in obtaining an equilibrium structure. Photomicrographs of representative epsilonized ingots are shown in Figure 1, 2 and 3. A direct correlation between silicon content and residual phase can not be made at this time because of insufficient data and possible segregation in the ingots for which analyses are available. Two of the ingots failed by disintegration, within 4 days in 650°F water. These ingots contained a relatively large amount of residual alpha plus delta. The others survived, showing varying corrosion rates, despite the presence of residual constituents. More data is being collected for both silicon analysis and corrosion properties.

Because the heat-treatment was not effective in several of the ingots examined, an investigation was initiated to determine if it can be improved. This is being carried out on both cast ingot and extruded rod samples. Effectiveness of various heat treatments will be checked by metallographic, hardness and corrosion tests. X-ray analysis was previously found to be insensitive in identification of phases in the U_3Si alloys.

D. Clad U-3.8 w/o Si with an Aluminum Alloy Barrier

In addition to investigating direct bonding of Zircaloy-2 to U_3Si and use of high melting point barrier layers applied by extrusion and drawing techniques, the feasibility of employing a low melting point alloy barrier by casting or brazing techniques is being investigated. This possibility appears especially promising from a fabrication standpoint because it permits careful inspection of extruded bare fuel and cladding prior to assembly. It also permits further heat treatment on the core rod to ensure attaining a corrosion resistant structure prior to assembly. In preliminary tests an Al-6 w/o Cu alloy is being used because Al was found to be effective as a barrier in work conducted by Sylvania Electric Products and because the Al-Cu alloy has been found to have relatively good corrosion resistance in 680°F water.

To check the ease of formation and corrosion resistance of bonds between Al-6 w/o Cu and U-3.8 w/o Si, samples of Al-Cu clad rods have been prepared by two methods. The first method consisted of dropping a rod of U_3Si into a 1 in. diameter x 3 in. long graphite crucible filled with the molten aluminum alloy and subsequently cooling. The U_3Si clad with the Al-Cu alloy was then sectioned yielding open-end corrosion samples of U_3Si with an aluminum cladding about 0.25 in. thick. After corrosion testing 14 days in 650°F water the test was discontinued due to severe attack of the U_3Si . It was observed, however, that the bond between the U_3Si and the aluminum alloy was not preferentially attacked.

The second method used to produce Al-6 w/o Cu clad U-3.8 w/o Si samples consisted of multiple dipping of a U_3Si rod heated to about 500°C into the molten aluminum alloy until a cladding of about 0.030 in. was built up on the surface. Short time corrosion testing of open-end samples produced in this

~~CONFIDENTIAL~~

where C.D. is the current density in milliamps/cm² and W is in volts. It should be noted from Fig. 8 and equation (1) that the overvoltage is very high (unalloyed uranium = $0.94 \pm 0.28 \log \text{C.D.}$) and an inflection occurs at about 10^{-5} amps/cm². In as much as the relationship, if any, between overvoltage and corrosion properties is not known at this time, no particular significance can be attached to the high overvoltage observed other than that it is consistent with the fact that U₃Si forms neither an internal hydride nor an external UH₃ layer.

II. Gamma Phase U-Mo and U-Nb Alloys

A. Variability of Corrosion Properties of Unclad U-12 w/o Mo

The investigation of various factors affecting the variability of corrosion properties of unclad U-12 w/o Mo has been essentially completed. It was previously indicated that several of the factors investigated appear to be of secondary importance in regard to corrosion properties. These included initial hydrogen content, grain size, induction versus duplex melting, extrusion temperature and annealing atmosphere. To these can now be added surface stresses resulting from rapid cooling from the homogenizing temperature. As seen in Table III a sample quenched from 900°C in a helium blast has a lower 3 day corrosion rate (in 650°F water) than a similar sample quenched in the same way followed by machining 0.02" from the surface. This trend, however, does not continue with longer time tests, the rates becoming roughly the same. Thus, the stressed layer is very thin and has little influence on long time properties.

Variables which were previously found to be particularly important in improving corrosion resistance included elimination of microsegregation by thorough homogenization and low temperature annealing following homogenization. Additional data obtained on these variables are shown in Tables IV through VII, inclusive. These data essentially complete the study on variability and confirm the conclusions previously made. The results may be summarized briefly as follows:

1. Homogenization of billets prior to extrusion greatly improves the corrosion life of the extruded rods by eliminating stringer type segregation which has poor corrosion resistance (Table IV).

2. Homogenization subsequent to extrusion of rods made from billets which were prehomogenized sometimes results in an additional improvement in corrosion properties. The improvement in this case is small and does not always occur. On the other hand homogenization of extruded rods made from billets which were not prehomogenized, as expected, results in a marked improvement of corrosion properties (Table IV of WAPD-PMM-238).

3. An appreciable increase in thermal stability is realized by homogenizing billets prior to extrusion or rods after extrusion. Thermal stability was indicated by comparing the corrosion life of extruded rods before and after a low temperature annealing treatment at either 400 or 500 °C (Table IV).

4. Cold drawing, in amounts varying from 17 to 50%, does not appear to affect corrosion properties adversely. However, cold-drawn rods have poor thermal stability, failing rapidly in corrosion tests when subjected to a low temperature anneal. Homogenization after cold drawing improves the corrosion life (Tables IV and VII).

5. Maximum benefit in corrosion resistance is obtained by annealing 5 weeks at 400°C if the annealing treatment is carried out after the extrusions are homogenized even though the billets may have received a prehomogenizing heat treatment (Table V).

The reason for the need of homogenization just prior to annealing at 400°C for five weeks is not too well understood, but there is good reason to believe that it is connected with the transformation that occurs during the five week anneal. Fig. 9a-d show bright field and polarized light views of samples of a pre-homogenized extrusion when annealed at 400°C for five weeks both with and without a prior gamma-quench. The sample that was not gamma-quenched after extrusion shows a relatively fine grain size with some alpha precipitation at the grain boundaries and essentially complete transformation to epsilon within the grains. The grains of the specimen that received a gamma-quench after extrusion, are considerably larger (not visible in Fig. 9c or d), do not reveal any alpha precipitation at grain boundaries and indicate only slight transformation within the grains. The hardness of both specimens is about 460 DPH units. The metallographic appearance of these specimens after 14 days of corrosion testing is shown in Fig. 10a-d. Both samples have the short needles typical of annealed samples, but the non-gamma quenched specimen has additional large areas of very dense hydride located around the grain boundary precipitate.

6. Low temperature annealing (600 and 700°C) of extrusion made from billets which were not homogenized prior to extrusion reduces the corrosion life by widening of segregated stringer areas. Annealing at 800, 900 and 1000°C improves corrosion resistance by eliminating microsegregation (Table VI and Fig. 11).

7. A trend toward shorter corrosion life for long annealing times at 900 and 1000°C is indicated and is believed to be associated with solution of possibly beneficial precipitates such as small quantities (0.1 to 1 w/o) of Zr, Cu and W as were found in extrusion No. 1101-1-13 (Table VI and Fig. 11).

B. Corrosion of Extruded Clad Alloys

Investigation of the effect of homogenization prior to extrusion and cold drawing was continued for Zircaloy-2 clad U-12 w/o Mo. The tests have not progressed sufficiently far to indicate whether the beneficial effects of prehomogenization apply to clad as well as to bare samples.

The 650°F corrosion tests of defected clad fuel elements were continued to determine the feasibility of heat treating subsequent to extrusion (and without prehomogenization of the extrusion billets). The alloys being investigated include U-Nb and U-Mo alloys, with and without ternary Pt additions and binary U-Nb and U-Mo alloys with barrier layers between cladding and core. The corrosion data accumulated to date is indicated in Table VIII.

It appears that the corrosion life of as-extruded material is quite good, surviving 140 days test in most cases. In the case of U-Nb alloys indications are that homogenization at 900°C after extrusion may be successfully carried out for the U-12 w/o Nb alloy without developing interdiffusion layers with poor corrosion resistance. For the U-8 and 10 w/o Nb, however, the corrosion life in this condition is appreciably lower than that of as-extruded material. Samples aged for 5 weeks at 400°C, after homogenization, have survived 98 and 84 days test for the 10 and 12 w/o Nb alloys but early failures occurred in the U-8 w/o Nb alloy. Cold-drawn (60% RA) samples of these alloys

show very early failures indicating cold-work-induced transformation. Heat treatment improves the corrosion resistance of the cold-drawn samples, but life is generally shorter and more variable than that of as-extruded samples.

Since bare samples of U-Nb alloys had previously shown very poor corrosion resistance (0-3 day life) in the homogenized and aged condition because the gamma phase was transformed, the relatively good results shown for the clad samples heat-treated in the same manner was questioned. To check this 2 samples of U-8 and 10 w/o Nb, were removed from test after 56 days and examined metallographically at the defect. It was found that the defects, which were introduced after heat treatment, were not always drilled clear through the diffusion layer. This was noted with certainty for one of the two specimens examined as is seen in Figure 12. This apparently explains the unexpected long life for homogenized and aged samples. The high hardness of the diffusion layers is no doubt responsible for failure of the drill to penetrate to the core.

The addition of Pt to U-10 w/o Nb and to U-8 and 12 w/o Mo, designed to improve the corrosion resistance of the core alloy and of the core-clad diffusion zone, resulted in appreciable beneficial effects in certain conditions of fabrication and heat-treatment. However, the effects were not outstanding. The U-10 w/o Nb-1 w/o Pt alloy appears superior to the equivalent binary alloy in the cold-drawn condition but not appreciably better in other conditions. The U-12 w/o Mo-0.5 w/o Pt alloy is superior to the U-8 w/o Mo-1 w/o Pt.

Of the alloys containing barrier layers between core and cladding, the U-10 Nb with a Nb barrier is exhibiting the most promising results. The Nb barrier has apparently doubled the life in the homogenized condition. Poor life, however, is observed for homogenized and aged samples and for cold-drawn samples, reflecting transformation in the core.

The defect size used for corrosion testing clad fuel elements was arbitrarily set at 0.040" diameter. To investigate the effect of smaller and larger defects on corrosion life 20 as-extruded elements of U-12 w/o Mo are being corrosion tested in 650°F water, 4 of each with defects varying in diameter from 0.003" to 0.080". The results obtained so far, shown in Table IX, indicate that 3 of the 4 elements with 0.080" defects have failed in 70 to 112 days and 2 of 4 with 0.040" defects have failed in 84 to 98 days. All other elements have survived 112 days of test. The tests have not progressed sufficiently long to show whether the larger the area of fuel exposed, the shorter the corrosion life of the element.

C. Corrosion of Bare Ternary Alloys

Samples from arc-melted buttons of U-9 and 12 w/o Mo containing ternary additions of Pt in the range 0.3 to 1.2 w/o, have been in test in 650°F water for time periods up to 224 days. The corrosion results for these alloys are summarized in Table X. Several samples which survived 126 to 168 days of test were removed from test for observation of hydrogen content, metallography and hardness. Where duplicates of these were available, they were allowed to remain in test for an additional eight weeks and then examined. Table XI shows

~~CONFIDENTIAL~~
CONFIDENTIAL

the completed post-test observations.

From Table XI it is apparent that the U-12 w/o Mo alloys containing Pt absorb less than 1% of the corrosion hydrogen (assuming the reaction $U + 2 H_2O \rightarrow UO_2 + 2H_2$). Binary U-Mo alloys have been repeatedly shown to absorb about 20% of the corrosion hydrogen. Metallography confirmed the hydrogen analysis, samples containing over 20 ppm showing the presence of hydride needles. Thus, Pt does not seem to affect the solubility of hydrogen in the matrix or influence the mode of hydride precipitation, but greatly reduces the amount of absorbed hydrogen. The hardness of samples was much higher than would normally be expected from the hydrogen content. Since the specimens were exposed to 650°F (343°C) for over 150 days, some transformation of gamma may have occurred.

Corrosion tests on extruded bare samples of U-8 and -12 w/o Mo containing 1 and 0.5 w/o Pt, respectively, are shown in Table XII. The data obtained so far confirm previous conclusions that Pt additions to U-Mo alloys serve to improve corrosion properties in all conditions of heat treatment.

All arc-melted button samples of miscellaneous ternary alloys that survived over 100 days in 650°F water were removed for observation along with the U-Mo-Pt samples. The results are also reported in Table XI. The U-7 and -9 w/o Mo alloys with Ti and Cr additions show a hydrogen absorption of somewhat less than 10% (less than half of the equivalent binary alloy). The microstructure of these samples was unexpected. Despite the presence of 100 to 200 ppm of hydrogen, the samples showed practically no hydride platelets. However, a second phase, present as isolated globules, appeared in the gamma matrix. Figure 13 shows a typical microstructure. A single grain, isolated from the bulk sample, was examined by X-ray diffraction. This grain consisted of a gamma-epsilon matrix with alpha precipitated therein. The alpha was partially oriented with respect to the matrix. No hydride was detected. It would appear that the alpha influences the mode of hydride formation, probably picking up the major portion of the absorbed corrosion hydrogen.

The sample of U-10 w/o Zr-4 w/o Nb, listed in Table XI, absorbed only 1% of the corrosion hydrogen. This was unexpected since the distorted alpha structure, present in this alloy, normally is attacked by molecular hydrogen. The U-12 w/o Mo alloys containing 1 and 5 w/o Ru also absorbed very little hydrogen (less than 1%). Ru has the lowest neutron absorption cross section of the Pt group of metals.

D. Effect of Internal Stress on Corrosion of U-12 w/o Mo

The effect of a bending stress (95,000 psi) on the corrosion behavior of clad and defected U-12 w/o Mo fuel elements was continued. All samples, including one with a defect on the tensile side, one with a defect on the compression side and two unstressed samples have survived 112 days in 650°F water. No signs of failure or relaxation (as determined by tightness of samples in the bending jig) have been noted. The samples will be removed from test after 126 days and examined for evidence of hydride formation and orientation of hydride platelets. The survival of the stressed specimens indicates that macroscopic stress is probably not important in influencing corrosion behavior.

A bare U-12 w/o Mo specimen, stressed in bending to 95,000 psi, and heated for 450 hours in an inert gas atmosphere at 650 F was observed to have relaxed 56%. Two bare specimens, stressed in the range of 18 to 26,000 psi, are being corrosion tested for short time periods to verify previous findings that state of stress may influence the orientation of hydride platelets. This is also being checked on bare samples stressed in bending and cathodically treated at 100°C to resolve previously observed differences in the orientation of platelets formed in the two methods of test.

E. Effect of Water Additions on Corrosion of Bare U-12 w/o Mo

It was previously indicated (WAPD-PMM-238) that the addition of 50 ppm of Ni ions added to the water as NiSO_4 greatly reduces the amount of corrosion hydrogen absorbed by U-12 w/o Mo and improves corrosion life by a factor of 2. Similar additions of Pt ions, added as chloroplatinic acid containing a small amount of lead acetate also reduced hydrogen absorption but did not increase corrosion life. To determine if the presence of lead acetate was responsible for this, two samples were tested to failure in water containing this addition. Failure times were 35-42 and 42-49 days, as compared to 35-40 days for degassed water at 650°F. Thus, the lead acetate has no effect.

A second extrusion of U-12 w/o Mo was tested in degassed water and in water containing additions of 50 and 500 ppm of Ni^{++} added as NiSO_4 , 50 ppm Ni^{++} as NiCl_2 , 50 ppm of Pt as $\text{H}_2\text{PtCl}_6 + \text{Pb}(\text{AC})_2$, 50 ppm of Hg + as Hg_2SO_4 and 50 ppm of Pb $^{++}$ as $\text{Pb}(\text{Ac})_2$. Enough samples were added so that one could be removed each period for observation. Testing was not continued to failure of the specimens but only until an effect was observed.

The Hg_2SO_4 addition was not detrimental with respect to either corrosion rate or corrosion life, as it was suspected it might be since Hg has a high hydrogen overvoltage. It would appear that this addition may have been even beneficial. The amount of hydrogen absorbed per amount of weight lost is shown graphically in Fig. 14 for the Hg_2SO_4 and the other additions. It would appear that Hg_2SO_4 has a very slight inhibiting action on the hydrogen absorption. The other high hydrogen overvoltage addition was 50 ppm of Pb as $\text{Pb}(\text{AC})_2$ and it affected the corrosion of specimens in a manner almost identical with Hg_2SO_4 . Only one hydrogen analyses is presently available for specimens tested in the lead acetate solution but this indicates a hydrogen absorption similar to that in degassed water. Neither of these additions had much effect on those samples corroding with the high rates but they seemed to extend the life of the low rate samples by two test periods. The additions of metal ions having low hydrogen overvoltages are seen in Fig. 14 to exhibit the expected inhibiting action on the hydrogen absorption of specimens. Furthermore all behave in an identical manner even though, in the case of Ni ions, there is a difference of an order of magnitude in the amount of the metal ion present.

III. Basic Metal Alloy Development

A. Alloying Behavior of Uranium

1. Specific Heat Measurements on U-Base Alloys

To gain a better understanding of the alloying behavior of uranium, an apparatus has been constructed to measure specific heats and latent heats of transformation as a function of temperature during ordering of U-Mo alloys. The apparatus is patterned after that of C. S. Smith. A radial gradient furnace is placed inside a high vacuum unit. A constant heat flux independent of sample temperature enters the sample. Thus, the time taken by the sample to move through a given temperature interval is proportional to the heat absorbed by the sample. A vacuum of 10^{-5} mm of Hg is maintained to minimize gas contamination.

Calibration of the newly constructed apparatus is complete, desired sensitivity being obtained. A sample of 2S Al is being used to obtain an estimate of the percentage accuracy of measurements. The product of density and specific heat of 2S Al is roughly the same as that of the U-alloys to be tested.

U-Mo samples from 7 to 15 w/o Mo have been stepwise ordered from 560°C down to 400°C during a period of 181 days. These samples will be used to establish the position of the eutectoid reaction isotherm in the U-Mo phase diagram. Samples of 10 w/o Mo ordered at 400, 500, 550, and 600°C for 96 days will be used to determine the degree of equilibrium order as a function of temperature.

2. Resistivity of U-alloys at low temperatures

A liquid nitrogen cryostat is being constructed for making electrical resistivity measurements in the range -196°C to room temperature (intervals of 10°C). Data obtained will help to explain the low temperature electrical resistivity anomaly of U-Mo, U-Nb and U-Zr alloys.

B. Uranium-Base Alloys with Transition Phase Structures

Work is now in progress to determine the atom positions of the alpha prime phase found in a 5 w/o Mo-U single-crystal specimen water quenched from 900°C . The structure has been established to be base-centered orthorhombic with $a = 7.0 \text{ \AA}$, $b = 6.84 \text{ \AA}$ and $c = 3.42 \text{ \AA}$. From the density of this material, the unit cell was found to contain eight atoms.

C. Effect of Stress Upon Decomposition of Gamma Phase

An experiment is now in progress to determine the effect of stress upon the decomposition of the uranium alloy gamma phase. A 7 w/o Mo-U specimen, water quenched from 900°C , is being held at 400°C under dead weight loading in a creep machine. It was found that at stress levels of 20,000 psi and above, the creep curve became discontinuous or step-wise in nature. Although

the phenomenon has not been fully investigated, it appears that the time for the start of the discontinuities decreases as the stress level increases. Furthermore, when the specimen was loaded at room temperature and then heated, it was found that the discontinuities appeared at 100°C using a load of 50,000 psi.

Metallographic and X-ray examination of these specimens reveal that decomposition of the gamma phase has taken place. It appears that the application of stress greatly accelerates the transformation and alters the mode of transformation. Fig. 15 shows the structure of a 7 w/o Mo-U alloy annealed for 100 hours at 400°C under no stress and indicates sub-grain and grain-boundary precipitation. A specimen similarly annealed for 200 hours shows some additional broadening of the transformation product along the grain boundaries. A micrograph of a specimen held for 140 hours under stress at 400°C is shown in Fig. 16. As can be seen, the morphology of the transformation product is different from that of an unstressed specimen. The X-ray diffraction pattern of this structure reveals that not all of the alpha peaks are observed, and that those which are present are shifted from their normal positions. It is planned to study this transformation further and to determine the stability of the transformation product.

D. Corrosion Mechanism in U and U-Base Alloys

1. Magnetic Measurements on Hydrided U-Mo Alloys

Equipment is being constructed to measure the magnetic susceptibility of corrosion tested U-Mo alloys. The objectives of this experiment are the following:

- a. To compare the Curie temperature of the platelets with that for UH_3 .
- b. To determine the effects of Mo on the magnetic properties of UH_3 .
- c. To determine the solubility limit of hydrogen by detecting the initial formation of the ferromagnetic hydride.

The Curie method of measurement will be used, this requires that HdH/dx be a constant in the region in which the sample is suspended. In order to obtain this field configuration the pole pieces for the magnet have been machined as sections of a cylindrical surface for which $xy^2 = c$. An electrodynamic microbalance has been constructed for measuring the force on the sample when it is suspended in the magnetic field. The apparatus is being calibrated using bismuth as a standard. The field configuration is being verified by measuring the force on a bismuth sample as a function of position in the field.

2. X-ray Diffraction Measurements on Hydrided U-Mo Alloys

An experiment is in progress to verify the identification of platelets formed in corrosion tested U-Mo by means of X-ray diffraction from single crystals of the gamma phase. Previous X-ray work on corrosion tested

polycrystalline samples show only 3 or 4 weak and very broad lines at about the correct positions for UH_3 . The (110) reflection of the gamma matrix had been observed to be somewhat broadened and in one case to have been partially resolved into two lines. Back reflection Laue photographs of large grained samples showed that the spots were doubled after corrosion testing.

Large grains of the gamma phase of a U-12 w/o Mo alloy have been grown by annealing a selected billet at 900°C for four days. The orientation of the crystals was determined and cylinders about 20 mils in diameter and 100 mils long have been cut so that the cube axis is parallel to the cylinder axis. Weissenberg zero layer photographs were taken to verify that the sample was truly a single crystal. The samples were then corrosion tested at 650°F in degassed water for 3, 7 and 14 days.

The samples were examined by taking zero and "first" layer Weissenberg photographs. All the samples were completely transformed to the epsilon phase, there was no evidence for the original gamma matrix, alpha uranium or any extra spots which could be associated with the platelet phase. The 3 and 14 day samples showed 3 fully developed U_2Mo crystals, a C axis along each of the original cube axes. The 7 day test showed only 2 U_2Mo crystals. The transformation of gamma to U_2Mo causes a tripling of the unit cell in one direction so that the first layer line in a rotating crystal photograph of the gamma phase becomes the third layer line of the U_2Mo . A Weissenberg photograph was then taken of the true first layer which is then composed of superlattice reflections only; the predicted spots were again observed.

A re-examination was made of the X-ray results of corroded samples. A series of samples tested for 5, 10, 15, 20, 25 and 42 days were examined for the presence of the strongest normal lattice line of the U_2Mo phase by using the X-ray spectrometer. This line is about 0.75° in 2θ away from the (110) peak of the gamma phase. In no case was this line detected in these polycrystalline samples. It thus appears that the transformation in single crystals is greatly accelerated. A series of tests will be performed to determine if this effect is associated solely with the corrosion environment.

3. Identification of Hydride Phases Formed during Corrosion of Gamma Phase Alloys

An experiment is in progress to identify the hydride phase formed during hot water corrosion of U-Mo alloys. The experiment consists of measurement of the decomposition (hydrogen) pressure as a function of temperature over samples of 12 w/o Mo alloy which were gamma-quenched and then hydrided by autoclave corrosion treatment in 650°F water.

Preliminary measurements on a specimen which was corroded for 14 days with an estimated hydrogen concentration of about 900 ppm have been completed. The values closely approximate the relation:

$$\log P_{\text{mm}} = \frac{810}{T} + 4.275$$

as compared with:

$$\log P_{\text{mm}} = -\frac{4480}{T} + 9.20$$

for the equilibrium between hydrogen and alpha-uranium + UH_3 . Plots of $\log P$ versus $\frac{1}{T^{\circ}\text{K}}$ are shown in Fig. 17. Extrapolation of this plot reveals a pressure

of about 38 mm at room temperature for the U-Mo specimen. The value for alpha-U is 0.6 mm at 200°C . Decreasing the temperature revealed that some of the gas is reabsorbed, at perceptible rates even at room temperature, indicating reversibility of the reaction on a qualitative basis.

Measurements were then begun on specimens which were corroded for 21 days with an estimated hydrogen concentration of about 2000 ppm. These measurements, made on specimens with twice the surface area and with a higher hydrogen concentration than that of the 14 day specimen, revealed reproducible equilibrium pressures. However, the plot of $\log P_{\text{mm}}$ vs $\frac{1}{T^{\circ}\text{K}}$ obtained for the 21

day specimen has a higher slope than for the 14 day specimen. The pressures obtained at any given temperature were found to be the same in approaching equilibrium both by heating and cooling.

It appears from the above that much higher hydrogen pressures and lower heats of formation are associated with the decomposition of the corrosion hydride compared with pure UH_3 . The corrosion hydride, therefore, is different than pure UH_3 . Also, its heat of formation appears to be dependent on the amount of hydride formed during corrosion.

IV. Irradiation Effects - Uranium-Base Alloys

A. Pre-Post Tests of U-Mo Alloys

1. Bare U-Mo Alloys Irradiated in MTR to High Burnups (MTR-WAPD 12 Met 2, 3 and 6)

These experiments involved the irradiation of unclad samples of U-10.5, 12 and 13.5 w/o Mo for periods up to 36 weeks. A summary of the irradiation history of these three experiments is shown in Table XIII. Since the last Resume, flux values have been obtained from the aluminum-cobalt flux monitors, hardness results have been obtained on samples from two of the experiments, and density results have been obtained from the final group of samples.

The flux values from the Al-Co monitors (Table XIII) were much lower by a factor of two to five, than the expected nominal values supplied by MTR personnel. In addition, there was an unexpected large variation in the flux for the three groups of samples representing the three experiments, especially since the three groups were irradiated in various corners of the same reflector position (A-6) and were separated by only four inches.

The irradiation induced density changes of all of the samples are shown in Table XIII, and are plotted versus exposure in Fig. 18. The results indicate that with the exception of two samples, the density of the unclad specimens gradually decreases with increasing exposure and that the density changes are not appreciably affected by structure or composition in the ranges studied. The two specimens which did not follow this trend exhibited large density changes of the order of 7%.

The hardness results on two of the experiments are shown in Table XIV. As the center of the samples are at a higher temperature than the surface during irradiation the possibility existed that a change in structure may have occurred across the diameters of the samples. Hence, a hardness traverse was made on a section cut approximately $\frac{1}{4}$ " from the end of the 0.187 in. diam x 2.000 in. long specimens. With the exception of two samples, the hardness values had increased approximately 50 DPH units and was uniform across the diameter. A hardness variation of approximately 150 DPH units, however, was observed in the gamma quenched U-12 w/o Mo sample exposed to 3500 MWD/T and the epsilonized U-13.5 w/o Mo sample exposed to 3650 MWD/T. The hardness was a maximum at the surface (increase over pre-irradiation hardness) and a minimum (decrease over pre-irradiation hardness) at the center of these two samples. These are the same samples which showed the larger density changes in Fig. 18. At the present time, the reasons for the different behavior of these two particular samples is not clear. Metallographic examination (which is now in progress) may clear up the situation by revealing radiation induced porosity or transformation.

2. Irradiation of Transformed Specimens of U-Mo Alloys (MTR-WAPD 12-Met 4)

Twenty specimens of U-9, 10.5, 12 and 13.5 w/o Mo alloys, some of which were heat treated prior to irradiation so as to produce the transformation products α/ξ , were irradiated in the MTR for a maximum exposure of about 1800 MWD/T. These samples were returned to the Hot Laboratory and have been measured for changes in dimension and density and are currently being measured for changes in electrical resistivity, hardness and microstructure. The results obtained to date are summarized in Table XV and XVI and in Figures 19, 20 and 21. These results are discussed below:

a. Dimensions and Density Changes

The U-9 w/o Mo alloy specimens which were heat-treated to produce the α/ξ phase showed decreases in density of 1.0 and 1.3 percent after exposures of 1060 and 1660 MWD/T, respectively. One U-10.5 w/o Mo alloy specimen showed a density decrease of 0.4% after an exposure of 1820 MWD/T. No density or diametrical changes were found in the U-9 w/o Mo or U-10.5 w/o Mo alloy specimens irradiated in the gamma phase. The U-12 w/o Mo and U-13.5 w/o Mo alloy specimens showed no changes in diameter or density regardless of their prior heat-treated condition on neutron flux exposure. It is interesting to note that the density decreases in the U-9 w/o Mo alloy specimens are such that the transformed specimens after irradiation have density values close to that of gamma-quenched U-9 w/o Mo alloys. The difference in density values of U-10.5, 12 and 13.5 w/o Mo, between the gamma-quenched condition and the transformed condition, is small or negligible (see WAPD-PMM-238, Table XXVII, p. 79) and if phase transformation reversal occurred in these alloys no density changes would be noted.

b. Electrical Resistivity Results

The changes in electrical resistivity in liquid nitrogen of these specimens after irradiation are shown in Table XVI. The gamma-quenched U-9 w/o Mo alloy specimen showed a decrease in electrical resistivity at -196 C of 1.2% while the transformed specimens of U-9 w/o Mo alloy showed increases of 125% and 114% respectively. The same behavior was found in the U-10.5 w/o Mo alloy specimens with the gamma-quenched specimen decreasing 3% and the transformed specimens increasing 14.6% and 21.7%, respectively. In the U-12 and 13.5 w/o Mo alloy specimens, those specimens which were initially in the gamma-quenched condition and those which were slightly transformed by aging at 525°C for 8 hours and 48 hours respectively, showed decreases in electrical resistivity. However, those specimens which were more completely transformed prior to irradiation by aging at 525 C for 312 hours show appreciable increases in electrical resistivity. It is interesting to note that all specimens of the U-12 w/o Mo alloy appear to approach an equilibrium value of electrical resistivity of approximately 74 $\mu\Omega$ cm regardless of prior heat treatment, exposure and temperature in-pile. Similarly the U-13.5 w/o Mo alloy specimens appear to approach equilibrium at about 76 $\mu\Omega$ cm, the U-10.5 w/o Mo at 69-73, and the U-9 w/o Mo at 68-71 $\mu\Omega$ cm.

It was reported in WAPD-PMM-238 (p. 35) that the gamma-quenched samples of U-9, 10.5, 12 and 13.5 w/o Mo exhibit a negative temperature coefficient of electrical resistivity between -196°C to 150°C and that the transformed specimens of the same composition exhibit a positive temperature coefficient of electrical resistivity in the same temperature range. Electrical resistivity measurements on the irradiated U-9, 10.5 and 12 w/o Mo alloy specimens at 25°C and approximately 100°C have been obtained and these results are shown in Figures 19, 20 and 21. It may be seen in Figures 19 and 20 that the U-9 and 10.5 w/o Mo alloy specimens irradiated in the gamma phase exhibit a negative temperature coefficient after irradiation similar to that prior to irradiation. However, the positive temperature coefficient of electrical resistivity of the transformed specimens has reversed to a negative coefficient after irradiation. Figure 21 shows the same effect in the U-12 w/o Mo alloy specimens. In order to normalize these data in Figure 21 all the specimens were compared to their original value of electrical resistivity in the gamma-quenched condition at -196°C which is defined as ρ_0 . It may be seen that the behavior of these irradiated specimens cannot be duplicated by transforming unirradiated gamma-quenched specimens at 525°C . This is shown by the dotted line which is the relationship between resistivity and temperature for a specimen which was aged at 525°C for 76 hours.

c. Hardness and Microstructure

To date only one hardness determination has been made on a specimen of U-9 w/o Mo alloy which was heat-treated prior to irradiation at 525°C for 312 hours. This is shown below:

Specimen #A-7 (all measurements at 5 kilogram load)

Hardness in gamma-quenched condition	-	DPH 282
" after 312 hr at 525°C	-	DPH 424
" after exposure of 1660 MWD/T	-	DPH 299

It may be seen that the hardness of this specimen has reverted to that of the gamma phase condition. Unirradiated heat-treated control specimens which were held at 300°C for 6 weeks (the approximate maximum temperature of specimen A-7 in-pile) showed slight decreases in hardness of about 20 DPH numbers.

No alpha phase could be detected in the irradiated specimen by metallographic examination. A photograph of the transformed sample prior to irradiation is shown in Fig. 22a and that of the material after irradiation in Fig. 22b. Note that, in spite of the poor quality of the micrograph, no definite trace of transformation either at the grain boundaries or within the grains is noted. Subgrain and grain boundaries however are heavily delineated. If impurity precipitation occurred at such points, it would be expected that irradiation would affect their appearance differently from that of a transformed structure.

The results above show that the stable α/δ phase of U-9, 10.5, 12 and 13.5 w/o Mo alloys reverts back to the metastable γ phase after being subjected to neutron bombardment. The electrical resistivity behavior of these alloys is similar to that shown in order-disorder alloys after neutron bombardment in that the disordered phase (γ) slightly orders while the ordered phase (δ) disorders, both conditions approaching the same degree of disorder. It may be surmised that neutron bombardment of the ordered epsilon phase reverts it to the disordered gamma. Subsequently (or perhaps simultaneously) the free alpha uranium present is taken back into solution. An in-pile experiment is being planned in the Brookhaven Reactor in which resistance measurements will be made so that the kinetics of the $\alpha/\delta \rightarrow \gamma$ reaction can be determined.

3. Clad U-Mo Alloys

The two remaining control samples of as-extruded U-10.5 w/o Mo, cut from the same extrusion as the samples irradiated as MTR-WAPD 11- Met 1, have accumulated 296 days of test time in 650°F water without failure. Un-irradiated control samples, machined from the same extrusion and heat treated at 700°C for 40 minutes, failed in 88 days or less. All irradiated samples, which were in the as-extruded condition, failed in 57 days or less.

Corrosion testing in 650°F water of defected Zircaloy-2 clad specimens of U-9, 10.5, 12 and 13.5 w/o Mo alloys containing 5 w/o uranium-235, which had been irradiated to a maximum exposure of 17,300 MWD/T as experiments MTR-WAPD 11-Met 3 and Met 4, has been completed. Prior to irradiation, all of these specimens had been given a heat treatment of 750°C for $\frac{1}{2}$ hour. The completed corrosion results are shown in Table XVII. Corrosion testing of the two groups of control samples, as described in WAPD-PMM-238, has continued. The results to date are shown in Table XVIII. It is evident from these data that the 750°C for $\frac{1}{2}$ hour heat treatment is deleterious to the corrosion life of all four alloys. However, the decrease in corrosion life due to heat treatment is not sufficient to account for the poor corrosion life of the irradiated specimens. The irradiation data indicate that the corrosion life of at least the core-clad interdiffusion layer if not of the entire core material is adversely affected by exposure. The poor behavior of these samples is to be contrasted with the results for in-pile exposure to hot water described in Section B-1, below, in which four months exposure at interface temperatures in excess of 650 F caused no failures. It is possible that irradiation induced stability of the gamma phase improves in-pile corrosion behavior as compared with that noted out-of-pile.

Seventeen specimens of Zircaloy-2 clad 5 w/o enriched U-9, 10.5, 12 and 13.5 w/o Mo alloys, which were irradiated 13 months in MTR process water to an estimated maximum exposure of 40,000 MWD/T, have been returned from the MTR. The cladding of one specimen (U-10.5 w/o Mo, irradiated in the highest flux position) was split open longitudinally in several places. Close examination indicated that some plastic flow had occurred in the cladding prior to failure. Pre-post dimensional measurements of all specimens showed an increase in both length and diameter. The length changes were a maximum of 0.4%

~~CONFIDENTIAL~~

037029.030

for the U-9 w/o Mo alloy, and diminished as the molybdenum content increased to a maximum of 0.2% for the U-13.5 w/o Mo alloy. The diameters of all specimens increased; the maximum diametrical change being 2.3%. It is planned to examine the clad structure of the ruptured rod as well as the core structure of representative samples of each alloy. The volume increases of all specimens appeared to be dependent only on burn-up and amounted to about 4% at the maximum exposure (41,000 MWD/T).

Twenty clad specimens of natural U-9, 10.5, 12 and 13.5 w/o Mo, which were irradiated in the as-extruded condition to a maximum exposure of 1725 MWD/T as experiment MTR-WAPD 11-Met 10, are being corrosion tested in 650°F water. One sample of U-9 w/o Mo (295 MWD/T) failed in the 21-28 day test period. All others are continuing in test after 35 days.

The 24 samples of 5 w/o enriched U-Mo alloys, which make up experiment WAPD 11-Met 13, have been irradiated to a maximum exposure of approximately 10,000 MWD/T and returned to Bettis Plant. The irradiation of experiments WAPD 11-Met 14 and Met 15 is continuing.

Four specimens each of Zircaloy-2 clad 5 w/o enriched U-9 and 10.5 w/o Mo, which had been transformed to alpha plus epsilon and irradiated in MTR process water for three weeks to an estimated maximum exposure of 2000 MWD/T, have been measured for any dimensional changes due to irradiation. No significant changes were observed. Representative samples will be sectioned and examined metallographically for structural changes due to irradiation.

B. In-Pile Tests of U-Mo Alloys

1. Irradiation of Clad U-Mo Alloys in X-Rod Loop

Seven samples of Zircaloy-2 clad, 3.6 w/o enriched U-10.5 w/o Mo and one specimen of clad U-12 w/o Mo, which were irradiated to a maximum exposure of 1545 MWD/T in the Chalk River X-1 loop as experiment CR-WAPD-Met 4A, have been corrosion tested in 650°F static water. Three samples of the 10.5 w/o Mo group were defected prior to irradiation. Three samples failed in the 7-14 day test period, and the other five in the 14-21 day test period. No correlation of corrosion results with exposure, extrusion temperature, type of end closure, or defecting has been found. Twelve samples of U-10.5 w/o Mo and two samples of U-12 w/o Mo, which were fabricated from the same extrusions as the CR-WAPD-Met 4A specimens, were irradiated in MTR process water to a maximum exposure of 8830 MWD/T. These specimens were defected and corrosion tested in the same autoclave with the loop specimens. One specimen (12.0 w/o Mo-8830 MWD/T) failed in 0-7 days; two specimens (10.5 w/o Mo-4460 MWD/T and a control specimen) failed in the 21-28 day test period. All others are continuing in test after 28 days. No reason for the early corrosion failure of the loop specimens as compared to the better life indicated for the specimens exposed to MTR process water is apparent. Note that the defected samples exposed in the loop survived the approximate six weeks of exposure to water during irradiation.

Thirteen specimens of Zircaloy-2 clad U-11 and 12 w/o Mo, including one defected specimen, were discharged from the Chalk River X-3 loop July 21 after an exposure of approximately 4000 MWD/T. Water activity during the test was less than 2000 counts/ml. The specimen train has been disassembled and a visual examination of the specimens made. All specimens were covered with a uniform black crud. No apparent failure or bulging of any specimen occurred. Seven specimens fabricated from the same extrusions as the X-3 loop samples have been irradiated in MTR process water to an estimated maximum exposure of 5000 MWD/T. Pre-post dimensional measurements indicated no change as a result of irradiation. The specimens have been defected and will be corrosion tested with the samples from the loop test.

C. Tests of Other Alloys

1. Clad U-Nb Alloys

Two samples of Zircaloy-2 clad natural U-10 w/o Nb, irradiated to an estimated maximum exposure of 2000 MWD/T in NaK capsules in the MTR, are being corrosion tested in 650 F static water. These samples are from the same extrusion as an unirradiated, as-extruded sample which has been corrosion tested in 650 F static water 302 days without failure. The sample which was given a heat treatment of 900°C for 24 hours prior to irradiation, failed in 0-7 days. The sample which was irradiated in the as-extruded condition is continuing in test after 14 days.

Two experiments of Zircaloy-2 clad natural U-10 w/o Nb samples have been irradiated in MTR process water to an estimated maximum exposure of 2600 MWD/T. The first experiment (MTR-WAPD 11-Met 11) consisted of ten samples which were irradiated in the conditions shown below.

<u>No. of Samples</u>	<u>Fabrication History</u>	<u>Heat Treatment</u>
2	As extruded	800°C-4 hrs-W.Q.
2	As extruded	900°C-24 hrs-W.Q.
2	Extruded / cold swaged straightened	800°C-4 hrs-W.Q.
2	Extruded / cold swaged straightened	900°C-24 hrs-W.Q.
2	Extrude to $\frac{1}{2}$ " / cold drawn to 0.304	800°C-4 hrs-W.Q.

No significant changes in dimensions due to irradiation were observed. These specimens have been defected and corrosion tested in 650°F static water for 9 days without failure. They are continuing in test.

The second experiment (MTR-WAPD 11-Met 17) consists of twelve samples which were given various heat treatments prior to irradiation. Pre-post dimensional measurements indicated only minor changes due to irradiation. The dimensional data, together with the heat treatment conditions, are given in Table XIX. No correlation with degree of transformation, thickness of diffusion zone, or exposure is apparent.

0371228.0300

2. Unclad U-Nb Alloys

Seven specimens of unclad uranium-10 w/o Nb, which were given various heat treatments, have been irradiated in NaK capsules in the MTR to a maximum exposure of 1820 MWD/T. Changes in dimensions, density, and electrical resistivity are shown in Table XX, together with the exposures and pre-irradiation conditions.

The changes in dimensions and density for the gamma-quenched specimens are of the same order of magnitude as the changes found in U-Mo alloys given a similar exposure, while the changes shown for the aged specimens are greater than changes observed in transformed U-Mo alloys. Note that the direction of the changes are toward the gamma condition in the aged alloys since on transformation of gamma, density increases.

The electrical resistivity data have been plotted vs. temperature as shown in Figure 23. Measurements at intermediate temperatures will be made to assess the shape of the curves shown. It is to be noted that all the transformed specimens have changed toward the gamma-quenched condition. It has been suggested that irradiation causes a transformation of the products of aging to the gamma phase. The density data are in agreement with this theory. It was originally felt that this phenomenon was unique to order-disorder reaction alloys, such as U-Mo alloys. However, the U-Nb equilibrium diagram, as presently known, shows no order-disorder reaction.

Examination of the electrical resistivity data for the three gamma-quenched specimens indicates the probability of two competing reactions. These may be considered as a thermal transformation reaction tending to decrease resistivity and an irradiation reaction, tending to increase resistivity. For the specimen in the highest flux position and consequently at the highest temperature (F-3 of Table XX), the thermal transformation reaction appears to predominate, as the electrical resistivity is reduced and the temperature coefficient of electrical resistivity is reversed. For the specimen in the lowest flux position and consequently at the lowest temperature (F-5), the electrical resistivity has increased, indicating that the irradiation reaction is predominating.

These samples will be cut and examined metallographically for indications of phase changes.

3. U-Si Alloys

A pre-epsilonized extrusion of Zircaloy-2 clad U-3.8 w/o Si was received from Nuclear Metals, Inc. It was planned to irradiate half of this material in the clad condition and half with the cladding removed. However, bare corrosion samples from the nose, middle, and tail of this extrusion completely disintegrated in one day in 650°F water. The microstructure, shown in Figure 24 shows the presence of many alpha stringers and islands of delta, indicating incomplete epsilonization. An attempt will be made to completely epsilonize this material by heat-treatment. If this can be performed satis-

factorily, unclad specimens of this material will be irradiated. No clad samples of this extrusion will be irradiated as an epsilonizing treatment would also cause growth of the diffusion zone. Two additional extrusions of clad U-3.8 w/o Si have been received from Nuclear Metals, Inc., but as yet, the material has not been evaluated.

4. Cold Water Irradiation of Prototype Rod Fuel Elements
(CR-WAPD-Met 2A)

Prototype fuel rods of uranium and U-2 w/c Zr alloy with enrichments which varied from 0.7 to 5.5 w/o U-235 have been irradiated in the Chalk River NRX reactor to a maximum burnup of 8400 MWD/T and have been returned to the Bettis Hot Laboratory. At regular intervals during the irradiation, the rods were removed from the reactor and X-rayed so that changes in length of the rods were obtained. These results indicated that the U-2 w/o Zr alloy rods exhibited greater growth (approximately 1 to 3%) than the unalloyed uranium rods (approximately 0.1 to 0.5%). However, when dimensional measurements were made on the irradiated rods in the Hot Laboratory, it was found that the percent change in volume of the rods ranged from 1 to 3% and appeared to be independent of core composition, and prior heat treatment of the rods. However, there appears to be a trend toward increasing volume change with increasing exposure, amounting to about 4% at 7000 MWD/T.

Visual examination of these rods showed that the four rods irradiated to 7500 MWD/T or greater exposure exhibited transverse and longitudinal splitting of the cladding in the vicinity of the end cap weld. In addition, smaller longitudinal splits and bulges were observed in the middle of these specimens. No cladding failures have been observed in specimens irradiated to lower exposures, indicating that 7500 MWD/T may be the upper limit of exposure before the cladding is excessively stressed by expansion of the core alloy. A more thorough examination of all rods will be made to verify this observation.

037291030

V. Properties and Preparation of UO_2

A. Powder Preparation

Work was continued on the preparation of UO_2 by various methods for irradiation and fabrication tests as well as for investigations of the physical and chemical properties of the oxide itself.

1. Hydrogen Reduced UO_3

This method of preparation is used primarily to produce uniformly enriched UO_2 for irradiation tests since the properties of this oxide closely resemble those of the Mallinckrodt powder.

Recently the procedure employed in the preparation of this material was altered to conform more closely to that employed at Mallinckrodt. Whereas previously the uranyl nitrate solutions were dehydrated and denitrated in porcelain dishes, these operations are now carried out in electrically heated stainless steel ignition pots equipped with stirrers. Besides increasing production, the new procedure permits more controllable and uniform pyrolysis. X-ray examination of the UO_2 powders produced at WAPD reveals no fundamental crystallographic differences between them and the Mallinckrodt oxide.

In support of the irradiations and sintering programs, studies of the effect of the hydrogen reduction temperatures of the UO_3 on the O/U ratio of the resulting UO_2 were made. The hydrogen reduction temperatures were varied from 480 - 800°C. The results indicate that the higher the reduction temperature, the less the U(VI) content of the UO_2 and the more closely its O/U ratio approaches 2.00. The hydrogen reduction periods were varied from 2 to 50 hours and were not found to be critical.

2. Hydrogen Reduced U_3O_8

In view of British reports that UO_2 prepared from U_3O_8 as an intermediate yields a product considerably more active than that prepared from UO_3 , attempts were made to reproduce these results. The U_3O_8 was prepared by ignition of the lower uranium oxides in a muffle furnace at 800°C while the reduction to UO_2 was performed at 780°C for a 15 hour period. The UO_2 was brown in color and contained less than 1% U(VI). The physical properties and sintering characteristics of this material are now under study.

3. Activated UO_2

Study of sulfated UO_2 as prepared by Battelle has continued in an effort to determine the reasons for its superior sinterability.

Reanalysis of material prepared by reducing in hydrogen a ball milled slurry of Mallinckrodt UO_3 in sulfuric acid indicates that 100-200 ppm of sulfate are present in the UO_2 . Moreover, UO_3 prepared by digesting MCW UO_3 for two hours in a 1 N sulfuric acid, filtering, washing with alcohol, drying for 16 hours at 70°C in a vacuum oven, and reducing with dry hydrogen

at 780°C also contains 100-200 ppm of sulfate. However, it was also found that the activated powder contains approximately 2% U(VI) as compared to the normal material which contains only 1% U(VI), and that the particle size of the active powder is generally smaller than that of the normal material. Thus, it is not known what the contribution of the sulfate ion is to the superior sinterability. To determine this, MCW powder will be treated with 200 ppm of uranyl sulfate and the treated powder will then be compacted and sintered in the same manner as the activated powder.

4. Low Pressure Steam Oxidized UO₂

Considerable amounts of U₃O₈, indicated by chemical analyses as being present in UO₂ prepared by low pressure steam oxidation of uranium foils, were not detected by X-ray examination. In order to clarify this apparent discrepancy, mechanical mixtures of UO₂ and U₃O₈ were prepared and analyzed by the X-ray method. It was found that at least 10% U₃O₈ must be present in the UO₂ to be detected. Since U₃O₈ could not be observed in samples with O/U ratios as high as 2.2 (corresponding to 25% free U₃O₈) it can be inferred that at least a large part of the excess oxygen is homogeneously dissolved in the UO₂ lattice rather than being present as free U₃O₈.

5. UH₃ Studies

Since surface area and density measurements showed that preparations of UO₂ from UH₃ yielded an extremely fine, high-density material, kilogram quantities of this oxide were prepared for the sintering program. Two methods were employed in the conversion of the UH₃ to UO₂. One batch of UH₃ was decomposed at 300°C under vacuum and then steam oxidized at 400°C, while another was ignited to U₃O₈ and subsequently reduced with hydrogen at 860 - 920°C. These powders are now being analyzed for their uranium and oxygen contents.

6. Precipitation Studies

Work was continued on the preparation of UO₂ by various precipitation methods. The major effort for this period was expended in the study of the precipitation of ammonium diuranate by reaction of ammonium hydroxide, ammonium carbonate, and urea with uranyl nitrate. These represent three distinctly different modes of precipitation: ammonium hydroxide causes immediate precipitation, decomposition of urea results in slow precipitation as the ammonia is released, while ammonium carbonate first causes the precipitation of ammonium uranyl carbonate which is then decomposed by boiling to yield ammonium diuranate.

In spite of wide variations in precipitating conditions, microscopic examination of the crystals produced by precipitation with ammonium hydroxide showed a wide range of irregular shapes and sizes (1-600 microns) in every case. Crystals obtained from the urea solution varied somewhat in size but were more uniform in shape, being roughly spherical particles. However, X-ray analyses of these crystals revealed no fundamental crystallographic differences among them although a slight line broadening for the powder obtained by precipitation with ammonium hydroxide indicates that its

CONFIDENTIAL
0370280030

crystallite size is somewhat smaller than that of the others. Surface area, density and refractive index measurements of these samples are in progress.

Ammonium diuranate powders pyrolyzed at 500°C and subsequently reduced with hydrogen at 800°C for 24 hours oxidized to a blue-black material with an O/U ratio of 2.40 when removed from the reduction tube. An additional 24 hour reduction gave a more stable light brown powder with an O/U ratio of 2.15. These oxides are being studied in detail.

7. Carbon and Silica Doped UO₂

Studies designed to determine the sensitivity of sintered UO₂ compacts to various impurities were continued. A series of samples containing 100, 500, and 1000 ppm of carbon was prepared by soaking Mallinckrodt oxide in a dilute Aquadag suspension and drying in vacuo. This method is expected to yield a powder in which the carbon particles are dispersed throughout the UO₂. Attempts are being made to introduce the carbon more homogeneously by dissolving sugar in a uranyl nitrate solution such that the desired carbon content will be present after pyrolysis and reduction. In order to minimize the loss of carbon reduction will be carried out with carbon monoxide instead of hydrogen. Samples containing 500, 1000, 2500, 4000 ppm of silica have also been prepared by dissolving freshly prepared silicic acid in the acidified uranyl nitrate solution so that the desired amount of silica would be uniformly dispersed throughout the UO₂ on pyrolysis and reduction.

These powders have been compacted to approximately 65% of theoretical density by cold pressing in a tungsten carbide die at 175,000 psi. Pellets of each carbon and silica content have been sintered in atmospheres of argon and hydrogen at 1500°C. Analysis and examination of the specimens are now in progress.

B. Fabrication and Sintering of UO₂

Study of the relative importance of the various factors affecting the sinterability of UO₂ to aid in the determination of the sintering mechanism as well as to act as a guide in the preparation and selection of suitable powder is continuing.

The results obtained on a study of the effect of bulk density, particle size, oxygen-to-uranium ratio and pressure on the as-pressed density of compacts are given in Table XXI. These indicate that (1) the bulk density of the powder has little relation to the as-pressed density, (2) the size fraction of MCW has no marked effect on the pressed density, (3) although the effect is not marked it appears that the as-pressed density of compacts decreases somewhat with increase in oxygen-to-uranium ratio, (4) there is a considerable difference in the as-pressed densities of pellets produced from powders prepared by various methods.

In a study of the effect of pre-sintering on the sintered density of pellets, compacts were pre-sintered at 1000 and 1400°C for 1-1/2 hr in hydrogen and then sintered for 1, 5, and 10 hr at 1725°C in hydrogen. The density attained by the compacts after both of the above sintering treatments was closely comparable to the density attained by compacts sintered at 1725°C without pre-sintering treatment. It is therefore concluded that no advantage is gained by pre-sintering the UO_2 compacts.

On sintering compacts pressed at 50, 75, 100, and 125 tons/in² for 1, 5, and 10 hr at 1725°C, it was found that a density of 91% theoretical is obtained if the compacts are pressed at 100 tsi and sintered for 10 hr at 1725°C. It appears on extrapolation of the data that a density of 94% theoretical can be attained by UO_2 pellets sintered at 1725°C for 10 hr if they are compacted at 135 tsi. The data also indicate that a density of 92% theoretical can be obtained from a sintering treatment of 5 hr at 1725°C if the compacts are pressed at 125 tsi. The results are shown graphically in Figures 25 and 26. The degree of water absorption by pellets of different densities is shown in Figure 27. It will be noted that pellets having densities of 90% theoretical absorb approximately 0.5% water whereas those having densities of 94% theoretical absorb only 0.04% water.

Experimental work on the hydraulic extrusion method of producing integral length UO_2 fuel cores has included studies of plasticizers, lubricants and densifying agents. As a result of several preliminary experiments, it was decided to standardize on 1.0 w/o Methocel (methyl cellulose) as the plasticizer and 0.1 w/o Sterotex (a refined hydrogenated vegetable oil) as the lubricant.

Extrusion batches of ball milled UO_2 powder (milling time 15 hr) were prepared which contained the standardized quantities of plasticizer and lubricant as well as additions of ZrO_2 , TiO_2 , Cr_2O_3 , CaO , or $PbO-Bi_2O_3-SiO_2$ glass (nominal w/o 27-56-9). Each of the aforementioned densifiers was added separately to individual mixes in quantities varying from 0.1 w/o to 1.0 w/o. Sintering was done at 1600°C and 1725°C for 10 hr in hydrogen. The resultant densities are tabulated in Table XXII. Note that in no case was it possible to attain a density in excess of 84%.

C. Stability of UO_2 in Water

Long term tests on the stability of UO_2 compacts in high temperature water were continued. Some specimens have now been exposed for 28 days in 750°F steam while others have been exposed at 650°F for 43 days in degassed water, 42 days in water containing 25 cc H_2 /kg, and for 25 days in degassed water maintained at a pH of 10.5 with LiOH. No significant change has been found in either the appearance or weight of hydrogen-sintered, cold-pressed pellets. However, hot pressed compacts showed some surface reaction as evidenced by rough and chipped surfaces and by small amounts of powder deposited in the containers.

Sintered UO_2 compacts obtained from the Armour Research Foundation with minor additions of either ceric nitrate, uranyl nitrate or U_3O_8 , were tested in degassed water for 10 days and sintered compacts containing

03130003

1% and 5% ZrO_2 , obtained from the same source, were tested in water containing hydrogen for 15 days. All the compacts appeared unchanged after exposure and showed no significant weight changes.

Compacts exposed to water containing 25 cc O_2 /kg were observed after 17 days. These remained intact in spite of surface oxidation evidenced by the formation of a green-yellow scale. The compact cores were unaffected.

An experiment was performed to determine whether transport of UO_2 can occur in steam at high temperatures and pressures in the presence of a temperature gradient. This was done by subjecting loose UO_2 powder and sintered compacts contained in platinum crucibles to a flow of steam ($0.1 \text{ g H}_2\text{O}/\text{cm}^2\text{-min}$) at a temperature of 650°F and a pressure of 1000 psi. Although the compacts remained unchanged the powder samples lost weight due to what is thought to be physical carryover by strong steam currents. In view of the inconclusive results the experiment will be repeated under more favorable conditions. Clarification of this point is important due to the possibility of such a phenomenon occurring in a defective fuel element.

In connection with the determination of the sensitivity of sintered UO_2 compacts to various impurities, it was indicated in the previous resume' that a number of identical pellets sintered in argon in a carbon resistor furnace disintegrated on corrosion, whereas those resintered in hydrogen or sintered in hydrogen initially, remained intact. It was found on analyses of duplicate samples that pellets sintered in argon contained between 130 and 400 ppm of carbon and between 54 and 100 ppm of nitrogen while those resintered in hydrogen contained only 70 - 80 ppm of carbon and less than 10 ppm of nitrogen. The compacts initially sintered in hydrogen contained up to 30 ppm of carbon and less than 10 ppm of nitrogen. Analyses of hexavalent uranium and other impurities indicated no other differences to which the corrosion behavior can be ascribed. Thus, it can be concluded that nitrogen as well as carbon may also contribute to the desintering of UO_2 , and that sintering in hydrogen is effective in reducing the quantities of both. As indicated previously, a systematic program involving the doping of UO_2 with various amounts of impurities is being carried on in an effort to pin down the role of the impurities in causing the pellets to desinter.

D. Kinetic Studies

Studies of the rates of oxidation and reduction of UO_2 and U_3O_8 powders at 650°F in degassed water, in degassed water containing 100 cc H_2 /kg and in degassed water containing 25 cc O_2 /kg, were continued. Samples were removed after exposure periods of 5, 15, 25, 35, and 45 days and changes in oxygen content of the samples were determined.

On the basis of these analyses, it was concluded that:

1. UO_2 is relatively unreactive in water containing only the small concentrations of dissolved hydrogen present due to corrosion of the autoclave (approximately $0.1 - 0.5 \text{ cc H}_2/\text{kg}$). The composition of the UO_2 powder (initially $UO_{2.01}$) was $UO_{2.02}$ after a 45 day exposure. The oxygen-uranium ratio of the UO_2 exposed to 100 cc H_2 /kg for an equivalent period also increased by 0.01. It is felt that the increase in oxygen content is within the range of analytical error.

3. U_3O_8 is unreactive in degassed water. In water containing dissolved hydrogen, reduction proceeds at an approximately linear rate of $1.5 \times 10^{-2}\%$ oxygen content per hour. Preliminary X-ray evidence indicates that during the course of this reduction, the orthorhombic U_3O_8 phase is gradually transformed into the α -cubic phase of UO_2 .

Additional samples are now being exposed to 650°F water containing 2 cc O₂/kg and 5 cc H₂/kg. This will yield information on the effect of variations in gas concentration on the rates of oxidation and reduction

E. Surface Area and Density of UO_2 Powders

Table XXIII summarizes the data obtained to date.

Thus, the surface area values range from 22.6 m²/cc (NHOL-1) to 2.4 m²/cc (NOL-9). The range of measured densities is 10.13 (ANL powder) to 10.98 (NHOL powder).

It is expected that these powders of high density and high surface area will sinter at relatively rapid rates to high final densities. The extent to which such a correlation exists will be known when experiments on the pressing and sintering properties of these powders have been completed.

The measurements on the two sieve fractions of MCW powder indicate that they are similar in structure and that the large particles are apparently agglomerates of small ones. This conclusion is consistent with that based on microscopic examination.

Some preliminary measurements of surface area, using a simple air permeability apparatus have been made on UO_2 powders. A comparison of the surface area values obtained by the B.E.T. and permeability methods indicates that the latter method consistently yields low results, ranging from 50% to 3% of the B.E.T. value. The low results obtained by permeability are not unexpected because the equation used to calculate surface areas is based on a

CONFIDENTIAL

model consisting of spherical non-porous particles. UO_2 powders are not of this ideal type. The ratio of the B.E.T. and permeability values for a powder may be a measure of the porosity and angularity of the individual particles in the powder. Microscopic examination of the powders has, thus far, failed to yield information on this point.

A sample of MCW powder was heated in vacuo (10^{-6} mm Hg) at 1000°C for 24 hours. Although the real density was not appreciably changed by the treatment, the surface area was reduced to $1/3$ its former value. This indicates that the outer surface of the UO_2 becomes more regular in shape on sintering but that the amount of closed porosity is not appreciably altered. The same conclusion was reached on the basis of sintering studies performed on compacts. Several additional samples treated at higher temperatures are now being measured in an effort to substantiate this conclusion.

F. In-Pile Fission Gas Release Experiment

Final layouts of the apparatus for the determination of the rate of release of fission gases from uranium dioxide during irradiation have been approved by the authorities at Brookhaven, where the experiment is to be performed. The method to be used consists of collecting the emanated fission gases from a flat plate sample in a circulating stream of helium. Fabrication of the equipment has begun and it is expected that the first insertion will be made during the pile shutdown closest to October 17, 1955.

The present design uses a concentric tube arrangement to carry helium at low pressure and low flow rate into the pile, over the sample, and out to the analytical apparatus. The inner tube, which is removable through a special fitting at the pile face, carries the sample of UO_2 . This arrangement permits changing of samples during shutdown without disturbing the in-pile furnace assembly. The latter consists of a nichrome furnace winding, supported on fired lava around the outer concentric tube. The winding is surrounded by mineral fiber insulation, the whole being contained in a stainless steel shell. Thermocouples will record the temperatures of the interior of the specimen, the specimen surface, the furnace winding and the channel wall. Specimen temperature will be controlled by the input to the furnace and to some extent by the helium pressure and rate of flow.

The out-of-pile analytical section has two parts. One part is constructed to permit continuous 24 hour monitoring of the gas stream emerging from the pile by means of a gamma ray spectrometer focussed on one or more appropriate peaks of the spectrum. With this arrangement, surges of activity caused by pile power level changes, cracking of the specimen, etc., can be noted. The flow through this section will be accurately known, so that the emanation rate at the specimen surface can be calculated.

The other part of the analytical system consists of a series of traps in parallel, containing activated charcoal. Gas samples will be trapped in these traps at liquid nitrogen temperatures, and transferred quantitatively to a dilution system where aliquots of diluted fission gas can be measured out and analyzed completely by means of a second gamma ray spectrometer.

The specimen itself will be used as a fission monitor by analyzing it after completion of an experiment for Cs^{137} or other appropriate fission product.

G. Magnetic Susceptibility Studies

Magnetic susceptibility studies on uranium oxides, performed for WAPD at the Carnegie Institute of Technology for the purpose of gaining more information on the structure of non-stoichiometric uranium-oxygen compounds have been completed. An antiferromagnetic transition occurs in $\text{UO}_{2.00}$ at 29°K . This transition is destroyed as more oxygen enters the lattice. The slope of the susceptibility vs. temperature curve changes rapidly with oxygen content. Another effect, as yet unexplained occurs at 4°K . From the data, now complete, on the entire series of specimens ranging from $\text{UO}_{2.00}$ to U_3O_8 it can be concluded that the uranium is found in the form of U(IV) and U(VI) and not in the form U(V) .

A final report has been promised to WAPD by September 19, 1955.

H. Diffusion Studies

A critical survey of the unclassified literature on the equilibrium diagram and mechanism of oxygen and uranium diffusion in $\text{UO}_2\text{-O}_2$ system has been completed for Bettis by Prof. Carl Wagner of the Massachusetts Institute of Technology. This work was carried out to aid Bettis in the formulation of a program which will contribute to an understanding of the sintering mechanism of UO_2 and its behavior under irradiation.

Prof. Wagner recommended the use of solid electrochemical cells for the measurement of the mobility of uranium and oxygen in UO_2 by coulometric analysis at constant potential. Prior to undertaking this measurement, tracer studies will be made using U^{235} and O^{18} . This work will not be started until the in-pile fission gas experiment, discussed elsewhere, is well underway.

I. Zr - UO_2 Reaction

Work on the Zr-UO_2 reaction at Battelle has been completed. It was concluded from this work that the reaction of UO_2 with zirconium appears to take place without the formation of ZrO_2 . The UO_2 seems to be reduced by reaction with the zirconium and the reduced elements, oxygen and uranium, simultaneously diffuse into the zirconium. At 1300°F , the reaction proceeds at a measurable rate. However, the reaction below 1100°F is quite slow.

In one experiment a zirconium jacketed sandwich was heated for 23 days at 750°F and for an additional 75 days at 1100°F . The reaction zone was less than 0.0002 in. thick and the oxygen penetration appeared to be of the order of 0.015 in. as determined from hardness measurements. Another Zircaloy-2 jacketed sandwich was heated for 65 days at 1100°F and again only slight evidence of reaction was found.

It is estimated that a UO_2 fuel element jacketed with 0.030 in. thick zirconium would have a life of about 300 days when operating under isothermal conditions at 1300°F prior to diffusion of uranium and oxygen to the clad surface.

J. Thermal Conductivity of UO_2

A new proposal on the measurement of the thermal conductivity of UO_2 at high temperatures has been received from the Heat Transfer Section of the Armour Research Foundation. This supersedes the proposal submitted by the Minerals and Ceramics Department. It was indicated in the new proposal that, by modification of the apparatus constructed by the Ceramics Department, measurements having an accuracy of +5% can be obtained at temperatures up to 3000°F. Steps are being taken to obtain Atomic Energy Commission approval of this subcontract.

Construction of an experiment which will enable measurement of the center and surface temperatures of UO_2 compacts while under irradiation is in progress. These measurements will supplement those of the Armour Research Foundation and supply heat transfer data to the engineering departments more quickly than it would otherwise be possible. It is expected that the experiment will be inserted in the MTR at the end of October.

K. Sintering Additives

The subcontract with Armour on sintering additives has been renewed.

It was found that small additions of ceric nitrate enhances sinterability of UO_2 .

L. UO_2 Porcelains and Cermets

A subcontract has been initiated with Battelle for work on porcelains and cermets.

A paper study of the physical and chemical reactions of UO_2 with various possible additives is now in progress. This will act as a guide for the experimental work which is expected to commence by the middle of September.

The subcontract with Corning on the determination of the mechanical properties of UO_2 and their relation to thermal fracture is awaiting approval of the Atomic Energy Commission.

VI. UO₂ Irradiation Program

A new pre-post irradiation program is being planned with the aid of Naval and Westinghouse statisticians, Miss B. Day and Mr. W. Horton which, by the application of statistical methods, will yield a maximum amount of information with a minimum number of samples.

As the program would become overly complicated and cumbersome if all the variables were investigated at one time the program has been split into two parts. The first will cover the variables considered to be of most immediate interest whereas the second would follow shortly thereafter and cover the remaining items. The following variables were selected for examination in the first group of experiments: density, dimetrical clearance, grain size, oxygen-to-uranium ratio, burnup rate, and total burnup.

In order to insure the validity of the information obtained from the irradiation program it is essential that the specimens be uniform and reproducible, the burnup rates achieved during irradiation be uniform throughout the specimen, and that certain groups of specimens be irradiated simultaneously. Although some additional developmental work is necessary on the control of specimen grain size and oxygen-to-uranium ratio, it is felt that the condition of specimen uniformity can be adequately fulfilled. The simultaneous irradiation of a number of groups of specimens under uniform irradiation conditions is practically unattainable in the MTR. This facility is particularly unsuited for the execution of the proposed program since the steep axial flux gradient would cause the specimens to be burned up in a non-uniform manner and produce as much as 1000°C variation in the center temperature from one end of the $4\frac{1}{2}$ in. specimen to the other. Moreover, a maximum of 26 holes would be required during a several month period to carry out the program in the recommended manner. In view of the increasing demand for space in the MTR by other installations, it is doubtful whether the occupancy of the requisite space would be tolerated.

All of these difficulties can probably be circumvented by performing the irradiations in the Hanford piles. Since the process holes are very long, and the flux distribution is quite flat throughout most of their length, it should be possible to irradiate a large number of samples simultaneously under essentially uniform conditions without imposing an intolerable load on the facility. Nevertheless, certain limitations must be recognized in the utilization of this facility. As in the MTR, the heat flux generated in the sample must not exceed that which would cause boiling of the coolant. Although the coolant pressure in the Hanford piles is greater than that in the MTR, it still does not permit attainment of PWR heat fluxes if the irradiations are done directly in the process water. PWR conditions can be achieved by irradiation in NaK capsules without causing boiling due to the larger heat transfer surface provided by the capsules.

037028.030

1. MTR-WAPD-14 Met-1 Irradiation of Fused MCW UO₂

A section of one of the specimens from this experiment which had been irradiated in MTR to about 1000 MWD/T burnup has been subjected to static leaching conditions in an autoclave at 650°F and 2200 psi. The extent of fission product release into the water was determined periodically by measuring the gross gamma activity in small aliquots of the water. Within four hours after the initiation of the test, the activity in the water had reached a level which increased very slightly during the ensuing two week test period. Early in the second two week period, however, the activity in the water exhibited a more rapid rise concurrent with the appearance of a yellow-brown material in the water. The test was terminated after the second two week period. Analyses are now being made for representative fission products in the water, in the fuel, and on the autoclave walls. In addition, analyses for uranium will be made on a number of water samples in an attempt to determine whether fission products are removed from the UO₂ by leaching only, or if they are associated in part with the presence of UO₂ in solution or suspension in the water.

2. MTR-WAPD 14-Met 6
Irradiation of Hot Pressed MCW and Steam Oxidized UO₂

Four samples of steam oxidized and MCW UO₂ which were hot pressed to 90% of theoretical density, were discharged from the MTR on July 12, after an estimated exposure of 5000 MWD/T. Measurements of the samples indicate that no dimensional changes have occurred as a result of the irradiation. A measurement of fission gas release at various temperatures is now being made.

3. MTR-WAPD 19-Met 1 and 2
Irradiation Cycling of Steam Oxidized and MCW UO₂ Rods

The thirteen samples of UO₂ shown below have been irradiated for nine weeks in an MTR A-Piece cycler in a thermal neutron flux of 2×10^{14} nv. The samples were cycled into and out of a region of high neutron flux a maximum of 7500 times and received an estimated exposure of 2000 MWD/T.

<u>No. Samples</u>	<u>Material</u>	<u>Method of Fabrication</u>
5	Steam Oxidized	CPS
4	Steam Oxidized	Hot Pressed
2	Mallinckrodt	CPS
2	Mallinckrodt	Hot Pressed

All the specimens have been examined and dimensions measured. No significant dimensional changes were noted. In addition, microstructures have been obtained on one of each type of sample with the exception of the sample of Mallinckrodt cold pressed and sintered UO₂. Although comparisons with unirradiated specimens are not completed at the present time no obvious changes were observed in any of the examinations other than the presence of gross cracking in all of the samples which were examined metallographically.

A measurement has been made of the fission gas liberated from an 81% dense MCW UO_2 sample but the fraction of gases liberated cannot be calculated until the specimen has been dissolved and a total gas analysis has been completed.

4. MTR-WAPD-19-Met 4 Third MTR Irradiation Cycling Experiment

Eight natural Mallinckrodt UO_2 samples cold pressed with PVA as a binder and sintered in hydrogen to 92-94% theoretical density have been cycled under irradiation for twelve weeks in a thermal neutron flux of 1×10^{14} neutrons/cm²-sec. The purpose of the test is to determine the effect of fit and end cap clearance on full length specimens under simultaneous conditions of irradiation and thermal cycling. The samples were discharged on September 12, 1955 after being cycled approximately 10,000 times into and out of the high neutron flux region. The estimated maximum exposure is 1250 MWD/T. The specimens irradiated in this experiment are shown below.

<u>No. Samples</u>	<u>Length of Samples</u>	<u>Diametral Clearance</u>	<u>End Cap Clearance</u>
2	9 3/4 in.	0.0015 in.	press fit
2	9 3/4 in.	0.0015 in.	0.150 in.
2	9 3/4 in.	0.0030 in.	press fit
2	9 3/4 in.	0.0030 in.	0.150 in.

5. MTR-WAPD 19-Met 5 Fourth MTR Irradiation Cycling Experiment

Four full length UO_2 specimens enriched to 5.5 w/o uranium-235 have been irradiated in an A-Piece cyclor for fifteen weeks in a maximum thermal neutron flux of 4×10^{13} neutrons/cm²-sec. The specimens are similar to those irradiated in experiment MTR-WAPD 19-Met 4 with two exceptions: (1) the specimen length has been increased from 9 3/4 in. to 10 5/16 in and (2) the specimens are being irradiated at a considerably higher power generation rate.

These specimens will be discharged October 3, after having been cycled into and out of the region of high neutron flux for approximately 12,500 times. The estimated exposure based on reported MTR thermal neutron flux values will be approximately 10,000 MWD/T.

6. CR-WAPD-Met 4A Irradiation of U-Mo and UO_2 in Chalk River X-1 Loop

A small portion of the UO_2 specimen which had been exposed to water through a defect in this experiment was subjected to a static leaching test. The analyses for representative fission products in the water and on the autoclave walls, as well as for those retained in the fuel material have been completed. The results are shown below.

Isotope	Sr ^{89,90}	Y ⁹¹	Zr ⁹⁵	Ru ^{103,106}	Cs ¹³⁷
% Activity in H ₂ O	2.4×10^{-2}	2.5×10^{-3}	3.2×10^{-4}	9.8×10^{-3}	6.5×10^{-1}
% Activity on Autoclave Wall	3×10^{-2}	7×10^{-3}	1×10^{-4}	9×10^{-3}	--

The relative amounts of the fission products released from the fuel material were roughly proportional to their respective solubilities. It appears that cesium is leached very efficiently from the UO_2 . Since the specimen in question may have lost some fission products during irradiation, it is planned to subject a section of the undefected control specimen from this experiment exposed under the same conditions to a similar leaching test in order to estimate more accurately the extent to which fission products are released during irradiation from UO_2 .

7. CR-WAPD-Met 5
Second Irradiation of UO_2 in Chalk River X-1 Loop

The second X-1 loop experiment was terminated prematurely and showed marked release of fission products. Cross sections of the defected specimen showed a central void while a similar undefected specimen showed no void. Microstructures of these samples were compared with the microstructure of an unirradiated control specimen in an attempt to determine the cause of the void in the defected specimen. Although there appear to be some differences in structure these are obscured by the non-uniformity of the samples. An attempt will be made to define the differences by measurement of the variation in density and oxygen-uranium ratios within the samples.

The 4.7 w/o enriched, steam-oxidized UO_2 which was hot pressed to 95% theoretical density and which was irradiated in this test was punctured under vacuum, and the liberation of fission gases as a function of temperature was measured. Kr^{85} , Xe^{131m} and Xe^{133} were detected.

Samples were taken of gas liberated at room temperature ($27^\circ C$), gas liberated between $27^\circ C$ and $360^\circ C$, and gas liberated between $360^\circ C$ and $900^\circ C$. In taking the first 2 samples, the temperature was maintained until no further increases in activity could be detected in the gas-trapping system. In the case of the 3rd sample when no further activity could be detected, the specimen was cycled between room temperature and $900^\circ C$ several times to determine whether thermal cycling would liberate any additional gas. The results obtained are listed below.

<u>Nuclide</u>		<u>Per Cent Liberated as a Function of Temperature</u>			
		$27^\circ C$	$27^\circ C-360^\circ C$	$360^\circ C-900^\circ C$	Total
10.3-yr	Kr^{85}	0.9	5×10^{-3}	2×10^{-2}	0.92
12.0-d	Xe^{131m}	0.7	2×10^{-2}	9×10^{-2}	0.81
5.27-d	Xe^{133}	1.4	3×10^{-3}	9×10^{-2}	1.5

The apparent high yield for Xe^{133} is not considered significant as considerable error is involved in its analysis. This error results from difficulties in analyzing for this nuclide and in the long decay time between the completion of the irradiation and puncturing of the specimen.

In a similar experiment on a 74% dense specimen, the fraction of gas liberated at room temperature varied from 5 to 12 per cent. On the basis of this limited information, it appears that specimen density may be an important factor in the liberation of volatile fission products from UO_2 .

8. CR-WAPD-Met 7

Third Irradiation of UO_2 in the Chalk River X-1 Loop

This test, containing one high density defected cold compacted and sintered UO_2 specimen as well as five other similar but undefected samples, operated without appreciable change in level of coolant water activity prior to the shutdown of the reactor. These specimens will remain in test for one cycle after the estimated reactor startup on September 5. They will then be replaced by five specimens designed to give the following heat fluxes.

<u>No. of Samples</u>	<u>Heat Flux (Btu/ft² hr)</u>	<u>Defect</u>
1	5×10^5	None
1	4×10^5	None
1	4×10^5	0.005 in. hole
1	3×10^5	None
1	3×10^5	Longitudinal crack

These specimens will be fabricated by October 1 and will be scheduled for insertion in the loop in the latter part of October.

9. MTR-WAPD-19 Met.-3 - Rabbit Tests

Microstructures have been obtained from sample 26S, one of the six specimens which had been cycled in a small water filled autoclave into and out of a thermal neutron flux of 5×10^{13} nw. The microstructure was apparently unaffected by the irradiation but gross cracking was once more observed as on a number of specimens examined previously. It was also observed that a circumferential crack extended completely around the specimen near the outer periphery in addition to the radial cracks usually observed in the irradiated specimens.

10. MTR-WAPD-13-4 - HB-5

A cold pressed and sintered UO_2 fuel sample, enriched to 2.07 w/o uranium-235, was irradiated in a thermal neutron flux of 4.5×10^{13} nw in the MTR HB-5 loop facility for a six week period. During irradiation the specimen was cycled into and out of the reactor with a five minute holding time in each position for an estimated total of 4000 cycles. The specimen received an estimated burnup of 600 MWD/T.

The specimen was fabricated according to the following specifications:

Material - H_2 -decomposed UO_3
Enrichment - 2.07%
Density of UO_2 - 90%

Length of UO_2 - 2.99 in.
Diam of UO_2 - 0.3445 in.
Sintering Atmosphere - H_2
Sintering Temperature - 1750
Defect - None

The specimen will be returned to WAPD by the middle of September for post-irradiation examination. It will be replaced on October 3, by a similar specimen with a higher enrichment having a 0.005 in. defect.

11. Thermal Cycling

Six UO_2 fuel elements, 10.25 in. in length and fabricated according to the PWR reference design, have completed 100 cycles of a 5000 cycle test. The rods were cycled in a NaK filled chamber between the temperature limits of 550°F and 1050°F with a five minute holding time at each temperature and a thirty second transfer time. The dimensional changes observed after 100 cycled are shown in the table below.

Thermal Cycling Test of UO_2 Rods

<u>Rod #</u>	<u>Diametral</u>	<u>End</u>	<u>Change in Length (in.)</u>	<u>Warpage at Center (in.)</u>	
	<u>Clearance</u>	<u>Clearance</u>	<u>0-100 cycles</u>	<u>0 cycles</u>	<u>100 cycles</u>
TS-1	Empty	Clad	-0.001	0.038	0.0483
TS-3	0.0015	0	+0.003	0.021	0.0261
TS-5	0.0015	0.0085	+0.000	0.0279	0.0306
TS-6	0.0015	0.0175	+0.000	0.0095	0.0072
TS-7	0.003	0	+0.010	0.0103	0.0125
TS-8	0.003	0.0085	+0.007	0.0218	0.0258

As a result of an emergency shutdown, the rod samples were removed after 300 cycles. cursory examination of the specimens before the test was continued indicated that no appreciable change in warpage conditions had occurred over that observed at the completion of 100 cycles. The rods were replaced in the cycler and will be removed again for measurement at the completion of 500 cycles.

TABLE I

Metallographic Examination of U-3.8 w/o Si Ingots
Epsilonized 7 days at 800°C

<u>Ingot No.</u>	<u>Residual Phase Present and (Sample Location)</u>	<u>Silicon Content and (Sample Location)</u>	<u>Corrosion Rates mg/cm²/hr</u>
454	alpha (B)	3.83 (T)	-1.38*
458	alpha plus delta (B)	3.91 (B)	--
460	alpha plus delta (B)	3.75 (T)	D*
484	delta (T)	3.69 (B)	-0.81
504	delta (B)	3.85 (T)	-1.48
524	alpha plus delta (B)	Unavail (B)	D
530	delta (T)	Unavail (T)	-0.73
534	delta (B)	Unavail (T)	-0.59
536	cored alpha (T)	Unavail (T & B)	-1.35
538	delta (B)	Unavail (T & B)	-0.86
546	delta (B)	Unavail (T & B)	--
548	cored delta (T)	Unavail (T)	-1.03
556	cored delta (T)	Unavail (B)	--

* 4 day rate, D indicates disintegrated

T indicates top of ingot

B indicates bottom of ingot

TABLE II

Corrosion Properties of Various Uranium-Silicon Alloys in 650°F Degassed Water

<u>Alloy</u>	<u>Corrosion Rate (mg/cm²/hr) after</u>									
	<u>1 da</u>	<u>4 da</u>	<u>7 da</u>	<u>14 da</u>	<u>28 d</u>	<u>42 d</u>	<u>56 d</u>	<u>70 d</u>	<u>84 d</u>	<u>98 d</u>
U-3.8 w/o Si (A 119)	- 2.6	--	-2.45	-1.99	-1.63	-1.50	-1.48	dis.	--	--
U-3.8 w/o Si (J 155)	- 1.8		-1.70	-1.60	-1.40	-1.40	-1.30	-1.20	-1.10	dis.
U-3.8 w/o Si / 1.0 w/o Pt	-10.2	-11.6	-8.5	-4.7*						
0.5 w/o Pt	-15	- 6	-6	-4.4*						
0.2 w/o Pt	dis.	--	--	--						
1.0 w/o Mo	dis.	--	--	--						
0.5 w/o Mo	-1.20	-2.50	-2.90	-2.57*						
0.2 w/o Mo	-0.69	-0.53	-0.49	-0.54*						
1.0 w/o Cu	dis.	--	--	--						
0.5 w/o Cu	-0.89	-2.01	-2.64	-2.10*						
0.2 w/o Cu	-0.05	-0.32	-0.92	-0.77*						
1.0 w/o Nb	dis.	--	--	--						
0.5 w/o Nb	-1.04	-1.86	-2.20	-1.81*						
0.2 w/o Nb	-0.21	-0.19	-0.33	-0.56*						

* still in test

TABLE III

Effect of Surface Stress upon the Corrosion
Properties of a U-12 w/o Mo Alloy

<u>Condition</u>	<u>Corrosion Rate (mg/cm²/hr) after</u>			
	<u>3 da</u>	<u>7 da</u>	<u>14 da</u>	<u>21 da</u>
900°C/2 hr/He Quench	-0.20	-0.37	-0.60	-0.96
900°C/2 hr/He Quench / 0.020" removed from surfaces	-0.34	-0.40	-0.53	-0.77

TABLE IV

Effect of Homogenization Prior to Extrusion on the Corrosion
Characteristics of Extruded U-12 w/o Mo

Material from Ingot No. J 875

<u>Pre-extrusion Heat Treatment</u>	<u>Extrusion Condition</u>	<u>Post Extrusion Heat Treatment</u>	<u>Corrosion Life (days)</u>
None	A	None	14-21
"	A	I	7-14
"	A	J	56-70
1000°C-48 hr-F.C.	A	None	21-28
"	A	I	28-42
"	A	J	42-70
None	B	None	14-21
"	B	I	7-14
"	B	J	56-70
1000°C-48 hr-F.C.	B	None	35-49
"	B	I	14-28
"	B	J	56-70
None	C	None	14-21
"	C	I	7-14
"	C	J	56-70
1000°C-48 hr-F.C.	C	None	35-49
"	C	I	14-28
"	C	J	42-70

A - As-extruded to clad rod

B - As-extruded and cold-drawn 17%

C - As-extruded and cold-drawn 30%

I - 400°C-5 wks, W.Q.

J - 900°C/24 hrs, W.Q. plus 400°C/5 wks, W.Q.

~~CONFIDENTIAL~~
DECLASSIFIED

TABLE V

Effect of Homogenizing Prior to Extrusion on the Corrosion
Properties of Duplex Melted U-12 Mo

Pre- Ext. Treat.	Ext. Temp.	Extruded						Extruded / Gamma Quenched					
				400°C-5 wk		500°C-1 wk				400°C-5 wk		500°C-1 wk	
		X	Y	X	Y	X**	Y	X	Y	X	Y	X**	Y
None	1600	0.28	21-28	0.67	14-28	9.1	1-7	0.17	35-42	0.07	>56	0.13	1-7
		0.25	21-28			-	0-1	0.15	35-42			0.10	1-7
A	1600	0.34	28-35	0.55	42***	4.3	1-7	0.24	28-35	0.08	>56	0.26	1-7
		0.28	28-35			4.6	1-7	0.20	28-35			0.09	1-7
B	1600	0.31	28-35	0.65	42***	1.6	7-14	0.24	28-35	0.07	>56	0.08	7-14
		0.26	28-35			1.6	7-14	0.21	28-35			0.08	14-21
None	1900	0.22	21-28	0.66	14-28	1.5	7-14	0.19	35-42	0.08	>56	0.08	7-14
		0.22	21-28			1.2	7-14	0.16	28-35			0.03	7-14
A	1900	0.67	14-21	0.46	28-42	1.2	1-7	0.21	21-28	0.07	>56	---	0-1
		0.43	14-21			1.4	7-14	0.20	28-35			0.10	1-7
B	1900	0.9	14-21	0.35	42***	1.6	1-7	0.20	21-28	0.07	>56	0.28	1-7
		1.3	7-14			1.3	1-7	0.09	21-28			---	0-1
None*	1600	1.4	7-14	1.2	7-14	---	0-1	0.43	21-28	0.15	42-56	0.37	7-14
		0.5	14-21			---	0-1	0.43	21-28			2.9	1-7
A*	1600	0.4	21-28	0.5	28-42	1.7	7-14	0.46	21-28	0.20	42-56	0.18	1-7
		0.4	21-28			1.7	1-7	0.43	21-28			0.11	7-14

A - 900°C-24 hr-vac.-furnace cool

B - 1000°C-48 hr-vac.-furnace cool

X - weight loss in mg/cm²/hr after 7 days

Y - failure time in days

* - high carbons

** - one day rates

*** - removed due to severe attack

TABLE VI

Effect of Annealing Time and Temperature on
the Corrosion of Extruded U-Mo Alloys

<u>Condition</u>	<u>Corrosion Life (days) in 650°F Water</u>	
	<u>Extrusion</u>	<u>Pre-Extrusion</u>
	<u>No. 1101-1-13</u> <u>U-11.2 w/o Mo</u>	<u>No. J 959</u> <u>U-12 w/o Mo</u>
As extruded	14-21	28-35
600°C - 24 hr	7-14	14-21
72	7-14	21-28
168	7-14	14-28
336	7-14	14-21
504	7-14	14-21
700°C - 24	14-21	21-28
72	14-21	21-35
168	14-21	14-28
336	14-21	21-28
504	14-21	21-28
800°C - 4	28-42	42-49
24	28-42	28-35
72	42-56	35-42
168	28-35	28-35
336	28-35	28-35
900°C - $\frac{1}{2}$	> 84	49-56
4	> 84	42-49
24	49-56	28-35
72	70-77	35-42
168	21-28	21-28
1000°C - $\frac{1}{2}$	> 84	49-56
4	> 84	---
24	35-49	35-42
72	28-35	---
168	28-35	28-35

TABLE VII

Effect of Fabricating Conditions

Sample No.	Composition w/o		A		B		C		D	
			X	Y	X	Y	X	Y	X	Y
Mo 3a1-1	12	Mo	1.6	14-28	0.2	28-42	0.7	14-28	0.16	28-42
			1.6	14-28	0.2	28-42	1.2	7-14	0.16	28-42
Mo 3a1-3	12	Mo	1.5	7-14	0.4	28-42	2.5	7-14	0.07	7-14
			1.2	14-21	0.4	28-42	1.2	14-28	0.08	7-14
Mo 2a1-7	12	Mo	0.4	21*	0.13	42-56				
			0.5	21*	0.17	42-56				
Mo 3a1-2	10.5	Mo	1.2	7-14	0.15	98-112	1.3	7-14		
			1.3	7-14	0.14	42-56	0.9	14-28		
Mo 3a2-6	10.5	Mo	0.6	7-21	0.20	28-42	1.6	7-14	0.23	56-70
			0.6	7-21	0.16	42-56	1.0	14-28	0.23	56-70
Mo 3a2-8	10.5	Mo	0.9	7-21	0.23	28-42	0.6	1-7	0.02	14-28
			0.9	7-21	0.21	42-56	0.3	1-7	0.02	7-14
Mo 3a2-9	10.5	Mo	0.7	7-21	0.20	28-42	0.6	14-28	0.24	42-56
			0.6	7-21	0.30	14-28	0.6	14-28	0.24	42-56
Mo 3a2-10	10.5	Mo	0.7	7-21	0.21	28-42	1.8	7-14	0.28	28-42
			0.6	7-21	0.20	28-42	1.6	7-14	0.27	28-42
Mo 3a2-12	10.5	Mo	0.6	7-21	1.3	14-28	0.7	14-28	0.21	56-70
			0.5	7-21	0.28	14-28	0.7	14-28	0.25	56-70
Mo 3a2-13	10.5	Mo	1.2	7-14	0.29	14-28	0.3	14-28	--	0-3
			1.3	7-14	0.79	14-28	0.3	14-28	--	0-3

X - mg/cm²/hr at 7 days

Y - failure time (days)

A - As-extruded

B - Extruded / γ Q

C - As-cold drawn (50% RA)

D - Drawn / γ Q

* Samples discontinued due to the severe attack

TABLE VIII

Corrosion Life of Simulated Fuel Elements Tested in 343°C
Degassed Water with 0.040 in. Defect in Clad

<u>Alloy Content</u> <u>w/o</u>	<u>Sample</u> <u>Condition*</u>	<u>No.</u> <u>Samples</u>	<u>Corrosion Life</u> <u>Days</u>
8 Nb	A	1	> 140
	A	1	84-98
	B	2	56-84
	C	2	14-70
	D	4	0-14
	E	4	42-84
	F	4	0-56
10 Nb	A	4	> 140
	A	2	84-140
	B	6	28-70
	C	5	> 98
	D	8	0-14
	E	9	14-70
	F	6	0-98
	F	2	> 98
12 Nb	A	2	> 112
	B	3	> 112
	C	2	> 84
	D	4	0-56
	E	2	> 112
	E	3	56-84
	F	5	> 84
10 Nb-Nb Barrier	A	2	> 140
	B	2	> 140
	C	2	0-28
	D	4	0-14
	E	3	> 112
	E	1	56-70
	F	4	0-14
10 Nb / 1 Pt	A	3	> 140
	B	3	70-112
	C	3	14-98
	D	2	> 112
	E	2	28-84
	F	2	> 84

TABLE VIII (Contd.)

<u>Alloy Content</u> <u>w/o</u>	<u>Sample</u> <u>Condition</u>	<u>No.</u> <u>Samples</u>	<u>Corrosion Life</u> <u>Days</u>
8 Mo / 1 Pt	A	3	> 140
	B	3	14-28
	C	3	0-14
	D	4	0-14
	E	4	28-112
	F	4	0-14
12 Mo / 0.5 Pt	A	2	> 140
	B	2	70-140
	C	2	56-98
	D	4	0-14
	E	4	56-98
	F	2	> 84
	F	2	56-84
10.5 Mo-Nb Barrier	A	1	> 98
	A	2	70-98
	B	3	56-70
	C	2	28-42
	D	4	28-56
	E	1	> 112
	E	3	28-84
	F	5	0-14
10.5 Mo-Mo Barrier	A	1	> 112
	A	2	42-70
	B	3	42-56
	C	1	> 98
	C	2	14-56
	D	4	0-28
	E	1	> 112
	E	3	14-112
	F	4	0-28
10.5 Mo-10 Nb Alloy Barrier	A	1	70-84
	A	1	> 112
	B	2	28-42
	C	2	0-14
	D	4	0-56
	E	4	14-28
	F	4	0-14
	G	1	> 77
	G	1	35-49

*A - As Extruded

B - Extruded / 900°C/24 hr/W.Q.

C - Extruded / 900°C/24 hr/W.Q.

- / 400°C/5 wk/W.Q.

D - Extruded / Cold Drawn

E - Extruded / Cold Drawn /
900°C/24 hr/W.Q.F - Extruded / Cold Drawn / 900°C/
24 hr/W.Q. / 400°C/5 wk/W.Q.G - Extruded / Cold Drawn / 900°C/
10 min/W.Q.

TABLE X

Corrosion of U-Mo-Pt Ternary Alloys (Arc Melted Buttons) in 650°F Water

Composition w/o	A*		B		C		AC-2		C-2		D/2	
	X	Y	X	Y	X	Y	X	Y	X	Y	X	Y
9 Mo	0.58 0.51	14-28 14-28	0.13 0.15	14-28 14-28	0.52 0.93	7-14 7-14	- -	0-1 0-1	No data		- -	0-1 0-1
9 Mo 0.3 Pt	0.12 0.11	84-98 70-84	0.021 0.021	84-98 42-56	0.32 0.24	14-28 14-28	47 -	1-7 0-1	- -	0-1	- -	0-1 0-1
9 Mo 0.6 Pt	0.10 0.10	168* 168*	0.014 0.014	70-84 84-98	0.015 0.015	56-70 28-42	61 42	1-7 1-7	- -	0-1	- -	0-1 0-1
9 Mo 1.2 Pt	0.08 0.08	168* 224*	0.006 0.008	112-126 112-126	0.003 0.003	98-112 84-98	2.6 1.8	7-14 7-14	18	1-7	0.03 0.05	14-28 14-28
12 Mo	0.22 0.30	28-42 28-42	0.16 0.26	42-56 42-56	0.06 0.24	28-42 1-7	0.67 0.89	7-14 7-14	0.07	> 14	0.46 0.13	28-42 56-70
12 Mo 0.3 Pt	0.15 0.15	112-126 112-126	0.16 0.16	112-126 154*	0.063 0.063	98-112 154*	0.63 0.68	14-28 14-28	0.05	7-14	0.07 0.08	140-154 154-168
12 Mo 0.6 Pt	0.11 0.11	154-168 154-168	0.13 0.13	154* 210*	0.031 0.031	154* 182-196	0.36 0.40	28-42 42-56	0.01	1-7	0.04 0.07	140-154 14-28

A - As melted

B - 900°C/24 hr/W.Q.

C - 900°C/24 hr/W.Q. $\neq$ 400°C/7 da/W.Q.AC-2 - 400°C/35 da/W.Q. (No $\neq$ Q)C-2 - 900°C/24 hr/W.Q. $\neq$ 400°C/35 da/W.Q.D/2 - 900°C/24 hr/W.Q. $\neq$ 500°C/2 da/W.Q.X - Weight loss rate (mg/cm²/hr)

Y - Corrosion Life (days)

* - removed for observation

TABLE XI

The Post-Test Observations on Some U-Mo-Pt Ternary Alloys
And Some Miscellaneous Ternary Alloys

Composition w/o	Condition	Test Time Days	Wt. Loss mg/cm ²	ppm H ₂	% H ₂ Pickup	D.P.H.	Metallographic Appearance
9 Mo 0.6 Pt	As melted	168	440	140	3.6	541	Needles at grain boundaries
9 Mo 0.6 Pt	As melted	168	300	170	6.7	543	Needles at grain boundaries
9 Mo 1.2 Pt	As melted	168	224	39	1.9	517	Few needles at grain boundaries
9 Mo 1.2 Pt	As melted	224	256				
12 Mo 0.3 Pt	γQ	154	420	13	0.3	443	No change from γQ structure
12 Mo 0.6 Pt	γQ	154	327	14	0.5	356	No change from γQ structure
12 Mo 0.6 Pt	γQ	210	388				
12 Mo 0.3 Pt	γQ / 400°C/ 7 da	154	226	13	0.7	472	No change from pre-test structure
12 Mo 0.6 Pt	γQ / 400°C/ 7 da	154	171	11	0.7	481	No change from pre-test structure
12 Mo 0.3 Pt	γQ / 500°C/ 2 da	154	1070	805	8.4	456	Almost entirely hydrided
12 Mo 1 Ru	γQ / 400°C/35 da	126	140	11	0.8	432	Few needles in one isolated spot
12 Mo 5 Ru	γQ	168	447	9	0.2	426	No change from pre-test structure
7 Mo 0.6 Ti	γQ	154	308	196	7.5	590	Practically no needles. Isolated globules of alpha uranium in a gamma matrix.
7 Mo 1.0 Ti	γQ	154	242	205	9.9	625	Practically no needles. Isolated globules of alpha uranium in a gamma matrix.
7 Mo 1.0 Cr	γQ	154	144	93	7.3	625	Practically no needles. Isolated globules of alpha uranium in a gamma matrix.
9 Mo 0.6 Cr	γQ	154	209	151	8.7	536	Practically no needles. Isolated globules of alpha uranium in a gamma matrix.
10 Zr 4 Nb	γQ	126	845	118	1.1	545	No change from pre-test structure which was acicular distorted alpha.

TABLE XII

Corrosion Properties of Two Duplex Melted and Extruded
U-Mo-Pt Alloys in 650°F Degassed Water

Heat Treatment	U-8 Mo-1 Pt		U-12 Mo-0.5 Pt	
	X	Y	X	Y
As Extruded	0.32	77-91	0.32	77-91
	0.11	>133	0.32	77-91
As Cold Drawn	2.0	7-14	0.30	42-56
	2.1	7-14	0.31	42-56
Ext. $\nearrow$ $\searrow$ Q	0.02	42-56	0.08	>126
	0.02	42-56	0.06	>126
Cold Drawn $\nearrow$ $\searrow$ Q	0.26	70-84	0.05	>98
	0.22	70-84	0.06	42-56
Ext. $\nearrow$ $\searrow$ Q $\nearrow$ 400°C/7 days	0.10	7-14	0.03	1-7
	0.04	7-14	0.02	>98
Ext. $\nearrow$ $\searrow$ Q $\nearrow$ 400°C/21 days	-	0-1	0.02	1-7
	-	0-1	0.02	>98
Ext. $\nearrow$ $\searrow$ Q $\nearrow$ 400°C/35 days	-	0-1	0.01	>84
	-	0-1	0.01	56-70
Ext. $\nearrow$ $\searrow$ Q $\nearrow$ 500°C/2 days	-	0-1	0.03	>98
	-	0-1	0.06	>98
Ext. $\nearrow$ $\searrow$ Q $\nearrow$ 500°C/7 days	-	0-1	0.12	>28
	-	0-1	0.12	>28(discontinued)
Ext. $\nearrow$ $\searrow$ Q $\nearrow$ 500°C/21 days	-	0-1	0.19	7-14
	-	0-1	0.17	7-14
Ext. $\nearrow$ $\searrow$ Q $\nearrow$ 500°C/35 days	-	0-1	0.38	1-7
	-	0-1	0.22	1-7

X - Rate of weight loss in mg/cm²/hr

Y - Failure time in days

TABLE XIII

Irradiation Data - Unclad U-Mo Alloys

Sample No.	Composition	Thermal Flux nv x 10 ⁻¹³	Ratio		Irrad- iation Time Weeks	Exposure MWD/T	Temperature °C		Changes in Density
			Non-Thermal Flux	Thermal Flux			Center	Surface*	
81	U-13.5 w/o Mo	0.85	---		12	1350	152	114	-0.5
83	"	1.6	---		"	2250	231	166	-1.1
84	"	2.0	---		"	3200	273	193	-2.8
89	U-13.5 w/o Mo**	2.4	0.49		"	3650	309	217	-7.6
61	U-12 w/o Mo	2.3	0.26		"	3500	296	207	-6.7
63	"	1.5	0.13		"	2450	218	156	-2.1
64	"	0.75	0.18		"	1200	141	106	-1.1
85	U-13.5 w/o Mo	0.35	0.08		36	2050	101	80	-1.1
86	"	0.65	0.37		"	2900	130	99	-2.2
87	"	1.0	0.89		"	4700	174	128	--
90	U-13.5 w/o Mo**	1.3	0.90		"	5700	200	145	-4.1
65	U-12 w/o Mo	1.4	0.75		"	6100	209	151	-4.0
62	"	1.2	0.41		"	5250	189	138	-3.0
67	"	0.90	0.16		"	3950	157	117	-1.6
42	U-10.5 w/o Mo	0.60	0.11		24	1600	124	95	-0.9
43	"	1.1	0.23		"	3000	180	132	-1.6
45	"	2.0	0.32		"	5350	279	197	-2.7
47	"	3.4	0.30		"	8500	413	285	-3.5
48	"	3.5	0.28		"	8800	428	295	-4.4
50	"	2.1	0.27		"	5500	301	217	-2.3
51	"	1.0	0.26		"	2800	168	124	-1.4

* Specimens 0.187 in. diam x 2.000 in. long

** Samples 60% γ and 40% ϵ (by X-ray measurements) all other samples gamma quenched.

TABLE XIV

DPH Hardness of Unclad Irradiated U-Mo Samples

<u>Sample No.</u>	<u>Composition</u>	<u>Exposure MWD/T</u>	<u>Calculated Temp. °C</u>		<u>Post Irradiation Hardness</u>	<u>Change in Hardness</u>
42	U-10.5 w/o Mo	1600	95	124	315 ± 2	± 27 ± 5
43	"	3000	132	180	330 ± 4	± 42 ± 7
45	"	5350	197	279	355 ± 3	± 67 ± 6
47	"	8500	285	413	360 ± 5	± 72 ± 8
48	"	8800	295	428	366 ± 2	± 78 ± 5
50	"	5500	217	301	369 ± 4	± 81 ± 7
51	"	2800	124	168	329 ± 3	± 41 ± 5
83	U-13.5 w/o Mo	2250	166	231	412 ± 5	± 90 ± 9
89	U-13.5 w/o Mo*	3650	217	309	401 Surface	± 94
					372	± 65
					289	- 18
					283	- 24
					257 Center	- 50
					265	- 42
					300	- 7
					402	± 95
					406 Surface	± 99
					386 Surface	± 75
					303	- 6
61	U-12 w/o Mo	3500	207	296	289	- 20
					277 Center	- 32
					289	- 20
					367 Surface	± 58
63	U-12 w/o Mo	2450	156	218	390 ± 6	± 81 ± 11
64	U-12 w/o Mo	1200	106	141	365 ± 7	± 66 ± 12

* Indicated sample heat treated to 60% gamma plus 40% epsilon (by X-ray measurements). All other samples irradiated in the gamma quenched condition.

** Samples 0.187 in. diam x 2.000 in. long. Where only one value is given for a sample, no variation in hardness occurred across the diameter of the sample.

TABLE XV

Changes in Dimensions and Density of Irradiated U-Mo Alloys

Sample No.	Composition	Heat Treatment	Estimated Exposure (MWD/T)	Diameter (in.)			Density (g/cm ³)		
				Pre	Post	% Change	Pre	Post	% Change
A-6	U-9 w/o Mo	#1	1440	.1880	.1887	n.s.	17.35 $\pm$.01	17.34	0
A-8	U-9 w/o Mo	#4	1060	.1875	.1887	+0.6)	17.47 $\pm$.01	17.29	-1.0
A-9	U-9 w/o Mo	#4	.1660	.1870	.1882	+0.7)		17.24	-1.3
B-1	U-10.5 w/o Mo	#1	1220	.1880	.1888	n.s.	17.15 $\pm$.01	17.16	0
B-12	U-10.5 w/o Mo	#4	1660	.1880	.1880	0)	17.18 $\pm$.01	17.16	-
B-9	U-10.5 w/o Mo	#4	1820	.1870	.1874	n.s.)		17.11	-0.4

Notes:

1. All specimens of U-12 w/o Mo and U-13.5 w/o Mo having heat treatments #1 to #4 respectively showed no change in dimensions or density.
2. n.s. indicates an insignificant change.
3. Heat Treatments

#1 - 900°C in kinetic vacuum for 24 hours, water-quenched.

#2 - #1 plus 525°C in evacuated Vycor tubes for 8 hours, water-quenched.

#3 - #1 plus 525°C in evacuated Vycor tubes for 48 hours, water-quenched.

#4 - #1 plus 525°C in evacuated Vycor tubes for 312 hours, water-quenched.

TABLE XVI

Changes In Electrical Resistivity Of Irradiated U-Mo Alloys

Sample No.	Composition	Heat Treatment	Calculated Exposure (MWD/T)	ρ at -196°C		% Change			
				Pre	Post		R_8 at -196°C	ρ/ρ_8 at -196°C	
A 6	U-9 w/o Mo	#1	446	72.20	71.36	-1.2			
A 8	U-9 w/o Mo	#4	1060	31.17	70.81	+125			
A 9	U-9 w/o Mo	#4	1660	31.15	67.52	+114			
B 1	U-10.5 w/o Mo	#1	1220	74.48	72.22	-3.0			
B 12	U-10.5 w/o Mo	#4	1660	59.75	68.52	+14.6			
B 9	U-10.5 w/o Mo	#4	1820	59.74	72.68	+21.7			
C 6	U-12 w/o Mo	#1	183	76.41	74.15	-3.0	76.41	1.000	.9704
C 8	U-12 w/o Mo	#2	880	76.23	74.71	-2.0	76.62	.9949	.9751
C 9	U-12 w/o Mo	#2	1010	75.99	74.09	-2.5	76.50	.9933	.9685
C 15	U-12 w/o Mo	#3	366	75.62	74.46	-1.5	76.54	.9980	.9728
C 16	U-12 w/o Mo	#3	1500	75.70	74.85	-1.1	76.64	.9877	.9766
C 22	U-12 w/o Mo	#4	1370	70.15	73.03	+4.1	76.75	.9140	.9515
C 23	U-12 w/o Mo	#4	1370	69.67	72.98	+4.8	76.68	.9086	.9517
D 2	U-13.5 w/o Mo	#1	183	79.57	76.32	-4.1	79.57	1.000	.9592
D 14	U-13.5 w/o Mo	#2	880	78.20	76.56	-2.1	78.64	.9944	.9736
D 9	U-13.5 w/o Mo	#2	1010	78.77	76.33	-3.1	79.06	.9963	.9655
D 15	U-13.5 w/o Mo	#3	366	76.78	75.81	-1.2	78.88	.9734	.9611
D 16	U-13.5 w/o Mo	#3	1500	76.48	76.26	-0.3	78.77	.9709	.9681
D 22	U-13.5 w/o Mo	#4	1370	72.09	76.40	+6.0	79.75	.9034	.9580
D 24	U-13.5 w/o Mo	#4	1370	72.96	75.77	+3.9	79.18	.9214	.9569

Notes:

Heat Treatments

- #1 - 900°C in kinetic vacuum for 24 hours, water-quenched.
 #2 - #1 plus 525°C in evacuated Vycor tubes for 8 hours, water-quenched.
 #3 - #1 plus 525°C in evacuated Vycor tubes for 48 hours, water-quenched.
 #4 - #1 plus 525°C in evacuated Vycor tubes for 312 hours, water-quenched.

TABLE XVII

Corrosion Life of Irradiated Clad U-Mo Alloys

(Pre-Irradiation Heat Treatment - 750°C for 1/2 Hr)

<u>Sample No.</u>	<u>Composition</u>	<u>Estimated Exposure in MWD/T</u>	<u>Test Days in 650°F Water to Failure</u>
A 21	U-9 w/o Mo	7,100	21-28
A 24	U-9 w/o Mo	8,000	14-21
A 22	U-9 w/o Mo	8,900	14-21
A 23	U-9 w/o Mo	10,100	6-9
A 25	U-9 w/o Mo	12,500	14-21
A 26	U-9 w/o Mo	15,500	3-6
A 27	U-9 w/o Mo	17,000	0-7
B 21	U-10.5 w/o Mo	7,100	28-35
B 25	U-10.5 w/o Mo	8,000	21-28
B 22	U-10.5 w/o Mo	8,900	35-42
B 24	U-10.5 w/o Mo	9,500	26-33
B 23	U-10.5 w/o Mo	10,100	14-21
B 26	U-10.5 w/o Mo	12,500	15-16
B 27	U-10.5 w/o Mo	15,500	0-3
B 28	U-10.5 w/o Mo	17,000	0-7
C 22	U-12.0 w/o Mo	9,900	6-9
C 24	U-12.0 w/o Mo	10,100	9-14
C 21	U-12.0 w/o Mo	10,300	6-9
C 23	U-12.0 w/o Mo	10,300	14-21
C 29	U-12.0 w/o Mo	15,500	0-7
C 26	U-12.0 w/o Mo	16,000	0-3
C 28	U-12.0 w/o Mo	17,000	0-7
C 27	U-12.0 w/o Mo	17,300	0-3
D 23	U-13.5 w/o Mo	8,000	9-14
D 24	U-13.5 w/o Mo	8,900	14-21
D 22	U-13.5 w/o Mo	9,500	6-9
D 21	U-13.5 w/o Mo	10,300	6-9
D 27	U-13.5 w/o Mo	14,000	3-6
D 26	U-13.5 w/o Mo	16,000	0-7
D 25	U-13.5 w/o Mo	17,300	0-7

DECLASSIFIED

TABLE XVIII

Corrosion Life in 650°F Water of Clad U-Mo Alloys

(Control Samples for Experiments MTR-WAPD 11-Met 3 & Met 4)

<u>Sample No.</u>	<u>Composition</u>	<u>Treatment</u>	<u>Test Days to Failure</u>
12-7	U-9.0 w/o Mo	As Extruded	42-56
12-8	"	"	28-42
12-9	"	"	28-35
12-1	"	750°C - $\frac{1}{2}$ hr	14-28
12-2	"	"	14-28
12-3	"	"	21-28
2-7	U-10.5 w/o Mo	As Extruded	O.K. after 112 days
2-8	"	"	84-98
2-9	"	"	O.K. after 56 days
2-1	"	750°C - $\frac{1}{2}$ hr	42-56
2-2	"	"	56-70
2-3	"	"	35-42
3-9	U-12.0 w/o Mo	As Extruded	O.K. after 112 days
3-10	"	"	O.K. after 56 days
3-2	"	750°C - $\frac{1}{2}$ hr	56-70
3-3	"	"	42-56
3-4	"	"	35-42
9-7	U-13.5 w/o Mo	As Extruded	O.K. after 112 days
9-8	"	"	"
9-9	"	"	O.K. after 56 days
9-1	"	750°C - $\frac{1}{2}$ hr	28-42
9-2	"	"	28-42
9-3	"	"	28-35

TABLE XIX

Dimensional Changes of Irradiated Clad U-Nb Alloys

<u>Specimen No.</u>	<u>Condition</u>	<u>Exposure MWD/T</u>	<u>Pre Length in.</u>	<u>Post Length in.</u>	<u>% Change</u>
G 6	800°C-4 hrs / 700°F-5 wks	700	4.239	4.238	-0.04
G 7	"	2650	4.241	4.241	---
G 9	800°C-4 hrs / 750°F-5 wks	1500	4.236	4.239	+0.12
G 10	"	2525	4.249	4.249	---
G 12	800°C-4 hrs / 865°F-5 wks	2200	4.237	4.237	---
G 13	"	2100	4.239	4.231	-0.32
G 30	900°C-24 hrs / 700°F-5 wks	700	4.236	4.219	-0.68
G 31	"	2650	4.229	4.230	+0.04
G 33	900°C-24 hrs / 750°F-5 wks	1500	4.241	4.241	---
G 34	"	2525	4.237	4.237	---
G 36	900°C-24 hrs / 865°F-5 wks	2200	4.228	4.227	-0.04
G 37	"	2100	4.230	4.205	-1.00

TABLE XX

Physical Property Changes of Irradiated unclad U-10 w/o Nb Alloys

Specimen No.	F-3	F-4	F-5	F-22	F-19	G-4	G-1
Pre-Irradiation Condition	900°C- 24 Hrs- W.Q.	900°C- 24 Hrs- W.Q.	900°C- 24 Hrs- W.Q.	900°C- 24 Hrs+ 400°C- 2 Wks	900°C- 24 Hrs+ 450°C- 2 Wks	900°C- 24 Hrs+ 500°C- 2 Wks	900°C- 24 Hrs+ 550°C- 2 Wks
Exposure (MWD/T)	1820	1660	1220	222	446	1060	1660
Pre-Length (in.)	1.992	1.993	1.995	1.983	1.983	1.984	1.984
Post-Length (in.)	1.995	1.995	1.996	1.995	1.993	2.014	2.052
% Change in Length	+0.2	+0.1	+0.1	+0.6	+0.5	+1.5	+3.4
Pre-Density (gm/cm ³)	16.51	16.49	16.49	16.71	16.76	16.79	16.82
Post-Density (gm/cm ³)	16.49	--	16.50	16.55	16.58	16.53	16.47
% Change in Density	-0.1	--	+0.1	-1.0	-1.1	-1.6	-2.1
Pre-Elect. Resist. at 196°C	71.19	71.22	71.19	35.71	21.73	18.04	16.57
Post-Elect. Resist. at 196°C	61.55	69.96	72.64	58.99	41.58	34.20	27.76
% Change	-13.5	-1.8	+2.0	+65.2	+91.4	+89.6	+67.5
Pre-Elect. Resist at R.T.	65.59	65.76	65.66	52.22	44.24	41.56	40.14
Post-Elect. Resist at R.T.	63.87	66.12	68.54	63.67	58.26	53.44	50.27
% Change	-2.6	+0.6	+4.4	+21.9	+31.7	+28.6	+25.2

TABLE XXI

PACKING AND PRESSING CHARACTERISTICS

Powder	Bulk Density Vibrated %T	Pressed 0.410" Die Stearic Acid Die Lubricant			Oxide Treatment	
		12 1/2 T	15 T	17 1/2 T		
MCW #5 As-received size dist.	37.0	67.1 66.9	69.3 69.1	70.9 70.9	5.7 gm in die 3.6 gm in die	As-received MCW 5-2 oxide
MCW #5 +325 fraction	38.6	66.8	68.8	70.7		Sieved MCW 5-8 oxide
MCW #5 -325 fraction	32.5	67.3	69.3	71.4		Sieved MCW 5-3 oxide
MR 3	37.9	67.4	69.0	71.0		MCW 5-2 oxide all size fraction red in H ₂ 15 hr at 785°C O/U2.01
MO 28	35.8	65.9	67.6	69.6		MCW 5-2 oxide all size fraction oxidized to UO _{2.1}
MO 26	38.9	65.2	67.1	69.3		MCW 5-2 oxide all size fraction oxidized to UO _{2.2}
ANL	38.8	64.5	66.3	67.9		Prepared by Argonne by spray denitration
NURS 3-6	16.6	63.0	65.7	68.3		MCW UO ₃ ball milled in H ₂ SO ₄ , dried, ground to pass 100 mesh reduced 15.5 hr at 800°C H ₂
NURS 7-9	23.5	65.0	67.1	69.3		MCW UO ₃ digested in H ₂ SO ₄ , dried, ground to pass 100 mesh reduced 15.5 hr at 780°C H ₂
NOH-20	34.8	73.3	15 1/2 T 75.5	75.9		Uranium metal reacted with steam for 48 hr at 2200 psi and 343°C

TABLE XXII

<u>Densifier</u>	<u>Concentration (w/o)</u>	<u>Sintering Temp (°C)</u>	<u>Density (%TD)</u>
ZrO ₂	0.1	1600	70.3
ZrO ₂	0.2	1600	73.4
ZrO ₂	0.5	1600	74.7
ZrO ₂	1.0	1600	77.5
ZrO ₂	0.1	1725	72.9
ZrO ₂	0.2	1725	80.7
ZrO ₂	0.5	1725	75.1
ZrO ₂	1.0	1725	77.6
TiO ₂	0.1	1600	82.4
TiO ₂	0.2	1600	82.5
TiO ₂	0.5	1600	85.2
TiO ₂	1.0	1600	85.0
TiO ₂	0.1	1725	78.0
TiO ₂	0.2	1725	81.4
TiO ₂	0.5	1725	79.5
TiO ₂	1.0	1725	81.2
Cr ₂ O ₃	0.1	1600	75.2
Cr ₂ O ₃	0.2	1600	82.8
Cr ₂ O ₃	0.5	1600	79.4
Cr ₂ O ₃	1.0	1600	83.5
Cr ₂ O ₃	0.1	1725	80.5
Cr ₂ O ₃	0.2	1725	83.6
Cr ₂ O ₃	0.5	1725	81.8
Cr ₂ O ₃	1.0	1725	78.0
CaO	0.1	1600	70.1
CaO	0.2	1600	72.1
CaO	0.5	1600	72.3
CaO	1.0	1600	78.4
CaO	0.1	1725	76.7
CaO	0.2	1725	77.0
CaO	0.5	1725	75.4
CaO	1.0	1725	83.8
PbO-Bi ₂ O ₃ -SiO ₂ Glass	0.1	1600	77.4
PbO-Bi ₂ O ₃ -SiO ₂ Glass	0.2	1600	77.5
PbO-Bi ₂ O ₃ -SiO ₂ Glass	0.5	1600	80.9
PbO-Bi ₂ O ₃ -SiO ₂ Glass	1.0	1600	76.8
PbO-Bi ₂ O ₃ -SiO ₂ Glass	0.1	1725	81.3
PbO-Bi ₂ O ₃ -SiO ₂ Glass	0.2	1725	81.1
PbO-Bi ₂ O ₃ -SiO ₂ Glass	0.5	1725	80.5
PbO-Bi ₂ O ₃ -SiO ₂ Glass	1.0	1725	79.5
None		1600	58.6
None		1600	74.0
None		1725	65.8
None		1725	77.2

<u>Powder Designation</u>	<u>Powder Type</u>	<u>Density (g/cc)</u>	<u>Surface Area (m²/cc)</u>
MCW (1954)	Prepared in large batches by H ₂ reduction of UO ₃	10.15	6.2
MCW (1954) -325 fraction	-325 sieve fraction	10.19	6.2
MCW (1954) +325 fraction	+325 sieve fraction	10.27	6.4
NHOL-1	Prepared by low pressure steam oxidation of UH ₃	10.98	22.6
NURS-1	Prepared by H ₂ reduction of UO ₃ which had been treated with H ₂ SO ₄ and ball milled	10.68	17.5
NOH-18	Prepared by high pressure steam oxidation of uranium foil	10.92	12.9
ANL	Prepared from UO ₃ made by denitration in a fluidized bed	10.13	9.5
NOL-9	Prepared by low pressure steam oxidation of uranium foil	10.85	2.4

Fig. 1

U-3.8 w/o Si (nominal) ingot
No. 536 epsilonized 7 days at
500°C. Structure shows
epsilon (U_3Si) matrix with
residual alpha U.

Met. No. 2589 B2-1

500 X

Fig. 2

U-3.85 w/o Si ingot No. 504
epsilonized 7 days at 800°C.
Structure shows epsilon
(U_3Si) matrix with residual
delta.

Met. No. 2587 B2

500 X

Fig. 3

U-3.8 w/o Si (nominal) ingot
No. 524 epsilonized 7 days at
800°C. Structure shows
epsilon (U_3Si) matrix with
residual alpha U and delta
(U_3Si_2).

Met. No. 2588 B1

500 X

Fig. 4. Bond produced between Al - 6 w/o Cu and U - 3.8 w/o Si during hot dipping.

Acid Polish

Met No. 2640 B-1

250 X

Fig. 5. Bond produced between Al - 6 w/o Cu and Zircaloy-2 during vacuum casting.

Acid Polish

Met. No. 2615 B

250 X

Fig. 6. U-3.8 w/o Si + 0.2 w/o Mo. Annealed 1 week at 800°C.

Elect. Etch

Met No. 2623 B-1

500 X

Fig. 7. U-3.8 w/o Si + 1.0 w/o Mo. Annealed 1 week at 800°C.

Elect. Etch

Met. No. 2619 B-2

500 X

- 71 -

FIG. 8
CATHODIC POLARIZATION CURVES FOR EPSILONIZED U-3.8 w/o Si
IN BUFFERED PHOSPHATE SOLUTION

a

1986 B-1-1

250 X

b

1986 B-1-2

250 Pd

c

1987 B-1-1

250 X

d

1987 B-1-2

250 Pd

Fig. 9. Transformation of U-12 w/o Mo extruded samples on aging at 400°C for 5 weeks. For sample "a" (bright field) and "b" (polarized light) no pre-homogenization was employed prior to extrusion. For sample "c" (bright field) and "d" (dark field) the billet was homogenized prior to extrusion.

a

2429 B-1

250 X

b

2429 B-2

1000 X

c

2430 B-1

250 X

d

2430 B-2

1000 X

Fig. 10. Appearance of samples of Fig. 6 after 14 days test in 650°F water.

a

As extruded. Corrosion life in
650°F water = 14 to 21 days.

1688 B2-1

250 X

b

Extruded + 1000°C - 1/2 hr - W.Q.
Corrosion life = >84 days.

1700 B1-1

250 X

c

Extruded + 1000°C - 24 hr - W.Q.
Corrosion life = 35 to 49 days.

1702 B1-1

250 X

d

Extruded + 1000°C - 168 hr - W.Q.
Corrosion life = 28 to 35 days

1763 B1-1

250 X

Fig. 11. Effect of Annealing Time on the Structure and Corrosion Life of a U-11.2 w/o Mo Alloy.

a

2345 B-1

U-8 w/o Nb

100 X

b

2003 B-5

U-10 w/o Nb

100 X

Fig. 12. Effect of Corrosion after 56 days in 650°F water of 8 and 10 w/o Nb alloys annealed for 24 hours at 900°C and aged for 5 weeks at 400°C.

2049 B-3-2

1000 X

Fig. 13. The metallographic appearance of a gamma quenched sample of U-7 Mo - 0.6 Ti after 154 days of testing in degassed 650°F water. A selected area, showing the few needles that were present and some of the alpha precipitate. The alpha precipitate was more dense and of greater particle size in other regions of the sample.

THE INFLUENCE OF WATER ADDITIONS ON THE PERCENT HYDROGEN ABSORPTION BY SPECIMENS

FIG. 14

Fig. 15. 7 w/o Mo-U, 100 hr at 400°C, no stress

7284 A-1

150 X

Fig. 16. 7 w/o Mo-U, 140 hr at 400°C, 40,000 psi tensile stress.

2617 B-1-6

250 X

DENSITY CHANGE VS EXPOSURE UNCLAD U-Mo ALLOYS

TEMPERATURE INDICATED ARE THOSE
EXISTING IN THE CENTER OF THE
SPECIMENS BASED ON FLUX VALUES
OBTAINED WITH AI-Co MONITORS.

X - SAMPLES PARTIALLY TRANSFORMED
PRIOR TO IRRADIATION. ALL OTHERS
IN GAMMA-QUENCHED CONDITION.

FIGURE 18

CONFIDENTIAL

WAPD-PMM-262

FIGURE 19

EFFECT OF NEUTRON BOMBARDMENT
THE ELECTRICAL RESISTIVITY OF
U-10.5 % Mo ALLOY

FIGURE 20

EFFECT OF NEUTRON BOMBARDMENT ON THE ELECTRICAL RESISTIVITY OF U-12 W% MO ALLOYS

DECLASSIFIED

a

U-9 w/o Mo gamma quenched and aged
at 525°C for 312 hours.

1341 B-2-1

250 X

b

Same specimen as above after expo-
sure of 1660 MWD/T.

E-176

250 X

Fig. 22. Microstructure of Transformed U-9 w/o Mo
alloy prior to and after irradiation.

EFFECT OF IRRADIATION ON ELECTRICAL RESISTIVITY
OF U-10 W% NB

2612 B-2

a

250 X

2612 B-3

b

500 X

Fig. 24. Residual alpha (stringers) and delta phases in epsilonized (7 days at 800°C) and extruded U-3.8 w/o Si.

Relationship Between Compacting Pressure
and Sintered Density
Compacts Sintered at 1725°C

Fig 25

Relationship Between Compacting Pressure and Sintering Time at 1725°C

Fig. 26

CONFIDENTIAL

WAPD-PM-262

CONFIDENTIAL

CONFIDENTIAL