2

DOE/PC/90361--T7

**CATALYTIC FABRIC FILTRATION FOR SIMULTANEOUS NO_x
AND PARTICULATE CONTROL**

Quarterly Technical Progress Report
for the Period April 1 - June 30, 1992

DOE/PC/90361--T7

DE93 000645

by

Greg F. Weber, Project Manager
Sumitra R. Ness, Research Engineer
Dennis L. Laudal, Research Engineer
Grant Dunham, Research Specialist

Energy and Environmental Research Center
University of North Dakota
Box 8213, University Station
Grand Forks, ND 58202-8213

Contracting Officer's Representative: Ms. Felixa Eskey

for

U.S. Department of Energy
Pittsburgh Energy Technology Center
626 Cochran Mill Road
Pittsburgh, PA 15236-0940

August 1992

Work Performed Under Contract No. DE-AC22-90PC90361

MASTER

Se
DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

TABLE OF CONTENTS

	<u>Page</u>
LIST OF FIGURES	ii
LIST OF TABLES	vi
1.0 INTRODUCTION	1
2.0 SCOPE OF WORK	2
3.0 GOALS AND OBJECTIVES	3
4.0 ACCOMPLISHMENTS	4
4.1 Task 2 Design and Construct Test Unit	4
4.2 Subtask 3.1 Fundamental Testing	4
4.3 Subtask 3.2 Process Testing/Reverse-Gas System	5
4.3.1 Nitric Oxide Removal Efficiency	5
4.3.1.1 PTC-BV-423	5
4.3.1.2 PTC-BT-424	11
4.3.1.3 PTC-BU-425	14
4.3.1.4 PTC-IL6-426	16
4.3.1.5 PTC-IL6-427	23
4.3.1.6 PTC-IL6-428	24
4.3.2 Particulate Collection	30
4.3.2.1 Run PTC-BV-423	30
4.3.2.2 Run PTC-BT-424	41
4.3.2.3 Run PTC-BU-425	41
4.3.2.4 Run PTC-IL6-426	41
4.3.2.5 Run PTC-IL6-427	52
4.3.2.6 Run PTC-IL6-428	56
4.3.3 Summary of Reverse-Gas Baghouse Test Results	56
4.4 Subtask 3.3 Process Testing/Pulse-Jet System	68
4.5 Subtask 3.4 Fabric Durability Testing/Pulse-Jet System	68
5.0 KEY PERSONNEL STAFFING REPORT	71
6.0 REFERENCES	71

LIST OF FIGURES

<u>Figure</u>	<u>Page</u>
1 NO _x removal efficiency as a function of time, Run PTC-BV-423	8
2 NO _x removal efficiency as a function of air-to-cloth ratio and ammonia/NO _x molar ratio, Run PTC-BV-423	10
3 NO _x removal efficiency as a function of time, Run PTC-BT-424	12
4 NO _x removal efficiency as a function of air-to-cloth ratio and ammonia/NO _x molar ratio, Run PTC-BT-424	14
5 NO _x removal efficiency as a function of time, Run PTC-BU-425	15
6 NO _x removal efficiency as a function of air-to-cloth ratio and ammonia/NO _x molar ratio, Run PTC-BU-425	18
7 NO _x removal efficiency as a function of coal type and air-to-cloth ratio	19
8 NO _x removal efficiency as a function of time, Run PTC-IL6-426	20
9 NO _x removal efficiency as a function of time @ 550°F, Run PTC-IL6-428	22
10 NO _x removal as a function of baghouse temperature	22
11 NO _x removal efficiency as a function of time, Run PTC-IL6-427	25
12 NO _x removal efficiency as a function of time, Run PTC-IL6-428	28
13 NO _x removal efficiency as a function of air-to-cloth ratio and ammonia/NO _x molar ratio, Run PTC-IL6-428	29
14 Respirable mass emissions as a function of time at an air-to-cloth ratio of 2 ft/min, Run PTC-BV-423	31
15 Respirable mass emissions as a function of time at an air-to-cloth ratio of 4.1 ft/min, Run PTC-BV-423	31
16 Respirable mass emissions as a function of time at an air-to-cloth ratio of 1.5 ft/min, Run PTC-BV-423	32

TABLE OF FIGURES (continued)

		<u>Page</u>
17	Respirable mass emissions as a function of time at an air-to-cloth ratio of 3 ft/min, Run PTC-BV-423	32
18	Respirable mass emissions as a function of time at an air-to-cloth ratio of 2 ft/min, Run PTC-BV-423	33
19	Respirable mass emissions as a function of time at an air-to-cloth ratio of 2 ft/min, Run PTC-BV-423	33
20	Respirable mass emissions as a function of time at an air-to-cloth ratio of 1.5 ft/min, Run PTC-BV-423	34
21	Respirable mass emissions as a function of time at an air-to-cloth ratio of 2 ft/min, Run PTC-BV-423	34
22	Respirable mass emissions for east and west reverse-gas baghouse chambers, Run PTC-BV-423	40
23	Baghouse differential pressure as a function of time, Run PTC-BV-423	40
24	Respirable mass emissions as a function of time at an air-to-cloth ratio of 2 ft/min, Run PTC-BT-424	42
25	Respirable mass emissions as a function of time at an air-to-cloth ratio of 2 ft/min, Run PTC-BT-424	42
26	Respirable mass emissions as a function of time at an air-to-cloth ratio of 4.2 ft/min, Run PTC-BT-424	43
27	Respirable mass emissions as a function of time at an air-to-cloth ratio of 3 ft/min, Run PTC-BT-424	43
28	Respirable mass emissions as a function of time at an air-to-cloth ratio of 1.6 ft/min, Run PTC-BT-424	44
29	Respirable mass emissions as a function of time at an air-to-cloth ratio of 1.5 ft/min, Run PTC-BT-424	44
30	Respirable mass emissions as a function of time at an air-to-cloth ratio of 2.1 ft/min, Run PTC-BT-424	45
31	Respirable mass emissions as a function of time at an air-to-cloth ratio of 2.1 ft/min, Run PTC-BT-424	45
32	Baghouse differential pressure as a function of time, Run PTC-BT-424	47

TABLE OF FIGURES (continued)

		<u>Page</u>
33	Respirable mass emissions as a function of time at an air-to-cloth ratio of 2 ft/min, Run PTC-BU-425	47
34	Respirable mass emissions as a function of time at an air-to-cloth ratio of 2 ft/min, Run PTC-BU-425	48
35	Respirable mass emissions as a function of time at an air-to-cloth ratio of 4 ft/min, Run PTC-BU-425	48
36	Respirable mass emissions as a function of time at an air-to-cloth ratio of 4.1 ft/min, Run PTC-BU-425	49
37	Respirable mass emissions as a function of time at an air-to-cloth ratio of 3.1 ft/min, Run PTC-BU-425	49
38	Respirable mass emissions as a function of time at an air-to-cloth ratio of 3 ft/min, Run PTC-BU-425	50
39	Respirable mass emissions as a function of time at an air-to-cloth ratio of 1.5 ft/min, Run PTC-BU-425	50
40	Respirable mass emissions as a function of time at an air-to-cloth ratio of 1.5 ft/min, Run PTC-BU-425	51
41	Respirable mass emissions as a function of time at an air-to-cloth ratio of 2 ft/min, Run PTC-BU-425	51
42	Baghouse differential pressure as a function of time, Run PTC-BU-425	53
43	Respirable mass emissions as a function of time at an air-to-cloth ratio of 2 ft/min, Run PTC-IL6-426	53
44	Respirable mass emissions as a function of time at an air-to-cloth ratio of 2 ft/min, Run PTC-IL6-426	54
45	Baghouse differential pressure as a function of time, Run PTC-IL6-426	54
46	Respirable mass emissions as a function of time at an air-to-cloth ratio of 2 ft/min, Run PTC-IL6-427	55
47	Respirable mass emissions as a function of time at an air-to-cloth ratio of 2 ft/min, Run PTC-IL6-427	55
48	Respirable mass emissions as a function of time at an air-to-cloth ratio of 2 ft/min, Run PTC-IL6-428	57

TABLE OF FIGURES (continued)

		<u>Page</u>
49	Respirable mass emissions as a function of time at an air-to-cloth ratio of 4 ft/min, Run PTC-IL6-428	57
50	Respirable mass emissions as a function of time at an air-to-cloth ratio of 1.5 ft/min, Run PTC-IL6-428	58
51	Respirable mass emissions as a function of time at an air-to-cloth ratio of 3 ft/min, Run PTC-IL6-428	58
52	Respirable mass emissions as a function of time at an air-to-cloth ratio of 2 ft/min, Run PTC-IL6-428	59
53	Baghouse differential pressure as a function of time, Run PTC-IL6-428	61
54	Coulter counter data for Illinois #6 bituminous coal	62
55	Coulter counter data for Blacksville bituminous coal	62
56	Coulter counter data for Black Thunder subbituminous coal	63
57	Coulter counter data for North Dakota Beulah lignite	63
58	Multicyclone data for Illinois #6 bituminous coal	64
59	Multicyclone data for Blacksville bituminous coal	64
60	Multicyclone data for Black Thunder subbituminous coal	65
61	Multicyclone data for North Dakota Beulah lignite	65

LIST OF TABLES

<u>Table</u>	<u>Page</u>
1 Reverse-Gas Test Matrix for 100-Hour Test Period	6
2 Results of Coal and Coal Ash Analysis for Runs PTC-BV-423 through PTC-IL6-428	7
3 Summary of Run PTC-BV-423	9
4 Summary of Run PTC-BT-424	13
5 Summary of Run PTC-BU-425	17
6 Summary of Run PTC-IL6-426	21
7 Summary of Run PTC-IL6-427	24
8 Summary of Run PTC-IL6-428	26
9 Particulate Sampling Data for Pilot-Scale Fabric Filter Tests	35
10 Multicyclone Data from Run PTC-BV-423	39
11 Multicyclone Data from Run PTC-BT-424	46
12 Multicyclone Data from Run PTC-BU-425	52
13 Multicyclone Data from Run PTC-IL6-428	60
14 Reverse-Gas Baghouse Ash Analysis Results	67
15 Vanadium Concentration on Reverse-Gas Bags	68
16 Vanadium Concentration Analysis Results for Coal and Ash Samples . .	69
17 Planned Versus Actual Work Hours for Key Personnel Through June 1992	71

CATALYTIC FABRIC FILTRATION FOR SIMULTANEOUS NO_x AND PARTICULATE CONTROL

1.0 INTRODUCTION

The University of North Dakota Energy and Environmental Research Center (EERC); Owens-Corning Fiberglas Corporation (OCF); and Stearns-Roger, a division of United Engineers & Constructors (UE&C) are conducting research to develop a catalytic fabric filter for simultaneous NO_x and particulate control. Funding for the project is being provided by the U.S. Department of Energy/Pittsburgh Energy Technology Center (DOE/PETC), Consolidated Edison Company of New York Inc. (Con Edison), and the Empire State Electric Energy Research Corporation (ESEERCO).

The DOE/PETC funding was secured as a result of a competitive award from the DOE/PETC Advanced NO_x Control program. The objective of this program is to develop advanced concepts for the removal of NO_x from flue gas emitted by coal-fired utility boilers, or for the control of NO_x formation by advanced combustion modification techniques. Funded projects are required to focus on the development of technology that significantly advances the state of the art using a process or a combination of processes capable of reducing NO_x emissions to 60 ppm or less. The concept must have successfully undergone sufficient laboratory-scale development to justify scaleup for further evaluation at the pilot scale (not to exceed 5 MWe in size). Other requirements include production of a nonhazardous waste or a salable by-product. The concept should have application to both new and retrofit coal-fired systems. The concept should also show the potential for a 50% cost savings when compared to a commercial selective catalytic reduction (SCR) process capable of meeting the 60-ppm NO_x emission limit.

The EERC approach to meeting the program objective involves the development of a catalytic fabric filter for simultaneous NO_x and particulate control. The idea of applying either permanent or throwaway catalysts to a high-temperature fabric filter for NO_x control is not new (1-4). However, advances at OCF have shown that a high-activity catalyst can be applied to a high-temperature woven glass cloth resulting in a fabric filter material that can operate at temperatures higher than the maximum operating temperatures of commercially available, coated glass fabric. The NO_x is removed by catalytic reduction with ammonia to form nitrogen and water. The catalyst employed at this time is vanadium/titanium, but the exact catalyst composition and the unique method of applying the catalyst to high-temperature glass fabric are the property of OCF (5). Other catalyst options are being evaluated by OCF in order to improve catalyst performance and minimize catalyst cost.

Bench-scale experimental results to date have shown that over 90% NO_x removal can be achieved, the catalyst/fabric has promising self-abrasion characteristics, and the potential exists for substantially reduced cost when compared with conventional SCR/fabric filtration technology (6, 7). However, development of the technology requires further evaluation of air-to-cloth ratio, ammonia slip, SO₂ oxidation to SO₃, temperature cycling, catalyst-coated fabric preparation, fuel impacts, fabric cleaning (reverse-gas versus pulse-jet), catalyst life (poisoning and resistance to erosion), and filter performance/life (particulate control, differential pressure, and durability).

2.0 SCOPE OF WORK

The specific approach being used to address these issues is represented by the following:

- Task 1--Program Definition
- Task 2--Design and Construct Test Unit
- Task 3--Experimental Program and Data Reduction
- Task 4--Conceptual Design and Economic Evaluation
- Task 5--Test Unit Removal

Task 1, Program Definition, required preparation of a Project Management Plan. This document contains a detailed scope of work, project schedule, and project budget; identifies key project personnel; and presents an appropriate QA/QC plan for the project. Task 2, Design and Construct Test Unit, is divided into three subtasks. Subtasks 2.1 and 2.2 involved the detailed design of the test facility on which the experimental program is being performed, the construction of the test facility, and an operational shakedown of the system prior to initiating the experimental effort. Subtask 2.3 involves preparation of the catalyst-coated fabric filters that are being evaluated in the experimental effort.

Task 3, Experimental Program and Data Reduction, has four subtasks. Subtask 3.1, Fundamental Testing, is intended as a support effort to the primary experimental test plan. This effort should supply information needed to thoroughly understand the process mechanism, allow screening of additional fabric samples, address the issue of catalyst poisoning, and generally support the pilot-scale effort. Subtask 3.2, Process Testing/Reverse-Gas System, is intended to evaluate process performance in a pilot-scale reverse-gas fabric filter, identify and optimize important process variables, and provide data for a conceptual design. Subtask 3.3, Process Testing/Pulse-Jet System, will evaluate process performance in a pilot-scale pulse-jet fabric filter. Subtask 3.4, Fabric Durability Testing/Pulse-Jet System, will evaluate catalyst-coated fabric durability/performance for up to 12,000 hours in a slipstream pulse-jet baghouse.

Based on the results of Task 3, a technical and economic assessment of the catalytic fabric filter concept will be completed in Task 4, Conceptual Design and Economic Evaluation. Task 5, Test Unit Removal, requires the identification of all major test facilities, equipment, and instruments and hardware, and their condition, ownership, and proposed disposition.

The EERC is the primary contractor for the project and is responsible for the management/direction of all technical and administrative project activities. The EERC has specifically performed all work associated with Task 1 and Subtasks 2.1 and 2.2 and will perform Tasks 3 and 5.

OCF will perform and/or supervise all work associated with Subtask 2.3, including manufacturing the "S" glass fabric, coating the fabric, and manufacturing the filter bags for the reverse-gas and pulse-jet systems. This effort, as well as technical support, is being provided by OCF as a cost share to the project.

UE&C, as a subcontractor to the EERC, provided technical support for Task 1 and will perform Task 4. EERC personnel involved in the Task 3 effort and OCF personnel will provide input to UE&C Task 4 activities.

The project schedule is based on a project start date of October 1, 1990, and assumes a project duration of 36 months. Therefore, the planned project completion date is September 30, 1993.

Federal funding accounts for roughly 56% of the total project budget. Commercial funding for the project makes up the remaining 44%. Con Edison and ESEERCO are each funding 12% of the project cost, and OCF is contributing 10% in the form of catalyst-coated filter bags and technical support for the project. The remaining 10% is uncommitted at this time, but the EERC and OCF are pursuing funding options in an effort to obtain a formal commitment for the remaining commercial cost share as soon as possible.

3.0 GOALS AND OBJECTIVES

The overall objective of this project is the development of a catalyst-coated fabric filter for simultaneous NO_x and particulate control. The catalyst-coated fabric filter must provide high removal efficiency of NO_x and particulate matter. An acceptable bag and catalyst life must be demonstrated, and process economics must show a significant cost savings when compared to a commercial SCR process and conventional particulate control. Specific goals include the following:

- Reduce NO_x emissions to 60 ppm or less
- Demonstrate particulate removal efficiency of >99.5%
- Demonstrate a bag/catalyst life of >1 year
- Control ammonia slip to <25 ppm
- Show that catalytic fabric filtration can achieve a 50% cost savings over conventional fabric filtration and SCR control technology
- Determine compatibility with SO₂ removal systems
- Show that the concept results in a nonhazardous waste product

Specific project activities during the past quarter (April through June 1992) were to include the following:

- Complete Task 2, Design and Construct Test Unit
- Continue Subtask 3.1, Fundamental Testing
- Continue Subtask 3.2, Process Testing/Reverse-Gas System
- Initiate Subtask 3.3, Process Testing/Pulse-Jet System
- Initiate Subtask 3.4, Fabric Durability Testing/Pulse-Jet System

4.0 ACCOMPLISHMENTS

4.1 Task 2 Design and Construct Test Unit

The Siemens ammonia analyzer was used during all pilot-scale experimental periods in April, May, and June. The general trends for ammonia slip, as determined by the instrument, were consistent with changes in process parameters (air-to-cloth ratio and ammonia/NO_x molar ratio) and resulting changes on NO_x reduction, but analytical results from wet chemistry measurements were 10% to 20% higher than the instrument results. Although the performance of the instrument has not been as good as originally anticipated, EERC personnel decided in April to keep the instrument. It is anticipated that the instrument will perform better quantitatively during the 500-hour tests, when test conditions will not be changed as often, resulting in more stable ammonia slip values. In late June, the Siemens ammonia analyzer was returned to the vendor for repair as a result of the instrument's inability to zero and calibrate properly. The instrument is expected to be available for use during the first 500-hour test in August.

4.2 Subtask 3.1 Fundamental Testing

Preparation of fabric samples for the bench-scale catalyst deactivation experiments was completed this past quarter. However, experimental activities did not begin as planned due to problems encountered with the bench-scale experimental system. Although most of the equipment problems were associated with the mass flow controllers, a quartz reactor was damaged and repaired, and a gas regulator required replacement.

New mass flow controllers were ordered as replacements for two existing mass flow controllers that would not calibrate properly at the desired system flow rates (<20 cm³/min) for the catalyst deactivation experiments. Once the replacement mass flow controllers arrived, they were calibrated and initially appeared to calibrate properly. Upon initiating experimental activities, the nitric oxide (NO) and ammonia (NH₃) mass flow controllers would not maintain proper calibration and eventually failed. Both mass flow controllers were returned to the vendor for repair, but, as of the end of the quarter, the vendor has not confirmed a return date.

EERC personnel are currently looking into the option of using calibrated flowmeters as replacements and/or backups to the mass flow controllers. A vendor delivery date for the calibrated flowmeters is unknown at this time. Therefore, it is unlikely that bench-scale activities will resume before August.

While the equipment problems have prevented the completion of planned experimental activities, EERC personnel are working towards completion of a literature review initiated this past spring concerning catalyst deactivation/poisoning. The literature review, along with the results of the bench-scale experimental activities, will be summarized in the Topical Report for Subtask 3.1.

4.3 Subtask 3.2 Process Testing/Reverse-Gas System

Subtask 3.2, Process Testing/Reverse-Gas System, activities continued this past quarter with the completion of six 100-hour test periods: PTC-BV-423, PTC-BT-424, PTC-BU-425, PTC-IL6-426, PTC-IL6-427, and PTC-IL6-428. The completed test matrix is shown in Table 1. The purpose of the first three 100-hour test periods was to evaluate the effects of coal type on the ability of the catalyst-coated fabric to control particulate and nitric oxide (NO_x) emissions. The last three 100-hour test periods were to determine the effect of baghouse bulk gas temperature on NO_x removal (PTC-IL6-426), to determine the effect of an acid dew point and a water dew point on NO_x removal (PTC-IL6-427), and to determine the effectiveness of Fabric DE992 (PTC-IL6-428), respectively.

To determine the effects of coal type on catalyst-coated fabric performance, the pilot-scale reverse-gas baghouse temperature was held constant at 650°F, and flue gas was generated by firing a Blacksville bituminous, a Black Thunder subbituminous, a North Dakota Beulah lignite, and a washed Illinois #6 bituminous coal in a pilot-scale pc-fired combustor. The average ultimate, proximate, and sieve analyses for each coal used for the 100-hour tests are presented in Table 2. The four fuels used during this series of experiments represent a broad range of fuel characteristics in terms of moisture content (<2% to 32%), ash content (5% to 11%) and characteristics (low and high alkali content), sulfur content (0.3% to 3.3%), and heating value (7,000 to 13,000 Btu/lb).

Owens-Corning Fiberglas Corporation provided catalyst-coated reverse-gas filter bags woven from S-glass fibers for each 100-hour test. All reverse-gas bags tested were 12 inches in diameter by 26 feet long. The catalyst-coated fabric filters used for Runs PTC-BV-423 through PTC-IL6-427 were made from a 14-oz/yd² single-beam weave (DE484) fabric, coated with seven coats of an organic-based vanadium/titanium catalyst. For the pilot-scale tests, this fabric has been designated Style DE484. For Run PTC-IL6-428, the bags were prepared using a double-beam woven S-glass consisting of D-fibers (6.5 microns) and having a fabric weight of 22 ounces/yd² (DE992 fabric). Seven coats of an organic-based vanadium/titanium catalyst were also applied to the 22-ounce/yd² double-beam fabric. Heat treatment for all bags consisted of a 3.5- to 5-hour period during which the baghouse temperature was raised from roughly 350° to 690°F, followed by a heat treatment period of roughly 4 to 7 hours at 700°F and 2.0% to 4.5% oxygen. The flue gas for heat treatment was generated by firing the pilot-scale combustor on natural gas.

4.3.1 Nitric Oxide Removal Efficiency

4.3.1.1 PTC-BV-423

During the first day of Run PTC-BV-423, the bag in the west chamber showed poor particulate collection efficiency and was removed. A spare bag was placed in the west chamber and heat-treated at 690°F for 3.5 hours. After replacing the bag in the west chamber, the system was operated at 2 and 1.5 ft/min (two bags on line), with no problems. The bag removed from the west chamber was inspected and found to have several holes near the top.

TABLE 1
Reverse-Gas Test Matrix for 100-Hour Test Period¹

Run	A/C Ratio	Ammonia/NO _x Molar Ratio			
PTC-BV-423 (DE484)	1.5	0.75	0.85	--	--
	2.0	0.75	0.85	0.95	--
	3.0	0.8	0.85	0.9	--
	4.0	--	0.8	0.9	1.0
PTC-BT-424 (DE484)	1.5	0.8	--	--	--
	2.0	0.8	0.85	0.9	--
	3.0	0.7	--	0.9	--
	4.0	0.8	0.85	--	--
PTC-BU-425 (DE484)	1.5	0.7	0.8	0.9	--
	2.0	--	0.85	0.95	1.0
	3.0	0.7	0.8	0.9	--
	4.0	0.65	0.7	0.95	1.0
PTC-IL6-426 (DE484)	2.0	--	--	0.9	--
PTC-IL6-427 (DE484)	2.0	--	0.8	0.9	--
PTC-IL6-428 (DE992)	1.5	0.7	0.8	0.9	--
	2.0	0.7	0.8	0.9	--
	3.0	0.7	0.8	0.9	--
	4.0	0.7	0.8	0.9	--

¹ Baghouse bulk gas temperature was 650°F for all 100-hour test periods, except PTC-IL6-426 and PTC-IL6-427. For Run PTC-IL6-426, baghouse bulk gas temperature ranged from 500° to 750°F. Run PTC-IL6-427 resulted in baghouse bulk gas temperatures of <150° and 650°F.

Flue gas for this 100-hour test was generated by firing a Blacksville bituminous coal in a pilot-scale pc-fired combustor. Nitric oxide reduction averaged almost 90% at an air-to-cloth ratio of 2 ft/min (two bags on line), an ammonia/NO_x molar ratio of 0.85 (roughly 940 ppm NO_x in the flue gas), and an average bulk gas baghouse temperature of 660°F. At an air-to-cloth ratio of 3 ft/min (one bag on line), an ammonia/NO_x molar ratio of 0.83, and an average bulk gas temperature of 651°F, nitric oxide removal averaged 74%. Figure 1 shows the NO_x removal efficiency as a function of time, and Table 3 summarizes each test period.

Figure 2 plots the NO_x removal efficiency and ammonia slip (% of inlet NO_x) as a function of ammonia/NO_x molar ratio. Results summarized in Figure 2 show two distinct sets of NO_x reduction data. The first set depicts NO_x reduction (83% to 90%) at air-to-cloth ratios of 1.5 and 2 ft/min for ammonia/NO_x molar ratios ranging from 0.75 to 0.95. Data resulting from air-to-cloth ratios of 3 and 4 ft/min show NO_x reduction ranging from 74% to 81%

TABLE 2
Results of Coal and Coal Ash Analysis for Runs
PTC-BV-423 through PTC-IL6-428^a

	Illinois #6 Bituminous	Blacksville Bituminous	Black Thunder Subbituminous	Beulah Lignite
Proximate Analysis, wt%				
Moisture	5.89	1.40	24.5	31.6
Volatile Matter	34.50	32.81	36.7	30.36
Fixed Carbon	48.42	56.92	33.92	29.84
Ash	11.18	8.85	4.86	8.19
Ultimate Analysis, wt%				
Hydrogen	4.98	4.4	6.5	6.47
Carbon	64.84	74.76	52.23	43.61
Nitrogen	1.22	1.36	0.65	0.54
Sulfur	3.26	2.31	0.36	0.94
Oxygen	14.49	8.31	35.37	40.23
Ash	11.18	8.85	4.86	8.19
Heating Value, Btu/lb	11,501	12,794	8,940	7,158
Percent as Oxides, wt%				
SiO ₂	49.24	44.3	32.6	27.58
Al ₂ O ₃	19.35	20.67	15.5	13.77
Fe ₂ O ₃	18.73	20.48	5.49	7.86
TiO ₂	0.82	1.01	1.13	0.47
P ₂ O ₅	0.30	0.38	1.17	0.83
CaO	3.92	5.58	22.16	16.21
MgO	1.21	1.18	8.06	7.66
Na ₂ O	0.79	0.61	1.1	6.31
K ₂ O	1.72	1.11	0.3	0.28
SO ₃	3.69	4.69	12.48	19.02
Ash Fusion Temp., °F				
Initial	2096	2292	2186	2226
Softening	2170	2357	2234	2279
Hemisphere	2251	2390	2249	2289
Fluid	2343	2425	2263	2308
Sieve Analysis				
Screen Mesh Size		wt% Retained		
100	19.00	17.18	26.80	24.66
140	12.77	12.94	13.60	13.11
200	9.78	13.82	13.50	11.26
230	9.64	9.03	5.1	5.83
270	8.85	14.85	5.30	3.86
325	1.72	0.33	1.90	3.98
Pan	37.26	30.86	30.10	34.71
Total %	99.07	99.01	96.30	397.41

^a Coal analysis is presented on an "as-fired" basis.

for ammonia/NO_x molar ratios of 0.8 to 1.0. At low air-to-cloth ratios (1.5 and 2) and ammonia/NO_x molar ratios (<0.85), NO_x reduction appears to be greater than the theoretical value based on Reactions 1, 2, and 3:

Figure 1. NO_x removal efficiency as a function of time, Run PTC-BV-423.

TABLE 3

Summary of Run PTC-BV-423

Reverse-Gas Baghouse						Measured										
Average Bulk Gas Temp.		Average ΔP in H ₂ O	East Bag wt. lb	West Bag wt. lb	NH ₃ ^a Slip ppm	SO ₂ Inlet ppm	SO ₂ Outlet ppm	O ₂ Inlet %	O ₂ Outlet %	NO _x Inlet ppm	NO _x Outlet ppm	NO _x ^b Removal %	NH ₃ Slip ppm	SO ₂ ^c Conc. ppm		
East	West															
°F	°F															
Test Period #1; A/C=4.2; Molar Ratio=0.89																
Average	673	--	2.9	65.6	71.0	136	1617	1543	4.1	4.6	902	162	81.50	120.8	3.8	
Max.	676	--	4.2	74.0	74.3	156	1737	1651	4.9	5.9	993	183	84.92			
Min.	670	--	2.0	58.6	67.6	121	1535	1420	3.3	4.1	826	134	78.20			
Test Period #2; A/C=4.1; Molar Ratio=0.87																
Average	671	--	2.8	73.5	72.8	140	1687	1598	4.1	4.5	877	188	78.54	162.9	5.4	
Max.	673	--	3.7	80.7	73.2	166	1750	1751	5.0	5.5	946	210	81.91			
Min.	667	--	2.2	64.8	72.6	120	1587	1470	3.1	3.0	793	160	76.38			
Test Period #3; A/C=4.1; Molar Ratio=0.8																
Average	671	--	2.8	72.5	72.6	27	1686	1626	3.5	4.5	872	210	74.41			
Max.	671	--	3.6	88.8	72.9	39	1743	1724	4.4	5.4	890	234	78.67			
Min.	669	--	2.3	64.3	72.5	23	1611	1581	2.9	3.9	747	179	70.55			
Test Period #4; A/C=4.1; Molar Ratio=1.01																
Average	670	--	3.0	74.4	72.2	36	1676	1486	3.0	4.4	846	176	79.15			
Max.	670	--	3.9	82.7	72.5	50	1914	1653	3.8	5.5	947	205	81.29			
Min.	670	--	2.3	71.7	71.9	28	1590	1368	1.5	2.4	743	154	76.03			
Test Period #5; A/C=3.0; Molar Ratio=0.88																
Average	655	--	2.4	67.8	67.1	125	1711	1575	4.4	4.5	881	172	80.48	152.4	5.4	
Max.	658	--	3.4	71.7	67.4	150	1833	1710	5.5	5.8	962	204	84.27			
Min.	652	--	1.5	61.8	66.5	100	1608	1435	3.2	3.8	797	140	74.95			
Test Period #6; A/C=3.0; Molar Ratio=0.92																
Average	652	--	2.3	69.2	66.9	135	1720	1585	3.3	4.4	841	167	78.65			
Max.	652	--	2.9	70.3	67.0	145	1777	1712	3.9	4.8	863	176	81.08			
Min.	652	--	1.6	68.2	66.8	114	1617	1528	2.9	4.1	800	147	77.56			
Test Period #7; A/C=3.1; Molar Ratio=0.83																
Average	651	--	2.1	68.8	64.6	89	1714	1595	3.0	4.5	840	199	74.11			
Max.	652	--	2.8	70.6	66.9	97	1872	1728	3.9	5.4	875	218	75.97			
Min.	650	--	1.4	68.1	49.2	62	1630	1478	2.2	3.3	785	182	71.11			
Test Period #8; A/C=2.0; Molar Ratio=0.85																
Average	670	633	1.1	67.5	54.0	36	1630	1599	4.6	4.8	936	98	89.40	29.3	14.5	
Max.	673	648	1.6	74.2	71.5	39	1690	1657	5.5	5.4	952	105	90.65			
Min.	668	629	0.4	61.7	40.5	33	1536	1526	4.2	4.2	906	81	88.79			
Test Period #9; A/C=2.0; Molar Ratio=0.87																
Average	667	631	1.6	70.7	61.9	47	1640	1616	4.6	4.5	856	111	87.07			
Max.	669	634	6.7	74.3	73.2	64	1740	1675	5.5	5.7	928	144	90.31			
Min.	664	595	0.1	67.3	54.4	23	1541	1525	3.6	3.4	701	78	82.95			
Test Period #10; A/C=2.0; Molar Ratio=0.78																
Average	668	625	1.4	72.5	61.3	33	1672	1635	4.4	4.3	816	136	83.41			
Max.	668	625	2.0	74.0	61.5	47	1791	1746	5.1	5.1	837	155	85.65			
Min.	667	623	0.8	71.7	61.1	29	1575	1530	3.8	3.7	736	117	80.88			
Test Period #11; A/C=2.0; Molar Ratio=0.96																
Average	663	617	1.5	68.0	59.4	86	1663	1557	4.3	4.7	824	107	86.72			
Max.	667	637	2.2	68.5	61.6	113	1715	1646	4.8	5.5	852	165	90.11			
Min.	652	597	0.8	67.9	55.0	58	1590	1462	3.7	4.1	727	79	79.93			
Test Period #12; A/C=1.5; Molar Ratio=0.86																
Average	658	638	0.7	71.7	58.8	44	1624	1568	4.6	5.0	813	89	88.84	23.7		
Max.	659	639	1.0	73.0	59.4	49	1769	1642	5.9	5.9	844	103	90.57			
Min.	657	635	0.4	71.4	58.1	36	1413	1468	3.2	4.0	765	70	87.01			
Test Period #13; A/C=1.5; Molar Ratio=0.76																
Average	656	638	0.7	72.2	58.6	30	1607	1563	4.6	5.3	799	115	84.97			
Max.	656	638	0.8	73.5	60.7	36	1663	1609	5.1	5.8	823	125	86.38			
Min.	656	637	0.5	71.9	58.4	27	1577	1492	4.2	4.8	777	100	83.55			
Test Period #14; A/C=2.0; Molar Ratio=0.84																
Average	661	644	1.2	71.8	58.4	64	1644	1562	4.5	4.7	821	112	86.17	31.3		
Max.	662	648	1.4	72.2	58.9	67	1683	1584	5.6	5.4	843	136	88.48			
Min.	660	639	0.8	71.7	57.4	62	1540	1510	4.1	4.5	788	95	82.90			

^a Siemens ammonia analyzer.^b Corrected to 4% O₂.^c NH₃ injection turned off.

If the observation is not due to data variability, one explanation may be that some of the nitric oxide (NO) or nitrogen dioxide (NO_x) is being reduced as a result of Reaction 4.

However, Reaction 4 is not consistent with mechanisms typically reported in the literature for an oxidizing environment. Further data evaluation and literature review will be necessary before a firm conclusion can be drawn.

Figure 2. NO_x removal efficiency as a function of air-to-cloth ratio and ammonia/NO_x molar ratio, Run PTC-BV-423.

Results from ammonia slip measurements using wet chemistry techniques are also presented in Table 3 and Figure 2. The data show ammonia slip values ranging from 24 to 163 ppm depending on operating conditions. Ammonia slip values in the range of 24 to 31 ppm represent operation at 1.5 and 2 ft/min at an ammonia/NO_x molar ratio of about 0.85. Nitric oxide reduction ranged from 86% to 89%, and the baghouse bulk flue gas temperature averaged roughly 650°F. If the measured flue gas flow rate and inlet NO_x concentration are correct and the mass flow controller delivered ammonia consistent with the vendor calibration specifications, these ammonia slip and NO_x reduction data imply that some of the NO_x reduction observed occurred according to Reaction 4.

Ammonia slip values in the range of 120 to 163 ppm represent operation at 3 and 4 ft/min at an ammonia/NO_x molar ratio of roughly 0.9. Nitric oxide reduction ranged from 78% to 81%, and the baghouse bulk flue gas temperature averaged 666°F. These ammonia slip values are also higher than expected based on a 1:1 ammonia/NO_x reaction. Again this implies that some of the NO_x reduction occurred according to Reaction 4. However, a 5% error in the flue gas flow rate measurement, the ammonia injection rate, or a combination of the two would also account for the difference between the measured and calculated ammonia slip values.

Results from sulfur trioxide (SO₃) measurements using wet chemistry techniques are presented in Table 3. Sulfur trioxide concentrations ranged from 3.8 to 5.8 ppm in the flue gas, which indicates little or no conversion of sulfur dioxide (SO₂) to SO₃ across the catalytic fabric filter. Typically, combustion of a high-sulfur coal, such as Blacksville, will result in SO₃ concentrations in this range.

4.3.1.2 PTC-BT-424

Nitric oxide reduction averaged 90% at an air-to-cloth ratio of 2 ft/min (two bags on line), an ammonia/NO_x molar ratio of 0.91 (roughly 780 ppm NO_x in the flue gas), and an average bulk gas baghouse temperature of 667°F. At an air-to-cloth ratio of 4 ft/min (one bag on line), an ammonia/NO_x molar ratio of 0.82, and an average bulk gas baghouse temperature of 660°F, nitric oxide removal averaged 76%. Figure 3 shows the NO_x removal efficiency as a function of time, and Table 4 summarizes data for each test period. Figure 4 plots the NO_x removal efficiency and ammonia slip (% of inlet NO_x) as a function of ammonia/NO_x molar ratio.

Results summarized in Figure 4 show two distinct sets of NO_x reduction data. The first set depicts NO_x reduction (78% to 90%) at air-to-cloth ratios of 1.5 and 2 ft/min for ammonia/NO_x molar ratios ranging from 0.8 to 0.9. Data resulting from air-to-cloth ratios of 3 and 4 ft/min show NO_x reduction ranging from 76% to 78% for ammonia/NO_x molar ratios of 0.7 to 0.9.

Results from ammonia slip measurements using wet chemistry techniques are also presented in Table 4 and Figure 4. The data show ammonia slip values ranging from 42 to 119 ppm, depending on the operating conditions. Ammonia slip values in the range of 40 to 60 ppm represent operation at 1.5 and 2 ft/min at an ammonia/NO_x molar ratio of 0.8 to 0.85. Nitric oxide reduction ranged from 83% to 86%, and the baghouse bulk flue gas temperature averaged roughly 650°F. Although the ammonia slip data indicate a general trend

Figure 3. NO_x removal efficiency as a function of time, Run PTC-BT-424.

TABLE 4

Summary of Run PTC-BT-424

Reverse-Gas Baghouse										Measured										NH ₃ Slip ppm	NO _x Removal %	SO ₃ Conc. ppm
Average Bulk Gas Temp. °F		Average ΔP in H ₂ O	East Bag wt. lb	West Bag wt. lb	NH ₃ Slip ppm	SO ₂ Inlet ppm	SO ₂ Outlet ppm	O ₂ Inlet %	O ₂ Outlet %	NO _x Inlet ppm	NO _x Outlet ppm											
East °F	West °F																					
Test Period #1; A/C=2.0; Molar Ratio=0.91																						
Average	673	661	0.9	70.9	75.6	129	366	309	4.6	4.9	781	75	90.14	118.5								
Max.	675	661	1.1	71.2	75.7	148	380	348	5.1	6.8	810	100	92.03									
Min.	671	661	0.6	70.5	75.4	106	355	253	4.2	4.5	721	60	86.05									
Test Period #2; A/C=2.0; Molar Ratio=0.84																						
Average	664	650	3.0	69.9	71.7	50	350	289	4.5	5.2	819	108	86.21	62.9								
Max.	671	655	4.4	91.0	77.8	79	414	335	5.4	8.0	920	215	89.56									
Min.	650	641	1.7	58.1	60.9	32	304	221	3.4	3.8	726	71	72.79									
Test Period #3; A/C=4.2; Molar Ratio=0.82																						
Average	660	---	7.8	69.5	74.4	116	344	250	4.7	5.7	817	182	76.22	95.1								
Max.	663	---	9.2	93.9	78.3	136	409	303	6.6	8.1	850	252	79.69									
Min.	656	---	5.8	63.5	72.9	95	296	217	3.8	4.8	778	175	69.66									
Test Period #4; A/C=4.2; Molar Ratio=0.84																						
Average	664	---	8.7	66.8	72.6	122	356	255	4.5	5.3	814	194	76.10	0.3								
Max.	669	---	9.8	92.9	73.0	146	420	322	6.6	8.1	895	232	79.42									
Min.	657	---	5.8	63.0	72.2	87	303	200	3.1	4.3	748	172	73.55									
Test Period #5; A/C=3.0; Molar Ratio=0.87																						
Average	645	---	8.2	68.0	71.7	153	317	183	4.5	5.3	790	182	77.66									
Max.	658	---	9.4	94.3	72.6	222	391	268	6.0	9.8	921	239	86.09									
Min.	634	---	5.4	60.9	71.1	108	255	115	3.2	4.0	704	103	70.71									
Test Period #6; A/C=3.1; Molar Ratio=0.73																						
Average	663	---	9.3	69.3	70.9	120	297	213	4.6	5.4	820	177	77.19	99.5								
Max.	665	---	10.0	89.2	71.0	137	363	258	5.4	6.1	851	229	80.16									
Min.	660	---	7.5	67.1	70.9	99	282	180	4.1	4.7	780	158	70.26									
Test Period #7; A/C=1.6; Molar Ratio=0.78																						
Average	672	640	3.7	70.8	72.0	72	306	251	4.6	5.0	803	114	85.47	41.8								
Max.	673	643	4.2	72.3	80.0	98	354	286	6.1	7.8	839	146	88.66									
Min.	671	635	2.9	68.8	63.9	58	270	228	4.0	3.7	749	88	82.00									
Test Period #8; A/C=1.5; Molar Ratio=0.79																						
Average	670	645	4.7	70.1	69.5	53	320	285	4.3	5.0	797	135	82.42	63.9								
Max.	675	649	5.8	80.8	76.6	94	399	388	5.7	7.7	860	183	88.26									
Min.	660	638	3.4	68.0	65.7	32	265	201	2.0	3.0	730	89	77.32									
Test Period #9; A/C=2.1; Molar Ratio=0.84																						
Average	670	668	6.7	69.2	72.8	112	331	271	4.4	5.0	781	129	82.92	47.6								
Max.	677	668	7.3	71.3	77.4	132	393	334	5.4	7.4	854	154	87.00									
Min.	663	668	5.9	68.1	69.9	91	282	227	3.7	4.4	722	94	79.73									
Test Period #10; A/C=2.1; Molar Ratio=0.78																						
Average	662	663	6.5	70.6	70.7	89	338	285	4.3	5.1	795	161	78.65	55.6								
Max.	668	670	7.6	95.9	79.7	103	398	362	5.8	8.5	882	212	83.17									
Min.	647	642	4.8	68.4	66.4	51	296	200	2.6	3.1	739	118	73.68									

* Siemens ammonia analyzer.

* Corrected to 4% O₂.* NH₃ injection turned off.

Figure 4. NO_x removal efficiency as a function of air-to-cloth ratio and ammonia/NO_x molar ratio, Run PTC-BT-424.

toward decreasing ammonia slip with a decreasing ammonia/NO_x molar ratio, the data are quite variable, and the ammonia concentrations are quite high.

Ammonia slip values in the range of 90 to 100 ppm represent operation at 3 and 4 ft/min at an ammonia/NO_x molar ratio of roughly 0.7 to 0.8. Nitric oxide reduction ranged from 76% to 77%, and the baghouse bulk flue gas temperature averaged 660°F. As in the previous test, these ammonia slip values are higher than what would be expected based on a 1:1 ammonia/NO_x reaction. Further evaluation of these data will be necessary to adequately explain the results.

Sulfur trioxide concentrations, presented in Table 4, ranged from 0.3 to 4.3 ppm in the flue gas, which are ≤ 1% of the flue gas SO₂ concentrations.

4.3.1.3 PTC-BU-425

Nitric oxide reduction averaged 91% at an air-to-cloth ratio of 2 ft/min (two bags on line), an ammonia/NO_x molar ratio of 0.99 (roughly 630-ppm NO_x in the flue gas), and an average bulk gas baghouse temperature of 658°F. At an air-to-cloth ratio of 3 ft/min (one bag on line), an ammonia/NO_x molar ratio of 0.73, and an average bulk gas baghouse temperature of 647°F, nitric oxide removal averaged 71%. Figure 5 shows the NO_x removal efficiency as a function

Figure 5. NO_x removal efficiency as a function of time, Run PTC-BU-425.

of time, and Table 5 summarizes data for each test period. Figure 6 plots the NO_x removal efficiency and ammonia slip (% of inlet NO_x) as a function of ammonia/ NO_x molar ratio.

Results summarized in Figure 6 show two distinct sets of NO_x reduction data as did similar figures for previous 100-hour tests discussed. The first data set depicts NO_x reduction (78% to 91%) at air-to-cloth ratios of 1.5 and 2 ft/min for ammonia/ NO_x molar ratios ranging from 0.73 to 0.99. Data resulting from air-to-cloth ratios of 3 and 4 ft/min show NO_x reduction ranging from 71% to 77% for ammonia/ NO_x molar ratios of 0.66 to 0.99.

Results from ammonia slip measurements using wet chemistry techniques are also presented in Table 5 and Figure 6. The data show ammonia slip values ranging from 60 to 190 ppm depending on the operating conditions. Ammonia slip values in the range of 60 to 117 ppm represent operation at 1.5 and 2 ft/min at an ammonia/ NO_x molar ratio of 0.84 to 0.99. Nitric oxide reduction ranged from 82% to 90%, and the baghouse bulk flue gas temperature averaged roughly 655°F. Again, the ammonia slip data indicate a general trend toward decreasing ammonia slip with a decreasing ammonia/ NO_x molar ratio, but the data are variable, and the ammonia concentrations are quite high.

Ammonia slip values in the range of 140 to 190 ppm represent operation at 3 and 4 ft/min at an ammonia/ NO_x molar ratio of roughly 0.9 to 0.95. Nitric oxide reduction ranged from 74% to 77%, and the baghouse bulk flue gas temperature averaged 648°F. Again, these ammonia slip values are higher than expected based on a 1:1 ammonia/ NO_x reaction. Further tests and evaluation of all of the flue gas data will be necessary to adequately explain the results.

Sulfur trioxide (SO_3) measurements were also made, and results range from 2.4 to 4.1 ppm in the flue gas, which is less than 1% of the flue gas SO_2 concentration. Results from SO_3 measurements using wet chemistry techniques are presented in Table 5.

Figure 7 plots NO_x removal as a function of air-to-cloth ratio for each coal. From the data, it appears there is no coal effect on NO_x removal, except at air-to-cloth ratios of 3 and 4 ft/min. At the higher air-to-cloth ratios, NO_x removal decreases for the Illinois #6 bituminous coal. It is suspected that this difference is due to pin-holing and gas channeling in the bags when the Illinois #6 is used. No other conclusions can be drawn due to the variability in the experimental data and the short duration of the test periods.

4.3.1.4 PTC-IL6-426

During this 100-hour test, seven individual experimental periods were completed in order to address the effects of bulk gas baghouse temperature (500°, 550°, 600°, 650°, 700°, and 750°F) on NO_x removal efficiency. For all tests, air-to-cloth ratio was held constant at 2 ft/min, and the ammonia/ NO_x molar ratio was nominally 0.9. Flue gas was generated by firing a washed Illinois #6 bituminous coal in the pilot-scale pc-fired combustor.

TABLE 5
Summary of Run PTC-BU-425

Reverse-Gas Baghouse						Measured										
Average Bulk Gas Temp.		Average	East	West		NH ₃ ^a	SO ₂	SO ₂	O ₂	O ₂	NO _x	NO _x				
East	West	ΔP	Bag wt.	Bag wt.		Slip	Inlet	Outlet	Inlet	Outlet	Inlet	Outlet	NO _x ^b	NH ₃	SO ₂ ^c	
°F	°F	in H ₂ O	lb	lb		ppm	ppm	ppm	%	%	ppm	ppm	Removal %	Slip ppm	Conc. ppm	
Test Period #1; A/C=2.0; Molar Ratio=0.99																
Average	663	663	0.9	63.4	72.6	35	958	857	4.2	4.7	648	60	90.44	117.4		
Max.	664	664	1.1	63.6	72.7	48	1020	903	6.2	6.1	677	69	92.42			
Min.	662	662	0.6	63.3	72.5	21	890	785	3.1	3.8	615	40	89.50			
Test Period #2; A/C=2.0; Molar Ratio=0.99																
Average	657	658	2.3	71.8	74.5	58	921	746	4.5	4.9	631	54	91.16	4.1		
Max.	659	660	3.2	113.5	110.2	75	1080	931	6.4	7.8	694	60	92.67			
Min.	655	656	1.4	62.6	72.5	37	781	625	2.8	3.1	563	37	89.51			
Test Period #3; A/C=2.0; Molar Ratio=0.96																
Average	652	650	2.6	59.5	64.7	24	877	732	4.6	5.2	654	90	85.67	96.6		
Max.	653	653	3.0	80.1	81.5	71	961	808	6.9	9.1	700	119	88.89			
Min.	649	647	1.9	51.6	59.8	7	800	635	3.5	4.0	584	61	82.08			
Test Period #4; A/C=4.0; Molar Ratio=0.95																
Average	651	---	6.2	61.2	69.1	119	927	662	4.1	5.0	650	140	76.90	189.5		
Max.	654	---	7.6	72.6	69.5	135	1108	815	5.1	7.7	711	163	80.21			
Min.	645	---	5.0	54.7	68.6	104	811	600	3.0	3.7	589	97	70.76			
Test Period #5; A/C=4.1; Molar Ratio=0.99																
Average	650	---	7.1	64.7	69.0	136	945	644	4.2	5.5	622	133	76.58	2.4		
Max.	654	---	7.9	106.6	69.4	154	1039	780	5.9	7.9	677	170	79.23			
Min.	646	---	4.7	57.7	68.9	114	807	589	2.4	2.8	584	96	70.79			
Test Period #6; A/C=4.1; Molar Ratio=0.66																
Average	654	---	7.0	68.3	69.1	58	742	672	4.7	6.1	632	167	71.81			
Max.	654	---	7.9	87.9	69.3	99	856	742	6.6	8.7	652	202	78.44			
Min.	644	---	5.5	65.1	68.9	40	624	594	3.5	5.1	616	138	66.49			
Test Period #7; A/C=4.1; Molar Ratio=0.72																
Average	649	---	7.2	67.9	69.2	77	795	658	4.5	5.8	645	169	72.60			
Max.	659	---	8.2	87.1	69.5	93	918	754	5.9	8.2	667	204	77.50			
Min.	628	---	4.7	64.4	68.9	62	589	552	2.3	4.3	640	131	67.07			
Test Period #8; A/C=3.1; Molar Ratio=0.89																
Average	645	---	6.5	69.4	68.9	75	894	675	4.4	5.0	642	152	74.38	148.1	3.1	
Max.	660	---	7.5	71.8	69.6	93	1094	868	6.4	7.6	699	196	79.35			144.8
Min.	626	---	3.9	67.4	68.1	60	704	523	2.5	3.3	559	112	62.77			
Test Period #9; A/C=3.0; Molar Ratio=0.73																
Average	647	---	5.7	70.9	69.2	54	867	697	4.6	5.6	666	184	70.63			
Max.	656	---	6.6	107.6	69.7	75	930	773	5.9	7.8	687	215	72.49			
Min.	637	---	3.9	69.2	69.0	44	741	587	3.8	4.5	638	157	62.04			
Test Period #10; A/C=3.0; Molar Ratio=0.82																
Average	642	---	6.0	70.7	69.1	64	875	688	4.6	5.0	647	180	71.42			
Max.	647	---	7.2	72.1	69.3	77	993	761	5.5	7.8	675	218	73.94			
Min.	635	---	3.9	70.0	68.8	38	687	604	2.7	2.8	593	154	67.10			
Test Period #11; A/C=1.5; Molar Ratio=0.91																
Average	647	620	2.8	74.5	64.2	68	874	696	4.6	5.1	670	91	86.05	80.5		
Max.	649	616	3.3	76.3	68.4	87	998	783	5.8	7.9	708	114	88.27			
Min.	644	624	1.1	73.1	62.4	55	764	563	3.3	3.1	615	76	82.52			
Test Period #12; A/C=1.5; Molar Ratio=0.90																
Average	645	624	3.0	76.3	68.1	50	974	784	3.8	4.3	635	99	83.94	2.9		
Max.	652	631	3.6	92.0	76.0	70	1097	899	6.9	7.9	685	116	87.08			
Min.	633	615	1.1	73.7	67.5	28	810	638	2.0	2.0	596	67	80.01			
Test Period #13; A/C=1.5; Molar Ratio=0.73																
Average	647	622	2.8	76.2	67.2	19	919	791	4.5	5.0	650	140	77.76			
Max.	650	624	3.5	77.6	68.8	39	1008	876	5.6	7.0	684	170	80.57			
Min.	643	620	1.2	75.7	66.6	10	810	639	3.9	4.2	625	112	74.10			
Test Period #14; A/C=1.5; Molar Ratio=0.80																
Average	639	616	2.7	75.8	69.2	37	922	781	4.1	4.5	637	124	79.10			
Max.	642	619	3.6	77.2	72.6	63	1075	987	6.0	7.1	648	146	82.08			
Min.	635	612	0.9	74.9	68.3	29	828	682	1.8	1.6	623	106	76.65			

TABLE 5 (continued)

Reverse-Gas Baghouse					Measured									
Average Bulk Gas Temp.					NH ₃ ^a Slip	SO ₂ Inlet	SO ₂ Outlet	O ₂ Inlet	O ₂ Outlet	NO _x Inlet	NO _x Outlet	NO _x ^b Removal %	NH ₃ Slip	SO ₂ ^c Conc.
East	West	Average ΔP in H ₂ O	East Bag wt. lb	West Bag wt. lb	ppm	ppm	ppm	%	%	ppm	ppm	%	ppm	ppm
Test Period #15; A/C=2.0; Molar Ratio=0.87														
Average	658	636	4.1	76.3	70.3	53	911	728	4.5	5.1	641	114	81.70	60.0
Max.	672	650	4.7	78.6	70.4	70	967	793	5.0	7.1	678	190	85.61	
Min.	643	622	3.6	74.6	70.2	21	849	614	3.9	4.7	611	78	70.99	

^a Siemens ammonia analyzer.^b Corrected to 4% O₂.^c NH₃ injection turned off. Figure 6. NO_x removal efficiency as a function of air-to-cloth ratio and ammonia/NO_x molar ratio, Run PTC-BU-425.

Figure 7. NO_x removal efficiency as a function of coal type and air-to-cloth ratio.

Nitric oxide reduction showed a strong dependence on temperature. At an average bulk gas baghouse temperature of roughly 700°F, NO_x reduction averaged 86%, and at an average bulk gas temperature of roughly 500°F, average NO_x removal dropped to 16% as shown in Figure 8. Table 6 summarizes each test period. The effect of temperature on NO_x removal was more dramatic than previous bench-scale tests had indicated. Therefore, near the end of a subsequent 100-hour test period (PTC-IL6-428), additional data were generated to verify the observed results during Run PTC-IL6-426. From a short test following Run PTC-IL6-428, Figure 9 plots NO_x removal as a function of time at 550°F. At an air-to-cloth ratio of 1.91, and an ammonia/ NO_x molar ratio of 0.81, NO_x removal averaged 67%. This is much higher than the 24% NO_x removal rate seen during Run PTC-IL6-426 at roughly the same conditions (see Figure 10). The difference may be due to different fabrics (DE484 vs. DE992). Another explanation may be the formation of ammonium sulfate or bisulfate during Run PTC-IL6-426 when operating at 550° and 500°F. When insulation was removed to lower the baghouse temperature, cool spots may have occurred allowing the formation of ammonium sulfate or bisulfate. The reaction of ammonia with sulfur dioxide would have reduced the amount of ammonia available for NO_x removal. Although ammonia slip measurements made during Run PTC-IL6-426 agreed with theoretical slip values, ammonium sulfate or bisulfate would show up as ammonia in the wet chemistry measurements.

Figure 8. NO_x removal efficiency as a function of time, Run PTC-IL6-426.

TABLE 6

Summary of Run PTC-IL6-426

Reverse-Gas Baghouse					Measured						NO _x ^a Removal %	NH ₃ Slip ppm	SO ₃ ^b Conc. ppm	
Average Bulk Gas Temp.		Average ΔP in H ₂ O		East Bag wt. lb	West Bag wt. lb	SO ₂ Inlet ppm	SO ₂ Outlet ppm	O ₂ Inlet %	O ₂ Outlet %	NO _x Inlet ppm				NO _x Outlet ppm
East °F	West °F													
Test #1; A/C=2.0; Molar Ratio=0.87														
Average	705	702	1.4	74.5	75.1	2602	2566	4.1	4.3	851	119	85.76	28.8	14.3
Max.	707	706	2.8	79.3	81.1	2723	2707	5.5	6.8	879	140	90.43		
Min.	702	699	0.3	74.2	74.9	2416	2427	3.4	3.4	733	79	81.81		
Test #2; A/C=2.0; Molar Ratio=0.90														
Average	658	650	1.9	66.9	69.5	2512	2479	4.3	4.6	884	139	83.93	148.6	1.8
Max.	665	654	3.3	74.9	75.4	2654	2586	5.9	7.3	940	189	88.68		
Min.	650	644	0.2	49.4	63.6	2394	2356	3.4	3.5	809	102	79.33		
Test #3; A/C=2.0; Molar Ratio=0.89														
Average	607	605	2.6	53.9	60.9	2580	2414	4.2	4.5	872	315	63.25	203.6	0.5
Max.	615	614	4.0	74.5	74.4	2718	2605	5.8	7.5	938	455	75.02		
Min.	659	598	1.0	49.8	58.6	2446	2229	3.2	3.5	772	204	50.40		
Test #4; A/C=1.8; Molar Ratio=0.90														
Average	554	550	2.8	69.9	71.5	2542	2070	4.1	4.8	862	624	24.49	555.7	1.1
Max.	557	551	8.8	87.6	86.9	2672	2270	5.1	6.4	932	708	33.89		
Min.	552	548	1.1	60.7	63.4	2401	1879	3.3	3.5	805	538	14.10		
Test #5; A/C=1.8; Molar Ratio=0.91														
Average	506	506	2.5	65.0	68.0	2614	2039	4.3	4.8	800	650	15.75	457.9	1.3
Max.	514	510	3.8	84.2	84.7	2782	2304	6.4	7.1	869	690	24.53		
Min.	500	499	1.6	57.5	60.0	2386	1890	3.1	3.6	723	513	11.25		
Test #6; A/C=2.0; Molar Ratio=0.91														
Average	742	708	2.5	77.2	77.4	2572	2502	4.2	4.6	711	120	82.68	129.5	16.6
Max.	744	712	3.1	80.0	79.0	2727	2638	4.9	6.9	748	145	85.81		
Min.	739	705	1.7	76.3	76.0	2463	2325	3.3	3.4	655	81	79.48		
Test #7; A/C=2.0; Molar Ratio=0.89														
Average	654	648	2.2	63.6	68.0	2564	2451	4.2	4.5	717	147	79.12	130.2	10.7
Max.	659	652	2.9	65.3	70.1	2669	2539	5.4	7.0	765	172	84.74		
Min.	650	640	1.3	60.8	66.7	2401	2300	3.7	3.6	660	107	75.74		

^a Corrected to 4% O₂.^b NH₃ injection turned off.

Figure 9. NO_x removal efficiency as a function of time @ 550°F, Run PTC-IL6-428.

Figure 10. NO_x removal as a function of baghouse temperature.

Ammonia slip measurements made using wet chemistry techniques showed slip values ranging from 29 ppm at an average bulk gas temperature of 700°F to 556 ppm at an average bulk gas temperature of 550°F. The high wet chemistry ammonia slip values are consistent with the low NO_x removal efficiencies at the lower temperatures. Sulfur trioxide (SO₃) measurements were also made and ranged from 0.5 to 16.6 ppm in the flue gas, depending on the baghouse temperature. For baghouse bulk gas temperatures <650°F, SO₃ concentrations were <2 ppm, <0.1% of the flue gas SO₂ concentration. At baghouse bulk gas temperatures of 650°-750°F, SO₃ concentrations ranged from roughly 10 to 17 ppm, <1% of the flue gas SO₂ concentration. These data indicate that the catalyst-coated fabric did not oxidize SO₂ to SO₃ at flue gas temperatures of ≤ 650°F. Ammonia slip and SO₃ concentration values are also reported in Table 6.

4.3.1.5 PTC-IL6-427

The bags used for this test were the same set used for the previous 100-hour test PTC-IL6-426. Two individual experimental periods were completed in order to address the effects of an upset condition on NO_x removal efficiency. The bags were exposed to temperatures below the acid dew point (approximately 150°F) and the water dew point (approximately 140°F). Air-to-cloth ratio was held constant at 2 ft/min, and the ammonia/NO_x molar ratio was nominally 0.9.

The 100-hour test was initiated by firing natural gas in the pilot-scale combustor. All system water-cooled heat exchangers were placed in service, and baghouse heaters were turned off in order to minimize the bulk flue gas temperature in the reverse-gas baghouse. It was apparent that the baghouse was operating below the water dew point by the amount of water draining from moisture traps upstream of the baghouse and the baghouse hopper. This dew point condition was maintained for over three hours. In addition, SO₃ was injected for two hours to achieve a flue gas concentration of roughly 20 ppm, exposing the catalyst-coated fabric to an acid dew point. After two hours, the SO₃ injection was discontinued, the heat exchangers were taken off-line, and the baghouse heaters were turned on. Natural gas firing continued until the baghouse temperature was stabilized at 650°F. At that point, pc-coal firing was initiated, and the performance of the catalyst-coated bags was evaluated during a 9-hour period.

After completing the 9-hour test period, coal firing was discontinued, natural gas firing was initiated, water-cooled heat exchangers were placed in service, and the baghouse heaters were shut off. The purpose in this case was to expose the catalyst-coated fabric to a second dew point (water only) to see if bag performance would be further impacted. After exposure to a water dew point for two hours, the heat exchangers were again taken off-line and the baghouse heaters turned on. Coal firing was again initiated after a stable baghouse temperature of 650°F was achieved.

Nitric oxide reduction was affected by the exposure of the catalyst-coated fabric to an acid dew point. After the first upset condition, the average bulk gas baghouse temperature was raised to roughly 655°F, and NO_x reduction averaged 65%. In a previous test (PTC-IL6-426), at similar operating conditions with the same set of bags, NO_x reduction averaged 84%. This represents a 23% decrease in NO_x reduction efficiency. After exposure to

the water dew point, NO_x reduction averaged 66% at an average bulk gas baghouse temperature of 658°F. Exposure to the water dew point did not have an additional effect on NO_x reduction. Therefore, we can conclude that exposure to the acid dew point adversely affected the catalyst-coated fabric, but no conclusion can be made concerning the effect of the water dew point. Bench-scale testing should clarify the effect of the water dew point on NO_x removal. Figure 11 shows the NO_x removal efficiency as a function of time, and Table 7 summarizes each test period.

Ammonia slip values from wet chemistry measurements ranged from 196 ppm at an average bulk gas temperature of 659°F after exposure to the water dew point, to 269 ppm at an average bulk gas temperature of 660°F after exposure to the acid dew point. The ammonia slip values from the wet chemistry techniques agree closely with the calculated theoretical values. Sulfur trioxide (SO₃) measurements were also made during coal firing, and values ranged from 1.7 to 4.4 ppm in the flue gas, depending on the operating conditions. The wet chemistry ammonia slip values and SO₃ concentration values are reported in Table 7.

4.3.1.6 PTC-IL6-428

Run PTC-IL6-428 was conducted using a different fabric (DE992 fabric) than the previous 100-hour tests reported in this document, and the pilot-scale combustor was fired using the washed Illinois #6 coal. The results from this 100-hour test period are summarized in Table 8. Nitric oxide reduction

TABLE 7
Summary of Run PTC-IL6-427

Reverse-Gas Baghouse						Measured								
Average Bulk Gas Temp.		Average	East	West		SO ₂	SO ₂	O ₂	O ₂	NO _x	NO _x		NH ₃	SO ₂ ^b
East	West	ΔP	Bag wt.	Bag wt.		Inlet	Outlet	Inlet	Outlet	Inlet	Outlet	Removal	Slip	Conc.
°F	°F	in H ₂ O	lb	lb		ppm	ppm	%	%	ppm	ppm	%	ppm	ppm
Test Period #1; Natural Gas; Molar Ratio=0.81														
Average	664	657	---	72.8	74.6	---	---	2.2	2.4	193	80	57.82		
Max.	669	666	---	72.8	74.6	---	---	2.2	2.4	203	89	65.26		
Min.	656	651	---	72.8	74.6	---	---	2.2	2.4	155	56	54.41		
Test Period #2; A/C=2.0; Molar Ratio=0.87														
Average	663	656	1.1	76.9	75.1	2387	2202	4.4	4.7	920	313	65.44	208.9	
Max.	675	665	1.7	77.4	75.3	2448	2364	5.2	6.6	948	342	67.54		
Min.	653	651	0.6	76.3	74.8	2287	2016	4.0	4.1	874	272	62.23		
Test Period #3; A/C=2.0; Molar Ratio=0.93														
Average	653	650	2.1	77.5	75.2	2500	2317	4.4	4.4	852	307	64.07		4.4
Max.	653	650	2.3	86.6	83.0	2534	2456	5.1	6.1	878	322	66.06		
Min.	653	649	1.5	76.9	74.7	2422	2173	4.2	4.0	792	279	62.82		
Test Period #4; A/C=2.0; Molar Ratio=0.93														
Average	660	658	1.9	100.6	55.3	2518	2368	4.1	4.7	849	273	66.72	196.1	
Max.	661	658	2.2	100.6	55.4	2592	2451	4.6	7.9	865	292	69.48		
Min.	659	658	1.7	100.5	55.1	2443	2152	3.7	3.5	827	229	64.45		
Test Period #5; A/C=2.0; Molar Ratio=0.92														
Average	658	657	2.7	100.7	55.7	2550	2341	4.2	4.8	841	285	64.85		1.7
Max.	659	659	3.0	100.8	55.9	2641	2557	4.7	6.8	861	302	67.39		
Min.	658	656	2.5	100.4	55.4	2484	2068	3.8	4.1	813	252	62.53		

^a Corrected to 4% O₂.

^b NH₃ injection turned off.

Figure 11. NO_x removal efficiency as a function of time, Run PTC-IL6-427.

TABLE 8
Summary of Run PTC-IL6-428

	Reverse-Gas Baghouse					Measured						NO _x ^a Removal %	NH ₃ Slip ppm	SO ₃ ^b Slip ppm
	Average Bulk Gas Temp.		Average ΔP in H ₂ O	East Bag wt. lb	West Bag wt. lb	SO ₂ Inlet ppm	SO ₂ Outlet ppm	O ₂ Inlet %	O ₂ Outlet %	NO _x Inlet ppm	NO _x Outlet ppm			
	East	West												
	°F	°F												
Test Period #1; A/C = 2.0; Molar Ratio = 0.91														
Average	667	660	0.8	70.1	70.1	2520	2486	3.9	4.5	838	34	95.80	17.5	
Max.	676	664	1.2	72.1	71.0	2655	2676	5.1	9.8	857	47	97.03		
Min.	660	658	0.7	67.7	69.2	2395	2326	2.9	3.1	786	23	94.45		
Test Period #2; A/C = 1.98; Molar Ratio = 0.89														
Average	660	655	1.6	60	62	2487	2427	4.1	4.8	866	48	94.16		0.0
Max.	661	657	2.0	60	62	2635	2593	5.0	6.7	895	57	95.81		
Min.	658	653	1.3	60	62	2386	2204	2.5	3.2	818	36	93.28		
Test Period #3; A/C = 2.0; Molar Ratio = 0.80														
Average	655	653	1.6	73	74	2465	2301	4.4	4.7	867	53	93.73		
Max.	662	654	2.0	107	105	2563	2450	5.4	8.2	890	80	96.08		
Min.	651	652	1.1	60	62	2325	2209	3.6	3.4	830	34	90.67		
Test Period #4; A/C = 2.0; Molar Ratio = 0.71														
Average	650	651	2.0	67	70	2470	2274	4.5	4.6	883	145	83.50		
Max.	651	652	2.3	71	74	2539	2347	6.6	5.9	912	162	86.75		
Min.	648	650	1.4	66	69	2216	2214	3.9	3.6	785	105	81.45		
Test Period #5; A/C = 4.0; Molar Ratio = 0.93														
Average	655	---	3.3	68.1	70.9	2490	2356	4.2	4.9	894	113	86.81	128.4	
Max.	660	---	4.5	105.9	72.5	2622	2464	4.9	7.1	932	166	89.25	109.7	
Min.	651	---	2.1	63.5	69.0	2315	2226	3.6	3.7	832	83	80.84		
Test Period #6; A/C = 4.0; Molar Ratio = 0.88														
Average	656	---	4.6	66.9	71.0	2523	2374	4.3	4.9	916	122	86.18		23.9
Max.	659	---	6.2	73.3	71.7	2645	2550	5.4	6.5	993	159	91.09		
Min.	653	---	2.6	63.8	70.6	2393	2211	3.3	1.1	845	94	82.75		
Test Period #7; A/C = 4.0; Molar Ratio = 0.81														
Average	654	---	5.5	64	71	2477	2348	4.0	4.9	875	154	81.45		
Max.	655	---	6.5	66.0	71	2548	2490	5.0	5.6	912	173	83.75		
Min.	651	---	4.3	63	71	2351	2185	2.2	4.4	755	139	78.23		
Test Period #8; A/C = 4.1; Molar Ratio = 0.72														
Average	650	---	5.5	75	71	2483	2342	4.3	4.7	799	168	78.57		
Max.	651	---	6.7	81.0	71	2680	2437	5.1	5.5	867	199	81.06		
Min.	648	---	4.2	72	70	2349	2209	3.5	4.0	727	144	76.09		
Test Period #9; A/C = 1.51; Molar Ratio = 0.91														
Average	653	653	3.1	79.1	72.8	2471	2348	4.2	4.8	808	37	95.25	21.8	20.7
Max.	658	658	3.8	81.9	76.1	2697	2529	6.1	6.9	834	77	97.54		
Min.	647	645	1.7	74.4	71.3	2261	2219	3.2	3.7	710	19	90.50		
Test Period #10; A/C = 1.51; Molar Ratio = 0.77														
Average	654	657	2.9	80.4	74.2	2391	2331	4.8	5.2	803	88	88.77		
Max.	656	658	3.8	82.1	77.6	2517	2445	6.5	8.7	820	114	92.39		
Min.	652	654	0.9	79.4	72.6	2210	2200	4.0	4.4	768	60	84.78		
Test Period #11; A/C = 1.53; Molar Ratio = 0.69														
Average	652	653	3.7	78.6	72.2	2474	2421	4.5	5.2	796	125	83.62		
Max.	654	655	4.6	80.4	75.5	2622	2560	5.9	7.3	819	160	88.02		
Min.	651	652	2.0	77.6	70.5	2309	2294	3.5	4.1	742	84	79.36		
Test Period #12; A/C = 3.0; Molar Ratio = 0.91														
Average	651	---	5.5	72.4	72.0	2426	2328	4.3	5.3	805	103	86.49	13.8	29.2
Max.	658	---	7.6	75.3	73.8	2616	2481	6.0	7.8	851	156	91.21		
Min.	637	---	3.1	69.2	71.1	2204	2118	3.3	4.0	688	53	80.20		

TABLE 8 (continued)

Reverse-Gas Baghouse					Measured						NO _x ^a Removal %	NH ₃ Slip ppm	SO ₃ ^b Slip ppm
Average	Bulk Gas Temp.	Average	East	West	SO ₂	SO ₂	O ₂	O ₂	NO _x	NO _x			
East	West	ΔP	Bag wt.	Bag wt.	Inlet	Outlet	Inlet	Outlet	Inlet	Outlet			
°F	°F	in H ₂ O	lb	lb	ppm	ppm	%	%	ppm	ppm			
Test Period #13; A/C=3.0; Molar Ratio=0.82													
Average	649	---	6.6	69.5	71.2	2438	2345	4.3	5.2	801	119	84.34	
Max.	653	---	8.3	73.9	71.5	2614	2509	7.0	7.1	849	170	88.26	
Min.	642	---	3.9	66.2	70.9	2225	2144	2.7	4.0	694	86	77.83	
Test Period #14; A/C=3.0; Molar Ratio=0.68													
Average	648	---	6.7	67.6	70.8	2515	2394	4.3	5.3	825	165	78.69	
Max.	648	---	8.2	70.8	71.0	2645	2490	5.1	7.9	845	210	81.36	
Min.	647	---	4.8	65.4	70.6	2386	2261	3.6	4.2	798	131	74.32	
Test Period #15; A/C=2.0; Molar Ratio=0.81													
Average	651	650	4.2	72.4	65.2	2528	2460	4.2	4.8	845	94	88.44	11.4
Max.	653	652	5.1	74.8	67.7	2689	2568	5.2	7.0	887	134	90.81	
Min.	648	648	2.9	71.4	63.3	2396	2291	3.3	3.8	653	60	83.62	
Test Period #16; A/C=1.91; Molar Ratio=0.81													
Average	549	547	3.9	59.4	54.9	2542	2442	4.1	4.4	858	275	67.41	
Max.	549	548	4.6	60.8	57.6	2658	2494	4.6	4.9	875	314	69.02	
Min.	548	545	3.0	58.8	53.5	2471	2370	3.5	4.0	826	236	64.06	

^a Corrected to 4% O₂.

^b NH₃ injection turned off.

averaged 96% at an air-to-cloth ratio of 2 ft/min (two bags on line), an ammonia/NO_x molar ratio of 0.91 (roughly 838-ppm NO_x in the flue gas), and an average bulk gas baghouse temperature of 664°F. At an air-to-cloth ratio of 4 ft/min (one bag on line), an ammonia/NO_x molar ratio of 0.72, and an average bulk gas baghouse temperature of 650°F, nitric oxide removal averaged 79%. During the initial test period at an air-to-cloth ratio of 2 ft/min, NO_x removal averaged 96%, which is 5% above what is theoretically possible based on a 1:1 ammonia/NO_x stoichiometry. As in previous tests, this indicates that some NO_x reduction may be occurring as a result of reaction stoichiometries of less than 1:1 ammonia/NO_x. This observation was made during all test periods involving air-to-cloth ratios of 1.5 and 2.0 ft/min, as well as during all test periods involving ammonia/NO_x molar ratios of 0.7 and 0.8. NO_x removal efficiency as a function of time is plotted in Figure 12, with NO_x removal efficiency and ammonia slip (% of inlet NO_x) plotted as a function of ammonia/NO_x molar ratio in Figure 13.

Results summarized in Figure 13 show two distinct sets of NO_x reduction data similar to previous data presented. The first set depicts NO_x reduction (84% to 96%) at air-to-cloth ratios of 1.5 and 2 ft/min for ammonia/NO_x molar ratios ranging from 0.7 to 0.9. Data resulting from air-to-cloth ratios of 3 and 4 ft/min show NO_x reduction ranging from 78% to 87% for ammonia/NO_x molar ratios of 0.68 to 0.93.

The most significant observation is the higher level of NO_x reduction which occurred during Run No. PTC-IL6-428 when compared to the previous 100-hour reverse-gas tests. At all air-to-cloth ratios, the 22-ounce/yd² DE992 fabric evaluated during this run demonstrated a five to six percentage point increase in NO_x reduction, 84% to 96% versus 78% to 90%. The most obvious

Figure 12. NO_x removal efficiency as a function of time, Run PTC-IL6-428.

Figure 13. NO_x removal efficiency as a function of air-to-cloth ratio and ammonia/NO_x molar ratio, Run PTC-IL6-428.

explanation for this increase in NO_x reduction is that the 22-ounce/yd² DE992 fabric has a higher catalyst concentration than the 14-ounce/yd² DE484 fabric. Preliminary analysis indicates that there is 25% more vanadium on the DE992 fabric compared to the DE484 fabric on a mass/yd² of fabric basis.

Ammonia slip measurement results using wet chemistry techniques are also presented in Table 8 and Figure 13. The data show ammonia slip values ranging from 11 to 128 ppm depending on operating conditions. Ammonia slip values in the range of 10 to 20 ppm represent operation at 1.5 and 2 ft/min at an ammonia/NO_x molar ratio of 0.8 to 0.9. Nitric oxide reduction ranged from 88% to 96%, and the baghouse bulk flue gas temperature averaged roughly 655°F.

Ammonia slip values exceeding 100 ppm represent operation at 4 ft/min at an ammonia/NO_x molar ratio of 0.93. Nitric oxide reduction averaged nearly 87%, and the baghouse bulk flue gas temperature averaged 655°F. As discussed previously in this report, these ammonia slip values are higher than what would be expected based on a 1:1 ammonia/NO_x reaction. During the last three outlet particulate sampling periods, the pressure drop across the backup filter increased quickly (<30 minutes), indicating plugging of the filter. When the filters were examined to determine the cause of plugging, they were found to be clean with no evidence of any ash buildup. The filters were checked for ammonium sulfate, which could cause plugging and higher ammonia slip values. These filters contained from 0.58 to 2.03 mg of ammonia. The two outlets with the ammonia injection on showed ammonia slips of 7.6 and 3.0

ppm before adding the filter ammonia. When the ammonia on the filters was included, the ammonia concentrations increased to 13.8 and 11.4 ppm, respectively. Future ammonia slip measurements will involve washing on the filter, filter housing, and sample probe in order to account for any sulfates forming in the sample train.

The ammonia slip data for this 100-hour reverse-gas test show a very sharp rise in ammonia slip as ammonia/NO_x molar ratio increases from 0.9. Although the data are limited, they indicate that ammonia slip is less than 1% of the inlet NO_x concentration when the ammonia/NO_x molar ratio is less than 0.9. Ammonia slip concentrations measured during the 100-hour reverse-gas tests also indicate that the DE992 fabric performed better than the DE484 fabric. More extensive sampling is planned during the first 500-hour test to better quantify ammonia slip over the entire range of operating conditions.

Sulfur trioxide (SO₃) values ranged from 20 to 30 ppm. These values represent roughly 1% of the flue gas SO₂ concentration. The wet chemistry ammonia slip and SO₃ concentration are also reported in Table 8.

4.3.2 Particulate Collection

Pressure drop and particulate emissions data were also collected during each 100-hour test. Using an aerodynamic particle sizer (APS), respirable mass data were collected for each test. EPA Method 5 and multicyclone particulate-sampling were also conducted for each test. A discussion of these results is presented in the following paragraphs.

4.3.2.1 Run PTC-BV-423

For Run PTC-BV-423, respirable mass was plotted as a function of time for air-to-cloth ratios of 1.5, 2, 3, and 4.1 ft/min, in Figures 14 through 21. The outlet respirable mass emissions averaged roughly 0.01 to 60, 0.02 to 30, 0.003, and 0.09 mg/m³ at air-to-cloth ratios of 1.5, 2, 3 and 4.1 ft/min, respectively. Tables 9 and 10 summarize EPA Method 5 and multicyclone particulate-sampling data for Run PTC-BV-423. Initial particulate collection efficiency was poor, roughly 96% at an air-to-cloth ratio of 2 ft/min and an inlet dust loading of 2.39 gr/scf. When the air-to-cloth ratio was changed to 4 ft/min, the particulate collection efficiency increased to 99.4% with an inlet dust loading of 2.63 gr/scf. When the air-to-cloth ratio was changed to 1.5 ft/min, the respirable mass measured with the APS increased. From the APS data, it was evident that the bag in the west chamber had holes or was not fitted properly to the thimble. Figure 22 plots the respirable mass for each bag at an air-to-cloth ratio of 4.1 ft/min. It was decided to operate at an air-to-cloth ratio of 3 ft/min (one bag on-line), while replacing the bag in the west chamber. With the new bag in place and at an air-to-cloth ratio of 2 ft/min, particulate collection efficiency improved to 99.4% at an inlet dust loading of 2.09 gr/scf. When examined, the damaged bag was found to have several holes near the top. The particulate mass loading in the flue gas prior to the reverse-gas baghouse ranged from 2.09 to 2.91 gr/scf. The overall collection efficiency for the undamaged reverse-gas bags ranged from 99.34% to 99.66%, depending on operating conditions.

Figure 14. Respirable mass emissions as a function of time at an air-to-cloth ratio of 2 ft/min, Run PTC-BV-423.

Figure 15. Respirable mass emissions as a function of time at an air-to-cloth ratio of 4.1 ft/min, Run PTC-BV-423.

Figure 16. Respirable mass emissions as a function of time at an air-to-cloth ratio of 1.5 ft/min, Run PTC-BV-423.

Figure 17. Respirable mass emissions as a function of time at an air-to-cloth ratio of 3 ft/min, Run PTC-BV-423.

Figure 18. Respirable mass emissions as a function of time at an air-to-cloth ratio of 2 ft/min, Run PTC-BV-423.

Figure 19. Respirable mass emissions as a function of time at an air-to-cloth ratio of 2 ft/min, Run PTC-BV-423.

Figure 20. Respirable mass emissions as a function of time at an air-to-cloth ratio of 1.5 ft/min, Run PTC-BV-423.

Figure 21. Respirable mass emissions as a function of time at an air-to-cloth ratio of 2 ft/min, Run PTC-BV-423.

TABLE 9
Particulate Sampling Data
for Pilot-Scale Catalytic Fabric Filter Tests

Test Date	Inlet gr/scf	Outlet gr/scf	%H ₂ O	% Efficiency ^a
Shakedown				
08-28-91	3.4774	---	10.5	---
08-28-91	---	0.0015	9.1	99.96
08-28-91	2.6611	---	10.2	---
PTC-IL6-408				
11-18-91	3.1843	---	10.7	---
11-18-91	---	0.0028	8.1	99.91
11-18-91	---	0.0036	7.8	99.89
11-19-91	2.7771 ^b	---	5.2	---
11-19-91	---	0.0008	7.5	99.97
11-19-91	2.8891	---	7.6	---
11-20-91	3.109	---	9.6	---
11-20-91	---	0.0065	7.9	99.79
11-21-91	3.3357	---	9.1	---
11-21-91	2.4938 ^b	---	3.9	---
11-21-91	---	0.0014	7.6	99.58
11-22-91	3.191	---	8.1	---
11-22-91	---	0.0008	7.6	99.97
PTC-IL6-414				
01-13-92	3.5102	---	9.1	---
01-13-92	---	0.0127	6.6	99.64
01-13-92	---	0.0076	5.6	99.78
01-14-92	--- ^c	---	---	---
01-14-92	2.7997	---	9.5	---
01-14-92	---	0.1099	6.9	96.07
PTC-IL6-415				
02-03-92	3.2273	---	7.5	---
02-03-92	---	0.0033	6.8	99.90
02-04-92	2.7413	---	8.5	---
02-04-92	---	0.007	6.5	99.74
02-04-92	3.1062	---	8.5	---
02-04-92	---	0.0134	8.3	99.57
02-05-92	2.5742	---	7.7	---
02-05-92	---	0.0182	7.9	99.29
02-05-92	2.3597 ^b	---	6.7	---
02-06-92	3.0250	---	7.6	---
02-06-92	---	0.0122	6.2	99.60
02-07-92	2.7319	---	6.3	---

TABLE 9 (continued)

Test Date	Inlet gr/scf	Outlet gr/scf	%H ₂ O	% Efficiency ^a
02-07-92	---	0.0250	6.3	99.08
02-07-92	2.7653 ^b	---	7.8	---
PTC-IL6-416				
02-10-92	2.6814	---	8.5	---
02-10-92	---	0.0114	7.5	99.57
02-10-92	---	0.0069	8.2	99.74
02-11-92	2.8368	---	7.6	---
02-11-92	---	0.0170	5.5	99.40
02-11-92	3.3836 ^b	---	6.3	---
02-12-92	2.8452	---	7.8	---
02-12-92	---	0.0138	5.7	99.52
PTC-IL6-417				
02-24-92	3.0147	---	9.3	---
02-24-92	---	0.0154	7.9	99.49
02-24-92	---	0.0186	7.3	99.38
02-25-92	2.8668	---	7.3	---
02-25-92	---	0.0178	7.7	99.38
02-25-92	2.8518 ^b	---	4.6	---
02-26-92	2.9464	---	8.0	---
02-26-92	---	0.0182	8.1	99.37
02-26-92	---	0.0338	8.1	99.85
02-27-92	3.0054	---	13.6	---
02-27-92	---	0.0322	7.6	99.13
02-27-92	3.6961 ^b	---	7.4	---
02-28-92	2.8621	---	7.2	---
02-28-92	---	0.0164	6.6	99.43
02-27-92	---	0.0186	7.5	99.35
PTC-IL6-419				
03-09-92	3.2729	---	8.3	---
03-09-92	---	0.0279	8.3	99.15
03-09-92	---	0.0126	8.5	99.61
03-10-92	2.9588	---	7.5	---
03-10-92	---	0.0212	7.2	99.28
03-10-92	2.8594 ^b	---	7.0	---
03-11-92	2.4762	---	9.1	---
03-11-92	---	0.0006	0.0	99.98
03-11-92	---	0.0088	7.2	99.64
03-13-92	---	0.0190	7.3	99.35
03-13-92	---	0.0157	7.0	99.47
03-12-92	2.7558 ^b	---	7.4	---
03-12-92	2.2041	---	6.5	---

TABLE 9 (continued)

Test Date	Inlet gr/scf	Outlet gr/scf	%H ₂ O	% Efficiency ^a
03-12-92 ^b	---	---	---	---
03-13-92	2.9318	---	8.0	---
PTC-BV-423				
04-20-92	2.2618	---	8.7	---
04-20-92	---	0.0708	6.4	96.87 ^d
04-20-92	---	0.0808	6.9	96.48 ^d
04-20-92	2.2943	---	7.9	---
04-21-92	2.6303	---	7.0	---
04-21-92	---	0.0169	6.0	99.36
04-21-92	2.3934 ^b	---	6.0	---
04-22-92	2.7201	---	7.2	---
04-22-92	---	0.0096	5.7	99.65
04-22-92	2.9149	---	6.6	---
04-22-92	---	0.0098	5.9	99.66
04-23-92	2.0867	---	6.9	---
04-23-92	---	0.0137	5.7	99.35
04-23-92	---	0.0188	5.7	99.43
04-24-92	2.4166	---	6.2	---
04-24-92	---	0.0096	5.8	99.60
04-24-92	---	0.0140	5.9	99.42
PTC-BT-424				
04-27-92	1.4438	---	11.2	---
04-27-92	---	0.0019	9.8	99.87
04-27-92	1.4580	---	13.0	---
04-28-92	1.4172	---	9.0	---
04-28-92	---	0.0013	10.4	99.91
04-28-92	---	0.0017	9.9	99.88
04-28-92	1.3724 ^b	---	10.0	---
04-29-92	1.6121	---	6.9	---
04-29-92	---	0.0014	11.1	99.91
04-29-92	1.6095	---	12.8	---
04-29-92	---	0.0031	11.1	99.81
04-30-92	1.6565	---	10.4	---
04-30-92	---	0.0020	11.4	99.88
04-30-92	1.5001 ^b	---	11.0	---
04-30-92	---	0.0022	11.2	99.86
05-01-92	1.2015	---	10.8	---
05-01-92	---	0.0012	10.8	99.90
PTC-BU-425				
05-04-92	3.1896	---	13.3	---
05-04-92	3.2460	---	13.4	---

TABLE 9 (continued)

Test Date	Inlet gr/scf	Outlet gr/scf	%H ₂ O	% Efficiency ^a
05-04-92	---	0.0016	11.9	99.95
05-05-92	2.8109	---	10.2	---
05-05-92	---	0.0024	12.3	99.93
05-05-92	---	0.0027	12.6	99.90
05-05-92	3.0938 ^b	---	10.9	---
05-06-92	2.9817	---	13.0	---
05-06-92	---	0.0022	12.5	99.93
05-06-92	2.6618	---	12.0	---
05-06-92	---	0.0020	13.1	99.93
05-07-92	2.9079	---	11.3	---
05-07-92	---	0.0022	12.7	99.92
05-07-92	2.3009 ^b	---	12.2	---
05-08-92	2.8196	---	13.5	---
05-08-92	---	0.0040	12.7	99.86
PTC-IL6-426				
05-11-92	---	3.9122	---	9.6
05-11-92	---	0.0273	8.2	99.30
05-12-92	3.0983	---	7.9	---
05-12-92	---	0.0141	7.6	99.55
05-12-92	---	0.0079	7.6	99.75
05-13-92	4.0802	---	7.4	---
05-13-92	---	0.0022	6.8	99.95
05-13-92	---	0.0026	6.5	99.94
05-14-92	4.1596	---	7.4	---
05-14-92	---	0.0295	7.6	99.29
05-15-92	3.7020	---	6.9	---
05-15-92	---	0.0148	6.7	99.60
PTC-IL6-427				
05-19-92	2.5287	---	9.0	---
05-19-92	---	0.0161	8.6	99.37
05-19-92	---	0.0110	9.1	99.57
05-21-92	2.6484	---	9.3	---
05-21-92	---	0.0069	9.1	99.74
05-21-92	---	0.0127	9.1	99.52
PTC-IL6-428				
06-08-92	2.7129	---	10.8	---
06-08-92	---	0.0142	10.1	99.48
06-08-92	---	0.0178	10.1	99.34
06-09-92	2.7043 ^b	---	9.7	---
06-09-92	---	0.0184	10.0	99.32
06-09-92	---	0.0170	9.1	99.37

TABLE 9 (continued)

Test Date	Inlet gr/scf	Outlet gr/scf	%H ₂ O	% Efficiency ^a
06-10-92	2.7906	---	10.5	---
06-10-92	---	0.0111	10.8	99.60
06-10-92	---	0.0141	9.4	99.49
06-11-92	2.6813 ^b	---	9.8	---
06-11-92	---	0.0107	10.0	99.60
06-11-92	---	0.0105	11.6	99.61
06-12-92	2.9665	---	10.2	---
06-12-92	---	0.0160	9.4	99.46
06-12-92	---	0.0151	9.0	99.49

^a Ammonia injection on.^b Multicyclone sampling.^c Sampling error.^d Damaged bag.

TABLE 10

Multicyclone Data from Run PTC-BV-423

PTC-BV-423 04-21-92	CY1	CY2	CY3	CY4	CY5	Backup Filter
d ₅₀ (μm)	9.47	6.21	3.34	2.29	0.95	---
Mass Collected (g)	1.6890	0.1214	0.1114	0.0357	0.029	0.0029
% Total Mass	84.89	6.10	5.60	1.79	1.48	0.14
Cumulative % Mass less than d ₅₀	15.11	9.01	3.41	1.62	0.14	---
Total Mass Collected = 1.9896 g, Dust Loading = 2.3934 gr/scf and % Isokinetic = 98.70						

The operational pressure drop across the bags was the second parameter for performance evaluation. The bags were cleaned such that the maximum differential baghouse pressure was approximately 4 inches W.C. Figure 23 shows the pressure drop as a function of time. As expected, the time between bag cleanings was dependent on air-to-cloth ratio, every 2 hours at 2 ft/min and every 30 minutes at 4 ft/min.

Figure 22. Respirable mass emissions for east and west reverse-gas baghouse chambers, Run PTC-BV-423.

Figure 23. Baghouse differential pressure as a function of time, Run PTC-BV-423.

4.3.2.2 Run PTC-BT-424

For the 100-hour Run PTC-BT-424, respirable mass was plotted as a function of time for air-to-cloth ratios of 1.5, 2, 3, and 4 ft/min in Figures 24-31. The outlet respirable mass emissions averaged roughly 0.001 mg/m³ for an air-to-cloth ratio of 1.5 ft/min, 0.1-0.0005 mg/m³ at an air-to-cloth ratio of 2.0 ft/min, 0.005 mg/m³ at an air-to-cloth ratio 3.0 ft/min, and 0.1 mg/m³ at an air-to-cloth ratio of 4.2 ft/min. Tables 9 and 11 summarize EPA Method 5 and multicyclone particulate-sampling data. The particulate mass loading in the flue gas prior to the reverse-gas baghouse ranged from 1.20 to 1.66 gr/scf. The overall collection efficiency for the reverse-gas baghouse ranged from 99.8% to 99.90%, depending on operating conditions.

Figure 32 plots the pressure drop across the bags as a function of time. At an air-to-cloth ratio of 2 ft/min, a 1-hour cleaning cycle was required to maintain a baghouse differential pressure of 5 inches W.C., and a 2-hour cleaning cycle was required at 1.5 ft/min. At 3 ft/min, a half-hour cleaning cycle was required to maintain a baghouse differential pressure drop of 9 inches W.C., and a 15-minute cleaning cycle was required at 4 ft/min. Fly ash from Black Thunder coal has been observed to cause high baghouse pressure drop during other pilot-scale tests at the EERC, indicating that the material may cause bag-cleaning problems.

4.3.2.3 Run PTC-BU-425

For the 100-hour Run PTC-BU-425, respirable mass was plotted as a function of time for air-to-cloth ratios of 1.5, 2, 3.1, and 4 ft/min, shown in Figures 33-41. The outlet respirable mass emissions averaged roughly 0.006 mg/m³ for an air-to-cloth ratio of 1.5 ft/min, 0.003 mg/m³ at an air-to-cloth ratio of 2 ft/min, 0.02 mg/m³ at an air-to-cloth ratio of 3.1 ft/min, and 0.003 mg/m³ at an air-to-cloth ratio of 4 ft/min. Tables 9 and 12 summarize EPA Method 5 and multicyclone particulate-sampling data. The particulate mass loading in the flue gas prior to the reverse-gas baghouse ranged from 2.66 to 3.25 gr/scf. An inlet dust loading of 2.30 gr/scf was observed during a multicyclone sampling period, which is low and may be due to low isokinetic efficiency. The overall collection efficiency for the reverse-gas baghouse ranged from 99.86% to 99.95%, depending on operating conditions.

Figure 42 plots the pressure drop across the bags as a function of time. At an air-to-cloth ratio of 1.5 ft/min, a 4-hour cleaning cycle was required to maintain a baghouse differential pressure of less than 6 inches W.C., and a 2-hour cleaning cycle was required at 2 ft/min to control differential pressure at 4 inches W.C. At 3 ft/min, a 1-hour cleaning cycle was required to maintain a baghouse differential pressure drop of 8 inches W.C., and a 30-minute cleaning cycle was required at 4 ft/min.

4.3.2.4 Run PTC-IL6-426

For Run PTC-IL6-426, respirable mass was plotted as a function of time at an air-to-cloth ratio of 2 ft/min (see Figures 43 and 44). The outlet respirable mass emissions ranged from 0.1 to 0.6 mg/m³; Table 9 summarizes EPA Method 5 particulate-sampling data. The particulate mass loading in the flue gas prior to the reverse-gas baghouse ranged from 3.10 to 4.16 gr/scf, which is much higher than the average inlet dust loading (2.77 gr/scf) for other

Figure 24. Respirable mass emissions as a function of time at an air-to-cloth ratio of 2 ft/min, Run PTC-BT-424.

Figure 25. Respirable mass emissions as a function of time at an air-to-cloth ratio of 2 ft/min, Run PTC-BT-424.

Figure 26. Respirable mass emissions as a function of time at an air-to-cloth ratio of 4.2 ft/min, Run PTC-BT-424.

Figure 27. Respirable mass emissions as a function of time at an air-to-cloth ratio of 3 ft/min, Run PTC-BT-424.

Figure 28. Respirable mass emissions as a function of time at an air-to-cloth ratio of 1.6 ft/min, Run PTC-BT-424.

Figure 29. Respirable mass emissions as a function of time at an air-to-cloth ratio of 1.5 ft/min, Run PTC-BT-424.

Figure 30. Respirable mass emissions as a function of time at an air-to-cloth ratio of 2.1 ft/min, Run PTC-BT-424.

Figure 31. Respirable mass emissions as a function of time at an air-to-cloth ratio of 2.1 ft/min, Run PTC-BT-424.

TABLE 11
Multicyclone Data from Run PTC-BT-424

PTC-BT-424 04-28-92	CY1	CY2	CY3	CY4	CY5	Backup Filter
d ₅₀ (μm)	9.31	6.13	3.31	2.25	0.94	---
Mass Collected (g)	0.8939	0.0785	0.0944	0.0409	0.0429	0.0134
% Total Mass	76.79	6.75	8.11	3.51	3.69	1.15
Cumulative % Mass less than d ₅₀	23.21	16.46	8.35	4.84	1.15	---
Total Mass Collected = 1.1640 g, Dust Loading = 1.372 gr/scf, and % Isokinetic = 99.50						
04-30-92	CY1	CY2	CY3	CY4	CY5	Backup Filter
d ₅₀ (μm)	11.18	8.13	4.54	3.01	1.24	---
Mass Collected (g)	0.7423	0.0601	0.0709	0.0382	0.0473	0.0217
% Total Mass	75.71	6.13	7.23	3.90	4.82	2.21
Cumulative % Mass less than d ₅₀	24.29	18.16	10.93	7.03	2.21	---
Total Mass Collected = 0.9804 g, Dust Loading = 1.5001 gr/scf, and % Isokinetic = 96.80						

runs with Illinois #6 bituminous coal. Dust loadings calculated using the flue gas flow rate, weight of the hopper ash, and run time confirm the high dust loadings. It appears the coal particle size was larger than average, causing an increase in carbon carryover which resulted in an increased inlet dust loading. The overall collection efficiency for the reverse-gas baghouse ranged from 99.29% to 99.95%, depending on operating conditions.

The baghouse differential pressure is plotted as a function of time in Figure 45. A 2-hour cleaning cycle was required to maintain a baghouse differential pressure of less than 4 inches W.C. at an air-to-cloth ratio of 2 ft/min.

Figure 32. Baghouse differential pressure as a function of time, Run PTC-BT-424.

Figure 33. Respirable mass emissions as a function of time at an air-to-cloth ratio of 2 ft/min, Run PTC-BU-425.

Figure 34. Respirable mass emissions as a function of time at an air-to-cloth ratio of 2 ft/min, Run PTC-BU-425.

Figure 35. Respirable mass emissions as a function of time at an air-to-cloth ratio of 4 ft/min, Run PTC-BU-425.

Figure 36. Respirable mass emissions as a function of time at an air-to-cloth ratio of 4.1 ft/min, Run PTC-BU-425.

Figure 37. Respirable mass emissions as a function of time at an air-to-cloth ratio of 3.1 ft/min, Run PTC-BU-425.

Figure 38. Respirable mass emissions as a function of time at an air-to-cloth ratio of 3 ft/min, Run PTC-BU-425.

Figure 39. Respirable mass emissions as a function of time at an air-to-cloth ratio of 1.5 ft/min, Run PTC-BU-425.

Figure 40. Respirable mass emissions as a function of time at an air-to-cloth ratio of 1.5 ft/min, Run PTC-BU-425.

Figure 41. Respirable mass emissions as a function of time at an air-to-cloth ratio of 2 ft/min, Run PTC-BU-425.

TABLE 12
Multicyclone Data from Run PTC-BU-425

PTC-BU-425 05-05-92	CY1	CY2	CY3	CY4	CY5	Backup Filter
d_{50} (μm)	10.18	7.05	3.86	2.60	1.07	---
Mass Collected (g)	1.7123	0.1978	0.2099	0.0994	0.0744	0.0428
% Total Mass	73.28	8.46	8.98	4.25	3.18	1.83
Cumulative % Mass less than d_{50}	26.72	18.25	9.27	5.01	1.83	---
Total Mass Collected = 2.3366 g, Dust Loading = 3.0938 gr/scf, and % Isokinetic = 97.50						
05-07-92	CY1	CY2	CY3	CY4	CY5	Backup Filter
d_{50} (μm)	12.20	9.27	5.27	3.44	1.40	---
Mass Collected (g)	0.9235	0.0855	0.1349	0.0741	0.0549	0.0677
% Total Mass	68.89	6.38	10.07	5.53	4.09	5.05
Cumulative % Mass less than d_{50}	31.11	24.73	14.67	9.14	5.05	---
Total Mass Collected = 1.3405 g, Dust Loading = 2.3009 gr/scf, and % Isokinetic = 93.20						

4.3.2.5 Run PTC-IL6-427

For Run PTC-IL6-427, respirable mass was plotted as a function of time for an air-to-cloth ratio of 2 ft/min, shown in Figures 46 and 47. The outlet respirable mass emissions ranged from 0.001 to 0.0002 mg/m³. Table 9 summarizes EPA Method 5 particulate-sampling data. Particulate collection efficiency during the 100-hour test averaged 99.6% at an inlet dust loading to the filters of roughly 2.6 gr/scf. It appears particulate collection efficiency was not affected by the dew point conditions, since similar

Figure 42. Baghouse differential pressure as a function of time, Run PTC-BU-425.

Figure 43. Respirable mass emissions as a function of time at an air-to-cloth ratio of 2 ft/min, Run PTC-IL6-426.

Figure 44. Respirable mass emissions as a function of time at an air-to-cloth ratio of 2 ft/min, Run PTC-IL6-426.

Figure 45. Baghouse differential pressure as a function of time, Run PTC-IL6-426.

Figure 46. Respirable mass emissions as a function of time at an air-to-cloth ratio of 2 ft/min, Run PTC-IL6-427.

Figure 47. Respirable mass emissions as a function of time at an air-to-cloth ratio of 2 ft/min, Run PTC-IL6-427.

collection efficiency was observed during the previous 100-hour test. Also, pressure drop was easily controlled; therefore, bag blinding was not a problem. The potential for bag blinding was minimized procedurally since dew point excursions were the result of natural gas firing and normal baghouse temperatures were achieved prior to resuming coal firing.

4.3.2.6 Run PTC-IL6-428

For the 100-hour Run PTC-IL6-428, respirable mass was plotted as a function of time for air-to-cloth ratios of 1.5, 2, 3, and 4 ft/min, shown in Figures 48-52. The outlet respirable mass emissions averaged roughly 0.002 mg/m³ for air-to-cloth ratios of 1.5 and 2 ft/min, 0.004 mg/m³ at an air-to-cloth ratio of 3 ft/min, and 0.005 mg/m³ at an air-to-cloth ratio of 4 ft/min. Tables 9 and 13 summarize EPA Method 5 and multicyclone particulate-sampling data. The particulate mass loading in the flue gas prior to the reverse gas baghouse ranged from 2.68 to 2.97 gr/scf. The overall collection efficiency for the reverse gas baghouse ranged from 99.3% at an air-to-cloth ratio of 4 ft/min to 99.6% at an air-to-cloth ratio of 3 ft/min.

The baghouse differential pressure is plotted as a function of time in Figure 53. At an air-to-cloth ratio of 1.5 ft/min, a 4-hour cleaning cycle was required to maintain a baghouse differential pressure of less than 4 inches W.C. A 4-hour cleaning cycle was required at 2 ft/min to maintain a baghouse differential pressure of less than 3 inches W.C. at the beginning of the 100-hour test. A 1-hour cleaning cycle was required at the end of the 100-hour test, when the air-to-cloth ratio was returned to 2 ft/min, to maintain a baghouse differential pressure drop of less than 5 inches W.C. A 1-hour cleaning cycle was required at air-to-cloth ratios of 3 and 4 ft/min to maintain respective baghouse differential pressure drops of less than 9 and 8 inches W.C.

4.3.3 Summary of Reverse-Gas Baghouse Test Results

During this reporting period, 100-hour tests were performed to determine the effect of coal type, temperature acid dew point, water dew point, and fabric type on NO_x and particulate removal efficiency.

Results from the 100-hour tests did not indicate that coal type has a significant effect on NO_x removal efficiency (see Figure 7). However, when firing the Illinois #6 bituminous coal reduced NO_x removal efficiency was observed at higher air-to-cloth ratios, but this may have been due to pinholing and the resulting gas channeling.

At this point, it is clear that NO_x reduction decreases as baghouse flue gas temperature decreases from 650°F. However, results from Run PTC-IL6-426 may have been affected by the formation of ammonium sulfate or bisulfate upstream of the baghouse. Therefore, the quantitative value of the data is questionable and the results must be considered qualitative. Future runs will include short test periods to verify the results from Run PTC-IL6-426.

It was also found that an acid dew point reduced NO_x removal efficiency by roughly 23%, and a water dew point had no additional effect on NO_x removal. Overall, the NO_x removal efficiencies for Runs PTC-BV-423, PTC-BT-424, PTC-BU-

Figure 48. Respirable mass emissions as a function of time at an air-to-cloth ratio of 2 ft/min, Run PTC-IL6-428.

Figure 49. Respirable mass emissions as a function of time at an air-to-cloth ratio of 4 ft/min, Run PTC-IL6-428.

Figure 50. Respirable mass emissions as a function of time at an air-to-cloth ratio of 1.5 ft/min, Run PTC-IL6-428.

Figure 51. Respirable mass emissions as a function of time at an air-to-cloth ratio of 3 ft/min, Run PTC-IL6-428.

Figure 52. Respirable mass emissions as a function of time at an air-to-cloth ratio of 2 ft/min, Run PTC-IL6-428.

425, and PTC-IL6-428 were quite good (71% to 96%). For each run there are two distinct sets of NO_x removal data: one set representing air-to-cloth ratios of 1.5 and 2 ft/min, and the second 3 and 4 ft/min.

When evaluating NO_x reduction as a function of time for each 100-hour run, it appears that during a few runs a small decrease in NO_x reduction may be occurring. Due to the relatively short duration of each run and frequent change in test conditions, a specific conclusion cannot be drawn at this time. The performance of the catalyst-coated fabric as a function of time will be evaluated during a 500-hour test planned for the next quarter.

Also, during each run, NO_x removal efficiencies greater than theoretical, based on a 1:1 NH_3/NO_x reaction, were observed. This occurred at lower ammonia/ NO_x (0.7 and 0.8) and air-to-cloth ratios (1.5 and 2) and may be due to an ammonia/ NO_x reaction stoichiometry of less than 1:1. Completion of additional test periods and further data evaluation will be necessary before a firm conclusion can be drawn.

Ammonia slip values presented in Figures 2, 4, 6, and 13 show a general trend toward increasing ammonia slip with increasing ammonia/ NO_x molar ratio. However, the data are quite variable and taken over a small range of ammonia/ NO_x molar ratios. During future tests, ammonia slip data will be collected at lower ammonia/ NO_x molar ratios in order to develop a more thorough understanding of ammonia slip.

TABLE 13

Multicyclone Data from Run PTC-IL6-428

PTC-IL6-428 06-09-92	CY1	CY2	CY3	CY4	CY5	Backup Filter
d_{50} (μm)	8.61	5.40	2.87	1.99	0.83	---
Mass Collected (g)	2.1431	0.2253	0.1331	0.0412	0.0206	0.0297
% Total Mass	82.65	8.69	5.13	1.59	0.79	1.14
Cumulative % Mass less than d_{50}	17.35	8.66	3.53	1.94	1.14	---
Total Mass Collected = 2.5930 g, Dust Loading = 2.7043 gr/scf, and % Isokinetic = 99.50						
06-11-92	CY1	CY2	CY3	CY4	CY5	Backup Filter
d_{50} (μm)	10.56	7.40	4.08	2.73	1.13	---
Mass Collected (g)	1.5065	0.1702	0.1372	0.0563	0.0404	0.0134
% Total Mass	78.30	8.85	7.13	2.93	2.10	0.70
Cumulative % Mass less than d_{50}	21.70	12.85	5.72	2.80	0.70	---
Total Mass Collected = 1.9240 g, Dust Loading = 2.6813 gr/scf, and % Isokinetic = 97.50						

To this point, the particulate collection efficiency for the reverse-gas bags made from DE484 fabric has ranged from 99.08%, based on a measured outlet loading of 0.025 gr/scf during PTC-IL6-415, to 99.97%, based on a measured outlet loading of 0.0008 gr/scf during PTC-IL6-408. The particulate collection efficiency for the DE484 fabric has averaged 99.69% over eight tests. From the data, it can be seen that the collection efficiency was highest for the Beulah North Dakota lignite and lowest for the Blacksville bituminous coal. Collection efficiency for bags made with DE992 fabric has ranged from 99.15%, based on a measured outlet loading of 0.0279 gr/scf during PTC-IL6-419, to 99.98%, based on a measured outlet loading of 0.0006 during the same run. The particulate collection efficiency for the DE992 fabric averaged 99.51% over three tests. The average particulate collection efficiencies for each type of fabric meets the project objective of 99.5%; however, 99.9% particulate control should be possible with each fabric. The

Figure 53. Baghouse differential pressure as a function of time, Run PTC-IL6-428.

DE484 fabric also met the 99.5% collection efficiency objective for each coaltyle, with the Beulah lignite performing the best. During outlet sampling for Run PTC-IL6-428, the formation of ammonium sulfate in the sample train was observed. It appears that the ammonium sulfate added to the outlet dust loadings for all runs, except PTC-BT-424 and PTC-BU-425, effectively decreased the particulate collection efficiencies. In future 100-hour tests, outlet sampling will be conducted with ammonia injection on and off in order to determine the effect of ammonia injection on particulate collection efficiency.

Multicyclone sampling at the inlet of the baghouse was completed in order to determine the aerodynamic particle size of the fly ash in the flue gas stream entering the baghouse for each test and each coal. Results show that for the Illinois #6 bituminous coal, roughly 81% of the mass had a particle size greater than $10\ \mu m$. For the Blacksville bituminous coal, roughly 85% of the mass had a particle size greater than $9.5\ \mu m$, and roughly 76% of the mass had a particle size greater than $10\ \mu m$ for the Black Thunder subbituminous coal. For the Beulah lignite, roughly 71% of the mass had a particle size greater than $11\ \mu m$.

From the multicyclone and Coulter counter data shown in Figures 54-61, the mass median diameter (volumetric median diameter) of the fly ash for each coal was determined. It was roughly $18\ \mu m$ for the Illinois #6 bituminous coal, $17\ \mu m$ for the Blacksville bituminous coal, and $21\ \mu m$ for the Black Thunder subbituminous coal. For the Beulah lignite, the mass median diameter was roughly $20\ \mu m$.

Figure 54. Coulter counter data for Illinois #6 bituminous coal.

Figure 55. Coulter counter data for Blacksville bituminous coal.

Figure 56. Coulter counter data for Black Thunder subbituminous coal.

Figure 57. Coulter counter data for North Dakota Beulah lignite.

Figure 58. Multicyclone data for Illinois #6 bituminous coal.

Figure 59. Multicyclone data for Blacksville bituminous coal.

Figure 60. Multicyclone data for Black Thunder subbituminous coal.

Figure 61. Multicyclone data for North Dakota Beulah lignite.

Bulk ash samples collected from the hopper of the reverse-gas baghouse for each test were analyzed for carbon and major elements. The carbon content of the ash, as determined by loss on ignition, and the major elements, as determined by x-ray fluorescence (XRF) analysis, for each coal are presented in Table 14. Loss-on-ignition data in the table indicates that combustion efficiency when firing the Blacksville bituminous coal was poor. Coal sieve analysis indicated that the coal particle size was larger than desired, only 50% to 55% -200 mesh. Extra attention will have to be given to the preparation of the Blacksville coal during future 100- and 500-hour tests. The chemical composition of the ash samples analyzed are fairly typical for the coals fired. High silica, alumina, and iron were observed in the bituminous coal ash, and the alkali constituents are found in relatively low concentrations. The subbituminous and lignite ash samples exhibit higher alkali content and lower silica, alumina, and iron.

A concern with the use of catalyst-coated bags is the possibility of catalyst erosion resulting in an increase in the vanadium content of the fly ash. Although vanadium is not a RCRA element, some vanadium compounds are considered to be hazardous materials. It is important to monitor vanadium concentration in the fly ash in order to determine if a catalyst is lost from the fabric. Table 15 presents the vanadium concentration on unused and used samples for most fabric types. From the results, it appears there was generally no loss of vanadium catalyst from the G143 and DE484 bags. Although the used fabric samples are cleaned before being submitted, they still contain a certain amount of ash. This potential dilution effect may explain the small vanadium concentration difference between the used and unused fabric samples. For Runs PTC-IL6-419 and PTC-IL6-427, extraneous ash could not be responsible for the large difference in vanadium concentration, and the results must be attributed to loss of catalyst from the bags. The DE992 bags from Run PTC-IL6-419 lost 19% of the vanadium catalyst. In this case, the loss of catalyst may be due to the undercoat applied to the bags. The upset conditions of Run PTC-IL6-427 appear to have caused approximately 25% loss of vanadium catalyst from the bags.

A used sample for the DE992 fabric used during Run PTC-IL6-428 had not been analyzed as of the preparation of this report. Based on the NO_x reduction and ammonia slip results previously discussed, analytical results are expected to show no loss of catalyst from the DE992 fabric.

Table 16 presents the vanadium content of the coal, fly ash from the inlet to the reverse-gas baghouse, and ash from the baghouse hopper as determined by atomic absorption (AA) analysis. The vanadium concentration in the reverse-gas baghouse ash for Run PTC-BV-423 was lower than that for the other coals due to a difference, in the vanadium content of the coal. For the remainder of the available data, when comparing the vanadium concentration of the inlet fly ash to the theoretical concentration based on the concentration of the vanadium and ash in the coal, there is a distinct increase in the vanadium in the fly ash. An explanation is that vanadium is known to be enriched in the fine particulate matter as a result of initial vaporization in the flame zone and subsequent condensation on fine ash particles (8). Although the concentration of the vanadium in the combustor bottom ash is not known, it is expected to be less than the concentration of the fly ash.

TABLE 14

Reverse-Gas Baghouse Ash Analysis Results

Loss on Ignition (wt%)	Illinois #6		Blacksville		Black Thunder		Beulah Lignite	
	<u>Average</u>	<u>Maximum</u>	<u>Minimum</u>	<u>Average</u>	<u>Maximum</u>	<u>Minimum</u>	<u>Average</u>	<u>Minimum</u>
Oxides (wt% of ash)								
SiO ₂	51.54	52.74	49.80	45.11	46.50	43.80	31.53	29.01
Al ₂ O ₃	19.47	20.90	17.41	21.22	21.99	20.40	14.41	13.13
Fe ₂ O ₃	18.49	21.90	16.10	21.38	23.29	18.54	6.69	4.84
TiO ₂	0.93	1.27	0.68	0.99	1.10	0.75	0.53	0.48
P ₂ O ₅	0.28	1.72	0.18	0.26	0.37	0.19	0.52	0.39
CaO	3.77	4.63	3.15	6.13	6.46	5.53	19.69	18.72
MgO	1.03	2.04	0.00	1.24	3.93	0.99	7.01	6.68
Na ₂ O	0.79	1.08	0.00	0.64	0.70	0.58	9.23	5.74
K ₂ O	2.05	2.30	0.62	1.22	1.39	1.11	0.41	0.35
SO ₃	1.62	3.77	1.13	1.81	2.51	1.36	10.02	4.18
							0.44	0.04
				1.14	1.76	0.87		
				41.34	43.57	39.90		
				16.65	17.21	16.24		
				5.60	5.96	5.34		
				1.17	1.21	1.15		
				0.66	0.72	0.56		
				24.06	24.86	22.48		
				7.02	7.27	6.86		
				1.26	1.45	1.05		
				0.38	0.43	0.33		
				1.86	2.22	1.41		

TABLE 15
Vanadium Concentration on Reverse-Gas Bags

Fabric Type	Vanadium Concentration, $\mu\text{g/g}$		Run
	Unused Bags	Used Bags	
G143	5300	5000	PTC-IL6-417 & PTC-NG-420
DE484	7900	7533	PTC-IL6-408/ 415 & PTC-NG-421
DE484	7900	5900	PTC-IL6-427
DE992- Undercoat	6200	5033	PTC-IL6-419
DE992	6800	---	PTC-IL6-428

4.4 Subtask 3.3 Process Testing/Pulse-Jet System

Work was initiated in March with respect to evaluating equipment needs and options for the oil-fired test to be completed as part of Subtask 3.3. At this point in time, it appears that all equipment modifications and setup have been completed, and the ability to fire oil was successfully demonstrated in late May.

Forty-four pulse-jet bags for this subtask arrived in June. The bags were prepared using 22-ounce/yd² fabric coated seven times with an organic-based vanadium/titanium catalyst coating corresponding to Fabrics #17 and #106B in previous bench- and pilot-scale tests. At this time, an adequate number of pulse-jet bags are available for the three 100-hour tests, and there may be sufficient spares to meet bag requirements for the 500-hour test. Performance of the three 100-hour pulse-jet tests planned for this subtask should begin in early July with completion in late July. The 500-hour test will most likely take place in August.

4.5 Subtask 3.4 Fabric Durability Testing/Pulse-Jet System

Subtask 3.4 activities were initiated in September 1991 in order to prepare the baghouse slipstream system at the University of North Dakota (UND) Steam Plant for operation. Selection of a catalyst-coated fabric for Subtask 3.4 was discussed during the project review meeting on March 3, 1992. Participants agreed that the 22-ounce/yd² fabric would be the best for pulse-jet applications; therefore, the DE992 fabric will be used.

Pulse-jet bags will be installed in the slipstream baghouse at the UND Steam Plant in early July. EERC personnel intend to install nine bags from the first set of twelve used for the first 100-hour pulse-jet test, assuming

TABLE 16

Vanadium Concentration Analysis Results for Coal and Ash Samples

	Coal Composite (ppm)	Coal Ash (ppm)	Inlet (ppm)	RGBH Ash (ppm)	Sample Conditions
PTC-IL6-408		160			Calculated theoretical (11.89% ash)
	19		220 250	240 250 260	A/C Ratio=2.0 ft/min
PTC-IL6-414				260	
PTC-IL6-415		240		270 260 260 260	A/C Ratio=1.5 ft/min A/C Ratio=2.0 ft/min A/C Ratio=3.0 ft/min A/C Ratio=4.0 ft/min
PTC-IL6-416				260 250 290	A/C Ratio=4.0 ft/min A/C Ratio=2.0 ft/min
PTC-IL6-417				230 220 250 250 250	A/C Ratio=1.5 ft/min A/C Ratio=2.0 ft/min A/C Ratio=2.0 ft/min A/C Ratio=3.0 ft/min A/C Ratio=4.0 ft/min
PTC-IL6-419				260 230 250 240 240	A/C Ratio=1.5 ft/min A/C Ratio=2.0 ft/min A/C Ratio=2.0 ft/min A/C Ratio=3.0 ft/min A/C Ratio=4.0 ft/min
PTC-BV-423	18			160 200 140 170	A/C Ratio=1.5 ft/min A/C Ratio=2.0 ft/min A/C Ratio=3.0 ft/min A/C Ratio=4.0 ft/min
PTC-BT-424	13			240 240 240 250	A/C Ratio=1.5 ft/min A/C Ratio=2.0 ft/min A/C Ratio=3.0 ft/min A/C Ratio=4.0 ft/min
PTC-BU-425	<5.0				
PTC-IL6-426	30			240 250 240 240 230 230 220	Baghouse Temp.=700°F Baghouse Temp.=650°F Baghouse Temp.=600°F Baghouse Temp.=550°F Baghouse Temp.=500°F Baghouse Temp.=750°F Baghouse Temp.=650°F

TABLE 16

Vanadium Concentration Analysis Results for Coal and Ash Samples

	Coal Composite (ppm)	Coal Ash (ppm)	Inlet (ppm)	RGBH Ash (ppm)	Sample Conditions
PTC-IL6-408		160			Calculated theoretical (11.89% ash)
	19		220 250	240 250 260	A/C Ratio=2.0 ft/min
PTC-IL6-414					
PTC-IL6-415		240		270 260 260 260	A/C Ratio=1.5 ft/min A/C Ratio=2.0 ft/min A/C Ratio=3.0 ft/min A/C Ratio=4.0 ft/min
PTC-IL6-416				260 250 290	A/C Ratio=4.0 ft/min A/C Ratio=2.0 ft/min
PTC-IL6-417				230 220 250 250 250	A/C Ratio=1.5 ft/min A/C Ratio=2.0 ft/min A/C Ratio=2.0 ft/min A/C Ratio=3.0 ft/min A/C Ratio=4.0 ft/min
PTC-IL6-419				260 230 250 240 240	A/C Ratio=1.5 ft/min A/C Ratio=2.0 ft/min A/C Ratio=2.0 ft/min A/C Ratio=3.0 ft/min A/C Ratio=4.0 ft/min
PTC-BV-423	18			160 200 140 170	A/C Ratio=1.5 ft/min A/C Ratio=2.0 ft/min A/C Ratio=3.0 ft/min A/C Ratio=4.0 ft/min
PTC-BT-424	13			240 240 240 250	A/C Ratio=1.5 ft/min A/C Ratio=2.0 ft/min A/C Ratio=3.0 ft/min A/C Ratio=4.0 ft/min
PTC-BU-425	<5.0				
PTC-IL6-426	30			240 250 240 240 230 230 220	Baghouse Temp.=700°F Baghouse Temp.=650°F Baghouse Temp.=600°F Baghouse Temp.=550°F Baghouse Temp.=500°F Baghouse Temp.=750°F Baghouse Temp.=650°F

TABLE 16 (continued)

Vanadium Concentration Analysis Results for Coal and Ash Samples

	Coal Composite (ppm)	Coal Ash (ppm)	Inlet (ppm)	RGBH Ash (ppm)	Sample Conditions
PTC-IL6-427				230	Upset condition #1
				220	Upset condition #2
PTC-IL6-428				230	A/C Ratio=1.5 ft/min
				220	A/C Ratio=2.0 ft/min
				240	A/C Ratio=3.0 ft/min
				240	A/C Ratio=4.0 ft/min

the results are positive. Successful completion of this 100-hour test and the results observed will establish an excellent baseline from which to evaluate fabric performance/durability in the pulse-jet baghouse at the Steam Plant.

Operation of the slipstream baghouse at the UND Steam Plant should begin in mid-July. The nine bags originally installed in the baghouse will be pre-coated with dolomite to establish an initial dust layer to protect the fabric from burning carbon particles that may enter the baghouse from the stoker-fired boiler. The three spare bags will be used as replacement bags after 1000, 2000, and 4000 hours of operation. The baghouse will be initially operated at an air-to-cloth ratio of 3 ft/min and a baghouse temperature of roughly 650°F. Ash injection will be used to augment the particulate mass loading from the stoker-fired boiler to achieve an inlet mass loading of roughly 3 gr/scf. Initially this injection ash will be material collected from the baghouse hopper of a pilot-scale circulating fluid-bed combustor. The chemical composition of the ash will be highly alkaline due to the large amount of calcium sulfate present.

Particulate collection efficiency will be measured during the first week of operation and on a monthly basis thereafter. Whether or not 12,000 hours of baghouse operation at the UND Steam Plant can be achieved will depend on UND Steam Plant operating plans in 1992 and 1993 and the availability of project funds to support the activity. It appears that the boiler from which the slipstream baghouse gets its flue gas will be operating for the remainder of the summer; therefore, some operating time (roughly 1,500 hours) will be recovered. At this point in time, sufficient funding is available to operate the baghouse through August and possibly September. By late September, additional funding will be required, or operation of the slipstream baghouse will have to be terminated.

5.0 KEY PERSONNEL STAFFING REPORT

Table 17 presents planned versus actual work hours for key EERC and UE&C personnel involved in the Catalytic Fabric Filtration project through June 1992.

TABLE 17
Planned Versus Actual Work Hours
for Key Personnel Through June 1992

Key Personnel	Planned Hours	Actual Hours	% of Total Available Work Hours Used
Greg Weber	1482	1204	81
Dennis L. Laudal	2224	971	44
Chris Robie	29	16	55

6.0 REFERENCES

1. Pirsh, E.A. U.S. Patent 4 220 633, September 2, 1980, assigned to Babcock and Wilcox Co.
2. Pirsh, E.A. U.S. Patent 4 309 386, January 5, 1982, assigned to Babcock and Wilcox Co.
3. Doyle, J.B. et al. U.S. Patent 4 793 981, December 27, 1988, assigned to Babcock and Wilcox Co.
4. Weber, G.F. "SO_x/NO_x Control, Low-Rank Coal Research under the UND/DOE Cooperative Agreement," Quarterly Technical Progress Report, University of North Dakota Energy and Environmental Research Center, Grand Forks, ND, DOE\FE\60181-1531, Jan. 1984, Section 6.
5. Kalinowski, M.R.; Nishioka, G.M. "Method for Applying Porous Metal Oxide Coatings to Relatively Nonporous Fibrous Substrates," United States Patent No. 4 732 879, Mar. 22, 1988.
6. Weber, G.F.; Laudal, D.L. "SO_x/NO_x Control - Catalytic Fabric Filtration for Simultaneous NO_x and Particulate Control," Final technical report for the period April 1, 1988, through June 30, 1989; Grand Forks, ND, DE-FC21-86MC10637, Aug. 1989.
7. Weber, G.F.; Miller, S.J.; Laudal, D.L. "Flue Gas Cleanup," Final technical report for the period July 1, 1989, through June 30, 1990; Grand Forks, ND, DE-FC21-86MC10637, Oct. 1990.

8. Markowski, G.W.; Filby, R. "Trace Element Concentration as a Function of Particle Size in Fly Ash from a Pulverized Coal Utility Boiler," *Environmental Science and Technology* 1985, 19 (9).

END

**DATE
FILMED**

12 / 9 / 92