50 MAY 25 AM 10:27

RECEIVED/PEIS

ALKALI/TX₂ CATALYSTS FOR CO/H₂ CONVERSION TO C₁-C₄ ALCOHOLS

Technical Progress Report for the Period

December 1989-February 1990

Kamil Klier
and
Richard G. Herman
with
Michelle Richards and Roy D. Bastian

Zettlemoyer Center for Surface Studies
and Department of Chemistry
Lehigh University
Bethlehem, PA 18015

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

PREPARED FOR THE UNITED STATES
DEPARTMENT OF ENERGY

Under Contract No. DE-FG22-88PC88933

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

jp

ALKALI/TX₂ CATALYSTS FOR CO/H₂ CONVERSION TO C₁-C₄ ALCOHOLS

Disclaimer

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States DOE, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

ALKALI/TX₂ CATALYSTS FOR CO/H₂ CONVERSION TO C₁-C₄ ALCOHOLS

OBJECTIVE AND SCOPE OF WORK

The objective of this research is to investigate and develop novel catalysts for the conversion of coal-derived synthesis gas into C₁-C₄ alcohols by a highly selective process. Therefore, the variations of catalyst activity and selectivity for the synthesis of alcohols from H₂/CO ≤ 1 synthesis gas for a series of A/TX₂ compounds, where A is a surface alkali dopant, T is a transition metal, and X is a S, Se, or Te, will be determined. The alkali component A, which is essential for C-O and C-C bond forming reactions leading to alcohols, will be highly dispersed on the TX₂ surfaces by using chemical vapor deposition (CVD) and chemical complexation/anchoring (CCA) methods.

The target alcohol space time yields are of the order of 1 kg of alcohol product per kg of catalyst per hour and the target selectivity is > 90% to alcohols. Among the A/TX₂ compounds initially investigated, preference will be given to A = Cs, T = Group VB element (V, Nb, Ta), and X = S or Se. So delimited A/TX₂ catalysts possess the strongest base (Cs), and the CCA preparation method using crown ethers is expected not only to disperse the alkali ions atomically but also to enhance the basicity of their counterions, thus further increasing the specific rates of the base-catalyzed C-O and C-C bond forming reactions.

The benefit of this research rests in providing a scientific foundation and a database for catalytic processes leading to high octane oxygenated fuels such as ethanol/methanol/propanol mixtures, as well as to low olefins obtained by further catalytic dehydration of the C₂-C₄ alcohols. Since the source of carbon can be coal-derived synthesis gas, this research will make a contribution to the technology for high quality clean transportation fuels and for basic chemicals from coal.

ALKALI/TX₂ CATALYSTS FOR CO/H₂ CONVERSION TO C₁-C₄ ALCOHOLS

SUMMARY OF TECHNICAL PROGRESS

A new preparation procedure using Li₂S as the sulfiding agent has been used to prepare RuS₂ catalysts. The newly prepared catalysts are undergoing bulk and surface analyses for comparison to the previously utilized sulfide catalysts prepared using NH₄SH as the sulfur-containing reagent.

High resolution ESCA analyses have been carried out with a tested RuS₂ catalyst. It is shown that the used catalyst did not contain impurities such as Fe, Mo, etc. and was free of carbon. It was demonstrated that the SCIENZA ESCA-300 gives excellent resolution of lines such as the 2p_{1/2,3/2} lines of sulfur and the 3d_{3/2,5/2} lines of ruthenium. The latter indicates that the sulfur environment is uniform, which in the pyrite-like structure of RuS₂ is expected to correspond to sulfur pairs.

Thermodynamic calculations had previously indicated that the higher alcohol synthesis reaction should be carried out over the RuS₂-based catalysts with H₂S-containing H₂/CO synthesis gas mixtures so that the RuS₂ is stabilized. These calculations have now been extended to Os, Re, and Nb sulfides, and it is shown that the NbS₂ should be the most stable catalyst in the absence or in the presence of very small quantities of H₂S.

TECHNICAL PROGRESS

Preparation of RuS₂-Based Catalysts

A new preparation method of synthesizing the RuS₂ catalysts was utilized during this quarter. The new synthesis of RuS₂ used Li₂S instead of NH₄SH as the precipitating agent, and the resulting precipitate was calcined to form RuS₂. The synthesis was carried out in three steps, all of which were completed under dry, non-aqueous, anarobic conditions in a glove box. The three preparation steps are summarized below:

1. Dissolution of RuCl₃ In a nitrogen filled glove box, ≈20 g of RuCl₃ was placed in a 500 ml beaker. A volume of dry ethyl acetate was then added to the beaker until the RuCl₃ was partially dissolved.
2. RuCl₃ + Li₂S Reaction While stirring continuously, 4.7 g of Li₂S was added directly to the RuCl₃/ethyl acetate slurry at ambient temperature. The ruthenium sulfide that precipitated from the solution was digested for 45 hr.
3. Removal of Li₂S After allowing the solution to stand for 1 hr, decantation was carried out. The solid was then washed with 200 ml of a 12% acetic acid/ethyl acetate solution, which was then decanted. A 200 ml aliquot of 12% acetic acid/ethyl acetate was added, and the solution was stirred for 15 min before the solid was filtered. After washing with 200 ml ethyl acetate, the solid was equilibrated with 100 ml acetic acid overnight, filtered, washed with 50 ml of ethyl acetate, filtered, and dried under nitrogen. The yield of RuS₂ was ≈10 g.

Characterization of the RuS₂ and Cs/RuS₂ Catalysts

X-Ray powder diffraction (XRD) patterns obtained for the newly prepared uncalcined RuS₂ showed that this material possessed little crystallinity. After calcination of this sample under N₂ at 550°C for 2 hr, the RuS₂ increased its crystallinity. This sample of RuS₂ will be tested for alcohol synthesis activity and will be further characterized.

A previously tested RuS₂ catalyst [1] was examined by HR-ESCA (also called X-ray photoelectron spectroscopy) to determine the components on the surface of the catalyst. A survey scan of the RuS₂ is shown in Figure 1. The new SCIENTA ESCA-300 instrument at Lehigh University that has a rotating anode was used to obtain this spectrum. The instrumental parameters were the following: pass energy = 300 eV, slit width = 1.1 mm, the energy step = 0.25 eV, X-ray power = 7.3 kW, and a transmission lens mode was used. The spectrum in Figure 1 was obtained in 18.5 min. The assignments of the lines are given in the figure, and a number of shake-up lines are also evident.

Higher magnification spectra were obtained in the Ru_{3d} and S_{2p} regions, and the resultant data are shown in Figures 2 and 3 respectively. The instrumental parameters were the same as given above except that a pass energy = 75 eV and an energy step of 0.05 eV were used. The data collection times were 17 min 55 sec and 13 min 29 sec for the Ru and S regions, respectively. These spectra show the excellent resolutions of the Ru_{3d}_{3/2,5/2} and S_{2p}_{1/2,3/2} lines that were obtained with the SCIENTA ESCA-300 instrument. The uniformity of the S lines in Figures 1 and 3 indicate that only one type of sulfur is present in this sample. Ruthenium disulfide has the pyrite crystal structure, and in stoichiometric RuS₂ the sulfur exists as S pairs, as shown in Figure 4.

The spectra shown in Figures 1-3 demonstrate that impurities are not present on the surface of this catalyst. Since the SCIENTA ESCA-300

instrument provides for a very high resolution, high sensitivity surface analysis method, the presence of impurities and mixed phases would be detected if present. The weak lines at about 450 eV in the survey spectrum in Figure 1 are due to a small amount of the In foil used for mounting the sample being detected.

Calculation of the Stability of RuS₂

The thermodynamics of the sulfidization of ruthenium and loss of sulfur from RuS₂ were considered in our previous quarterly progress report [2]. It was shown that there is an equilibrium between RuS₂ and Ru⁰ that depends on the associated H₂S/H₂ ratio. As pointed out, testing of the sulfide catalysts is carried out in a continuous flowing reaction system with H₂/CO ≈ 1 synthesis gas. It was calculated that the critical gas phase H₂S concentration that is needed to maintain the RuS₂ stoichiometry in the catalysts is a function of temperature. Thus, at 300°C ≈35 ppm of H₂S is required to stabilize RuS₂, while ≈100 ppm of H₂S is needed at 330°C.

Using data contained in Barin and Knacke [3] and in Mills [4] a comparison of the critical H₂S concentration (see Equation 1) needed to maintain the sulfides in H₂ at 25°C was made for M = Os, Re, Ru, Mo, and Nb.

The results of these calculations are shown in Figure 5. The critical concentrations will be appreciably higher at elevated temperatures, as noted above for the RuS₂ catalyst.

It is predicted that ReS₂ and NbS₂ would behave very differently in terms of stability in flowing synthesis gas, even under ambient conditions. Additional thermodynamic data for NbS₂ have not yet been found, so the calculations have not been carried out for higher temperature conditions.

However, based on our experience with the MoS_2 and RuS_2 catalysts, it is predicted that the alkali/ NbS_2 catalyst would be very stable under higher alcohol synthesis conditions. Since it is desirable to carry out the synthesis of higher alcohols without the necessity of maintaining a controlled level of H_2S in the synthesis gas stream, the NbS_2 catalyst would be a promising catalyst if it were an active and selective catalyst. Thus, the NbS_2 -based catalysts will be prepared and tested in the future.

References:

1. K. Klier, R. G. Herman, R. D. Bastian, and K. L. Flanagan, "Alkali/ TX_2 Catalysts for CO/H_2 Conversion to $\text{C}_1\text{-C}_4$ Alcohols," Technical Progress Report DOE/PC/88933-3.
2. K. Klier, R. G. Herman, M. Richards, and R. Bastian, "Alkali/ TX_2 Catalysts for CO/H_2 Conversion to $\text{C}_1\text{-C}_4$ Alcohols," Technical Progress Report DOE/PC/88933-4.
3. I. Barin and O. Knacke, "Thermodynamic Properties of Inorganic Substances--Supplement," Springer-Verlag, New York (1973).
4. K. C. Mills, "Thermodynamic Data for Inorganic Sulphides, Selenides, and Tellurides," Butterworths, London (1974).

Binding Energy [eV]

FIGURE 1

FIGURE 2

FIGURE 3

FIGURE 4

RUTHENIUM DISULFIDE PYRITE STRUCTURE ($a=5.6\text{\AA}$, $x=0.1\text{\AA}$)

Critical H₂S Concentration to
Maintain the Sulfides at 25°C

$$M + 2H_2S = MS_2 + 2H_2$$

FIGURE 5

END

**DATE
FILMED**

12 / 21 / 92