301/587-8202

MANUFACTURED TO AIIM STANDARDS
BY APPLIED IMAGE, INC.

1 of 1

ELASTIC ANISOTROPY IN HOT-PRESSED Si_3N_4 COMPOSITES: ROLE OF
IN SITU $\beta\text{-Si}_3\text{N}_4$ GRAINS AND ADDED $\beta\text{-Si}_3\text{N}_4$ WHISKERS*

M. H. Manghnani, E. S. Fisher, F.-Y. Li, and R.-J. Wang
Mineral Physics Group, School of Ocean and Earth Science and Technology
University of Hawaii
Honolulu, HI 96822

J. P. Singh and J. L. Routbort
Energy Technology Division
Argonne National Laboratory
Argonne, Illinois 60439

June 1994

The submitted manuscript has been authored
by a contractor of the U. S. Government
under contract No. W-31-109-ENG-38.
Accordingly, the U. S. Government retains a
nonexclusive, royalty-free license to publish
or reproduce the published form of this
contribution, or allow others to do so, for
U. S. Government purposes.

MASTER

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

To appear in the Proc. of Ceramic Matrix Composites Symposium held at the
96th ACerS Annual Meeting and Exposition, Indianapolis, IN, April 24-28,
1994.

*Work supported by U.S. Department of Energy, Office of Fossil Energy,
Advanced Research and Technology Development Materials Program,
under Contract W-31-109-Eng-38.

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

JP

ELASTIC ANISOTROPY IN HOT-PRESSED Si_3N_4 COMPOSITES: ROLE OF IN-SITU β - Si_3N_4 GRAINS AND ADDED β - Si_3N_4 WHISKERS

Murli H. Manghnani, Edward S. Fisher, Feng-ying Li, and Ru-ju Wang
Mineral Physics Group, School of Ocean and Earth Science and Technology,
University of Hawaii, Honolulu, HI 96822

Jitendra P. Singh and Jules L. Routbort
Argonne National Laboratory, Argonne, IL 60439

ABSTRACT

The elastic anisotropy in hot-pressed samples of β - Si_3N_4 monolithic polycrystalline composites and in composites with 5 to 35% β - Si_3N_4 whiskers have been investigated at room temperature by high precision acoustic interferometry. All of the samples, including the monolithic Si_3N_4 , show anisotropy characterized as transverse isotropic about the hot-pressing (HP) direction and are described using the five elastic stiffness moduli for hexagonal symmetry. The principal anisotropy is revealed in the shear modulus difference, $(C_{66} - C_{44})/C_{44}$, which increases from 7% in the monolithic sample to 15% in samples with 10% or more whiskers. All the stiffness moduli except for C_{44} increase with the addition of whiskers. Young's modulus in the HP direction is 5% smaller than in the HP plane in all samples. The whiskers enhance the shear anisotropy produced by the in-situ elongated β -grains.

INTRODUCTION

About two decades ago Lange¹ reported the beneficial effects of elongated β - Si_3N_4 grains (henceforth, designated as β -grains) on the mechanical properties of the monolithic ceramic matrix. The elongated β -grains were grown in-situ by hot pressing 90% α - Si_3N_4 powder at 1750°C for 2 hours, whereas the exact same preparation schedule for 90% β powder produced equi-axed grains. Although both final products were over 99% of theoretical density and 100% β phase Si_3N_4 crystal structure, the high α powder also produced the highest strength and fracture toughness. Lange also noted that the axial directions of the elongated grains were

parallel to the c axes of the hexagonal β crystals and were also predominately perpendicular to the uniaxial hot-pressing (HP) direction. There have been a large number of publications since Lange's report that describe the growth of the elongated β grains in Si_3N_4 containing either MgO or Y_2O_3 sintering aid materials²⁻⁵. Many of these studies describe aspects of the anisotropy of physical properties. The results for fracture toughness show that for a crack propagating parallel to HP direction, the ceramic material is generally significantly tougher than for a crack moving perpendicular to HP direction. This difference is attributed to greater deflection of a crack propagating along grain boundaries transverse to the elongated grains.

The effect of the elongated grains on the elastic properties of hot-pressed Si_3N_4 is, however, not at all clear. For example, Yeheskal and Gefen⁶ report that a hot-isostatically pressed sample, that had apparently been preformed by unidirectional die pressing, had a Young's modulus, E , of 320 GPa in a direction perpendicular to HP direction and 306 GPa parallel to HP direction. This sample contained 6.5% of α phase and an undefined wt. % of Y_2O_3 sintering aid. Lee and Bowman⁵, however, report the opposite anisotropy for a sample hot pressed with 10% MgO , and give an E value of 332 GPa parallel to HP direction and 315 GPa in the perpendicular direction. (The higher values for E of the latter samples⁵ indicate that they contained a greater α phase concentration; this conclusion is based on the data⁶ that indicate an E value of 362 GPa for α phase versus 312 GPa for 100% β phase). Buljan et al.⁷ report no elastic anisotropy in their samples that were hot pressed with 7.5% $\text{Y}_2\text{O}_3 + \text{Al}_2\text{O}_3$ sintering aids. The reasons for these differences may be related to differences in sample preparation, or there may be errors or uncertainty in relating the HP direction to the directions of acoustic wave propagation. The major factor may, however, be in the assumptions involved in calculating an E value from acoustic velocity data taken in two different directions. The raw data generally used are, respectively, the compressional wave velocity V_p in each of the two orthogonal directions and a shear wave velocity V_s again in each of two directions. The values of E in each direction are then generally calculated from the equation derived for an isotropic solid, where

$$\rho V_p^2 = \lambda + 2G \quad (1)$$

$$\rho V_s^2 = G, \text{ and } \lambda = \text{Lamé constant} \quad (2)$$

$$E_{\text{iso}} = 2G \left(1 + \frac{\lambda}{2\lambda + 2G} \right) = G \left(\frac{3\rho V_p^2 - 4\rho V_s^2}{\rho V_p^2 - \rho V_s^2} \right) \quad (3)$$

Since V_p and V_s are generally slightly or substantially different in each different direction, the use of the above equations to evaluate $E_{\parallel}$ or $E_{\perp}$ is immediately not applicable, but they are often used without reference to the fact that the results are merely approximations. There is, however, an even greater oversight in the use of these equations (the use of a single value for V_s), whereas in any anisotropic solid there are two normal transverse modes along any single direction of wave propagation. In most of the investigations of polycrystalline aggregates, the measurements usually involve only one measured V_s for each direction; the second, V_{s2} , for shear polarization normal to the first V_s , is mostly disregarded for unknown reasons. Consequently, the values given for $E_{\parallel}$ and $E_{\perp}$ in hot pressed samples will depend not only on the accuracy of measuring V_p but also on which of the two generally different V_s values are possible when a texture or preferred grain orientation is present in the sample. This can result in incorrect characterization of the elastic anisotropy in the composite, particularly when its microstructure contains elongated β - Si_3N_4 grains or in which short fibers are preferentially oriented perpendicular to the HP direction. The present investigation was performed to obtain a better understanding of the extent of elastic anisotropy in hot pressed monolithic Si_3N_4 and in samples of Si_3N_4 whisker reinforced composites. Whereas preliminary study⁸ of similar samples did not indicate significant effects of whisker content on elastic properties, the use of more precise ultrasonic velocity measurement techniques and measurements of the two different shear wave velocities in the present study reveal significant increases in moduli and changes in anisotropy.

EXPERIMENTAL PROCEDURES

Sample Preparation

The procedures for preparing and characterizing the monolithic Si_3N_4 and composites containing 5%, 10%, 15%, 20% and 35% Si_3N_4 whiskers are described⁸. All samples contained 2.5% MgO as sintering aid, the whiskers after final processing were about 15 microns long x 0.6 microns diam., and the samples were hot pressed for 2 hours at a temperature sufficiently close to 1750°C to yield 100% β phase as monitored by x-ray diffraction⁹.

The discs produced by hot-pressing were cut into rectangular bars, each with 3 sets of orthogonal faces, with 3 to 4 mm between faces. These faces were then ground and polished (finally, with 1 micron diamond paste), so as to be flat and have uniform thickness between parallel faces for measuring velocities of the acoustic waves to be propagated in each of the three orthogonal directions. The measured densities of each of the six samples are listed in Table I.

Table I. Acoustic wave velocities (in units of km/s) measured in HP direction and 2 orthogonal directions, as function of β -Si₃N₄ whisker content. The propagation and polarization directions are with respect to the three axes (*a, b, c*) of the specimen. The *a* and *b* directions are $\perp$ to HP direction and *c* direction is $\parallel$ to HP direction.

Velocity	prop. dir.	polar. dir.	vol. % β -Si ₃ N ₄ whiskers					
			0	5	10	15	20	35
V ₁	<i>a</i>	<i>a</i>	11.373	11.490	11.608	11.521	11.524	11.500
V ₂	<i>b</i>	<i>b</i>	11.380	-	-	-	-	11.500
V ₃	<i>c</i>	<i>c</i>	11.131	11.220	11.337	11.226	11.249	11.234
V ₄	<i>c</i>	<i>a</i>	6.159	6.122	6.113	6.123	6.118	6.074
V ₅	<i>c</i>	<i>b</i>	6.158	6.122	6.112	6.124	6.107	6.085
V ₆	<i>a</i>	<i>c</i>	6.160	6.128	6.119	6.135	6.114	6.075
V ₇	<i>a</i>	<i>b</i>	6.366	6.484	6.564	6.502	6.512	6.525
V ₈	<i>b</i>	<i>c</i>	6.158	-	-	-	-	6.071
V ₉	<i>b</i>	<i>a</i>	6.391	-	-	-	-	6.529
% difference in velocities								
V ₃			0.01	0.00	0.01	0.01	0.18	0.18
V ₄ - V ₆			0.01	0.10	0.10	0.20	0.08	0.00
V ₄ - V ₈			0.01					0.05
V ₇ - V ₉			0.39					0.08
V ₇ - V ₄			3.40	5.90	7.40	6.20	6.40	7.40
V ₇ - V ₃			2.20	2.30	2.30	2.60	2.40	2.30
Density, ρ (g/cm ³)			3.154	3.172	3.179	3.183	3.179	3.178

Wave Velocity Measurements

The acoustic wave velocities were measured by the phase comparison method¹⁰. The sample face normal to the direction of wave propagation is placed on the top end face of a round fused silica buffer rod, the bottom end of which is permanently bonded to a thin wafer quartz crystal piezoelectric transducer. The sample is acoustically bonded to the buffer rod with either a stop-cock grease for longitudinal

waves or a viscous clear compound for transverse waves. The wave velocity, V , is calculated from

$$V = 2tf / n,$$

where t is the thickness between parallel faces, f is the carrier wave frequency at which an integral number of wave lengths, n , within the sample are in phase. Because of dispersion of velocity with wave frequency, the true free space velocity, V , is established at carrier frequencies above 30 MHz.

Computing the Elastic Moduli

The wave velocities measured in each of the six samples are listed in Table I, arranged among the three orthogonal Cartesian coordinates, a , b and c . The a and b coordinates are perpendicular to the HP direction. The c coordinate is parallel to the HP direction. Among the longitudinal wave velocities, V_1 , V_2 and V_3 , those in the HP deviation, parallel to the c coordinate, V_3 , are clearly smaller than V_1 , measured parallel to the a coordinate in all six samples, and smaller than V_2 in the b direction of the monolithic Si_3N_4 (0% whiskers) or in the sample containing 35% whiskers. Secondly, it is to be noted that in each sample, V_1 and V_2 are the same within 0.1% in the 0% and 35% whisker samples, indicating that the elastic anisotropy is similar to that for hexagonal single crystals or for transverse-isotropic symmetry in polycrystalline aggregates with fiber textures. In conformance with the elastic stiffness moduli for hexagonal symmetry, the V_p values parallel to HP direction are designated as defining the C_{33} modulus via

$$\rho V_3^2 = C_{33} \quad (4)$$

where ρ is the sample density. The two velocities perpendicular to HP direction, V_1 and V_2 , are converted to the C_{11} modulus

$$\rho V_1^2 = \rho V_2^2 = C_{11} \quad (5)$$

If we are correct in designating HP direction as the axis of 6-fold symmetry, analogous to the hexagonal c axis, the two transverse (shear mode) velocities propagated parallel to HP direction, V_4 and V_5 , should be equal to each other within the error of measurement and designated as defining the C_{44} modulus in the hexagonal system.

$$\rho V_4^2 = \rho V_5^2 = C_{44} \quad (6)$$

whereas the transverse mode velocities propagated in the a and b perpendicular directions, V_6 , V_7 , V_8 and V_9 should differ, depending on the directions of particle displacement, *i.e.*, polarization direction. The velocities of the transverse modes propagated perpendicular to HP direction but polarized parallel to HP direction should conform to

$$\rho V_6^2 = \rho V_8^2 = \rho V_4^2 = C_{44} \quad (7)$$

When the polarization and propagation directions are both perpendicular to the HP direction

$$\rho V_7^2 = \rho V_9^2 = C_{66} = (C_{11} - C_{12})/2 \quad (8)$$

From measurements of V_1 through V_9 in each sample we should then determine whether the assumed transverse-isotropic symmetry is, indeed, the correct elastic symmetry for hot pressed aggregates of Si_3N_4 and calculate values of C_{11} , C_{12} , C_{33} and C_{44} . These four moduli are not sufficient to establish values for the anisotropic Young's moduli, $E_{\parallel}$ or $E_{\perp}$, with respect to the HP direction, nor to calculate other elastic parameters of engineering interest. These parameters can, however, be semi-quantitatively predicted from judicious estimates of the fifth stiffness modulus, C_{13} .

RESULTS

Conformation with Transverse Isotropy

The major test of the transverse isotropic assumption is in the measurements of the shear moduli for the two directions of polarization. The six velocities involved in these cross-checks are given in equations (6), (7) and (8) and the measured values and differences, *i.e.*, disagreements, are tabulated in Table I. These cross-checks have been completed only for the monolithic Si_3N_4 sample and the 35% whisker composite. For the C_{44} modes the velocities agree to within 0.01% for the monolithic sample and to within 0.20% for the composite samples. For the C_{66} modes, where both wave propagation and wave polarization are perpendicular to HP direction, the disagreement in the monolithic sample is somewhat larger but still within 0.40%, whereas the disagreement is less than 0.10% for the 35% composite. These disagreements are considered small deviations, since we are dealing here with textured polycrystals rather than single crystals and they are certainly small relative to the magnitude of $(C_{44} - C_{66})$. This suggests that the whiskers enhance the preferred orientation of the elongated β grain axes. The other factor that confirms that the anisotropic treatment of elastic properties is appropriate is the differences between the velocities of the C_{44} and C_{66} modes, as represented by the differences $V_7 - V_4$. In the monolithic Si_3N_4 this difference is 3.4%, or about 10 times as large as the cross-check difference $V_7 - V_9$. As noted in Table I,

the $V_7 - V_4$ difference increases by a factor of two with 10% whiskers and remains so up to 35% whiskers.

These results support the conclusion that the whiskers do in fact enhance the preferred orientation of the elongated β grains over that of the in-situ microstructure.

Evaluation of Anisotropic Elastic Moduli

In view of the above results, the elastic moduli of hot pressed monolithic Si_3N_4 containing near 100% β phase and composites containing $\beta\text{-Si}_3\text{N}_4$ whiskers should be reported with reference to a hexagonal Cartesian coordinate system in which the HP direction becomes the c axis. The four directly measured moduli, C_{11} , C_{22} , C_{33} , and C_{44} and the C_{12} value derived from Equation 5, are listed in Table II as a function of whisker content up to 35%, and are plotted in Figs. 1 and 2. Both of the longitudinal moduli increase significantly with the addition of 10 vol. % of whiskers and drop off slightly from 10% to 35%. The difference between C_{11} and C_{33} remains in the range of $5.5 \pm 1.0\%$ as whisker content increases, with C_{11} being larger in magnitude. This evidently reflects a larger stiffness modulus along the elongated in-situ or whisker grain axis, since these axes lie primarily perpendicular to the HP direction.

Table II. Elastic stiffness moduli (in units of GPa) with reference to a , b , c directions; HP direction is along c axis.

Modulus	vol. % Si_3N_4 whiskers					
	0	5	10	15	20	35
C_{11}	407.9	424.3	428.4	422.5	422.2	420.3
C_{33}	390.7	399.2	408.5	401.1	402.3	401.1
C_{44}	119.6	118.9	118.8	119.4	118.8	117.8
C_{66}^*	127.8	133.3	137.0	134.6	134.8	135.3
C_{12}	152.3	157.7	154.4	153.3	153.0	149.7
$(C_{11} - C_{33})/C_{33}$	4.4%	6.3%	4.9%	5.3%	4.9%	4.8%
$(C_{66} - C_{44})/C_{44}$	6.9%	12.1%	15.3%	12.7%	13.5%	15.1%

* $C_{66} = (C_{11} - C_{12})/2$

Figure 1. Longitudinal moduli, C_{11} and C_{33} , perpendicular and parallel, respectively, to HP versus volume % of Si_3N_4 whiskers in $B\text{-Si}_3\text{N}_4$.

Figure 2. Shear moduli, C_{44} and C_{66} , versus volume % of Si_3N_4 whiskers.

The difference between the C_{66} and C_{44} shear moduli is, however, strongly affected by the addition of β - Si_3N_4 whiskers. As noted in Table II, this difference increases by over a factor of 2, *i.e.*, 6.9% to 15.3%, with the addition of the first 10% of whiskers. The C_{44} shear modulus, which represents a shearing of the hot pressed planes relative to each other, is essentially unaffected by the whisker addition, whereas the C_{66} modulus, representing a distortion of the HP planes, increases in strength with whisker additions.

DISCUSSION OF RESULTS

Estimates of Compliance Moduli and Engineering Parameters

Because the data that we have obtained from the three orthogonal directions of wave propagation permit only the evaluation of four of the five stiffness moduli, the evaluation of the compliance moduli, S_{ij} , the Young's moduli, and Poisson's ratio requires that we first make a reasonable estimate of the magnitude of the C_{13} modulus, which cannot be extracted from the present data. In making such an estimate, we first note that the C_{12} moduli, given in Table II, remains nearly constant with the addition of whiskers. Secondly, because the difference $(C_{11} - C_{33})$ is relatively small (*i.e.*, $C_{11} \sim C_{33}$), we may assume $C_{44} = (C_{33} - C_{13})/2$. From this, we estimate C_{13} to be 150 ± 10 GPa. This estimate can, of course, be guided to some extent by the values of the Young's moduli, E , and bulk moduli, K , that result from the subsequent calculations and by comparison with value of E and K that have been quoted in the literature for isotropic β - Si_3N_4 . For evaluating the Young's moduli parallel ($E_{\parallel}$) and perpendicular ($E_{\perp}$) to HP direction, we have

$$E_{\parallel} = 1/S_{33} = [C_{33}(C_{11} + C_{12}) - 2C_{13}^2] / (C_{11} + C_{12}) \quad (9)$$

$$E_{\perp} = 1/S_{11} = 2C_{66} [C_{33}(C_{11} + C_{12}) - 2C_{13}^2] / (C_{11}C_{33} + C_{13}^2) \quad (10)$$

As an approximation, we use

$$E_{\text{ISO}} = (E_{\parallel} + 2E_{\perp})/3 \quad (11)$$

as the value of E that would be measured in an isotropic polycrystal.

For evaluating the bulk moduli, K , we first calculate the compressibilities, parallel ($\beta_{\parallel}$) and perpendicular ($\beta_{\perp}$) to HP direction:

$$\beta_{\parallel} = (S_{33} + 2S_{13}) = (C_{11} + C_{12} - 2C_{13}) / [C_{33}(C_{11} + C_{12}) - 2C_{13}^2] \quad (12)$$

$$\beta_{\perp} = (S_{11} + S_{12} + S_{13}) = (C_{33} - C_{13}) / [C_{33}(C_{11} + C_{12}) - 2C_{13}^2] \quad (13)$$

Thus,

$$K = \frac{1}{\beta_{\text{vol}}} = \frac{1}{2\beta_{\perp} + \beta_{\parallel}} \quad (14)$$

or
$$K = \frac{1}{S_{33} + 2S_{11} + 2S_{12} + 4S_{13}}$$

The results of computing Equations 9-14, assuming $C_{13} = 150$ GPa, are given in Table III and plotted in Figs. 3 and 4. Young's modulus, perpendicular to HP direction, $E_{\perp}$, is significantly larger and the difference between $E_{\perp}$ and $E_{\parallel}$ remains at about 5% as whiskers are added to the composites. There is, however, a significant increase in both $E_{\perp}$ and $E_{\parallel}$ values with addition of the first 10% of whiskers. Although there is no experimental evidence for explaining the maxima in the elastic modulus values near 10% whisker composition, a correlation of the measured ultrasonic and density data, suggests that the maxima may, in part, be attributed to densification (packing) during hot-pressing.

Table III. Calculated Young's moduli, compressibilities and bulk moduli for Si_3N_4 composites containing $\beta\text{-Si}_3\text{N}_4$ whiskers, assuming $C_{13} = 150$ GPa .

Parameter	vol. % Si_3N_4 whiskers					
	0	5	10	15	20	35
$E_{\parallel}$ (GPa)	310	322	331	323	324	322
$E_{\perp}$ (GPa)	325	340	347	341	341	340
$(E_{\perp} - E_{\parallel})/E_{\parallel}$ (%)	4.8	5.6	4.8	5.6	5.2	5.6
$\beta_{\parallel}$ ($10^3/\text{GPa}$)	1.50	1.46	1.46	1.48	1.48	1.47
$\beta_{\perp}$ ($10^3/\text{GPa}$)	1.38	1.33	1.34	1.35	1.35	1.37
K (GPa)	235	240	242	239	239	238

The compressibility is largest in the HP direction and is relatively unaffected by whisker additions. Overall, bulk modulus is only slightly affected by whisker additions.

Comparison with Previous Results

As noted in Table IV, the present measurements and calculated anisotropic parameters for the monolithic sample are in good agreement with the results of Yeheskal⁶ and in contradiction to other results⁵. From our estimated results, the

Figure 3. Anisotropic Young's moduli, $E_{\parallel}$ and $E_{\perp}$ to HP as a function of volume % of Si_3N_4 Whiskers, assuming $C_{13} = 150$ GPa.

Figure 4. Bulk modulus, K , as a function of volume % Si_3N_4 whiskers, assuming $C_{13} = 150$ GPa.

average value of E , E_{ISO} , in a randomly oriented polycrystalline-monolithic $\beta\text{-Si}_3\text{N}_4$ would be about 320 GPa and the average shear modulus, $G_{\text{ISO}} = (C_{44} + 2C_{66})/3$, would be 125 GPa. The calculated value of bulk modulus, K , is 235 GPa, which is in excellent agreement with that estimated from the average values of E and G for isotropic aggregates.

Table IV. Comparison of $E_{\parallel}$, $E_{\perp}$, E_{ISO} , K and G (shear modulus) values (in GPa) for monolithic Si_3N_4 .

Reference	$E_{\parallel}$	$E_{\perp}$	E_{ISO}^*	K	G_{ISO}^{**}
Present study	310	322	320	235	125
6	307	320		234	122
6			310	220	125
5	322	315			
11			317	215	126

$$* E_{\text{ISO}} = (E_{\parallel} + 2E_{\perp})/3$$

$$** G_{\text{ISO}} = (C_{44} + 2C_{66})/3$$

CONCLUSIONS

The elastic moduli of hot-pressed monolithic $\beta\text{-Si}_3\text{N}_4$ composites measured at ambient temperature exhibit anisotropic behavior with transverse isotropy in the plane perpendicular to the hot-pressing (HP) direction. Young's modulus parallel to the HP direction, $E_{\parallel}$, is about 5% smaller than $E_{\perp}$. These values increase with addition of $\beta\text{-Si}_3\text{N}_4$ whiskers up to 10 vol. % and decrease slightly to 35 vol. % whiskers. The largest effect of the texture in the elongated β -grains in the monolithic material and the whiskers in the composite is in the shear modulus anisotropy, where the shear stiffness in the HP plane, C_{66} , is about 7% higher than C_{44} (shear stiffness between HP planes) in the monolithic sample and increases to 15% with addition of 10% whiskers. Measurements of the single-crystal elastic constants, C_{ij} , of Si_3N_4 and the variations in the crystallographic texture (preferred orientation) in monolithic Si_3N_4 and whisker-reinforced Si_3N_4 composites would be necessary in order to explain the observed anisotropy in the elastic properties.

ACKNOWLEDGMENTS

We thank John Balogh for technical help in experimental work. We are grateful to Dr. Zhuang Li for reviewing the manuscript. Support for this research was provided by the University of Hawaii, Materials and Applied Science Program. School of Ocean and Earth Science and Technology contribution No. 3573

REFERENCES

1. F.F. Lange, Relation Between Strength, Fracture Energy and Microstructure in Hot Pressed Si_3N_4 , J. Am. Ceram. Soc. 56[10], 518-522 (1973).
2. L.J. Bowen, R.J. Weston, T.G. Carruthers and R.J. Brook, Hot Pressing and the α - β phase transformation in silicon nitride, J. Mat. Science 13, 341-350 (1978).
3. K-R Lai and T-Y Tien, Kinetics of β Si_3N_4 Grain Growth in Si_3N_4 Ceramics Sintered under High Nitrogen Pressure, J. Am. Ceram Soc. 76[1], 91-96 (1993).
4. D. Suttor and G.S. Fishman, Densification and Sintering Kinetics in Sintered Silicon Nitride, J. Am. Ceram. Soc. 75[5], 1063-67 (1992).
5. F. Lee and K.J. Bowman, Texture and Anisotropy in Silicon Nitride, J. Am. Ceram. Soc. 75[7], 1748-55 (1992).
6. O. Yeheskel and Y. Gefen, The Effect of the α Phase on the Elastic Properties of Si_3N_4 , Mat. Sci. and Eng. 71, 95-99 (1985).
7. S.T. Buljan, J. Baldoni and M.L. Huchabee, Si_3N_4 -SiC Composites, Am. Ceram. Soc. Bull. 66, 347-52 (1987).
8. C.Y. Chu and J.P. Singh, Mechanical Properties and Microstructure of Si_3N_4 Whisker Reinforced Si_3N_4 Matrix Composites, Ceram. Eng. Sci. Proc. 11[7-8], 709-720 (1990).
9. C.P. Gazzara and D.R. Messier, Determination of Phase Content of Si_3N_4 by X-Ray Diffraction Analysis, Am. Ceram. Soc. Bull. 56[9], 777-780, (1977).
10. E.S. Fisher and C.J. Renken, Single Crystal Elastic Moduli and h.c.p.-b.c.c. Transformation in Ti, Zr and Hf. Phys. Rev. A135, 482-94 (1964).
11. E.S. Fisher, M.H. Manghnani, J.F. Wang and J.L. Routbort, Elastic Properties of Al_2O_3 and Si_3N_4 Matrix Composites with SiC whisker Reinforcement J. Am. Ceram. Soc. 75[4], 908-914 (1992).

**DATE
FILMED**

10/18/94

END