2

EGG-FSP-10341
July 1992

**Idaho
National
Engineering
Laboratory**

*Managed
by the U.S.
Department
of Energy*

OXIDATION AND VOLATILIZATION OF A
NIOBIUM ALLOY

G. R. Smolik
K. A. McCarthy

*Work performed under
DOE Contract
No. DE-AC07-76ID01570*

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This book was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights. References herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

OXIDATION AND VOLATILIZATION OF A NIOBIUM ALLOY

Fusion Safety Program/Activation Products Task

G. R. Smolik
K. A. McCarthy

July 1992

Idaho National Engineering Laboratory
EG&G Idaho, Inc., P.O. Box 1625
Idaho Falls, Idaho 83415-3523

Prepared for the
U.S. Department of Energy
Office of Energy Research
Under DOE Field Office, Idaho
Contract DE-AC07-76ID01570

MASTER

ABSTRACT AND SUMMARY

This report presents the findings from a preliminary investigation into oxidation and volatilization characteristics of a niobium alloy. Niobium is a candidate alloy for use in plasma facing components (PFCs) in experimental fusion reactors like the International Thermonuclear Experimental Reactor (ITER). An experimental alloy was tailored to simulate small changes in chemistry which could result from transmutations from irradiation. The alloy was exposed in air and steam between 800°C and 1200°C. Volatilized products and hydrogen were collected and measured. Posttest examinations were also performed on the samples to determine the amount of material loss during the exposures. The obtained measurements of volatilization flux ($\text{g/m}^2\text{-s}$), hydrogen generation rates ($\text{liters/m}^2\text{-s}$), and recession rates (mm/s) are data which can be used for safety analyses and material performance to predict consequences which may result from an accident involving the ingress of air or steam into the plasma chamber of fusion reactor.

In our volatility tests, only molybdenum and niobium were found at release levels above the detection limit. Although molybdenum is present at only 0.12 wt%, the quantities of this element volatilized in air are nearly comparable to the quantities of niobium released. The niobium release in steam is only three to four times higher than that of molybdenum in steam.

The hydrogen production of the niobium alloy is compared with other PFC materials that we have tested, specifically, beryllium, graphite, and a tungsten alloy. At high temperatures, the hydrogen production rate of the niobium alloy is among the lowest of these materials, significantly lower than beryllium. To understand what this means in an accident situation, modeling is necessary to predict temperatures, and therefore total hydrogen production. The INEL is currently doing this modeling.

The maximum dose mobilized for niobium and copper alloys are compared using copper data from previous tests at the INEL, since copper and niobium are candidates for divertor substrate material. We found that the maximum mobilized dose due to niobium is generally around an order of magnitude lower than that due to copper. Molybdenum is known to be highly volatile and our experiments confirmed this with high mass release of molybdenum relative to molybdenum weight percent in the niobium alloy we tested. Based on this and the dose hazard of molybdenum, we expect that molybdenum, another candidate divertor substrate material, would show a higher maximum dose mobilized than either niobium or copper.

ACKNOWLEDGMENTS

We wish to thank Dr. Vernod Sikka from Oak Ridge National Laboratories for preparing the alloy for this study. The contributions of Ron Wallace for performing the tests and Ed McNew for developing procedures and performing the chemical analyses have been a critical part of this investigation. We also thank Vonda Smith-Wackerle and Gary Fletcher for providing the metallographic support.

We appreciate the time taken by Steve Piet and Doug Holland of the INEL Fusion Safety Program for reviewing the manuscript and providing helpful comments.

TABLE OF CONTENTS

1. INTRODUCTION.....	1
2. RECOMMENDATIONS.....	1
3. REVIEW OF OXIDATION PROCESSES	2
4. EXPERIMENTAL PROCEDURES.....	7
4.1 Alloy Preparation	7
4.2 Air Tests	8
4.3 Steam Tests.....	9
4.4 Posttest Evaluations	9
5. EXPERIMENTAL RESULTS.....	9
5.1 Oxidation Products	9
5.2 Oxidation Rates	10
5.3 Volatilization Measurements.....	16
6. DISCUSSION	16
6.1 Recession Rates.....	16
6.2 Hydrogen Generation Rates.....	19
6.3 Volatilization	20
7. REFERENCES	26

Oxidation and Volatilization of a Niobium Alloy

1. INTRODUCTION

Niobium has been identified as a candidate material for use in plasma facing components for fusion reactors. In particular, it has been identified as a possible substrate material for the divertor. Safety analyses for such fusion devices as the International Thermonuclear Experimental Reactor (ITER) are needed to assess consequences from various accident scenarios. Oxidation and volatility data are needed to support analyses addressing the intrusion of air and steam into the plasma chamber. The oxidation and volatilization processes determine the amount of activated products that can potentially be released by aerosol formations and the amount of hydrogen produced which could form explosive mixtures. We performed a series of tests where a niobium alloy was exposed to air and steam using internal sample heating and flowing environments. Such tests likely simulate the nonequilibrium conditions existing at the first wall during potential accident scenarios. This report presents the oxidation rates, hydrogen production rates, volatilization rates, and resulting doses, determined from these tests performed at the Idaho National Engineering Laboratory (INEL). This preliminary investigation gives us an idea of the safety ramifications of the use of niobium.

2. RECOMMENDATIONS

These tests of the experimental heat of a niobium alloy in air and steam have provided preliminary rates of volatilization and alloy consumption in air and steam, and hydrogen production when exposed in steam. Volatilization rates for niobium and molybdenum, the only other element to have detectable volatility in this investigation, are reported in Section 5 for various conditions. Alloying elements were added to represent transmutation products. Molybdenum that was added as a small concentration, however, showed significant volatility compared to niobium. Other elements, viz., strontium and manganese which were attempted to be added to the alloy during fabrication were lost during melting. It is expected that transmutation products having volatility as high as these elements would also be lost during oxidation at rates comparable or higher than those observed for molybdenum. These contributions should be considered in activated product release calculations.

Based on our measured niobium alloy volatilization rates, we have calculated the maximum dose mobilized for niobium, and compared it with results from previously measured copper volatilization rates. We have found that the maximum dose mobilized in air and steam from the niobium alloy is generally at least an order of magnitude less than that from the copper alloy.

Recession rates recommended for niobium in oxygen and steam environments are given below. The relationship for the recession rate in oxygen environments (Equation A) results from Ong and Fassell's (1) review of several investigations for pure niobium. This relationship provided a fair correlation with the INEL test data. The relationship for recession rates in steam environments (Equation B) has been derived from the INEL investigation. Both relationships express temperature (T) in degrees K and oxygen pressure in terms of atmospheres.

$$dx/dt \text{ (cm/h)} = 1.19e^{(-4.750/T)} P_{O_2}^{1/2} \quad (A)$$

$$dx/dt \text{ (mm/s)} = 3.27e^{(-16.300/T)} P_{H_2O}^{1/2} \quad (B)$$

The expression derived from the INEL tests for the rate of hydrogen generation when reacted in high temperature steam is shown below as Equation C, where T is in units of degrees K. This relationship is recommended for use in safety calculations concerning potential hydrogen generation and the formation of explosive mixtures.

$$\text{Hydrogen Generation Rate (liters/m}^2\text{s)} = 100e^{(-9.170/T)} \quad (C)$$

Tests in steam at temperatures of 1000°C and higher showed a tendency for the material to become embrittled and crack. This appears to be due to the incorporation of hydrogen. The impact of the dissolution of oxygen and hydrogen upon the mechanical properties of niobium, and other refractory metals, should be held in mind when considering design and safety.

We want to emphasize that the results presented here are the result of a limited number of tests. More testing is necessary to build up a database that can be used for regulatory assessments such as will be necessary for ITER. This testing should include the investigation of mechanical spalling, effect of composition on volatility, and transport of volatilized products.

3. REVIEW OF OXIDATION PROCESSES

The oxidation behavior of niobium is intricately influenced by temperature, time, and oxygen availability. Oxygen supply is influenced by surface mechanisms involving physical adsorption of oxygen molecules and their chemisorption. Each oxygen molecule will require two active sites for dissociation. This mechanism causes oxidation kinetics of niobium, as well as tantalum, to be proportional to $P_{O_2}^{1/2}$ at high temperatures and low oxygen pressures. Rate constants, however, become independent of oxygen pressure at low temperatures and high oxygen pressures. An example of these relationships between oxidation rate constants, temperature, and oxygen pressure are shown by Kofstad (2) for niobium at pressures below 100 torr and temperatures at, or below, 550°C in Figure 1(a). This dependence upon $P_{O_2}^{1/2}$ persists for temperatures at 800°C and higher pressures as shown in Figure 1(b). This indicates that the dissociative adsorption process likely remains the responsible controlling mechanism at higher temperatures and pressures.

The oxidation behavior of niobium is also complexly influenced by the large number of oxide phases that can develop and by the high solubility of oxygen within the metallic structure. For these reasons, the oxidation kinetics of niobium resembles that of tantalum for which Kofstad (2) has schematically shown with respect to temperature in Figure 2. The sequence may, in fact, be even more complex for niobium which has even a greater number of oxide phases. At low temperature, i.e., below 600°C to 650°C, oxygen is dissolved in the metal and can form two possible metallic oxide phases (suboxides). These suboxides NbO_x and NbO_z both have a tetragonal structure. The latter phase, however, has a larger unit cell and is stable to temperatures of about 600°C. NbO_x has been found only below 450°C. The importance of the NbO_z phase is that it forms plate-like structures near the surface. These are the nucleation sites on which Nb_2O_5 develops and leads to the breakaway, or linear oxidation rates at the lower temperatures. The transition time for breakaway decreases with increasing

(a)

(b)

Figure 1. Relationships of oxidation kinetics of niobium to temperature and oxygen pressure. Referenced information presented by Kofstad (2).

Figure 2. Schematic of rate kinetics presented by Kofstad (2) for the oxidation of tantalum with respect to time and temperature.

Figure 3. Linear oxidation rates of niobium plotted with respect to reciprocal temperature. The review of the various investigations in oxygen environments was presented by Ong and Fassell (1).

temperature and oxygen pressure. It is too brief to detect at temperatures above 500°C and at oxygen pressures near one atmosphere. NbO₂ decomposes above about 600°C and the following oxidation steps are indicated by Kofstad (2):

The NbO is believed to form irregular crystals that do not completely cover the surface and are therefore nonprotective. NbO₂ is believed to form a compact protective scale and to be responsible for the parabolic behavior between 650°C and 850°C. It is not known whether a low temperature γ -Nb₂O₅ also contributes to protection during this parabolic behavior. However, it is clear that the formation of a porous Nb₂O₅ scale is associated with the ensuing linear oxidation rate. The parabolic behavior is short lived and oxidation is generally expressed as by linear oxidation rates. Ong and Fassell (1) have summarized linear rate constants from several studies encompassing temperatures from 400°C to 1200°C and a wide range of oxygen pressures. These rates plotted with respect to reciprocal temperature are shown in Figure 3. The marked deviation in rate constant at approximately 650°C is believed to be due to the extent of formation, or absence, of the suboxide and to the development of a protective NbO₂ layer. These processes are time and pressure dependent and therefore dependent upon heating rate. There is also a transformation from a low temperature γ -Nb₂O₅ to a higher temperature α -Nb₂O₅ between 800°C and 900°C. The phase change that is also dependent upon heating rate has been associated with a change in temperature dependence upon the linear rate constant (1).

Expressions for the recession (cm/h) of niobium have been developed by Ong and Fassell (1) for the temperature and oxygen pressure ranges shown in Figure 3. Relationships for both low and high temperature regions were developed which included correlations with $P_{O_2}^{1/2}$. These relationships are shown below as Equation (1) for temperatures below 650°C and Equation (2) for temperatures from 650°C to 1200°C.

$$dx/dt \text{ (cm/h)} = \frac{10.23 \times 10^{(-2.684/T)} P_{O_2}^{1/2}}{1 + (5.7 \times 10^{-14}) \times 10^{(9.780/T)} P_{O_2}^{1/2}} \quad (1)$$

$$dx/dt \text{ (cm/h)} = 1.19 \times 10^{(-2.060/T)} P_{O_2}^{1/2} \quad (2)$$

Temperature (T) is expressed as degrees K and $P_{O_2}^{1/2}$ is oxygen pressure in atmospheres. Equation (2) encompasses the temperatures and pressures used in the current study.

Kofstad (2) reports that above 1200°C reaction rates become too rapid to measure at oxygen pressures of one atmosphere. Nb₂O₅ become liquid at 1500°C and above this temperature oxide evaporation increases. The formation of the oxide which is proportional to $P_{O_2}^{1/2}$ and the extent of oxide evaporation or retention depend upon time and oxygen pressure.

Oxidation of pure niobium in environments containing water vapor has not been characterized as well as the behavior in air. Blackburn (3) presents a similar oxidation sequence of niobium in water vapor as observed for air. This includes the dissolution of oxygen into the metal, the formation of the lower oxides, i.e., NbO and NbO₂, and then the nucleation and growth of Nb₂O₅ upon NbO₂. Principle differences are slower nucleation and growth processes due to the lower oxygen availability in steam. This results in longer times before breakaway, i.e., onset of nonprotective conditions. Blackburn performed tests between 200°C and 1100°C in water vapor in 5×10^{-3} atm. Although he observed some differences due to surface preparation he also presented a fairly good agreement to a cubic relationship over

Figure 4. Reaction kinetics measured for niobium in 5×10^{-3} atmosphere water vapor by Blackburn (3). (a) log weight gain versus log time plot. (b) Arrhenius plot of log cubic rate constant versus reciprocal temperature.

much of the temperature range (see Figure 4). There is evidence of a deviation in the reaction rates above 750°C, and the rates also tend to become linear for the higher temperature tests after 5 to 60 minutes. Fromm and Jehn (4) also address the reaction of niobium in water vapor, but at higher temperatures of 1800°C to 2400°C and lower pressures, i.e., 10^{-1} to 10^{-5} torr. They presume that the reaction is controlled by the decomposition of H₂O molecules and the absorption of oxygen by the metal. They report that niobium will absorb oxygen and form an oxide at even very low vapor pressures. The oxide may collect at temperatures below 1600°C, but at temperatures above 1800°C oxide volatilization becomes significant. Equilibrium solubilities and material losses are eventually reached. Niobium would lose approximately 10 $\mu\text{m/h}$ in a water vapor pressure of 10^{-3} torr at 1800°C.

Enhancement of oxide volatilization by complexes formed in water vapor has not been reported for niobium and tantalum. Speiser and St. Pierre (5) report that, although hydrated oxides markedly increase the volatility of tungsten and molybdenum, this mechanism has not been observed in niobium and tantalum. They point out that Elliot and Brewer (6) observed no Nb₂O₅ transport at 850°C and that Blackburn (3) demonstrated no volatility of niobium oxides in water vapor at temperature of up to 1100°C.

4. EXPERIMENTAL PROCEDURES

An experimental niobium alloy was prepared with minor additions to represent chemical changes resulting from transmutations. This alloy was then tested in both air and steam at temperatures ranging from 800°C to 1200°C. The following sections describe the alloy fabrication, test methods and procedures used for posttest evaluations.

4.1 Alloy Preparation

Transmutation products which would form in a Nb-Zr alloy are strontium, yttrium, molybdenum, and technetium. It would be ideal if these elements, or reasonable substitutes (for example, manganese for technetium since technetium does not have a stable isotope) could be alloyed with the base composition. An attempt was made to melt a twenty pound ingot of Nb, Zr, Sr, Y, Mo, and Mn at Teledyne Wah Chang Albany and process it into plate representative of irradiated material (using stable elements). This attempt was abandoned since strontium was lost during melting. Ultimately, a vacuum arc melting process was used at Oak Ridge National Laboratory which prepared "finger-sized" ingots. Zirconium, yttrium, molybdenum, and manganese were added prior to melting, however, most of the manganese was lost by evaporation. Some copper was picked up from the water-cooled mold. The ingots measuring approximately 12 mm x 12 mm x 12 cm were cold rolled to thicknesses of approximately 2.5 mm without annealing. The resulting composition of the as-rolled plate is shown in Table 1. Anneals were performed at 1050°C in high purity helium in an attempt to provide a recrystallized structure. However, since yttrium was lost during this thermal cycle, specimens of approximately 2.5 mm x 12.4 mm x 25.4 mm were prepared from the as-rolled plate.

Table 1. Chemical Composition of Niobium Alloy Samples (weight percent)

<u>Copper</u>	<u>Molybdenum</u>	<u>Yttrium</u>	<u>Manganese</u>	<u>Zirconium</u>	<u>Niobium</u>
0.19	0.12	0.12	0.003	1.04	Balance

N92 0199

Figure 5. Schematic of the VAPOR test apparatus used for testing niobium alloy samples in air and steam environments.

4.2 Air Tests

Samples were tested in flowing air in the VAPOR (Volatilization of Activation Product Oxides Reactor) system shown in Figure 5. A Type R (Pt:Pt-13%Rh) thermocouple embedded into the sample was used to monitor and control the specimen temperature. A two-color infrared pyrometer was also used as a secondary temperature measurement. Two liters of dry air per minute were preheated and flowed upward passed the specimen. The specimen was inductively heated in a quartz reaction chamber. Tests were initiated by heating the specimens to their targeted test temperature in the preheated air. Oxides that volatilized could deposit on the reaction chamber walls, a collector positioned approximately 1.5 cm above the specimen, the cap of the reaction chamber, a condenser tube, or a quartz wool filter. Temperatures at these locations depended upon specimen temperature and ranged from 190°C to 300°C for the reaction chamber and collector. The reaction cap had temperatures ranging from 150°C to 195°C. Temperatures in the condenser tube and at the quartz wool remained between 55°C and 65°C for all tests. The gas stream was then bubbled through a liquid trap and released to the atmosphere. Pressure within the system was approximately ambient atmospheric pressure, i.e., 85 kPa (0.85 atm).

4.3 Steam Tests

Steam tests were performed in a similar apparatus. A different start-up procedure, however, consisted of initially purging and then heating the sample to near the targeted temperature with argon flowing at 2 liters per minute. Steam flow of 2.5 liters per minute was then initiated and argon flow was terminated. The specimen temperature was adjusted and maintained at the targeted value based upon the embedded thermocouple. The higher heat content of the steam compared to air resulted in higher temperatures in the downstream components. Temperatures for the reaction chamber and the collector ranged from 380°C to 580°C. The reaction cap had temperatures from 300°C to 450°C, while those for the condenser tube and quartz wool ranged from 90°C to 225°C. The gas stream was directed from the condenser tube through a copper coil in an ice bath to ensure complete steam condensation. The product gas, hydrogen, was then collected in a volumetric flask. Measurements of these gas volumes were used to provide indications of reaction rates.

4.4 Posttest Evaluations

The sample and as much of the spalled oxide as possible were removed from the glassware following the test. The various components were rinsed with a hydrofluoric (HF) and nitric (HNO₃) acid solutions. These solutions were heated and treated with hydrogen peroxide to ensure that the oxidation products were put into solution. The solutions were analyzed by atomic emission spectroscopy inductive coupled plasma (AES/ICP). Measurements of weight to determine oxygen pick-up were obtained from the oxidized samples and as much of the spalled oxide which could be collected. Samples were also sectioned and metallographically prepared to determine the amount of the alloy affected by the oxidation process.

5. EXPERIMENTAL RESULTS

5.1 Oxidation Products

The niobium alloy developed a visually apparent oxide layer rather quickly in the flowing air environment at all temperatures. This oxide was light yellowish in appearance at 800°C but white when formed at higher temperatures. This scale, consisting of a form of Nb₂O₅ and/or possibly other forms of the several higher niobium oxides, thickened and sometimes spalled during longer term or higher temperature exposures. However, generally the scale would remain on the specimen during testing but almost entirely spall off when cooled or gently handled. A very adherent bluish-black oxide layer, probably NbO₂, existed beneath the outer scale. The appearance of the spalled oxide and adherent oxide layer for a sample tested at 800°C in air are shown in Figure 6. The scales which formed at higher temperatures in air sintered into a harder oxide and underwent less fragmentation.

Samples exposed in steam developed only a dense, darker appearing scale. This scale developed sufficient thickness for samples exposed at or above 1000°C to generate thermal stresses that caused spalling during cooling. Examples of remnant scales are shown in metallographic sections in Figure 7. The scale remaining on the sample exposed 5 hours in air at 1200°C, Figure 7(a), is approximately 0.02 mm thick. The scale on the sample tested 5 hours 800°C in steam which did not show much spalling is evident in Figure 7(b). This scale is about 0.02 to 0.04 mm thick. An annealed, recrystallized structure is apparent in the sample tested at 1200°C compared to the cold-worked structure remaining in the sample exposed at

Nb-1Zr Alloy
Spec. 92-1
800°C -- 5 h
in air

Figure 6. Photograph of the niobium alloy tested at 800°C in air showing the thick light colored oxide scale which spalled off and the dark adherent underlying oxide.

only 800°C. These cross sections also showed that samples exposed to steam environments at or above 1000°C were cracked indicating that the material had become somewhat embrittled.

5.2 Oxidation Rates

Measurements of oxidation rates of niobium by weight change are complicated by oxygen pick-up that may be dissolved into the alloy, by the large number of oxide phases which may form, some of which may be of varying stoichiometries, and by oxide spalling. Weight changes reported in Table 2 are rough indications of oxygen pick-up obtained from the samples and as much of spalled oxide as possible which could be recovered. Oxidation rates for air and steam tests have therefore been determined from amounts of base alloy which has been reacted as measured from metallographic cross sections. Rates of material losses for both the air and steam tests are shown in Table 2. The recession rates for the niobium alloy in air are also listed in Table 3 along with the values predicted from Equation 2 by Ong and Fassell (1). Gas collected from the steam tests was used to determine hydrogen generation rates. Examples of hydrogen release with time at temperatures from 800°C to 1200°C are shown in Figure 8. Although the releases initially appeared parabolic, linearity appeared to develop with time at higher temperatures. Linear rates were therefore assumed based upon the amount of gas collected during the first hour of each test. These rates are included in Table 2. The recession

(a)

(b)

Figure 7. Cross sections of niobium alloy specimens showing microstructures and residual oxide scales. (a) Specimen tested 5 hours in air at 1200°C. (b) Specimen tested 5 hours in steam at 800°C.

Table 2. Data for niobium air and steam tests

Temp. (°C)	Time (h)	Test Gas	Initial Mass (g)	Oxygen Pick-up (g)	Oxide Spalling	Recession Rate (mm/s)	Total Hydrogen Generation liters (STP)	Rate of Hydrogen Generation (liters/m ² -s)
804	1	air	8.353	0.280	major	1.21E-5	---	---
805	5	air	8.414	1.045	major	8.5E-6	---	---
815	20	air	7.014	2.787	major	8.9E-6	---	---
909	20	air	7.018	0.972	some	2.3E-6	---	---
909	1	air	8.193	0.302	major	2.00E-5	---	---
999	5	air	8.294	1.010	major	1.38E-5	---	---
989	20	air	7.023	1.872	major	6.83-6	---	---
1092	5	air	7.007	1.148	major	1.87E-5	---	---
1095	5	air	7.026	1.207	major	2.06E-5	---	---
1184	1	air	8.357	0.882	major	7.27E-5	---	---
1204	5	air	8.327	2.351	major	3.86E-5	---	---
800	1	steam	8.350	0.077	none	1.1E-6	0.064	0.0204
800	5	steam	8.450	0.130	minor	1.8E-6	0.145	0.0215
813	20	steam	7.015	0.092	minor	3.4E-7	0.265	0.0238
904	1	steam	7.012	0.023	minor	2.2E-6	0.127	0.0420
912	5	steam	7.019	0.057	minor	1.5E-6	0.360	0.0791
1002	1	steam	8.380	0.150	some	8.4E-6	0.179	0.0572
1001	5	steam	7.015	0.270	major	7.5E-6	0.718	0.0585
1004	10	steam	7.001	0.315	major	6.2E-6	1.160	0.0694
1109	1	steam	7.011	0.337	major	2.67E-5	0.460	0.1524
1198	1	steam	8.367	0.522	major	5.65E-5	0.790	0.2519

Table 3. Comparison of recession rates for oxidation in air.

Temp. °C	Time (h)	Measured Recession Rate (cm/h)	Recession Rate Equation 2
804	1	0.0044	0.0059
805	5	0.0031	0.0059
815	20	0.0032	0.0059
909	20	0.0008	0.0086
1001	1	0.0072	0.0118
999	5	0.0050	0.0118
989	20	0.0024	0.0118
1092	5	0.0067	0.0153
1095	5	0.0074	0.0153
1184	1	0.0262	0.0196
1204	5	0.0139	0.0196

Figure 8. Hydrogen release with respect to time for the niobium alloy tested in steam at various temperatures.

Table 4. Volatilization data for niobium tests in air and steam

Temp (C)	Temp Control	Time (h)	Test gas	***** Chamber	Measured Collect	Niobium, $\mu\text{g/ml}$ Cap	Q.W.	***** CW Tube	Sum Excess Chamber	Ratio Chamber: Sum	Flux ($\text{g/m}^2\text{-s}$)
804	a,b	1	air	0.040	0.000	0.000	0.000	0.000	0.000	---	d.l.
815	a,b	20	air	0.834	0.000	0.013	0.124	0.004	0.141	6	2.3E-07
909	a,b	20	air	7.354	0.000	0.027	0.110	0.012	0.149	50	2.4E-07
1001	a,b	1	air	0.140	0.000	0.000	0.000	0.000	0.000	---	d.l.
999	a,b	5	air	3.184	0.000	0.000	1.004	0.000	1.004	3	6.6E-06
989	a,b	20	air	8.304	0.020	0.085	0.344	0.000	0.449	20	3.0E-07
1092	a,b	5	air	18.024	0.025	0.002	0.102	0.000	0.129	140	1.2E-06
1095	a,b	5	air	37.224	0.030	0.311	0.769	0.000	1.160	30	8.6E-06
1184	a,b	1	air	2.764	0.000	0.000	0.906	0.000	0.906	3	3.0E-05
1204	a,b	5	air	7.364	0.000	0.000	0.415	0.000	0.415	20	2.7E-06
***** Measured Molybdenum, $\mu\text{g/ml}$ *****											
804	a,b	1	air	0.000	0.000	0.000	0.000	0.000	0.000	---	d.l.
815	a,b	20	air	0.000	0.000	0.000	0.000	0.000	0.000	---	d.l.
909	a,b	20	air	0.000	0.000	0.000	0.000	0.000	0.000	---	d.l.
1001	a,b	1	air	0.000	0.000	0.000	0.000	0.000	0.000	---	d.l.
999	a,b	5	air	0.000	0.000	0.000	0.000	0.000	0.000	---	d.l.
989	a,b	20	air	0.063	0.031	0.049	0.053	0.000	0.133	0.5	3.2E-07
1092	a,b	5	air	0.404	0.232	0.160	0.192	0.000	0.584	0.7	6.8E-06
1095	a,b	5	air	0.063	0.010	0.037	0.057	0.002	0.106	0.6	8.2E-07
1184	a,b	1	air	0.049	0.025	0.000	0.197	0.000	0.222	0.2	8.9E-06
1204	a,b	5	air	0.080	0.060	0.032	0.162	0.000	0.254	0.3	2.4E-06
800	a,c	1	steam	0.000	0.000	0.000	0.000	0.000	0.000	---	d.l.
800	a,c	5	steam	0.000	0.000	0.000	0.000	0.000	0.000	---	d.l.
813	a,c	20	steam	0.014	0.001	0.000	0.000	0.000	0.001	---	4.9E-09
904	a,c	1	steam	0.000	0.000	0.000	0.053	0.000	0.053	---	1.7E-06
912	a,c	5	steam	0.000	0.000	0.000	0.000	0.000	0.000	---	d.l.
1002	a,c	1	steam	0.063	0.000	0.000	0.000	0.000	0.000	---	d.l.
1001	a,c	5	steam	0.252	0.003	0.269	0.268	0.000	0.540	0.5	3.6E-06
1004	a,c	10	steam	0.611	0.077	0.191	0.313	0.000	0.581	1.1	2.4E-06
1109	a,c	1	steam	0.516	0.054	0.080	0.228	0.000	0.362	1.4	1.5E-05
1198	a,c	1	steam	0.691	0.378	0.441	0.495	0.000	1.314	0.5	6.8E-05

Footnotes:

- Temperature control estimated as ± 25 C.
- Air flow rate is 2 liters per minute.
- Environment is 100% steam with a flow rate of 2.5 liters per minute.

Detection limits:

Niobium:	(1h) = $2.5\text{E-}6$,	(5h) = $5.0\text{E-}7$,	(20h) = $1.2\text{E-}7$
Molybdenum:	(1h) = $1.7\text{E-}6$,	(5h) = $3.3\text{E-}7$,	(20h) = $8\text{E-}8$
Zirconium:	(1h) = $8.0\text{E-}7$,	(5h) = $1.6\text{E-}7$,	(20h) = $4\text{E-}8$
Yttrium:	(1h) = $3.6\text{E-}7$,	(5h) = $7\text{E-}8$,	(20h) = $2\text{E-}9$
Manganese:	(1h) = $1.6\text{E-}7$,	(5h) = $3\text{E-}8$,	(20h) = $8\text{E-}9$
Copper:	(1h) = $1.8\text{E-}6$,	(5h) = $3.7\text{E-}7$,	(20h) = $9\text{E-}8$

Figure 9. Temperature dependence of the extent of niobium alloy consumed in high temperature steam.

rates measured for the one hour tests in steam are also shown plotted on an Arrhenius plot in Figure 9. Fairly good linear fits were obtained for both recession rate and hydrogen generation rate over the region from 800°C to 1200°C. The relationship obtained to show recession (mm/s) is expressed in Equation 3, while the hydrogen generation rate as (liters/m²-s) is shown in Equation 4.

$$dx/dt \text{ (mm/s)} = 3.27e^{(-16,300/T)} \quad (3)$$

$$\text{Hydrogen Generation Rate (liters/m}^2\text{s)} = 100e^{(-9,170/T)} \quad (4)$$

For the steam tests, there was a fairly consistent correlation between the recession measurements and the quantities of total hydrogen collected as indicated in Table 2. This ratio

showed that 0.22 ± 0.04 mm of alloy was lost for each liter of hydrogen collected. This corresponds to a generation of 2.3 to 3.2 moles of hydrogen for each moles of niobium reacted based upon the specimen surface area of 8.4 cm^2 . This ratio of hydrogen to niobium reaction would indicate the formation of Nb_2O_5 . However, the oxide was dark colored indicative of a lower oxide such as NbO or NbO_2 . This suggests that the extra hydrogen may be contributed from reactions involving the formation of an oxide:hydroxide complex which have been associated with higher volatilization for other refractory metals.

5.3 Volatilization Measurements

Analyses of the solutions prepared from the various glassware components and the quartz wool showed only niobium and molybdenum to be above detection limits. Detection limits for all elements in the 100-ml solutions are shown in Table 4. The amounts of niobium and molybdenum collected from each component are also shown. Some of the contributions in the test chamber were due to oxide which spalled and could not be completely removed. Amounts measured at the remaining locations are assumed to be due to volatilization. The sum from these latter components are shown in Table 4 and plotted in Figure 10 to show dependence upon temperature and time. These results show that niobium release was not detected at 800°C for the one and five hour exposures in air and steam but was detected for the 20 hour tests. Some niobium releases were detected in steam at and above 900°C with one hour exposures. No niobium release was detected from the one hour 1000°C air exposure, but, releases were observed for longer term and higher temperature exposures.

No molybdenum releases were detected for the 800°C tests, the 900°C tests, and the short term 1000°C tests in either environment. Releases occurred for the 20-hour air test, the 5- and 20- hour steam tests at 1000°C , and at all other higher temperature tests. The plots in Figure 10 demonstrate higher volatility for both niobium and molybdenum in steam compared to in air. The relative amounts of niobium and molybdenum measured in the test chamber compared to that deposited on the other components (see Table 4) provides additional indications of the volatility of these elements. Ratios ranging from 3 to 140 show that most of the niobium in the test chamber was due to spalling. However, the ratios from 0.2 to 1.4 for molybdenum indicated that volatilization and deposition account for much of the quantities of this element measured in the test chamber. To correct for the deposition in the test chamber, the areas of the collector and chamber were considered, and volatilized products in the tests chamber were set at 2 times the amounts measured on the collector. Total volatilized quantities were obtained and were used to calculate release rates from the specimens. Detection limits were used for flux calculations for zirconium, yttrium, manganese, and copper. These rates are summarized in Table 4.

6. DISCUSSION

6.1 Recession Rates

Recession rates we have measured in air and have listed in Table 3 show a general agreement with the relationship presented by Ong and Fassell (1). Our data show a lower value for the 900°C test compared to 800°C and 1000°C . This may reflect the distinct minimum displayed by Ong and Fassell (see Figure 3) but with a shift to a higher temperature. We noted a relatively uniform rate with time indicating linear oxidation at 800°C . The rates that we observed at 1000°C , however, appeared to decrease with time. In general our shortest duration tests provided the best correlation with the values calculated from Ong and Fassell's

(a)

(b)

Figure 10. Releases of niobium and molybdenum measured in air and steam at various times and temperatures. (a) Niobium releases. (b) Molybdenum releases.

Figure 11. Comparison of hydrogen generation rates for several candidate plasma facing materials when reacted in steam.

relationship. They considered the oxidation kinetics to be linear in time. Data from the high pressure tests in their survey are also likely to be from short term tests. Our data shifts from values of 25 percent lower at 800°C to approximately 30 percent higher at 1200°C. This may be due to our material changing from a cold-worked structure to an annealed structure as test temperature increases. The cold-worked structure may also influence the nucleation and growth processes for the various oxide phases and thus cause some change in the temperature at which the oxidation minimum occurs. In summary, we recommend the use of Equation 2 by Ong and Fassell for fusion safety calculations since it considers the temperature range of 650°C to 1200°C and a wide range of pressures.

Although temperature and pressure conditions of the tests by Fromm and Jehn (4) are too different from those of the INEL tests to provide meaningful comparison, Blackburn's (3) data helps provide insight into recession rates of niobium in steam. If we assume that the oxidation process is controlled by the oxygen adsorption process and is proportional to $P_{O_2}^{1/2}$, then we would expect a factor of 13 difference between our data from 0.85 atm. and Blackburn's data from 5×10^{-3} atm. of water vapor. Recession rates which have been extracted from Blackburn's work and rates which we have obtained from our tests are summarized in Table 5. The ratios of the rates which we have obtained compared to Blackburn's range from seven to seventeen. This supports a correlation of the recession rate to the square root of the water vapor pressure. We therefore recommend combining Equation 3 with this correlation to provide the following relationship for use in fusion safety calculations.

$$dx/dt \text{ (mm/s)} = 3.27e^{(-16,300/T)} P_{H_2O}^{1/2} \quad (5)$$

Table 5. Comparison of recession rates from oxidation in steam

Temp.(°C)- Time(h)	Blackburn (3) (mm/s)	INEL (mm/s)	Ratio: INEL/Blackburn
800 - 1	6E-8	1E-6	17
950 - 1	3E-7	2E-6	7
1100 - 1	3E-6	3E-5	10

6.2 Hydrogen Generation Rates

Hydrogen releases at the various temperatures shown in Figure 8 appear somewhat parabolic in time. Some of the initial contributions are inherent to the test system. Extrapolations to zero time indicate a volume of approximately 50 ml. This is particularly apparent for the 800°C and 900°C tests. This is likely the result of argon being flushed from the system. However, higher temperature tests continue to show some minor reduction in release rate with time. This may be due to decreasing temperatures at the outer surfaces as oxide scales grow in thickness and are cooled by the flowing steam, or, by reductions in the active sites involved in the dissociation of the water molecules. Fromm and Jehn (4) also provide a relationship indicating the concentrations of hydrogen which could be dissolved in niobium. The maximum which could be dissolved at 1200°C is about 0.5 atomic percent. This would amount to about 5 ml and would therefore not significantly impact our volumetric measurements. Such dissolved hydrogen, however, is likely responsible for lower ductility and the cracking which occurred in steam tests. In summary, however, the linear release rates based upon hydrogen generation within the first hour, which are expressed by Equation 4, should represent conservatively high rates and be appropriate for fusion safety calculations.

The rate for hydrogen generation by niobium reaction with steam as represented by Equation 4 is compared with rates reported (7) for other candidate plasma facing materials in Figure 11. We do not have measurements of hydrogen generation rates for copper in steam, but we have measured hydrogen generation in steam reactions with graphite, beryllium, and tungsten. Hydrogen generation was not measured directly in the tungsten alloys tests, it was determined from previously tested specimens using weight-change measurements and information from the literature, and is a conservative estimate. We would expect the actual curve to lie somewhere below, but close to this curve. We are currently testing plasma-sprayed

tungsten, and the hydrogen generation rate appears comparable to that of the niobium alloy. Hydrogen generation by niobium is significantly lower than by fully dense beryllium in steam, and less than graphite at temperatures above 1000°C.

6.3 Volatilization

Volatilization rates shown for niobium in steam in Table 4 are one to two orders of magnitude higher than those observed in air. This contrasts with the early reports (3,6) that no enhancement of volatility of niobium was observed in water vapor. A possible explanation may be that early studies were often based upon weight change without compensation for oxygen pick-up.

A comparison of data for niobium and molybdenum in Table 4 provides some insight into the relative volatility of these two elements in air and steam. Although molybdenum is present at only 0.12 wt%, the quantities of this element volatilized in air are nearly comparable to the quantities of niobium released. The niobium release in steam is only three to four times higher than that of molybdenum in steam.

The data that we have gathered can be used to determine isotope releases, and therefore doses, from a particular PFC component. Copper and molybdenum are the two other primary candidates for the divertor substrate identified in the Conceptual Design Activity (CDA) (8). We have not tested a molybdenum alloy, but the literature indicates that molybdenum is an extremely reactive metal and that its oxide, MoO_3 , is very volatile. This information, in addition to the high volatility of the molybdenum in the niobium alloy, indicates that molybdenum would be easily released. With respect to prompt dose, a study by Piet, et al. (9), concluded that the prompt dose rating for molybdenum was the same as that for copper and niobium (D on a scale from A to G, G being the worst; each letter grade difference represents an order of magnitude in the figure of merit). The latent (or chronic) dose ratings were niobium: C, copper: D, and molybdenum: E. Thus, on a per kilogram basis, niobium is the least hazardous from a radioactivity contamination point of view, while molybdenum is the worst, molybdenum being two orders of magnitude worse than niobium.

Table 6. Composition of Nb-1Zr alloy after 1 MW-yr/m² fluence (weight percent)

<u>Molybdenum</u>	<u>Yttrium</u>	<u>Strontium</u>	<u>Zirconium</u>	<u>Niobium</u>
0.0002	0.001	0.00001	0.99	Balance

Volatility is important because it determines dose releases in an accident. Figures 12-13 give the maximum mobilized dose as a function of temperature for niobium and copper (10) in air and steam, respectively, based on our volatility measurements. We have not tested molybdenum, but we would expect it to be worse than niobium and copper because of its high volatility and dose. We have assumed a 1-week LOCA involving the entrance of air or steam into the plasma chamber. The fluence is 1 MW-yr/M². The divertor area is 200 m², and the material thickness is .005m. No credit has been taken for confinement (thus the graphs show maximum mobilized dose, not necessarily dose released to the environment), the primary aim of this analysis being a qualitative comparison. Table 6 shows the divertor composition for a fluence of 1 MW-yr/M². Notice that the alloy composition of our test samples differed somewhat from this divertor composition. For this study, we have assumed that the volatility flux of each element scales linearly with composition. This assumption had a large effect on the yttrium dose, reducing it by two orders of magnitude. An initial investigation into this

scaling for steel alloys was done by Piet, et al. (11). Future studies that focus on the scaling of the volatility flux with composition are necessary to confirm this assumption; we plan to begin this type of study next fiscal year. We assumed a volatility flux at the detection limits for zirconium and yttrium. Because the strontium was released during sample production due to its high volatility, we have assumed that all strontium is released. Technetium and molybdenum were not produced in the activation analysis that we have used (the activation code used in this analysis does not track radioactive chains past stable daughters). Technetium and molybdenum would be present in very small amounts, and would probably not contribute significantly to the total dose. A significant amount of molybdenum would be very hazardous because of its high volatility and dose hazard. In both the air and steam cases, the dose released is less for niobium than copper. Accident temperatures are most likely to be below 1000°C, and there is generally at least an order of magnitude difference between the copper and niobium alloys at these temperatures. Figures 14-15 give the dose mobilized by element for the niobium alloy. Niobium is the major source of dose hazard for this alloy.

Based on these results, niobium appears more desirable than copper or molybdenum as a divertor substrate material. The mobilized dose is significantly less for niobium than copper. The high volatility and dose hazard of molybdenum indicate that it would be much less attractive than either copper or niobium. For these reasons, we recommend niobium over copper or molybdenum as a divertor substrate material.

Figure 12. Comparison of the maximum mobilized dose for a niobium alloy and a copper alloy exposed to air.

Figure 13. Comparison of the maximum mobilized dose for a niobium alloy and a copper alloy exposed to steam.

Figure 14. Elements contributing to the maximum mobilized dose for a niobium alloy exposed to air.

Figure 15. Elements contributing to the maximum mobilized dose for a niobium alloy exposed to steam.

7. REFERENCES

1. J. N. Ong, Jr. and W. M. Fassell, Jr., "Kinetics of Oxidation of Columbium and Other Refractory Metals" Corrosion, 18 (1962) pp. 382-389.
2. P. Kofstad, High Temperature Oxidation of Metals, John Wiley & Sons, Inc., New York, N.Y., (1966). pp. 190-227.
3. P. E. Blackburn, "The Mechanism of the Niobium Reaction with Water Vapor and with Oxygen", J. Electrochemical Soc., 109 (1962) pp. 1142-1150.
4. E. Fromm and H. Jehn, "Reaction of Niobium and Tantalum with Gases at High Temperatures and Low Pressures", Vacuum 19 (1969) pp. 191-197.
5. R. Speiser and G. R. St. Pierre, "Fundamentals of Refractory Metal-Gaseous Environmental Interaction," The Science and Technology of Tungsten, Tantalum, Molybdenum, Niobium and Their Alloys, ed. N. E. Promisel, Pergamon Press (1964) pp. 301-306.
6. Elliot and Brewer, UCRL Report 1831, June 1952.
7. G. R. Smolik, "Tungsten Alloy Oxidation Behavior in Air and Steam", EGG-FSP-10166, March 1992.
8. D. Smith, et al., ITER Blanket, Shield, and Material Data Base, IAEA ITER Documentation Series No. 29, 1991.
9. S. J. Piet, E. T. Cheng, and L. J. Porter, "Accident Safety Comparison of Elements to Define Low Activation Materials," EGG-FSP-8552, July 1989.
10. G. R. Smolik, R. M. Neilson, Jr., and S. J. Piet, "Volatility from Copper and Tungsten Alloys for Fusion Reactor Applications", IEEE Thirteenth Symposium on Fusion Engineering, Knoxville, TN, October 2-6, 1989.
11. S. J. Piet, R. M. Neilson, Jr., G. R. Smolik, and G. A. Reimann, "Initial Experimental Investigation of the Elemental Volatility From Steel Alloys For Fusion Safety Application," EGG-FSP-8459, April 1989.

**DATE
FILMED**

12/18/92