DOE/ER/45400--T4

SC71014.ATR

SC71014.ATR

Copy No. 9

MECHANISMS OF MECHANICAL FATIGUE IN CERAMICS

ANNUAL TECHNICAL PROGRESS REPORT NO. 2
For the period August 15, 1990 through August 14, 1991

GRANT NO. DE-FG03-89ER45400

Prepared for:

**U.S. Department of Energy
1333 Broadway
Oakland, CA 94605
Attn: James Solomon**

Received by AS

NOV 18 1992

Prepared by:

Brian Cox

OCTOBER 1992

**Rockwell International
Science Center**

TABLE OF CONTENTS

	Page
1.0 INTRODUCTION	1
2.0 THEORY OF BRIDGED CRACKS.....	1
3.0 EXPERIMENTAL RESEARCH.....	2
4.0 COLLABORATIONS AND SUPERVISION OF A STUDENT	4
5.0 REFERENCES	5
6.0 CUMULATIVE LIST OF PUBLICATIONS.....	6
7.0 APPENDIX	6

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

1.0 INTRODUCTION

This report covers work done in the second twelve month period of our initial two-year contract on "Mechanisms of Mechanical Fatigue in Ceramics." A large portion of our work in that period consisted of developing the theory of bridged cracks, with especial emphasis on interpreting fatigue and fracture experiments in terms of micromechanical mechanisms. In the experimental area, we shifted our focus away from room temperature tests of metal reinforced ceramics such WC/Co to high temperature testing of fibrous composites. We also participated in a major review of experimental progress in the fatigue of ceramic materials through an international conference, edited proceedings, and a published review.

2.0 THEORY OF BRIDGED CRACKS

Our theoretical work on bridged cracks began with the adaptation of our model of bridged cracks in fibrous composites under monotonic loading¹ to the case of cyclic loading. The model accounts for bridging tractions and fracture and fatigue properties of brittle matrix composites in which the matrix is coupled to the fibers by friction in terms of their microstructure and interfacial properties. We began by detailing the analogies between experimental observations for bridged cracks in ceramic composites under monotonic loading and bridged cracks in fiber-reinforced metal matrix composites in fatigue.² These experimental observations are the essential reason for choosing a model of the given form. Bridging traction laws for sliding fibers were generalized to deal with the case of cyclic loading² and numerical methods were formulated for calculating the effective cyclic stress intensity factor in the presence of bridging for specimens of various common shapes.³

Exhaustive solutions for bridged cracks under monotonic and cyclic loading were presented, showing the crucial role played by the "bridging length scale" that is introduced by the presence of bridging tractions. The very complex possibilities for the functional dependence of crack growth rates on crack length in notched, finite specimens were displayed and interpreted simply in terms of the bridging length scale.³ Simplified analytical approximations to the results of these calculations were computed (under other funding) to allow easy analysis of experiments with bridged cracks.⁴

The problem of applying our models to fatigue and fracture of brittle materials was explained and an approach to analyzing high temperature bridged crack experiments was presented.⁵

3.0 EXPERIMENTAL RESEARCH

In the first twelve months of our program, our experimental work was a study of crack bridging and plasticity in metal reinforced ceramic composites, especially WC/Co, which are primarily room or moderate temperature materials. In our second year, we established experimental facilities for conducting high temperature tests with the capability of *in situ* microscopy.

High Temperature Test Facility with in situ Microscopy

A computer controlled miniature loading frame (Fig. 1) was developed for studying hot specimens in fully-reversed bending in a scanning electron microscope (SEM). The apparatus provides data at SEM magnification on microscopic deformation and microcrack openings as the applied load is varied. The specimen is heated to temperatures up to 850°C (in the current version) by a resistance heater inserted in the hot side heat source (H). Damage to the X-Y stage of the SEM is prevented by a water cooled heat sink (C), on which the base of the loading frame sits.

In the fully assembled jig, heat shields are placed above and below the specimen to protect the SEM optics and the load cell from thermal damage. These connect through a copper wall (W) to the cold side of the loading frame. They have been removed in Fig. 1 to allow the internal parts of the frame to be seen. A single stainless steel support (S) isolates the heater from the cold frame base and wall. Additional cooling for the load cell (L) is provided by a flexible copper braid which extends from the top of the cell to W. The only direct connection of the specimen to the cold side of the frame is through a 2.0 x 0.1 mm thick stainless steel loading rod (R). Stainless steel is ideal in this application as its heat conductivity is smaller than that of many ceramics and it is easily machined.

Analysis of heat flow and radiation for this system indicates that the temperature of the specimen gauge section will be within 20°C of the heater temperature. The frame is configured in Fig. 1 for viewing the top of the specimen (i.e. parallel to the puller rod). By rotating the drive assembly 90° and remounting the motor, specimens can also be photographed from the side.

SCP-0187-E

Fig. 1 View of the *in situ* high temperature bending loading frame: (C) water cooled heat sink; (D) screw drive train; (G) specimen gauge section; (H) resistance heater assembly; (L) load cell; (M) stepping motor; (R) stainless steel coupling rod; (S) stainless steel heater standoff; (W) vertical copper cooling wall to which heat shields (removed for viewing) are attached.

Samples are fatigued in bending. The load train is driven on a screw by a miniature stepping motor (M), which is coupled to the loading rod through a chain drive and worm gear assembly (D). The specimen tip displaces approximately 0.25 nm per microstep, so that 10^6 such steps are required to reach the typical full stroke. With the current load train, the motor stall velocity limits the cyclic frequency to 2 min^{-1} . The loading rod passes through the heat shield and is coupled to the drive screw through a miniature load cell.

The loading frame is driven under load control by a small computer, which reads the load cell and directs and tracks the motor position. At intervals during fatigue, cycling is suspended briefly while micrographs of the specimen are recorded. These may be of either the specimen surface or its side, depending on the angle of tilt chosen for the SEM stage.

In making this device a reliable research tool, it was important to establish the optimum trade-off between specimen size, puller rod thickness, load measurement accuracy, and heat

transfer to the load cell. Stiffer specimens require larger loads and therefore larger load cell ranges, resulting in greater load cell measurement accuracy. But the pull rod must then also be thicker and more heat can be conducted to the load cell and from the specimen when the specimen is under load. The major problem with heat transfer is not that it is damaging to the cell or that it significantly changes specimen temperature, but rather that it causes false loading drifts as the load cell temperature changes, especially at smaller loads. This difficulty is minimized satisfactorily with a thin puller rod.

The jig is designed primarily for testing small rectangular bar specimens into which shallow notches have been ground to maximize bending stress near the heater. Stresses for various notch dimensions have been examined by finite element analysis to identify a satisfactory geometry. One of the principal virtues of the system is that it uses small specimens (cross-sections as small as 2 mm x 2 mm), which are often the only size available when dealing with new materials.

The loading system will also accept tapered cantilever beams as test specimens. These would be preferable for crack initiation experiments, providing constant stresses over a large specimen area as well as suppressing grip initiated failures.

Experimental results obtained with this apparatus will be presented in our next annual report.

Review of Fatigue in Ceramics and Ceramic Composites

As part of a continuous collaboration, an international conference on "Fatigue of Advanced Materials" was organized under the auspices of the Engineering Foundation by Brian Cox, Reiner Dauskardt, and Rob Ritchie (the last two of Lawrence Berkeley Laboratory and UC Berkeley). The proceedings were published, along with an overview by the organizers of the work presented and other work on fatigue in ceramics.⁶ An extended review paper was then published independently.⁷ We believe that this activity provided a timely analysis of the essential problems and laid out a clear guide to future research.

4.0 COLLABORATIONS AND SUPERVISION OF A STUDENT

Active collaborations have been maintained with Dr. Reiner Dauskardt and Professor Rob Ritchie of Lawrence Berkeley Laboratory and UC Berkeley. Apart from jointly organizing the Engineering Foundation Conference,⁶ we have exchanged several visits. Dr. Dauskardt has

assisted us in developing a high temperature experimental test facility, while we have provided him with guidance on theoretical aspects of fatigue in polycrystalline monolithic ceramics.

We have also continued to collaborate with various researchers at UC Santa Barbara, especially Professor Bob McMeeking. One of Dr. McMeeking's Ph. D. students, Calvin Lo, was supervised primarily by Dr. Cox in research for his thesis, which led to Refs. 3 and 4.

5.0 REFERENCES

1. D. B. Marshall, B. N. Cox, and A. G. Evans, "The Mechanics of Matrix Cracking in Brittle Matrix Fiber Composites," *Acta Metall. Mater.* 33, 2013-21 (1985).
- *2. B. N. Cox and D. B. Marshall, "Crack Bridging in the Fatigue of Fibrous Composites," *Fatigue and Fracture of Engng Mater. and Struct.* 14, 847-61 (1991).
- *3. B. N. Cox and C. S. Lo, "Load Ratio, Notch, and Scale Effects for Bridged Cracks in Fibrous Composites," *Acta Metall. Mater.* 40, 69-80 (1992).
4. B. N. Cox and C. S. Lo, "Simple Approximations for Bridged Cracks in Fibrous Composites," *Acta Metall. Mater.* 40, 1487-96 (1992) .
- *5. B. N. Cox, "Fatigue and Fracture of Brittle Fibrous Composites," invited paper in *Fatigue of Advanced Materials*, ed. R. O. Ritchie, B. N. Cox, and R. Dauskardt, (MCE Publ., Birmingham, England, 1991).
- *6. *Mechanical Fatigue of Advanced Materials*, Proc. Engng Foundation Conference, Santa Barbara, January 1991, ed. R. O. Ritchie, B. N. Cox, and R. H. Dauskardt (MCE Publ., Birmingham, England, 1991).
- *7. R. H. Dauskardt, R. O. Ritchie, and B. N. Cox, "Fatigue of Advanced Materials," *Mechanical Engineering*, in press.

*Publications of work done in the period covered by this report.

6.0 CUMULATIVE LIST OF PUBLICATIONS UNDER THIS CONTRACT

Papers

Published work from the first year of the contract

1. B. N. Cox and D. B. Marshall, "The Determination of Crack Bridging Forces," *Int. J. Fracture* 49, 159-176 (1991).
2. B. N. Cox and D. B. Marshall, "Stable and Unstable Solutions for Bridged Cracks in Various Specimens," *Acta Metall. et Mater.* 39, 579-89 (1991).
3. B. N. Cox, "Extrinsic Factors in the Mechanics of Bridged Cracks," *Acta Metallurgica et Materialia* 39, 1189-1201 (1991).

Published work from the period covered by this report

References 2, 3, 5, and 7 from the list of references.

Edited Book

Reference 6 from the list of references.

7.0 APPENDIX

Reprints or preprints of Refs. 2, 3, 5, and 7. Approximately 90% of the work described in Refs. 2, 3, and 5 was performed under this contract, with most of the work performed under other funding reported in Ref. 2. All of the work of Brian Cox in contributing to Ref. 7 was performed under this contract.

Reprints + Preprints removed

END

**DATE
FILMED**

12 / 4 / 92