JUL 19 1962

15-452

MASTER

Correlation between Heat Capacity Anomaly in Tb
and Magnetic Transition in $Tb_2O_3^*$

B. C. Gerstein, F. J. Jelinek, and F. H. Spedding

Institute for Atomic Research and Departments of Chemistry and Physics
Iowa State University, Ames, Iowa

Measurements on the heat capacity of Tb below 4°K by Kurti and Safrata¹ and Stanton, Jennings, and Spedding² yielded an anomaly which was attributed to an oxide impurity.² Subsequent measurements by Lounasmaa³ on a sample of presumably higher purity than the first two, confirmed this to the extent that no anomaly was found in the region in question. The fact that an oxide impurity can give rise to heat capacity anomalies in the He region was definitely established for the case of Gd by Crane.⁴ In order to confirm the evidence for the anomaly in Tb found by Kurti and Safrata, and Stanton et al. being caused by an oxide phase, the magnetic susceptibility of Tb_2O_3 was measured from 1.3 to 250°K. The lower stable form of the oxide was chosen for this measurement because presumably this is the form that would exist as an oxide phase in the metal.

As shown in Fig. 1, there exists a maximum in the susceptibility, characteristic of antiferromagnetic ordering, at 2.42°K. The transition in the heat capacity of Tb corresponds, to within 0.02°K, to the maximum in the susceptibility. The inverse of the susceptibility is not linear below 250°K, so it would be supposed that the crystal field splitting of the lowest J value for Tb ion in the oxide would be at least of the order of magnitude of 170 cm^{-1} . This is in accord with

*Contribution No. 1148. Work was performed in the Ames Laboratory of the U.S. Atomic Energy Commission.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

crystal field splittings found for other rare-earth oxides by Justice and Westrum.⁵

The susceptibility was measured using an ac bridge technique,⁶ the field at the sample being roughly two oe.

ACKNOWLEDGMENTS

The authors wish to gratefully acknowledge a helpful suggestion by Professor C. A. Swenson.

REFERENCES

- ¹N. Kurti and R. S. Safrata, *Phil. Mag.* 3, 780 (1958).
- ²R. M. Stanton, L. D. Jennings, and F. H. Spedding, *J. Chem. Phys.* 32, 630 (1960).
- ³O. V. Lounasmaa, "The Heat Capacity of Tb from 0.4 to 4°K" (to be published in *Phys. Rev.* circa July, 1962).
- ⁴L. T. Crane, *J. Chem. Phys.* 36, 10 (1962).
- ⁵Private communication from E. F. Westrum, Chemistry Department, University of Michigan, Ann Arbor, Mich.
- ⁶F. R. McKim and W. P. Wolf, *J. Sci. Instr.* 34, 64 (1957).

Fig. 1. Inverse molar susceptibility of Tb_2O_3 .

Caption for Insert: Comparison between C_p of Tb and X_m of Tb_2O_3 in region of anomaly in C_p .