DOE/METC/C-94/7145

Characterization and Fixed-Bed Testing of a Nickel-Based Hot Gas
Desulfurization Sorbent

Authors:

Gasper-Galvin, Lee D. (METC)
Swisher, James H. (Southern Illinois University at Carbondale)
Hammerbeck, Kurt (Oak Ridge Associated Universities)

Conference Title:

Coal Fired Power Systems 94 --
Advances in IGCC and PFBC Review Meeting

Conference Location:

Morgantown, West Virginia

Conference Dates:

June 21-23, 1994

Conference Sponsor:

U.S. Department of Energy, Morgantown Energy Technology Center

MASTER

rb

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

This report has been reproduced directly from the best available copy.

Available to DOE and DOE contractors from the Office of Scientific and Technical Information, 175 Oak Ridge Turnpike, Oak Ridge, TN 37831; prices available at (615) 576-8401.

Available to the public from the National Technical Information Service, U.S. Department of Commerce, 5285 Port Royal Road, Springfield, VA 22161; phone orders accepted at (703) 487-4650.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

Characterization and Fixed-Bed Testing of a Nickel-Based Hot Gas Desulfurization Sorbent

Lee D. Gasper-Galvin
Morgantown Energy Technology Center

James H. Swisher
Southern Illinois University at Carbondale

Kurt Hammerbeck
Oak Ridge Associated Universities

OBJECTIVES

The objective of this project was to (1) extend a preliminary investigation completed earlier on dispersed nickel sorbents¹ by developing new processing methods, characterizing sorbent materials more extensively, and evaluating the materials in fixed bed reactor tests, and (2) to determine the feasibility of using dispersed nickel sorbents with reductive regeneration for hot gas desulfurization.

BACKGROUND

There has been interest and active research on desulfurization of coal-derived gases since they were first produced by coal carbonization more than a century ago. A comprehensive review of the literature on metal and binary oxide sorbents was published by Swisher and Schwerdtfeger². A later paper by the same authors³ reviewed literature on mixed oxide sorbents and discussed the importance of thermodynamics in research on sulfur sorbents.

During the past 10 years, research in this field has focused on desulfurization at high temperatures because of the need for application of the technology to Integrated Gasification Combined Cycle (IGCC) systems. In the

1980's, the sorbent material receiving the most attention was zinc ferrite⁴. While it was very effective in reducing hydrogen sulfide (H_2S) concentrations in the product gas to the low ppmv level, it suffered from zinc loss due to vaporization and poor resistance to decrepitation and attrition.

More recently, zinc titanate sorbents have been shown to have comparable desulfurizing ability to zinc ferrite and to be better in durability⁵⁻¹⁰. There is now more research being done on zinc titanate than any other class of sorbents. However, there are still unanswered questions about its durability and reactivity over many sulfidation/regeneration cycles and its ability to serve applications in which the temperature of the gas to be desulfurized is 750°C or higher. Therefore, continuing research is justified on alternate sorbent materials.

There has been some, but not an extensive amount, of prior work on sorption of sulfur (S) by nickel (Ni) for hot gas desulfurization applications. One of the properties of nickel that is somewhat unique is that it forms a liquid sulfide at sufficiently high temperatures with high sulfur potentials or H_2S levels^{11,12}. A eutectic exists in the Ni-S phase diagram at 637°C and a composition of 33.4 wt % or 21.5 wt % S¹³. Under controlled conditions, the formation of a liquid

phase can be used to advantage in hot gas desulfurization. The approach used by Steiner and Gutterman¹⁴ was to use pellets of Ni and NiO in a fixed-bed reactor. When simulated coal gas was passed through the beds at 740°C, liquid sulfide formed and flowed away from the pellets. Thus, there was no solid sulfide present to serve as a diffusion barrier and curtail the reaction. Their concept included a provision for collecting the sulfide formed and regenerating it in a separate reactor.

Thermodynamic calculations show that the solid Ni-liquid Ni sulfide equilibrium will not reduce H₂S levels in coal gasification product gas to the low ppmv level. Fortunately, however, another mechanism can be used for sorption of S by Ni in the low concentration range. Patel, Rich, and Maru¹⁵ showed that chemisorption of S on Ni occurs readily in the 500 to 700°C temperature range. They evaluated ten commercial catalysts containing dispersed Ni in a fixed-bed reactor, and success was achieved in reducing S species concentrations from 10 ppmv to 20 ppbv. The sulfur capacity varied from 2,000 to 10,000 ppmw or 0.2 to 1.0% by weight, depending on reactor conditions.

Initial work on sorbents containing dispersed Ni in an alumina (Al₂O₃) matrix was carried out by Swisher and Schwerdtfeger¹⁶. Two compositions were studied. One contained 26 wt % Ni in Al₂O₃, and the other contained 24 wt % Ni plus 7 wt % copper (Cu) in Al₂O₃. Copper was added because it is known to decrease the melting temperature and broaden the composition range of the liquid sulfide formed during sulfur sorption. There is a ternary eutectic reaction in the Ni-Cu-S system at 575°C. The eutectic composition in wt % is 69.8% Ni, 5.7% Cu, and 24.5% S^{17,18}. The reactivity of individual pellets was studied in a Cahn thermogravimetric analyzer (TGA). Sulfidation was carried out in a mixture of 1 volume % H₂S in H₂, and regeneration was carried out in H₂.

Results of the TGA experiments showed that the sorbents could be subjected to four sulfidation/regeneration cycles with no loss of reactivity. The temperature range for the experiments was 500° to 1000°C. It was found through visual observation and scanning electron microscopy that the liquid sulfide was retained in the Al₂O₃ structure during these TGA experiments.

PROJECT DESCRIPTION

Sorbent Preparation

The sorbent was prepared for evaluation using traditional powder processing methods. Reagent-grade NiO, CuO, and Al₂O₃ powders (all -325 mesh size) were blended in a 1 wt % solution of starch in water. Excess water was decanted, and the resulting paste was extruded through a metal tube to produce cylindrical pellets 9.3 mm in diameter and 10 to 12 mm long. The extrudates were dried in an oven at 120°C for 24 h. The dried extrudates were then placed in an electrically heated kiln; the temperature of the kiln was ramped up over a period of several hours, with a holding time of 2 h at the final sintering temperature of 1520°C. The extrudates were crushed and sieved to obtain samples in the -6, +16 mesh size range for fixed bed testing. The sorbent designation was 24Ni-7Cu-Al₂O₃, indicating a nominal composition of 24 wt % nickel and 7 wt % copper.

Description of Experimental Unit

The experimental studies were carried out in a bench-scale fixed bed reactor. A simplified schematic of the reactor system is shown in Figure 1. The reactor tube was alonized 316 stainless steel with an inside diameter of 2.21 cm (0.87 in) and a 0.165-cm (0.065-in) wall thickness. The sorbent bed was located in approximately the center of the 114.3-cm (45-in) long reactor tube, and the bed height was 5.08 cm

M94001521W

Figure 1. One-Inch Sorbent Screening Unit

(2 in). Gases were supplied from gas cylinders, and the flow rates were controlled through MKS mass flow controllers. All of the gases except hydrogen sulfide were first mixed together in a manifold prior to being fed into the reactor. Hydrogen sulfide gas was added to the other gases separately just upstream of the reactor inlet. Steam was provided by adding a predetermined amount of water into the preheated gas stream via an Isco model 100DM syringe pump. Both sulfidation and regeneration were conducted in the downflow mode. A heavy metal shield and a hydrogen flame detector with automatic reactive gas shutoff were installed for the protection of the operators from possible flames or explosions due to hydrogen leaks. The reactor temperature was maintained with a single-zone tubular electric furnace. The temperatures of the gases flowing into the bed and

at the core of the bed (3.8 cm [1.5 in] from the bottom of the bed) were measured using type K thermocouples. The maximum allowable temperature of the reactor was 927°C (1700°F), which precluded doing the regeneration at higher and possibly kinetically more favorable temperatures. A preheat coil consisting of a 0.635-cm (0.25-in) outside diameter, 0.089-cm (0.035-in) wall thickness 316 stainless steel tube placed between the reactor and the furnace was used to preheat all inlet components, except for hydrogen sulfide and water, during the first two and a half cycles of sulfidation/regeneration. (A cycle is defined as one complete sulfidation followed by a complete regeneration of the sorbent.) This preheat coil was removed, and gases were heated to the required temperatures while passing through the top portion of the reactor tube during all subsequent experiments.

Experimental Procedure

Before the first sulfidation could be performed, the sorbent was pretreated to reduce the NiO to Ni metal. A 3-hour pretreatment with pure hydrogen was conducted at 871°C (1600°F) at the beginning of each series of cycles. A simulated Shell oxygen-blown entrained gasifier mixture was used as the sulfidation gas, and pure hydrogen was used as the regeneration gas. The Shell gas was chosen because it is the most likely to be applicable to this sorbent; clean fuel gas of this type could potentially be used instead of hydrogen for regeneration. The inlet gas compositions and other reaction conditions for sulfidation and regeneration are given in Table 1. Each sulfidation of the sorbent was stopped when the outlet concentration of H₂S reached 1000 ppmv. The regenerations were stopped when the outlet concentration of H₂S was less than or equal to 200 ppmv. The outlet stream was tested for hydrogen sulfide by the use of Sensidyne gas detector tubes of various ranges and gas grab samples, which were analyzed using gas chromatography.

A first series of six and a half cycles (designated JS1 experiments) were performed on the sorbent; afterward, the sorbent was removed from the reactor and sent for analysis. Blank runs on the empty reactor were conducted before and after the six and a half cycles of JS1 were performed; the blank runs consisted of two complete cycles of sulfidation/regeneration in each case. The reactor tube was replaced, and a second series of cycles were performed. The second series consisted of three and a half cycles (designated JS2 experiments). Two complete cycles of blank runs were conducted on the empty reactor just prior to performing the JS2 experiments.

The main difference between the JS1 and the JS2 series was that a preheat coil was located upstream of the reactor for the first two

and a half cycles of the JS1 series. However, the preheat coil was removed after two and a half cycles and not replaced during the remaining experiments. The reason for removing it was that extensive carbon deposition in it caused a significant increase in pressure drop. It was thought that the carbon deposition occurred because, although the unalloyed preheat coil had been passivated with nitric acid, it catalyzed the reaction in which carbon monoxide disproportionated to form carbon dioxide and carbon solids.

RESULTS

The H₂S breakthrough curves for the JS1 and JS2 series experiments are shown in Figures 2 and 3, respectively. It appears that the sorbent increased in capacity with each successive cycle, as evidenced by the longer times required for breakthrough. (Breakthrough is defined here as the point at which the concentration of H₂S in the outlet gas reaches 200 ppmv.) After the first three cycles of series JS1, and the first two cycles of JS2, the prebreakthrough concentration of H₂S in the outlet gas plateaued between 50 and 100 ppmv, with a gradual drift above these values as the sorbent approached breakthrough.

Since pure hydrogen was used as the regeneration gas, H₂S was released during regeneration. The regeneration curves showing H₂S outlet concentration as a function of time on-stream are shown in Figures 4 and 5 for the JS1 and JS2 series experiments, respectively. Note that the time required for regeneration increased during the first three cycles and then tended to stabilize. Regeneration took significantly more time than the corresponding sulfidation of the same cycle. Typically, the duration of each regeneration was more than six times that of the previous sulfidation.

Table 1. Reaction Conditions

Regeneration	Sulfidation
871°C (1600°F)	704°C (1300°F)
205 kPa (15 psig)	205 kPa (15 psig)
320 cc/min or 1000 l/hr	639 cc/min or 2000 l/hr
Regeneration Gas	Gas Mixture (Volume %)
Hydrogen 100.0%	Carbon Monoxide 64.1
End at 200 ppmv H ₂ S in Outlet	Hydrogen Sulfide 0.3
	Nitrogen 4.3
	Hydrogen 27.3
	Water 2.0
	Carbon Dioxide 2.0
	End at 1000 ppmv H ₂ S in Outlet

M94002377W

Figure 2. JS1 Sulfidation of 24Ni - 7Cu - Al₂O₃ at 704°C (1300°F)

Figure 3. JS2 Sulfidation of 24Ni - 7Cu - Al₂O₃ at 704°C (1300°F)

Fig. 4 JS1 Regeneration of 24Ni - 7Cu - Al₂O₃ at 871°C (1600°F)

Figure 4. JS1 Regeneration of 24Ni - 7Cu - Al₂O₃ at 871°C (1600°F)

Figure 5. JS2 Regeneration of 24Ni - 7Cu - Al₂O₃ at 871°C (1600°F)

Figure 6 shows the H₂S breakthrough curves for the blank runs (empty reactor tests), which were conducted before and after the JS1 experiments and on the new reactor before the JS2 experiments. Breakthrough time on the empty reactor was significantly longer for runs conducted at the end of the test than those conducted at the beginning. However, the blank runs conducted at the end of the JS1 series had a much shorter breakthrough time than the 7th sulfidation, which was performed just prior to these, indicating that the sorbent had indeed increased remarkably in capacity.

Both the H₂S breakthrough curves and the regeneration curves shown in Figures 2 through 6 were determined using Sensidyne detector tubes. Gas chromatographic analysis of the reactor outlet gas, collected downstream from the condenser units during sulfidations,

showed the dry basis volume concentrations of all the major gaseous components, in addition to H₂S, SO₂, and COS. Small amounts of methane (CH₄) were formed, resulting in a concentration that was always less than 0.8%. The SO₂ concentration usually stayed below 5 ppmv, with a few excursions to higher values during some of the sulfidations, after several hours on-stream. The concentrations of CO, CO₂, and H₂ indicated that little, if any, water-gas shift occurred. The COS concentration usually remained below 100 ppmv, and tended to increase during each experiment, as H₂S increased toward breakthrough.

The chemical compositions of the fresh sorbent and the sorbent reacted for six and a half cycles (JS1 series) are shown in Table 2. The atomic absorption analysis was run twice on both the fresh and spent sorbents to recheck the

Figure 6. Blank Runs of 24Ni - 7Cu - Al₂O₃ at 704°C (1300°F)

Table 2. Chemical Compositions of Fresh and Reacted Sorbent

Element	Fresh (wt %)	Reacted (wt %)
Aluminum	28.10	28.60
Nickel	23.60	15.80
Copper	3.75	3.90
Total Sulfur	0.08	6.63

Ni content, resulting in exactly the same results for each. The analysis of Ni in the fresh sorbent also agreed quite well with the amount of Ni that was put into the sorbent during preparation (i.e., 24.0 wt % Ni was added during preparation, and the analysis showed 23.6 wt % Ni).

Calculations from the atomic absorption analysis of Al, Ni, and Cu were made assuming that the total amount of Al in the sorbent remained constant during the six and a half cycles. The calculations showed a 32% loss of Ni after the six and a half cycles; however,

there was no loss of Cu. The sulfided sorbent contained 6.63 wt % sulfur. If it is assumed that each three Ni atoms can react with two S atoms to form Ni₃S₂ (although there are many different stoichiometric forms of Ni_xS_y possible¹), and two Cu atoms react with one S atom to form Cu₂S, then the theoretical capacity of the sorbent is 9.54 g S/100 g fresh sorbent. Assuming the Al content of the sorbent to be constant, the actual sulfur content of the sorbent was 6.75 g S/100 g fresh sorbent, or 70.7% of theoretical capacity.

It should be noted that there is some question as to how the breakthrough time increased with each cycle, while there was simultaneously a loss of Ni from the sorbent. For example, fairly extensive redistribution of the remaining Ni would have to take place during hydrogen regeneration to compensate for this apparent volatilization loss of Ni.

Table 3 shows the physical characteristics of the fresh sorbent and the sorbent reacted for six and a half cycles (JS1 series). The mercury skeletal density, particle density, and cumulative pore volume remained essentially constant. However, the nitrogen pore volume increased seven-fold, and the BET nitrogen surface area increased 33-fold. The average pore diameter decreased to 28 percent of its original value. Porosity increased very little, if at all.

Electron micrographs of cross sections of the fresh and JS1 reacted sorbents are shown in Figure 7(a) and Figure 7(b), respectively. The sorbent appeared to be more uniform and more dispersed after reaction for six and a half cycles.

There was a concern about the possibility that some hydrogen embrittlement of the stainless steel reactor may have occurred, particularly during regeneration. Hydrogen embrittlement occurs when H_2 diffuses into the metal lattice and reacts with C in the metal to form CH_4 . Cracks are formed as the CH_4 escapes. To determine whether this may have occurred, the reactor used during the JS1 series experiments was cut open length-wise, and electron micrographs were taken of the inner reactor wall. Microcracks and pitting were indeed observed on this inner surface of the reactor wall.

DISCUSSION

The 24Ni-7Cu- Al_2O_3 sorbent was unusual, compared to zinc-based and other sorbents, in that it increased in capacity with each successive cycle. The breakthrough curve performance of most sorbents tend to either stabilize after about three cycles, or gradually deteriorate with successive cycles. The physical characteristics of the fresh and reacted sorbent indicate that there was a large increase in surface area and in the number of small pores. This may have occurred through redistribution of the Ni and Cu to finer dispersions during each hydrogen regeneration.

The blank runs conducted on the empty reactor before and after the JS1 series experiments showed that there was increased sulfur sorption by the apparatus. Two possible explanations follow. Since there was an apparent large loss of Ni through volatilization from the sorbent, Ni may have been deposited on the walls of the reactor or downstream tubing, where it might have reacted with H_2S , resulting in a longer breakthrough time for the empty reactor. Electron micrographs suggested that hydrogen embrittlement of the reactor walls may also have occurred, resulting in microcracks which could penetrate the alonized surface, creating additional surface area for S sorption. However, it should be noted that the increase in breakthrough time on the empty reactor was small compared to the increase in breakthrough time between the first and seventh sulfidations. Therefore, the largest part of the increase in apparent sorbent capacity was due to changes in the sorbent itself. Corrective actions for the problem of hydrogen embrittlement could include the use of a reactor made of ceramic material, quartz, or an alloy with a very low C content.

Table 3. Physical Characteristics of Fresh and Reacted Sorbent

Item	Fresh	Reacted
N ₂ Pore Volume (cc/g)	0.006354	0.04684
Hg Skeletal Density (g/ml)	4.16	4.20
Hg Bulk Density (g/ml)	2.38	2.37
Cum. Hg Pore Vol. (ml/g)	0.18	0.19
Surface Area (m ² /g)	0.0963	3.21
Avg. Pore Diameter (μm)	0.5858	0.1622
Porosity (%)	42.79	43.76

7a. Fresh

7b. After Six and a Half Cycles

**Figure 7. 24 Ni - 7Cu - Al₂O₃ Sorbent
Magnified 3,000 Times**

The prebreakthrough concentration of H_2S in the outlet gas was higher than expected. Patel, Rich, and Maru¹⁵ had observed a reduction in S species concentration from 10 ppmv to 20 ppbv; in that case, a typical commercial Ni catalyst, 20 wt % Ni on Al_2O_3 , was used for H_2S removal from a simulated coal gas. However, in the present study, the higher levels of inlet H_2S concentration apparently caused the reactive surface sites to become rapidly occupied by sulfur, after which bulk sulfidation took place.

Sulfides that form in commonly studied sorbents, such as zinc ferrite and zinc titanate, are solids at their hot gas desulfurization reaction temperatures. However, nickel sulfide became a liquid at the reaction conditions studied here. Since liquids tend to have higher vapor pressures than solids, it might be expected that the liquid nickel sulfide could give rise to vapors which could then be swept away by the simulated coal gas.

Long regeneration times were required by the sorbent (usually at least six times as long as the respective sulfidation breakthrough time, and as much as 22 times longer). If it is assumed that the species to be regenerated were Ni_3S_2 and Cu_2S , 70.7% of theoretical capacity of the sorbent had been reached (9.54 g sulfur/100 g fresh sorbent), and the shortest regeneration time observed is considered (i.e., from the first cycle of the JS1 series), then 310 gmoles of H_2 were required to remove each gmole of S from the sorbent. This makes the sorbent impractical for commercial use in a fixed-bed mode under these conditions, since at least as many reactors as the greatest number of times the length of regeneration was greater than its respective sulfidation would be required. Also, large volumes of reducing gas would be required for regeneration.

However, it should be noted that Jhunjunwala¹ showed in TGA experiments that when sulfidation was carried out at 700°C and regeneration at 950°C on the same type of sorbent, the regeneration time was slightly less than the time required for sulfidation. Unfortunately, the fixed-bed unit used in the present studies could not be operated at temperatures greater than 871°C.

FUTURE WORK

Since the presence of copper tends to reduce the temperature at which liquid nickel sulfides form, a Ni/Al_2O_3 without copper will be studied. Also, a lower reaction temperature will be used (593°C [1100°F] instead of 704°C [1300°F]); hopefully, this will help avoid nickel loss through volatilization. Since the time required for hydrogen regeneration was unacceptably long, oxidative regeneration will be attempted and directly compared with hydrogen regeneration.

ACKNOWLEDGMENTS

The authors would like to gratefully acknowledge the work performed by the METC operators of the bench-scale, fixed-bed reactor, which was used for these studies. Many 12-hour shifts were conducted by Lanny Golden, Todd Gardner, Ed Fisher, Grover Evans, Gary McDaniel, and Karl Warnick to make collection of this data possible.

This research was supported in part by an appointment to the U.S. Department of Energy Fossil Energy Postgraduate Research Training Program, administered by the Oak Ridge Institute for Science and Education.

REFERENCES

1. Jhunjhunwala, M., "Evaluation of Dispersed Nickel Sorbents for Hot Gas Desulfurization," Masters Thesis, Department of Mechanical Engineering and Energy Processes, Southern Illinois University at Carbondale, July, 1993.
2. Swisher, J. H., and Schwerdtfeger, K., "Review of Metals and Binary Oxides as Sorbents for Removing Sulfur from Coal-Derived Gases," *J. Mat. Eng. and Perf.*, 1(3), 1992, 399-407.
3. Swisher, J. H., and Schwerdtfeger, K., "Thermodynamic Analysis of Sorption Reactions for the Removal of Sulfur from Hot Gases," *J. Mat. Eng. and Perf.*, 1(4), 1992, 565-571.
4. Grindley, T. and Steinfeld, G., "Development and Testing of Regenerable Hot Coal-Gas Desulfurization Sorbent," Report No. DOE/METC-16545-1125, Morgantown Energy Technology Center, Morgantown, WV, 1981.
5. Mei, J. S., Gasper-Galvin, L. D., Everitt, C. E., and Katta, S., "Fixed-Bed Testing of a Molybdenum-Promoted Zinc Titanate Sorbent for Hot Gas Desulfurization," *Proceedings of the Coal-Fired Power Systems 93--Advances in IGCC and PFBC Review Mtg.*, D. L. Bonk, ed., DOE/METC-93/6131, Springfield, Va.: National Technical Information Service, 1993, 315-325.
6. Ayala, R. E., Gal, E., and Gupta, R. P., "Testing of Zinc Titanate Desulfurization Sorbents for Moving Bed Applications," *Ibid.*, 136-145.
7. Gangwal, S. K., and Gupta, R. P., "Enhanced Durability of Desulfurization Sorbents for Fluidized-Bed Application," *Ibid.*, 146-157.
8. Swisher, J. H., "An Attrition-Resistant Zinc Titanate Sorbent for Sulfur," Final Technical Report submitted to the Illinois Clean Coal Institute, Carterville, Illinois, Sept. 1993.
9. Swisher, J. H., O'Brien, W. S., and Gupta, R. P., "An Attrition-Resistant Zinc Titanate Sorbent for Sulfur," Quarterly Technical Reports submitted to the Illinois Clean Coal Institute, Carterville, IL, Dec. 1993 and Mar. 1994.
10. Gupta, R. P., Gangwal, S. K., and Jain, S. C., "Fluidizable Zinc Titanate Materials with High Chemical Reactivity and Attrition Resistance," U. S. Patent No. 5,254,516, Awarded to Research Triangle Institute, Research Triangle Park, NC, 1993.
11. Nagamori, M., and Ingram, T. R., "Thermodynamic Properties of Ni-S Melts Between 700° and 1100°C," *Met. Trans.*, 1, 1970, pp. 1821-1825.
12. Rosenquist, T., "A Thermodynamic Study of the Iron, Cobalt, and Nickel Sulphides," *J. Iron and Steel Inst.*, 175, 1954, 37-57.
13. Elliott, R. P., *Constitution of Binary Alloys, First Supplement*, McGraw-Hill, New York, 1965, 669.
14. Steiner, P. and Gutterman, C., "Nickel Sulfide Method for Separating Hydrogen Sulfide," Foster Wheeler Energy Corp., Clinton, NJ, German Patent No. DE 29 03 377 A1, 1979 (in German).

15. Patel, P. S., Rich, S. M., and Maru, H. C., "Trace Contaminant Removal from Hot Coal Gas for Molten Carbonate Fuel Cell Applications," *Proceedings of the Fifth Annual Contractors Meeting on Contaminant Control in Coal-Derived Gas Streams*, D. C. Cicero and K. E. Markel, eds., DOE/METC-85/6025, Springfield, Va.: National Technical Information Service, 1986, 419-424.
16. Swisher, J. H., and Schwerdtfeger, K., "The Behavior of Sulfur Sorbents Containing Dispersed Nickel," *Proc. 9th Annual Int. Pittsburgh Coal Conf.*, 1991, 646-653, Available from Conference Services, P.O. Box 270, Greensburg, Pennsylvania 15601.
17. Boldt, J. R., *The Winning of Nickel*, Methuen and Co., Ltd., London, UK, 1967, 275-280.
18. Sproule, K., Harcourt, G. A., and Renzoni, L. S., "Treatment of Nickel-Copper Matte," in *Extractive Metallurgy of Copper, Nickel, and Cobalt*, P. Queneau, ed., Interscience Publ., New York, New York, 1961, 33-52.