COMPATIBILITY OF REFRIGERANTS AND LUBRICANTS WITH ELASTOMERS

Quarterly Report

1 April 1992 - 30 June 1992

Dr. Gary R. Hamed
Robert H. Seiple

Institute/Department of Polymer Science
Polymer Science Building
University of Akron
Akron, Ohio 44325-3909

July 1992

Prepared for
The Air-Conditioning and Refrigeration Technology Institute
Under
ARTI MCLR Project Number 650-50500

This research project is supported, in whole or in part, by U.S. Department of Energy grant number DE-FG02-91CE23810: Materials Compatibility and Lubricants Research (MCLR) on CFC-Refrigerant Substitutes. Federal funding supporting this project constitutes 93.94 % of allowable costs. Funding from non-government sources supporting this project consists of direct cost sharing of 6.06 % of allowable costs; and in-kind contributions from the air-conditioning and refrigeration industry.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

The U.S. Department of Energy's and the air-conditioning industry's support for the Materials Compatibility and Lubricants Research (MCLR) program does not constitute an endorsement by the U.S. Department of Energy, nor by the air-conditioning and refrigeration industry, of the views expressed herein.

NOTICE

This report was prepared on account of work sponsored by the United States Government. Neither the United States Government, nor the Department of Energy, nor the Air-Conditioning and Refrigeration Technology Institute, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, expressed or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product or process disclosed or represents that its use would not infringe privately-owned rights.

COPYRIGHT NOTICE

(for journal publication submissions)

By acceptance of this article, the publisher and/or recipient acknowledges the right of the U.S. Government and the Air-Conditioning and Refrigeration Technology Institute, Inc. (ARTI) to retain a nonexclusive, royalty-free license in and to any copyrights covering this paper.

TABLE OF CONTENTS

DE93 000539

ABSTRACT		
SCOPE		2
SIGNIFICANT RESULTS		3
DISCUSSION		3-5
Figure 1a	Elastomer Diameter Change in R-123	6-7
Figure 1b	Elastomer Diameter Change in R-142b	8-9
Figure 1c	Elastomer Diameter Change in R-124	10-11
Figure 1d	Elastomer Diameter Change in R-22	12-13
Figure 2a	Elastomer Diameter Change in R-125	14-15
Figure 2b	Elastomer Diameter Change in R-134a	16-17
Figure 2c	Elastomer Diameter Change in R-143a	18-19
Figure 2d	Elastomer Diameter Change in R-152a	20-21
Figure 2e	Elastomer Diameter Change in R-32	22
Figure 3a	Elastomer Diameter Change in Alkyl Benzene	23-24
Figure 3b	Elastomer Diameter Change in Mineral Oil	25-26
Figure 3c	Elastomer Diameter Change in Pentaerythritol Ester Mixed Acid	27-28
Figure 3d	Elastomer Diameter Change in Pentaerythritol Ester Brached Acid	29-30
Figure 3e	Elastomer Diameter Change in Polypropylene Glycol Diol	31-32
Figure 3f	Elastomer Diameter Change in Polypropylene Glycol Butyl Monoether	33-34
Figure 3g	Elastomer Diameter Change in Modified Polyglycol	35-36
APPENDIX A	ELASTOMER SWELL DATA	37-97
APPENDIX B	GAS CHROMATOGRAPHY DATA ON REFRIGERANTS	98-108
APPENDIX C	FTIR DATA ON REFRIGERANTS & LUBRICANTS	109-125
APPENDIX D	TGA ANALYSIS OF ELASTOMERS	126-186
APPENDIX E	ODR CURVES-ELASTOMERS	187-236

→ This data is available as a
separate supplement.

COMPATIBILITY OF REFRIGERANTS AND LUBRICANTS WITH ELASTOMERS

ABSTRACT

The information contained in this report is designed to assist the air-conditioning and refrigeration industry in the selection of suitable elastomeric gasket and seal materials that will prove useful in various refrigerant and refrigeration lubricant environments. Swell measurements have been made on approximately 50 % of the proposed elastomers (94 total) in both the lubricant (7 total) and refrigerant (10 total) materials. Swell behavior in these fluids have been determined using weight and in situ diameter measurements for the refrigerants and weight, diameter and thickness measurements for the lubricants. Weight and diameter measurements are repeated after 2 hours and 24 hours for samples removed from the refrigerant test fluids and 24 hours after removal from the lubricants.

SCOPE

The Compatibility of Refrigerants and Lubricants with elastomers program is an 11 month research effort supported by a grant from the Department of Energy through the Air-Conditioning and Refrigeration Technology Institute. The elastomers research effort was initiated at the University of Akron on March 1, 1992 and is expected to continue through January 31, 1991.

First quarter (Jan 1, 1992-Mar 31, 1992) efforts centered around ordering materials, mixing some of the 84 compounds needed for the study and the fabrication of 120 pressure vessels required for the in situ evaluation of the swell behavior of elastomers in refrigerants. The moisture content was determined for the lubricant samples.

Second quarter (April 1, 1992-Jun 30, 1992) efforts revolved around the implementation of proposed methodologies for the acquisition of elastomer swell data in refrigerants and lubricants. During the second quarter, swell tests were begun and the appropriate measurements were made on approximately 50 % of the proposed elastomer formulations.

SIGNIFICANT RESULTS

Swelling measurements have been carried out for different rubber compositions immersed for 14 days at ambient temperature in a variety of hydrochlorofluorocarbon (HCFCs, R-123, R-142b, R-124, R-22) or hydrofluorocarbon (HFCs, R-125, R-134a, R-143a, R-152a, R-32) refrigerants, or in various lubricants: alkyl benzene (AB), mineral oil (MO), pentaerythritol ester mixed acid (PEMA), pentaerythritol ester branched acid (PEBA), polypropylene glycol diol (PPGD), polypropylene glycol butyl monoether (PPGBM), or a modified polyglycol(MPG). Appropriately cured elastomers, encompassing both general purpose and specialty rubbers were tested. Gum and black-filled compounds were tested, as were some thermoplastic elastomers (TPEs).

Results are given in Figures 1-3: Figures 1a - 1d for the HCFCs, Figures 2a - 2c for the HFCs, and Figures 3a - 3g for the lubricants. Solid bars (with brief composition descriptors) are used to show the *in situ* percent change in diameter after immersion. A blank indicates that the composition has not yet been tested. In all cases, compositions containing carbon black had reduced swelling compared to the unfilled counterpart.

Among the HCFCs, the dichloro-substituted R-123 generally had the highest swelling power, although an EPDM/PP TPE with 87 Shore A (#45), a butyl rubber/PP TPE (#85), and a fiber-filled Neoprene (#88) all were quite resistant to swelling by R-123. Moderately resistant to R-123 were the thermoset EPDM compositions (#83, #80, #74). Some compositions (e.g. #46, #47, #48) shrunk during swelling, indicating that the swellant was removing a component (probably plasticizer) from the elastomer. Two of the monochlorinated HCFCs (R-124, R-22) had similar swelling behavior, while the third

(R-142b) gave some noteworthy differences. Epichlorohydrin and nitrile elastomers were significantly more resistant to R-142b than they were to R-124 or R-22. It can be readily seen in Figures 1b - 1d that several of the elastomeric compositions exhibit less than 5% diameter gain after equilibrium immersion in the monochloro-HCFCs.

All the HFCs (Figures 2a - 2e) have substantially less swelling power than the HCFCs. Progressing from Figure 2a to Figure 2e, the swellants have a decreasing ratio of fluorine to carbon (F:C) as show below:

<u>Figure</u>	<u>Refrigerant</u>	<u>F:C</u>
2a	R-125	5:2
2b	R-134a	4:2
2c	R-143a	3:2
2d	R-152a	2:2
2e	R-32	2:1

The fluoroelastomers and fluorosilicone elastomers exhibit the greatest swelling in the HFCs. This is expected in view of the similar structure (and solubility parameter) of these swellants and elastomers. R-143a is the refrigerant which gave the least swelling overall. This is the only refrigerant which does not contain at least one proton bonded to a carbon atom which also has fluorine substitution. Since fluorine is highly electronegative (electron withdrawing), protons of the above type will be acidic. Hence, R-143a is the least acidic of the refrigerants. Because acrylonitrile (ACN) contains a basic nitrogen atom, nitrile rubber is a basic elastomer which exhibits increased swelling as swellant acidity increases. Note among the HFCs that R-143a swells the nitrile rubbers the least.

A great variety of elastomers are resistant to swelling by the HFCs, including both the least inexpensive general purpose hydrocarbon elastomers as well as several of the specialty and thermoplastic elastomers.

Lubricant swelling behavior was substantially different from that of the refrigerants. The completely hydrocarbon lubricants, AB and MO, readily swelled the general purpose hydrocarbon elastomers, while the nitrile rubbers with high ACN content, the fluoroelastomers and the nitrile/PP TPEs were very resistant to these swellants. The other (oxygen-containing) lubricants had little tendency to swell many of the hydrocarbon elastomers, which exhibit less swelling than Neoprene or nitrile rubber of low and medium ACN content. The two pentaerythritol ester lubricants (PEMA and PEBA) gave quite similar swelling behavior; also, the three glycol types (PPGD, PPGBM, MPG) behaved somewhat similarly.

Some elastomers were resistant to swelling by all the lubricants. These include the fluoroelastomers, the high ACN nitriles and the nitrile/PP TPEs. The lubricant with the least swelling power overall was the MPG; the PPGD also was a poor swellant for most compositions.

FIGURE 1a

In Situ Diameter Change
14 Days In R-123
(1,1-Dichloro-2,2,2-Trifluoroethane)

FIGURE 1a

7

In Situ Diameter Change 14 Days In R-123

(1,1-Dichloro-2,2,2-Trifluoroethane)

FIGURE 1b

In Situ Diameter Change
14 Days In R-142b
(1-Chloro -1,1-Difluoroethane)

FIGURE 1b

9

In Situ Diameter Change
14 Days In R-142b
(1-Chloro-1,1-Difluoroethane)

In Situ Diameter Change
14 Days In R-124
(1-Chloro -1,2,2,2-Tetrafluoroethane)

FIGURE 1c

11

In Situ Diameter Change 14 Days In R-124

(1-Chloro-1,2,2,2-Tetrafluoroethane)

In Situ Diameter Change
14 Days In R-22
(Chlorodifluoromethane))

In Situ Diameter Change
14 Days In R-22
(Chlorodifluoromethane)

In Situ Diameter Change
14 Days In R-125
(Pentafluoroethane)

FIGURE 2a

In Situ Diameter Change
14 Days In R-125
(Pentafluoroethane)

In Situ Diameter Change
14 Days In R-134a
(1,1,1,2-Tetrafluoroethane)

In Situ Diameter Change
14 Days In R-134a
(1,1,1,2-Tetrafluoroethane)

In Situ Diameter Change
14 Days In R-143a
(1,1,1 Trifluoroethane)

In Situ Diameter Change
14 Days In R-143a
(1,1,1 Trifluoroethane)

In Situ Diameter Change
14 Days In R-152a
(1,1 Difluoroethane)

In Situ Diameter Change
14 Days In R-152a
(1,1 Difluoroethane)

In Situ Diameter Change 3 Days In R-32 (Difluoromethane)

Diameter Change 14 Days In Lubricant (Alkyl Benzene)

Diameter Change
14 Days In Lubricant
(Alkyl Benzene)

FIGURE 3b

25

Diameter Change 14 Days In Lubricant (Mineral Oil)

Diameter Change
14 Days In Lubricant
(Mineral Oil)

Diameter Change
14 Days In Lubricant
(pentaerythritol ester mixed acid)

Diameter Change 14 Days In Lubricant (pentaerythritol ester mixed acid)

Diameter Change 14 Days Lubricant

(pentaerythritol ester branched acid)

Diameter Change 14 Days In Lubricant (pentaerythritol ester branched acid)

Diameter Change 14 Days In Lubricant (polypropylene glycol diol)

Diameter Change 14 Days In Lubricant (polypropylene glycol diol)

Diameter Change 14 Days In Lubricant (polypropylene glycol butyl monoether)

Diameter Change 14 Days In Lubricant (polypropylene glycol butyl monoether)

Diameter Change 14 Days In Lubricant (modified polyglycol)

Diameter Change 14 Days In Lubricant (modified polyglycol)

COMPLIANCE WITH AGREEMENT

The University of Akron has complied with all aspects of the agreement.

PRINCIPAL INVESTIGATOR EFFORT

Dr. Gary Hamed and R.H. Seiple are the principal investigators for the UA/ARTI MCLR program. During the second quarter of the contract period, Dr. Gary Hamed has devoted a total of 25 hours (5 % of his available work hours) and R. Seiple has devoted 250 hours (50 % of his available work hours) on the UA/ARTI MCLR program.

APPENDIX A
ELASTOMER SWELL DATA

Formula # 1	Ingredient	pphr
	Polyisoprene	100
	Zinc Oxide	5
	Stearic Acid	2
	Sulfur	2.25
	N-t-butyl-2-benzothiazyl sulfenamide	.7

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	10.3	10.4	10.2	45.3/42.4 43.9
R-32	2.8	2.7		
R-124	5.6	5.6	5.8	30.2/29.8 30.0
R-134a	1.4		1.2	4.9/4.8 4.9
R-125	4.6	4.2	4.2	14.9/14.3 14.6
R-143a	2.2	1.7	1.9	5.4/4.9 5.2
R-152a	4.1	4.2	4.2	12.3/13.1 12.7
R-123	48.1	47.5	48.0	328/327 328
R-142b	10.3	10.0	10.2	40.1/38.7 39.4
R-134				
AB	41.8		57.3/55.7 56.5	264/261 263
MO	43.1		53.1/53.2 53.2	248/247 247
PEMA	16.1		29.2/28.0 28.6	117/113 115
PEBA	12.6		26.5/25.7 26.1	106/104 105
PPGD	1.0		2.1/2.2 2.2	7.9/7.7 7.8
PPGBM	4.3		8.1/8.0 8.1	28.1/27.8 28.0
MPG				

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 2

Ingredient	pphr
Polyisoprene	100
Zinc Oxide	5
Stearic Acid	2
Sulfur	2.25
N-t-butyl-2-benzothiazyl sulfenamide	.7
N330 Carbon Black	35

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	9.3	9.3	9.0	33.3/30.8 32.1
R-32	1.7	1.6		
R-124	5.5	5.8	5.6	22.4/22.5 22.5
R-134a	1.1		1.0	3.7/3.8 3.8
R-125	2.9	2.8	3.1	9.5/8.7 9.1
R-143a	2.0	2.5	2.2	3.8/3.4 3.6
R-152a	2.2	2.3	2.5	8.1/8.3 8.2
R-123	36.0	36.0	37.6	220/221 221
R-142b	7.8	7.8	7.8	31.2/29.8 30.5
R-134				
AB	29.5		46.2/45.9 46.1	186/182 184
MO	31.0		41.1/40.3 40.7	166/165 165
PEMA	11.5		21.8/21.6 21.7	77.6/77.6 77.6
PEBA	9.8		18.4/17.9 18.2	65.9/62.9 64.4
PPGD	1.6		2.3/2.1 2.2	6.6/6.5 6.6
PPGBM	3.4		7.0/6.2 6.6	21.0/20.6 20.8
MPG				

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 3

Ingredient

pphr

Polyisoprene	100
Zinc Oxide	5
Stearic Acid	2
N-oxydiethylene-2-benzothiazyl-sulfenamide	1
Tetramethylthiuram disulfide	1
Di-morpholino disulfide	1

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	9.6	10.1	8.9	44.4/42.5 43.5
R-32	1.3	0.8		
R-124	6.5	6.5	6.1	28.2/28.3 28.3
R-134a	1.0		1.2	3.8/3.4 3.6
R-125	3.3	2.9	2.7	10.3/10.1 10.2
R-143a	2.0	2.5	2.7	4.6/4.1 4.4
R-152a	3.1	2.8	3.1	8.3/9.5 8.9
R-123				
R-142b	9.2	9.1	9.5	40.1/39.1 39.6
R-134				
AB	47.0		56.2/55.6 55.9	257/257 257
MO	49.5		56.7/57.0 56.9	271/272 271
PEMA	18.8		22.0/21.9 22.0	83.1/83.2 83.2
PEBA	14.7		20.3/20.2 20.3	75.8/76.4 76.1
PPGD	0.6		0.7/0.6 0.7	1.4/1.7 1.6
PPGBM	4.5		5.7/5.9 5.8	17.7/18.1 17.9
MPG				

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 4

Ingredient

pphr

Poly(chlorobutadiene)	100
Zinc Oxide	5
Stearic Acid	0.5
Magnesium Oxide	4

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	6.3	6.1	6.1	22.2/21.6 21.9
R-32	1.1	1.1		
R-124	1.9	2.7	2.8	10.3/10.1 10.2
R-134a	1.1		1.2	3.4/3.4 3.4
R-125	1.4	2.4	2.7	5.5/5.0 5.3
R-143a	1.1	1.3	1.2	3.3/3.6 3.5
R-152a	2.9	3.1	3.0	7.6/7.5 7.6
R-123	16.0	15.6	15.3	65.0/65.2 65.1
R-142b	6.6	6.6	6.5	18.4/18.6 18.5
R-134				
AB	10.0		19.6/20.1 19.9	51.1/53.2 52.2
MO	12.9		26.5/26.0 26.3	74.7/71.9 73.3
PEMA	25.7		53.7/53.3 53.5	202/211 206
PEBA	11.4		35.4/26.0 30.7	128/77 103
PPGD	3.7		7.3/7.9 7.6	19.9/18.7 19.3
PPGBM	4.8		12.3/11.4 11.9	29.7/31.1 30.4
MPG				

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 5

Ingredient	pphr
Poly(chlorobutadiene)	100
Zinc Oxide	5
Stearic Acid	0.5
Magnesium Oxide	4
N330 Carbon Black	30

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	4.8	4.9	4.9	17.2/16.8 17.0
R-32	1.3	1.57		
R-124	1.1	2.8	1.6	7.6/7.7 7.7
R-134a	0.6		1.0	2.7/2.6 2.7
R-125	0.5	1.8	2.1	4.6/4.6 4.6
R-143a	0.4	0.9	0.8	2.5/2.1 2.3
R-152a	2.5	2.9	2.9	5.6/5.9 5.8
R-123	11.9	11.8	11.4	48.9/49.5 49.2
R-142b	4.6	5.1	4.8	14.4/14.5 14.5
R-134				
AB	7.6		16.1/15.3 15.7	23.5/38.5 31.0
MO	7.9		18.9/18.2 18.6	49.0/48.4 48.7
PEMA	12.5		30.5/28.7 29.6	93.0/91.8 92.4
PEBA	7.3		22.1/22.1 22.1	65.9/63.6 64.9
PPGD	2.5		5.0/4.8 4.9	13.2/13.9 13.6
PPGBM	3.2		9.2/9.5 9.4	23.0/23.0 23.0
MPG				

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 6

Ingredient	pphr
Isobutyl isoprene (0.7% unsaturated)	100
Zinc Oxide	3
Stearic Acid	1
Sulfur	1.66
Tetramethyl thiuram disulfide	1

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	4.5	4.5	3.9	21.8/22.4 22.1
R-32	0.5	0.7		
R-124	1.0	1.5	3.2	16.3/16.4 16.4
R-134a	0.3		0.6	3.0/2.7 2.9
R-125	1.6	2.4	2.6	8.2/7.2 7.7
R-143a	0.7	0.6	1.3	4.1/3.5 3.8
R-152a	0.6	1.0	1.7	7.6/6.4 7.0
R-123	16.8	16.8	16.3	90.2/90.2 90.2
R-142b	4.7	6.1	6.2	25.5/25.8 25.7
R-134				
AB	23.4		67.5/67.7 67.6	341/338 339
MO	27.7		72.1/65.7 68.9	386/335 361
PEMA	1.6		3.1/2.8 3.0	10.1/9.9 10.0
PEBA	0.9		2.0/2.4 2.2	6.9/7.5 7.2
PPGD	-0.1		0.4/-0.3 0.1	-0.1/-0.1 -0.1
PPGBM	0.0		0.2/0.2 0.2	-0.4/0.4 0.0
MPG				

PEMA - Pentacrythritol Ester Mixed Acid
 PEBA - Pentacrythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 7

Ingredient	pphr
Isobutyl isoprene (2.2% unsaturated)	100
Zinc Oxide	3
Stearic Acid	1
Sulfur	1.75
Tetramethyl thiuram disulfide	1

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	5.6	5.2	5.2	22.5/22.5 22.5
R-32	0.4	0.6		
R-124	1.3	1.4	3.5	17.1/16.7 16.9
R-134a	0.2		0.6	2.7/2.8 2.8
R-125	2.1	2.6	3.0	8.9/7.9 8.4
R-143a	0.5	0.7	1.4	4.2/4.3 4.3
R-152a	1.1	1.4	1.9	10.1/7.9 9.0
R-123	16.6	16.5	16.3	90.1/89.9 90.0
R-142b	4.1	6.5	6.6	26.7/25.8 26.3
R-134				
AB	18.0		54.6/55.2 54.9	254/253 253
MO	24.7		59.4/56.4 57.9	292/271 282
PEMA	1.8		3.0/3.0 3.0	10.0/10.7 10.4
PEBA	0.1		1.3/2.6 2.0	7.2/7.9 7.55
PPGD	0.1		0.5/-0.5 0.0	0.3/0.5 0.4
PPGBM	0.2		0.7/0.5 0.6	1.0/1.4 1.2
MPG				

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 8

Ingredient

pphr

Isobutyl isoprene (2.2 % unsaturated)	100
Zinc Oxide	3
Stearic Acid	1
Sulfur	1.75
Tetramethyl thiuram disulfide	1
N330 Carbon Black	50

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	4.2	4.4	4.4	15.0/15.1 15.1
R-32	0.4	0.8		
R-124				
R-134a	0.1		0.4	1.9/1.9 1.9
R-125	0.6	1.5	1.9	5.4/5.4 5.4
R-143a	0.3	0.1	0.7	2.7/2.3 2.5
R-152a				
R-123	11.9	11.9	12.0	57.9/57.8 57.9
R-142b	2.5	4.9	4.7	17.3/17.3 17.3
R-134				
AB	8.1		35.9/35.3 35.6	129/126 128
MO	10.7		39.8/39.4 39.6	151/151 151
PEMA	0.5		2.1/2.3 2.2	6.7/6.6 6.7
PEBA	0.5		1.5/1.7 1.6	4.1/4.8 4.5
PPGD	-0.1		0.4/0.3 0.4	0.0/0.2 0.1
PPGBM	0.2		0.5/0.5 0.5	0.7/0.6 0.7
MPG				

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 9

Ingredient

pphr

Bromobutyl

100

Zinc Oxide

5

Stearic Acid

1

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	5.3	5.6	5.3	23.5/23.4 23.5
R-32	0.8	1.1		
R-124	1.7	2.4	4.1	17.4/18.3 17.9
R-134a	0.1		0.6	3.1/2.8 3.0
R-125	1.6	2.6	2.9	8.5/7.6 8.1
R-143a	0.4	0.4	1.1	4.3/4.4 4.4
R-152a	0.6	1.6	1.9	6.9/6.1 6.5
R-123	18.7	18.9	18.8	102/102 102
R-142b	4.9	6.7	6.5	26.9/26.3 26.6
R-134				
AB	30.3		85.9/77.2 81.6	523/447 485
MO	37.8		86.2/86.2 86.2	521/509 515
PEMA	1.6		5.9/6.0 6.0	21.2/21.5 21.4
PEBA	1.1		3.3/4.0 3.7	10.9/12.9 11.9
PPGD	0.6		0.8/1.5 1.2	5.1/5.3 5.2
PPGBM	0.0		1.0/0.8 0.9	4.0/4.1 4.1
MPG				

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 10

Ingredient	pphr
Bromobutyl	100
Zinc Oxide	5
Stearic Acid	1
N330 Carbon black	40

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	3.9	3.9	3.8	17.0/16.8 16.9
R-32	0.3	0.2		
R-124	0.8	1.4	2.5	12.5/12.6 12.6
R-134a	0.2		0.4	1.6/1.9 1.8
R-125	1.3	2.0	2.7	7.9/7.1 7.5
R-143a	0.5	0.4	0.9	3.1/2.7 2.9
R-152a	0.4	0.7	1.2	4.6/5.0 4.8
R-123	14.3	14.4	14.4	71.6/71.8 71.7
R-142b	2.2	5.3	5.6	19.2/19.2 19.2
R-134				
AB	15.5		47.1/47.6 47.4	187/190 188
MO	19.2		52.2/50.9 51.6	229/225 227
PEMA	1.5		4.0/3.9 4.0	12.6/12.0 12.5
PEBA	0.2		2.0/2.2 2.1	8.0/6.4 7.1
PPGD	0.5		1.4/1.1 1.3	3.2/3.2 3.2
PPGBM	0.5		1.0/0.6 0.8	3.0/2.7 2.9
MPG				

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 11	Ingredient	pphr
	Chlorobutyl	100
	Zinc Oxide	5
	Stearic Acid	1

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	5.8	6.1	5.7	26.2/25.5 25.9
R-32	0.6	0.7		
R-124	1.3	2.0	3.6	19.7/17.6 18.7
R-134a	0.1	0.3	0.5	2.8/2.6 2.7
R-125				
R-143a	0.5	0.7	1.3	4.0/3.8 3.9
R-152a	0.8	1.1	1.9	6.7/6.6 6.7
R-123	18.2	18.2	18.5	32.9/34.1 33.5
R-142b	4.9	6.7	7.0	27.9/28.1 28.0
R-134				
AB	29.9		62.7/61.3 62.0	304/292 298
MO	38.3		69.1/69.0 69.0	385/371 378
PEMA	1.4		4.2/4.1 4.2	15.0/14.5 15.0
PEBA	1.0		3.4/3.7 3.6	13.0/13.1 13.1
PPGD	0.3		1.3/1.4 1.3	4.4/4.4 4.4
PPGBM	-0.2		0.6/0.7 0.7	3.1/3.3 3.2
MPG	0.5		0.1/0.1 0.1	1.1/1.1 1.1

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 12

Ingredient

pphr

Chlorobutyl

100

Zinc Oxide

5

Stearic Acid

1

N330 Carbon Black

40

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	5.0	5.0	4.0	26.0/15.0 25.2
R-32	0.3	0.3		
R-124	1.0	2.0	3.0	13.2/13.2 13.2
R-134a	0.1	0.0	0.3	2.0/2.0 2.0
R-125	1.0	1.0	2.0	5.0/4.0 4.0
R-143a	0.2	0.2	1.0	2.0/2.5 2.3
R-152a	0.4	0.6	1.1	5.1/4.9 5.0
R-123	13.8	13.6	13.6	73.2/73.4 73.3
R-142b	3.7	4.9	5.3	20.0/20.1 20.0
R-134				
AB	17.6		39.5/38.6 39.1	151/145 148
MO	23.4		45.1/43.9 44.5	186/183 184
PEMA	1.0		3.3/3.4 3.3	10.4/10.5 10.5
PEBA	1.1		2.7/3.2 2.9	8.7/9.3 9.0
PPGD	0.2		0.8/0.5 0.6	2.7/2.4 2.6
PPGBM	-0.3		0.2/0.3 0.3	2.3/2.3 2.3
MPG	-0.3		0.3/-0.1 0.1	0.9/1.0 1.0

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 13

Ingredient	pphr
SBR (23.5 % Styrene Content)	100
Zinc Oxide	3
Sulfur	1.75
Stearic Acid	1
N-t-butyl-2-benzothiazyl sulfenamide	1

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	9.9	10.0	9.8	41.1/39.5 40.3
R-32	2.0	1.6		
R-124	5.9	5.4	4.1	22.5/22.5 22.5
R-134a	1.1		1.0	5.0/5.0 5.0
R-125	3.1	3.8	3.6	10.8/10.0 10.4
R-143a	1.4	1.5	1.5	5.2/5.2 5.2
R-152a	3.0	3.1	2.8	11.1/10.6 10.9
R-123	41.4	41.2	40.8	271/271 271
R-142b	7.8	7.5	7.3	31.1/30.3 30.7
R-134				
AB	29.7		43.6/42.3 43.0	175/171 173
MO	32.5		44.5/44.1 44.3	186/186 186
PEMA	16.3		22.9/22.6 22.8	85.6/84.7 85.2
PEBA	9.4		16.0/16.1 16.1	57.0/56.5 56.8
PPGD	1.6		1.2/1.8 1.5	5.9/5.5 5.7
PPGBM	5.9		10.0/9.2 9.6	29.4/29.5 29.5
MPG				

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 14

Ingredient	pphr
SBR 1502 (23.5 % Styrene content)	100
Zinc Oxide	3
Stearic Acid	1
Sulfur	1.75
N-t-butyl-2-benzothiazyl sulfenamide	1
N330 Carbon Black	50

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	7.6	7.1	7.1	26.9/27.1 27.0
R-32	1.2	1.2		
R-124	3.4	3.4	3.1	15.0/15.3 15.2
R-134a	0.9		0.6	3.3/3.7 3.5
R-125	2.0	2.1	2.1	7.0/6.5 6.8
R-143a				
R-152a	2.3	2.1	2.0	6.4/6.6 6.5
R-123	24.3	24.2	24.9	138/138 138
R-142b	6.0	6.0	5.9	20.1/20.0 20.1
R-134				
AB	15.7		24.0/24.2 24.1	81.9/81.2 81.6
MO	17.4		24.2/23.7 24.0	88.8/88.6 88.7
PEMA	8.8		13.2/13.2 13.2	45.5/45.1 45.3
PEBA	4.2		9.2/9.2 9.2	31.3/30.8 31.1
PPGD	1.1		2.1/1.4 1.8	5.0/4.8 4.9
PPGBM	3.3		5.5/5.4 5.5	18.8/18.0 18.9
MPG				

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 15

Ingredient

pphr

SBR (Medium Styrene) Content	100
Zinc Oxide	3
Stearic Acid	1
Sulfur	1.75
N-t-butyl-2-benzothiazyl sulfenamide	1

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	10.2	11.3	11.4	43.8\41.9 42.9
R-32	1.3	1.2		
R-124				
R-134a	1.9	1.6	1.7	7.5\7.4 7.5
R-125	2.3	2.7	1.9	10.1\9.8 10.0
R-143a	1.7	1.6	1.6	7.1\6.9 7.0
R-152a				
R-123	43.5	44.6	45.7	316\313 315
R-142b	8.3	8.6	7.6	-0.7\ -0.9 -0.8
R-134				
AB				
MO				
PEMA				
PEBA				
PPGD				
PPGBM				
MPG				

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 16

Ingredient

pphr

SBR (High Styrene) Content

100

Zinc Oxide

3

Stearic Acid

1

Sulfur

1.75

N-t-butyl-2-benzothiazyl sulfenamide

1

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	10.7	10.6	10.2	44.7/42.5 43.6
R-32	2.3	2.3		
R-124				
R-134a	2.1	1.9	1.7	7.6/6.7 7.2
R-125	2.9	3.0	2.8	9.2/8.8 9.0
R-143a	1.4	1.6	1.4	-0.4/-0.4 -0.4
R-152a				
R-123	52.9	53.1	52.6	380/393 386
R-142b	7.9	7.8	7.8	31.0/30.1 30.5
R-134				
AB				
MO				
PEMA				
PEBA				
PPGD				
PPGBM				
MPG				

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 17

Ingredient	pphr
Very High ACN Nitrile	100
Zinc Oxide	3
Stearic Acid	1
Magnesium Carbonate Coated Sulfur	1.5
N-t-butyl-2-benzothiazyl sulfenamide	0.7

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	47.8	47.5	47.6	255/238 247
R-32	8.5	8.5		
R-124	39.6	39.7	40.2	257/241 249
R-134a	2.0	3.0	4.9	20.7/20.4 20.6
R-125	0.8	0.0	1.7	7.4/9.7 8.6
R-143a	0.2	0.4	0.9	3.2/3.4 3.3
R-152a	7.8	7.9	7.9	24.9/24.3 24.6
R-123	78.5	79.2	77.5	669/664 666
R-142b	3.8	5.6	7.3	28.8/28.7 28.8
R-134				
AB	0.2		0.2/-0.1 0.1	0.2/0.2 0.2
MO	-0.2		0.3/0.3 0.3	1.5/1.6 1.6
PEMA	0.8		1.6/1.9 1.7	5.0/5.3 5.2
PEBA	0.4		1.0/1.1 1.0	3.1/3.6 3.4
PPGD	1.0		2.0/2.0 2.0	5.6/5.7 5.7
PPGBM	0.4		0.3/0.1 0.2	0.3/0.5 0.4
MPG	0.4		-0.4/-0.3 -0.3	-0.2/-0.1 -0.1

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 18

Ingredient	pphr
High ACN Nitrile	100
Zinc Oxide	3
Stearic Acid	1
Magnesium Carbonate Coated Sulfur	1.5
N-t-butyl-2-benzothiazyl sulfenamide	.7

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	51.4	50.8	51.4	275/260 268
R-32	8.3	8.3		
R-124	45.4	45.3	45.9	289/274 282
R-134a	2.5	4.1	5.1	22.0/21.9 22.0
R-125	1.5	2.0	3.9	16.2/15.9 16.1
R-143a	0.6	1.0	2.0	5.8/5.8 5.8
R-152a	8.6	8.7	8.8	27.5/27.3 27.4
R-123	83.0	83.4	83.7	720/713 716
R-142b	6.5	8.6	8.7	34.2/34.4 34.3
R-134				
AB	0.4		0.2/0.2 0.2	0.7/0.9 0.8
MO	0.4		0.7/0.9 0.8	2.5/2.7 2.6
PEMA	1.6		3.8/3.2 3.5	10.9/10.4 10.7
PEBA	1.0		2.1/2.6 2.4	6.3/7.2 6.7
PPGD	1.5		3.2/2.7 2.9	9.7/8.3 9.0
PPGBM	0.3		0.4/0.2 0.3	1.0/1.1 1.1
MPG	0.3		-0.2/-0.3 -0.2	0.1/0.0 0.1

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 19	Ingredient	pphr
	Medium ACN Nitrile	100
	Zinc Oxide	3
	Stearic Acid	1
	Magnesium Carbonate Coated Sulfur	1.5
	N-t-butyl-2-benzothiazyl sulfenamide	.7

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	49.8	49.8	50.4	262/244 253
R-32	7.7	7.7		
R-124	46.2	46.1	45.8	311/284 298
R-134a	5.1	5.8	5.7	25.0/23.7 24.4
R-125	3.5	5.1	6.2	23.5/23.1 23.3
R-143a	1.4	2.3	2.7	9.0/9.0 9.0
R-152a	8.8	8.9	8.7	28.4/27.8 28.1
R-123	94.2	94.1	94.4	875/883 879
R-142b	11.6	11.6	11.6	47.2/46.8 47.0
R-134				
AB	0.9		1.7/1.9 1.8	5.1/4.9 5.0
MO	1.3		2.6/2.7 2.7	8.3/8.7 8.5
PEMA	6.4		9.9/9.7 9.8	33.2/33.2 33.2
PEBA	3.8		7.7/7.7 7.7	25.4/25.6 25.5
PPGD	5.8		8.0/7.9 7.9	25.6/25.4 25.5
PPGBM	1.3		2.0/1.8 1.9	5.9/5.8 5.9
MPG	0.5		0.7/0.7 0.7	2.6/2.9 2.8

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 20

Ingredient	pphr
Low ACN Nitrile	100
Zinc Oxide	3
Stearic Acid	1
Magnesium Carbonate Coated Sulfur	1.5
N-t-butyl-2-benzothiazyl sulfenamide	.7

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	35.6	35.1	35.4	180/174 177
R-32	6.2	6.1		
R-124	31.0	31.2	29.9	199/187 193
R-134a	4.5	4.3	4.3	19.2/18.8 19.0
R-125	5.0	5.3	5.2	21.9/21.4 21.7
R-143a	2.8	3.2	3.4	11.9/11.1 11.5
R-152a	7.4	8.1	7.4	27.3/27.0 27.2
R-123	73.9	71.3	73.2	739/755 747
R-142b	13.8	14.1	14.0	59.9/58.9 59.4
R-134				
AB	4.8		6.9/7.1 7.0	21.0/22.0 21.5
MO	4.2		7.0/8.4 7.7	26.9/26.9 26.9
PEMA	21.5		23.5/24.7 24.1	98.4/98.9 98.6
PEBA	13.1		18.9/19.2 19.0	72.0/72.1 72.1
PPGD	11.0		11.1/11.4 11.3	39.9/39.9 39.9
PPGBM	4.0		7.2/7.6 7.4	23.7/23.8 23.7
MPG	2.3		4.3/3.9 4.1	13.9/14.3 14.1

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 21

Ingredient	pphr
Low ACN Nitrile	100
Zinc Oxide	3
Stearic Acid	1
MgCO ₃ Coated Sulfur	1.5
N-t-butyl-2-benzothiazyl sulfenamide	.7
N330 Carbon Black	35

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	25.8	23.0	22.0	121/115 118
R-32	4.3	4.5		
R-124				
R-134a	3.3	3.4	3.5	15.5/15.4 15.5
R-125	3.0	3.8	3.4	15.8/15.6 15.7
R-143a	1.6	1.7	1.4	8.0/7.9 8.0
R-152a				
R-123	42.5	41.9	40.9	352/362 357
R-142b	8.5	9.0	9.1	41.3/40.5 40.9
R-134				
AB				
MO				
PEMA				
PEBA				
PPGD				
PPGBM				
MPG				

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 22

Ingredient

pphr

Very High ACN Nitrile	100
Zinc Oxide	3
Stearic Acid	1
MgCO ₃ Coated Sulfur	1.5
N-t-butyl-2-benzothiazyl sulfenamide	.7
N330 Carbon Black	35

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	31.5	31.6	31.7	157/165 161
R-32	6.3	6.4		
R-124				
R-134a	1.2	2.5	4.2	15.7/15.8 15.8
R-125	0.4	0.8	1.6	6.8/7.0 6.9
R-143a	0.4	0.3	0.8	2.8/2.3 2.6
R-152a				
R-123	49.3	49.4	49.7	388/391 390
R-142b				
R-134				
AB				
MO				
PEMA				
PEBA				
PPGD				
PPGBM				
MPG				

PEMA - Pentaerythritol Ester Mixed Acid

PEBA - Pentaerythritol Ester Branched Acid

PPGBM - Polypropylene Glycol Butyl Monoether

MO - Mineral Oil

MPG - Modified Polyglycol

PPGD - Polypropylene Glycol Diol

AB - Alkyl Benzene

Formula # 24	Ingredient	pphr
	38 % ACN Hydrogenated Nitrile	100
	Zinc Oxide	5
	Stearic Acid	1
	MgCO ₃ Coated Sulfur	1.5
	TMTM	.3
	MBTS	1.5
	N774 Carbon Black	40

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.	
R-22	68.4	66.4	66.0	320/208	264
R-32	6.3	6.2			
R-124					
R-134a	4.7	5.3	5.5	21.1/21.2	21.2
R-125	5.2	6.7	6.7	26.0/26.1	26.1
R-143a	1.2	2.1	2.4	8.0/15.2	11.6
R-152a					
R-123	122	121	115	1293/1301	1301
R-142b	10.8	10.6	11.0	42.1/40.8	41.45
R-134					
AB					
MO					
PEMA					
PEBA					
PPGD					
PPGBM					
MPG					

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 29

Ingredient

pphr

Fluoroelastomer	100
Litharge (Sublimed)	3
Triallyl Isocyanurate	3
2,5-Dimethyl-2,5-bis(t-butylperoxy) hexane	3

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	36.2	35.9	35.5	91.2/83.8 87.5
R-32	19.5	19.6		
R-124	39.8	40.4	39.9	125/120 122
R-134a	30.4	30.4	30.2	79.0/77.0 78.0
R-125	19.8	19.7	19.6	49.9/48.7 49.3
R-143a	20.7	20.7	20.8	38.4/37.8 38.1
R-152a	34.8	35.0	34.4	62.7/58.9 60.8
R-123	35.7	37.0	37.8	121/121 121
R-142b	37.9	38.0	37.6	95.2/91.1 93.2
R-134				
AB	0.8		0.2/0 0.1	0.2/0.1 0.2
MO	-0.6		-0.2/0.8 0.3	0.2/0.2 0.2
PEMA	1.0		0.7/0.7 0.7	1.1/1.1 1.1
PEBA	0.8		1.3/0.9 1.1	1.6/1.7 1.6
PPGD	1.0		0.5/1.0 0.7	0.8/0.7 0.7
PPGBM	0.5		0.2/0 0.1	0.4/0.3 0.3
MPG	0.1		-0.3/0.1 -0.1	0.2/0.2 0.2

PEMA - Pentaerythritol Ester Mixed Acid

PEBA - Pentaerythritol Ester Branched Acid

PPGBM - Polypropylene Glycol Butyl Monoether

MO - Mineral Oil

MPG - Modified Polyglycol

PPGD - Polypropylene Glycol Diol

AB - Alkyl Benzene

Formula # 30

Ingredient	pphr
Fluoroelastomer	100
Litharge (Sublimed)	3
Triallyl Isocyanurate	3
2,5-Dimethyl-2,5-bis (t-butylperoxy) hexane	3
N330 Carbon Black	30

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	22.0	22.2	22.5	57.8/56.4 57.1
R-32	13.6	12.7		
R-124	24.1	23.4	24.0	73.7/68.4 71.1
R-134a	19.2	18.8	18.2	50.0/47.2 48.6
R-125	13.4	13.5	13.3	36.5/35.8 36.2
R-143a	13.8	14.2	14.0	27.9/26.9 27.4
R-152a	21.5	21.9	21.5	41.8/40.2 41.0
R-123	22.6	22.9	24.3	70.7/58.5 64.6
R-142b	23.2	23.6	23.0	56.2/52.5 54.4
R-134				
AB	0.3		0.1/0 0.1	0.2/0.3 0.3
MO	-0.1		0.5/0.3 0.4	0.3/0.3 0.3
PEMA	0.4		1.0/0.4 0.7	1.0/1.0 1.0
PEBA	0.3		1.0/0.5 0.8	1.5/1.6 1.6
PPGD	0		0.4/0.5 0.5	0.9/0.9 0.9
PPGBM	0.2		0.3/0.2 0.2	0.4/0.4 0.4
MPG	0.1		0.3/0.4 0.3	0.2/0.2 0.2

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 31

Ingredient	pphr
Fluoroelastomer	100 g
Litharage (Sublimed)	1.8 g
Triallyl Isocyanurate	1.8 g
2,5-Dimethyl-2,5-bis (t-butylperoxy) hexane	1.8 g

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.	
R-22	25.8	25.6	25.9	71.6/69.1	70.4
R-32	17.4	17.5			
R-124					
R-134a	15.7	15.6	16.2	43.2/42.2	42.7
R-125	5.8	7.6	8.6	22.0/22.0	22.0
R-143a	9.9	10.0	10.2	22.7/22.4	22.6
R-152a					
R-123	27.8	27.3	29.1	106/108	107
R-142b	26.3	25.9	25.1	67.1/66.9	67.0
R-134					
AB					
MO					
PEMA					
PEBA					
PPGD					
PPGBM					
MPG					

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 34

Ingredient

pphr

Epichlorohydrin Homopolymer

100 g

Stearic Acid

1 g

Nickel Dibutyldithiocarbamate

1 g

Red Lead

5 g

Ethylene Thiourea

1.85 g

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	12.3	21.1	12.3	38.9/38.4 38.7
R-32	4.7	4.3		
R-124				
R-134a	0.3	0.9	1.3	4.2/4.3 4.3
R-125	0.0	0.1	0.1	1.3/1.4 1.3
R-143a	0.2	0.4	0.9	2.6/2.7 2.7
R-152a				
R-123	16.4	17.5	17.1	68.0/68.0 68.0
R-142b	2.3	4.3	5.0	14.4/14.3 14.3
R-134				
AB				
MO				
PEMA				
PEBA				
PPGD				
PPGBM				
MPG				

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 35

Ingredient	pphr
Epichlorohydrin Homopolymer	100 g
Stearic Acid	1 g
Nickel Dibutyldithiocarbamate	1 g
Red Lead	5 g
Ethylene Thiourea	1.85 g
N330 Carbon Black	40 g

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	8.7	8.7	5.6	28.8/28.1 28.5
R-32	3.7	3.4		
R-124				
R-134a	0.2	0.3	1.0	2.7/3.0 2.8
R-125	0.0	0.1	0.1	0.9/0.9 0.9
R-143a	0.2	0.4	0.6	1.6/1.8 1.7
R-152a				
R-123	10.4	12.0	11.8	45.7/45.8 45.7
R-142b	1.1	2.8	2.9	10.3/10.5 10.4
R-134				
AB				
MO				
PEMA				
PEBA				
PPGD				
PPGBM				
MPG				

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 36

Ingredient	pphr
Epichlorohydrin Copolymer	100 g
Stearic Acid	1 g
Nickel Dibutyldithiocarbamate	1 g
Red Lead	5 g
Ethylene Thiourea	1.85 g

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	36.3	36.5	36.0	133/120 126
R-32	6.9	6.4		
R-124				
R-134a	3.8	3.6	3.7	12.1/12.1 12.1
R-125	2.2	3.0	3.1	10.6/10.6 10.6
R-143a	1.2	1.6	1.6	4.8/4.8 4.8
R-152a				
R-123	67.3	67.2	68.0	418/418 418
R-142b	6.8	6.6	5.8	20.8/20.6 20.7
R-134				
AB				
MO				
PEMA				
PEBA				
PPGD				
PPGBM				
MPG				

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 37

Ingredient

pphr

Epichlorohydrin Copolymer	100 g
Stearic Acid	1 g
Nickel Dibutyldithiocarbamate	1 g
Red Lead	5 g
Ethylene Thiourea	1.85 g
N330 Carbon Black	40 g

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	25.6	26.1	23.8	89.6/83.8 86.7
R-32	5.5	5.7		
R-124				
R-134a	2.7	2.5	2.7	8.8/8.3 8.5
R-125	1.5	2.1	2.4	7.3/7.3 7.3
R-143a	0.8	1.1	1.2	3.4 3.4
R-152a				
R-123	43.1	44.6	43.2	210/113 211
R-142b	5.0	5.3	4.8	14.9/15.0 15.0
R-134				
AB				
MO				
PEMA				
PEBA				
PPGD				
PPGBM				
MPG				

PEMA - Pentacrythritol Ester Mixed Acid
 PEBA - Pentacrythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula #38

Ingredient

pphr

Epichlorohydrin Terpolymer	100 g
Stearic Acid	1 g
Nickel Dibutyldithiocarbamate	1 g
Red Lead	5 g
Ethylene Thiourea	1.85 g

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	39.8	39.0	38.4	154/145 149
R-32	7.5	7.4		
R-124				
R-134a	4.3	3.4	4.5	14.4/14.5 14.5
R-125	2.8	3.2	3.4	12.2/12.0 12.1
R-143a	1.7	1.7	1.5	4.8/4.7 4.8
R-152a				
R-123	69.4	69.5	70.5	447/449 448
R-142b	8.0	7.4	7.4	22.5/22.3 22.4
R-134				
AB				
MO				
PEMA				
PEBA				
PPGD				
PPGBM				
MPG				

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 39

Ingredient

pphr

Epichlorohydrin Terpolymer	100 g
Stearic Acid	1 g
Nickel Dibutyldithiocarbamate	1 g
Red Lead	5 g
Ethylene Thiourea	1.85 g
IRB6	40 g

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	26.7	26.8	26.3	102/96 99
R-32	5.1	5.5		
R-124				
R-134a	3.0	3.0	3.1	10.2/10.3 10.2
R-125	2.0	2.5	3.0	9.0/8.6 8.8
R-143a	1.0			
R-152a				
R-123	42.3	43.2	41.8	227/227 227
R-142b	5.5	5.5	5.1	16.4/16.1 16.3
R-134				
AB				
MO				
PEMA				
PEBA				
PPGD				
PPGBM				
MPG				

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 41

Ingredient

pphr

Dimethyl Silicone Rubber

100 g

Dicumyl Peroxide on Calcium Carbonate

1 g

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	50.0	51.9	52.4	222/199 211
R-32	5.8	5.9		
R-124	41.5	41.0	40.0	210/190 200
R-134a	6.1	18.3	6.0	18.5/16.4 17.5
R-125	7.2	7.6	7.2	21.7/21.8 21.7
R-143a	9.9	9.8	9.3	21.0/19.1 20.1
R-152a	17.3	17.1	17.0	49.0/39.7 44.3
R-123	60.4	60.9	59.9	398/387 393
R-142b	53.0	51.6	50.7	247/216 232
R-134				
AB	15.9		15.7/15.9 15.8	44.6/44.2 44.4
MO	7.9		7.1/7.4 7.3	19.5/19.4 19.5
PEMA	1.5		1.2/1.5 1.4	3.7/3.7 3.7
PEBA	2.8		2.5/2.3 2.4	7.3/7.2 7.2
PPGD	0.6		0.2/0.2 0.2	0.2/0.2 0.2
PPGBM	0.4		-0.1/0.1 0	0.7/0.6 0.6
MPG	4.7		-0.3/-0.4 -0.4	-0.2/-0.4 -0.3

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 42

Ingredient

pphr

Methylphenylvinyl Silicone Rubber

100 g

Dicumyl Peroxide on Calcium Carbonate

0.6 g

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	50.8	51.3	50.5	218/210 214
R-32	4.8	4.8		
R-124	41.8	41.8	42.6	195/193 194
R-134a	5.1	5.3	5.4	17.0/17.1 17.1
R-125	5.8	5.9	6.0	16.0/17.0 16.6
R-143a	6.8	6.8	6.1	14.5/12.9 13.7
R-152a	14.0	14.6	14.8	37.7/33.1 35.4
R-123	62.8	63.2	65.1	415/399 407
R-142b	52.8	55.6	53.5	252/227 240
R-134				
AB	25.9		26.5/26.7 26.6	78.1/77.4 77.8
MO	11.5		12.0/12.5 12.3	32.5/32.8 32.7
PEMA	9.7		9.6/8.0 8.8	26.3/26.2 26.2
PEBA	12.1		12.3/12.9 12.6	37.2/37.2 37.2
PPGD	2.6		1.6/0.6 1.1	3.7/3.8 3.7
PPGBM	4.5		4.2/3.5 3.8	9.5/9.5 9.5
MPG	3.0		2.8/2.8 2.8	8.6/8.9 8.8

PEMA - Pentaerythritol Ester Mixed Acid

PEBA - Pentaerythritol Ester Branched Acid

PPGBM - Polypropylene Glycol Butyl Monoether

MO - Mineral Oil

MPG - Modified Polyglycol

PPGD - Polypropylene Glycol Diol

AB - Alkyl Benzene

Formula # 43

Ingredient

pphr

Silicone Rubber

100

Dicumyl Peroxide on Calcium Carbonate

0.8

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	21.3	21.6	22.1	97.1/86.6 91.9
R-32	3.4	3.8		
R-124	17.5	17.2	17.4	89.2/82.3 85.7
R-134a	3.6	3.9	3.6	12.6/12.0 12.3
R-125	4.5	4.4	4.8	15.8/15.5 15.7
R-143a	6.1	5.9	5.9	15.7/13.8 14.8
R-152a	9.1	9.1	9.2	28.0/25.7 26.9
R-123	23.0	23.0	22.3	139/136 137
R-142b	22.0	22.0	22.0	91.5 91.5
R-134				
AB	8.5		8.1/7.9 8.0	22.1/22.0 22.1
MO	5.4		4.5/4.6 4.6	12.6/12.5 12.6
PEMA	2.2		1.7/1.8 1.8	5.1/5.0 5.1
PEBA	2.7		2.3/2.1 2.2	7.0/7.0 7.0
PPGD	0.5		0.4/0.5 0.4	1.6/1.4 1.5
PPGBM	0.8		0.6/0.9 0.7	2.7/2.6 2.7
MPG	0.9		0.7/0.5 0.6	2.5/2.7 2.6

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 44

Ingredient

pphr

Fluorosilicone

100

Iron Oxide

1.5

Bis(2,4-dichlorobenzoyl peroxide)

1.3

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	42.0	42.0	43.0	141/129 135
R-32	31.6	31.7		
R-124	32.5	33.1	32.2	137/127 132
R-134a	34.6	35.0	35.4	127/122 125
R-125	15.0	15.0	15.0	50.0/48.2 49.0
R-143a	24.0	24.0	24.5	64.1/58.0 61.0
R-152a	39.6	39.8	39.4	106/102 104
R-123	31.7	31.0	31.4	137/137 137
R-142b	43.3	43.0	42.0	151 151
R-134				
AB	0.8		-0.3/0.3 0	1.1/1.0 1.1
MO	1.0		0.6/0.4 0.5	0.8/0.9 0.9
PEMA	2.5		2.1/1.9 2.0	4.9/4.9 4.9
PEBA	2.3		2.7/3.6 3.1	7.5/7.5 7.5
PPGD	1.1		0.7/0.7 0.7	1.3/1.4 1.3
PPGBM	0		-0.1/0.1 0	0.6/0.5 0.6
MPG	-0.6		-0.7/0 -0.3	0.3/0.5 0.4

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 45

Ingredient

pphr

EPDM/Polypropylene TPE Shore A 87

100

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	-0.7	-0.9	-0.9	5.9/3.1 4.5
R-32	0.7	0.9		
R-124	-0.8	-0.9	-1.3	8.8/8.9 8.9
R-134a	0.0		0.1	2.4/2.4 2.4
R-125	1.0	1.4	1.7	9.6/10.4 10.0
R-143a	0.8	0.6	0.9	2.9/3.0 2.9
R-152a	0.8	0.7	0.8	5.9/4.2 5.1
R-123	0.3	0.1	0.1	19.2/19.2 19.2
R-142b	-0.1	-0.3	-0.6	7.0/6.2 6.6
R-134				
AB	3.6		4.5/4.6 4.6	17.3/18.1 17.7
MO	6.6		6.6/6.7 6.7	26.0/26.2 26.1
PEMA	-1.3		-1.7/-1.7 -1.7	-1.7/-2.0 -1.9
PEBA	-0.8		-1.2/-1.6 -1.4	-1.7/-1.8 -1.8
PPGD	-2.8		-3.5/-2.7 -3.1	-9.0/-8.9 -8.9
PPGBM	-1.2		-1.9/-2.4 -2.2	-4.4/-4.4 -4.4
MPG				

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 46

Ingredient

pphr

EPDM/Polypropylene TPE Shore A 73

100

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	-2.5	-3.2	-3.5	-7.0/-8.1 -7.6
R-32	0.7	0.7		
R-124	-2.4	-3.4	-4.2	-5.9/-6.4 -6.2
R-134a	0.4		0.1	2.6/2.7 2.6
R-125	1.3	2.7	3.2	11.3/12.9 12.1
R-143a	0.1	0.2	0.4	3.3/3.5 3.4
R-152a	0.7	0.3	0.6	4.5/3.9 4.2
R-123	-1.3	-1.3	-1.4	15.2/15.1 15.2
R-142b	-3.3	-3.8	-4.2	-6.1/-6.4 -6.3
R-134				
AB	8.7		11.1/10.3 10.7	38.6/38.5 38.6
MO	13.8		13.2/14.1 13.7	54.2/54.0 54.1
PEMA	-3.9		-8.0/-5.1 -6.6	-13.5/-13.7 -13.6
PEBA	-3.2		-4.2/-4.2 -4.2	-12.5/-12.6 -12.6
PPGD	-5.6		-6.0/-7.3 -6.7	-21.6/-21.3 -21.5
PPGBM	-4.0		-6.1/-6.5 -6.3	-18.1/-17.9 -18.0
MPG				

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 47

Ingredient

pphr

EPDM/Polypropylene TPE Shore D 40

100

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	-0.4	-0.4	-0.5	7.6/3.4 5.5
R-32	0.4	0.2		
R-124	-0.4	-0.5	-0.5	11.8/10.6 11.2
R-134a	0.2		0.3	2.2/2.1 2.1
R-125	0.8	1.7	1.8	9.4/9.5 9.4
R-143a	0.7	0.6	0.6	2.8/2.7 2.7
R-152a	0.3	0.6	0.6	6.1/4.8 5.4
R-123	0.9	0.5	0.5	18.8/18.5 18.7
R-142b	0.2	-0.2	-0.2	8.1/7.0 7.6
R-134				
AB	2.9		3.4/2.9 3.2	13.5/14.4 14.0
MO			4.1/3.9 4.0	18.3/18.0 18.2
PEMA	-0.5		-0.6/-0.2 -0.4	1.0/1.2 1.1
PEBA	-0.5		0.1/-0.4 -0.2	0.9/1.1 1.0
PPGD	-1.0		-1.2/-1.1 -1.2	-3.2/-3.2 -3.2
PPGBM	-0.4		-0.3/-0.9 -0.5	-0.4/-0.5 -0.5
MPG				

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 48

Ingredient

pphr

EPDM/Polypropylene TPE Shore D 50

100

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	0.1	0.5	0.1	7.6/6.4 7.0
R-32				
R-124	0.1	-0.2	-0.3	9.7/9.3 9.5
R-134a	0.3		0.3	1.9/2.2 2.1
R-125	0.6	1.3	1.4	8.8/9.4 9.1
R-143a	0.2	0.4	0.7	2.3/2.4 2.3
R-152a	0.1	-0.2	-0.1	2.0/1.2 1.6
R-123	1.4	1.0	1.1	17.8/17.8 17.8
R-142b	0.7	0.7	0.4	7.9/7.7 7.8
R-134				
AB	1.5		2.5/2.2 2.4	9.5/9.2 9.4
MO	2.6		2.7/2.6 2.7	13.9/13.7 13.8
PEMA	0.6		0.2/0.0 0.1	2.0/1.6 1.8
PEBA	0.0		-2.5/0.0 -1.3	1.5/1.8 1.7
PPGD	-0.6		-1.1/-1.3 -1.2	-1.5/-1.6 -1.6
PPGBM	-0.5		-0.4/-0.4 -0.4	0.8/0.7 0.8
MPG				

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 49

Ingredient

pphr

Nitrile/Polypropylene TPE Shore A 87

100

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	9.9	10.3	10.2	65.2/54.7 60.0
R-32				
R-124	5.7	5.8	6.6	51.1/50.0 50.6
R-134a	0.4	0.7	-0.2	4.4/4.0 4.2
R-125	1.3	14.2	1.7	7.8/8.8 8.3
R-143a	1.1	0.4	-0.4	0.7/1.5 1.1
R-152a	1.0	0.3	0.4	2.6/3.4 3.0
R-123	19.6	20.0	20.6	140/139 139
R-142b	2.3	1.7	1.7	12.3/12.1 12.2
R-134				
AB	1.0		0.5/0.7 0.6	-0.9/-0.9 -0.9
MO	1.8		0.9/0.4 0.7	1.1/1.1 1.1
PEMA	0.9		0.7/1.1 0.9	3.6/3.6 3.6
PEBA	0.0		0.3/0.9 0.6	2.5/2.5 2.5
PPGD	0.6		0.4/-0.1 0.2	0.5/0.8 0.6
PPGBM	-0.2		-0.4/-0.8 -0.6	-2.2/-2.1 -2.1
MPG	-1.4		-1.2/1.2 1.2	-2.7/-2.4 -2.6

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Nitrile/Polypropylene TPE Shore A 80

100

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	14.3	14.6	14.6	78.4/75.5 77.0
R-32				
R-124	10.5	10.2	10.6	77.7/74.8 76.3
R-134a	0.7	-0.2	-1.3	1.2/3.7 2.5
R-125	1.8	1.7	0.3	4.8/4.7 4.7
R-143a	0.4	2.8	-1.2	-2.6/-0.2 -1.4
R-152a	-0.4	-0.3	-0.4	0.4/0.1 0.3
R-123	31.1	31.5	31.8	216/216 216
R-142b	1.5	1.1	0.6	11.1/11.5 11.3
R-134				
AB	-0.3		-1.4/-1.3 -1.4	-5.9/-5.7 -5.8
MO	0.7		-0.8/-0.9 -0.9	-3.3/-3.1 -3.2
PEMA	1.4		0.9/0.8 0.9	3.3/3.5 3.4
PEBA	0.4		0.3/-0.1 0.1	1.4/1.4 1.4
PPGD	1.0		0.6/0.7 0.6	1.3/1.5 1.4
PPGBM	-0.8		-1.9/-1.9 -1.9	-6.0/-6.2 -6.1
MPG	-1.9		-2.8/-2.5 -2.7	-7.7/-7.9 -7.8

PEMA - Pentaerythritol Ester Mixed Acid

PEBA - Pentaerythritol Ester Branched Acid

PPGBM - Polypropylene Glycol Butyl Monoether

MO - Mineral Oil

MPG - Modified Polyglycol

PPGD - Polypropylene Glycol Diol

AB - Alkyl Benzene

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	6.9	7.1	7.4	47.4/42.9 45.2
R-32				
R-124	4.7	4.6	4.5	39.7/39.0 39.4
R-134a	0.9	0.9	0.5	6.6/7.2 6.9
R-125	1.0	1.8	1.8	7.5/8.2 7.9
R-143a	0.8	1.3	0.3	1.8/2.0 1.4
R-152a	1.2	0.4	0.3	3.0/3.0 3.0
R-123	14.2	14.5	15.4	103/101 102
R-142b	2.3	1.9	1.7	12.0/11.5 11.8
R-134				
AB	1.4		0.7/1.1 0.9	1.0/1.0 1.0
MO	1.8		1.1/1.1 1.1	2.9/3.1 3.0
PEM0	0.8		0.9/0.8 0.8	3.4/3.3 3.4
PEBA	0		0.5/0.4 0.5	2.8/2.6 2.7
PPGD	0		-0.2/-0.2 -0.2	0.4/0.5 0.4
PPGBM	-0.1		-0.2/-0.4 -0.3	-0.8/-0.9 -0.9
MPG	-0.6		-1.0/-0.6 -0.8	-1.6/-1.5 -1.5

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 68

Ingredient

pphr

Chlorosulfonated PE

100

Litharge

25

Benzothiazyl disulfide

0.5

Sulfur

2

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	9.1	8.6	8.2	27.8/27.9 27.8
R-32				
R-124				
R-134a	0.3	0.3	1.2	3.5/3.2 3.3
R-125	0.7	0.9	1.2	3.5/2.8 3.2
R-143a	1.0	1.4	2.2	5.0/4.9 4.9
R-152a				
R-123	18.6	18.9	18.8	75.2/75.0 75.1
R-142b	3.6	6.0	6.1	17.7/17.9 17.8
R-134				
AB				
MO				
PEMA				
PEBA				
PPGD				
PPGBM				
MPG				

PEMA - Pentaerythritol Ester Mixed Acid

PEBA - Pentaerythritol Ester Branched Acid

PPGPM - Polypropylene Glycol Butyl Monoether

MO - Mineral Oil

MPG - Modified Polyglycol

PPGD - Polypropylene Glycol Diol

AB - Alkyl Benzene

Chlorosulfonated PE	100 g
Litharge	20 g
Benzothiazyl disulfide	0.5 g
Dipentamethylenethiuram hexasulfide	0.75 g
Magnesia	10 g
Nickel Dibutyldithiocarbamate	3 g

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	7.8	7.2	7.3	23.2/23.1 23.1
R-32				
R-124				
R-134a	-0.1	0.0	0.9	3.6/3.5 3.5
R-125	1.1	1.2	1.3	3.8/3.8 3.8
R-143a	0.7	1.3	1.9	4.4/4.2 4.3
R-152a				
R-123	17.9	17.8	17.5	71.2/71.3 71.2
R-142b	3.9	5.9	5.7	16.6/16.8 16.7
R-134				
AB				
MO				
PEMA				
PEBA				
PPGD				
PPGBM				
MPG				

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 72

Ingredient

pphr

EP Rubber
Dicumyl Peroxide

100 g
3 g

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	6.0	6.0	5.9	27.6/26.9 27.3
R-32				
R-124	2.8	3.0	2.7	19.1/18.2 18.7
R-134a	1.8	2.3	3.4	10.3/5.6 8.0
R-125	3.3	3.3	2.8	9.2/7.6 8.4
R-143a	1.4	1.5	0.9	4.1/3.7 3.9
R-152a	1.0	1.0	1.1	5.8/5.0 5.4
R-123	15.9	16.1	16.2	105/105 105
R-142b	7.5	7.4	7.6	31.7 31.7
R-134				
AB	58.9		70.7/72.8 71.7	434/425 429
MO	66.2		83.4/83.3 83.4	560/534 547
PEMA	3.1		3.2/3.1 3.2	12.7/12.6 12.7
PEBA	3.2		3.2/2.6 2.9	12.1/12.3 12.2
PPGD	0.1		0.2/0 0.1	0.4/0.3 0.3
PPGBM	0.7		0.4/0.4 0.4	1.5/1.6 1.6
MPG	-0.2		-0.4/-0.1 -0.3	-0.3/0.4 0.1

PEMA - Pentaerythritol Ester Mixed Acid

PEBA - Pentaerythritol Ester Branched Acid

PPGBM - Polypropylene Glycol Butyl Monoether

MO - Mineral Oil

MPG - Modified Polyglycol

PPGD - Polypropylene Glycol Diol

AB - Alkyl Benzene

Formula # 73

Ingredient

pphr

EP Rubber
Dicumyl Peroxide

100 g
3 g

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	4.5	4.4	4.5	19.5/19.3 19.4
R-32				
R-124	2.1	2.4	2.4	10.8/11.3 11.1
R-134a	0.9	1.1	0.8	2.0/1.3 1.7
R-125	2.2	2.1	2.1	7.8/6.7 7.3
R-143a	1.3	1.3	1.2	2.7/2.6 2.6
R-152a	1.1	1.1	1.2	4.3/3.8 4.1
R-123	9.1	9.0	9.0	52.1/52.2 52.1
R-142b	4.9	4.9	4.8	19.8/19.5 19.6
R-134				
AB	41.0		49.7/48.4 49.1	231/232 231
MO	53.6		58.2/59.3 58.8	314/317 315
PEMA	2.6		2.5/1.6 2.1	9.4/9.3 9.4
PEBA	2.5		2.8/2.4 2.6	9.6/9.8 9.7
PPGD	0.8		0.4/0.1 0.3	1.2/1.4 1.3
PPGBM	1.3		1.1/0.4 0.7	2.9/1.3 2.1
MPG	0.4		0.1/0.0 0.1	0.3/-0.1 0.1

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 74

Ingredient

pphr

EP Rubber
Dicumyl Peroxide
N330 Carbon Black

100 g
3 g
40 g

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	2.7	2.8	2.6	13.0/13.2 13.1
R-32				
R-124	1.1	1.2	1.2	7.1/7.4 7.3
R-134a	0.2	0.3	0.2	0.3/0.3 0.3
R-125	1.8	1.8	1.7	5.6/5.4 5.5
R-143a	1.2	0.9	1.2	2.4/3.1 2.8
R-152a	0.6	0.3	0.5	2.9/3.0 2.9
R-123	6.8	6.6	6.1	35.9/36.3 36.1
R-142b	3.5	3.4	3.3	13.6/13.3 13.5
R-134				
AB	31.5		36.6/36.6 36.6	148/147 147
MO	38.5		45.0/43.4 44.2	206/200 203
PEMA	2.0		1.4/1.1 1.3	6.0/6.0 6.0
PEBA	1.4		1.9/1.4 1.6	6.3/6.5 6.4
PPGD	0.3		0.0/0.1 0.1	0.4/0.4 0.4
PPGBM	-0.1		-0.2/0.4 0.1	0.8/0.9 0.9
MPG	0.1		-0.6/-0.1 -0.4	-0.2/-0.2 -0.2

PEMA - Pentaerythritol Ester Mixed Acid
PEBA - Pentaerythritol Ester Branched Acid
PPGBM - Polypropylene Glycol Butyl Monoether
MO - Mineral Oil

MPG - Modified Polyglycol
PPGD - Polypropylene Glycol Diol
AB - Alkyl Benzene

Formula # 75

Ingredient

pphr

Ethylene Acrylic Elastomer

100 g

Methylene Diamine

1 g

Diphenylguanidine

3.2 g

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	78.6	77.5	77.4	116/334 225
R-32				
R-124				
R-134a	11.9	11.9	12.3	50.7/49.6 50.0
R-125	16.9	17.0	16.7	74.2/74.0 74.1
R-143a	5.3	5.5	5.5	18.5/18.0 18.3
R-152a				
R-123	119.0	117.0	116.0	1209/1194 1202
R-142b	31.4	30.6	31.1	130/126 128
R-134				
AB				
MO				
PEMA				
PEBA				
PPGD				
PPGBM				
MPG				

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 76

Ingredient

pphr

Ethylene Acrylic Elastomer

100

N 774

35

Methylene Dianiline

1

Diphenylguanidine

4

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.	
R-22	47.2	46.0	46.7	183/164	174
R-32					
R-124					
R-134a	8.5	8.3	7.9	29.9/29.9	29.9
R-125	11.7	12.0	11.5	44.8/44.7	44.7
R-143a	4.4	4.5	4.7	10.7/10.5	10.6
R-152a					
R-123	65.3	66.0	69.1	458/455	456
R-142b	21.2	20.5	20.1	81.4/78.6	80.0
R-134					
AB					
MO					
PEMA					
PEBA					
PPGD					
PPGBM					
MPG					

PEMA - Pentaerythritol Ester Mixed Acid

PEBA - Pentaerythritol Ester Branched Acid

PPGBM - Polypropylene Glycol Butyl Monoether

MO - Mineral Oil

MPG - Modified Polyglycol

PPGD - Polypropylene Glycol Diol

AB - Alkyl Benzene

Chlorinated PE	100 g
Magnesium Dioxide	10 g
Triallyl Isocyanurate	2 g
Dicumyl Peroxide on Clay	4 g
N330 Carbon Black	40 g

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
------------	------------------------	------------------------	-----------------------	-----------------------

R-22	4.7	4.2	4.5	18.6/18.4	18.5
R-32					
R-124					
R-134a	0.2	0.3	0.6	2.2/2.0	2.1
R-125	0.0	0.3		2.2/2.1	2.2
R-143a	-0.1	0.2	0.5	1.7/1.8	1.8
R-152a					
R-123	10.2	11.7	10.2	49.0/49.5	49.2
R-142b	1.0	3.5	3.8	12.6/12.6	12.6
R-134					
AB					
MO					
PEMA					
PEBA					
PPGD					
PPGBM					
MPG					

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

EPDM	100 g
Zinc Oxide	5 g
Sulfur	15 g
Stearic Acid	1 g
TMTD	1 g
MBT	.5 g

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	3.9	4.3	3.8	16.7/16.0 16.4
R-32				
R-124	1.7	2.2	2.1	10.2/10.6 10.4
R-134a	0.5		0.6	2.4/2.5 2.5
R-125	2.3	2.9	2.8	9.0/9.0 9.0
R-143a	1.0	0.9	0.7	2.7/2.4 2.6
R-152a	1.1	1.0	0.9	4.0/3.6 3.8
R-123	7.9	8.8	8.8	46.5/46.4 46.5
R-142b	3.7	3.6	3.9	15.3/15.5 15.4
R-134				
AB	30.3		35.8/35.6 35.7	142/141 142
MO	37.6		42.4/42.2 42.3	186/185 186
PEMA	2.7		2.3/2.3 2.3	7.1/7.4 7.3
PEBA	1.9		2.3/2.4 2.4	8.2/8.0 8.1
PPGD	0.3		0.2/0.0 0.1	0.1/0.2 0.2
PPGBM	0.9		0.2/0.6 0.4	1.5/1.6 1.6
MPG				

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

EPDM	100 g
Zinc Oxide	5 g
Sulfur	1.5 g
Stearic Acid	1 g
TMTD	1 g
MBT	.5 g

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	5.5	5.3	5.0	24.3/23.8 24.1
R-32				
R-124	3.1	3.8	3.5	15.5/19.1 17.3
R-134a	0.9		0.7	3.7/3.8 3.8
R-125	3.8	3.6	3.6	11.5/10.9 11.2
R-143a	1.1	1.2	1.0	5.0/4.5 4.8
R-152a	1.4	1.6	1.6	5.6/5.9 5.8
R-123	14.6	14.6	14.5	79.3/79.6 79.5
R-142b	6.3	6.3	6.1	25.5/25.3 25.4
R-134				
AB	28.5		35.6/37.1 36.4	149/148 148
MO	32.0		41.7/42.6 42.2	188/188 188
PEMA	2.6		3.2/3.2 3.2	10.6/10.6 10.6
PEBA	2.2		3.4/3.3 3.4	11.1/10.9 11.0
PPGD	0.5		-0.6/-0.1 -0.4	0.3/0.6 0.5
PPGBM	0.5		-0.3/0.6 0.2	2.2/2.4 2.3
MPG				

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

EPDM	100 g
Zinc Oxide	5 g
Sulfur	1.5 g
Stearic Acid	1 g
TMTD	1 g
MBT	.5 g

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	4.4	4.9	4.5	19.0/18.5 18.8
R-32				
R-124	2.2	2.5	2.5	12.5/12.1 12.3
R-134a				
R-125	2.6	3.5	3.3	10.6/9.5 10.1
R-143a	0.8	0.7	0.6	3.4/3.4 3.4
R-152a	1.3	1.3	1.3	4.0/5.2 4.6
R-123	10.0	9.8	9.6	56.4/56.2 56.3
R-142b	4.9	5.0	5.1	19.5/19.1 19.3
R-134				
AB	28.4		35.1/34.9 35.0	143/143 143
MO	35.9		41.9/41.8 414.9	184/186 185
PEMA	2.8		2.4/2.3 25.4	7.4/7.4 7.4
PEBA	1.5		2.2/2.3 2.3	8.0/7.9 8.0
PPGD	0.2		0.2/-0.4 -0.1	0.1/0.0 0.1
PPGBM	0.4		-0.5/1.1 0.5	1.6/1.6 1.6
MPG				

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

EPDM	100 g
Zinc Oxide	5 g
Sulfur	1.5 g
Stearic Acid	1 g
TMTD	1 g
MBT	.5 g
N330 Carbon Black	40 g

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	3.1	3.4	2.8	11.3/11.2 11.3
R-32				
R-124	1.3	1.8	1.5	7.1/7.1 7.1
R-134a	0.2		0.7	1.5/1.7 1.6
R-125	1.7	2.6	2.5	7.4/7.4 7.4
R-143a	0.8	0.6	0.4	2.1/1.9 2.0
R-152a	1.0	1.0	0.8	3.5/2.6 3.1
R-123	6.5	6.3	6.5	32.6/32.4 32.5
R-142b	3.8	3.8	3.4	11.1/10.9 11.0
R-134				
AB	20.6		26.8/25.3 26.1	85.8/85.6 85.7
MO	25.9		29.4/29.8 29.6	113/112 112
PEMA	0.6		1.3/1.5 1.4	5.3/5.3 5.3
PEBA	1.5		1.8/1.5 1.7	5.4/5.7 5.6
PPGD	0.3		0.4/0.5 0.5	0.3/0.2 0.3
PPGBM	0.6		1.1/0.0 0.6	1.3/1.2 1.3
MPG				

PEMA - Pentaerythritol Ester Mixed Acid
PEBA - Pentaerythritol Ester Branched Acid
PPGBM - Polypropylene Glycol Butyl Monoether

MPG - Modified Polyglycol
PPGD - Polypropylene Glycol Diol
AB - Alkyl Benzene

EPDM	100 g
Zinc Oxide	5 g
Stearic Acid	1 g
Dicumyl Peroxide	1 g

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	4.3	4.3	4.0	19.7/19.8 19.8
R-32				
R-124	2.4	2.5	2.4	12.8/12.3 12.6
R-134a	0.5	0.6	0.6	2.2/2.2 2.2
R-125	2.6	3.1	2.7	9.8/8.7 9.3
R-143a	0.7	0.8	0.8	3.2/3.1 3.2
R-152a	1.3	1.1	1.2	4.5/4.2 4.4
R-123	9.9	10.1	9.9	55.4/55.5 55.5
R-142b	4.7	4.7	4.4	19.1/18.6 18.8
R-134				
AB	48.5		59.0/59.5 59.3	285/286 285
MO	61.8		72.8/72.3 72.6	412/403 407
PEMA	3.0		2.6/2.5 2.6	8.7/6.8 7.8
PEBA	0.5		2.6/2.6 2.6	9.8/9.8 9.8
PPGD	0.8		0.5/0.9 0.7	1.9/1.8 1.9
PPGBM	1.0		0.7/0.9 0.8	2.5/2.4 2.5
MPG	0.5		0.1/0.2 0.2	0.9/0.8 0.8

PEMA - Pentaerythritol Ester Mixed Acid
PEBA - Pentaerythritol Ester Branched Acid
PPGBM - Polypropylene Glycol Butyl Monoether
MO - Mineral Oil

MPG - Modified Polyglycol
PPGD - Polypropylene Glycol Diol
AB - Alkyl Benzene

Formula # 85

Ingredient

pphr

Butyl/Polypropylene TPE

100

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22				
R-32				
R-124	0.4	-0.2	-1.8	-0.7/0.7 0
R-134a	0.2	0.3	0.3	2.7/2.7 2.7
R-125	1.8	2.0	2.3	10.0/8.3 9.2
R-143a	0.3	0.3	0.5	3.2/3.8 3.5
R-152a	-0.3	-0.7	-1.4	-1.5/0.1 -0.8
R-123	2.1	1.9	2.4	33.7/33.7 33.7
R-142b	0.3	-1.2	-2.4	-1.2/-0.8 -1.0
R-134				
AB	11.9		20.5/20.9 20.7	87.4/85.1 86.3
MO	16.7		25.0/25.1 25.4	114/112 113
PEMA	-2.6		-2.9/-2.9 -2.9	-6.4/-6.1 -6.3
PEBA	-2.0		-3.2/-3.5 -3.4	6.4/-6.1 0.2
PPGD	-2.8		-5.7/-5.5 -5.6	-15.9/-15.7 -15.8
PPGBM	-2.4		-5.8/-5.4 -5.6	-15.7/-14.5 -15.1
MPG	-1.6		-4.9/-4.8 -4.9	-14.7/-14.9 -14.8

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula #86

Ingredient

pphr

Chloroprene Rubber (Vendor Supplied Cured Sheets)

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	0.3	-0.6	-0.8	2.1/2.3 2.2
R-32				
R-124				
R-134a	-0.6	-1.5	-2.6	-4.8/-4.8 -4.8
R-125	-0.3	-0.9	-2.2	-4.0/-4.0 -4.0
R-143a	-0.8	-1.6	-2.5	-5.2/-5.2 -5.2
R-152a				
R-123	5.7	5.5	4.9	24.1/23.7 23.9
R-142b	0.1	-1.2	-1.5	92.2/107 99.4
R-134				
AB				
MO				
PEMA				
PEBA				
PPGD				
PPGBM				
MPG				

PEMA - Pentacrythritol Ester Mixed Acid
 PEBA - Pentacrythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula #87

Ingredient

pphr

ACN Compound (Vendor Supplied Cured Sheets)

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	23.8	23.7	23.9	118/106 112
R-32				
R-124				
R-134a	1.7	1.6	1.3	6.7/7.1 6.9
R-125	1.9	2.5	2.1	8.2/8.9 8.5
R-143a	0.7	1.3	1.3	2.6/2.7 2.7
R-152a				
R-123	42.5	40.7	39.9	238/237 238
R-142b	5.1	3.9	3.8	16.4/17.0 16.7
R-134				
AB				
MO				
PEMA				
PEBA				
PPGD				
PPGBM				
MPG				

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula #88

Ingredient

pphr

Neoprene/Synthetic Fiber Compound (Vendor Supplied Cured Sheets)

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	-0.5	0	-0.6	10.8/8.7 9.8
R-32				
R-124				
R-134a	0.5			
R-125	0.3	0.4	-0.1	9.1/7.1 8.1
R-143a	0.2	0	-0.5	5.4/3.7 4.6
R-152a				
R-123	1.3	0.7	1.1	17.7/17.5 17.6
R-142b	0	-0.3	-0.4	11.9/7.2 9.6
R-134				
AB				
MO				
PEMA				
PEBA				
PPGD				
PPGBM				
MPG				

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

DOE/CE/23810-3E

**COMPATIBILITY OF REFRIGERANTS AND LUBRICANTS
WITH
ELASTOMERS**

Supplement to
Quarterly Report

1 April 1992 - 30 June 1992

Dr. Gary R. Hamed
Robert H. Seiple

Institute/Department of Polymer Science
Polymer Science Building
University of Akron
Akron, Ohio 44325-3909

July 1992

Prepared for
The Air-Conditioning and Refrigeration Technology Institute
Under
ARTI MCLR Project Number 650-50500

This research project is supported, in whole or in part, by U.S. Department of Energy grant number DE-FG02-91CE23810: Materials Compatibility and Lubricants Research (MCLR) on CFC-Refrigerant Substitutes. Federal funding supporting this project constitutes 93.94% of allowable costs. Funding from non-government sources supporting this project consists of direct cost sharing of 6.06% of allowable costs; and in-kind contributions from the air-conditioning and refrigeration industry.

DISCLAIMER

The U.S. Department of Energy's and the air-conditioning industry's support for the Materials Compatibility and Lubricants Research (MCLR) program does not constitute an endorsement by the U.S. Department of Energy, nor by the air-conditioning and refrigeration industry, of the views expressed herein.

NOTICE

This report was prepared on account of work sponsored by the United States Government. Neither the United States Government, nor the Department of Energy, nor the Air-Conditioning and Refrigeration Technology Institute, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, expressed or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product or process disclosed or represents that its use would not infringe privately-owned rights.

COPYRIGHT NOTICE

(for journal publication submissions)

By acceptance of this article, the publisher and/or recipient acknowledges the right of the U.S. Government and the Air-Conditioning and Refrigeration Technology Institute, Inc. (ARTI) to retain a nonexclusive, royalty-free license in and to any copyrights covering this paper.

TABLE OF CONTENTS

APPENDIX B	GAS CHROMATOGRAPHY DATA ON REFRIGERANTS	98-108
APPENDIX C	FTIR DATA ON REFRIGERANTS & LUBRICANTS	109-125
APPENDIX D	TGA ANALYSIS OF ELASTOMERS	126-186
APPENDIX E	ODR CURVES-ELASTOMERS	187-236

APPENDIX B

GAS CHROMATOGRAPHY DATA
ON REFRIGERANTS

Gas Chromatography Analysis

Method Parameters

Detector	FID
Detector Temp (°C)	275
Injector Mode	Splitless
Injector Temp (°C)	50
Column Type	Restek RXT-1
Length	100 m
ID	0.25 mm, 1 um df
Initial Column Temp (°C)	30
Column Hold	70 min
Final Column Temp	150
Column Flow (linear cm/s)	4
Injection Volume (ul)	10 (vapor)

The following retention times were observed:

<u>Sample</u>	<u>Retention Time</u> <u>(minutes)</u>
R-125	50.74
R-32	51.04
R-143a	51.58
R-134a	52.41
R-152a	53.53
R-22	54.95
R-124	57.81
R-142b	59.74
R-123	57.66*

* Isothermal 120 °C.

The GC chromatograms are included for your reference.

CHART SPEED 0.1 CM/MIN
ATTEN: 16 ZERO: 5% 5 MIN/TICK

CHANNEL: 1A - 1

TITLE:

R-125

12:17 10 JUL 92

SAMPLE:

METHOD: FREON

CALCULATION: AX - ANALYS - OP

PEAK NO	PEAK NAME	RESULT AREA%	TIME (MIN)	AREA COUNTS	SEP CODE
1		0.2809	0.107	5003	BB
2		0.1407	21.968	2505	BV
3		0.0430	22.037	766	VB
4		0.1339	38.165	2385	BB
5		0.0399	40.947	710	BB
6		99.1081	50.744	1765097	BV
7		0.0148	51.385	263	T
8		0.2387	62.152	4252	BB

TOTALS: 100.0000

1780981

DIVISOR: 1.00000

AMT STD:

1.00000

MULTIPLIER:

1.00000

CHART SPEED 0.1 CM/MIN
ATTEN: 16 ZERO: 5% 5 MIN/TICK

CHANNEL: 1A - 1 TITLE: R-32 14:23 10 JUL 92

SAMPLE: METHOD: FREON CALCULATION: A% - ANALYS - OP

PEAK NO	PEAK NAME	RESULT AREA%	TIME (MIN)	AREA COUNTS	SEP CODE
1		99.9772	51.036	997582	BV
2		0.0227	51.712	227	T

TOTALS: 100.0000 997809

DIVISOR: 1.00000 AMT STD: 1.00000 MULTIPLIER: 1.00000

INSTRUMENT ERRORS:
COL TEMP

CHART SPEED 0.1 CM/MIN
ATTEN: 16 ZERO: 5% 5 MIN/TICK

CHANNEL: 1A - 1 TITLE: R-143a 11:05 9 JUL 92

SAMPLE: METHOD: FREON CALCULATION: AX - ANALYS - OP

PEAK NO	PEAK NAME	RESULT AREA%	TIME (MIN)	AREA COUNTS	SEP CODE
1		0.1367	0.168	8042	88
2		0.0263	13.832	1545	88
3		0.0186	20.292	1097	88
4		0.0093	36.175	550	88
5		0.0142	42.646	833	88
6		99.7949	51.579	5872498	88

TOTALS: 100.0000 5884565

DIVISOR: 1.000000 AMT STD: 1.00000 MULTIPLIER: 1.00000

CHART SPEED 0.1 CM/MIN
ATTEN: 16 ZERO: 5% 5 MIN/TICK

CHANNEL: 1A - 1 TITLE: R-134a 15:07 9 JUL 92

SAMPLE: METHOD: FREON CALCULATION: AX - ANALYS - OP

PEAK NO	PEAK NAME	RESULT AREA%	TIME (MIN)	AREA COUNTS	SEP CODE
1		0.2049	0.156	8269	BB
2		1.0955	21.060	44214	BV
3		0.9334	21.119	37669	VB
4		0.0714	22.779	2881	BB
5		0.0597	23.505	2410	BB
6		97.6265	52.406	3940044	BV
7		0.0086	53.194	346	T

TOTALS: 100.0000 4035833

DIVISOR: 1.00000 AMT STD: 1.00000 MULTIPLIER: 1.00000

CHART SPEED 0.1 CM/MIN
ATTEN: 16 ZERO: 5% 5 MIN/TICK

CHANNEL: 1A - 1

TITLE:

R-152a

10:25 10 JUL 92

SAMPLE:

METHOD: FREON

CALCULATION: A% - ANALYS - OP

PEAK NO	PEAK NAME	RESULT AREA%	TIME (MIN)	AREA COUNTS	SEP CODE
1		0.1097	0.161	6300	BB
2		0.0248	16.201	1423	BB
3		0.0775	17.655	4448	BB
4		0.0842	34.549	4833	BV
5		0.0765	34.802	4393	VV
6		0.0238	34.889	1364	VB
7		0.0442	36.796	2538	BB
8		0.0377	49.716	2164	BB
9		0.0406	52.745	2331	BV
10		99.4810	53.533	5711357	VB

TOTALS: 100.0000 5741151

DIVISOR: 1.00000

AMT STD: 1.00000

MULTIPLIER: 1.00000

CHART SPEED 0.1 CM/MIN
ATTEN: 16 ZERO: 5% 5 MIN/TICK

CHANNEL: 1A - 1 TITLE: R-22 12:50 9 JUL 92

SAMPLE: METHOD: FREON CALCULATION: A% - ANALYS - OP

PEAK NO	PEAK NAME	RESULT AREA%	TIME (MIN)	AREA COUNTS	SEP CODE
1		0.4898	0.189	9187	BB
2		99.5102	54.948	1866558	BB

TOTALS: 100.0000 1875745

DIVISOR: 1.00000 AMT STD: 1.00000 MULTIPLIER: 1.00000

CHART SPEED 0.1 CM/MIN
ATTEN: 16 ZERO: 5% 5 MIN/TICK

CHANNEL: 1A - 1 TITLE: R-124 14:31 9 JUL 92

SAMPLE: METHOD: FREON CALCULATION: AX - ANALYS - OP

PEAK NO	PEAK NAME	RESULT AREA%	TIME (MIN)	AREA COUNTS	SEP CODE
1		0.1019	0.165	4110	BB
2		99.8981	57.810	4030831	BB
TOTALS:		100.0000		4034941	

DIVISOR: 1.00000 AMT STD: 1.00000 MULTIPLIER: 1.00000

INSTRUMENT ERRORS:
COL TEMP

CHART SPEED 0.1 CM/MIN
ATTEN: 16 ZERO: 5% 5 MIN/TICK

CHANNEL: 1A - 1 TITLE: R-142b 8:22 10 JUL 92

SAMPLE: METHOD: FREON CALCULATION: AX - ANALYS - OP

PEAK NO	PEAK NAME	RESULT AREA%	TIME (MIN)	AREA COUNTS	SEP CODE
1		0.1052	0.174	8025	BB
2		0.0200	1.608	1526	BV
3		0.0507	1.724	3863	VB
4		0.0449	4.914	3424	BB
5		0.0842	52.264	6419	BB
6		98.9254	59.745	7543271	BB
7		0.0800	65.938	6097	BB
8		0.0532	66.547	4053	BV
9		0.1094	66.585	8343	VB
10		0.3688	67.609	28121	BB
11		0.1583	78.190	12073	BB

TOTALS: 100.0000 7625215

DIVISOR: 1.00000 AMT STD: 1.00000 MULTIPLIER: 1.00000

CHART SPEED 0.1 CM/MIN
ATTEN: 16 ZERO: 5% 5 MIN/TICK

108

CHANNEL: 1A - 1 TITLE: R-123 18:01 12 JUL 92
SAMPLE: METHOD: FREON CALCULATION: AX - ANALYS - OP

PEAK NO	PEAK NAME	RESULT AREA%	TIME (MIN)	AREA COUNTS	SEP CODE
1		0.0034	0.195	2505	BV
2		0.0034	0.244	2507	VB
3		0.0075	10.170	5524	BB
4		0.0013	10.709	960	BV
5		0.0038	10.755	2810	VB
6		0.0042	18.234	3105	BB
7		0.0042	33.288	3063	BB
8		0.0089	38.796	6600	BB
9		0.0070	51.540	5189	BB
10		99.7328	57.655	73564064	BB
11		0.0290	60.661	21410	BB
12		0.0079	62.399	5840	BV
13		0.0049	62.465	3592	VB
14		0.0051	64.787	3777	BB
15		0.0439	66.301	32413	BV
16		0.0229	66.546	16896	VV
17		0.0146	66.713	10793	VV
18		0.0138	67.479	10200	VB
19		0.0128	82.548	9453	BB
20		0.0215	90.525	15851	BV
21		0.0174	90.832	12847	VV
22		0.0101	91.240	7426	VV
23		0.0107	91.501	7925	VV
24		0.0086	91.923	6366	VB

TOTALS: 100.0000 73761120

APPENDIX C

**FTIR DATA ON REFRIGERANTS
AND LUBRICANTS**

R-22

R-32

R-123

R-124

R-125

R-134A

R-142B

R-143A

R-152A

EMKAROX VG32

EMKARATE RL244

POLYGLYCOL

EMERY 2927 - A ISO 32

BRL 150

APPENDIX D
TGA ANALYSIS OF ELASTOMERS

Sample: #1: UNFILLED
Size: 22.0550 mg
Method: TGA

TGA

File: C:TGA.04
Operator: SKL
Run Date: 6-May-92 11:22

Comment: HEAT BY 20°C/MIN UPTO 800°C IN N2

Sample: #2: FILLED

Size: 23.2780 mg

Method: TGA

Comment: RM TO 600°C BY 20°C/MIN IN N2 THEN SWITCHED TO AIR

TGA

File: C:TGA.05

Operator: SKL

Run Date: 6-May-92 14:17

Sample: #3: UNFILLED
Size: 23.4170 mg
Method: TGA
Comment: HEAT BY 20°C/MIN UPTO 800°C IN N2

TGA

File: C:TGA.06
Operator: SKL
Run Date: 6-May-92 15:58

Sample: #4 FILLED
Size: 21.1020 mg
Method: TGA
Comment: HEAT BY 20°C/MIN UPTO 600 °C IN N2 THEN SWITCHED TO AIR

TGA

File: C:TGA.66
Operator: SKL
Run Date: 1-Jun-92 13:47

Sample: #5 FILLED
Size: 24.0340 mg
Method: TGA

TGA

File: C:TGA.68
Operator: SKL
Run Date: 2-Jun-92 10:00
Comment: HEAT BY 20°C/MIN UPTO 600 °C IN N2 THEN SWITCHED TO AIR

Sample: #6 UNFILLED

Size: 21.7670 mg

Method: TGA

Comment: HEAT BY 20°C/MIN UPTO 800°C IN N2

TGA

File: C:TGA.16

Operator: SKL

Run Date: 18-May-92 10:30

Sample: #7 UNFILLED
Size: 21.9250 mg
Method: TGA
Comment: HEAT BY 20°C/MIN UPTO 800°C IN N2

TGA

File: C:TGA.38
Operator: SKL
Run Date: 22-May-92 10:12

Sample: #8 FILLED
Size: 20.7900 mg
Method: TGA
Comment: HEAT BY 20°C/MIN UPTO 600 °C IN N2 THEN SWITCHED TO AIR

TGA

File: C:TGA.53
Operator: SKL
Run Date: 28-May-92 11:12

Sample: #9 UNFILLED
Size: 22.3140 mg
Method: TGA
Comment: HEAT BY 20°C/MIN UPTO 800°C IN N2

TGA

File: C:TGA.17
Operator: SKL
Run Date: 18-May-92 13:27

Sample: #10 FILLED
Size: 21.7540 mg
Method: TGA

File: C:TGA.54

Operator: SKL

Run Date: 28-May-92 12:19

Comment: HEAT BY 20°C/MIN UPTO 600 °C IN N2 THEN SWITCHED TO AIR

TGA

Sample: #11 UNFILLED
Size: 20.4270 mg
Method: TGA
Comment: HEAT BY 20°C/MIN UPTO 800°C IN N2

TGA

File: C:TGA.39
Operator: SKL
Run Date: 22-May-92 12:15

Sample: #12 FILLED

Size: 18.6150 mg

Method: TGA

Comment: HEAT BY 20°C/MIN UPTO 600 °C IN N2 THEN SWITCHED TO AIR

File: C:TGA.56

Operator: SKL

Run Date: 28-May-92 15:34

TGA

Sample: #13 UNFILLED
Size: 23.8180 mg
Method: TGA

TGA

File: C:TGA.62
Operator: SKL
Run Date: 29-May-92 16:37

Comment: HEAT BY 20°C/MIN UPTO 800 °C IN N2

Sample: #14 FILLED
Size: 22.0670 mg
Method: TGA

TGA

File: C:TGA.61
Operator: SKL
Run Date: 29-May-92 14:39
Comment: HEAT BY 20°C/MIN UPTO 600 °C IN N2 THEN SWITCHED TO AIR

Sample: #15 UNFILLED
Size: 21.0580 mg
Method: TGA
Comment: HEAT BY 20°C/MIN UPTO 800°C IN N2

TGA

File: C:TGA.70
Operator: SKL
Run Date: 9-Jun-92 10:00

Sample: #16 UNFILLED

Size: 19.7240 mg

Method: TGA

Comment: HEAT BY 20°C/MIN UPTO 800°C IN N2

TGA

File: C:TGA.71

Operator: SKL

Run Date: 9-Jun-92 11:14

Sample: #17 UNFILLED
Size: 25.0910 mg
Method: TGA

TGA

File: C:TGA.40
Operator: SKL
Run Date: 22-May-92 13:24

Comment: HEAT BY 20°C/MIN UPTO 800°C IN N2

Sample: #18 UNFILLED
Size: 21.5010 mg
Method: TGA

TGA

File: C:TGA.42
Operator: SKL
Run Date: 22-May-92 15:46

Comment: HEAT BY 20°C/MIN UPTO 800°C IN N2

Sample: #19 UNFILLED
Size: 18.0420 mg
Method: TGA
Comment: HEAT BY 20°C/MIN UPTO 800 °C IN N2

File: C:TGA.43
Operator: SKL
Run Date: 26-May-92 09:42

TGA

Sample: #20 UNFILLED

Size: 21.2650 mg

Method: TGA

Comment: HEAT BY 20°C/MIN UPTO 800 °C IN N2

TGA

File: C:TGA.44

Operator: SKL

Run Date: 26-May-92 10:53

Sample: #21 FILLED
Size: 17.3340 mg
Method: TGA

TGA

File: C:TGA.87
Operator: SKL
Run Date: 17-Jun-92 08:54
Comment: HEAT BY 20°C/MIN UPTO 600°C IN N2 THEN SWITCH TO AIR

Sample: #22 FILLED

Size: 20.0410 mg

Method: TGA

Comment: HEAT UPTO 600°C BY 20°C/MIN IN N2 THEN SWITCH TO AIR

File: C:TGA.98

Operator: SKL

Run Date: 24-Jun-92 10:42

TGA

Sample: #24 FILLED
Size: 20.2860 mg
Method: TGA

TGA

File: C:TGA.89
Operator: SKL
Run Date: 17-Jun-92 15:04
Comment: HEAT BY 20°C/MIN IN N2 AND SWITCH TO AIR @ 600°C

Sample: #29 UNFILLED

Size: 23.3690 mg

Method: TGA

Comment: HEAT BY 20°C/MIN UPTO 800 °C IN N2

TGA

File: C:TGA.45

Operator: SKL

Run Date: 26-May-92 13:10

Sample: #30 FILLED
Size: 25.9760 mg
Method: TGA

TGA

File: C:TGA.58
Operator: SKL
Run Date: 29-May-92 09:34
Comment: HEAT BY 20°C/MIN UPTO 600 °C IN N2 THEN SWITCHED TO AIR

Sample: #31 UNFILLED
Size: 34.6690 mg
Method: TGA
Comment: HEAT UPTO 800°C BY 20°C/MIN IN N2

TGA

File: C:TGA.92
Operator: SKL
Run Date: 18-Jun-92 16:43

Sample: #34 FILLED
Size: 22.8680 mg
Method: TGA

TGA

File: C:TGA.72
Operator: SKL
Run Date: 9-Jun-92 13:04
Comment: HEAT BY 20°C/MIN UPTO 600°C IN N2 THEN SWITCHED TO AIR

Sample: #35 FILLED
Size: 18.9220 mg
Method: TGA

TGA

File: C:TGA.75
Operator: SKL
Run Date: 10-Jun-92 09:41
Comment: HEAT BY 20°C/MIN UPTO 600°C IN N2 THEN SWITCHED TO AIR

Sample: #36 FILLED
Size: 16.4860 mg
Method: TGA

TGA

File: C:TGA.76
Operator: SKL
Run Date: 10-Jun-92 10:58
Comment: HEAT BY 20°C/MIN UPTO 600°C IN N2 THEN SWITCHED TO AIR

Sample: #37 FILLED
Size: 23.3930 mg
Method: TGA
Comment: HEAT BY 20°C/MIN UPTO 600°C IN N2 THEN SWITCH TO AIR

TGA

File: C:TGA.79
Operator: SKL
Run Date: 11-Jun-92 08:51

Sample: #38 FILLED
Size: 23.3280 mg
Method: TGA

File: C:TGA.80
Operator: SKL
Run Date: 11-Jun-92 10:05

Comment: HEAT BY 20°C/MIN UPTO 600°C IN N2 THEN SWITCH TO AIR

Sample: #39 FILLED
Size: 21.4480 mg
Method: TGA

File: C:TGA.81
Operator: SKL
Run Date: 11-Jun-92 13:24
Comment: HEAT BY 20°C/MIN UPTO 600°C IN N2 THEN SWITCH TO AIR

TGA

Sample: #41 UNFILLED
Size: 21.1740 mg
Method: TGA
Comment: HEAT BY 20°C/MIN IN N2 UPTO 800°C

TGA

File: C:TGA.18
Operator: SKL
Run Date: 18-May-92 14:37

Sample: #42 UNFILLED

Size: 24.3960 mg

Method: TGA

Comment: HEAT BY 20°C/MIN IN N2 UPTO 800°C

TGA

File: C:TGA.26

Operator: SKL

Run Date: 20-May-92 11:13

Sample: #43 UNFILLED
Size: 29.5880 mg
Method: TGA
Comment: HEAT BY 20°C/MIN IN N2 UPTO 800°C

TGA

File: C:TGA.27
Operator: SKL
Run Date: 20-May-92 12:28

Sample: #44 UNFILLED
Size: 28.1160 mg
Method: TGA
Comment: HEAT BY 20°C/MIN IN N2 UPTO 800°C

TGA

File: C:TGA.28
Operator: SKL
Run Date: 20-May-92 14:13

Sample: #45 UNFILLED
Size: 18.3950 mg
Method: TGA
Comment: HEAT BY 20°C/MIN UPTO 800 °C IN N2

TGA

File: C:TGA.46
Operator: SKL
Run Date: 26-May-92 15:50

Sample: #46 UNFILLED
Size: 21.9470 mg
Method: TGA
Comment: HEAT BY 20°C/MIN UPTO 800°C IN N2

TGA

File: C:TGA.24
Operator: SKL
Run Date: 19-May-92 15:32

Sample: #48 UNFILLED
Size: 18.1320 mg
Method: TGA

Comment: HEAT BY 20°C/MIN UPTO 800 °C IN N2

File: C:TGA.48
Operator: SKL
Run Date: 27-May-92 10:12

TGA

Sample: #49 FILLED
Size: 22.8650 mg
Method: TGA
Comment: HEAT BY 20°C/MIN UPTO 600 °C IN N2 THEN SWITCHED TO AIR

TGA

File: C:TGA.63
Operator: SKL
Run Date: 30-May-92 11:09

Sample: #50 FILLED
Size: 25.0840 mg
Method: TGA

TGA

File: C:TGA.64
Operator: SKL
Run Date: 1-Jun-92 09:49
Comment: HEAT BY 20°C/MIN UPTO 600 °C IN N2 THEN SWITCHED TO AIR

Sample: #51 FILLED
Size: 19.2750 mg
Method: TGA

File: C:TGA.65
Operator: SKL

Run Date: 1-Jun-92 11:15

Comment: HEAT BY 20°C/MIN UPTO 600 °C IN N2 THEN SWITCHED TO AIR

Sample: #67 FILLED
Size: 16.1690 mg
Method: TGA

TGA

File: C:TGA.82
Operator: SKL
Run Date: 12-Jun-92 09:16
Comment: HEAT BY 20°C/MIN UPTO 600°C IN N2 THEN SWITCH TO AIR

Sample: #68 FILLED
Size: 20.8470 mg
Method: TGA

TGA

File: C:TGA.83
Operator: SKL
Run Date: 12-Jun-92 10:27
Comment: HEAT BY 20°C/MIN UPTO 600°C IN N2 THEN SWITCH TO AIR

Sample: #71 FILLED
Size: 28.7220 mg
Method: TGA
Comment: HEAT BY 20°C/MIN UPTO 600°C IN N2 THEN SWITCH TO AIR

TGA

File: C:TGA.84
Operator: SKL
Run Date: 12-Jun-92 13:20

Sample: #72 UNFILLED

Size: 19.2330 mg

Method: TGA

Comment: HEAT BY 20°C/MIN UPTO 800 °C IN N2

TGA

File: C:TGA.47

Operator: SKL

Run Date: 27-May-92 09:04

Sample: #73 UNFILLED
Size: 18.7410 mg
Method: TGA
Comment: HEAT BY 20°C/MIN UPTO 800 °C IN N2

TGA

File: C:TGA.49
Operator: SKL
Run Date: 27-May-92 12:06

Sample: #74 FILLED
Size: 19.6710 mg
Method: TGA

TGA

File: C:TGA.59
Operator: SKL

Run Date: 29-May-92 11:02
Comment: HEAT BY 20°C/MIN UPTO 600 °C IN N2 THEN SWITCHED TO AIR

Sample: #75 UNFILLED
Size: 22.8370 mg
Method: TGA
Comment: HEAT UPTO 800°C BY 20°C/MIN IN N2

TGA

File: C:TGA.97
Operator: SKL
Run Date: 23-Jun-92 13:14

Sample: #76 FILLED
Size: 16.3870 mg
Method: TGA

TGA

File: C:TGA.96
Operator: SKL
Run Date: 19-Jun-92 15:27
Comment: HEAT UPTO 600°C BY 20°C/MIN IN N2 AND SWITCH TO AIR

Sample: #77 UNFILLED
Size: 22.2080 mg
Method: TGA

TGA

File: C:TGA.78
Operator: SKL
Run Date: 10-Jun-92 14:19

Comment: HEAT BY 20°C/MIN UPTO 800°C IN N2

Sample: #80 UNFILLED
Size: 20.6570 mg
Method: TGA
Comment: RM TO 600°C BY 20°C/MIN IN N2 THEN SWITCHED TO AIR

TGA

File: C:TGA.13
Operator: SKL
Run Date: 12-May-92 13:22

Sample: #81 UNFILLED
Size: 22.5130 mg
Method: TGA
Comment: RM TO 600°C BY 20°C/MIN IN N2 THEN SWITCHED TO AIR

TGA

File: C:TGA.11
Operator: SKL
Run Date: 11-May-92 14:13

Sample: #82 UNFILLED

Size: 21.6550 mg

Method: TGA

Comment: RM TO 600°C BY 20°C/MIN IN N2 THEN SWITCHED TO AIR

File: C:TGA.12

Operator: SKL

Run Date: 11-May-92 15:59

TGA V5.1A DuPont 2000

Sample: #83 FILLED
Size: 26.4400 mg
Method: TGA

TGA

File: C:TGA.60
Operator: SKL
Run Date: 29-May-92 13:15
Comment: HEAT BY 20°C/MIN UPTO 600 °C IN N2 THEN SWITCHED TO AIR

Sample: #84 UNFILLED

Size: 20.3160 mg

Method: TGA

Comment: HEAT BY 20°C/MIN UPTO 800 °C IN N2

TGA

File: C:TGA.52

Operator: SKL

Run Date: 27-May-92 16:23

Sample: #85 UNFILLED
Size: 21.0240 mg
Method: TGA

TGA

File: C:TGA.51
Operator: SKL
Run Date: 27-May-92 15:24

Comment: HEAT BY 20°C/MIN UPTO 800 °C IN N2

Sample: #86 FILLED

Size: 18.3850 mg

Method: TGA

Comment: HEAT UPTO 600°C BY 20°C/MIN IN N2 AND SWITCH TO AIR

File: C:TGA.93

Operator: SKL

Run Date: 19-Jun-92 09:46

TGA

Sample: #87 FILLED
Size: 18.4640 mg
Method: TGA
Comment: HEAT UPTO 600°C BY 20°C/MIN IN N2 AND SWITCH TO AIR

TGA

File: C:TGA.94
Operator: SKL
Run Date: 19-Jun-92 10:51

Sample: #88 FILLED
Size: 30.7000 mg
Method: TGA
Comment: HEAT UPTO 600°C BY 20°C/MIN IN N2 AND SWITCH TO AIR

File: C:TGA.95
Operator: SKL
Run Date: 19-Jun-92 14:10

TGA

APPENDIX E

ODR CURVES-ELASTOMERS

Monsanto ODR

60 Minute Chart Motor
100 Range Selector

Stock: Polyisoprene
3 Degree Arc

Formulation # 1
Operator: P. Greene

Temperature: 300F

Monsanto ODR

60 Minute Chart Motor
100 Range Selector

Stock: Polyisoprene
3 Degree Arc

Formulation # 2
Operator: P. Greene

Temperature: 300F

Monsanto ODR

60 Minute Chart Motor
100 Range Selector

Stock: Polyisoprene
3 Degree Arc

Formulation # 3
Operator: P. Greene

Temperature: 300°F

Monsanto ODR

60 Minute Chart Motor
100 Range Selector

Stock: Poly(chlorobutadiene)
3 Degree Arc

Formulation # 4
Operator: P. Greene

Temperature: 307F

Monsanto ODR

60 Minute Chart Motor
100 Range Selector

Stock: Poly(chlorobutadiene)
3 Degree Arc

Formulation # 5
Operator: P. Greene

Temperature: 307F

Monsanto ODR

60 Minute Chart Motor
100 Range Selector

Stock: Isobutyl isoprene
3 Degree Arc

Formulation # 6
Operator: P. Greene

Temperature: 320F

Monsanto ODR

60 Minute Chart Motor
100 Range Selector

Stock: Isobutyl isoprene
3 Degree Arc

Formulation # 7
Operator: P. Greene

Temperature: 320°F

Monsanto ODR

60 Minute Chart Motor
100 Range Selector

Stock: Isobutyl isoprene
3 Degree Arc

Formulation # 8
Operator: P. Greene

Temperature: 320°F

Monsanto ODR

60 Minute Chart Motor
100 Range Selector

Stock: Bromobutyl
3 Degree Arc

Formulation # 9
Operator: P. Greene

Temperature: 320F

Monsanto ODR

60 Minute Chart Motor
100 Range Selector

Stock: Bromobutyl
3 Degree Arc

Formulation # 10
Operator: P. Greene

Temperature: 320°F

Monsanto ODR

60 Minute Chart Motor
100 Range Selector

Stock: Chlorobutyl
3 Degree Arc

Formulation # 11
Operator: P. Greene

Temperature: 302°F

Monsanto ODR

60 Minute Chart Motor
100 Range Selector

Stock: Chlorobutyl
3 Degree Arc

Formulation # 12
Operator: P. Greene

Temperature: 302°F

Cure time: 30.5 min.

Monsanto ODR

120 minute Chart Motor

100 Range Selector

Stock: SBR 1502

3 Degree Arc

Formulation # 13

Operator: P. Greene

Date: 3/31/92

Temperature: 293 F

Monsanto ODR

120 minute Chart Motor

100 Range Selector

Stock: SBR 1502
3 Degree Arc

Formulation # 14
Operator: P. Greene

Date: 3/31/92
Temperature: 293 F

Monsanto ODR

60 Minute Chart Motor
100 Range Selector

Stock: SBR (med styrene cont)
3 Degree Arc

Formulation # 15
Operator: P. Groene

Temperature: 320°F

Monsanto ODR

60 Minute Chart Motor
100 Range Selector

Stock: SBR (high styrene cont)
3 Degree Arc

Formulation # 16
Operator: P. Greene

Temperature: 320F

Cure time: 35 min.

Monsanto ODR

60 Minute Chart Motor
100 Range Selector

Stock: Nitrile (very high ACN)
3 Degree Arc

Formulation # 17
Operator: P. Greene

Temperature: 330F

Monsanto ODR

60 Minute Chart Motor

100 Range Selector

Stock: Nitrile (high ACN)
3 Degree Arc

Formulation # 18
Operator: P. Greene

Temperature: 330F

Monsanto ODR

60 Minute Chart Motor
100 Range Selector

Stock: Nitrile (medium ACN)
3 Degree Arc

Formulation # 19
Operator: P. Greene

Temperature: 330F

Monsanto ODR

60 Minute Chart Motor

100 Range Selector

Stock: Nitrile (low ACN)

3 Degree Arc

Formulation # 20

Operator: P. Greene

Temperature: 330F

Monsanto ODR

60 Minute Chart Motor
100 Range Selector

Stock: Nitrile (low ACN)
3 Degree Arc

Formulation # 21
Operator: P. Greene

Temperature: 330°F

Monsanto ODR

60 Minute Chart Motor
100 Range Selector

Stock: Nitrile (very high ACN)
3 Degree Arc

Formulation # 22
Operator: P. Groene

Temperature: 330°F

Monsanto ODR

60 Minute Chart Motor

200 Range Selector

Stock: Hydrogenated Nitrile

3 Degree Arc

Formulation # 24

Operator: P. Greene

Temperature: 330F

Monsanto ODR

60 Minute Chart Motor
100 Range Selector

Stock: Fluoroclastomer
3 Degrees Arc

Formulation # 29
Operator: P. Greene

Temperature: 350F

Monsanto ODR

60 Minute Chart Motor

100 Range Selector

Stock: Fluoroelastomer

3 Degree Arc

Formulation # 30

Operator: P. Greene

Temperature: 350F

Monsanto ODR

60 Minute Chart Motor
100 Range Selector

Stock: Fluoro/chloroclastomer
3 Degrees Arc

Formulation # 31
Operator: P. Greene

Temperature: 350F

Monsanto ODR

60 Minute Chart Motor
100 Range Selector

Stock: Epichlorohydrin
3 Degree Arc

Formulation # 34
Operator: P. Greene

Temperature: 320F

Monsanto ODR

60 Minute Chart Motor
100 Range Selector

Stock: Epichlorohydrin
3 Degree Arc

Formulation # 35
Operator: P. Greene

Temperature: 320F

Monsanto ODR

60 Minute Chart Motor
100 Range Selector

Stock: Epichlorohydrin
3 Degree Arc

Formulation # 36
Operator: P. Greene

Temperature: 320°F

Monsanto ODR

60 Minute Chart Motor
100 Range Selector

Stock: Epichlorohydrin
3 Degree Arc

Formulation # 37
Operator: P. Greene

Temperature: 320F

Monsanto ODR

60 Minute Chart Motor
100 Range Selector

Stock: Epichlorohydrin
3 Degrees Arc

Formulation # 38
Operator: P. Greene

Temperature: 320°F

Monsanto ODR

60 Minute Chart Motor
100 Range Selector

Stock: Epichlorohydrin
3 Degree Arc

Formulation # 39
Operator: P. Greene

Temperature: 320°F

Monsanto ODR

60 Minute Chart Motor

100 Range Selector

Stock: Silicone (high strength)

3 Degree Arc

Formulation # 41

Operator: P. Greene

Temperature: 320F

Monsanto ODR

60 Minute Chart Motor
100 Range Selector

Stock: Silicone
3 Degree Arc

Formulation # 42
Operator: P. Greene

Temperature: 320F

Monsanto ODR

60 Minute Chart Motor
100 Range Selector

Stock: Silicone
-3 Degree Arc

Formulation # 43
Operator: P. Greene

Temperature: 320F

Monsanto ODR

60 Minute Chart Motor
100 Range Selector

Stock: Fluorosilicone
3 Degree Arc

Formulation # 44
Operator: P. Greene

Temperature: 240F

Monsanto ODR

60 Minute Chart Motor
100 Range Selector

Stock: Chlorosulfonated PE
3 Degrees Arc

Formulation # 68
Operator: P. Greens

Temperature: 320F

Monsanto ODR

60 Minute Chart Motor
200 Range Selector

Stock: Chlorosulfonated PE
3 Degree Arc

Formulation # 70
Operator: P. Greene

Temperature: 320F

Monsanto ODR

60 Minute Chart Motor
100 Range Selector

Stock: EPM
3 Degree Arc

Formulation # 72
Operator: P. Greene

Temperature: 320F

Monsanto ODR

60 Minute Chart Motor
100 Range Selector

Stock: EPM
3 Degree Arc

Formulation # 73
Operator: P. Greene

Temperature: 320F

Monsanto ODR

60 Minute Chart Motor
100 Range Selector

Stock: EPM
3 Degrees Arc

Formulation # 74
Operator: P. Groene

Temperature: 320F

Monsanto ODR

60 Minute Chart Motor
100 Range Selector

Stock: Ethylene/Acrylic
3 Degree Arc

Formulation # 75
Operator: P. Groene

Temperature: 350F

Cure time: 28 min.

Monsanto ODR

60 Minute Chart Motor
200 Range Selector

Stock: Ethylene/Acrylic
3 Degree Arc

Formulation # 76
Operator: P. Greene

Temperature: 350F

Monsanto ODR

60 Minute Chart Motor
200 Range Selector

Stock: Chlorinated PE
3 Degree Arc

Formulation # 78
Operator: P. Greene

Temperature: 320F

Monsanto ODR

60 minute Chart Motor
100 Range Selector

Stock: Royalene BPDM
3 Degree Arc

Formulation # 80
Operator: P. Greene

Date: 4/1/92
Temperature: 320 F

Monsanto ODR

60 minute Chart Motor
100 Range Selector

Stock: EPDM
3 Degree Arc

Formulation # 81
Operator: P. Greene

Date: 3/30/92
Temperature: 320 F

Monsanto ODR

60 minute Chart Motor
100 Range Selector

Stock: BPDM
3 Degree Arc

Formulation # 82
Operator: P. Greene
Date: 3/30/92
Temperature: 320 F

Monsanto ODR

60 minute Chart Motor
200 Range Selector

Stock: EPDM
3 Degree Arc

Formulation # 83
Operator: P. Greene

Date: 3/31/92
Temperature: 320 F

Monsanto ODR

60 Minute Chart Motor
100 Range Selector

Stock: EPDM
3 Degree Arc

Formulation # 84
Operator: P. Greene

Temperature: 320F

END

**DATE
FILMED**

12 / 4 / 92