ROLE OF STRUCTURE IN ION MOVEMENT OF GLASSES

Progress Report

for Period January 15, 1992 to November 1, 1992

Himanshu Jain

Lehigh University
Bethlehem, Pennsylvania 18015

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

November 3, 1992

Prepared for

THE U. S. DEPARTMENT OF ENERGY
AGREEMENT NO. DE-FG02-90ER45419

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

fp

Summary of the Work Completed and in Progress
(Grant No. DE-FG02-90ER45419)
September 1992

A. PROGRESS REPORT

It is convenient to summarize the progress by dividing it into the results of three kinds of experiments and a short comment on the commonly observed dielectric loss peak in glass.

A.1. The Modified Random Network Model and Ion Movement

Having noted that the revolutionary idea contained in the MRN model is based primarily on a few EXAFS experiments on alkali silicate glasses, we decided to check the validity and universality of this concept for glasses in general. Of course, our primary interest is in how would MRN structure affect ion transport differently from Zachriassen's CRN model. So we have determined electrical transport in and the structure of the same glass samples. EXAFS and X-ray photoelectron spectroscopy (XPS) have been primarily used to characterize the structure.

So far we have studied the $x\text{Rb}_2\text{O}:(1-x)\text{GeO}_2$ and $0.2(\text{Rb},\text{Ag})_2\text{O}:0.8\text{GeO}_2$ glass series. These systems were selected because the alkali germanates are very different from silicates with regard to phase separation and, hence in the tendency to form MRN structure. Preliminary EXAFS experiments have been completed for the network former, Ge, as well as the modifier, Rb and Ag, cations around their respective K-edges. The data analysis has given the first shell bond distances for all the three cations and the second shell distance from Rb atom i.e. Rb-Ge distance. Coordination number (CN) and the degree of disorder around each species have been also determined but with relatively less accuracy. Indirectly CN around Ge has been obtained from XPS as well.

In the binary rubidium germanate series the activation energy of electrical conductivity, E , shows a characteristic maximum which has been attributed in the literature to the change in coordination

of Ge from 4-fold to 6-fold configuration. E seems to correlate rather well with the change in molar volume with composition. The Ge-O, Rb-O and Rb-Ge bond distances also vary with composition but they do not correlate so well with E. Thus it gives an impression that there is effectively a region of 'unoccupied volume' which varies with composition without affecting interatomic distances. This suggestion does not necessarily imply that there is a micro-segregation of different species in the structure. In fact, the disorder around Rb in our glasses is considerably more than reported for alkalis in the silicates. In other words, the distribution of Rb is far more random and hence homogeneous than expected from the MRN model proposed for the silicates. Therefore, it appears that the MRN model may not be equally applicable for understanding ion dynamics or any other property of different glasses. Further experiments are needed to quantitatively assess the variation of homogeneity in our glasses.

The electrical conductivity of (Rb,Ag) germanate series shows typical mixed alkali or mobile ion effect (MME) as Rb is replaced by Ag. The EXAFS results show that the replacement of Rb by Ag has the same effect on Rb-O distance and disorder around Rb as the reduction of Rb in the binary Rb-germanate series. Therefore, as far as Rb is concerned only the concentration of Rb and not the presence of Ag seem to affect its local structure. However, we can not say if this is also true for Ag ions which are more polarizable and, therefore, more susceptible to feel the presence of the other cation. To determine this we need to investigate the silver germanate binary system as well, which is part of our future plans. The Ag-O distance and disorder around Ag show composition dependence which is opposite to that of the Rb-O distance and disorder around Rb, when Ag and Rb replace each other, respectively. So the mobile ion's distance from oxygen and the disorder around it do not appear to be very important for the development of the MME.

A.2. Role of Melt Structure in Ion Transport in the Glassy State

Sodium triborate composition was selected to determine: Can a glass have memory of the structure of melt (much above T_g) from which it was prepared? To answer this question the melt was equilibrated at a high temperature, T_g (1400 C), and then quickly cooled to and annealed at a lower temperature, T_b (850 C, still in the liquid state). Glass samples were prepared, following an identical cooling procedure, from the melt kept at T_b for varying times (t). Thus if there was a variation in the properties or structure of such samples as a function of t , one should conclude that the structure of melt at T_g evolves into the structure of melt at T_b in a time comparable to the annealing time (~ seconds). From common sense any effect of melt annealing should not be observable because the viscosity relaxation time for our conditions is ~ nanoseconds.

We have measured the activation energy of conductivity (E) below T_g for varying values of annealing time (t) because it can be measured with high relative accuracy and is very sensitive to the local structure around sodium ions. To our surprise, E shows a small decrease with increasing t . The decreasing trend of E is reproducible and outside the error bars of the electrical measurements. Also it is supported by a parallel decrease in density, the total IR absorption and 'average' IR refractive index. From literature it is shown that the observed trends could not be accounted by any selective evaporation from the melt at T_b . Thus we are led to conclude that in this system there are extremely slow structural relaxations which could not be predicted from the conventional wisdom. The glassy state seems to retain the signatures of what has happened in the molten state much above T_g or even the equilibrium melting temperature! The relaxation time in glass is known to have a wide distribution. Then very likely we are seeing the effects of the very long time tail of such a distribution function.

Another unexpected phenomenon is shown by the data: the

density decreases with annealing time although its equilibrium value reported in literature increases with decreasing melt temperature. In other words, the transient variation of density with t is extremely slow as well as anomalous. H_2O and SiO_2 are well known examples where anomalous expansion has been observed, but the present observation is even more peculiar because it concerns the transient, not the equilibrium, behavior of density. A detailed analysis of the IR spectrum has revealed that the anomalous expansion occurs because of the conversion of BO_4^- units (with all bridging oxygen) to BO_3^- units (with two bridging and one non-bridging oxygen) with increasing t. The literature confirms a volume expansion associated with this conversion [1].

A.3. Ion Movement in Fluorozirconate Glass - Breakdown of Correspondence between Electrical and Nuclear Spin Relaxation

The electrical relaxation (ER) and NSR were measured on the same samples of fluorozirconate glasses with the specific objective of establishing whether or not the two techniques perceive ion movement in the same way. This has been a puzzle in the field for several years until a correspondence between ER and NSR was established for oxide glasses [2]. However, the present data on fluoride glasses has shown a new discrepancy between the two properties, as summarized below:

It is well established now that the electrical conductivity (σ) of glasses remains frequency (ω) independent at low frequencies (dc plateau) [3]. This gaussian behavior changes into an ac dispersive behavior at high frequencies, which is reasonably well described by a power law: $\sigma \sim \omega^s$. The transition from gaussian to dispersive region occurs at a frequency which is determined by the material and its temperature. Consequently, if one makes Arrhenius plot of conductivity ($\sigma.T$ vs $1/T$) at a fixed frequency (ω^*), a break in slope occurs at some temperature, T^* (see Figure [30]). Then ω^* will be the frequency representing the transition from

gaussian to dispersive region in σ vs ω plot at T^* . Now if ER and NSR perceive ion movement in the same way T^* should also be the temperature, $T_{\max}$, at which the NSR rate ($1/T_1$) becomes maximum. In the case of common oxide glasses, the $1/T_1$ is not observed generally because of low ion jump rate (i.e. conductivity). Fortunately, in the case of fluoride glasses we could readily observe this maximum. Then we discovered that T^* is significantly lower than $T_{\max}$ (see Figure). This was the first reported example of a glass in which simple correspondence between NSR and ER breaks down. Tatsumisago et al. [5] have considered this as the new discrepancy of ion dynamics in glass and shown it to be present in fast ion conducting glass as well. We have offered the following explanation for this discrepancy [6]:

First we note that both σ and $1/T_1$ at the experimental frequencies include the effects arising from ion-ion interactions. However, in our NSR experiments the ion movement relaxes nuclear spins via dipolar interactions which vary as r_{ij}^{-3} where r_{ij} is the distance between i^{th} and j^{th} moving ions. In contrast, electrical transport, which relates to diffusion via Nernst-Einstein relation, depends on mean square displacement. Thus the ion-ion interactions affect the correlation functions for NSR and ER differently. That is, although the primitive ion jump is the same, the perception of ion-ion interactions, which affects our observations, is sensitive to the technique employed.

A.4. Comment on Dielectric Loss Peak in Glasses

Finally, we pursued a question which has been debated for years and concerns the dielectric loss peak in all kinds of glasses [7-9]. This peak was attributed to some bulk relaxation process of ambiguous origin but related to dc conduction. In a previous study we showed that most of the observations in the literature could be simply from electrode polarization wherein the sample is a combination of two parallel R-C circuits [10]. However, Kim and Tomozawa [11] clearly show a bulk process independent of the electrode effects. To confirm the presence of a real bulk

phenomenon and determine its origin, two sodium silicate and one sodium-cesium silicate glasses were investigated. It is shown that much of the dielectric loss in these glasses is from the electrode effects. There is, however, some residual loss of bulk origin which can be traced simply to the so called Jonscher's universal behavior. Therefore, we conclude that there are no dipolar or any other loss mechanisms common to all glasses in addition to what is expected from the well known universal behavior of electrical relaxation. We also note that the universal behavior accounts only for a part of the frequency dispersion of conductivity of solids. A comparison of electrical relaxation in glass with that in quartz crystal has most clearly separated the so called universal relaxation found in complex systems from other mechanisms. In the remaining time of the current project we plan to use quartz as a model for determining the role of crystallinity in ion dynamics.

A.5 References

1. A. Karki, S. Feller, H.P.Lim, J.Stark, C.Sanchez and M. Shibata, J. Non-cryst. Solids 92(1987)11.
2. (a) R. Kuchler, O. Kanert, S. Ruckstein and H. Jain, J. Non-cryst. Solids 128(1991)328.
(b) M. Trunnell, D. R. Torgeson, S.W. Martin and F. Borsa, J. Non-cryst. Solids 139(1992)257.
3. H. Jain, J. Non-cryst. Solids 131(1991)961.
4. O. Kanert, R. Kuchler, S. Estalji, K.L. Ngai and H. Jain in: Physics of Non-cryst. Solids, L.D.Pye et al., eds., Taylor and Francis, 1992. p. 178.
5. M. Tatsumisago, C. A. Angell and S.W. Martin, J. Chem. Phys. In press.
6. R. Kuchler, R. Bolter, O. Kanert, H. Jain and K.L. Ngai in: Proc. Int. Conf. Defects Insul. Mater., Nordkirchen, Germany. In press.
7. M. Tomozawa in: Treat. Mater. Sci. Eng., vol 12, M.Tomozawa and R. Doremus, eds., Academic Press, 1977. p. 283.
8. H. Namikawa, J. Non-cryst. Solids 18(1975)173.

9. M. D. Ingram, Phys. Che. Glass. 28(1987)215.
10. W. K. Lee, S. Aronson-Unger, A.S. Nowick and H. Jain, J. Non-cryst. Solids 122(1990)197.
11. C. Kim and M. Tomozawa, J. Am. ceram. Soc. 59(1976)127.

B. LIST OF PUBLICATIONS ACKNOWLEDGING THE CURRENT GRANT

- I. Ion Movement Relaxation in Inorganic Glasses - Salient Features. H. Jain, J. Non-cryst. Solids, 131 (1991) 961. (Invited Contribution) (Received the best paper presentation award at International Meeting Relaxation in Complex Systems, Crete, Greece, 1990.)
- II. X-ray Photoelectron Spectroscopy for Understanding Ionic Conduction in Glasses. H. Jain, C.H. Hsieh and O. Kanert, Trans. Ind. Cer. Soc. 50 (1991) 14. (Invited Contribution)
- III. Nuclear Spin Relaxation in Fluorozirconate Glass. O. Kanert, R. Kuchler, S. Estalji, K.L. Ngai and H. Jain, The Physics of Non-crystalline Solids, L.D. Pye et al. eds., Taylor and Francis, 1992. p. 178.
- IV. On the Nature of Bulk Electrical Relaxation in Silicate Glasses. W.K. Lee, S. Aronson-Unger, J.F. Liu, A.S. Nowick and H. Jain, *ib.id.* p.332
- V. Nuclear Magnetic Resonance and Ionic Motion in Fluorozirconate Glasses. S. Estalji, R. Kuchler, O. Kanert, R. Bolter, H. Jain and K.L. Ngai, J. Physique, Pt IV, in press.
- VI. Ionic Motion in Inorganic Glasses. H. Jain and O. Kanert, Proc. Int. Conf. Def. Insulating Materials, Germany, 1992, in press. (Invited Contribution)
- VII. Study of Ionic Motion in Fluorozirconate Glasses by NSR and Electrical Conductivity. S. Estalji, R. Kuchler, O. Kanert, R. Bolter, H. Jain and K. L. Ngai, *ibid.* in press, 1992.
- VIII An Explanation of Significant Differences between NSR and Conductivity Relaxation. R. Kuchler, R. Bolter, O. Kanert, H. Jain and K.L. Ngai, *ibid.* in press, 1992.
- IX. Measurement of Electrical Conductivity of Glasses. H. Jain, Trans. Am. Ceram. Soc., in press, 1992. (Invited Contribution)
- X. Anomalous Expansion of Sodium Triborate Melt and its Effect on Glass Properties. W. C. Huang, H. Jain, E. I. Kamitsos and A. P. Patsis, submitted to J. Non-cryst. Solids, 1992.

Figure: Fluorine NSR rate in the rotating frame, and electrical conductivity at the same frequency of 28 kHz for a fluorozirconate glass.

END

**DATE
FILMED**

12 / 3 / 92