FINAL REPORT

DIRECT CONVERSION OF LIGHT HYDROCARBON
GASES TO LIQUID FUEL

Report No. 33

May 16, 1992

Project Manager: R. D. Kaplan

Principal Investigator: M. J. Foral

Work performed under Contract No. DE-AC22-89PC89866

For

U. S. Department of Energy
Pittsburgh Energy Technology Center
Pittsburgh, Pennsylvania

By

Amoco Oil Company
Research & Development Department
Post Office Box 3011
Naperville, IL 60566

FINAL REPORT SUBMITTED TO:

1. George Cinquegrane (5 copies)
Contracting Officer's Representative
U.S. DOE/PETC
P.O. Box 10940
Pittsburgh, PA 15236
2. Dona G. Sheehan
Contract Specialist
U.S. DOE/PETC
P.O. Box 10940
Pittsburgh, PA 15236
3. Robert M. Hamilton
FE-231, E-155/GTN
U.S. Department of Energy
Washington, DC 20545
4. U.S. Department of Energy (3 copies)
Office of Technology Transfer, MS 58-M217
Pittsburgh Energy Technology Center
P.O. Box 10940
Pittsburgh, PA 15236
5. Joanne Wastek
Project Management Assistant
U.S. DOE/PETC, MS 922-H
P.O. Box 10940
Pittsburgh, PA 15236
6. Gilbert V. McGurl
Program Manager
U.S. DOE/PETC, MS 922-H
P.O. Box 109940
Pittsburgh, PA 15236

ADDITIONAL CIRCULATION OF FINAL REPORTS TO:

Amoco Corporation
Suite 600
305 East Shuman Boulevard
Naperville, IL 60563-8408
T. H. Fleisch

Amoco Oil Company
P.O. Box 3011
Naperville, IL 50566
R. D. Kaplan, H-4
M. J. Foral, H-4
A. R. LaPuma, H-4
D. W. Washecheck, H-2
A. S. Couper, H-1
F. W. Hauschildt, H-3

TABLE OF CONTENTS

	<u>Page</u>
LIST OF FIGURES	6
EXECUTIVE SUMMARY	11
OBJECTIVE	15
INTRODUCTION	15
PROJECT OVERVIEW	16
PREVIOUS WORK	17
EXPERIMENTAL EQUIPMENT AND PROCEDURES	18
RESULTS AND DISCUSSION	20
Task 3.1: Comparison of Previous Data With Los Alamos Kinetic Model	20
Task 3.2: Process Variable Studies	21
1. Effect of Hydrocarbon Feed Composition .	21
2. Effect of Oxygen Concentration	22
3. Effect of Temperature	24
4. Effect of Pressure	25
5. Effect of Residence Time	25
Task 3.3: Study of Different Feed Injection Systems ...	26
1. Effect of Mixer Configuration	27
2. Effect of Reaction Modifiers	28
A. Addition of Steam and Acetone	28
B. Addition of Nitrous Oxide	30
Task 3.4: Effect of Product Quench	31

TABLE OF CONTENTS (continued)

	<u>Page</u>
Task 3.5: Effect of Reactor Design	32
1. Reactor Diameter Experiments	32
A. Temperature Effects	33
B. Oxygen Concentration Effects	34
2. Plug Flow Internals	35
Task 3.6: Effect of Reactor Recycle	36
1. Effect of Added CO ₂	36
2. Effect of Added H ₂	37
3. Effect of Added CO	38
4. Effect of Added CO/H ₂ Mixture	39
Task 3.7: Enhanced Yield Catalyst Study	40
CONCLUSIONS	43
ACKNOWLEDGEMENT	45
REFERENCES	46
FIGURES	47
APPENDIX A: Statistical Data Adjustment Procedure	84
APPENDIX B: Quality and Reproducibility of the Data	85
APPENDIX C: Experimental Data - Process Conditions	92
APPENDIX D: Experimental Data - Feed Molar Flow Rates ...	97
APPENDIX E: Experimental Data - Product Molar Flow Rates	102

LIST OF FIGURES

- FIGURE 1 Methane Conversion Pilot Plant
- FIGURE 2 Effect of Feed Type on Methanol Yield
- FIGURE 3 Effect of Feed Type on Methanol Selectivity
- FIGURE 4 Effect of Feed Type on Methane Conversion
- FIGURE 5 Effect of Ethane Concentration on Hydrocarbon Conversion
- FIGURE 6 Effect of Ethane Concentration on Methane Conversion
- FIGURE 7 Effect of Ethane Concentration on Methanol Selectivity
- FIGURE 8 Effect of Ethane Concentration on Methanol Yield
- FIGURE 9 Effect of Oxygen Concentration on Product Selectivity
- FIGURE 10 Effect of Oxygen Concentration on Hydrocarbon Conversion
- FIGURE 11 Effect of Oxygen Concentration on Product Yield
- FIGURE 12 Effect of Oxygen Concentration on Methane Conversion
- FIGURE 13 Effect of Temperature on Methanol Yield
- FIGURE 14 Effect of Temperature on Methanol Selectivity
- FIGURE 15 Effect of Temperature on Methane Conversion
- FIGURE 16 Effect of Pressure on Methanol Yield
- FIGURE 17 Effect of Pressure on Methanol Selectivity
- FIGURE 18 Effect of Residence Time on Methanol Yield
- FIGURE 19 Effect of Residence Time on Methanol Selectivity
- FIGURE 20 Effect of Residence Time on Methane Conversion
- FIGURE 21 Effect of Gas Flow Rate on Methane Conversion
- FIGURE 22 Effect of Residence Time on Hydrocarbon Conversion

LIST OF FIGURES (continued)

- FIGURE 23 Effect of Mixer Type on Methanol Selectivity
- FIGURE 24 Effect of Mixer Type on Methane Conversion
- FIGURE 25 Effect of Mixer Type on Hydrocarbon Conversion
- FIGURE 26 Effect of Mixer Type on Methanol Yield
- FIGURE 27 Effect of Steam Addition on Methanol Selectivity
- FIGURE 28 Effect of Product Quench on Hydrocarbon Conversion
- FIGURE 29 Effect of Product Quench on Methane Conversion
- FIGURE 30 Effect of Product Quench on Product Selectivity
- FIGURE 31 Effect of Product Quench on Methanol Yield
- FIGURE 32 Effect of Reactor Diameter and Temperature on Methanol Selectivity
- FIGURE 33 Effect of Reactor Diameter and Temperature on Methanol Yield
- FIGURE 34 Effect of Reactor Diameter and Oxygen Concentration on Methanol Selectivity
- FIGURE 35 Effect of Reactor Packing on Methanol Selectivity
- FIGURE 36 Effect of Reactor Packing on Methanol Yield
- FIGURE 37 Effect of Reactor Diameter and Oxygen Concentration on Conversion
- FIGURE 38 Effect of Fritted Disk Internals on Methanol Selectivity
- FIGURE 39 Effect of Fritted Disk Internals on Conversion
- FIGURE 40 Effect of Fritted Disk Internals on Methanol Yield
- FIGURE 41 Effect of Added CO₂ on Methanol Selectivity
- FIGURE 42 Effect of Added CO₂ on CO Selectivity
- FIGURE 43 Effect of Added CO₂ on CO₂ Selectivity
- FIGURE 44 Effect of Added CO₂ on Formaldehyde Selectivity

LIST OF FIGURES (continued)

- FIGURE 45 Effect of Added CO_2 on Hydrocarbon Conversion
- FIGURE 46 Effect of Added CO_2 on Methanol Yield
- FIGURE 47 Effect of Added H_2 on Methanol Selectivity
- FIGURE 48 Effect of Added H_2 on Carbon Oxide Selectivity
- FIGURE 49 Effect of Added H_2 on Formaldehyde Selectivity
- FIGURE 50 Effect of Added H_2 on Oxygen-based H_2O Selectivity
- FIGURE 51 Effect of Added H_2 on Conversion
- FIGURE 52 Effect of Added H_2 on Methanol Yield
- FIGURE 53 Effect of Added H_2 on Hydrogen Production/Consumption
- FIGURE 54 Effect of Added CO on Methanol Selectivity
- FIGURE 55 Effect of Added CO on CO_2 Selectivity
- FIGURE 56 Effect of Added CO on CO Selectivity
- FIGURE 57 Effect of Added CO on Formaldehyde Selectivity
- FIGURE 58 Effect of Added CO on Conversion
- FIGURE 59 Effect of Added CO on Methanol Yield
- FIGURE 60 Effect of Added CO on CO Production/Consumption
- FIGURE 61 Effect of Recycle on Methanol Selectivity
- FIGURE 62 Effect of Recycle on Feed Conversion
- FIGURE 63 Effect of Recycle on Methanol Yield
- FIGURE 64 Effect of Recycle on CO_2 Selectivity
- FIGURE 65 Effect of Recycle on CO Selectivity
- FIGURE 66 Catalyst Post-Bed Reactor Internals

LIST OF FIGURES (continued)

- FIGURE 67 Effect of Catalyst Post-Bed on Methanol Selectivity
- FIGURE 68 Equilibrium Consumption of Methanol in Catalyst Bed
- FIGURE 69 Effect of Catalyst Post-Bed on CO Selectivity
- FIGURE 70 Equilibrium Methanol Consumption in Catalyst Post-Bed
- FIGURE B-1 Methane Partial Oxidation Data Quality
- FIGURE B-2 Standard Deviation of Methanol Selectivity Values
- FIGURE B-3 Standard Deviation of Methanol Yield Values
- FIGURE B-4 Standard Deviation of Methane Conversion Values
- FIGURE B-5 Standard Deviation of Hydrocarbon Conversion Values

DISCLAIMER

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor any agency thereof, nor any of their employees, makes any warranty, expressed or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process or service by trade name, mark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of the authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

TECHNICAL STATUS

This technical status report is being transmitted in advance of DOE review, and no further dissemination or publication will be made of this report without prior approval of the DOE Project/Program Manager.

EXECUTIVE SUMMARY

Amoco Oil Company, under a contract with the United States Department of Energy, has investigated the direct, non-catalytic conversion of light hydrocarbon gases to liquid fuels (particularly methanol) via partial oxidation. The primary hydrocarbon feed used in these studies was natural gas. This report describes work completed in the course of our two-year project. In general we determined that the methanol yields delivered by this system were not high enough to make it economically attractive. More detailed highlights of the work are given below in task order.

Task 3.1: Comparison of Preliminary Data With Los Alamos Kinetic Model.

After conducting preliminary experiments with both pure methane and natural gas (mixed hydrocarbon) feeds, it was determined that the Los Alamos model was not a suitable tool for guiding this experimental project. The reasons were two-fold. First, the Los Alamos model was written and tuned for pure methane feeds, whereas our data showed that the presence of higher hydrocarbons in our natural gas feed significantly affect the system. Secondly, the Los Alamos model assumes constant temperature conditions, whereas we observed as much as a 100 degree F temperature rise in the reactor. For these reasons additional work on this task was not done and emphasis was placed on the process variable studies in Task 3.2.

Task 3.2: Process Variable Studies. By comparing the above-mentioned runs with a pure methane feed with similar runs using a natural gas (mixed hydrocarbon) feed, it was found that the presence of higher (i.e. C₂+) hydrocarbons significantly decreases the per-pass methane conversion in this system. This occurred because the higher hydrocarbons are more reactive, and consumed much of the limited oxygen available before the methane could react with it. Since methane would be a major constituent of any light hydrocarbon stream from a coal conversion process, a decrease in per-pass methane conversion would translate into a larger recycle loop and poorer overall process economics.

Oxygen concentrations between 1.5 and 12.5 vol% were investigated, and it was determined that lower oxygen concentrations improve methanol selectivity, but reduce per-pass hydrocarbon conversion. Methanol yield increased with increasing oxygen concentration, and was maximized at uneconomic levels between 2.5 and 3.0 mol% at higher oxygen concentrations (above about 9 vol%).

Temperatures between 700 and 1200°F and pressures between 500 and 1300 psig were also investigated. Although the trends were relatively weak, it appears that lower temperatures (between 700 and 800°F) and higher pressures (1300 psig) maximize methanol yield. In addition, there appeared to be a broad maximum in methanol yield at residence times between 30 and 60 seconds. Moreover, the residence time experiments suggest that conversion

of methane in this system is limited by a mass or heat transfer effect, rather than by the partial oxidation kinetics.

Task 3.3: Study of Different Feed Injection Systems. A series of discussions with Professor Gesser at the University of Manitoba indicated that thorough mixing of the hydrocarbon and oxygen streams may be critical to obtaining the high methanol yields that he reports (around 90% methanol selectivity and 9% methanol yield). To determine the effect of feed mixing on methanol selectivity and yield, five different hydrocarbon/oxygen mixer configurations were studied. It was found that mixer type has some effect on methanol selectivity at low oxygen concentrations (below about 6 vol%), but no effect at higher oxygen levels where yields were higher. The best mixer tested was a 4-inch diameter in-line static mixer manufactured by Kenics.

After discussions with DOE personnel, the scope of this Task was broadened to include the study of different reaction modifiers. Work in this area focussed on the effect of added water, acetone (a source of methyl radicals), and nitrous oxide (a strong chemical oxidizer). The addition of steam to the reacting system decreased methanol selectivity significantly, while acetone addition had little or no effect on methanol selectivity or yield. The reaction between natural gas and nitrous oxide was difficult to initiate, requiring temperatures in excess of 1300°F. At these conditions, the products of the reaction were primarily carbon oxides. The reaction of nitrous oxide and methane in a catalytic system remains a valid avenue of research, but beyond the scope of this project.

Task 3.4: Effect of Product Quench. Studies were conducted both with and without rapid quenching of the product gases. No effect was observed. This result was anticipated, given the long residence times (30-90 seconds) employed in these studies.

Task 3.5: Effect of Reactor Geometry. Investigations were made of the effects of reactor diameter (length-to-diameter ratio), reactor packing, and the presence of internals to ensure plug flow in the reactor. At temperatures below about 900°F and oxygen concentrations below about 6 vol%, smaller diameter reactors gave higher methanol selectivities. At higher oxygen concentrations, reactor diameter had no effect on methanol selectivity or yield. At higher temperatures, large diameter reactors gave higher methanol yields, probably because there was less surface area to promote the thermal decomposition of methanol to carbon monoxide and hydrogen.

Packing a large-diameter reactor made it behave like a smaller diameter reactor, i.e. it improved methanol selectivity at low oxygen concentrations. The main conclusion from the reactor diameter and packing studies is that the surface area-to-volume ratio of the reactor is apparently an important factor at low

oxygen concentrations (below 6 vol%). At higher oxygen concentrations there was no effect of reactor geometry on methanol selectivity or yield.

Preventing backmixing in the reaction zone through the use of plug-flow enhancing internals did not improve methanol yield. We conclude from this that forced convective backmixing from the feed inlet jets is not limiting methanol selectivity in this system. However, it is still possible that backmixing caused by thermal convection in the reaction zone may be present in this system.

Task 3.6: Effect of Reactor Recycle. Since in this partial oxidation system there is only partial per-pass conversion of the hydrocarbon feed, a recycle loop would be necessary in any commercial manifestation of this process. For this reason a simulated mixed feed/recycle stream was studied to determine the effects of product gases on methanol selectivity and feed conversion. The product gases studied were CO₂, CO, and H₂. These gases were spiked in various amounts into the fresh hydrocarbon feed.

In the spiking experiments it was found that CO₂ has very little effect on methanol selectivity or hydrocarbon conversions even up to CO₂ concentrations of 20 vol% in the reactor feed. The presence of both CO and H₂ in the reactor feed, on the other hand, decreased methanol selectivity significantly. The decrease in methanol selectivity was proportional to the amount of CO or H₂ present in the feed. When added to the system together, it appears that the effects of CO and H₂ are additive, and therefore the effects of the mixture can be readily estimated from the pure-component effects.

In the course of these experiments we found that the factor controlling hydrocarbon conversion in this system is the concentration of oxygen in the reactor feed, and not the hydrocarbon-to-oxygen ratio in the feed. This is true even when other oxidizable species (e.g. CO and H₂) are present in the reactor feed. This is important because it suggests that the concentration of byproducts and diluents in the recycle stream will affect the amount of oxygen required to achieve a given per-pass hydrocarbon conversion.

Task 3.7: Enhanced-Yield Catalyst Study. One method that has been proposed for increasing the overall yield of methanol from this system is to use a catalyst post-bed to convert some or all of the CO formed in the thermal reactions described above. To test such a process, a bed of methanol synthesis catalyst was placed downstream of the thermal reaction zone and its effects on methanol selectivity and yield were determined. In all cases it was found that the presence of the catalyst bed either had no effect on the methanol selectivity or actually caused it to decrease. A subsequent thermodynamic analysis of this system showed that under all practical conditions, the thermodynamic driving force in the

catalyst bed is toward methanol decomposition, rather than methanol formation. The cause of this is the relative abundance of methanol and lack of hydrogen in the product gases from the thermal reaction zone. Based on these thermodynamic studies, it was determined that this post-bed system did not hold significant promise for improving methanol selectivity.

Based on these findings, it is evident that the gas phase free radical reactions that define this non-catalytic system are inherently unselective to methanol. The maximum methanol yield observed in these studies was between 2.5 and 3.0 mol%, far below the 15 mol% yield predicted to be necessary for economic viability. Extensive efforts to improve methanol selectivity through control of process variables, reactor and process design, and the presence of reaction modifiers have proven unsuccessful. Any future investigation of direct conversion of methane to methanol should concentrate on developing a catalyst that will allow the reaction to proceed at low temperatures ($< 600^{\circ}\text{F}$) where these unselective free radical reactions do not take place.

DIRECT CONVERSION OF LIGHT HYDROCARBON GASES TO LIQUID FUELS

FINAL REPORT

OBJECTIVE

The objective of this project was to investigate the direct conversion of light hydrocarbon gases to liquid transportation fuels via a partial oxidation process. The process has been tested in a small pilot-scale unit so that credible mass balances could be obtained.

INTRODUCTION

Fischer-Tropsch synthesis, gasification processes like Lurgi dry bottom gas, direct coal liquefaction, and remote natural gas all represent sources of substantial quantities of light hydrocarbon gases. Methane is the major and most stable component of all these gases. Steam reforming methane to produce synthesis gas is capital-intensive because it is highly endothermic and requires severe reaction conditions. A process for direct conversion of light gases, especially methane, to methanol, gasoline, or other liquid fuels could be far superior.

Steam reforming is the first stage in traditional commercial methods for the production of liquid fuels. This first step produces synthesis gas:

The synthesis gas is then converted into methanol via a catalytic process.

Reaction 1 produces more hydrogen than required by reaction 2. The excess can either be utilized elsewhere in the case of a domestic refinery or, in the case of a remote operation, is lost. A third step could be the catalytic condensation of methanol to gasoline.

A more efficient route of converting light hydrocarbons would be to directly form methanol by partial oxidation.

Such a process could substantially reduce capital and energy requirements for methanol production. The methanol could be used as a fuel or a fuel blending component, as in the case of M80 fuels (80% methanol, 20% gasoline), or else converted into gasoline through well-known processes, such as MTG. A plant based on Reactions 1 and 2 followed by methanol condensation to gasoline has been built and is operating in New Zealand. However, the process is uneconomical if it were not for the New Zealand Government support. If a

process for the direct conversion of light hydrocarbons to methanol is feasible, thereby eliminating the process steps shown by Reactions 1 and 2, then a gas-to-gasoline process could become economically viable.

A proposed process for converting light hydrocarbon gases directly to hydrocarbon liquids, e.g., methanol or formaldehyde, is not new. In 1932 Newitt and Haffner reported the formation of methanol, along with smaller amounts of formaldehyde and formic acid, in the high-pressure oxidation of methane.⁽¹⁾ The reaction was carried out in a static system at 360–393°C and 50–150 atm. The maximum methanol selectivity was ca. 22%; however, CH₄ conversion was only a few percent. More recently, Gesser, Hunter and co-workers have reported methanol selectivities up to 90% and yields of around 9%.⁽²⁾ However, other workers have in general been unable to reproduce these results (see below).

PROJECT OVERVIEW

The project was of two years' duration and contained three major tasks. The third task (Pilot Plant Experiments) contained seven subtasks, corresponding to the project objectives outlined above. The tasks and subtasks are described below.

Task 1: Project Management Plan: A plan was prepared describing the work to be done, milestones, and manpower requirements and costs.

Task 2: Pilot Plant Modification: An existing pilot plant dedicated to investigation of light hydrocarbon conversion was modified to provide it with the capability to handle the processes and conditions of this program. These modifications included construction of a new reactor, as well as construction and installation of reactant injection and mixing systems.

Task 3.1: Comparison of Preliminary Data With Los Alamos Model: We determined that the kinetic model developed by Los Alamos National Laboratory was not suitable to be used as a guide to our experimental effort. Instead, an evolutionary operations approach was utilized.

Task 3.2: Process Variable Studies: The methane conversion data base was extended over the following range of conditions:

Temperature:	700 to 1200°F
Pressure:	500 to 1300 psig
Reaction Time:	3 to 350 seconds

The goal of these and all other studies was the maximizing of methanol yield.

Task 3.3: Study of Different Injection Systems: Different schemes for introducing and mixing reactants were experimentally evaluated.

- Task 3.4: Study of the Effect of Product Quenching: The efficacy of product quenching was investigated to determine its effects on product composition and methanol yield.
- Task 3.5: Effect of Reactor Geometry: The effect of reactor geometry, primarily aspect (i.e. length/diameter) ratio and surface area-to-volume ratio, were investigated to determine their effects on product composition and methanol yield.
- Task 3.6: Effect of Reactor Recycle: The effects of recycling reaction byproducts (hydrogen gas and carbon oxides) to the reactor inlet were evaluated by appropriately blending the feed stream to simulate reactor recycle. Since these results were not promising relative to methanol production, the pilot plant was not modified to incorporate a recycle compressor and recycle line.
- Task 3.7: Enhanced-Yield Catalyst Study: An attempt was made to develop a combined thermal/catalytic process in which byproduct carbon monoxide and hydrogen from the thermal process would be converted to methanol over a heterogeneous catalyst. Such a combined process could provide higher methanol yields than the thermal process alone.

PREVIOUS WORK

Direct conversion of methane to methanol is not a new approach. In 1932 Newitt and Haffner reported the formation of methanol, formaldehyde and formic acid in the high-pressure oxidation of methane.⁽¹⁾ The reaction was carried out in a static system at temperatures of 680-740°F and pressures of 725-2200 psig. The maximum methanol selectivity was ca. 22% at only a few percent methane conversion. The partial oxidation of methane and other hydrocarbons was the focus of a study by Wiezevich and Frolich in 1934.⁽⁴⁾ They found that methanol selectivity increased with increasing pressure up to 135 atmospheres. The presence of higher hydrocarbons (ethane and propane) significantly lowered the temperature at which the reaction first occurred. Partial oxidation of the higher hydrocarbons resulted in scission of C-C bonds, leading to the formation of lower derivatives.

In 1937 Boomer et al.⁽⁵⁻⁷⁾ reported a series of high-pressure methane partial oxidation experiments using both copper and silver catalysts. With an empty copper-lined reactor,⁽⁵⁾ methanol selectivity decreased with decreasing pressure between 185 and 120 atm. A maximum in methanol selectivity with pressure was observed at 185 atmospheres in a reactor filled with copper catalyst.⁽⁷⁾ In this system⁽⁶⁾ they also found that lower oxygen concentrations increased methanol selectivity, but decreased methane conversion. A maximum in methanol yield (near 3%) was observed at 10 vol% O₂ in the feed. The effect of temperature seemed to depend on the concentration of oxygen in the feed. At higher oxygen concentrations (12.7 vol%) higher temperatures significantly decreased methanol selectivity,⁽⁶⁾ but at lower

oxygen levels (3.7 vol%) temperature had little effect on selectivity. Like many other methane partial oxidation studies, these results were plagued by poor oxygen balance closures (generally between 60-90%).⁽⁵⁻⁷⁾

More recently, Gesser et al.^(2,8-12) have reported methane partial oxidation experiments in which methanol selectivities as high as 90% were observed at methane conversions of up to 10%,⁽⁸⁾ giving an overall methanol yield of 9%. These results were obtained in the absence of catalyst at 50 atm. and 350°C with a glass-lined reactor and 5.7 vol% oxygen in the feed. This yield is significantly higher than reported by other workers.^(4-7,13) Both pre-mixed feed⁽¹¹⁾ and dual-flow^(2,8,9) systems gave similar results, provided that the gases in the dual-flow system were thoroughly mixed.^(10,12) Like Boomer et al.,^(6,7) they found that lower oxygen levels increased methanol selectivity but decreased methane conversion. The effect of temperature on the system depended on both pressure and oxygen level in a complex manner.⁽⁹⁾ Wall composition did not affect methanol selectivity,⁽⁸⁾ but the presence of catalysts in the reactor did. Of the catalysts studied, Cu/SiO₂ and SnO₂ showed the highest activity for methanol formation.

Burch et al.⁽¹³⁾ recently attempted to reproduce the results of Gesser et al. by studying the effect of temperature, pressure, reactor type, residence time, oxygen concentration and gas mixing on the partial oxidation of methane in a dual-feed flow system. They found that glass-lined reactors were best for maximizing methanol production. At high pressures (40-50 atm), none of the experimental parameters had a significant influence on the selectivity to methanol. Methanol selectivities were generally around 40%, significantly lower than those reported by Gesser et al..⁽⁸⁾ Burch et al. suggested that there may be something unique about the design of Gesser's reactor which allows high methanol selectivity at high methane conversion. Rytz and Baiker⁽¹⁴⁾ showed recently that residence time in the reactor was an important parameter below about 8 seconds, but at longer residence times than this had little effect on methanol selectivity or yield. They also observed methanol selectivities in the 30-40 mol% range at 5 vol% oxygen.

Brown and Parkyns⁽¹⁵⁾ recently published an exhaustive review of the literature regarding both catalytic and noncatalytic partial oxidation of methane to methanol and formaldehyde. They conclude that, though this is not a new field, it is still in its relative infancy and is characterized by a marked lack of reproducibility between workers and research groups.

EXPERIMENTAL EQUIPMENT AND PROCEDURES

The present experiments were carried out in a small pilot plant designed for studying the direct conversion of light hydrocarbon gases into products such as methanol, gasoline, ethylene, and synthesis gas. A schematic diagram of the plant is shown in Figure 1. The reactor was located in a Fluitron containment cell to allow safe operation over a wide range of hydrocarbon to oxygen ratios at temperatures up to 1600°F and pressures to 1300 psig (at 1000°F). The unit was fully instrumented to allow unattended (24-hour) operation. Process conditions were monitored and controlled by computer, with additional monitoring and emergency shutdown procedures provided by two separate and redundant computers.

The feed section of the plant was used to meter, mix, and deliver the hydrocarbon and oxygen feeds. Flows were monitored and controlled with Brooks mass flow controllers. A compressor located in the hydrocarbon feed line allowed plant operation at pressures up to 1300 psig (88 atm.). Hydrocarbon feeds were CP grade methane or natural gas. The natural gas varied somewhat in composition, but averaged 93% methane, 4% ethane, 1% C_3+ , 0.6% CO_2 and 1.4% N_2 . Pure oxygen (Matheson Zero Gas) was used in all experiments.

Two different reactors were used in the course of this work. One reactor was machined from solid Incolloy 800 stock into a 30-inch long, 1-inch ID, 2 1/4-inch OD pipe. The other reactor was fabricated from a 30-inch long section of 1.5-inch ID, 2.5-inch OD 316 stainless steel pipe. In both reactors, the upper 13 inches of the reactor tube were heated with a three-zone electric furnace. The lower 10 inches of the reactors were wrapped with a cooling water coil to rapidly quench the product gases. An inert quartz tube inserted into the reactors served as the reactor liner. Internal temperatures were monitored by a 1/8-inch OD, 316 stainless steel-sheathed, four-junction thermocouple. A quartz sleeve covered the thermocouple to maintain all internal reactor surfaces inert.

The product gases were further cooled in the product recovery section and the liquid and gas phases were separated. The liquid phase was directed to a product receiver where product accumulation was continuously monitored. The gas-phase pressure was reduced through a back pressure regulator valve, and the offgases passed through a wet test meter to measure flow rate. The entire product recovery section was enclosed in a 1/4-inch thick steel plate explosion cage for safety.

Slipstreams from both the hydrocarbon feed and the product gas were analyzed with a 5580 Hewlett-Packard gas chromatograph refinery gas analyzer. This chromatograph allowed resolution of $C_1 - C_5$ hydrocarbons (paraffins and olefins), as well as H_2 , O_2 , N_2 , CO and CO_2 . Liquid samples were analyzed off-stream on a 5790 Hewlett-Packard gas chromatograph with a Porapak-QS column and thermal conductivity detector. This chromatograph could resolve water and $C_1 - C_4$ alcohols, but could not detect formaldehyde. Formaldehyde concentration in the aqueous product was determined colorimetrically, but was never found to be significant (i.e. less than 1% selectivity). In a typical test, conditions were set in the morning and the plant was allowed to reach steady state (usually 4-5 hours) before the test was begun. Tests generally lasted 16-17 hours.

Using these procedures, accurate mass and element balances were obtained. In all runs reported below, mass balances were closed within 3%, as were carbon and hydrogen atom balances. Oxygen balances were somewhat less accurate, but were always within 10%, and usually within 5%. Appendix B discusses the quality and reproducibility of the experimental data in more detail.

In this report, selectivity is defined as the moles of carbon in the product divided by the total moles of carbon present in all products detected. Methane conversion is calculated using the formula

$$CH_4 \text{ Conversion} = \frac{(\text{moles } CH_4 \text{ in}) - (\text{moles } CH_4 \text{ out})}{(\text{moles } CH_4 \text{ in})}$$

Hydrocarbon (HC) conversion (methane plus other hydrocarbons) is calculated based on carbon atom conversion:

$$HC \text{ Conv.} = \frac{(\text{moles C in feed}) - (\text{moles unreacted C in product})}{(\text{moles C in feed})}$$

The unreacted moles of carbon in the product gas were defined as those contained in methane, ethane, propane, butanes, and pentanes. Other carbon-containing compounds were considered to be products. Methanol yield is defined as the product of methanol selectivity and hydrocarbon conversion.

The data reported below were statistically adjusted to better than 99% closure on the mass, carbon, hydrogen, and oxygen balances with a data adjustment program (see Appendix A). Otherwise, plus-or-minus 3% carbon balance closures translated to absolute differences of +/-3% in methane conversion and methanol yield. This is significant, since methane conversions and methanol yields were typically on the order of about 5% and 2-3%, respectively. The adjustment significantly improved the reproducibility of the data, especially in the low conversion cases.

RESULTS AND DISCUSSION

The results obtained in this investigation cover a very wide range of conditions, reactor designs, and process configurations. The experimental data will be presented here in terms of the experimental tasks outlined above. In addition to the results presented in the sections below, Appendix B discusses the quality of the data generated in this project, including standard deviations of all of the important calculated parameters. Appendices C-E contain listings of the process conditions for each run as well as feed and product component molar flow rates.

Task 3.1: Comparison of Preliminary Data With Los Alamos Model.

One of the first steps taken on this project was a determination made of the feasibility of using a methanol partial oxidation kinetic model developed by workers at Los Alamos National Laboratory to guide our experimental program. The model incorporates over 150 elementary gas-phase reactions⁽¹⁶⁾ and has been tuned according to experimental data obtained in a static partial oxidation reactor at Los Alamos. As such, it was not clear whether the model could predict the results of experiments performed in our continuous flow reactor.

Operation of our unit showed that it was not in the best interest of the project to pursue the evaluation of the Los Alamos model. The reasons for this

were two-fold. First, the Los Alamos model was written and tuned for pure methane feeds. Since our data show that the presence of higher hydrocarbons has a significant effect on methane conversion (see Task 3.2 below), optimization with a model based on pure methane feeds would have little relevance to feeds containing higher hydrocarbons. Secondly, the Los Alamos model assumes isothermal (i.e. constant temperature) conditions, while our reactor is more nearly adiabatic. We observed as much as a 100 degree F temperature rise through the heated (reaction) zone of the reactor. It was therefore highly unlikely that results from the Los Alamos model would match our pilot plant results. For these reasons work on this task was concluded and emphasis was placed on the process variable studies in Task 3.2.

Task 3.2: Process Variable Studies.

Before any reactor or process design experiments were conducted, a series of process variable studies was undertaken to determine the conditions where methanol selectivity and yield were maximized. Five main effects were studied: hydrocarbon feed composition, oxygen concentration, temperature, pressure, and residence time.

1. Effect of Hydrocarbon Feed Composition

To investigate the effect of feed composition on the system, runs using both pure methane and natural gas feeds were made and compared at a number of temperatures and pressures. The natural gas contained about 93% methane, 4% ethane, 1% C_3+ , 0.6% CO_2 , and 1.4% nitrogen. The major impurity in the "pure" methane was ethane at 0.02%. The effect of feed type on methanol yield, methanol selectivity, and methane conversion are shown in Figures 2, 3 and 4, respectively. In all cases the residence time was near 35 seconds and hydrocarbon/oxygen was 10.

These data show a number of significant trends. It is apparent that methanol yields are generally slightly higher with natural gas feeds than with pure methane. This is because methanol selectivity is slightly higher with natural gas feeds, except at higher pressures and temperatures, where it becomes slightly lower (Figure 3). Methane conversion with natural gas feeds is only about half the 6-8% observed in the pure methane runs (Figure 4). This can be attributed to limited oxygen availability in these experiments. The higher hydrocarbons in the natural gas react more easily than methane, consuming much of the oxygen and leaving little to combine with the less-reactive methane.

To further study the effect of higher hydrocarbons on the system, pure methane was spiked with 1-5 vol% ethane before being fed to the reactor. The effects of ethane level on hydrocarbon and methane conversion, product selectivity and product yield were studied. In these runs temperature was constant at 800°F, pressure was 1300 psig, residence time was between 30 and 60 seconds, and hydrocarbon/oxygen was 10. These conditions had been found to maximize methanol production, as described in later sections.

Figure 5 shows that hydrocarbon conversion increases slightly with increasing ethane content of the feed. As in the natural gas runs, this increase occurs because the ethane reacts more easily with oxygen than the methane. Ethane

conversion in the reactor was 40%, independent of ethane concentration. Hydrocarbon conversion with natural gas feed increases to slightly above the line for spiked, pure methane feed in Figure 5. This is probably due to the presence of propane and butanes in the natural gas feed and their greater reactivity compared to ethane.

Methane conversion decreases with increasing ethane concentration (see Figure 6). This is also similar to the natural gas runs and occurs because the more reactive ethane preferentially consumes the oxygen, leaving less to react with methane. Figure 6 also shows that natural gas feeds give lower methane conversions than feeds with equivalent amounts of ethane. This is probably due to the even higher reactivity of propane and butanes in the natural gas (present in sum at the 1.0 vol% level).

That methane conversion is lower in the presence of higher hydrocarbons (such as ethane) could have a significant impact on the economics of this process. Since a lower per-pass methane conversion translates to a larger recycle loop for the process (and therefore higher equipment cost), any effect that lowers the methane conversion significantly will probably be detrimental to process economics. We would expect this effect to be less significant at higher oxygen feed levels, since more oxygen would be available to react with methane. Runs related to the effect of oxygen level are presented in the following section.

Surprisingly, the selectivity of the reaction is practically independent of ethane concentration, even at ethane concentrations of up to 5 vol% (Figure 7). At this ethane concentration, nearly 40% of the carbon in the products comes from ethane conversion. Since selectivity does not change over this range of ethane concentrations, it appears that the partial oxidation of ethane takes place with a selectivity pattern similar to that of methane. This result is supported by the early work of Wiezevich and Frolich⁽⁴⁾ who found that carbon-carbon bond scission is an important step in the partial oxidation of higher hydrocarbons. One possible explanation is that both methane and ethane oxidation have the same rate-limiting step (and therefore a common reaction intermediate).

Methanol yield is essentially independent of ethane concentration (Figure 8), since hydrocarbon conversion increases only very slightly and selectivity remains unchanged.

These results indicate that the level of C_{2+} hydrocarbons in the feed significantly influences per-pass methane conversion, but not methanol yield or selectivity. This demonstrates the importance of using the proper feed in methane partial oxidation studies. Specifically, feeds containing higher hydrocarbons should be used, since any commercial operation would probably contain higher hydrocarbons in the feed. Consequently, all subsequent runs were made with a mixed hydrocarbon (natural gas) feed.

2. Effect of Oxygen Concentration:

In order to study the effect of oxygen on the system, a number of runs were made in which oxygen concentration varied between 1.5 and 12.5 vol% of the

total feed. Other parameters were held constant at $T=800^{\circ}\text{F}$, $P=1300$ psig and a 35 second residence time. Figures 9-12 show the effect of oxygen concentration on product selectivity, hydrocarbon conversion, product yield, and methane conversion, respectively.

The data presented in this and following sections are corrected for the amount of ethane in the natural gas feed. The natural gas was not a standard mixture; it was taken from the city supply line and compressed for use in these experiments. Therefore, the composition of the hydrocarbon feed varied slightly over time, primarily in the amount of ethane present. Since the level of higher hydrocarbons significantly affects methane conversion and slightly affects hydrocarbon conversion (see previous section), it was necessary to adjust the methane and hydrocarbon conversion levels in each run to a standard ethane concentration (arbitrarily chosen to be 4.0 vol% ethane). The correction factors for this standardization were derived from the slopes of Figures 5 and 6.

Methanol selectivity increases with decreasing oxygen concentration (Figure 9). Selectivity to CO stays relatively constant, while selectivity to CO_2 decreases with decreasing oxygen concentration. The highest methanol selectivity observed was 46% at 1.5 vol% O_2 in the feed, and the major product at all oxygen levels is CO, with a selectivity of around 55%. An increase in methanol selectivity with decreasing oxygen level has also been reported by Gesser et al.⁽⁹⁾ and Boomer et al..^(6,7) The trends observed in Figure 9 are consistent with the methane oxidation mechanism proposed by workers at Los Alamos.⁽¹⁶⁾ In this mechanism a methoxy radical ($\text{CH}_3\text{O}\cdot$) can combine with either gas-phase oxygen (to form carbon oxides), or gas phase methane (to form methanol). Higher oxygen concentrations promote the carbon oxide formation branch at the expense of the methanol formation branch.

Hydrocarbon conversion increases steadily with increasing oxygen concentration, as shown in Figure 10. The effect of oxygen level on product yield (selectivity times hydrocarbon conversion) is shown in Figure 11. Methanol yield increases with increasing oxygen level, as do the yields of carbon oxides (CO and CO_2). The maximum methanol yield is around 2.5-3.0 mol% and is observed at the higher oxygen levels (above 9 vol%).

As expected, methane conversion increases steadily with increasing oxygen concentration (Figure 12). Methane conversion is more sensitive to oxygen concentration than is hydrocarbon conversion: at 1.5 vol% oxygen methane conversion is nearly zero, while hydrocarbon conversion is around 2%. This means that at the lower oxygen levels with a natural gas feed (where methanol selectivity is highest), almost all of the products result from partial oxidation of the higher (C_2+) hydrocarbons in the feed. At higher oxygen concentrations, more oxygen is left after reaction with higher hydrocarbons to react with methane.

These oxygen studies indicate that lower oxygen concentrations give higher methanol selectivity, while methanol yield is maximized at oxygen concentrations above about 9 vol%. Based on methanol selectivity, then, lower oxygen concentrations are desirable. As mentioned above, however, at these low oxygen levels methane conversion is almost zero: nearly all of the

products result from conversion of C_{2+} species in the natural gas. Since the extent of methane conversion significantly impacts the economics of the process, higher oxygen concentrations are preferred. This trade-off between selectivity and conversion is typical of partial oxidation systems.⁽¹⁵⁾ The optimal oxygen level will be intermediate between these extremes and would be fixed in a commercial operation by economic considerations. In this study, all subsequent runs used 9% oxygen (hydrocarbon/oxygen = 10) as the base concentration, since methane conversion is significant (nearly 5%) at this concentration and methanol yield is maximized at around 2.5 mol%.

3. Effect of Temperature

With the preferred hydrocarbon feed and oxygen level determined, experiments were run to determine the optimum temperature and pressure for methanol production and methane conversion. A series of runs was made in which temperatures were varied between 700–1200°F and pressures between 500–1300 psig. At temperatures lower than about 680°F, the reaction was not initiated in this non-catalytic system. The residence time was 35 seconds for all experiments. The temperature effects will be discussed in this section; pressure effects will be covered in the following section.

The temperatures indicated here correspond to average temperatures in the reaction zone. Even though the reactor heater was set for constant temperature, the size of the reactor (approximately 1 inch diameter) and the design of the furnace precluded isothermal operation. A significant temperature rise through the reactor (generally between 100 and 200°F) was observed in all runs. External thermocouples measured temperatures at three different points on the reactor (corresponding to the beginning, middle, and end of the reaction zone), and the temperatures reported below are averages of these three readings.

The effect of temperature on methanol yield is shown in Figure 13. At every pressure, methanol yield decreased with increasing temperature. This suggests that lower temperatures are desirable for maximizing methanol yield. The effect of temperature on product selectivity is shown in Figure 14. Temperature has some effect on product selectivity over the range between 700 and 1200°F. As temperature increases, methanol selectivity drops and CO selectivity rises. Carbon dioxide selectivity is unchanged over the entire range. The decrease in methanol selectivity at higher temperatures (and the resulting increase in CO selectivity) are probably caused by the thermal decomposition of methanol to CO and H_2 .

The effect of temperature on methane conversion is shown in Figure 15 to be negligible. Temperature also has no significant effect on hydrocarbon conversion in the range studied.

The primary conclusion that can be drawn from the temperature studies is that lower temperatures appear to be desirable for both methanol yield and methane conversion. The literature is not consistent on the effect of temperature on this system, probably because different researchers use different sets of conditions (pressures, oxygen levels, residence times) at which to evaluate the effect of temperature. In this study, the trends with temperature are not

large, particularly below about 900°F (see Figure 14). This may indicate that in non-isothermal operation, tight temperature control might not be necessary in order to maximize methanol production. In any case, temperatures between 700 and 800°F appear to be optimal for methanol production and methane conversion in this system.

4. Effect of Pressure

The effects of pressure on methanol yield, product selectivity, methane conversion, and hydrocarbon conversion were studied between 500 and 1300 psig. At every temperature studied, methanol yield increases with increasing pressure (Figure 16). This indicates that higher pressures are desirable for maximizing methanol production, but these trends are very weak. The significantly lower methanol yield at higher temperatures noted in the previous section is apparent in Figure 16.

The effect of pressure on product selectivity is shown in Figure 17. Again, the trends are not large, but CO selectivity decreases slightly with increasing pressure, while CO₂ selectivity increases with increasing pressure. Methanol selectivity is relatively constant over the range of pressures studied. Burch et al.⁽¹³⁾ found that pressure had little effect on methanol selectivity in glass-lined reactors, but Boomer et al.⁽⁷⁾ observed a maximum in methanol selectivity at 184 atmospheres. Wiezevich and Frolich,⁽⁴⁾ on the other hand, observed higher methanol selectivity at higher pressures (up to 2000 psig). In this study, pressure has no discernable effect on either methane conversion or hydrocarbon (methane and C₂₊) conversion.

Like the temperature trends, the trends with pressure are quite small. They indicate, however, that higher pressures are marginally better for increasing methanol yield.

5. Effect of Residence Time

The effects of residence time on methanol yield, product selectivity, methane conversion and hydrocarbon conversion were studied. All experiments were carried out at P=1300 psig, T=800°F and hydrocarbon/oxygen=10.0. Three different sizes of reactor liner were used in these residence time studies: a "large" 31 mm diameter tube (for the longer residence times), a "medium" 19 mm diameter tube (for intermediate residence times), and a "small" 10.5 mm diameter tube (for the shorter residence times). All reactors utilized the same 13-inch long furnace.

Figure 18 shows the effect of residence time on methanol yield. There is a difference in the results from the large-, medium- and small-diameter reactors. The large and medium diameter reactors gave relatively consistent and reproducible results, while the data from the smaller diameter reactor were much more scattered and generally gave lower selectivities. The overall trend using data from all three reactors suggests that there may be a broad maximum in methanol yield at residence times between 30-60 seconds. Methanol yield drops sharply at lower residence times and gradually at higher residence times. It should be noted that there was not much overlap between the residence time regimes studied with the different reactors, so it is possible

that reactor size effects come into play in shaping these trends. However, additional studies with different diameter reactors (see Task 3.5) show that this is probably a true residence time effect — reactor diameter has little effect on methanol selectivity at oxygen concentrations of 9 vol% where these residence time studies were made.

Figure 19 presents the effect of residence time on methanol selectivity. It has the same characteristics as the methanol yield plot, with methanol selectivity decreasing significantly at residence times below about 10 seconds. These results have been corroborated by a recent study by Rytz and Baiker⁽¹⁴⁾ in a quartz-packed reactor. They reported that methanol selectivity decreased significantly at residence times below about 9 seconds.

Figure 20 shows the effect of residence time on methane conversion. Once again there is a definite distinction between data from the different diameter reactors. All three data sets show a linear decrease in methane conversion with increasing residence time, but the three data sets are not collinear. The three distinct lines in Figure 20 can be made to converge relatively well into a single curve (see Figure 21) by plotting methane conversion as a function of total gas flow rate, rather than residence time. This suggests that gas flow rate, rather than residence time, is a key parameter in this system.

Two explanations for this behavior are proposed. First, there may be some mass or heat transfer operation in the reactor itself that strongly affects methane conversion. Second, mixing of the gases prior to reaction may be important. At the higher flow rates, better mixing occurs and methane conversion is higher. Calculations show that in the 1/4" transfer lines present in the pilot plant, laminar flow conditions (and resulting poor mixing) prevail at total (oxygen + natural gas) flow rates below about 85 standard cc/sec, while turbulent flow (better mixing) begins to occur above about 95 standard cc/sec. Turbulent flow is defined as flow where $N_{Re} > 2000$. The laminar-to-turbulent transition, therefore, occurs within the range of flow rates studied and may account for better mixing and therefore better methane conversion at the higher flow rates. Subsequent studies of various types of mixers, however, indicate that the degree of mixing has little effect on methane conversion (see Task 3.3 below). In either case, the fact that methane conversion correlates with flow rate rather than residence time suggests that a heat or mass transfer effect, rather than a kinetic effect, is controlling methane conversion in this system.

The effect of residence time on hydrocarbon (methane and C_{2+}) conversion is shown in Figure 22. These data appear to fall on a single line and show that hydrocarbon conversion decreases only slightly with increasing residence time. Rytz and Baiker⁽¹⁴⁾ reported that hydrocarbon (methane) conversion decreased significantly at residence times below about 8 seconds in a quartz-packed reactor.

Task 3.3: Study of Different Injection Systems

Initially, the experiments in this task were aimed at studying the effect of reactant mixing on methanol selectivity and yield. In discussions with DOE

personnel after the completion of these mixing studies, the scope of this task was broadened to include the study of different reaction modifiers. Work in this area focused on the effect of added water, acetone (a source of methyl radicals), and nitrous oxide (a strong chemical oxidant used in place of molecular oxygen). The results from these two areas of study are given below.

1. Effect of Mixer Configuration

During the course of discussions with Professor Gesser at the University of Manitoba about his results, he mentioned that thorough mixing of the hydrocarbon and oxygen streams seems to be critical to obtaining the high methanol yields that he reports.^(2,8-12) On the basis of these discussions, a series of experiments was conducted to elucidate the effects of mixing the feed hydrocarbon and oxygen streams to various degrees. Five different mixer configurations have been tested, including Professor Gesser's mixing system and several other available configurations:

- 1) a packed bed mixer consisting of $\frac{1}{4}$ -inch ceramic balls in a $\frac{1}{2}$ -inch diameter tube (this is the original mixer configuration used in all of the previous process variable studies),
- 2) a partially closed needle valve (similar to the mixer used by Professor Gesser at the University of Manitoba),
- 3) a series of two partially closed needle valves,
- 4) a $\frac{1}{2}$ -inch diameter static mixer manufactured by Kenics containing 24 fixed mixing elements, and
- 5) a $\frac{1}{2}$ -inch diameter Kenics static mixer containing 27 fixed mixing elements.

Experiments were carried out over a variety of oxygen feed concentrations between 1.5 and 12.5 vol%. Based on the previous process variable studies and the desire to maximize methanol yield, the pressure was held at 1300 psig, the temperature at 800°F and the residence time at 55 seconds in all runs. The residence time in these studies was slightly longer than those used in previous experiments because a larger (30 mm) diameter reactor was used. The process variable studies reported above showed that residence times in the range of around 30-60 seconds maximize methanol yields.

Figures 23-26 show the effects of mixer type and oxygen concentration on methanol selectivity, methane conversion, hydrocarbon conversion and methanol yield, respectively. At lower oxygen concentrations (below about 6 vol%) some differences were apparent between mixers, as shown in Figure 23. Mixers (1) through (4) all gave similar results, with methanol selectivity peaking between 30 and 35 mol% (at 4-6 vol% O₂) and falling to around 20-25 mol% at lower oxygen levels (1.5 vol%). This maximum in methanol selectivity was due to the large (30 mm) diameter reactor used in these experiments and not to the types of mixers used (see Task 3.5). The $\frac{1}{2}$ -inch Kenics mixer (mixer (5)) performed the best in this range of oxygen concentrations, showing a monotonic increase in methanol selectivity with decreasing oxygen level. The maximum

methanol selectivity with this mixer was slightly over 40 mol% at an oxygen concentration of 1.5 vol%. This is equivalent to the best selectivity determined in the earlier process variable studies. At oxygen concentrations above about 6-8 vol%, mixer type had little effect on methanol selectivity. Figures 24 and 25 show that methane and hydrocarbon conversions were not significantly affected by mixer type over the entire range of oxygen concentrations.

With every mixer type the maximum methanol yield was around 2.5 mol% (Figure 26) and occurred at high oxygen concentrations (> 8 vol% O_2). As would be expected from the methanol selectivity results, there is a difference in performance at lower oxygen levels (at and below about 6 vol% O_2), where the $\frac{1}{4}$ -inch Kenics mixer produced higher yields than the other mixer types. The superior performance of the $\frac{1}{4}$ -inch Kenics mixer is probably due to improved mixing brought about by the efficient design of the static mixing elements and the fact that this mixer operates in the turbulent flow regime.

These results indicate that mixer configuration does have some effect on the performance of the system, particularly in terms of methanol selectivity. However, since the methanol yield is not significantly affected, and the maximum methanol yield not affected at all, it does not appear that improved mixing will lead to any significant improvement in process economics.

2. Effect of Reaction Modifiers

As mentioned above, work in this area focused on the effect of different reaction modifiers and oxidizers on this system. The reaction modifiers that were studied were water, acetone (a source of methyl radicals), and nitrous oxide (a strong chemical oxidant).

A. Addition of Water and Acetone—One method of controlling the selectivity of methane, partial oxidation is to attempt to exert control over the free radical reactions that drive this reacting system. Two potential reaction modifiers are water and acetone (CH_3COCH_3). One of the detrimental free radical reactions that can take place during partial oxidation is the formation of water through the abstraction of a hydrogen atom from methane by a hydroxyl radical:

When this reaction occurs, the hydrogen balance of the system forces the production of unwanted highly oxidized species, including carbon oxides. By adding water to the system this reaction may be driven to the left. Of course, another possibility is that with more water present there would also be more hydroxyl radicals available to react with methane. In this case, overall methanol selectivity would decrease with steam addition.

The addition of acetone to the system may introduce a source of methyl radicals:

This may serve to initiate the reaction in a different way than by standard hydrogen abstraction, possibly at a lower temperature more conducive to methanol formation (see Task 3.2 above). To test these possibilities the reactor was modified to allow the introduction of a liquid stream in addition to the standard gas feed. Water, acetone, and water/acetone mixtures could be prepared and pumped to the reactor at precise flow rates using a standard Beckman liquid chromatograph pump.

Figure 27 shows that the addition of steam (at 10 g/min) appears to have a detrimental impact on methanol selectivity. In other experiments both dilute acetone (5 wt% in water) and pure acetone was added to the reactor. Figure 27 shows that addition of dilute acetone at 5 wt% concentration increases methanol selectivity somewhat, bringing it near or slightly above the levels observed when there was no liquid addition. The data in the figure also indicate that doubling the flow rate of the acetone/water feed has only a small effect on methanol selectivity.

Since the addition of small amounts of acetone appeared to increase methanol selectivity, experiments were made using pure acetone as the liquid feed. The effects of pure acetone addition were calculated even though there were problems with the mass balances of these runs and the data could not be analyzed in the normal manner. This was done by noticing that the overall stoichiometry of the partial oxidation reactions is such that the methanol selectivity can be estimated from the ratio of water and methanol in the product liquid. This is possible because water is generated in the partial oxidation only when CO_x (CO and CO_2) are formed:

If we know the relative amounts of H_2O and methanol produced in this reaction, from the above stoichiometry we can make an estimation of the methanol selectivity, defined as:

$$\text{Est'd MeOH Selectivity} = \frac{\text{moles MeOH formed}}{(\text{moles MeOH} + \text{moles } \text{CO}_x)}$$

The determination of water and methanol in the liquid product is accomplished by gas chromatography, and this measurement has been found to be quite accurate and reproducible. In previous mass-balanced runs, this procedure produced estimates of methanol selectivity that were reasonable, but generally higher (by about 10-20 abs%) than those calculated using all of the analytical and flow data.

Using this procedure, the methanol selectivities of the three pure acetone addition runs were estimated. They are given in Table I along with their respective uncertainties.

Table I
Methanol Selectivity for Runs with Pure Acetone Co-Feed

Run Number	vol% O ₂ in feed	Estimate of MeOH Selectivity from Stoichiometry, %	Methanol Sel. without Liquid Feed,* %
44.012	1.6	30 ± 15	40 ± 3
44.010	9.1	25 ± 15	29 ± 3
44.011	12.5	30 ± 15	23 ± 2

*Average of methanol selectivities from earlier runs at similar temperature, pressure, and residence time, but without steam or acetone addition. Standard deviation of average selectivity value is also given (from Figure B-2 in Appendix B).

Even though these estimates are relatively rough, they are good enough to conclude that adding pure acetone to the system does not improve methanol selectivity significantly above that observed in the absence of acetone co-feed. Moreover, other runs investigating temperature effects showed that addition of acetone does not facilitate the initiation of the partial oxidation reaction at lower temperatures. The above results indicate that the addition of water and acetone as reaction modifiers does not improve methanol selectivity in this system.

B. Use of Nitrous Oxide in Place of Pure Oxygen—There is a substantial body of oxidative coupling literature that indicates that the use of nitrous oxide (N₂O) as an oxidant in the system provides higher selectivities to desired products than the use of molecular oxygen (O₂). An attempt was made to extend these studies to this lower temperature, non-catalytic partial oxidation system. After a thorough safety review, a cylinder of nitrous oxide was purchased and attached to the oxygen feed system of the pilot plant. The reaction of nitrous oxide with methane is more exothermic than the reaction of molecular oxygen and methane:

Because of safety considerations, a maximum system pressure of 600 psig was allowed (to prevent nitrous oxide condensation in the feed lines), and as a further precaution the reactor was packed with inert 6 mm quartz beads to reduce reactor dead volume. An extensive series of tests was made to determine the effect of using nitrous oxide in place of oxygen. It was soon discovered that, even though the reaction of methane with nitrous oxide is more exothermic than the reaction of methane with oxygen, it is much more difficult to initiate the nitrous oxide reaction. At 600 psig, no reaction was observed with N₂O even at temperatures of 1200°F. In a number of runs oxygen was added to the feed in small concentrations to initiate the reaction,

but in these cases there was no observable reaction of nitrous oxide, and the products of the reaction were typical of CH_4/O_2 reaction (methanol selectivities between 20 and 40 mol%).

Another series of runs was made after removal of the quartz bead reactor packing. The pressure was lowered to 50 psig and the temperature raised to 1500°F, the highest temperature achievable on the pilot plant. Only at these conditions were reaction products observed, but only carbon monoxide formation was detected. It is possible that methanol was the primary product of the partial oxidation, but at this temperature it would quickly decompose to carbon monoxide and hydrogen. Also, significant coking of the reactor was observed at these conditions. We concluded that the reaction of methane and nitrous oxide is not feasible in a non-catalytic system. Other, successful studies of the nitrous oxide + methane reaction have taken place at higher temperatures in catalytic systems where ethane and ethylene were the desired products.

After these studies were completed, a paper describing a detailed study of the noncatalytic reaction of methane and nitrous oxide appeared in the Russian literature.⁽¹⁷⁾ With a N_2O oxidant at atmospheric pressure, temperatures of 1300°F (700°C) were needed to obtain appreciable methane conversions (~5 mol%). Under these conditions the products were C_2+ hydrocarbons and carbon oxides. This paper essentially corroborates our results. The fact that we did not observe any C_2+ hydrocarbon formation is not surprising because our feed contained substantial amounts of ethane and propane. Any small increase in these species through chemical reaction would not be readily observable. Based on these results we conclude that the reaction of methane with nitrous oxide to selectively form methanol is not feasible in a noncatalytic system. The addition of a catalyst to the system to reduce the activation energy of the reaction remains a possible avenue of research, but was beyond the scope of this project.

Task 3.4: Effect of Product Quench

Scoping studies were performed to test the effects of rapidly quenching the hot product gases. As noted in the "Experimental Equipment" section, the current pilot plant design utilizes an external cooling water quench located just downstream of the heated reaction zone. A series of experiments of varying oxygen concentration was run both with and without this cooling water quench system operating. The results of these experiments are presented in Figures 28-31. There is no observable effect of the cooling water quench on conversion (Figures 28 and 29), product selectivity (Figure 30), or methanol yield (Figure 31). Since relatively long residence times (20-60 seconds) were found to be optimal (see Task 3.2 above), it was not expected that rapid quenching of the products would have any significant effect on this system. In these experiments gas flow rates were adjusted to achieve a residence time of 55 seconds (with the quench on). Based on temperature profiles observed in the reaction and quench zones, running without the cooling water quench caused the product gases to see kinetically significant temperatures (i.e. above 680°F) for about 65 seconds. This is only 10 seconds longer than with the quench operating, leaving the product distribution essentially

unchanged. These results corroborate the residence time studies reported above under Task 3.2.

Task 3.5: Effect of Reactor Design

Burch et al.⁽¹³⁾ suggest that one possible reason that they were not able to reproduce the high methanol selectivities and yields reported by Gesser et al. might be differences in reactor design between the respective experimental systems. To study this effect, we investigated three different reactor design parameters: reactor diameter (aspect ratio), reactor packing, and the presence of reactor internals designed to ensure plug flow in the reaction zone. The results from these studies are reported in the following sections.

1. Reactor Diameter Experiments

Experiments were made to explore the effects of different reactor diameters and surface-to-volume (S/V) ratios on methanol yield and selectivity. Different size quartz reactor liners were used in these studies: a "large" 31 mm diameter tube, a "medium" 19 mm diameter tube, and a "small" 10.5 mm diameter tube. All reactor configurations utilized the same 13-inch long, 3-zone electric furnace. The packed bed mixer (see Task 3.3) was used in all experiments. The calculated surface-to-volume (S/V) ratios of the heated zone of the different reactors are given in Table II. These calculations include the additional surface area (and reduced volume) caused by the presence of a quartz-sheathed thermocouple probe which intruded into the reaction zone. Also included in the table is the S/V for a quartz-packed reactor, which will be described in a following section.

With each size of reactor, the effects of temperature and oxygen concentration were investigated. These two parameters were chosen for study because they had the largest effect on methanol yield and selectivity in previous process variable experiments (see Task 3.2 above). For each reactor size, temperatures were varied between 700°F and 1200°F and oxygen concentrations between 1.5 vol% and 12.5 vol%. Pressures between 1100 and 1300 psig were used in all runs because methanol yield is maximized in this range. Because of plant size considerations, the use of different reactor diameters precluded operating at constant residence time between reactor sizes. For the small, medium and large diameter reactors the residence times were around 16, 30, and 55 seconds, respectively. Previous process variable studies showed that methanol yield and selectivity did not vary significantly within this residence time range.

Table II
Surface-to-volume ratio of various reactor configurations

Reactor Diameter (mm)	Surface Area (cm ²)	Heated Volume (cm ³)	Surface/Volume (cm ⁻¹)
31	311	230	1.4
19	235	88	2.7
10.5	147	23	6.4
31 (packed)	1540*	86†	17.9

*Assumes all surface area of beads is exposed; zero contact area between beads

†Void volume

A. Temperature Effects—Experiments were made to test the effect of reactor temperature with each reactor size and results are presented in Figures 32 and 33. As mentioned above, the temperatures indicated in these figures correspond to average temperatures in the reaction zone. Even though the reactor heater was set for constant temperature, the size of the reactor (1.5 inch ID) and the design of the furnace precluded isothermal operation. A significant temperature rise through the reactor (generally between 100 and 200°F) was observed in all runs. External thermocouples measured temperatures at three different points on the reactor (corresponding to the beginning, middle, and end of the reaction zone), and the temperatures reported below are averages of these three readings.

The most noticeable trend in these figures is that the small diameter reactor appears to be much more sensitive to high temperatures ($T > 900^{\circ}\text{F}$) than the medium or large diameter reactors. Figure 32 shows that with the small reactor methanol selectivity dropped from 26% to only 7% as temperature increased from 900 to 1100°F. It should be noted that this observation is strongly based on a single high-temperature data point. With the medium and large diameter reactors methanol selectivity decreased to only 20% from 27% over the same temperature range. This effect is probably due to increased decomposition of methanol on the walls of the reactor at higher temperatures. The smaller diameter reactor has a higher surface to volume ratio and therefore is more sensitive to these wall effects.

It is also possible that there existed higher temperature regions in the smaller reactor because there was a significant dead space between the quartz reactor liner and the external (heated) steel pressure shell. This dead space may have hindered heat transfer from the exothermic reaction zone to the cooler steel pressure shell, leading to higher hot spot temperatures than measured with the external thermocouples. Using similar reasoning, the larger diameter reactors would have had enhanced heat transfer. Internal thermocouples indicated slightly higher internal temperatures in the smaller diameter reactor, but these indications are inconclusive because measurements were taken at only one point in the reaction zone and probably do not

represent reactor hot spot temperatures. In any case, it appears that the methanol selectivity is relatively independent of reactor diameter below about 900°F.

Hydrocarbon conversion was not affected by reactor diameter, so the change in methanol selectivity is reflected in the methanol yield trends (Figure 33). Methanol yield is highest (ca. 2.5 mol%) at temperatures below about 900°F. Higher temperatures are more detrimental to methanol yield in the smaller-diameter reactor.

B. Oxygen Concentration Effects—A series of experiments was performed where the oxygen concentration was varied between 1.5 and 12.5 vol% in each of the three open tube reactors. The most significant difference between the various sized reactors is in methanol selectivity (Figure 34). With both the "medium" (19 mm) and "small" (10.5 mm) diameter reactors, selectivity to methanol increased monotonically with decreasing oxygen concentration. With the "large" (31 mm) reactor, however, there is a clear maximum in methanol selectivity in the range of 3-5 vol% oxygen.

To study this behavior more thoroughly, a series of runs was made in which the large-diameter reactor was packed with 6 mm x 6 mm quartz beads. In this way reactor diameter and surface-to-volume ratio were effectively decoupled. The void fraction of this packed reactor was measured by water displacement and found to be 0.37. Figures 35 and 36 present results of a series of packed bed and open tube runs with different oxygen concentrations. Figure 35 clearly indicates that packing the large diameter reactor makes it behave more like the smaller (10.5 mm diameter) reactor. Figure 36 indicates that, in general, methanol yields in the packed reactor are not significantly different than those in the open (unpacked) reactors. This is because at lower oxygen concentrations, where the selectivity difference is greatest, hydrocarbon conversion and therefore methanol yield are quite low. The maximum methanol yield approaches 2.5 mol% regardless of reactor diameter and occurs at the higher oxygen concentrations.

At this stage it appears that reactor surface-to-volume ratio is an important reactor design parameter only at low oxygen concentrations and higher temperatures. Higher surface-to-volume ratios seem to increase methanol selectivity at low (<5 vol%) oxygen concentrations. There are two possible explanations for this. One is that there is a kinetic (wall) effect that stabilizes methanol-producing intermediates at low oxygen concentrations. Another possibility is that heat transfer is better in the packed reactor than in the large open tube reactor. If this were the case, the reaction exotherm would cause the internal temperature of the reactor to be higher in the open tube reactor versus the packed reactor. High reaction temperatures ($T > 900^\circ\text{F}$) were shown to be detrimental in the previous section. As mentioned above, actual measurements of internal temperature have proven inconclusive because they are taken at discrete points in the reactor and these may not correspond to the reactor hot spot.

Interestingly, when a different pre-reaction mixer was used (see Task 3.3 above) this selectivity maximum disappeared and the curve was monotonic, even with a large diameter reactor. This behavior is therefore more complex than

simple reactor diameter experiments can completely illuminate. Although this behavior is quite intriguing, further study was not pursued because the observed maximum in methanol selectivity occurs at low oxygen concentrations where hydrocarbon conversion (and therefore methanol yield) is very low.

In all three reactors, both methane and overall hydrocarbon conversions increase with increasing oxygen concentration, as shown in Figure 37.

The selectivity results reported above are interesting and may help explain some inconsistencies apparent in the methane partial oxidation literature. Most workers report a monotonic increase in methanol selectivity with decreasing oxygen (as in our smaller diameter reactors), but some^(3,12) have observed a maximum selectivity occurring around 4-8 vol% oxygen (as in our large diameter reactor). It is possible that wall effects and/or wall reactivity could play a role in explaining these discrepancies.

2. Plug Flow Internals

A series of experiments was run to test the efficacy of reactor internals designed to promote plug flow in the reaction zone. Since the desired product in this system (methanol) reacts more readily with oxygen than the methane feed, any backmixing in the reaction zone will serve to reduce both methanol selectivity and overall yield. To help promote plug flow in the reaction zone, a quartz fritted disk was placed at the top of the reaction (heated) zone. This prevented any eddies or jets that may be created at the feed inlet ports from entering the reaction zone. A series of runs was then made at various oxygen concentrations and pressures using a 25 mm diameter reactor and a packed bed mixer.

Figures 38-40 show the effects of these plug-flow internals on methanol selectivity, methane conversion, hydrocarbon conversion, and methanol yield, respectively, as a function of oxygen concentration. The runs with the fritted disk internals are compared with runs at similar conditions without the fritted disk (i.e. open tube runs).

All of the figures show that there is no significant effect of the fritted disk on either selectivity or conversion. Figure 38 indicates that methanol selectivity increases monotonically with decreasing oxygen concentration both with and without the fritted disk internals. Differences between the two series of runs are well within the experimental uncertainty. Figure 39 shows that conversion is not affected by the presence of the fritted disk internals, while Figure 40 indicates that with both configurations the maximum methanol yield is around 2.5 mol%. This maximum occurs at oxygen concentrations above 8 vol%. A series of runs at pressures between 500 and 1300 psig also showed that the fritted disk internals had no effect on the reaction.

These results indicate that the observed selectivities and conversions are not being limited by backmixing caused by eddies or jets from the feed injection ports. We cannot, however, conclude from this that backmixing in the reactor is not a problem. Due to the high temperatures and relatively long residence times in the vertical reactor, the existence of thermal convection currents cannot be ruled out. Such thermal convection in the reaction zone would not

be affected by the fritted disk at the very top of the reactor. The fact that the reactor is top-fed would magnify the detrimental effects of any convection currents because the methanol-rich convection current would be carried up into the more oxygen-rich zones where the methanol could be further oxidized.

Task 3.6: Effect of Reactor Recycle

A series of runs was made in which various product gas species (CO_2 , CO and H_2) were added to the natural gas feed to simulate the effects of reactor recycle. In the initial runs, these product gases were individually added to the feed to determine their fate in the reactor and any effects they may have on hydrocarbon conversion or product selectivity. In the later runs, mixtures of these gases were simultaneously added to more closely simulate a true mixed feed/recycle stream. In all of these runs the base conditions were: 800°F , 1300 psig, and 20-60 second residence time. A 30 mm diameter reactor and $\frac{1}{4}$ -inch diameter Kenics mixer were used in all runs.

1. Effects of Added Carbon Dioxide

A number of runs were made in which CO_2 was added to the hydrocarbon feed and the oxygen concentration in the reactor was varied. As indicated in Figures 41-44, the addition of 5-20 vol% CO_2 to the hydrocarbon feed has a negligible effect on product selectivity and feed conversion. Figure 41 compares methanol selectivity in runs with feeds containing 0, 5, 10 and 20 vol% added CO_2 . Methanol selectivity appears to be slightly (2-3 abs%) lower in the presence of added CO_2 at all oxygen concentrations. However, given the amount of scatter in the data, this difference is only statistically significant (> 90% confidence) at 12.5 vol% oxygen. At lower oxygen concentrations the scatter in the data renders any CO_2 effect indistinguishable within experimental error. In any event the decrease in methanol selectivity is not large, particularly given the high concentrations of CO_2 studied (up to 20 vol%). Figures 42 and 43 show the effects of added CO_2 on net CO and CO_2 selectivity, respectively. They indicate that addition of 0-20 vol% CO_2 to the feed gas has no apparent effect on CO_x selectivity. There is considerable scatter in these data, particularly at high levels of CO_2 addition and low oxygen concentrations. This occurs because under these circumstances the added CO_2 accounts for a majority of the carbon oxide in the product. Calculated CO_x selectivities therefore depend on a small difference between two large numbers, leading to large experimental errors. Figure 44 further shows that formaldehyde selectivity in these systems is low (0.5-4 mol%) and is unaffected by the addition of CO_2 .

In addition, conversion of the hydrocarbon feed is not affected by adding CO_2 to the feed gas, as shown in Figure 45, nor is methanol yield affected (Figure 46). These data conclusively show that the presence of up to 20 vol% CO_2 in the feed has no effect on product selectivity or feed conversion in this system. Therefore, recycle of carbon dioxide will not affect the system (to CO_2 levels of 20 vol%) and so highly efficient CO_2 removal systems will not be needed.

2. Effects of Added Hydrogen

Following the CO₂ addition studies, the natural gas feeds were spiked with varying levels (3-15 vol%) of hydrogen gas. Again, various oxygen concentrations were used in these runs. Methanol selectivity is considerably lower in the presence of added hydrogen, especially at lower oxygen concentrations (Figure 47). Moreover, it appears that the higher the level of H₂ in the feed, the lower the methanol selectivity in the reactor. For example, adding 15 vol% hydrogen to the feed lowered methanol selectivity by 5-15 mol%, while adding 3 vol% H₂ lowered selectivity by only around 2 mol% (within the experimental uncertainty in selectivity values - see Appendix B). Figure 48 shows that the decrease in methanol selectivity is accompanied by a slight increase in selectivity to carbon oxides (CO and CO₂). There is no discernable change in formaldehyde selectivity with hydrogen addition, as shown in Figure 49.

Figure 50 shows the oxygen-based selectivity values for water, indicating that adding hydrogen to the reactor feed increases the amount of feed oxygen that is converted to water. From this it can be postulated that oxygen reacts with hydrogen in the reaction zone. It is somewhat surprising, then, that hydrocarbon conversion in general and methane conversion in particular appear to be unaffected by hydrogen addition to the feed (Figure 51) up to H₂ concentrations of 15 vol%. This apparent contradiction can be explained by noting that the conversion values in Figure 51 are plotted as a function of oxygen concentration. This means that, when added hydrogen is present, it displaces some of the hydrocarbon in the system and therefore the hydrocarbon-to-oxygen molar ratio decreases. Normally, lower hydrocarbon-to-oxygen ratios would lead to higher hydrocarbon conversion, but in this case the hydrogen reacts with some of the oxygen, leaving hydrocarbon conversion unchanged.

This result is important because it indicates that hydrocarbon conversion in this system is driven by the concentration of oxygen in the feed, not by hydrocarbon-to-oxygen ratio. This means that, to keep hydrocarbon conversions constant, more oxygen must be fed to the reactor when the byproduct and diluent concentrations in the recycle stream are higher.

The effects of added hydrogen on methanol selectivity and hydrocarbon conversion combine in such a way that overall methanol yield is lowered upon addition of hydrogen to the reactor feed (Figure 52).

Under standard conditions (i.e. without hydrogen addition), H₂ has been observed to be a minor product of the methane partial oxidation reaction. This being the case, the above results suggest that recycling the unreacted gases from the methanol recovery section will serve to lower per-pass methanol selectivity and yield since hydrogen would build up in the recycle stream. However, we would also expect addition of hydrogen to the reactor feed to affect the production of hydrogen in the reactor itself. Figure 53 illustrates this effect using data from these studies, showing how the level of H₂ in the feed affects the net yield of hydrogen in the reactor. It can be seen that at concentrations up to about 7 vol% hydrogen in the feed, H₂ is still a net product of the reaction at all oxygen concentrations. At the 15 vol% H₂ level, however, there is net consumption of hydrogen at every oxygen

concentration. This suggests that in a steady state recycle operation, the hydrogen concentration at the reactor inlet should stabilize at a value somewhere between 7 and 15 vol%. The extent of the yield penalty in this hydrogen concentration range will depend somewhat on the level of oxygen in the reactor feed, but should fall between 0.1 and 0.5 abs% (from Figure 52).

3. Effects of Added Carbon Monoxide

Following the hydrogen addition studies, the natural gas feed was spiked with carbon monoxide to levels of 3, 7 and 20 vol% and oxygen concentrations were once again systematically varied between 1.5 and 12.5 vol%. Overall it was discovered that the effects of added carbon monoxide on the system were almost identical to the effects of added hydrogen described above.

Figure 54 indicates that the presence of CO in the feed gas lowers the selectivity to methanol, especially at low oxygen concentrations. Moreover, the decrease in methanol selectivity seems to be proportional to the amount of CO in the feed: higher CO levels lead to lower methanol selectivities. This decrease in methanol production is accompanied by an increase in CO₂ selectivity (Figure 55) and a decrease in net CO selectivity (Figure 56). This increase in CO₂ selectivity at the expense of CO is not due to the action of the water gas shift reaction

because no increase in hydrogen production was observed to mirror the increase in CO₂. The CO, then, appears to react directly with the molecular oxygen in the reactor to form carbon dioxide. It might be noted that at 20 vol% CO in the feed and low oxygen concentration, the hydrocarbon-based selectivity to CO₂ is greater than 100%. This is due to the fact that CO conversion under these conditions is significant and produces CO₂. Formaldehyde selectivity increases somewhat with increasing CO concentration (Figure 57), but the effect is not as pronounced as with the other products.

As with hydrogen addition, the presence of CO had no discernable effect on hydrocarbon or methane conversion (Figure 58). Once again this is not because CO does not react with oxygen, but because the determining factor for hydrocarbon conversion is oxygen concentration, not the molar hydrocarbon-to-oxygen ratio.

Because hydrocarbon conversion is unaffected by the presence of CO, the trends observed in methanol selectivity are mirrored in the methanol yield plots, shown in Figure 59. The effect of low levels of CO (3 - 7 vol%) is negligible, but at 20 vol% CO there is a clear decrease in methanol yield. As in previous experiments, the maximum methanol yield is around 2.5 mol% and is obtained at oxygen concentrations between 9 and 12.5 vol%.

Since CO is itself a product of the reaction, we would expect that the presence of CO in the feed might affect the production of CO in the reactor. Figure 60 shows the net production and/or consumption of CO in the reactor as a function of both CO and oxygen concentration. In this figure, CO production

is indicated by a positive value, consumption by a negative value. It is clear that at the lower CO concentrations (0-7 vol%), CO is still a net product of the reaction. With 20 vol% CO in the feed, however, there is net consumption of CO in the reactor at low oxygen concentrations (< 10 vol%), and a small production of CO at the highest oxygen feed level. Based on these observations we would anticipate that in a commercial operation (i.e., with recycle) CO would build up in the recycle loop to a level between 7 and 20 vol%, probably closer to 20 vol%. At this level, methanol selectivity would be depressed by between 2 and 20 abs%, depending on the oxygen level in the feed (from Figure 54).

4. Effects of Added Hydrogen/CO Mixture

The above sections report the effect of recycle gases on the system when added individually to the hydrocarbon feed. It was observed that, while the presence of CO₂ has no effect on the system, the addition of CO and H₂ had a significant impact on methanol selectivity and yield. In the runs reported below, a mixture of CO and H₂ was added to the feed to more closely simulate a true mixed feed/recycle stream.

The CO/H₂ mixture used in these studies had the composition 83% CO and 17% H₂. This particular composition was used because previous studies found that CO and H₂ are produced by the reaction in about this ratio over a wide range of oxygen concentrations. Therefore, addition of this mixture to the natural gas feed should simulate a recycle operation quite well. Carbon dioxide was not added to the mixture because of plant hardware limitations and the finding that CO₂ levels up to 20 vol% had no significant effect on the conversion or selectivity of this reaction. The natural gas feed was spiked with this CO/H₂ mixture to levels of 5, 10 and 20 vol%, which led to CO concentrations of 4, 8 and 16 vol%, and hydrogen concentrations of 1, 2 and 4 vol% in the feed, respectively. Oxygen concentrations were systematically varied between 1.5 and 12.5 vol%, but a full series of oxygen runs was only made for the 10 vol% mixture case, since supplies of the CO/H₂ mixture were limited.

Figure 61 indicates that the presence of mixed CO/H₂ in the feed gas lowers the selectivity to methanol, especially at low oxygen concentrations. This was expected based on the results with pure CO and H₂ spikes, both of which lowered overall methanol selectivity. Moreover, it appears that the effects of CO and H₂ in the reactor are additive. Figure 61 shows how 10 vol% of the mixture (equal to 8% CO and 2% H₂ in the feed) affects methanol selectivity over a range of oxygen concentrations (solid circles and solid line). Also shown is a prediction (open circles and dashed line) of this effect based on a linear interpolation and addition of the previously determined pure H₂ and pure CO effects taken from Figures 47 and 54 respectively. These data show that, within experimental error, the effects of this CO/H₂ mixture can be accurately predicted based on the linear addition of pure component effects. This behavior would prove helpful in predicting real selectivities and yields in a true recycle operation.

As with pure CO and H₂ addition, hydrocarbon and methane conversion are not affected by the presence of the mixture (Figure 62). Since methanol

selectivity decreases and hydrocarbon conversion is unaffected, there is an overall decrease in methanol yield with the addition of CO/H₂, as shown in Figure 63.

The decrease in methanol selectivity observed in Figure 61 is accompanied by an increase in CO₂ selectivity (Figure 64) and a decrease in net CO selectivity (Figure 65). These data consistently show that the presence of CO in the reactor results in much higher CO₂ selectivity, and that the increase in CO₂ selectivity is directly related to the concentration of CO in the feed.

These results, combined with the results from the pure component spiking studies, offer strong evidence that adding recycle to the reactor system would have a significant negative impact on methanol selectivity and yield. Selectivity to carbon dioxide would increase significantly, while hydrocarbon and methane conversion would be unaffected as long as the concentration of oxygen in the reactor feed remains unchanged.

Task 3.7: Enhanced-Yield Catalyst Study

One method that has been proposed for increasing the overall yield of methanol from this system is to use a catalyst post-bed to convert some or all of the CO formed in the partial oxidation reaction. This catalyst bed would be placed downstream of the thermal conversion zone. Several series of runs have been made in our pilot plant to test such a process. Figure 66 shows the reactor configuration that was used in these studies. The catalyst used was a commercial Cu/ZnO/Al₂O₃ methanol synthesis catalyst obtained from United Catalysts Incorporated. A standard methanol catalyst activation procedure was followed consisting of stepwise reduction, flowing H₂/N₂ mixtures of increasing H₂ concentration (between 1 and 20 vol%) and at increasing temperatures (between 380 and 470°F). Tests performed in a separate syngas conversion reactor confirmed that these activation procedures produced an active methanol synthesis catalyst.

Several preliminary runs were made to determine the furnace settings in the thermal zone that would provide typical methanol synthesis temperatures of 450–500°F at the inlet of the catalyst bed. Figure 67 shows that the catalyst post-bed has no observable benefit in terms of overall methanol selectivity, and in some of the runs the methanol selectivity actually decreased when the catalyst post-bed was present. One of the anticipated problems with this system is that the lack of hydrogen in the gas exiting the thermal zone (only around 1 vol%) could severely reduce the amount of methanol that could be formed. To mitigate this effect, hydrogen was added to the reactor feed. Other tests (reported above) indicate that most of this added hydrogen survives the thermal zone of the reactor, and is therefore available for reaction in the catalyst bed. Figure 67 indicates that hydrogen addition does not improve the methanol selectivity: even when up to 25 vol% hydrogen is present in the feed, little or none of the carbon monoxide converts to methanol in the catalyst bed.

In order to better understand this unexpected result, some thermodynamic calculations were made to determine the equilibrium limitations of this system. Based on previous runs without the catalyst post-bed, we are able to

estimate the composition of the gas as it exits the thermal zone and enters the catalyst bed. This composition varies somewhat with the oxygen concentration of the feed, and estimates are given in Table III.

TABLE III
Estimates of Gas Composition (vol%) at Catalyst Bed Inlet

Component	<u>Case 1:</u> 1.6 vol% O ₂ in reactor feed	<u>Case 2:</u> 9.0 vol% O ₂ in reactor feed	<u>Case 3:</u> 12.5 vol% O ₂ in reactor feed
N ₂ and hydrocarbons	95.3	82.2	76.3
CO	1.0	4.4	5.7
CO ₂	1.8	2.0	2.7
H ₂ O	1.0	8.0	11.8
H ₂	0.3	1.2	1.3
Methanol	0.6	2.2	2.2

Given these gas compositions and the temperature measured at the inlet of the catalyst bed, calculations were made to estimate the equilibrium composition of the products at the catalyst bed exit. A Gibbs Free Energy minimization routine was utilized to determine these equilibrium compositions, and the results are presented in Table IV for the same three cases shown in Table III.

Shown in the bottom line of Table IV is the net methanol consumption in the catalyst bed. This is defined as the difference between the moles of methanol entering the catalyst bed and those exiting the catalyst bed, expressed as a percentage of the inlet methanol. It can clearly be seen that in every case, thermodynamics predicts there to be almost complete consumption of methanol in the catalyst bed, i.e. methanol will decompose to CO and H₂ at the prevailing conditions. This methanol decomposition is due to the composition of the gas entering the catalyst bed; it is very lean in hydrogen and the ratio of methanol to CO is relatively high. These factors combine to drive the reaction in the catalyst bed in the direction of methanol decomposition. Lowering the temperature of the catalyst bed improves the thermodynamics slightly, but even at bed temperatures of 400°F (well below commercial methanol plant operating temperatures and in the regime of severe kinetic limitations), more than 85% of the inlet methanol would be decomposed in the catalyst bed. The methanol consumption data in Table IV are presented graphically in Figure 68.

TABLE IV
Equilibrium Composition (vol%) of Gas At Catalyst Bed Exit at Various Temperatures

Catalyst Bed Inlet Temp (°F) →	Case 1: 1.6 vol% O ₂ in feed			Case 2: 9.0 vol% O ₂ in feed			Case 3: 12.5 vol% O ₂ in feed		
	400° F	450°F	500°F	400° F	450°F	500°F	400°F	450°F	500°F
"Inerts"*	95.1	95.1	95.0	79.3	79.1	78.9	73.5	73.3	73.2
CO	0.6	0.6	.07	0.2	0.4	0.5	0.1	0.2	0.4
CO ₂	1.8	1.8	1.8	7.7	7.7	7.6	9.8	9.8	9.7
H ₂ O	0.0	0.1	0.1	1.9	1.9	2.0	4.2	4.1	4.2
H ₂	2.4	2.5	2.4	10.5	10.8	10.9	12.1	12.4	12.4
MeOH	0.1	0.0	0.0	0.3	0.2	0.1	0.3	0.1	0.1
Net MeOH Consumption in Catalyst Bed (mol%)	92.0	97.7	99.3	84.5	92.4	96.5	86.2	93.2	96.8

* Nitrogen and all hydrocarbon species are assumed to be inert in the catalyst bed.

While this thermodynamic analysis predicts a significant decrease in methanol selectivity in the presence of the catalyst post-bed, our experimental data show no such trends. This indicates that the system that has been studied is kinetically limited and equilibrium is not reached in the catalyst bed. In addition to predicting a decrease in methanol concentration, the above thermodynamic analysis predicts a net decrease in CO selectivity. Figure 69 shows that the presence of the catalyst post-bed does indeed lead to less CO production. This is an indication that the bed is catalytically active, but is under kinetic control.

The above thermodynamic calculations were based on gas compositions where no extra hydrogen was added to the reactor feed. Whereas the experimental results showed no beneficial effects of added H₂ (Figure 67), Table V shows that extra hydrogen improves the thermodynamics of the system slightly, giving less methanol consumption, particularly at high hydrogen concentrations and low catalyst bed temperatures.

The effect of hydrogen on methanol consumption is shown graphically in Figure 70. Only with 25 vol% added H₂ and a catalyst bed temperature of 400°F does thermodynamics predict that there will be methanol produced in the catalyst bed (in this case about 15% more methanol at the catalyst bed outlet than at the inlet). The addition of this much hydrogen (producing an H₂/CO ratio of around 5) will not be cost-effective, and the catalyst activity at bed temperatures of around 400°F is far below commercial levels. Moreover, addition of these high levels of hydrogen to the reactor feed decreased methanol yield in the thermal reaction zone (by 20 to 40% - see Task 3.6).

TABLE V
Effect of Added Hydrogen on Equilibrium Catalyst Bed Exit Gas Composition
and Methanol Production (9.0 vol% O₂ in reactor feed)

Temperature	7.0 vol% added hydrogen				25 vol% added hydrogen			
	400°F	450°F	500°F	550°F	400°F	450°F	500°F	550°F
"Inerts"	73.3	72.8	72.5	72.3	57.6	56.7	56.0	55.5
CO	0.2	0.4	0.7	1.0	0.2	0.4	0.8	1.3
CO ₂	7.3	7.4	7.3	7.1	5.9	6.3	6.5	6.4
H ₂ O	2.5	2.3	2.3	2.5	4.2	3.6	3.3	3.3
H ₂	15.9	16.7	17.0	17.0	29.6	31.3	32.4	33.0
MeOH	0.8	0.5	0.2	0.1	2.5	1.7	1.0	0.5
MeOH Consump. in Cat. Bed (mol%)	61.1	78.1	89.1	94.9	-14.7	22.3	52.8	74.6

Based on these experimental and theoretical results, we determined that it was not beneficial to pursue the study of catalytic post-bed systems any further. The experimental results show that the presence of a catalyst post-bed had no beneficial effect on methanol selectivity, even at high levels of added H₂. Although there is evidence for kinetic limitations in our catalyst post-bed, even with a more active catalyst the thermodynamic analysis presented here indicates that under almost all operating conditions the driving force for the catalytic conversion is toward methanol decomposition, rather than formation.

CONCLUSIONS

The results reported above can be conveniently grouped into three main areas of study: process variable studies, reactor and process design studies, and the effect of reaction modifiers on the system. The main conclusions from each of these areas of study are given below:

1. Process Variable Studies

1. Higher (C₂₊) hydrocarbons in the feed significantly decrease per-pass methane conversion in this system. This behavior could impact the process economics, since lower per-pass methane conversions generally translate to poorer economics.
2. Lower oxygen concentrations improve methanol selectivity, but reduce per-pass hydrocarbon conversion. Methanol yield increases with increasing oxygen concentration, and the maximum methanol yield observed was between 2.5 and 3.0 mol%. This is far below the 15 mol% yield expected to be necessary for economic viability.

3. Lower temperatures and higher pressures are desirable for maximizing methanol yield. Average reactor temperatures of 700–800°F and a pressure of 1300 psig appear to be optimal within the ranges studied.
4. There appears to be a broad maximum in methanol yield at residence times of 30–60 seconds. Methanol yield drops sharply at residence times lower than this, and gradually at higher residence times.
5. The residence time experiments suggest that conversion of methane in this system appears to be limited by a mass or heat transfer effect, rather than by the kinetics of the partial oxidation.

2. Reactor and Process Design Studies

1. Reactor diameter (surface-to-volume ratio) can be an important parameter in this system. This is particularly true at higher temperatures ($T > 900^{\circ}\text{F}$) where a larger diameter reactor gave significantly higher methanol yield, and at low oxygen concentrations, where a smaller diameter reactor gave the best results.
2. Packing the large diameter reactor with quartz beads improved methanol selectivity at low oxygen concentrations (below 6 vol% O_2), but had little effect at higher oxygen levels.
3. Preventing backmixing in the reaction zone through the use of plug flow-inducing internals did not significantly affect methanol selectivity or yield. It is still possible, however, that backmixing caused by thermal convective currents may be present in this system.
4. In this system, rapid quenching of the product gases did not improve methanol yield or selectivity.
5. Mixer type had some effect on methanol selectivity at low oxygen concentrations (below about 6 vol% O_2), but no effect at higher oxygen levels. The best mixer tested was a ¼-inch Kenics in-line static mixer.

3. Effect of Reaction Modifiers

1. Carbon dioxide is essentially inert in the reactor. There is no significant effect of added carbon dioxide on either product selectivity or hydrocarbon conversion up to CO_2 levels of 20 vol%.
2. Both added CO and added H_2 decrease overall methanol selectivity in this reaction by as much as 30% (relative). The magnitude of the selectivity decrease is proportional to the amount of CO and/or H_2 added. When CO and H_2 are added simultaneously, their effects on methanol selectivity appear to be additive.

3. The factor controlling hydrocarbon conversion in this system is the concentration of oxygen in the reactor feed, not hydrocarbon-to-oxygen ratio. This is true even when other oxidizable species (e.g. CO and H₂) are present in the reactor feed.
4. The presence of a post-bed of methanol synthesis catalyst does not improve overall methanol selectivity. A thermodynamic analysis shows that, given the gas composition exiting the thermal zone of the reactor, a catalyst post-bed would be detrimental, leading to decomposition of any methanol formed in the thermal zone.
5. The addition of acetone and steam as reaction modifiers did not improve and in some cases decreased methanol selectivity and yield in this system.
6. The non-catalytic reaction of methane (natural gas) and nitrous oxide is initiated only at temperatures above about 1300°F. Under these conditions carbon oxides are the primary products of the reaction, and there is significant coking in the reactor. In order to achieve any methanol production benefits from this reaction, a catalyst is needed to lower the activation energy of this reaction so it can occur at lower temperatures.

Based on all of the above conclusions, it is evident that the gas phase free radical reactions that define this non-catalytic system are inherently unselective to methanol. The maximum methanol yield observed in these studies was between 2.5 and 3.0 mol%, far below the 15 mol% yield expected to be necessary for economic viability. Extensive efforts to improve methanol selectivity through control of process variables, reactor and process design, and the presence of reaction modifiers have proven unsuccessful. Any future investigation of direct conversion of methane to methanol (if any) should concentrate on developing a catalyst that will allow the reaction to proceed at low temperatures (<600°F) where these unselective free radical reactions do not take place.

ACKNOWLEDGEMENT

We would like to acknowledge the United States Department of Energy for providing financial support for this work, and Mr. Anthony La Puma for expert operation of the pilot plant.

REFERENCES

1. D. M. Newitt and A. E. Haffner, Proc. R. Soc. London, Ser. A, 134, 591, (1932).
2. H. D. Gesser, N. R. Hunter and L. A. Morton, U.S. Patent 4,618,732; October 21, 1986.
3. C. D. Chang, Catalysis Reviews, Heinz Heinemann (ed.), 25(1), 1-129, (1983).
4. P. J. Wiezevich and P. K. Frolich, Ind. Eng. Chem., 26(3), 267-76, (1934).
5. E. H. Boomer and J. W. Broughton, Can. J. Res., 15(B), 375-82, (1937).
6. E. H. Boomer and V. Thomas, Can. J. Res., 15(B), 401-13, (1937).
7. E. H. Boomer and V. Thomas, Can. J. Res., 15(B), 414-33, (1937).
8. N. R. Hunter, H. D. Gesser, L. A. Morton, P. S. Yarlagadda and D. P. C. Fung, Appl. Catal., 57, 45-54, (1990).
9. P. S. Yarlagadda, L. A. Morton, N. R. Hunter and H. D. Gesser, Ind. Eng. Chem. Res., 27, 252-6, (1988).
10. P. S. Yarlagadda, L. A. Morton, N. R. Hunter and H. D. Gesser, Fuel Sci. & Tech. Int'l., 5(2), 169-83, (1987).
11. N. R. Hunter, H. D. Gesser and L. A. Morton, Preceedings of the International Symposium on Alcohol Fuels Technology, Vol II, May 21-25, 1984, Ottawa, Canada, 147-53.
12. H. D. Gesser, N. R. Hunter and C. B. Prakash, Chemical Reviews, 85(4), 235-44, (1985).
13. R. Burch, G. D. Squire and S. C. Tsang, J. Chem. Soc., Faraday Trans. 1, 85(10), 3561-8, (1989).
14. D. W. Rytz and A. Baiker, Ind. Eng. Chem. Res., 30, 2287-92, (1991).
15. M. J. Brown and N. D. Parkyns, Catalysis Today, 8, 305-35, (1991).
16. I. Tepermeister and J. Smith, Report LA-11396-MS, MIT-LANL-3, August 1987.
17. N. I. Il'chenko, L. N. Raevskaya et al., Kinet. Katal., 32(2), 260-66, 1991.

FIGURE 1
Methane Conversion Pilot Plant

FIGURE 2

Effect of Feed Type on Methanol Yield
Natural Gas vs. Pure Methane Feed; 9 vol% O₂

Methanol Yield (%)

FIGURE 3

Effect of Feed Composition on MeOH Selectivity
Natural Gas vs. Pure Methane Feed; 9 vol% O₂

Methanol Selectivity (%)

FIGURE 4

Effect of Feed Composition on Methane Conversion
Natural Gas vs. Pure Methane Feed; 9 vol% O₂

Methane Conversion (%)

FIGURE 5

Effect of Ethane Level on Hydrocarbon Conversion
P=1300 psig; T=800 F; 9 vol% O₂

Hydrocarbon Conversion (%)

FIGURE 6

Effect of Ethane Level on Methane Conversion

P=1300 psig; T=800 F; 9 vol% O₂

CH₄ Conversion (%)

FIGURE 7

Effect of Ethane Level on Product Selectivity

P=1300 psig; T=800 F; 9 vol% O₂

Product Selectivity (%)

Methanol CO CO₂

FIGURE 8

Effect of Ethane Level on Product Yield
 $P=1300$ psig; $T=800$ F; 9 vol% O_2

FIGURE 9

Effect of Oxygen Level on Product Selectivity
 $T=800$ F; $P=1300$ psig; Res. Time=35 sec.

FIGURE 10

Effect of Oxygen Level on Hydrocarbon Conversion

T=800 F; P=1300 psig; Res. Time=35 sec

Hydrocarbon Conversion (%)

FIGURE 11

Effect of Oxygen Level on Product Yield

T=800 F; P=1300 psig; Res. Time=35 sec.

Yield (mol%)

FIGURE 12

Effect of Oxygen Level on Methane Conversion

T=800 F; P=1300 psig; Res. Time=35 sec

Methane Conversion (%)

FIGURE 13

Effect of Temperature on Methanol Yield

Res. Time=35 sec; HC/O₂=10

Methanol Yield (%)

FIGURE 14

Effect of Temperature on Product Selectivity
Res. Time=35 sec; HC/O₂=10; 825-1300 psig

FIGURE 15

Effect of Temperature on Methane Conversion
Res. Time=35 sec; HC/O₂=10

FIGURE 16

Effect of Pressure on Methanol Yield

Res. Time=35 sec; HC/O₂=10

FIGURE 17

Effect of Pressure on Product Selectivity

Res. Time=35 sec; HC/O₂=10; 800 F

FIGURE 18

Effect of Residence Time on Methanol Yield

T=800 F; P=1300 psig; HC/O₂=10

FIGURE 19

Effect of Residence Time on Methanol Selectivity

T=800 F; P=1300 psig; HC/O₂=10

FIGURE 20

Effect of Residence Time on Methane Conversion

T=800 F; P=1300 psig; HC/O₂=10

Methane Conversion

FIGURE 21

Effect of Flow Rate on Methane Conversion

T=800 F; P=1300 psig; HC/O₂=10

Methane Conversion

FIGURE 22

Effect of Residence Time on HC Conversion

T=800 F; P=1300 psig; HC/O₂=10

Hydrocarbon Conversion

FIGURE 23

Effect of Mixer Type on Methanol Selectivity

T=800 F; P=1300 psig; 30 mm Diameter Reactor

Methanol Selectivity (mol%)

FIGURE 24

Effect of Mixer Type on Methane Conversion
 T=800 F; P=1300 psig; 30 mm Diameter Reactor

Methane Conversion (mol%)

FIGURE 25

Effect of Mixer Type on Hydrocarbon Conversion
 T=800 F; P=1300 psig; 30 mm Diameter Reactor

Hydrocarbon Conversion (mol%)

FIGURE 26

Effect of Mixer Type on Methanol Yield

T=800 F; P=1300 psig; 30 mm Diameter Reactor

Methanol Yield (mol%)

FIGURE 27

Effect of Acetone on Methanol Selectivity

T=725 F; P=1300 psig; Res. Time=60 sec.

Methanol Selectivity (mol%)

FIGURE 28

Effect of Product Quench on Hydrocarbon Conv.
T=800 F; P=1300 psig; 25 mm Diameter Reactor

Hydrocarbon Conversion (mol%)

FIGURE 29

Effect of Product Quench on Methane Conversion
T=800 F; P=1300 psig; 25 mm Diameter Reactor

Methane Conversion (mol%)

FIGURE 30

Effect of Product Quench on Methanol Selectivity
T=800 F; P=1300 psig; 25 mm Diameter Reactor

Methanol Selectivity (mol%)

FIGURE 31

Effect of Product Quench on Methanol Yield
T=800 F; P=1300 psig; 25 mm Diameter Reactor

Methanol Yield (mol%)

FIGURE 32

Reactor Diameter Effect on Methanol Selectivity

T=800 F; P=1300 psig; Res Time=10-60 sec.

Methanol Selectivity (mol%)

FIGURE 33

Effect of Reactor Diameter on Methanol Yield

T=800 F; P=1300 psig; Res Time=10-60 sec.

Methanol Yield (mol%)

FIGURE 34

Effect of Reactor Diameter on MeOH Selectivity

T=800 F; P=1300 psig; Res Time=10-60 sec.

Methanol Selectivity (mol%)

FIGURE 35

Effect of Reactor Packing on MeOH Selectivity

T=800 F; P=1300 psig; Res Time=10-60 sec.

Methanol Selectivity (mol%)

FIGURE 36

Effect of Reactor Packing on Methanol Yield
 T=800 F; P=1300 psig; Res Time=10-60 sec.

Methanol Yield (mol%)

FIGURE 37

Effect of Reactor Diameter on Feed Conversion
 T=800 F; P=1300 psig; Res Time=10-60 sec.

Conversion (mol%)

FIGURE 38

Effect of Plug Flow Internals on Methanol Selec.
 T=800 F; P=1300 psig; 25 mm Diameter Reactor

Methanol Selectivity (mol%)

FIGURE 39

Effect of Plug Flow Internals on Feed Conversion
 T=800 F; P=1300 psig; 25 mm Diameter Reactor

Conversion (mol%)

FIGURE 40

Effect of Plug Flow Internals on Methanol Yield
T=800 F; P=1300 psig; 25 mm Diameter Reactor
Methanol Yield (mol%)

FIGURE 41

Effect of Added CO₂ on Methanol Selectivity
P=1300 psig; T=800 F; RT=40-50 sec.

Methanol Selectivity (mol%)

FIGURE 42

Effect of Added CO₂ on CO Selectivity
P=1300 psig; T=800 F; RT=40-50 sec.

CO Selectivity (mol%)

FIGURE 43

Effect of Added CO₂ on Net CO₂ Selectivity

P=1300 psig; T=800 F; RT=40-50 sec.

Net CO₂ Selectivity (mol%)

FIGURE 44

Effect of Added CO₂ on Formaldehyde Selectivity

P=1300 psig; T=800 F; RT=40-50 sec.

Formaldehyde Selectivity (mol%)

FIGURE 45Effect of Added CO₂ on Hydrocarbon Conversion

P=1300 psig; T=800 F; RT=40-50 sec.

Hydrocarbon Conversion (mol%)

FIGURE 46 Effect of Added CO₂ on Methanol Yield

P=1300 psig; T=800 F; RT=40-50 sec.

Methanol Yield (mol%)

FIGURE 47

Effect of Added H₂ on Methanol Selectivity

P=1300 psig; T=800 F; RT=40-50 sec.

Methanol Selectivity (mol%)

FIGURE 48

Effect of Added H₂ on CO_x Selectivity

P=1300 psig; T=800 F; RT=40-50 sec.

CO_x Selectivity (mol%)

FIGURE 49

Effect of Added H₂ on Formaldehyde Selectivity

P=1300 psig; T=800 F; RT=40-50 sec.

Formaldehyde Selectivity (mol%)

FIGURE 50

Effect of Added H₂ on O₂-Based Water Selectivity

P=1300 psig; T=800 F; RT=40-50 sec.

Oxygen Selectivity (mol%)

FIGURE 51

Effect of Added H₂ on Hydrocarbon Conversion

P=1300 psig; T=800 F; RT=40-50 sec.

Hydrocarbon Conversion (mol%)

FIGURE 52

Effect of Added H₂ on Methanol Yield

P=1300 psig; T=800 F; RT=40-50 sec.

Methanol Yield (mol%)

FIGURE 53

Effect of Added H₂ on H₂ Production/Conversion

P=1300 psig; T=800 F; RT=40-50 sec.

H₂ Production (+) and Conversion (-) (mmol/hr)

FIGURE 54

Effect of Added CO on Methanol Selectivity

P=1300 psig; T=800 F; RT=40-50 sec.

Methanol Selectivity (mol%)

FIGURE 55

Effect of Added CO on CO₂ Selectivity
P=1300 psig; T=800 F; RT=40-50 sec.

CO₂ Selectivity (mol%)

FIGURE 56

Effect of Added CO on Net CO Selectivity
P=1300 psig; T=800 F; RT=40-50 sec.

Net CO Selectivity (mol%)

FIGURE 57

Effect of Added CO on Formaldehyde Selectivity

P=1300 psig; T=800 F; RT=40-50 sec.

Formaldehyde Selectivity (mol%)

FIGURE 58

Effect of Added CO on Hydrocarbon Conversion

P=1300 psig; T=800 F; RT=40-50 sec.

Hydrocarbon Conversion (mol%)

FIGURE 59

Effect of Added CO on Methanol Yield
 $P=1300$ psig; $T=800$ F; $RT=40-50$ sec.

Methanol Yield (mol%)

FIGURE 60

Effect of Added CO on CO Production/Conversion
 $P=1300$ psig; $T=800$ F; $RT=40-50$ sec.

CO Production(+)/Conversion(-) (mmol/hr)

FIGURE 61

Effect of Recycle on Methanol Selectivity

T=800F; P=1300 psig; RT=40 sec.

Methanol Selectivity (mol%)

Neat feed □	4% CO, 1% H ₂ ▲	8% CO, 2% H ₂ ●
16% CO, 4% H ₂ ■	8% CO, 2% H ₂ (Pred.) ○	

FIGURE 62

Effect of Recycle on Feed Conversion

T=800F; P=1300 psig, RT=40 sec.

Hydrocarbon Conversion (mol%)

FIGURE 63

Effect of Recycle on Methanol Yield

T=800 F; P=1300 psig; RT=40 sec.

Methanol Yield (mol%)

FIGURE 64

Effect of Recycle on CO₂ Selectivity

T=800F; P=1300 psig; RT=40 sec.

Carbon Dioxide Selectivity (mol%)

FIGURE 65

Effect of Recycle on CO Selectivity

T=800F; P=1300 psig; RT=40 sec.

Carbon Monoxide Selectivity (mol%)

FIGURE 66
Catalyst Post-Bed Reactor Internals

FIGURE 67

Effect of Catalyst Post-Bed on MeOH Selectivity

T=725 F; P=1300 psig; Res. Time=60 sec.

Methanol Selectivity (mol%)

FIGURE 68

Equilibrium Consumption of MeOH in Catalyst Bed

Function of Temperature, O₂ Feed Concentration

FIGURE 69

Effect of Catalyst Post-Bed on CO Selectivity

T=725 F; P=1300 psig; Res. Time=60 sec.

FIGURE 70

Equilibrium MeOH Consumption in Catalyst Bed

Effect of Temperature and Added Hydrogen

APPENDIX A

Statistical Data Adjustment Procedure

A Fortran program was written to adjust the input and outlet flow and composition data to achieve better than 99.99% mass, carbon and hydrogen balances while minimizing a chi-square objective function

$$\sum_{i=1}^n \frac{(Y_i - y_i)^2}{s_i^2}$$

In this function Y_i is the adjusted value, y_i is the original value, and s_i is the standard deviation of the measurement for each variable "i" ("n" total variables). A non-linear iterative algorithm was employed which allowed simultaneous adjustment of both flow and composition data. Values for the standard deviations of the variables were either calculated using historical calibration data for the process instruments, or estimated from past experience with plant operation.

APPENDIX B

Quality and Reproducibility of the Experimental Data

A valid concern in any study of methane partial oxidation is the quality of the experimental data that is generated. In fact, most published reports of methane partial oxidation either do not address the issue of data quality or admit to having poor mass or element balances.⁽¹⁵⁾ Data quality is particularly important considering the wide range of often conflicting observations made by different researchers at different times with this system. One of the primary reasons for carrying out the present study in a relatively large-scale reactor system was to obtain credible mass and element balances so that firm conclusions could be drawn.

During the course of this project a total of 310 experimental runs were made. Listings of all experimental data (process conditions and molar flow rates) are given in Appendices C-E. We found that the most important measures of data quality were the mass, carbon, and oxygen balances obtained in the run. The majority (>50%) of the runs had carbon and mass balances that closed to within $\pm 3\%$ and oxygen balances that closed within $\pm 6\%$. A plot of the fraction of total runs with mass and element closures within given limits is shown in Figure B-1. From this plot it can be seen that over 80% of the runs had mass and carbon balance closures within $\pm 5\%$, and over 80% had oxygen balance closures within $\pm 10\%$. These closure values ($\pm 5\%$ for mass and carbon, $\pm 10\%$ for oxygen) were used during this project as criteria for accepting an experimental run. These particular criteria were chosen because it was determined that the statistical adjustment procedure described in the "Experimental Equipment" section and Appendix A could reliably handle runs with these types of experimental errors, but was not robust when handling errors much larger than this.

Another measure of data quality is the standard deviation of a calculated value. Most of the conclusions drawn from this study depend on comparing selectivities and conversions between two treatments (two sets of conditions) and therefore depend on differences in these values. Figures B-2 through B-5 show the averages and calculated error bars (equal to 2σ : 95% confidence interval) for methanol selectivity, methanol yield, methane conversion, and hydrocarbon conversion as a function of oxygen concentration. The actual trends observed in these plots are discussed in the "Results and Discussion" section above. These calculations were based on nearly 100 runs using similar temperature (800°F), pressure (1100-1300 psig) and residence time (10 sec. < R.T. < 60 sec.). Included in this base set of runs are those runs performed with treatments that were determined to have no effect on the system (for example, runs with fritted disk internals, without product quench, with various mixers, etc.). The overall standard deviations (over the entire range of oxygen concentrations) are 2.5 abs% for methanol selectivity, 0.2 abs% for methanol yield, 0.5 abs% for methane conversion, and 0.2 abs% for hydrocarbon conversion.

From the above plots and the low overall standard deviations, we can conclude that the data generated during this project are of very high quality. For

this reason we can have confidence that the conclusions drawn from these data are valid and reflect the true nature of this partial oxidation system.

FIGURE B-1

Methane Partial Oxidation Data Quality
Percent of Total Runs With Given Balance Closure
Percent of Runs with Given Balance Closure

FIGURE B-2

Standard Deviation of MeOH Selectivity Values
d.f. = 90; T = 800 F; P = 1300 psig; R.T. = 10-60 sec.

FIGURE B-3

Standard Deviation of MeOH Yield Values
d.f. = 90; T = 800 F; P = 1300 psig; R.T. = 10-60 sec.

FIGURE B-4

Standard Deviation of Methane Conversion Values

d.f. = 90; T = 800 F; P = 1300 psig; R.T. = 10-60 sec.

FIGURE B-5

Standard Deviation of HC Conversion Values
d.f. = 90; T = 800 F; P = 1300 psig; R.T. = 10-60 sec.

APPENDIX C**Experimental Data — Process Conditions**

This Appendix contains a complete listing of the experimental runs completed under this contract and the process conditions at which they were performed. Included in this listing is a compilation of the mass and element balances of the raw data. As mentioned in the body of this report and expounded in Appendix A, the raw data were statistically adjusted to close the mass and element balances. The raw balances are given here because they were used to determine if individual runs were to be used or discarded (see Appendix B). The process conditions tabulated in the following pages are:

Reactor Dia (mm): Internal diameter of quartz reactor liner, in mm.

Mixer Type: Self Explanatory (see discussion on Task 3.5).

Equiv. PctEth: Volume percent of C₂+ material in the natural gas feed, expressed as ethane equivalent (on a C atom basis).

Hours on Stream: Number of hours the quartz liner was subjected to reaction conditions.

Temp (deg F): Average reactor temperature, in °F.

Press (psig): Reactor pressure, in psig.

ResTime (sec): Average residence time of gas in heated zone of reactor, in seconds.

Vol% O₂: Volume percent of oxygen in the total feed.

Balances: All of the balances reported in the table (mass, carbon, hydrogen, oxygen, and nitrogen) were computed using the formula:

$$100 \cdot (\text{out} - \text{in}) / \text{in}$$

Run #	Reactor Dia (mm)	Comments	Mixer Type	Equv Pd/Eth	Hours on Stream	Temp (deg F)	Press (psig)	ResTime (sec)	Vol% O ₂	Original Balances (mol%)				
										MassBal	CBal	HBal	OBal	NBal
27.002	19		Packed Bed	0.25%	48	867	849	46.2	7.26%	5.6	5.2	4.1	8.8	613.9
27.003	19		Packed Bed	0.25%	48	842	825	36.9	8.62%	2.4	2.4	1.8	3.3	61.8
27.004	19		Packed Bed	4.90%	98	839	825	37.3	8.67%	-0.7	-2.7	-2.1	9.1	-3.1
27.005	19		Packed Bed	4.90%	120	867	850	50.2	7.87%	-0.7	-0.3	-0.9	-2.8	1.0
27.006	19		Packed Bed	4.90%	139	838	1099	36.7	8.88%	-2.5	-2.5	-2.3	-4.1	3.4
27.007	19		Packed Bed	4.90%	139	986	1100	27.6	8.99%	-1.8	-1.3	-2.0	-3.9	0.4
27.008	19		Packed Bed	0.25%	187	986	1100	27.4	8.80%	1.7	2.3	2.4	-2.3	114.7
27.009	19		Packed Bed	0.25%	211	840	1100	36.4	8.84%	0.3	1.3	0.7	-4.3	61.7
27.010	19		Packed Bed	4.90%	235	839	825	37.8	8.83%	-3.5	-3.2	-3.6	-4.4	-2.8
28.001	19		Packed Bed	4.61%	25	853	1100	32.8	8.98%	2.0	2.3	1.8	0.4	7.9
28.002	19		Packed Bed	4.90%	47	804	1100	32.9	9.03%	1.6	2.0	1.8	-0.5	4.4
28.003	19		Packed Bed	4.63%	71	803	1300	33.2	9.05%	-1.3	-1.0	-1.2	-2.9	-0.2
28.004	19		Packed Bed	5.07%	97	882	1300	32.3	9.05%	4.3	8.2	4.7	0.2	5.6
28.005	19		Packed Bed	4.87%	121	822	1300	33.1	9.02%	-0.4	0.3	-0.3	-3.0	0.2
28.006	19		Packed Bed	5.10%	145	991	1300	32.8	8.98%	0.1	2.5	2.0	-11.7	4.3
28.007	19		Packed Bed	0.17%	169	992	1300	32.8	8.77%	1.8	3.1	2.5	-4.1	0.0
28.008	19		Packed Bed	0.02%	193	855	1300	32.7	8.84%	2.0	4.3	3.3	-8.7	-57.9
28.009	19		Packed Bed	0.02%	193	807	1300	33.0	8.86%	0.3	0.2	0.2	0.9	0.2
28.010	19		Packed Bed	5.00%	240	853	1100	33.4	8.99%	-1.5	-0.8	-0.6	-5.3	-0.6
28.011	19		Packed Bed	0.20%	267	856	1100	33.1	8.79%	1.5	1.6	1.3	1.3	0.0
28.012	19		Packed Bed	5.12%	260	806	1300	34.7	8.80%	9.8	12.3	10.6	-1.9	8.4
28.013	19		Packed Bed	5.02%	314	804	1300	34.1	8.82%	-1.3	-1.6	-1.8	0.1	-2.3
28.014	19		Packed Bed	5.02%	338	802	1300	18.8	9.14%	-2.3	-1.8	-2.1	-4.3	-4.2
28.015	19		Packed Bed	5.03%	362	802	1300	35.5	4.48%	-12.8	-14.2	-14.1	0.4	-13.8
28.016	19		Packed Bed	5.11%	386	803	1300	35.1	9.06%	-10.7	-11.6	-12.0	-1.8	-10.7
31.001	19		Packed Bed	5.02%	20	828	1300	32.6	8.97%	-2.4	-3.3	-3.8	3.4	-4.3
31.002	19		Packed Bed	4.70%	36	828	1300	33.9	9.03%	-8.9	-8.6	-8.5	-10.1	-2.8
31.003	19		Packed Bed	4.78%	48	777	1300	32.1	8.97%	-0.5	-0.9	-1.9	1.5	11.8
31.004	19		Packed Bed	4.89%	60	729	1300	31.4	8.99%	3.2	2.8	1.7	5.9	10.3
31.005	19		Packed Bed	4.56%	102	821	1300	30.7	9.11%	-14.3	-16.7	-17.2	-2.4	-13.0
31.006	19		Packed Bed	5.16%	126	828	1300	31.7	7.22%	3.3	2.4	1.9	7.9	11.1
31.007	19		Packed Bed	5.17%	146	830	1300	38.9	8.41%	-0.2	-1.9	-2.0	9.4	-3.8
31.008	19		Packed Bed	4.94%	173	823	1300	30.7	12.51%	8.2	7.6	7.3	10.8	7.3
31.009	19		Packed Bed	4.75%	197	826	1300	32.4	8.97%	-1.8	-4.2	-3.1	8.5	-3.4
31.010	19		Packed Bed	4.92%	221	824	1300	17.1	9.12%	0.2	-0.2	1.1	1.6	-8.2
31.011	19	Ethane spike	Packed Bed	0.91%	245	829	1300	30.3	8.79%	-0.4	-0.5	-0.8	0.4	0.0
31.012	19	Ethane spike	Packed Bed	2.03%	269	828	1300	39.8	8.81%	1.2	1.5	1.0	-0.1	0.0
31.013	19	Ethane spike	Packed Bed	3.34%	293	827	1300	30.4	8.83%	-0.8	0.1	-0.5	-3.1	-1.9
31.014	19	Ethane spike	Packed Bed	4.64%	317	827	1300	30.9	8.84%	-2.1	-1.7	-2.3	-3.4	-5.0
31.018	19		Packed Bed	5.46%	406	826	1300	33.2	9.06%	-6.8	-5.9	-6.9	-12.3	7.8
31.019	19		Packed Bed	4.29%	430	875	1300	32.5	8.96%	-2.0	-1.1	-1.8	-8.3	2.1
31.028	19		Packed Bed	4.45%	701	1018	1100	32.5	8.82%	-0.7	-2.0	-1.6	6.6	-11.3
31.029	19		Packed Bed	4.07%	725	881	1100	32.4	8.84%	-2.0	-2.2	-2.2	-0.1	-10.8
31.030	19		Packed Bed	3.85%	747	829	1100	32.7	8.85%	-3.8	-2.4	-3.2	-8.9	-5.3
31.031	19		Packed Bed	3.86%	771	1018	1100	31.9	8.78%	2.6	5.1	3.4	-7.8	-1.0
31.032	19		Packed Bed	3.82%	795	827	1300	31.5	8.90%	3.7	4.4	4.1	1.8	-8.6
31.033	19		Packed Bed	3.47%	819	878	1300	32.0	8.85%	0.5	4.1	2.0	-16.1	13.0
31.034	19		Packed Bed	3.36%	843	1016	1300	33.0	8.76%	-4.0	-2.8	-4.2	-8.1	-9.4
31.035	19		Packed Bed	3.50%	867	1019	1100	32.7	8.86%	-1.9	-2.4	-2.6	1.3	5.2
31.036	19		Packed Bed	3.08%	891	882	1100	32.6	8.77%	-2.6	-3.3	-3.3	0.2	8.7
31.037	19		Packed Bed	2.72%	915	828	1100	32.7	8.82%	-2.4	-2.9	-3.5	-0.3	14.9
31.038	19		Packed Bed	2.69%	939	1019	1100	32.8	8.80%	-2.2	-3.4	-3.8	4.3	-2.2
31.039	19		Packed Bed	2.87%	968	1016	1300	32.4	8.86%	-0.7	-1.8	-2.0	5.8	-9.9
31.040	19		Packed Bed	1.91%	1036	829	1100	32.2	8.86%	0.9	-0.7	-1.1	10.0	-4.1
31.041	19		Packed Bed	1.42%	1080	825	1300	32.3	4.21%	1.8	-0.3	-0.4	25.2	-12.1
31.042	19		Packed Bed	2.69%	939	1019	1100	32.8	8.80%	-2.2	-3.4	-3.8	4.3	-2.2
32.001	19		Packed Bed	3.00%	24	861	1300	34.2	8.86%	-0.1	-0.1	-0.2	-0.6	19.2
32.002	19		Packed Bed	2.81%	48	880	1300	34.2	8.86%	-0.3	-0.0	-0.3	-2.9	29.3
32.003	19		Packed Bed	2.78%	72	869	825	34.1	8.71%	2.0	1.0	1.3	6.5	5.1
32.004	19		Packed Bed	2.75%	96	918	825	34.8	8.89%	-1.3	-2.0	-2.0	1.7	1.3
32.005	19		Packed Bed	2.77%	60	1077	825	34.5	8.82%	-0.1	-0.9	-1.7	4.5	12.0
32.006	19		Packed Bed	3.17%	144	811	1100	34.5	8.85%	-1.9	-2.3	-2.4	0.4	-2.6
32.007	19		Packed Bed	3.57%	166	766	1100	34.2	8.91%	-0.4	-0.7	-0.5	1.8	-7.0
32.008	19		Packed Bed	3.41%	168	857	1300	34.8	4.22%	-0.4	-0.8	-1.1	-1.0	34.3
32.009	19		Packed Bed	4.11%	216	865	1300	30.0	8.71%	-2.5	-3.4	-3.3	2.4	-6.3
32.010	19		Packed Bed	3.43%	240	866	1300	19.5	9.07%	-1.6	-0.9	-1.2	-5.8	-1.7
32.011	19		Packed Bed	3.46%	264	859	1300	34.4	8.78%	-0.3	-0.3	-0.3	0.5	-10.3
32.012	19		Packed Bed	3.12%	288	853	1300	35.3	2.84%	-3.9	-3.5	-3.8	-8.5	-13.8
32.013	19		Packed Bed	2.91%	312	852	1300	35.3	1.84%	-2.8	-3.5	-3.6	12.2	2.6
33.001	11		Packed Bed	3.32%	20	882	1300	36.8	7.70%	0.3	-10.2	-4.5	49.5	40.4
33.002	11		Packed Bed	3.10%	44	888	1300	34.3	7.77%	13.9	2.8	8.7	68.8	29.8
33.003	11		Packed Bed	3.03%	68	877	1300	17.0	8.52%	0.0	2.0	0.8	-9.6	11.1
33.004	11		Packed Bed	3.07%	92	871	1300	9.9	8.62%	-0.6	0.4	-0.2	-5.9	16.1
33.005	11		Packed Bed	3.07%	60	870	1300	8.8	8.68%	1.6	0.7	1.0	4.9	11.0
33.006	11		Packed Bed	2.97%	140	869	1300	4.4	9.07%	-1.5	-1.6	-1.4	-1.1	-2.4
33.007	11		Packed Bed	3.09%	140	878	1300	9.7	8.64%	1.8	1.8	1.4	0.7	7.0
33.008	11		Packed Bed	3.11%	184	867	1300	4.4	9.06%	-0.6	-0.0	-0.0	-3.3	-2.3
33.009	11		Packed Bed	3.04%	188	870	1300	8.9	8.57%	-0.9	-1.5	-1.3	2.2	-10.2
33.010	11		Packed Bed	3.04%	239	878	1300	16.9	8.83%	1.5	0.4	1.0	6.8	-6.8
33.011	11		Packed Bed	2.99%	260	886	1300	36.9	7.70%	-0.3	-1.2	-1.0	5.1	-5.2
33.012	11		Packed Bed	2.83%	284	880	1300	17.0	12.17%	-2.4	-1.6	-2.2	-5.2	4.5
33.013	11		Packed Bed	2.94%	308	765	1300	16.6	8.57%	2.2	2.4	2.2	1.7	-0.1
33.014	11		Packed Bed	2.81%	308	1103	1300	17.0	8.38%	-1.0	-1.3	-1.6	1.6	-8.4
33.015	11		Packed Bed	2.67%	356	984	1300	13.9	8.44%	1.6	1.6	1.3	1.2	0.1
33.016	11		Packed Bed	2.70%	380	1101	1300	16.8	9.11%	-0.4	-0.6	-1.0	1.4	-5.0
33.017	11		Packed Bed	2.44%	400	1100	1300	16.9	8.58%	1.0	0.8	0.3	3.1	-5.5
33.018	11		Packed Bed	2.53%	428	782	1300	16.8	8.55%	-0.0	-0.1	-0.1	0.5	-1.7
33.019	11		Packed Bed	2.57%	452	980	1300	16.3	8.43%	8.7	9.4	8.7	6.3	5.4
33.020	11		Packed Bed	2.62%	476	880	1100	16.8	8.35%	6.4	2.6	3.8	18.3	-2.2
33.021	11		Packed Bed	2.46%	500	886	825	17.2	8.04%	3.4	2.7	2.7	7.2	0.4
33.022	11		Packed Bed	2.47%	525	878	1100	16.8	8.36%	6.6	2.3	3.8	21.9	0.0
33.023	11		Packed Bed	2.35%	525	886	825	17.2	8.04%	4.4	1.8	2.6	16.9	21.6
33.024	11		Packed Bed	2.30%	573	877	1300	17.0	9.07%	3.8	1.3	1.8	68.1	33.7
33.025	11		Packed Bed	2.70%	621	878	1300	16.9	4.19%	3.4	3.4	2.9	2.4	20.2
33.026	11		Packed Bed	3.09%	644	870	1300	17.2	1.00%	2.0	0.7	1.0	37.3	10.2
33.027	11		Packed Bed	3.18%	669	872								

Run #	Reactor Dg (mm)	Comments	Mixer Type	Eqw Pg/Eth	Hours on Stream	Temp (deg F)	Press (psig)	ResTime (sec)	Vol% O2	Original Balance MassBal	Balance C/Bal	H/Bal	O/Bal	N/Bal
33.034	11		Packed Bed	3.29%	821	895	1300	8.0	1.21%	-0.5	-0.5	-0.5	-1.1	-1.4
33.035	11		Packed Bed	2.90%	845	905	1300	7.6	12.80%	0.3	0.3	0.4	0.4	-1.6
33.036	11		Packed Bed	2.51%	863	872	1300	8.2	1.27%	-6.9	-6.4	-6.4	18.1	-19.7
33.037	11		Packed Bed	2.65%	917	888	1300	8.1	4.24%	-4.4	-4.8	-6.3	-0.8	0.9
33.038	11		Packed Bed	3.25%	917	886	1300	8.0	5.82%	-1.8	-1.8	-1.8	-2.1	3.1
33.039	11		Packed Bed	3.28%	969	872	1300	8.0	2.85%	-3.8	-3.8	-3.9	1.8	-8.8
33.040	11		Packed Bed	3.22%	1013	868	1300	8.1	1.58%	-4.5	-4.5	-4.3	-0.8	-12.3
34.001	30		Packed Bed	3.88%	24	798	1300	84.0	9.05%	-0.8	-0.1	-0.1	-5.3	19.1
34.002	30		Packed Bed	3.70%	48	797	1300	84.2	9.08%	-0.9	-0.1	-0.4	-3.7	-4.1
34.003	30		Packed Bed	4.00%	72	798	1300	986.0	7.80%	5.1	1.9	3.5	21.5	0.6
34.004	30		Packed Bed	3.78%	96	797	1300	180.2	8.86%	-2.4	-6.8	-4.8	18.9	-7.0
34.005	30		Packed Bed	4.01%	80	798	1300	120.5	8.79%	-1.0	-1.6	-1.2	1.5	-0.5
34.006	30		Packed Bed	3.94%	144	798	1300	91.0	8.91%	-4.0	-3.7	-3.8	-6.8	-3.3
34.007	30		Packed Bed	3.86%	188	798	1300	178.7	8.86%	-1.5	-1.7	-1.5	-0.9	-1.8
34.008	30		Packed Bed	3.96%	192	798	1300	378.8	7.80%	-1.9	-0.4	-0.8	-10.3	-0.3
34.013	30		Packed Bed	3.99%	288	701	1300	53.9	9.20%	-0.4	0.7	0.2	-8.4	9.2
34.021	30		Packed Bed	3.10%	24	702	1300	53.4	9.29%	1.8	0.0	-3.5	13.0	1.1
34.022	30		Packed Bed	2.87%	48	1002	1300	84.8	9.28%	-1.9	-2.7	-6.0	8.4	-4.5
34.023	30		Packed Bed	3.50%	76	862	1300	84.4	9.31%	0.8	-2.3	-7.5	18.9	2.9
34.024	30		Packed Bed	2.97%	100	798	1300	84.2	12.88%	0.8	-1.3	-8.0	16.7	-6.8
34.025	30		Packed Bed	3.13%	124	792	1300	84.2	4.48%	2.0	-1.8	-4.3	31.8	14.0
34.026	30		Packed Bed	4.04%	148	793	1300	83.9	8.14%	-1.9	1.3	0.7	8.0	-48.5
34.028	30		Packed Bed	4.80%	168	797	1300	85.3	12.39%	-8.0	-6.5	-6.3	-6.9	-24.9
34.043	30		Packed Bed	4.81%	800	791	1300	86.2	1.17%	-4.1	-4.1	-4.5	-1.2	-4.4
34.046	30		Packed Bed	4.70%	824	791	1300	86.4	1.18%	-4.0	-4.7	-5.3	0.8	-1.8
34.048	30		Packed Bed	4.72%	824	797	1300	82.9	12.39%	0.5	1.7	0.5	-2.0	-10.1
34.049	30		Packed Bed	4.01%	796	797	1300	80.7	12.37%	6.3	7.1	6.2	0.8	-22.3
34.050	30		Packed Bed	2.92%	820	793	1300	85.1	5.71%	-2.1	-2.3	-3.0	-0.1	7.9
34.051	30		Packed Bed	3.54%	844	791	1300	86.2	2.61%	-3.8	-4.1	-5.0	3.5	2.4
35.001	30		Lg Kneec	4.18%	24	794	1300	84.5	8.93%	-2.3	-2.4	-3.2	-1.0	8.3
35.002	30		Lg Kneec	4.03%	48	795	1300	84.8	8.93%	-3.4	-2.7	-4.1	-5.7	9.7
35.003	30		Lg Kneec	4.82%	72	795	1300	48.4	8.97%	-3.1	-2.4	-3.1	-6.3	4.9
35.004	30		Lg Kneec	4.70%	96	795	1300	124.9	8.81%	-7.0	-5.5	-7.7	-6.0	1.4
35.005	30		Lg Kneec	4.73%	120	795	1300	91.2	8.87%	-4.9	-5.1	-5.4	-3.4	-6.3
35.006	30		Lg Kneec	4.48%	144	795	1300	127.7	8.81%	-10.7	-11.2	-11.9	-7.6	-12.7
35.007	30		Lg Kneec	4.59%	168	798	1300	48.1	8.97%	-2.0	-1.4	-2.3	-3.4	-5.9
35.008	30		Lg Kneec	4.51%	192	795	1300	91.7	8.87%	-5.5	-4.5	-6.0	-8.0	-0.7
35.009	30		Lg Kneec	4.47%	216	798	1100	40.3	8.98%	0.1	1.0	-0.4	-2.2	-8.8
35.010	30		Lg Kneec	4.58%	240	799	900	33.9	8.97%	-6.8	-6.4	-6.5	-6.4	-4.3
35.011	30		Lg Kneec	4.71%	264	798	1300	51.7	12.44%	-0.8	0.3	-1.2	-2.0	-2.9
35.012	30		Lg Kneec	4.77%	288	792	1300	82.0	4.31%	-0.2	0.4	-0.5	-3.5	-2.9
35.013	30		Lg Kneec	4.47%	312	792	1300	52.1	5.85%	-0.3	-0.1	-1.4	-7.8	96.9
35.014	30		Lg Kneec	4.77%	336	801	700	25.6	8.98%	-0.5	-0.8	-2.0	-0.4	18.8
35.015	30		Lg Kneec	5.02%	360	792	1300	52.2	3.00%	-0.2	-0.0	-0.7	-3.7	0.9
35.016	30		Lg Kneec	5.14%	384	791	1300	52.0	1.72%	-0.1	1.4	0.7	-19.8	-14.0
35.017	30		Lg Kneec	4.58%	408	791	1300	53.5	1.34%	-4.8	-4.3	-5.0	-19.0	3.4
35.018	30		Lg Kneec	4.43%	432	807	500	19.0	8.99%	-8.5	-8.3	-10.2	-8.6	-16.2
36.001	30		2 Needle Vah	4.54%	24	797	1200	84.8	8.94%	-4.5	-3.5	-4.2	-9.5	-0.5
36.002	30		2 Needle Vah	4.39%	48	797	1200	84.8	12.41%	-3.9	-3.4	-4.4	-5.1	3.3
36.003	30		2 Needle Vah	3.58%	72	793	1200	55.1	4.27%	-3.2	-3.3	-3.9	-1.0	-1.1
36.004	30		2 Needle Vah	3.58%	96	794	1200	55.5	5.82%	-5.3	-4.9	-5.7	-7.1	-7.2
36.005	30		2 Needle Vah	3.69%	120	791	1200	84.8	2.84%	-1.9	-1.3	-2.1	-7.0	-0.6
36.006	30		2 Needle Vah	3.67%	144	792	1200	55.0	1.67%	-2.3	-2.0	-2.7	-5.8	0.3
36.007	30		2 Needle Vah	3.80%	168	791	1200	55.3	1.30%	-3.4	-2.8	-3.7	-15.9	8.3
36.008	30		1 Needle Vah	3.78%	192	798	1200	84.7	8.89%	-3.0	-2.3	-3.8	-6.3	1.7
36.009	30		1 Needle Vah	3.81%	216	797	1200	84.0	12.42%	-3.5	-2.7	-4.1	-5.0	-1.7
36.010	30		1 Needle Vah	4.14%	240	793	1200	84.7	4.29%	-2.2	-2.2	-2.9	-0.4	-2.1
36.011	30		1 Needle Vah	4.30%	264	793	1200	85.2	5.89%	-4.3	-3.7	-4.7	-7.7	1.3
36.012	30		1 Needle Vah	4.22%	288	791	1200	85.7	2.98%	-6.4	-4.0	-5.1	-21.5	-4.6
36.013	30		1 Needle Vah	4.27%	312	791	1200	55.3	1.88%	-3.7	-2.2	-3.3	-30.1	-4.6
36.014	30		1 Needle Vah	4.28%	336	792	1200	84.9	1.31%	-2.4	-1.6	-2.5	-17.1	-3.1
37.001	30		Sm Kneec	4.35%	24	795	1300	84.1	8.87%	-1.4	-1.3	-2.2	-0.9	-2.8
37.002	30		Sm Kneec	4.27%	48	798	1300	84.5	12.45%	-4.0	-2.3	-3.9	-8.1	-12.8
37.003	30		Sm Kneec	4.11%	72	791	1300	84.5	4.30%	-2.2	-0.5	1.7	-15.3	-6.7
37.004	30		Sm Kneec	4.08%	96	793	1300	62.8	5.88%	-0.1	0.1	-1.0	0.3	-0.1
37.005	30		Sm Kneec	4.20%	120	791	1300	84.3	2.98%	-0.3	-0.8	-1.4	8.5	5.6
37.006	30		Sm Kneec	5.51%	144	792	1300	84.4	1.70%	-1.2	0.2	-1.1	-29.5	13.2
37.007	30		Sm Kneec	4.78%	168	791	1300	53.1	1.33%	4.8	4.4	3.8	18.2	4.3
37.008	30		Sm Kneec	4.51%	192	806	500	20.9	8.98%	-4.5	-4.7	-6.0	-2.1	-3.6
37.009	30		Sm Kneec	4.59%	216	802	700	29.2	8.99%	-3.5	-3.3	-4.6	-3.1	-2.1
37.010	30		Sm Kneec	4.88%	240	799	900	37.2	8.99%	-0.5	-0.7	-1.8	1.8	0.8
37.011	30		Sm Kneec	4.25%	264	791	1300	84.8	1.70%	-1.5	-2.2	-2.6	18.8	-7.4
37.012	30		Sm Kneec	4.37%	288	792	1300	84.1	4.31%	0.3	0.4	-0.5	1.8	0.8
37.013	30		Sm Kneec	4.34%	312	791	1300	84.2	1.70%	0.6	0.0	-0.5	14.8	3.4
37.014	30		Sm Kneec	4.34%	336	791	1300	55.1	1.33%	-3.2	-3.3	-3.9	2.7	-3.0
38.001	25	Frit disk internal	Sm Kneec	4.07%	24	796	1300	87.1	8.89%	-3.1	-2.2	-3.7	-6.7	-1.2
38.002	25	Frit disk internal	Sm Kneec	3.80%	48	795	1300	87.2	12.42%	-3.1	-2.2	-4.8	-4.0	0.4
38.003	25	Frit disk internal	Sm Kneec	5.12%	72	791	1300	87.0	4.22%	-1.2	-0.4	-1.6	-6.8	-5.3
38.004	25	Frit disk internal	Sm Kneec	4.57%	96	793	1300	87.3	5.78%	-2.7	-2.0	-3.4	-6.9	-0.5
38.005	25	Frit disk internal	Sm Kneec	4.65%	120	791	1300	87.9	2.98%	-3.9	-3.0	-4.4	-13.5	-1.7
38.006	25	Frit disk internal	Sm Kneec	4.45%	144	791	1300	87.7	1.88%	-2.5	-3.3	-3.9	14.2	5.5
38.007	25	Frit disk internal	Sm Kneec	4.47%	168	791	1300	88.0	1.19%	-3.2	-3.9	-4.4	19.4	-4.0
38.008	25	Frit disk internal	Sm Kneec	4.80%	192	791	1300	88.0	2.98%	-3.9	-3.8	-4.8	-2.0	-3.6
38.009	25	Frit disk internal	Sm Kneec	4.72%	216	790	1300	47.5	0.97%	-4.0	-4.4	-4.8	13.0	-4.6
38.010	25	Frit disk internal	Sm Kneec	4.57%	240	791	1300	58.2	1.20%	-4.3	-4.9	-5.5	15.6	-4.5
38.011	25	Frit disk internal	Sm Kneec	4.37%	264	791	1300	39.3	1.88%	-2.0	-2.4	-3.1	9.1	0.5
38.012	25	Frit disk internal	Sm Kneec	4.31%	288	791	1300	39.4	2.96%	-2.6	-3.1	-3.9	5.1	6.2
38.013	25	Frit disk internal	Sm Kneec	4.52%	312	791	1300	39.4	1.33%	-2.3	-2.8	-3.4	15.2	-2.9
38.014	25	Frit disk internal	Sm Kneec	4.50%	336	792	1300	39.4	4.53%	-2.9	-3.0	-4.1	1.0	-3.3
38.015	25	Frit disk internal	Sm Kneec	5.08%	360	750	1900	40.8	4.55%	-3.4	-3.3	-4.2	-2.4	-1.8
38.016	25	Frit disk internal	Sm Kneec	5.13%	384	793	900	28.4	4.58%	-3.3	-3.6	-4.4	0.9	-2.4
38.017	25	Frit disk internal	Sm Kneec	5.10%	384	797	500	14.7	4.58%	-3.7	-3.9	-4.4	-0.8	-3.7
38.018	25	No quench	Sm Kneec	4.47%	432	794	1900	58.1	8.93%	-6.2	-5.5	-6.8	-7.1	-4.2
38.019	25	No quench	Sm Kneec	3.99%	456	792	1300	58.4	12.43%	-7.1	-6.5	-6.4	-6.5	6.2
38.020	25	No quench	Sm Kneec	4.11%	480	792	1300	58.2	4.21%	-4.2	-4.			

Run #	Reactor Dia (mm)	Comments	Mixer Type	Equip Pct/Eth	Hours on Stream	Temp (deg F)	Press (psig)	ResTime (sec)	Vol% O2	Original Balancee (mol%) Mass(Bal)	CBal	HBal	OBal	NBal
39.003	30	O2z packed bed	Pkd Bed	4.26%	72	795	1300	38.7	4.38%	0.5	0.8	-0.3	-0.7	1.2
39.004	30	O2z packed bed	Pkd Bed	4.24%	96	798	1300	38.7	5.96%	-0.8	-0.2	-1.3	-2.8	-1.5
39.006	30	O2z packed bed	Pkd Bed	5.00%	216	793	1300	39.0	3.00%	-1.0	-1.5	-1.0	8.0	-1.7
39.008	30	O2z packed bed	Pkd Bed	5.06%	240	793	1300	39.9	1.71%	-0.4	-0.2	-0.2	-3.7	-0.3
39.010	30	O2z packed bed	Pkd Bed	5.10%	264	792	1300	39.2	1.36%	-1.7	-1.6	-1.4	-8.5	-1.1
39.011	30	O2z packed bed	Pkd Bed	4.97%	288	800	1300	39.9	12.60%	-4.3	-2.9	-3.2	-9.7	-0.6
39.012	30	O2z packed bed	Pkd Bed	4.67%	312	717	1300	38.5	8.98%	-2.7	-1.8	-1.6	-7.6	-3.1
39.013	30	O2z packed bed	Pkd Bed	4.81%	336	782	1300	39.0	9.06%	-3.7	-3.0	-3.1	-7.4	-2.3
39.015	30	O2z packed bed	Pkd Bed	4.80%	384	1003	1300	39.8	9.01%	-6.0	-5.3	-5.3	-9.9	-3.4
39.016	30	O2z packed bed	Pkd Bed	5.00%	408	806	1300	39.2	9.04%	-3.8	-3.6	-3.5	-6.6	-1.2
39.017	30	O2z packed bed	Pkd Bed	4.94%	432	801	1300	39.0	12.67%	-4.8	-3.8	-3.7	-9.4	-2.2
39.018	30	O2z packed bed	Pkd Bed	4.82%	456	1102	1300	37.3	9.01%	-6.4	-5.8	-5.8	-9.8	-3.7
39.019	30	O2z packed bed	Pkd Bed	4.60%	480	1202	1300	34.5	9.00%	-4.1	-3.9	-4.0	-5.1	-4.4
40.001	25		Sm Kinex	4.43%	24	797	1300	39.8	8.80%	-1.9	-0.3	-0.8	-8.9	-5.0
40.002	25		Sm Kinex	4.11%	48	795	1300	40.4	11.98%	-6.0	-2.6	-3.7	-13.0	-3.2
40.003	25		Sm Kinex	4.06%	72	792	1300	39.9	4.22%	-1.2	-0.9	-0.9	-8.1	5.8
40.004	25		Sm Kinex	3.90%	96	793	1300	40.2	5.75%	-2.6	-1.7	-2.0	-8.9	-1.3
40.005	25		Sm Kinex	3.89%	120	792	1300	40.2	2.91%	-2.3	-1.9	-1.9	-7.9	-2.3
40.006	25		Sm Kinex	3.98%	144	793	1300	39.9	1.66%	-0.7	-0.8	-0.4	-5.8	-0.5
40.007	25		Sm Kinex	3.89%	168	792	1300	39.8	1.30%	0.4	0.3	0.5	1.8	0.2
40.008	25	5% added CO2	Sm Kinex	3.75%	192	795	1300	40.3	8.89%	-2.8	-2.8	-2.8	-4.8	2.1
40.009	25	10% added CO2	Sm Kinex	3.61%	216	795	1300	40.7	8.91%	-3.7	-3.0	-3.2	-5.9	0.9
40.010	25	5% added CO2	Sm Kinex	3.59%	240	791	1300	40.1	1.67%	0.8	0.2	0.5	5.8	-0.0
40.011	25	10% added CO2	Sm Kinex	3.61%	264	793	1300	40.5	1.66%	-0.5	-0.5	-0.4	0.1	-4.4
40.012	25	5% added CO2	Sm Kinex	3.54%	288	798	1300	39.9	12.33%	-2.4	-1.8	-1.7	-4.8	-1.6
40.013	25	10% added CO2	Sm Kinex	3.56%	312	798	1300	40.5	12.36%	-4.3	-3.7	-3.7	-5.3	-7.5
40.014	25	20% added CO2	Sm Kinex	3.57%	336	797	1300	41.5	9.01%	-6.8	-6.2	-5.3	-8.4	-4.3
40.015	25	20% added CO2	Sm Kinex	3.12%	360	793	1300	41.7	1.70%	-3.0	-4.1	-5.2	0.8	-2.9
40.016	25	5% added CO	Sm Kinex	3.36%	384	796	1300	40.1	8.63%	-1.9	-0.8	-1.4	-8.8	5.8
40.017	25	7% added CO	Sm Kinex	2.77%	408	798	1300	40.5	8.87%	-0.3	-1.3	-5.6	8.3	0.2
40.018	25	5% added CO	Sm Kinex	4.24%	432	792	1300	40.1	1.67%	-0.3	-0.1	-0.3	-3.1	-0.0
40.019	25	7% added CO	Sm Kinex	4.25%	456	792	1300	40.1	1.67%	0.1	0.0	0.3	-0.8	3.9
40.020	25	5% added CO	Sm Kinex	4.20%	480	797	1300	39.0	12.29%	2.1	4.1	3.5	-4.3	6.4
40.021	25	7% added CO	Sm Kinex	4.12%	504	798	1300	40.0	12.34%	-1.2	-0.6	-0.3	-3.5	2.9
40.022	25	5% added CO	Sm Kinex	4.58%	528	797	1300	39.8	12.29%	-1.9	-0.8	-1.0	-5.8	1.7
40.023	25	20% added CO	Sm Kinex	3.70%	552	795	1300	41.2	8.98%	-2.4	-1.5	-1.6	-4.5	-1.5
40.024	25	5% added H2	Sm Kinex	4.59%	576	795	1300	39.2	8.83%	1.8	2.9	2.5	-3.5	4.4
40.025	25	7% added H2	Sm Kinex	4.25%	600	798	1300	39.9	8.88%	-0.2	0.5	-0.2	-2.7	
40.026	25	5% added H2	Sm Kinex	5.12%	624	791	1300	40.0	1.67%	0.4	0.3	0.2	2.2	0.8
40.027	25	7% added H2	Sm Kinex	5.71%	648	792	1300	40.0	1.66%	0.9	0.4	0.6	9.2	0.1
40.028	25	15% added H2	Sm Kinex	5.52%	672	793	1300	40.8	1.66%	-2.4	-2.5	-1.8	-3.5	-1.8
40.029	25	15% added H2	Sm Kinex	4.29%	696	799	1300	40.3	8.90%	-2.3	-1.3	-1.7	-5.7	-6.9
40.030	25	7% added H2	Sm Kinex	3.89%	720	798	1300	40.1	12.34%	-2.2	-1.1	-1.8	-5.5	-0.2
40.031	25	5% added H2	Sm Kinex	3.84%	744	797	1300	39.7	12.29%	-1.5	-0.6	-0.7	-4.1	-5.1
40.032	25	15% added H2	Sm Kinex	3.45%	768	801	1300	40.3	12.44%	-1.8	-1.3	-1.4	-3.0	-4.5
40.033	25	20% added CO2	Sm Kinex	3.30%	792	794	1300	41.4	1.70%	-3.3	-3.7	-3.1	-2.3	-4.5
40.034	25	7% added CO	Sm Kinex	3.17%	816	792	1300	40.1	1.67%	0.8	0.5	0.6	3.1	0.8
40.035	25	20% added CO2	Sm Kinex	3.33%	840	792	1300	41.4	1.70%	-2.9	-3.3	-2.7	-2.8	3.3
40.036	25	20% added CO2	Sm Kinex	3.59%	864	798	1300	40.3	9.01%	-0.0	0.7	1.1	-1.6	1.7
40.037	25	20% added CO2	Sm Kinex	3.28%	888	798	1300	41.6	12.51%	-5.8	-7.2	-9.3	-2.8	1.2
40.038	25	20% added CO2	Sm Kinex	3.98%	912	796	1300	41.3	12.51%	-5.5	-4.9	-5.7	-6.2	-6.0
40.039	25	5% added Mx	Sm Kinex	4.08%	936	795	1300	40.6	8.85%	-3.9	-3.4	-3.9	-6.0	-1.8
40.040	25	10% added Mx	Sm Kinex	3.77%	960	796	1300	40.1	8.89%	0.0	-0.6	-0.8	2.2	1.2
40.041	25	20% added Mx	Sm Kinex	3.20%	984	796	1300	41.6	8.98%	-3.9	-3.9	-3.4	-4.1	-2.8
40.042	25	10% added Mx	Sm Kinex	3.57%	1008	798	1300	40.4	12.37%	-1.3	-1.3	-2.5	-0.8	1.6
40.043	25	10% added Mx	Sm Kinex	4.05%	1032	791	1300	40.1	1.73%	2.1	0.8	0.2	12.7	1.3
40.044	25	5% added Mx	Sm Kinex	4.25%	1056	796	1300	40.0	12.31%	-1.5	-1.3	-2.4	-1.5	1.5
40.045	25		Sm Kinex	5.00%	1080	794	1300	39.5	8.80%	0.3	0.3	-0.6	1.0	2.0
40.046	25		Sm Kinex	5.06%	1104	761	1300	40.7	12.26%	-0.3	-1.3	-3.5	3.8	6.7
40.047	25		Sm Kinex	5.39%	1128	756	1300	40.9	4.27%	0.8	0.5	-0.1	2.3	6.7
40.048	25		Sm Kinex	5.33%	1142	754	1300	40.9	5.79%	0.3	1.0	1.1	-7.3	6.6
40.049	25		Sm Kinex	4.09%	1176	751	1300	41.6	2.94%	-1.8	-2.4	-2.1	5.8	1.0
40.050	25		Sm Kinex	4.17%	1200	762	1300	41.1	1.68%	-0.3	-0.0	0.3	-9.0	0.7
40.051	25		Sm Kinex	4.17%	1224	763	1300	40.9	1.32%	1.8	1.8	2.7	-3.7	2.6
40.052	25	20% added CO	Sm Kinex	2.60%	1248	763	1300	42.2	1.75%	1.8	1.3	1.3	2.9	-2.0
40.053	25	20% added CO	Sm Kinex	2.48%	1272	763	1300	42.1	12.48%	-1.7	-0.9	-0.5	-3.8	3.0
41.002	30	7% added H2	Sm Kinex	3.30%	48	728	1300	63.2	12.39%	-1.3	1.6	0.2	-9.9	2.8
41.003	30	7% added H2	Sm Kinex	3.77%	72	728	1300	62.5	8.85%	-0.1	0.7	0.4	-4.0	1.6
41.004	30		Sm Kinex	3.54%	96	727	1300	63.2	1.34%	-6.5	-6.3	-6.5	-11.1	-6.5
41.005	30		Sm Kinex	3.74%	120	727	1300	63.5	12.28%	-3.6	-2.6	-3.3	-7.3	3.7
41.006	30		Sm Kinex	4.51%	176	737	1300	64.0	1.32%	-4.9	-4.7	-4.8	-16.7	1.5
41.007	30		Sm Kinex	4.87%	200	727	1300	64.7	12.27%	-7.9	-7.6	-7.3	-7.9	-16.7
41.008	30	Cat Post-Bed	Sm Kinex	4.13%	24	722	1300	65.1	12.36%	-6.8	-5.8	-6.1	-8.3	-10.5
41.009	30	Cat Post-Bed	Sm Kinex	4.05%	48	723	1300	65.1	8.88%	-6.0	-5.6	-5.8	-7.2	-6.7
41.010	30	Cat Post-Bed	Sm Kinex	5.11%	76	724	1300	65.4	1.33%	-6.8	-5.8	-5.5	-19.6	-20.6
41.011	30	Cat Post-Bed	Sm Kinex	4.36%	76	722	1300	64.3	1.29%	-3.1	-3.8	-3.6	9.6	1.3
41.012	30	Cat Post-Bed	Sm Kinex	4.62%	124	722	1300	63.2	12.27%	-2.5	-1.4	-2.3	-5.7	-2.8
41.013	30	Cat Post-Bed	Sm Kinex	4.95%	148	724	1300	63.1	8.83%	-1.8	-1.1	-1.5	-5.2	0.3
41.014	30	Cat Post-Bed	Sm Kinex	5.15%	172	722	1300	65.2	9.00%	-2.7	-1.2	-2.4	-7.8	-0.2
41.015	30	Cat Post-Bed	Sm Kinex	4.90%	196	725	1300	66.7	9.06%	-5.5	-5.2	-5.6	-6.5	-5.2
42.001	30	Steam @ 13 g/min	Sm Kinex	4.74%	24	791	1300	19.0	3.83%	-4.0	-6.3	-5.2	-2.3	5.2
42.002	30	Steam @ 10 g/min	Sm Kinex	5.31%	72	791	1300	23.7	0.52%	-2.3	0.1	-2.3	-3.8	9.8
42.003	30	Steam @ 10 g/min	Sm Kinex	5.20%	96	792	1300	23.5	3.45%	-1.8	-1.9	-2.4	-1.4	4.7
42.004	30	Steam @ 10 g/min	Sm Kinex	5.64%	120	801	1300	24.7	3.84%	-1.1	0.6	-1.0	-2.3	12.6
42.005	30	Steam @ 10 g/min	Sm Kinex	5.94%	144	953	1300	21.8	3.19%	-2.2	-4.5	-3.8	-1.1	3.2
42.006	30	Steam @ 10 g/min	Sm Kinex	5.80%	168	1102	1300	26.9	2.97%	-1.7	-5.1	-3.7	-0.4	10.7
42.007	30	Steam @ 5 g/min	Sm Kinex	5.35%	192	1103	1300	29.6	4.42%	3.9	-4.2	-1.8	10.0	19.0
42.008	30	Steam @ 5 g/min	Sm Kinex	6.15%	216	793	1300	34.0	5.03%	-1.3	-6.5	-4.0	6.9	-10.3
42.009	30	5/95 acetone/H2O @ 5 g/min	Sm Kinex	6.02%	240	791	1300	33.8	5.02%	-1.9	-7.8	-2.5	3.1	-5.2
42.010	30	5/95 acetone/H2O @ 5 g/min	Sm Kinex	2.84%	240	897	1300	34.7	5.18%	-0.8	0.9	2.0	-3.0	4.9
42.011	30	5/95 acetone/H2O @ 5 g/min	Sm Kinex	3.43%	288	842	1300	37.0	5.18%	-3.3	-2.7	-0.8	-4.8	-8.7
42.012	30	5/95 acetone/H2O @ 5 g/min	Sm Kinex	3.60%	312	880	1300	36.0	5.18%	0.7	-0.1	2.9	0.5	

Run #	Reactor Dia (mm)	Comments	Mixer Type	Equip Pol/Eh	Hours on Stream	Temp (deg F)	Press (psig)	ResTime (sec)	Vol% O2	Original Balance (mol%)					
44.008	30		Sm. Kinex		24	795	1300	614	8.98%	-7.6	-4.6	-3.1	-17.0	-38.3	
44.010	30	Pure sositone @ 3 g/min	Sm. Kinex		48	791	1300	634	7.78%	-7.6	-11.2	-4.3	0.6	-2.6	
44.011	30	Pure sositone @ 3 g/min	Sm. Kinex		72	794	1300	635	10.96%	-3.3	-6.3	-2.8	-8.8	-39.9	
44.012	30	Pure sositone @ 3 g/min	Sm. Kinex		96	791	1300	645	1.14%	-4.9	-3.6	-0.7	-23.6	10.6	

APPENDIX D

Experimental Data — Feed Molar Flows

This Appendix contains the molar flows of all components of the reactor feed for every run performed under this contract. These molar flows (given in millimols/hour where one millimol is 0.001 mol) correspond to the statistically-adjusted (mass-balanced) data, not to the raw data. The mass, carbon, hydrogen, oxygen, and nitrogen balances of the statistically adjusted data all close to within $\pm 0.1\%$. In conjunction with the product molar flow rates given in Appendix E, all conversion, selectivity, and yield values given in the body of this report can be calculated. The feed components are:

CH ₄ :	Methane
C ₂ H ₆ :	Ethane
C ₃ H ₈ :	Propane
i-C ₄ :	iso-Butane
n-C ₄ :	n-Butane
i-C ₅ :	iso-Pentane
n-C ₅ :	n-Pentane
C ₆ _Plus:	All hexanes and higher hydrocarbons
CO:	Carbon Monoxide
CO ₂ :	Carbon Dioxide
H ₂ :	Hydrogen
N ₂ :	Nitrogen
O ₂ :	Oxygen
H ₂ O:	Water
Oth.Alcs:	All other components added to the reactor (this includes acetone addition in the final group of experiments).

INFLOWS (mmol/hr)																
Run #	CH4	C2H6	C3H8	i-C4	n-C4	i-C5	n-C5	C6 plus	CO	CO2	H2	N2	O2	H2O	Oth	Alas
27 002	2335.2	5.2	0.0	0.1	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.7	183.8	0.0	0.0	
27 003	7059.2	14.1	0.0	0.2	0.1	0.0	0.0	0.0	0.0	0.0	0.0	2.0	667.6	0.0	0.0	
27 004	6547.0	253.1	46.5	5.4	8.1	2.7	2.2	3.9	0.0	55.9	0.0	159.5	668.9	0.0	0.0	
27 005	2043.5	78.7	14.6	1.8	2.7	1.0	0.8	1.3	0.0	16.7	0.0	49.0	183.3	0.0	0.0	
27 006	8955.4	338.7	64.5	7.5	11.3	2.5	1.8	5.1	0.0	63.7	0.1	215.6	915.3	0.0	0.0	
27 007	10666.1	383.4	76.0	9.8	14.5	4.9	4.0	6.5	0.1	90.7	5.0	237.1	1103.8	0.0	0.0	
27 008	11394.8	21.4	1.3	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.8	3.2	1102.1	0.0	0.0	
27 009	9636.8	20.4	1.0	0.3	0.0	0.0	0.0	0.0	0.0	0.0	0.5	2.7	914.1	0.0	0.0	
27 010	8575.3	235.1	46.5	6.0	8.7	2.9	2.2	4.2	0.0	54.2	2.8	140.2	668.6	0.0	0.0	
28 001	9759.3	327.8	68.7	10.2	13.2	5.0	3.8	0.0	0.0	81.4	0.0	180.5	1006.6	0.0	0.0	
28 002	10102.3	351.8	73.9	10.8	14.2	5.4	4.4	5.3	0.0	83.6	4.0	190.2	1049.9	0.0	0.0	
28 003	12065.5	422.0	87.6	12.6	16.6	5.1	3.7	5.3	0.0	100.4	0.0	214.6	1254.5	0.0	0.0	
28 004	11543.7	418.2	86.0	12.9	17.1	7.2	5.2	5.9	0.0	93.7	0.0	214.6	1203.3	0.0	0.0	
28 005	10973.8	383.3	79.6	11.5	15.5	5.6	4.1	5.5	0.0	97.2	4.4	189.6	1137.9	0.0	0.0	
28 006	10450.6	385.3	79.8	12.0	15.4	4.9	3.1	5.9	0.0	89.0	4.9	189.1	1079.0	0.0	0.0	
28 007	11195.4	18.7	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	1.2	0.0	1077.8	0.0	0.0	
28 008	12397.4	0.0	1.4	0.4	0.0	0.0	0.0	0.0	0.0	0.0	0.0	3.8	1193.8	0.0	0.0	
28 009	12916.0	0.0	1.4	0.0	0.1	0.0	0.0	0.0	0.0	0.0	0.0	1.3	1253.5	0.0	0.0	
28 010	9713.8	366.4	74.3	14.0	0.0	4.1	0.0	5.3	0.0	71.5	4.8	179.0	1006.0	0.0	0.0	
28 011	10416.8	19.0	1.1	0.3	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	1005.3	0.0	0.0	
28 012	4477.6	156.5	33.1	5.9	6.9	3.2	2.4	3.9	0.0	40.1	0.0	66.0	441.1	0.0	0.0	
28 013	6997.8	244.4	50.7	8.0	9.7	3.8	3.0	5.3	0.0	64.5	3.4	108.5	699.7	0.0	0.0	
28 014	2137.1	763.9	159.7	24.6	30.1	10.0	7.1	16.2	0.0	185.0	10.8	339.0	2252.5	0.0	0.0	
28 015	10623.3	381.4	80.4	13.1	15.8	6.1	4.2	8.1	0.0	91.5	5.5	168.9	621.2	0.0	0.0	
28 016	10911.8	393.4	81.9	13.2	16.0	6.3	4.4	8.3	0.0	93.1	5.5	178.4	839.0	0.0	0.0	
31 001	12140.1	437.9	87.9	12.7	16.6	6.5	6.0	8.1	0.0	123.7	0.0	213.9	1255.0	0.0	0.0	
31 002	12074.7	416.5	82.1	11.4	14.9	4.7	3.3	7.3	0.0	139.6	0.0	187.5	1255.4	0.0	0.0	
31 003	12697.8	433.0	85.4	13.6	16.6	7.7	5.2	8.5	0.0	149.2	0.0	202.2	1311.0	0.0	0.0	
31 004	13256.6	451.4	88.5	15.0	18.9	10.2	7.8	9.2	0.0	152.2	0.0	206.1	1371.3	0.0	0.0	
31 005	20303.7	758.3	137.2	11.5	14.9	0.0	0.0	6.5	0.0	342.6	7.3	343.8	2143.3	0.0	0.0	
31 006	12340.2	463.3	89.6	13.8	17.7	8.3	5.1	9.0	0.0	143.2	4.4	210.1	1009.0	0.0	0.0	
31 007	4403.8	165.9	32.1	4.8	6.1	2.9	1.8	3.2	0.0	52.7	1.6	71.6	424.7	0.0	0.0	
31 008	11729.4	390.4	85.0	15.1	18.5	9.5	6.8	9.0	0.0	128.9	2.8	170.9	1754.5	0.0	0.0	
31 009	12191.9	410.7	86.9	13.3	16.4	4.6	3.1	8.2	0.0	129.7	2.4	183.3	1255.7	0.0	0.0	
31 010	22705.7	777.7	172.1	27.5	33.1	9.6	7.6	16.6	0.0	187.5	4.5	327.2	2377.4	0.0	0.0	
31 011	12891.1	114.1	1.4	0.4	0.0	0.0	0.0	0.9	0.0	0.9	1.6	1.3	1254.3	0.0	0.0	
31 012	12713.3	263.8	1.5	0.0	0.0	0.0	0.0	0.9	0.0	1.4	1.1	0.0	1253.7	0.0	0.0	
31 013	12492.3	444.2	1.4	0.4	0.0	0.0	0.0	0.0	0.0	2.7	1.1	7.9	1254.8	0.0	0.0	
31 014	12300.0	628.0	0.0	0.4	0.1	0.0	0.0	0.0	0.0	2.0	1.5	4.1	1254.2	0.0	0.0	
31 018	11915.5	567.4	81.0	4.8	9.6	1.6	1.7	3.0	0.0	89.6	2.7	375.2	1256.0	0.0	0.0	
31 019	11742.9	422.0	59.6	0.0	8.3	3.8	2.4	3.9	0.0	77.7	3.2	225.2	1204.8	0.0	0.0	
31 028	8936.8	303.7	51.0	6.6	9.2	3.1	3.1	4.3	0.0	61.8	2.3	147.2	901.6	0.0	0.0	
31 029	9999.5	303.7	53.1	7.2	9.7	0.0	2.8	4.7	0.0	63.8	2.1	137.7	1007.2	0.0	0.0	
31 030	10438.3	300.3	49.4	7.2	9.4	3.5	2.7	5.2	0.0	65.1	2.0	124.8	1050.3	0.0	0.0	
31 031	9041.7	246.2	44.0	6.7	9.0	4.9	3.8	5.0	0.0	57.3	1.6	108.8	901.7	0.0	0.0	
31 032	12426.6	333.8	57.5	10.2	12.6	6.7	5.4	7.0	0.0	66.1	1.8	123.5	1255.2	0.0	0.0	
31 033	12012.7	284.9	49.8	10.1	11.4	6.1	5.0	6.7	0.0	69.5	1.2	92.5	1203.7	0.0	0.0	
31 034	10854.3	265.3	46.4	8.9	9.4	0.0	3.2	0.0	0.0	39.3	1.6	71.4	1079.1	0.0	0.0	
31 035	9180.6	220.4	36.5	8.4	6.0	4.6	3.9	4.0	0.0	57.6	1.5	1.1	901.1	0.0	0.0	
31 036	10160.4	238.9	37.2	6.6	7.0	3.0	2.0	0.5	0.0	63.7	2.0	62.0	1007.0	0.0	0.0	
31 037	10579.9	189.7	41.2	7.0	7.6	0.0	0.0	5.2	0.0	78.5	4.9	87.9	1080.7	0.0	0.0	
31 038	9136.0	125.5	48.1	7.2	8.7	0.0	2.6	5.2	0.0	77.7	0.0	112.1	902.5	0.0	0.0	
31 039	10831.5	178.8	52.9	8.9	10.1	0.0	2.6	5.8	0.0	85.2	5.0	118.9	1080.5	0.0	0.0	
31 040	10654.0	65.6	45.9	6.4	0.0	0.0	0.0	4.6	0.0	88.7	0.0	108.8	1051.0	0.0	0.0	
31 041	13343.2	49.4	56.9	9.4	0.1	0.0	3.9	5.8	0.0	112.5	0.0	137.9	592.7	0.0	0.0	
31 042	9136.0	125.5	48.1	7.2	8.7	0.0	2.6	5.2	0.0	77.7	0.0	112.1	902.5	0.0	0.0	
32 001	12526.2	291.5	37.2	5.2	6.6	3.0	2.0	4.1	0.0	71.7	2.9	99.9	1256.0	0.0	0.0	
32 002	12546.3	290.7	34.7	4.5	5.8	0.0	0.0	4.0	0.0	71.4	0.2	92.0	1256.8	0.0	0.0	
32 003	7858.2	184.2	20.6	3.2	0.0	0.0	1.1	2.9	0.0	45.2	4.9	70.4	769.8	0.0	0.0	
32 004	7546.4	168.6	18.6	2.7	3.0	1.3	0.9	2.3	0.0	46.1	3.8	66.4	737.2	0.0	0.0	
32 005	6726.8	154.8	17.0	3.2	0.0	1.4	0.9	2.2	0.0	52.1	0.0	68.5	653.0	0.0	0.0	
32 006	10935.3	280.4	36.6	5.0	6.0	0.0	1.7	3.7	0.0	79.2	5.9	124.1	1008.9	0.0	0.0	
32 007	11366.0	315.4	49.4	7.9	9.7	0.0	0.0	5.4	0.0	91.7	9.6	126.5	1150.2	0.0	0.0	
32 008	13047.2	330.9	53.1	7.5	10.1	4.3	2.9	5.7	0.0	107.4	0.0	158.0	592.9	0.0	0.0	
32 009	7076.2	204.8	40.3	5.6	8.7	3.0	2.2	4.1	0.0	56.9	2.6	110.4	700.9	0.0	0.0	
32 010	21935.7	531.2	99.2	14.3	20.8	6.7	5.3	11.4	0.0	149.3	22.9	244.7	2256.5	0.0	0.0	
32 011	12858.9	314.1	55.6	8.6	12.2	5.0	3.6	7.1	0.0	89.6	9.9	128.1	812.8	0.0	0.0	
32 012	13317.2	298.2	50.9	7.5	10.5	3.9	3.3	5.7	0.0	97.4	9.4	113.5	400.9	0.0	0.0	
32 013	13516.1	284.2	47.2	7.4	9.5	3.5	2.8	5.5	0.0	103.8	2.7	108.8	217.6	0.0	0.0	
33 001	2652.9	83.4	10.2	1.7	2.1	0.4	0.6	1.2	0.0	15.2	1.6	30.6	228.0	0.0	0.0	
33 002	2661.8	59.2	9.9	1.6	2.0	0.8	0.7	1.2	0.0	16.4	2.0	24.4	227.9	0.0	0.0	
33 003	5756.4	120.9	21.5	3.8	4.5	2.1	1.6	2.6	0.0	42.5	1.1	47.7	550.8	0.0	0.0	
33 004	9954.0	221.3	36.1	6.1	7.2	2.8	2.1	4.6	0.0	87.1	6.9	85.3	990.0	0.0	0.0	
33 005	14296.4	319.5	49.8	8.4	9.5	4.9	3.0	6.9	0.0	99.2	10.5	146.9	1446.6	0.0	0.0	
33 006	22376.4	526.7	76.0	11.1	12.7	2.7	4.4	1.9	0.0	145.3	43.2	215.6	2296.5	0.0	0.0	
33 007	9935.9	238.7	33.2	6.4	0.0	3.9	1.9	4.5	0.0	68.1	5.0	95.0	991.0	0.0	0.0	
33 008	22339.4	555.5	73.5	11.5	13.3	0.0	0.0	9.8	0.0	132.6	45.9	233.3	2297.5	0.0	0.0	
33 009	14290.0	341.3	44.1	7.6	8.3	0.0	2.7	6.4	0.0	100.7	21.6	130.6	1449.1	0.0	0.0	
33 010	5748.3	133.7	17.3	3.6	3.5	1.5	1.0	2.4	0.0	39.2	6.8	46.9	551.3	0.0	0.0	
33 011	266															

INFLOWS (mmol/hr)																
Run_#	CH4	C2H6	C3H8	i-C4	n-C4	i-C5	n-C5	C6_plus	CO	CO2	H2	N2	O2	H2O	Oth	Alcs
33 028	12412.6	300.9	45.3	5.7	7.3	2.7	2.0	4.3	0.0	84.3	20.8	161.8	1261.3	0.0		
33 029	11881.1	319.4	42.9	4.8	6.9	2.3	0.0	4.0	0.0	76.5	27.9	178.4	1211.7	0.0		
33 030	12084.6	345.9	46.3	4.3	6.4	2.2	1.9	3.2	0.0	86.5	37.9	196.3	804.2	0.0		
33 031	12817.3	310.6	42.1	5.3	7.8	2.3	1.6	3.4	0.0	95.6	7.1	190.8	821.8	0.0		0
33 032	13196.9	335.5	50.3	6.3	8.7	2.2	1.8	4.0	0.0	92.7	18.1	191.6	408.4	0.0		0
33 033	13208.6	333.1	53.0	7.1	9.4	3.4	0.0	4.3	0.0	94.7	20.9	176.0	225.6	0.0		
33 034	13437.9	334.7	54.1	7.3	9.3	3.3	2.3	4.6	0.0	92.8	23.7	178.5	170.9	0.0		
33 035	11977.0	260.8	41.1	5.5	7.3	2.4	1.8	4.0	0.0	76.5	29.8	155.2	1756.8	0.0		
33 036	13469.0	264.7	43.9	2.7	4.3	2.8	2.1	0.8	0.0	106.4	35.4	191.5	195.4	0.0		
33 037	13089.2	258.1	45.8	5.1	7.0	2.6	1.9	2.3	0.0	112.6	13.9	177.5	603.7	0.0		
33 038	12805.5	299.2	58.9	7.2	10.3	3.1	2.5	4.2	0.0	99.8	17.8	182.0	815.0	0.0		
33 039	13340.3	314.8	62.3	7.2	11.0	3.2	2.5	4.6	0.0	105.9	23.7	196.9	403.4	0.0		
33 040	13364.2	317.2	62.4	6.7	10.5	1.1	1.0	4.0	0.0	97.4	40.4	193.1	221.0	0.0		
34 001	19151.8	511.1	92.0	12.7	16.7	5.4	3.1	7.8	0.0	135.4	24.1	233.8	1971.9	0.0		0.0
34 002	19155.7	511.2	93.2	14.6	18.6	6.7	4.8	8.6	0.0	149.4	15.0	215.8	1971.9	0.0		0.0
34 003	2793.1	79.3	15.3	2.4	3.2	1.1	0.7	1.4	0.0	21.6	4.0	30.7	245.1	0.0		0.0
34 004	5849.7	164.1	32.4	4.7	6.3	1.6	1.1	3.2	0.0	60.2	9.2	65.2	567.1	0.0		0.0
34 005	8820.9	243.8	48.8	7.6	9.7	3.3	2.1	4.7	0.0	70.8	11.0	97.0	862.1	0.0		0.0
34 006	11888.0	312.7	68.6	10.4	13.5	4.1	2.7	6.5	0.0	96.9	14.0	132.6	1174.9	0.0		0.0
34 007	5853.1	148.7	35.0	5.5	7.1	2.4	1.7	3.3	0.0	46.8	6.2	67.8	587.0	0.0		0.0
34 008	2797.4	71.9	17.4	2.8	3.6	1.2	0.8	1.8	0.0	20.6	3.1	32.5	245.0	0.0		0.0
34 013	20611.1	552.5	130.8	18.4	25.9	7.6	6.0	9.5	0.0	144.3	21.6	434.3	2158.9	0.0		0.0
34 021	20544.8	0.0	207.3	23.0	52.4	36.5	18.8	27.7	0.0	287.6	6.8	999.8	2145.3	0.0		0.0
34 022	18074.7	8.4	148.1	32.4	23.3	19.3	26.2	14.5	0.0	244.4	5.3	776.4	1673.4	0.0		0.0
34 023	17296.7	0.0	164.6	19.8	23.7	63.1	47.3	17.2	0.0	274.2	0.0	925.1	1816.2	0.0		0.0
34 024	18099.0	0.0	171.6	26.0	34.6	47.7	24.1	8.5	0.0	351.0	6.0	827.2	2740.8	0.0		0.0
34 025	19886.6	0.0	180.2	38.4	31.5	38.2	30.1	19.1	0.0	259.1	6.1	926.1	951.4	0.0		0.0
34 026	19494.7	54.6	260.9	44.7	61.0	26.4	25.5	27.7	0.0	278.2	7.5	791.3	1292.5	0.0		0.0
34 043	11897.7	377.5	85.0	17.3	19.4	7.9	5.6	7.9	0.0	78.8	2.6	96.9	1753.7	0.0		0.0
34 046	13387.2	431.1	94.9	18.2	21.5	10.3	6.4	8.1	0.0	110.9	0.4	117.7	165.5	0.0		0.0
34 047	13405.0	415.5	92.1	18.5	21.1	10.8	6.7	8.2	0.0	116.8	2.9	110.3	164.5	0.0		0.0
34 048	11879.6	369.7	81.9	16.1	18.8	9.2	6.6	7.4	0.0	103.8	2.6	90.8	1753.7	0.0		0.0
34 049	11995.3	323.9	65.6	13.6	15.8	7.3	4.3	5.7	0.0	85.2	2.6	68.3	1752.8	0.0		0.0
34 050	13019.7	273.8	45.4	9.1	10.7	0.0	4.8	4.8	0.0	102.7	2.4	81.5	810.4	0.0		0.0
34 051	13342.9	322.7	59.5	12.0	13.5	8.4	6.1	4.4	0.0	112.2	2.6	82.8	399.5	0.0		0.0
35 001	18306.8	540.3	110.5	20.0	23.9	9.6	7.0	7.5	0.0	196.5	4.0	146.8	1967.7	0.0		0.0
35 002	19298.4	536.4	109.0	19.9	23.8	10.0	7.9	7.3	0.0	206.1	4.0	149.9	1967.7	0.0		0.0
35 003	21501.5	734.7	153.3	26.1	32.9	12.5	8.3	8.4	0.0	230.2	7.2	210.1	2217.9	0.0		0.0
35 004	8502.0	285.6	58.6	9.2	12.1	5.2	3.5	3.0	0.0	100.8	2.1	90.0	860.4	0.0		0.0
35 005	11520.7	380.7	81.6	13.5	17.0	6.7	4.1	5.7	0.0	123.4	2.9	110.3	1172.5	0.0		0.0
35 006	8524.1	270.1	57.7	8.5	11.6	4.0	2.5	3.3	0.0	105.1	1.4	83.8	860.4	0.0		0.0
35 007	21568.9	685.4	142.6	24.4	31.2	14.1	10.1	10.5	0.0	232.0	5.8	210.1	2217.9	0.0		0.0
35 008	11527.7	364.0	74.9	12.2	15.7	6.8	5.7	4.9	0.0	133.8	3.1	117.6	1172.7	0.0		0.0
35 009	21574.4	652.5	137.0	24.5	31.4	17.4	11.3	10.0	0.0	236.8	5.4	224.2	2217.4	0.0		0.0
35 010	21522.0	703.7	140.9	21.0	28.2	14.0	10.7	7.2	0.0	247.0	4.9	225.8	2217.4	0.0		0.0
35 011	19114.0	632.9	127.6	21.8	27.8	13.8	8.3	8.7	0.0	201.8	4.4	195.6	2840.2	0.0		0.0
35 012	20629.9	682.5	138.4	25.8	31.4	17.8	14.4	10.0	0.0	194.1	0.0	206.5	984.1	0.0		0.0
35 013	20666.7	635.4	125.7	21.0	27.5	16.6	12.1	8.5	0.0	197.7	4.6	265.9	1337.5	0.0		0.0
35 014	21423.4	724.9	141.5	23.6	31.4	15.2	12.1	8.6	0.0	215.7	6.1	322.6	2217.4	0.0		0.0
35 015	20989.8	756.4	142.3	24.1	31.2	17.0	11.2	10.6	0.0	187.2	24.7	381.5	680.9	0.0		0.0
35 016	21304.0	786.2	147.9	26.2	33.6	15.8	11.7	10.8	0.0	167.8	7.4	349.4	390.1	0.0		0.0
35 017	21492.7	727.4	135.2	20.1	26.2	10.6	7.3	8.6	0.0	194.5	2.2	316.4	306.0	0.0		0.0
35 018	21473.4	728.8	134.2	17.0	24.1	5.5	3.3	6.8	0.0	233.4	2.2	296.2	2217.4	0.0		0.0
36 001	17891.4	602.1	103.3	13.7	18.7	5.5	3.4	5.2	0.0	119.3	6.2	186.2	1813.4	0.0		0
36 002	17020.8	576.1	97.4	12.6	17.2	5.2	3.5	4.8	0.0	132.7	7.9	156.5	2520.8	0.0		0
36 003	18779.8	504.8	86.3	13.9	16.9	7.0	0.0	5.5	0.0	153.0	5.9	157.5	866.9	0.0		0
36 004	18460.2	492.4	87.9	14.1	17.2	3.3	0.0	6.1	0.0	174.2	3.2	151.0	1181.1	0.0		0
36 005	19020.8	504.9	90.6	0.0	19.8	9.4	0.0	7.4	0.0	164.4	7.6	163.1	597.3	0.0		0
36 006	19280.3	511.9	91.7	0.0	19.8	8.8	0.0	7.1	0.0	167.4	7.7	156.5	338.5	0.0		0
36 007	19359.4	502.4	89.9	15.1	18.2	8.7	5.8	6.3	0.0	177.9	8.1	165.0	263.8	0.0		0
36 008	17791.8	489.1	86.3	15.2	19.0	7.5	4.2	6.3	0.0	175.5	7.5	165.1	1810.5	0.0		0
36 009	17098.3	478.4	83.6	13.9	16.3	7.2	4.4	6.0	0.0	169.5	6.9	165.3	2517.9	0.0		0
36 010	18599.1	570.2	100.9	16.0	20.1	7.5	5.4	6.8	0.0	169.9	9.1	225.6	866.9	0.0		0
36 011	18230.1	590.8	101.6	13.8	18.4	8.8	7.3	5.7	0.0	168.2	8.7	256.2	1181.4	0.0		0
36 012	18782.1	626.5	108.6	1.7	21.0	1.6	4.3	7.1	0.0	166.6	9.6	272.4	597.3	0.0		0
36 013	19041.4	638.0	111.6	1.8	22.4	1.6	5.7	8.3	0.0	162.4	9.7	273.7	338.5	0.0		0
36 014	19128.8	624.3	109.2	16.6	21.4	9.3	6.5	0.0	0.0	166.9	9.8	284.0	263.8	0.0		0
37 001	19152.0	616.0	104.9	15.6	20.2	9.1	5.4	7.1	0.0	180.8	9.8	250.8	1967.7	0.0		0.0
37 002	18467.6	583.8	102.3	16.0	20.6	8.9	6.3	6.9	0.0	173.8	0.0	216.1	2734.1	0.0		0.0
37 003	20248.9	612.0	110.0	19.5	23.5	11.9	8.2	0.0	0.0	173.8	0.0	208.3	945.5	0.0		0.0
37 004	20555.4	593.1	105.9	19.0	24.3	11.9	8.5	8.8	0.0	197.4	0.0	196.9	1286.2	0.0		0.0
37 005	20469.1	638.4	114.5	9.7	23.7	11.5	7.9	6.9	0.0	191.9	0.0	247.6	653.4	0.0		0.0
37 006	20709.1	650.5	124.1	38.1	46.0	49.3	39.9	20.1	0.0	79.9	0.0	253.1	373.0	0.0		0.0
37 007	20706.7	704.8	125.5	22.6	28.4	17.9	13.4	9.6	0.0	166.0	0.0	295.6	292.1	0.0		0.0
37 008	19044.7	665.7	113.3	16.0	22.7	8.3	2.9	4.9	0.0	218.1	0.0	292.3	1968.0	0.0		0.0
37 009	19039.1	666.8	114.3	15.0	20.3	10.4	7.1	6.6	0.0	201.3	0.0	291.9	1967.2	0.0		0.0
37 010	19038.0	665.0	114.5	16.2	21.4	12.9	9.0	7.3	0.0	197.7	0.0	290.7	1967.2	0.0		0.0
37 011	20709.6	677.1	117.6	0.0	23.4	10.0	8.4	8.4	0.0	197.0	0.0	258.4	373.			

INFLOWS (mmol/hr)															H2O	Oth	Alas
Run #	CH4	C2H6	C3H8	i-C4	n-C4	i-C5	n-C5	C6 plus	CO	CO2	H2	N2	O2				
38 016	20350.6	800.5	145.0	17.3	26.1	10.3	7.9	7.9	0.0	202.4	0.0	410.1	1023.6	0.0	0.0	0.0	0.0
38 017	20377.9	801.4	145.7	17.7	26.4	8.9	5.9	7.8	0.0	189.6	0.0	332.4	1021.0	0.0	0.0	0.0	0.0
38 018	13017.2	431.7	78.4	10.9	15.0	4.8	3.3	3.9	0.0	128.0	0.0	180.7	1329.9	0.0	0.0	0.0	0.0
38 019	12532.0	377.8	67.4	8.1	11.1	3.9	4.7	3.5	0.0	140.6	0.0	176.0	1853.2	0.0	0.0	0.0	0.0
38 020	13714.8	415.2	75.8	10.2	13.9	7.6	5.4	4.1	0.0	139.6	0.0	190.6	827.5	0.0	0.0	0.0	0.0
38 021	13392.8	456.5	84.2	13.6	0.0	10.3	7.8	6.0	0.0	137.4	5.2	239.5	861.2	0.0	0.0	0.0	0.0
38 022	13726.7	526.0	96.0	13.4	18.8	8.2	0.0	5.6	0.0	140.4	0.0	261.5	425.7	0.0	0.0	0.0	0.0
38 023	13972.2	492.1	92.8	15.1	20.2	11.1	10.3	7.1	0.0	129.0	6.1	239.4	232.9	0.0	0.0	0.0	0.0
38 024	14014.3	495.6	92.1	12.4	18.2	7.0	6.5	5.0	0.0	149.7	6.1	238.6	177.1	0.0	0.0	0.0	0.0
38 025	13870.9	531.6	97.1	11.5	18.3	7.0	4.8	5.1	0.0	142.9	6.5	299.5	232.9	0.0	0.0	0.0	0.0
39 001	19029.6	591.5	106.8	16.6	20.9	10.3	6.3	8.8	0.0	193.3	0.0	282.2	1954.3	0.0	0.0	0.0	0.0
39 002	18124.9	577.6	105.8	15.1	20.5	8.0	4.8	8.2	0.0	178.1	0.0	417.0	2715.7	0.0	0.0	0.0	0.0
39 003	19749.7	670.0	83.6	13.8	17.5	14.4	4.2	7.8	0.0	187.6	0.0	536.4	943.3	0.0	0.0	0.0	0.0
39 004	19442.7	662.6	82.7	13.7	16.6	12.2	4.1	6.4	0.0	182.1	0.0	528.8	1281.8	0.0	0.0	0.0	0.0
39 008	19855.0	771.6	140.7	15.4	24.4	4.5	3.9	10.9	0.0	130.7	35.7	483.9	648.7	0.0	0.0	0.0	0.0
39 009	20226.9	781.1	143.4	17.2	26.7	7.4	8.5	12.0	0.0	132.3	22.3	489.9	370.2	0.0	0.0	0.0	0.0
39 010	20219.4	817.1	138.7	15.3	23.9	4.8	3.8	10.0	0.0	133.8	31.7	547.6	289.7	0.0	0.0	0.0	0.0
39 011	19798.5	712.3	118.5	13.2	20.6	3.0	2.6	8.5	0.0	104.0	0.6	468.3	2715.7	0.0	0.0	0.0	0.0
39 012	20260.9	785.1	128.6	13.8	21.5	0.0	0.0	8.4	0.0	120.0	39.2	504.3	2085.6	0.0	0.0	0.0	0.0
39 013	18380.2	744.3	127.0	13.2	21.3	3.3	0.0	8.3	0.0	131.5	31.5	477.9	2021.4	0.0	0.0	0.0	0.0
39 015	18016.4	612.9	102.4	10.8	17.6	2.4	1.9	7.0	0.0	107.1	7.8	372.2	1862.2	0.0	0.0	0.0	0.0
39 016	17153.4	686.6	116.5	12.2	19.5	2.3	2.3	7.7	0.0	115.0	27.8	416.8	1790.0	0.0	0.0	0.0	0.0
39 017	17097.9	710.1	122.4	12.3	20.3	2.1	1.5	7.9	0.0	113.5	45.8	424.2	2715.7	0.0	0.0	0.0	0.0
39 018	18028.5	614.7	108.5	11.4	18.4	2.0	1.5	4.9	0.0	120.5	8.8	341.6	1862.2	0.0	0.0	0.0	0.0
39 019	18105.3	557.9	99.2	11.5	17.6	3.6	2.7	7.4	0.0	135.1	5.8	312.6	1862.2	0.0	0.0	0.0	0.0
40 001	18470.8	632.4	110.8	15.0	21.2	6.6	5.6	6.2	0.0	129.8	8.7	355.8	1907.1	0.0	0.0	0.0	0.0
40 002	17832.4	580.8	98.9	12.3	18.2	4.6	4.0	4.9	0.0	150.9	0.2	305.2	2580.3	0.0	0.0	0.0	0.0
40 003	19800.3	610.9	108.7	12.6	19.1	5.4	4.3	5.1	0.0	163.8	0.2	345.6	915.2	0.0	0.0	0.0	0.0
40 004	19189.6	560.7	99.5	11.6	18.6	5.1	4.0	8.6	0.0	164.0	17.9	357.5	1245.8	0.0	0.0	0.0	0.0
40 005	19826.7	569.0	105.6	13.0	19.8	5.1	4.3	9.3	0.0	174.3	9.3	326.7	631.9	0.0	0.0	0.0	0.0
40 006	20048.8	575.9	112.6	14.4	21.8	6.3	4.9	9.9	0.0	171.7	1.5	368.2	359.9	0.0	0.0	0.0	0.0
40 007	20132.2	568.0	108.4	13.2	20.9	6.4	5.3	9.2	0.0	164.3	5.9	382.3	281.1	0.0	0.0	0.0	0.0
40 008	17749.5	514.3	105.7	8.8	15.3	2.6	2.2	6.5	0.0	803.4	7.6	396.6	1907.2	0.0	0.0	0.0	0.0
40 009	18858.0	487.1	114.1	5.7	11.5	0.4	3.7	5.4	0.0	1596.1	27.6	394.8	1907.2	0.0	0.0	0.0	0.0
40 010	19157.7	557.9	88.8	7.9	12.9	3.9	5.5	5.9	0.0	859.0	18.9	457.7	369.9	0.0	0.0	0.0	0.0
40 011	18219.4	530.4	114.3	7.7	12.3	3.8	3.1	5.8	0.0	1713.4	25.9	421.5	359.9	0.0	0.0	0.0	0.0
40 012	17082.8	483.3	85.8	6.3	10.5	3.5	2.8	2.8	0.0	755.3	28.7	384.4	2651.0	0.0	0.0	0.0	0.0
40 013	18198.9	484.0	99.4	4.7	7.7	3.1	2.6	3.0	0.0	1541.7	41.6	360.7	2651.0	0.0	0.0	0.0	0.0
40 014	15154.9	465.7	112.8	4.3	0.0	2.5	1.8	2.5	0.0	3129.5	76.5	321.0	1907.1	0.0	0.0	0.0	0.0
40 015	16594.6	474.9	107.7	4.7	0.0	1.5	1.3	2.8	0.0	3291.8	17.7	324.4	359.9	0.0	0.0	0.0	0.0
40 016	17955.1	545.5	58.2	4.6	7.3	2.6	2.1	2.8	573.7	130.4	37.1	380.7	1907.2	0.0	0.0	0.0	0.0
40 017	17717.7	486.3	30.8	0.0	0.0	2.6	2.0	1.8	738.9	267.8	0.0	342.4	1907.2	0.0	0.0	0.0	0.0
40 018	19144.2	723.0	82.8	9.1	12.8	3.7	3.0	4.5	619.6	131.7	36.4	478.7	359.9	0.0	0.0	0.0	0.0
40 019	18198.4	727.4	81.7	8.6	12.0	3.8	3.1	3.7	1488.9	111.8	29.9	516.8	359.9	0.0	0.0	0.0	0.0
40 020	17028.2	638.7	62.7	10.0	12.3	2.5	2.1	6.9	532.2	87.2	40.1	498.2	2651.0	0.0	0.0	0.0	0.0
40 021	18126.4	652.1	64.5	5.8	9.1	0.0	0.0	2.6	1309.4	82.3	64.0	527.6	2651.0	0.0	0.0	0.0	0.0
40 022	16687.0	711.9	73.8	6.8	10.6	2.9	2.3	4.1	542.4	93.6	47.6	538.0	2651.0	0.0	0.0	0.0	0.0
40 023	14175.4	590.3	56.9	5.6	8.6	2.2	1.8	3.3	3885.8	76.5	52.3	466.2	1907.1	0.0	0.0	0.0	0.0
40 024	17858.5	723.2	71.1	9.2	11.9	2.6	2.2	4.8	0.0	104.0	570.2	522.2	1907.1	0.0	0.0	0.0	0.0
40 025	17082.4	648.0	80.6	7.2	10.0	2.1	1.7	5.2	0.0	123.9	1314.7	333.3	1908.0	0.0	0.0	0.0	0.0
40 026	19114.6	854.9	111.6	12.2	17.3	3.9	3.1	0.0	12.5	139.4	829.1	348.9	359.9	0.0	0.0	0.0	0.0
40 027	18162.8	879.1	127.1	14.1	20.9	5.1	4.3	5.5	0.0	133.5	1447.3	365.6	380.9	0.0	0.0	0.0	0.0
40 028	18556.2	805.8	108.6	7.1	12.3	4.5	3.7	1.9	0.0	101.5	3053.4	330.4	361.6	0.0	0.0	0.0	0.0
40 029	15655.1	585.9	88.0	6.0	9.6	2.6	2.1	2.9	0.0	106.2	2817.4	279.2	1908.7	0.0	0.0	0.0	0.0
40 030	16530.4	541.1	57.0	5.1	7.9	2.3	1.7	0.3	0.0	114.3	1304.9	270.7	2651.0	0.0	0.0	0.0	0.0
40 031	17325.5	553.3	74.1	7.9	11.6	3.4	2.9	2.4	0.0	112.7	593.6	233.8	2651.0	0.0	0.0	0.0	0.0
40 032	15136.6	444.6	52.7	4.4	7.2	2.6	2.1	2.2	0.0	100.9	2735.1	190.9	2652.8	0.0	0.0	0.0	0.0
40 033	16610.6	501.7	121.4	0.0	1.4	2.1	1.8	2.1	0.0	3250.5	83.8	245.9	359.9	0.0	0.0	0.0	0.0
40 034	18571.4	556.8	53.5	6.0	8.2	2.3	1.9	2.5	1472.7	129.9	76.1	284.7	359.9	0.0	0.0	0.0	0.0
40 035	16473.2	515.7	116.7	0.0	0.4	1.8	1.9	1.3	0.0	3292.6	80.2	305.3	359.9	0.0	0.0	0.0	0.0
40 036	15177.6	486.4	120.5	5.4	8.6	1.8	1.5	1.7	0.4	3116.3	63.7	287.8	1907.1	0.0	0.0	0.0	0.0
40 037	14578.0	465.6	95.5	0.0	0.0	1.6	2.1	2.1	0.4	3049.9	11.4	337.4	2651.0	0.0	0.0	0.0	0.0
40 038	14351.0	512.4	124.2	1.6	2.4	2.3	2.0	2.6	0.0	3149.1	52.2	342.2	2651.0	0.0	0.0	0.0	0.0
40 039	17399.5	636.4	82.1	7.2	11.4	1.6	3.3	2.8	844.5	146.1	193.6	314.4	1907.2	0.0	0.0	0.0	0.0
40 040	16311.5	564.2	73.5	7.1	12.0	3.8	3.7	4.3	1782.8	151.1	349.1	290.3	1907.2	0.0	0.0	0.0	0.0
40 041	14266.6	463.4	65.0	4.2	8.4	3.9	3.2	2.5	3483.3	116.4	674.4	233.7	1907.2	0.0	0.0	0.0	0.0
40 042	15694.5	493.4	76.5	7.0	12.8	3.3	2.3	4.4	1705.1	188.9	310.5	305.1	2651.0	0.0	0.0	0.0	0.0
40 043	17577.8	611.9	93.1	10.8	18.3	8.5	4.7	7.6	1907.0	176.8	324.9	336.9	378.4	0.0	0.0	0.0	0.0
40 044	18601.0	594.1	91.9	10.0	15.6	4.9	2.6	6.5	930.5	167.9	147.1	314.2	2651.0	0.0	0.0	0.0	0.0
40 045	18264.6	728.4	106.3	14.5	19.4	11.0	6.6	8.4	0.0	177.3	0.0	426.3	1907.2	0.0	0.0	0.0	0.0
40 046	17283.5	770.3	92.7	8.8	12.3	5.7	3.7	3.4	0.0	220.9	0.0	566.6	2685.8	0.0	0.0	0.0	0.0

INFLOWS (mmol/hr)																
Run #	CH4	C2H6	C3H8	i-C4	n-C4	i-C5	n-C5	C6_plus	CO	CO2	H2	N2	O2	H2O	Oth	Alca
42 005	15356.5	821.3	111.7	6.7	11.8	0.0	0.0	1.7	0.0	182.6	0.0	485.6	1669.9	32972.5	0.0	
42 006	13819.5	732.0	94.9	6.3	5.3	0.0	0.0	1.8	0.0	161.4	0.0	452.5	1524.8	32972.5	0.0	
42 007	13754.9	706.3	81.8	0.7	1.3	0.0	0.0	0.0	0.0	237.7	0.0	484.4	1556.2	10652.8	0.0	
42 008	11170.0	615.8	103.8	8.8	1.7	0.0	3.9	0.0	0.0	281.4	0.0	6359.8	1935.9	10652.8	0.0	
42 009	17414.8	957.7	135.2	5.9	10.9	0.0	0.0	0.7	0.0	75.7	113.8	531.2	1860.7	15841.8	251.6	
42 010	20067.1	246.9	106.4	0.0	20.3	0.0	0.0	10.8	0.0	39.8	127.8	223.1	2025.7	15841.8	251.6	
42 011	19906.7	366.8	109.2	14.4	15.8	0.0	0.0	10.2	0.0	5.0	180.5	243.8	2025.6	15841.8	251.6	
42 012	19903.3	416.4	119.8	11.0	21.6	0.0	0.0	7.1	0.0	3.1	147.7	246.6	2025.6	15841.8	251.6	
42 013	19893.2	409.1	116.8	11.6	20.7	0.2	0.0	6.8	0.0	25.2	121.3	265.7	2025.6	15841.8	251.6	
42 014	19979.1	519.3	119.5	10.0	18.2	0.0	3.8	11.9	0.0	0.0	0.0	238.1	2026.7	31366.8	498.1	
42 015	20115.5	473.9	114.2	2.9	18.1	0.0	0.0	8.4	0.0	0.0	5.9	198.9	2026.3	31366.8	498.1	
42 016	18760.7	434.4	107.0	13.6	15.9	0.0	0.0	12.6	0.0	0.0	0.0	174.5	2729.1	31366.8	498.1	
42 017	18761.6	424.0	106.4	9.4	15.1	0.0	0.0	10.4	0.0	0.0	1.9	191.2	2728.5	15841.8	251.6	
42 018	21074.7	436.0	105.1	16.5	22.0	6.0	4.9	9.7	0.0	10.8	1.5	237.2	291.8	15841.8	251.6	
42 020	17255.9	370.7	90.3	12.2	18.1	3.2	1.9	5.4	0.0	24.2	1.4	220.8	0.0	15841.8	251.6	
42 021	21359.6	459.2	112.5	16.6	24.3	6.1	4.6	7.6	0.0	32.8	1.7	253.9	0.0	15841.8	251.6	
42 022	21296.4	432.6	102.8	16.3	22.3	8.7	8.6	4.9	0.0	88.1	1.7	277.9	0.0	15418.8	382.7	
42 023	21302.2	435.1	102.7	15.1	20.1	6.6	2.8	6.6	0.0	69.6	1.7	307.0	297.3	15467.1	367.8	
44 009	17717.2	594.2	124.2	21.0	25.2	0.0	0.0	14.8	0.0	33.9	3.1	414.2	1869.9	0.0	0.0	
44 010	17983.3	586.9	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	3.1	129.1	1804.8	0.0	2747.9	
44 011	17023.0	574.0	105.4	0.0	0.0	0.0	0.0	0.0	0.0	100.0	3.0	324.5	2549.9	0.0	2613.6	
44 012	19004.6	596.8	111.2	0.0	25.5	0.0	12.3	14.1	0.0	109.3	3.9	273.4	263.8	0.0	2613.6	

APPENDIX E

Experimental Data — Product Molar Flow Rates

This Appendix contains the molar flows of all components of the reactor effluent for every run performed under this contract. These molar flows (given in millimols/hour where one millimol is 0.001 mol) correspond to the statistically-adjusted (mass-balanced) data, not to the raw data. The mass, carbon, hydrogen, oxygen, and nitrogen balances of the statistically adjusted data all close to within $\pm 0.1\%$. In conjunction with the feed molar flow rates given in Appendix D, all conversion, selectivity, and yield values given in the body of this report can be calculated. In addition to the components listed in the feed (see Appendix D), the following compounds appeared in the reactor effluent:

C₂H₄: Ethylene
C₃H₆: Propylene
1-C₄=: 1-Butene
c-2-C₄=: cis-2-Butene
t-2-C₄=: trans-2-Butene
i-C₄=: iso-Butene
MeOH: Methanol
EtOH: Ethanol
CH₂O: Formaldehyde

OUTFLOWS (mmole/hour)

Run #	CH4	C2H6	C2H4	C3H8	C3H6	LC4	n-C4	1-C4=	c-2-C4=	1-2-C4=	i-C4=	LC5	n-C5	C6 plus	CO	CO2	H2	N2	O2	H2O	MeOH	EtOH	CH3O	Oth Alcs
27002	2178.9	7.1	0.0	1.2	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	106.5	17.8	53.0	0.7	0.4	188.8	28.8	0.0	0.0	0.0
27003	6510.0	14.7	0.0	2.3	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	328.5	91.7	140.1	2.1	1.3	688.4	123.3	1.7	0.0	0.0
27004	6744.5	180.9	0.0	2.2	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	375.1	137.4	95.8	158.8	2.8	633.7	158.0	2.2	1.3	0.0
27005	1987.6	61.9	0.2	7.3	0.5	0.5	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	107.3	37.3	27.1	49.1	0.8	172.7	43.1	0.5	0.0	0.0
27006	8535.3	209.4	0.1	31.4	1.1	3.0	4.6	0.0	0.0	0.0	0.0	0.0	0.0	0.0	454.6	206.5	111.7	215.3	3.2	648.8	231.8	3.1	3.0	0.0
27007	10135.1	240.1	0.8	37.2	2.0	3.7	4.2	0.0	0.0	0.0	0.0	0.0	0.0	0.0	612.9	229.4	183.5	237.3	3.7	1020.9	280.4	4.1	3.4	0.0
27008	10502.4	21.2	0.0	2.2	0.0	0.1	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	485.3	179.5	157.5	3.4	1.9	1134.0	217.1	3.6	0.0	0.0
27009	8910.1	14.9	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	413.3	140.1	91.8	140.4	2.2	941.3	190.5	0.0	0.0	0.0
27010	6287.2	150.7	0.5	22.8	1.0	2.3	2.8	0.0	0.0	0.0	0.0	0.0	0.0	0.0	382.3	141.1	141.9	181.0	3.0	833.0	259.0	3.1	3.0	0.0
28001	9274.7	208.8	0.0	32.6	0.0	1.9	2.9	0.0	0.0	0.0	0.0	0.0	0.0	0.0	535.9	218.2	132.7	190.9	3.2	965.0	274.6	3.5	3.1	0.0
28002	9634.1	224.3	0.1	34.6	1.1	2.2	2.4	0.0	0.0	0.0	0.0	0.0	0.0	0.0	584.5	225.0	147.5	214.8	4.9	1145.7	343.7	4.5	4.2	0.0
28003	11471.7	263.2	0.0	41.4	1.0	4.2	4.9	0.0	0.0	0.0	0.0	0.0	0.0	0.0	648.2	277.0	169.0	214.0	10.2	1072.8	315.1	4.2	3.8	0.0
28004	1038.4	262.5	0.0	37.5	1.2	1.3	1.5	0.0	0.0	0.0	0.0	0.0	0.0	0.0	610.9	258.8	175.2	169.8	5.1	1048.1	277.8	3.7	2.5	0.0
28005	10463.1	241.4	1.4	35.6	1.3	3.7	0.0	0.1	0.0	0.0	0.0	0.0	0.0	0.0	545.1	267.0	162.8	169.1	3.0	983.4	223.1	3.3	1.0	0.0
28006	10051.0	240.9	2.0	33.2	1.6	2.9	2.6	0.0	0.0	0.0	0.0	0.0	0.0	0.0	495.4	161.1	197.4	0.0	1.7	1118.0	217.9	0.0	0.0	0.0
28007	10320.6	18.7	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	538.4	0.0	1.5	1.9	1077.3	227.2	0.0	0.0	0.0
28008	11634.8	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	560.8	187.2	192.5	2.7	2.0	1237.5	280.5	0.0	0.0	0.0
28009	11870.2	16.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	489.8	232.0	116.5	178.7	3.8	920.8	288.6	3.3	12.1	0.0
28010	9249.0	226.5	1.2	33.0	1.2	3.9	4.1	0.0	0.0	0.0	0.0	0.0	0.0	0.0	469.5	141.1	171.3	0.0	2.8	1042.1	211.5	3.1	6.3	0.0
28011	9585.9	20.8	0.0	2.4	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	224.7	115.1	68.5	66.0	1.3	398.6	183.2	2.3	3.8	0.0
28012	4324.8	99.0	1.2	14.8	0.4	0.6	0.6	0.0	0.0	0.0	0.0	0.0	0.0	0.0	359.3	164.9	91.5	108.5	1.9	640.5	193.3	0.0	3.6	0.0
28013	6572.5	159.8	1.2	24.7	0.6	2.5	2.7	0.0	0.0	0.0	0.0	0.0	0.0	0.0	1186.7	456.6	271.8	338.7	5.8	2069.4	658.9	0.0	35.6	0.0
28014	20253.1	481.0	1.3	77.7	3.2	10.0	10.5	0.2	0.0	0.0	0.0	0.0	0.0	0.0	1186.7	456.6	271.8	338.7	5.8	2069.4	658.9	0.0	35.6	0.0
28015	10558.5	291.8	0.5	47.1	1.4	5.5	6.4	0.0	0.0	0.0	0.0	0.0	0.0	0.0	445.2	157.3	75.2	169.0	2.5	525.9	225.8	3.5	3.4	0.0
28016	10531.4	280.1	0.4	44.6	1.3	5.7	0.0	0.4	0.0	0.0	0.0	0.0	0.0	0.0	445.2	157.3	75.2	169.0	2.5	525.9	225.8	3.5	3.4	0.0
31001	11577.5	288.8	1.3	40.9	1.2	3.5	5.2	0.0	0.0	0.0	0.0	0.0	0.0	0.0	689.7	294.5	199.9	213.9	3.4	1159.5	311.6	0.0	3.7	0.0
31002	11410.0	262.5	1.2	42.7	1.3	7.5	7.5	0.0	0.0	0.0	0.0	0.0	0.0	0.0	689.7	294.5	199.9	213.9	3.4	1159.5	311.6	0.0	3.7	0.0
31003	11998.3	294.5	1.0	48.4	1.4	6.5	4.4	0.0	0.0	0.0	0.0	0.0	0.0	0.0	712.0	314.9	216.2	202.3	3.7	1226.8	336.6	4.3	3.7	0.0
31004	12572.7	313.2	0.8	49.1	1.5	1.0	2.1	0.0	0.0	0.0	0.0	0.0	0.0	0.0	736.7	341.3	223.5	208.0	3.6	1261.8	348.6	3.2	4.2	0.0
31005	18849.4	489.5	1.8	94.8	2.3	24.3	25.1	0.0	0.0	0.0	0.0	0.0	0.0	0.0	1214.8	498.9	350.4	343.7	5.7	2209.0	635.4	7.9	0.0	0.0
31006	1918.7	326.8	0.4	50.5	1.5	3.2	4.9	0.1	0.0	0.0	0.0	0.0	0.0	0.0	587.6	268.3	178.4	210.2	2.9	921.5	248.4	3.1	3.2	0.0
31007	4210.5	106.2	0.0	17.7	0.8	1.6	1.7	0.0	0.0	0.0	0.0	0.0	0.0	0.0	223.8	116.9	74.4	71.6	1.1	377.6	114.5	1.5	1.4	0.0
31008	10900.76	221.856	0.0	37.4	1.4	1.1	1.3	0.0	0.0	0.0	0.0	0.0	0.0	0.0	881.9	435.3	241.4	171.0	4.2	1699.6	349.6	2.4	4.4	0.0
31009	11874.0	218.1	0.0	39.3	1.2	8.0	6.1	0.0	0.0	0.0	0.0	0.0	0.0	0.0	881.9	435.3	241.4	171.0	4.2	1699.6	349.6	2.4	4.4	0.0
31010	22117.0	275.2	0.0	53.7	3.2	9.7	9.7	0.0	0.0	0.0	0.0	0.0	0.0	0.0	1294.9	552.2	231.8	328.0	6.0	2118.1	588.0	8.0	5.9	0.0
31011	11923.9	70.7	0.0	6.1	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	575.8	181.1	197.1	1.4	2.5	1277.7	288.3	1.6	0.0	0.0
31012	11834.7	158.4	0.0	6.7	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	801.7	174.1	198.4	0.3	2.7	1257.1	284.9	3.4	0.0	0.0
31013	11708.0	270.1	0.0	6.7	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	616.1	173.3	196.5	8.2	2.5	1228.0	313.0	4.5	0.0	0.0
31014	11633.4	383.8	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	639.6	174.7	173.3	8.2	2.5	1228.0	313.0	4.5	0.0	0.0
31015	11197.9	395.9	1.0	49.9	1.4	2.9	8.5	0.1	0.0	0.0	0.0	0.0	0.0	0.0	652.2	238.1	172.9	375.2	4.4	1207.3	340.6	6.6	2.1	0.0
31016	1089.1	269.2	0.8	30.4	1.0	2.0	2.4	0.0	0.0	0.0	0.0	0.0	0.0	0.0	620.9	238.1	169.1	225.5	3.8	1139.0	318.1	4.2	2.1	0.0
31017	8537.5	178.6	0.0	24.2	2.2	2.1	2.3	0.0	0.0	0.0	0.0	0.0	0.0	0.0	500.9	188.5	157.8	146.8	1.9	863.7	189.7	1.7	0.7	0.0
31018	9519.8	178.1	0.0	25.4	1.1	2.1	2.3	0.0	0.0	0.0	0.0	0.0	0.0	0.0	500.9	188.5	157.8	146.8	1.9	863.7	189.7	1.7	0.7	0.0
31019	9806.8	182.8	0.0	25.4	1.1	2.1	2.3	0.0	0.0	0.0	0.0	0.0	0.0	0.0	500.9	188.5	157.8	146.8	1.9	863.7	189.7	1.7	0.7	0.0
31020	8581.8	183.7	0.0	19.1	1.9	1.6	1.5	0.0	0.0	0.0	0.0	0.0	0.0	0.0	483.2	160.8	169.7	109.5	1.8	1172.8	204.7	2.2	1.4	0.0
31021	8581.8	183.7	0.0	19.1	1.9	1.6	1.5	0.0	0.0	0.0	0.0	0.0	0.0	0.0	483.2	160.8	169.7	109.5	1.8	1172.8	204.7	2.2	1.4	0.0
31022	11800.9	201.4	0.0	24.2	1.1	2.4	2.5	0.0	0.0	0.0	0.0	0.0	0.0	0.0	516.7	188.9	139.8	61.5	2.3	984.2	260.2	2.9	2.3	0.0
31023	11333.0	186.0	0.2	24.5	1.3	2.6	2.5	0.0	0.0	0.0	0.0	0.0	0.0	0.0	516.7	188.9	139.8	61.5	2.3	984.2	260.2	2.9	2.3	0.0
31024	10230.5	170.5	0.8	24.5	1.9	2.2	1.8	0.0	0.0	0.0	0.0	0.0	0.0	0.0	502.8	202.4	127.7	125.4	2.1	977.2	221.6	2.8	0.8	0.0
31025	8686.4	139.2	1.2	20.1	1.8	1.8	1.3	0.0	0.0	0.0	0.0	0.0	0.0	0.0	502.8	202.4	127.7	125.4	2.1	977.2	221.6	2.8	0.8	0.0
31026	9533.8	152.2	1.0	20.7	1.1	1.9	1.7	0.0	0.0	0.0	0.0	0.0	0.0	0.0	502.8	202.4	127.7	125.4	2.1	977.2	221.6	2.8	0.8	0.0
31027	9909.8	108.0	0.0	27.1	1.1	2.4	2.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	502.8	202.4	127.7	125.4	2.1	977.2	221.6	2.8	0.8	0.0
31028	8556.1	85.6	0.0	26.6	0.1	2.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	502.8	202.4	127.7	125.4	2.1	977.2	221.6	2.8	0.8	0.0
31029	10253.1	66.4	0.0	27.3	1.9	2.1	1.9	0.0	0.0	0.0	0.0	0.0	0.0	0.0	502.8	202.4	127.7	125.4	2.1	977.2	221			

Run #	C2H4	C3H6	C4H8	n-C4	i-C4	1-C4	2-C4	3-C4	4-C4	5-C4	6-C4	CO	CO2	H2	N2	O2	H2O	MeOH	EtOH	CH3OH	Orth. Area
32.013	13324.7	268.1	3.4	67	0.2	0.0	0.0	0.0	0.0	0.0	0.0	146.4	96.1	60.6	108.5	2.3	184.6	117.1	0.0	0.0	0.0
33.001	2544.5	38.6	0.7	0.3	0.0	0.0	0.0	0.0	0.0	0.0	0.0	117.7	58.9	56.3	30.7	0.7	224.5	25.3	0.0	0.0	0.0
33.002	2568.1	36.1	0.8	0.3	0.0	0.0	0.0	0.0	0.0	0.0	0.0	124.2	61.2	58.5	24.4	0.7	232.2	8.6	0.0	0.0	0.0
33.003	5429.1	79.6	1.0	0.9	0.0	0.0	0.0	0.0	0.0	0.0	0.0	276.9	120.0	98.9	47.9	1.7	624.9	128.2	0.0	0.0	0.0
33.004	9377.5	146.0	0.0	19.4	0.1	0.0	0.0	0.0	0.0	0.0	0.0	504.1	209.6	155.0	86.4	3.4	961.5	202.7	0.0	0.0	0.0
33.005	13415.7	209.2	3.3	23.3	0.1	0.0	0.0	0.0	0.0	0.0	0.0	754.9	284.2	236.8	147.0	7.1	1418.3	333.0	6.1	0.0	0.0
33.006	20933.1	334.6	17.6	47.4	0.1	0.0	0.0	0.0	0.0	0.0	0.0	1246.7	394.8	993.4	215.5	6.5	2370.3	464.2	0.0	0.0	0.0
33.007	9339.7	146.1	1.6	17.9	0.1	0.0	0.0	0.0	0.0	0.0	0.0	506.5	202.7	168.9	96.5	6.0	964.6	242.2	0.0	0.0	0.0
33.008	21020.4	350.2	15.4	42.1	0.0	0.0	0.0	0.0	0.0	0.0	0.0	1283.9	404.7	231.1	130.3	13.2	2565.3	343.2	0.0	0.0	0.0
33.009	13404.0	211.4	4.7	26.3	0.1	0.0	0.0	0.0	0.0	0.0	0.0	506.5	202.7	168.9	96.5	6.0	964.6	242.2	0.0	0.0	0.0
33.010	5431.3	81.3	0.0	9.2	0.0	0.0	0.0	0.0	0.0	0.0	0.0	120.2	57.0	59.3	20.3	0.9	211.2	48.5	0.0	0.0	0.0
33.011	2536.8	36.6	0.7	4.2	0.0	0.0	0.0	0.0	0.0	0.0	0.0	356.4	186.3	126.8	46.0	1.6	782.6	140.7	0.0	0.0	0.0
33.012	5059.1	60.9	0.9	10.6	0.0	0.0	0.0	0.0	0.0	0.0	0.0	309.7	121.0	85.9	43.8	2.2	575.6	149.1	0.0	0.0	0.0
33.013	5958.6	75.4	0.5	9.9	0.0	0.0	0.0	0.0	0.0	0.0	0.0	309.7	121.0	85.9	43.8	2.2	575.6	149.1	0.0	0.0	0.0
33.014	4649.3	57.3	0.5	5.4	0.0	0.0	0.0	0.0	0.0	0.0	0.0	277.6	127.6	153.9	34.1	1.8	476.8	86.6	0.0	0.0	0.0
33.015	5048.6	59.6	2.6	7.2	0.0	0.0	0.0	0.0	0.0	0.0	0.0	326.4	133.4	269.4	29.4	1.7	455.4	35.8	0.0	0.0	0.0
35.016	4617.4	51.7	2.8	5.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	302.0	118.3	258.7	26.3	1.5	426.2	34.0	0.0	0.0	0.0
33.017	4643.4	53.7	1.6	4.9	0.1	0.0	0.0	0.0	0.0	0.0	0.0	292.3	133.9	79.7	38.3	2.0	591.7	143.0	0.0	0.0	0.0
33.018	5965.6	66.5	0.7	9.6	0.0	0.0	0.0	0.0	0.0	0.0	0.0	271.6	122.0	149.8	27.9	1.5	481.8	97.8	0.0	0.0	0.0
33.019	5059.3	57.1	2.2	6.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	271.6	122.0	149.8	27.9	1.5	481.8	97.8	0.0	0.0	0.0
33.020	4605.9	60.0	0.8	7.0	0.5	0.0	0.0	0.0	0.0	0.0	0.0	174.6	70.2	63.8	19.5	1.1	330.6	72.5	0.0	0.0	0.0
33.021	3396.7	36.3	1.0	5.0	0.4	0.0	0.0	0.0	0.0	0.0	0.0	174.6	70.2	63.8	19.5	1.1	330.6	72.5	0.0	0.0	0.0
33.022	4598.9	47.8	0.7	7.0	0.4	0.0	0.0	0.0	0.0	0.0	0.0	174.6	70.2	63.8	19.5	1.1	330.6	72.5	0.0	0.0	0.0
33.023	3369.5	36.8	1.3	5.4	0.5	0.4	0.3	0.0	0.0	0.4	0.5	60.2	41.2	34.9	43.7	2.2	54.0	16.5	0.2	0.0	0.0
33.024	6223.2	102.5	2.4	14.7	1.5	1.7	1.9	0.1	0.0	0.0	0.0	196.1	68.6	68.4	67.3	4.0	224.7	100.9	0.0	0.0	0.0
33.025	5854.2	97.4	1.3	12.0	0.7	0.0	0.0	0.0	0.0	0.0	0.0	151.2	42.5	32.6	68.7	1.8	48.9	21.7	0.0	0.0	0.0
33.026	617.3	132.8	2.8	17.2	1.7	2.0	2.2	0.1	0.0	0.0	0.0	154.5	65.0	67.9	72.6	3.0	228.3	105.1	0.0	0.0	0.0
33.027	5814.3	115.5	2.1	12.8	0.7	1.1	1.3	0.2	0.0	0.0	0.0	121.5	41.8	21.5	181.3	7.7	1222.4	321.7	0.0	0.0	0.0
33.028	11615.3	202.1	2.2	26.3	1.3	1.7	1.8	0.0	0.0	0.0	0.0	648.3	241.8	227.6	176.3	7.7	1167.1	295.7	4.3	0.0	0.0
33.029	11159.6	189.4	2.5	23.3	1.1	1.4	1.6	0.0	0.0	0.0	0.0	623.4	236.5	123.0	196.3	4.5	520.2	241.9	0.0	0.0	0.0
33.030	12865.5	239.6	2.7	27.6	1.5	2.1	2.5	0.0	0.0	0.0	0.0	343.6	133.4	178.4	190.8	6.2	740.2	278.0	0.0	0.0	0.0
33.031	12268.4	217.6	2.5	25.2	1.1	1.8	2.0	0.1	0.0	0.0	0.0	468.4	164.8	96.8	190.8	6.0	323.7	188.8	0.0	0.0	0.0
33.032	12962.4	274.5	3.0	32.8	1.9	3.1	3.4	0.0	0.0	0.0	0.0	236.8	112.6	96.8	191.4	6.0	323.7	188.8	0.0	0.0	0.0
33.033	13102.4	293.2	3.5	39.3	2.4	3.9	4.8	0.0	0.0	0.0	0.0	145.7	99.2	62.9	176.0	4.4	169.6	115.9	1.5	0.0	0.0
33.034	13402.7	279.7	3.7	40.8	2.5	4.6	5.7	0.2	0.1	0.0	0.0	117.7	97.5	57.0	117.8	5.9	117.5	83.8	1.1	0.0	0.0
33.035	10902.8	139.6	1.7	22.3	1.2	1.2	1.2	0.0	0.0	0.0	0.0	630.9	360.1	277.7	165.4	9.1	1775.4	316.3	6.8	0.0	0.0
33.036	13298.7	231.8	3.4	35.1	2.1	4.9	6.2	0.0	0.0	0.0	0.0	126.9	92.3	62.3	191.6	1.0	178.3	113.4	1.2	0.0	0.0
33.037	12570.7	222.8	2.7	35.1	1.7	2.8	5.4	0.0	0.0	0.0	0.0	344.5	136.1	137.5	175.3	1.0	565.2	264.4	2.9	0.0	0.0
33.038	12303.9	205.3	3.1	35.0	1.8	2.9	4.5	0.0	0.0	0.0	0.0	442.7	174.9	142.7	182.0	3.2	738.7	269.4	3.6	0.0	0.0
33.039	13099.8	244.0	3.7	39.7	2.2	6.1	6.1	0.0	0.0	0.0	0.0	243.7	114.9	88.8	196.6	4.7	311.6	221.0	2.2	0.0	0.0
33.040	13342.3	226.1	3.4	36.7	2.2	5.9	7.5	0.2	0.0	0.0	0.0	496	148.6	49.6	183.6	4.8	168.9	108.8	0.0	0.0	0.0
34.001	18137.4	301.6	0.0	37.2	0.7	2.9	3.3	0.0	0.0	0.0	0.0	912.9	472.8	256.6	233.4	14.7	1839.7	485.1	0.0	0.0	0.0
34.002	18031.0	331.3	0.0	46.5	1.3	4.2	4.2	0.1	0.0	0.0	0.0	904.8	470.6	249.8	216.0	7.1	1826.7	543.8	8.2	0.0	0.0
34.003	2682.0	48.1	0.1	6.9	0.1	0.8	0.8	0.0	0.0	0.0	0.0	111.2	71.2	42.5	30.7	0.9	218.2	61.8	0.0	0.0	0.0
34.004	5549.7	86.6	0.4	16.0	0.2	2.3	2.5	0.0	0.0	0.0	0.0	298.5	162.7	86.1	64.6	1.9	629.6	136.0	0.0	0.0	0.0
34.005	8218.6	140.1	0.6	23.7	0.4	2.6	3.0	0.0	0.0	0.0	0.0	403.5	228.3	122.9	97.0	2.5	786.4	199.4	2.3	0.0	0.0
34.006	10975.9	187.4	0.7	33.1	0.6	4.2	5.0	0.0	0.0	0.0	0.0	549.8	166.2	96.3	87.8	3.3	1098.1	294.3	3.4	0.0	0.0
34.007	6586.3	86.9	0.3	16.4	0.3	1.8	2.0	0.0	0.0	0.0	0.0	264.1	154.9	86.3	32.5	0.6	520.1	128.8	0.0	0.0	0.0
34.008	2688.1	48.1	0.1	7.8	0.1	0.9	0.9	0.0	0.0	0.0	0.0	113.2	70.5	41.3	32.5	0.6	223.4	61.9	0.0	0.0	0.0
34.013	18318.1	408.5	5.4	65.4	0.7	6.9	7.1	0.0	0.0	0.0	0.0	973.9	479.8	219.4	434.0	7.4	2034.8	610.6	8.6	0.0	0.0
34.021	1014.4	101.4	0.0	107.9	0.1	0.4	0.4	0.0	0.0	0.0	0.0	1071.2	408.9	575.3	778.3	0.0	2009.0	628.4	15.8	0.0	0.0
34.022	14690.1	48.2	0.0	81.6	2.8	28.0	28.3	18.4	0.0	0.0	0.0	1282.8	458.9	629.3	925.2	0.0	2533.2	878.7	12.9	0.0	0.0
34.023	15972.5	89.6	0.0	134.0	2.8	33.3	33.3	18.4	0.0	0.0	0.0	1540.5	704.2	918.6	928.1	0.0	790.5	359.3	6.5	0.0	0.0
34.024	15838.3	201.6	0.0	105.5	1.1	3.8	4.9	0.0	0.0	0.0	0.0	748.7	287.6	520.5	791.3	4.2	964.9	267.0	4.9	0.0	0.0
34.025	18955.1	100.1	0.0	168.8	3.3	33.2	41.2	0.0	0.0	0.0	0.0	946.5	435.5	148.3	86.4	0.0	1620.2	391.0	0.0	0.0	0.0
34.026	19580.3	0.0	0.0	48.8	0.7	2.4	2.4	0.0	0.0	0.0	0.0	748.9	493.8	217.0	86.4	4.2	1620.2	391.0	0.0	0.0	0.0
34.043	11249.7	180.7	0.0	76.5	0.7	2.4	2.4	0.0	0.0	0.0	0.0	179.2	100.9	46.6	109.5	2.1	146.3	36.1	0.3	0.0	0.0
34.047	13406.8	401.2	0.0	77.9	2.4	12.8	14.7	0.0	0.0	0.0	0.0	776.8	441.5	142.5	68.3	3.0	1691.9	316.1	0.0	0.0	0.0
34.048	11121.1	185.6	0.0	23.1	0.0	1.6	1.6	0.0	0.0	0.0	0.0	776.8	441.5	142.5	68.3	3.0	1691.9	316.1	0.0	0.0	0.0
34.049	11266.2	158.6	0.0	16.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	776.8	441.5	142.5	68.3	3.0	1691.9	316.1	0.0	0.0	0.0
34.050	12548.3	207.9	0.0	25.7	0.0	3.1	3.1	0.0	0.0	0.0	0.0	451.7	142.5	108.8	81.2	2.8	769.1	234.8	0.0	0.0	0.0
35.001	13091.4	309.3</																			

Run #	CH4	C2H6	C2H4	C3H8	C3H6	LC4	n-C4	i-C4	i-C4=	n-C5	C6 plus	CO	CO2	H2	N2	O2	H2O	MeOH	EtOH	CH3O	Oth Alc
35 006	8130.4	171.5	0.0	27.1	0.0	4.2	4.1	0.0	0.0	0.0	0.5	445.8	231.9	101.5	83.9	2.8	817.7	193.7	2.0	0.0	0.0
35 007	20512.1	445.2	0.0	66.3	0.0	8.2	9.4	0.0	0.0	0.0	0.0	1162.6	528.0	209.7	211.3	5.5	2001.3	603.0	7.2	0.0	0.0
35 008	10984.7	236.3	0.0	36.4	0.0	5.3	4.9	0.0	0.0	0.0	0.0	596.3	312.0	135.7	117.3	3.0	1007.5	281.3	3.4	0.0	0.0
35 009	20406.0	452.0	0.0	63.9	0.0	4.6	3.5	0.0	0.0	0.0	0.0	1202.6	505.8	235.8	225.8	6.7	2072.9	600.8	0.0	0.0	0.0
35 010	20350.9	466.8	0.0	72.3	0.0	12.8	15.9	0.0	0.0	0.0	0.0	1242.7	452.6	214.3	225.8	8.3	2144.3	610.5	8.8	0.0	0.0
35 011	17680.5	365.3	0.0	48.7	0.0	6.8	4.4	0.0	0.0	0.0	0.0	1329.7	681.8	222.1	186.3	6.1	2784.8	808.4	0.0	0.0	0.0
35 012	20608.7	554.7	0.0	85.7	0.0	10.0	12.4	0.0	0.0	0.0	0.0	624.9	280.2	125.7	208.6	0.0	628.8	322.5	4.9	0.0	0.0
35 013	19745.0	539.3	0.0	87.9	0.0	9.1	14.5	0.0	0.0	0.0	0.0	753.8	307.5	207.6	268.1	6.3	1180.4	481.4	6.6	0.0	0.0
35 014	20238.8	528.9	0.0	75.9	0.0	7.0	6.4	0.0	0.0	0.0	0.0	1284.6	414.9	271.8	322.7	5.8	2133.8	599.2	0.0	0.0	0.0
35 015	20780.2	672.3	0.0	99.7	0.0	2.6	13.6	0.0	0.0	0.0	0.0	468.6	271.9	120.2	361.5	0.0	583.0	211.9	4.1	0.0	0.0
35 016	21441.2	675.5	0.0	105.6	0.0	3.2	14.4	0.0	0.0	0.0	0.0	320.5	203.0	64.0	360.3	0.0	245.4	131.9	2.6	0.0	0.0
35 017	21300.5	703.1	0.0	119.5	0.0	3.1	19.9	0.0	0.0	0.0	0.0	249.7	185.2	52.7	318.5	0.0	335.2	72.2	0.0	0.0	0.0
35 018	20273.4	457.2	0.0	70.9	0.0	18.3	18.5	0.0	0.0	0.0	0.0	1315.7	368.9	203.0	296.3	0.0	2297.5	545.6	0.0	0.0	0.0
36 001	16895.2	315.1	0.0	42.4	0.0	3.9	4.3	0.0	0.0	0.0	0.0	939.3	351.5	158.7	186.3	5.4	1717.6	478.2	3.5	0.0	0.0
36 002	15839.4	256.8	0.0	37.8	0.0	2.9	3.0	0.0	0.0	0.0	0.0	1147.9	586.8	195.1	165.2	4.4	1735.6	498.8	0.0	0.0	0.0
36 003	18292.2	399.9	0.0	58.0	0.0	16.0	10.7	0.0	0.0	0.0	0.0	625.2	194.6	114.2	157.8	2.3	788.4	494.9	4.3	0.0	0.0
36 004	17770.5	360.6	0.0	52.5	0.0	8.2	8.7	0.0	0.0	0.0	0.0	685.5	264.2	136.7	161.0	2.9	1112.3	363.9	0.0	0.0	0.0
36 005	18753.4	432.6	0.0	63.9	0.0	7.7	8.8	0.0	0.0	0.0	0.0	407.2	191.2	101.4	163.2	0.0	527.0	184.8	0.0	0.0	0.0
36 006	19154.9	458.8	0.0	72.0	0.0	2.3	10.3	0.0	0.0	0.0	0.0	275.6	158.4	61.3	156.5	0.0	309.7	96.3	1.7	0.0	0.0
36 007	19181.4	494.3	0.0	78.8	0.0	2.5	14.2	0.0	0.0	0.0	0.0	918.8	396.9	195.1	165.2	4.4	1735.6	498.8	0.0	0.0	0.0
36 008	16752.8	321.2	0.0	43.7	0.0	4.3	7.0	0.0	0.0	0.0	0.0	1182.0	578.3	247.3	165.7	6.3	2499.3	528.0	0.0	0.0	0.0
36 009	15875.9	285.3	0.0	64.6	0.0	3.1	3.3	0.0	0.0	0.0	0.0	551.5	217.5	115.3	225.7	3.0	822.2	248.0	0.0	0.0	0.0
36 010	18184.1	476.9	0.0	64.6	0.0	1.8	10.9	0.0	0.0	0.0	0.0	687.1	265.7	135.9	255.2	3.8	1131.5	323.1	4.7	0.0	0.0
36 011	17637.6	451.4	0.0	60.1	0.0	9.4	10.7	0.0	0.0	0.0	0.0	417.6	177.2	94.8	272.4	2.8	807.3	128.2	2.1	0.0	0.0
36 012	18521.9	633.0	0.0	75.6	0.0	11.9	13.9	0.0	0.0	0.0	0.0	281.9	146.6	61.7	273.6	2.0	349.7	62.7	1.0	0.0	0.0
36 013	18929.8	674.4	0.0	85.1	0.0	2.4	10.8	0.0	0.0	0.0	0.0	1021.2	448.0	210.3	250.8	6.3	1887.4	499.3	0.0	0.0	0.0
36 014	19071.5	679.2	0.0	90.6	0.0	11.4	14.9	0.0	0.0	0.0	0.0	1282.7	653.0	250.7	216.0	6.8	2708.0	469.1	0.0	0.0	0.0
37 001	18206.9	397.4	0.0	51.8	0.0	2.9	3.8	0.0	0.0	0.0	0.0	629.6	252.9	126.7	209.5	2.8	908.5	168.8	0.0	0.0	0.0
37 002	17161.9	306.9	0.0	41.3	0.0	3.5	3.7	0.0	0.0	0.0	0.0	747.8	297.8	178.6	187.1	0.0	1144.9	449.3	5.5	0.0	0.0
37 003	19962.9	470.2	0.0	82.2	0.0	1.7	6.3	0.0	0.0	0.0	0.0	456.0	193.6	121.2	247.4	2.8	543.9	279.2	4.7	0.0	0.0
37 004	19842.4	472.2	0.0	62.0	0.0	4.4	7.2	0.0	0.0	0.0	0.0	456.0	193.6	121.2	247.4	2.8	543.9	279.2	4.7	0.0	0.0
37 005	20123.8	657.3	0.0	79.2	0.0	2.1	8.8	0.0	0.0	0.0	0.0	313.0	296.4	217.3	253.1	0.0	217.3	0.0	0.0	0.0	0.0
37 006	21303.7	628.6	0.0	48.9	0.0	2.8	10.8	0.0	0.0	0.0	0.0	1186.0	335.0	246.0	262.3	0.0	2021.1	463.2	0.0	0.0	0.0
37 007	20700.5	690.6	0.0	101.8	0.0	2.8	7.4	0.0	0.0	0.0	0.0	1186.0	335.0	246.0	262.3	0.0	2021.1	463.2	0.0	0.0	0.0
37 008	17929.2	431.0	0.0	55.7	0.0	2.6	6.5	0.0	0.0	0.0	0.0	1186.0	335.0	246.0	262.3	0.0	2021.1	463.2	0.0	0.0	0.0
37 009	18072.7	408.1	0.0	55.7	0.0	2.6	6.5	0.0	0.0	0.0	0.0	1186.0	335.0	246.0	262.3	0.0	2021.1	463.2	0.0	0.0	0.0
37 010	18105.3	408.1	0.0	51.3	0.0	1.8	4.7	0.0	0.0	0.0	0.0	1186.0	335.0	246.0	262.3	0.0	2021.1	463.2	0.0	0.0	0.0
37 011	20518.3	693.8	0.0	92.8	0.0	2.5	12.9	0.0	0.0	0.0	0.0	584.2	246.2	154.1	239.4	0.0	779.2	380.4	6.1	0.0	0.0
37 012	19702.6	525.4	0.0	69.7	0.0	1.8	5.0	0.0	0.0	0.0	0.0	584.2	246.2	154.1	239.4	0.0	779.2	380.4	6.1	0.0	0.0
37 013	20562.8	616.4	0.0	93.4	0.0	2.5	8.9	0.0	0.0	0.0	0.0	1186.0	335.0	246.0	262.3	0.0	2021.1	463.2	0.0	0.0	0.0
37 014	20855.5	609.0	0.0	90.1	0.0	2.8	14.1	0.0	0.0	0.0	0.0	280.2	181.2	72.8	244.6	0.0	215.8	183.3	3.4	0.0	0.0
38 001	12412.0	247.8	0.0	33.6	0.0	3.4	3.8	0.0	0.0	0.0	0.0	729.1	280.2	185.9	132.5	3.8	1272.6	335.0	0.0	0.0	0.0
38 002	11423.4	252.5	0.0	38.4	0.0	1.4	5.0	0.0	0.0	0.0	0.0	968.3	365.6	265.3	128.2	4.7	1930.7	171.6	2.8	0.0	0.0
38 003	13348.9	412.2	0.0	59.4	0.0	1.6	6.2	0.0	0.0	0.0	0.0	440.9	169.0	111.1	242.2	2.9	778.9	244.7	2.8	0.0	0.0
38 004	13043.6	344.2	0.0	45.0	0.0	4.8	6.0	0.0	0.0	0.0	0.0	547.4	200.8	149.9	212.7	3.1	778.9	244.7	2.8	0.0	0.0
38 005	13779.1	399.5	0.0	61.1	0.0	1.7	8.9	0.0	0.0	0.0	0.0	330.3	147.8	99.3	163.9	1.9	396.9	88.2	0.0	0.0	0.0
38 006	13968.0	424.0	0.0	70.5	0.0	2.1	10.2	0.0	0.0	0.0	0.0	1186.0	335.0	246.0	262.3	0.0	2021.1	463.2	0.0	0.0	0.0
38 007	14004.8	453.7	0.0	75.1	0.0	2.2	10.6	0.0	0.0	0.0	0.0	1186.0	335.0	246.0	262.3	0.0	2021.1	463.2	0.0	0.0	0.0
38 008	13593.1	428.9	0.0	64.2	0.0	1.7	8.8	0.0	0.0	0.0	0.0	1186.0	335.0	246.0	262.3	0.0	2021.1	463.2	0.0	0.0	0.0
38 009	17172.4	567.8	0.0	94.6	0.0	2.6	13.8	0.0	0.0	0.0	0.0	1186.0	335.0	246.0	262.3	0.0	2021.1	463.2	0.0	0.0	0.0
38 010	14048.1	419.7	0.0	71.6	0.0	2.1	10.7	0.0	0.0	0.0	0.0	1186.0	335.0	246.0	262.3	0.0	2021.1	463.2	0.0	0.0	0.0
38 011	20440.5	654.5	0.0	86.3	0.0	2.8	13.4	0.0	0.0	0.0	0.0	1186.0	335.0	246.0	262.3	0.0	2021.1	463.2	0.0	0.0	0.0
38 012	19930.7	694.1	0.0	98.2	0.0	2.3	12.5	0.0	0.0	0.0	0.0	1186.0	335.0	246.0	262.3	0.0	2021.1	463.2	0.0	0.0	0.0
38 013	20397.4	698.8	0.0	110.4	0.0	2.8	14.7	0.0	0.0	0.0	0.0	1186.0	335.0	246.0	262.3	0.0	2021.1	463.2	0.0	0.0	0.0
38 014	19275.2	698.2	0.0	98.9	0.0	1.9	9.0	0.0	0.0	0.0	0.0	1186.0	335.0	246.0	262.3	0.0	2021.1	463.2	0.0	0.0	0.0
38 015	19232.9	618.2	0.0	89.6	0.0	0.0	8.8	0.0	0.0	0.0	0.0	1186.0	335.0	246.0	262.3	0.0	2021.1	463.2	0.0	0.0	0.0
38 016	19803.7	644.1	0.0	93.5	0.0	2.6	9.1	0.0	0.0	0.0	0.0	1186.0	335.0	246.0	262.3	0.0	2021.1	463.2	0.0	0.0	0.0
38 017	20008.8	587.4	0.0	78.8	0.0	5.0	11.7	0.0	0.0	0.0	0.0	1186.0	335.0	246.0	262.3	0.0	2021.1	463.2	0.0	0.0	0.0
38 018	11442.3	234.9	0.0	36.2	0.0	0.0	2.7	0.0	0.0	0.0	0.0	1186.0	335.0	246.0	262.3	0.0	2021.1	463.2	0.0	0.0	0.0
38 019	11442.3	234.9	0.0	36.2	0.0	0.0	2.7	0.0	0.0	0											

Run #	OUTFLOWS (mmol/hour)	CH4	C2H4	C3H8	C3H6	LC4	n-C4	1-C4=	c-2-C4=	1,2-C4=	LC4=	n-C5	C6 plus	CO	CO2	H2	N2	O2	H2O	MeOH	EtOH	CH3CO	Oth Alcs
41.004	19072.1	643.4	1.7	74.2	1.4	12.7	16.2	0.0	0.0	0.0	0.4	2.0	1.5	111.0	139.5	78.5	470.1	0.0	365.0	102.0	1.9	8.254	0.3
41.005	15658.5	368.1	0.8	41.5	0.4	1.9	2.6	0.0	0.0	0.0	0.0	0.0	0.0	1086.9	603.8	324.1	488.0	6.7	2680.4	620.3	6.3	0	2.6
41.006	18921.1	754.1	1.9	88.5	1.7	11.8	16.6	0.0	0.0	0.0	0.0	0.0	0.0	122.7	135.5	72.7	587.2	7.0	266.3	154.9	3.5	6.263	0.8
41.007	15847.6	334.9	0.0	44.4	0.9	1.8	2.4	0.0	0.0	0.0	0.0	0.0	0.0	1086.9	636.1	285.0	483.2	0.0	2610.8	518.2	6.3	0	0.0
41.008	14841.1	284.8	0.0	42.2	0.0	2.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	880.0	822.8	1372.6	386.3	4.5	2468.2	431.1	8.0	0	0.0
41.009	15913.8	343.8	0.0	47.7	0.1	2.5	3.2	0.0	0.0	0.0	0.0	0.0	0.0	684.8	570.3	322.8	399.1	6.0	1716.2	413.5	6.2	0	0.0
41.010	18218.0	597.3	0.0	72.2	0.1	12.8	16.5	0.0	0.0	0.0	0.0	0.0	0.0	121.4	165.9	139.1	409.1	7.0	170.3	83.2	3.1	0	1.0
41.011	19157.3	709.9	0.8	85.1	1.2	11.7	15.9	0.0	0.0	0.1	0.4	2.7	2.0	122.1	165.9	139.1	409.1	7.0	170.3	83.2	3.1	0	1.0
41.012	15860.0	381.1	0.5	43.6	0.8	2.1	2.8	0.0	0.0	0.0	0.0	0.0	0.0	1081.1	688.7	339.8	424.2	6.9	2388.9	527.9	10.7	0	1.6
41.013	16910.5	483.5	0.6	50.7	0.8	2.9	4.2	0.0	0.0	0.0	0.0	0.0	0.0	828.8	487.7	339.8	424.2	6.9	2388.9	527.9	10.7	0	1.6
41.014	13518.1	389.0	0.0	39.2	0.0	2.3	2.3	0.0	0.0	0.0	0.0	0.0	0.0	893.7	480.5	325.2	368.7	4.9	1754.2	498.0	6.6	0	2.3
41.015	11909.1	316.2	0.0	40.8	0.0	1.9	1.6	0.0	0.0	0.0	0.0	0.0	0.0	596.4	496.5	466.7	308.8	0.0	2089.9	224.7	0.0	0	0.0
42.001	16902.5	469.7	0.9	63.9	0.7	2.1	3.2	0.0	0.0	0.0	0.0	0.0	0.0	1120.6	631.3	242.4	479.7	0.0	47784.7	497.6	0.0	0	0.0
42.002	18965.9	849.9	0.8	103.3	1.9	6.3	12.6	0.0	0.0	0.0	0.0	0.0	0.0	298.8	112.0	121.0	521.4	6.0	33249.9	70.5	0.0	0	0.0
42.003	16736.8	537.8	0.0	60.7	0.0	3.2	9.6	0.0	0.0	0.0	0.0	0.0	0.0	997.4	411.2	236.0	473.5	0.0	34828.7	403.7	0.0	0	0.0
42.004	18871.4	961.4	0.2	129.6	1.3	16.3	17.3	0.0	0.0	0.0	0.0	0.0	0.0	327.8	178.7	58.8	546.3	145.6	33714.7	27.4	0.0	0	0.0
42.005	14561.8	565.3	0.0	73.2	0.0	1.1	10.7	0.0	0.0	0.0	0.0	0.0	0.0	1018.5	390.0	434.6	485.6	0.0	34600.8	278.5	0.0	0	0.0
42.006	13057.8	609.1	0.0	70.3	0.0	3.3	3.5	0.0	0.0	0.0	0.0	0.0	0.0	918.4	405.6	524.2	482.2	0.0	34445.8	171.0	0.0	0	0.0
42.007	17717.5	516.5	0.0	81.6	2.8	3.3	3.5	0.0	0.0	0.0	0.0	0.0	0.0	1077.8	362.3	639.7	485.8	0.0	16248.5	191.5	0.0	0	0.0
42.008	17275.8	330.9	0.0	51.3	0.9	2.0	3.0	0.0	0.0	0.0	0.0	0.0	0.0	1139.8	529.3	393.5	6389.3	0.0	18518.7	271.8	0.0	0	0.0
42.009	17439.7	364.3	0.0	41.2	0.9	3.5	10.6	0.0	0.0	0.0	0.0	0.0	0.0	910.4	509.7	95.1	531.1	6.7	17472.8	369.2	0.0	0	152.9
42.010	18372.9	132.2	509.5	39.0	5.3	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	888.8	220.3	8.8	223.1	0.0	18256.6	450.8	0.0	0	157.9
42.011	19996.7	275.3	187.3	88.9	0.3	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	5.8	307.2	9.7	243.7	1436.7	18478.6	0.0	0.0	0	184.3
42.012	18983.8	228.1	438.3	30.8	1.0	4.4	0.0	0.0	0.0	0.0	0.2	1.5	1.2	908.5	172.3	0.0	246.4	7.4	18200.0	495.3	0.0	0	189.7
42.013	18481.0	233.2	446.0	34.7	1.0	4.2	9.5	0.0	0.0	0.0	0.0	0.0	0.0	942.4	163.7	0.0	286.0	1.3	18235.2	478.6	0.0	0	190.6
42.014	18824.3	214.7	421.8	19.9	1.1	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	883.6	190.0	0.0	237.7	78.3	33509.2	524.8	0.0	0	484.2
42.015	19423.6	208.8	493.9	32.9	2.4	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	1301.4	293.6	0.0	188.3	0.9	33522.1	505.0	0.0	0	0.0
42.016	16880.7	148.6	550.2	2.6	1.0	3.8	1.5	0.0	0.0	0.0	0.0	0.0	0.0	1106.2	222.4	0.0	175.3	126.3	34499.6	501.8	0.0	0	520.8
42.017	16864.6	138.4	601.1	12.2	0.8	3.1	4.2	0.0	0.0	0.0	0.2	1.0	0.0	1256.3	240.0	0.0	191.5	3.9	19158.2	481.9	0.0	0	167.4
42.018	20978.4	381.1	157.2	84.8	1.9	13.1	16.2	0.2	4.5	0.1	0.7	8.6	0.0	158.2	57.2	0.0	237.2	0.8	18122.2	100.4	0.0	0	201.4
42.020	21356.8	450.5	111.0	92.7	1.5	16.9	22.3	0.0	0.0	0.0	0.3	8.1	0.0	0.0	38.6	4.9	221.2	0.0	18885.9	0.0	0.0	0	204.6
42.021	21356.8	397.3	154.5	112.9	1.4	17.4	25.8	0.0	0.0	0.0	0.0	12.4	8.7	0.0	58.2	2.0	234.1	0.8	18885.9	0.0	0.0	0	184.3
42.023	21018.9	402.7	179.3	93.8	4.6	14.2	19.7	0.4	0.0	0.0	0.0	6.0	3.0	168.0	118.3	8.9	273.9	0.3	16414.8	0.0	0.0	0	356.6
44.009	17053.0	300.2	41.8	32.8	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	761.3	512.4	302.7	303.7	0.0	15787.6	79.7	0.0	0	333.3
44.010	19453.2	198.6	1.6	118.4	0.0	0.0	147.8	0.0	0.0	0.0	0.0	0.0	0.0	2236.2	878.6	0.0	129.1	1.6	1304.6	261.4	0.0	0	810.1
44.011	16482.4	318.7	1.3	73.6	0.0	54.2	80.2	0.0	0.0	0.0	0.0	0.0	0.0	1672.8	701.9	0.0	324.3	1.0	2336.8	638.9	0.0	0	1880.1
44.012	19085.6	643.4	0.6	85.6	1.3	4.6	0.0	0.0	0.0	0.0	0.0	0.0	4.0	261.6	103.8	44.5	273.4	1.2	234.8	0.0	0.0	0	2503.9

END

**DATE
FILMED**

2 / 18 / 93