STUDY OF MECHANICAL BEHAVIOR AND INTERNAL STRUCTURE

OF FERRITIC NANOCRYSTALLINE MATERIAL

DOE/ER/45229--27

DE92 040858

Technical Progress Report

For period 1 August 1991 - 1 August 1992

J. R. Weertman, Principal Investigator
Walter P. Murphy Professor of Materials Science and Engineering

Northwestern University
Evanston, Illinois 60208

August 1992

THE U.S. DEPARTMENT OF ENERGY

UNDER CONTRACT DE-FG-02-86ER45229

NOTICE

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the Department of Energy, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability of responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product or process disclosed or represents that its use would not infringe privately-owned rights.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

TECHNICAL PROGRESS REPORT FOR THE PERIOD

1 AUGUST 1991 TO 1 AUGUST 1992

The research thrust of this grant has been directed into two areas. The principal effort has been spent in an investigation of the synthesis, mechanical behavior and internal structure of ferritic nanocrystalline material. A second effort involves a study of the high temperature behavior of several ferritic steels. In particular, we are investigating the precursors and earliest stages of fatigue crack initiation, especially how initiation is affected by hold times and by environment.

1. Nanocrystalline Material

A major effort in the nanocrystalline research this past year was devoted to trying to understand the origin of the "negative Hall-Petch slope". (This research thrust was begun last year and is continuing.) A number of workers [1-3] have reported that at the finest grain sizes, the hardness of nanocrystalline metals drops markedly with decreasing grain size. Various explanations have been put forth to explain this anomalous behavior [e.g., 3,4]. A literature survey we carried out seemed to indicate that a negative Hall-Petch slope is most likely to be observed when a curve of hardness vs grain size is obtained by use of a single, originally fine-grained sample that is repeatedly heated. Studies in which only as-received material was used generally reported normal Hall-Petch behavior [5-7]. (All of the samples we had used were in the as-received state, and we consistently have found a positive slope of hardness or yield strength vs $(\text{grain size})^{-0.5}$). To test this hypothesis, Gretchen Fougere has taken samples of Pd and of Cu and measured the effect of repeated annealings on their grain size and hardness. Whereas the specimens in their as-received state all corresponded to points on hardness--grain size curves with positive Hall-Petch slopes, the heating produced an initial hardening

as well as increased grain size. Only after extended annealing did a further increase in grain size lead to a decrease in hardness. This work has been published in Scripta Metallurgica et Materialia (a reprint is enclosed) and presented at the NATO ASI on nanocrystalline materials this summer as an invited lecture.

Although it now seems clear that annealing not only increases grain size but also initially strengthens as-compacted nanocrystalline material, the reason for this behavior is not known. The presence of large residual strains in the as-prepared material may be responsible. Valiev et al. [8] have noted a drop in strain contrast around grain boundaries after annealing in TEM micrographs of submicron grain size metals produced by intense deformation. At the same time the hardness increases. To study the relationship between residual strain, grain size, hardness, and annealing, wide angle diffraction was carried out last month by Paul Sanders and Carl Youngdahl on nanocrystalline samples on the MATRIX line at the NSLS. A number of small samples, all cut from the same disk to insure uniformity, were subjected to various annealing temperatures. Three such series were measured. The data are still being analyzed for grain size and residual strain.

Atomic force microscopy has been used to follow changes in grain size with heating, and thus to check the results obtained by x-ray. This study is forming the master's thesis of Andrea Wilford. After a great deal of difficulty in achieving just the right conditions she has obtained AFM images of the surface grains in the nanocrystalline Pd samples used in the synchrotron experiment described above. It is difficult to obtain precise grain size values from the AFM pictures because not all grains on the surface are picked up by the probe. It appears that some surface grains stick up while others lie below the average level of the surface. Using various stereological techniques, average grain sizes are being measured and will be compared with the synchrotron results. A very distinct increase in grain size can be seen with increasing annealing temperature (see Fig. 1).

Work on designing a new compaction unit has continued by graduate student Gretchen Fougere and scientists at ANL. The work has accelerated since we received the supplemental funding for the unit, and now parts are being ordered and construction has begun. This extra funding gave a great boost to the research.

Paul Sanders is constructing a creep machine suitable for testing small nanocrystalline samples in vacuum at elevated temperatures. The creep behavior of nanocrystalline metals is largely unknown. Diffusional creep should become important at comparatively low temperatures because of the small grain size, but grain boundary sliding also may be a major factor.

New procedures for operating the equipment to make nanocrystalline material have been formulated and instituted at Argonne to meet safety standards. The students have completed, or are in the process of completing, an extended training course so that they will be allowed to conduct evaporations on their own.

2. Influence of Environment and Hold Time on High Temperature Fatigue Life in Chromium Ferritic Steels

The goal of this work is to understand the influence of environment and hold pattern on the high temperature fatigue behavior of two chromium ferritic steels, Fe2.25Cr1Mo and Fe9Cr1Mo+V,Nb.

It was expected that this research, which constitutes the thesis work of Rena Hecht, would be completed within the last year. However the MTS equipment was down for an extended period because of the MS&E Department's move to our new building. Delivery on the new MTS instrument, purchased on a DOE Instrumentation Grant, was held off until it could be installed directly in the new building. That has now been completed, and personnel from MTS have supervised the final hook ups and conducted training sessions for the graduate students and technician in charge of the facility. There is much joy in anticipating the use of

the new MTS unit with its sophisticated electronic controls and servohydraulic system.

The Fe2.25Cr1Mo study is completed. A paper describing part of the results has been submitted to Metallurgical Transactions and accepted (with minor revisions). A copy is attached. The major effort this last year has been on the effect of oxidation on the hold time behavior of the Fe9Cr1Mo+NbV steel. Although the rate of oxidation is considerably less in the higher chromium steel (and thus cracking patterns and cross-sections are much harder to observe), the effect of holds on cracking behavior and spalling in the oxide layer is about the same as in the Fe2.25Cr1Mo material. A few differences are noted. For example, whether tested in air or vacuum of 10^{-5} T, a compressive hold pattern is almost always more damaging than tensile holds in the Fe9Cr1Mo+NbV, whereas in the other steel tensile holds are more damaging in vacuum, compressive in air. The latter steel appears to be more subject to creep-type damage than the 9Cr steel, so the flip in behavior between air and vacuum is not surprising. Once the harmful effects of the oxide layer are largely removed by testing in a 10^{-5} vacuum, the creep damage incurred during tensile holds becomes the dominant factor in determining life. Figure 2 shows Coffin-Manson plots for the Fe9Cr1Mo+NbV steel tested with various cycling patterns at 600° C. Tension hold points, for both air and vacuum, and compressive hold points for vacuum, lie on about the same line. This result probably follows from the resistance to creep damage by the Fe9Cr1Mo+NbV steel, together with the fact that in the case of tension holds in air the oxide is likely to spall off without creating the deep, damaging intrusions seen with compressive holds. When compressive holds are combined with an air environment, the fatigue life does not follow a Coffin-Manson relationship. Figures 3 and 4 show the progression of oxidation in Fe9Cr1Mo+NbV fatigued at 600° C with a total strain amplitude of 1.05%. In the case of 2 minute tension holds (Fig. 3), the slip steps that form approximately at 45° with respect to the stress axis (vertical) can

still be seen after 1400 cycles. Oxidation, which appears as white regions, is evident in the polishing scratches and on the exposed ridges of the slip steps. In the case of compression holds, the slip steps no longer are visible after 1100 cycles, and horizontal cracks have already started to form in the oxide (Fig. 4). Oxidation is quite heterogeneous, as seen in Fig. 5, and seems to appear first in regions of high residual stress. Figure 5 clearly demonstrates the relationship between an oxide coating and cracking. Figure 6 shows that the rate of oxidation is greatly enhanced by fatigue.

REFERENCES

1. K. Lu, W. D. Wei and J. T. Wang, Scripta Met. et Mater., 24, 2319 (1990).
2. T. Christman and M. Jain, Scripta Met. et Mater., 25, 767 (1991).
3. A. H. Chokshi, A. Rosen, J. Karch and H. Gleiter, Scripta Met. 23, 1679 (1989).
4. T. G. Nieh and J. Wadsworth, Scripta Met. et Mater., 25, 955 (1991).
5. J.S.C. Jang and C. C. Koch, Scripta Met. et Mater., 24, 1599 (1990).
6. G. W. Nieman, J. R. Weertman, and R. W. Siegel, Scripta Met. 23, 2013 (1989).
7. S. K. Ganapathi and D. A. Rigney, Scripta Met. et Mater., 24, 1675 (1990).
8. R. Z. Valiev, F. Chmelik, F. Bordeaux, G. Kapelski and B. Baudalet, Scripta Met. et Mater., in press.

PLANS FOR THE BALANCE OF THE GRANT YEAR

- * Continue investigation of internal structural changes that lead to an initial strengthening upon annealing of as-prepared samples. This goal will be pursued by X-ray diffraction and TEM.
- * Complete the compaction unit. The improved vacuum and sample encapsulation feature is needed especially by Gretchen Fougere in the preparation of iron samples, and will also be of great value to everyone who is using the evaporation instruments.
- * Continued preparation of samples. This will include both pure metals and more complex material (alloys and metal/oxide

composites). The Argonne evaporation unit that used E-beam heating probably will be used for the latter. After the long shut down of the evaporation units at Argonne for safety modifications, the first year students are becoming familiar with evaporation techniques, and working out the optimum evaporation conditions for each material.

- * Continue construction of creep equipment.
- * Finish PhD thesis on hold-time effects and prepare further papers for publication.

STATEMENT OF EFFORT

The Principal Investigator is devoting 15% of her effort during the academic year to this project. During the summer 25% of her time is being devoted to it. Note that she will complete her term as department chairman 1 September 1992. Rena Hecht, who is working on the hold time effect in chromium steels, has finished five years in graduate school and will complete her PhD during the current grant year. She has accepted a position with Ford. Gretchen Fougere will be starting her third year of graduate school. She is working on nanocrystalline iron and steel. She will be supported again this year by Argonne. Carl Youngdahl and Paul Sanders have finished their first year of graduate studies. Their research topics are not yet totally defined, but Carl probably will work on the fabrication, mechanical behavior and characterization of more complex nanocrystalline material. Paul probably will continue the work of Bill Nieman and look further into mechanical behavior/structure of pure metals, including creep and fatigue behavior. (There are few data available on creep properties of nanocrystalline material and essentially none on fatigue behavior.) We are collaborating with Richard Siegel and Jeff Eastman at Argonne National Laboratory.

Andrea Wilford is completing her MS thesis on AFM studies of the annealing response of nanocrystalline Pd. She was primarily supported on a GEM (minority) fellowship. She has accepted a

position with the Nuclear Regulatory Commission. The measurements on the growth rate of oxide on Fe_{2.25}Cr₁Mo under no load conditions (Fig. 6) were taken this summer by Courtney Armstrong, supported by the NSF Materials Research Internships for Minority Undergraduates program.

PAPERS DURING PAST GRANT YEAR

Published

"Characterization of Modified Fe₉Cr₁Mo Steel by Anomalous Small-Angle Scattering", P. R. Jemian, J. R. Weertman, G. C. Long and R. D. Spal, Acta Metallurgica et Materialia 39, 2477 (1991).

"Grain-Size Dependent Hardening and Softening of Nanocrystalline Cu and Pd", G. E. Fougere, J. R. Weertman, R. W. Siegel and S. Kim, Scripta Metallurgica et Materialia 26 1879 (1992).

Accepted for Publication

"Periodic Oxide Cracking on Fe_{2.25}Cr₁Mo Produced by High Temperature Fatigue Tests with a Compression Hold", R. L. Hecht and J. R. Weertman, Metallurgical Transactions.

Submitted for Publication

"SANS and TEM Studies of Isothermal M₂C Carbide Precipitation in Ultrahigh Strength AF1410 Steel", A. J. Allen, D. Gavillet and J. R. Weertman.

ORAL PRESENTATIONS DURING GRANT YEAR

"Mechanical Behavior of Nanocrystalline Metals", G. W. Nieman, J. R. Weertman and R. Siegel:

- * ASM-MSD Committee, TMS Fall Meeting, Cincinnati, OH, 10/24/91
- #* MIT, Cambridge, MA, 11/14/91
- #* Alcoa Corporate Research Lab, Alcoa, PA, 12/13/91

#* Westinghouse Corporate Lab, Pittsburgh, PA, 2/6/92

#* NATO ASI on Nanostructured Materials, Portugal, 6/28/92

"Effect of Environment and Hold Pattern on Fatigue Behavior of Fe9Cr1MoNbV Steel Compared to Fe2.25Cr1Mo Steel", R. Hecht and J. R. Weertman, TMS Annual Meeting, San Diego, CA, 3/4/92

"Periodic Surface Cracking on Fe2.25Cr1Mo Steel that Results from High Temperature Compressive Hold Fatigue Tests", R. Hecht and J. R. Weertman, TMS Annual Meeting, San Diego, CA, 3/4/92.

"Use of ASAXS to Study the High Temperature Behavior of a Carbide Species in a Complex Steel, P. Jemian, G. Long and J. R. Weertman, NSLS Workshop on SAXS for Materials Science, Brookhaven National Lab, Upton, NY, 5/18/92

Invited lecture

(a)

(b)

Fe9Cr1MoNbV Fatigue Lifetime Data for $T = 600^{\circ}\text{C}$

Fig. 2. Plastic strain range vs number of cycles to failure for Fe9Cr1Mo+NbV specimens tested in total strain control at 600°C . Vacuum was 10^{-5} T. Continuous cycling data is from the PhD thesis of S. Kim.

(a)

(b)

Fig. 3. SEM micrographs of surfaces of Fe9Cr1Mo+NbV specimens fatigued with a tension hold in air at 600° C with a total strain range of 1.05%. The tests were stopped after (a) 800 cycles, and (b) 1400 cycles.

Fig. 5. Cracks in small patches of oxide on sample of Fe9Cr1Mo+NbV fatigued with a 2 minute compression hold at 600° C, total strain range = 1.0%, cycled to failure, $N_f = 1480$.

Fig. 6. A comparison of oxide thickness vs time on Fe_{2.25}Cr₁Mo at 600°C. Oxidation on specimens fatigued with either a compression hold (CH) or a tension hold (TH) far exceeds the thickness observed for static growth conditions. "Predicted" line is from the work of K. D. Challenger, A. K. Miller, and R. L. Langdon, J. Mater. Ener. Sys. 3, 51 (1981).

END

**DATE
FILMED**

12 / 8 / 92