ANL/CHM/CP-84363
ICSM '94 Seoul, Korea
(to be published in Synthetic Metals)

CONF-9407117--4

Studies of the Microwave Resistivity of κ -(BEDT-TTF)₂Cu[N(CN)₂]Cl

M. Dressel^{a*}, G. Grüner^a, K.D. Carlson^b, H.H. Wang^b, and J.M. Williams^b

^a Department of Physics, University of California, Los Angeles, 405 Hilgard Ave., Los Angeles, CA 90024-1547

^b Chemistry and Material Science Division, Argonne National Laboratory, Argonne, IL 60349⁺

Abstract

We have performed temperature dependent measurements of the surface impedance of κ -(BEDT-TTF)₂Cu[N(CN)₂]Cl in both directions, parallel and perpendicular to the highly conducting planes. In both orientations the microwave resistivity basically follows the dc behavior for $T > 15$ K: the crystal undergoes a broad metal-insulator transition at around 50 K. While there are no indications of superconductivity at ambient pressure found in the dc resistivity and by ac susceptibility, the microwave resistivity clearly drops at 13 K and again at 5 K, indicating two superconducting phases. When pressure is applied by embedding it in grease, only the well known superconducting phase transition at $T_c = 13$ K remains.

1 Introduction

Although (BEDT-TTF)₂Cu[N(CN)₂]Cl is the organic superconductor of the BEDT-TTF family with the highest transition temperature ($T_c = 12.8$ K at $p = 0.3$ kbar) [1, 2], only little investigations have been conducted on material because of the very sensitive pressure dependence of many physical parameters. In contrast to the isostructural compound (BEDT-TTF)₂Cu[N(CN)₂]Br at ambient pressure κ -(BEDT-TTF)₂Cu[N(CN)₂]Cl remains semiconductive below 100 K and finally undergoes a transition near 40 K to an insulating ground state (Fig. 1) [1] which was identified as an antiferromagnetic transition [3]; a weak ferromagnetic state is found below 22 K. In a series of papers Sushko et al. [5, 4] studied the pressure and Br-doping dependence of the thermopower, magnetization and resistivity, and found reentrant superconductivity.

2 Experimental

The single crystals were characterized by dc resistivity and ac susceptibility measurements. We performed microwave cavity perturbation experiments [6] at 35 GHz to obtain the high frequency conductivity as a function of temperature. The sample was placed in a cylindrical TE₀₁₁ cavity in two different positions to measure the (ac) resistivity and to probe the losses perpendicular to the planes.

3 Results and Discussion

In Fig. 1 the dc resistivity of (BEDT-TTF)₂Cu[N(CN)₂]Cl is displayed as a function of temperature for both directions parallel and perpendicular to the highly conducting (ac)-planes. At room temperature we obtain $\rho_{||} = 1.2 \Omega\text{cm}$ and $\rho_{\perp} = 164 \Omega\text{cm}$. Basically the temperature dependence is the same for both directions with a slight increase of the anisotropy from 1:130 to 1:470 upon cooling down to 10 K.

Figure 1: Temperature dependent dc resistivity of (BEDT-TTF)₂Cu[N(CN)₂]Cl in both orientations.

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

*Supported by the Alexander von Humboldt-Foundation

⁺Office of Basic Energy Sciences, Division of Materials Sciences, of the US Department of Energy. Contract No. W-31-109-ENG-38

MASTER

The submitted manuscript has been authored by a contractor of the U. S. Government under contract No. W-31-109-ENG-38. Accordingly, the U. S. Government retains a nonexclusive, royalty-free license to publish or reproduce the published form of this contribution, or allow others to do so, for U. S. Government purposes.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, make any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

The temperature dependence of the high frequency resistivity is displayed in Fig. 2. The upper panel shows the case when the electric field was in the (*ac*)-plane, in the lower panel the resistivity perpendicular to the plane is plotted. The semiconductor-insulator transition at around 40 K shows up much stronger in the perpendicular direction than it does in the parallel one. In agreement with the dc results (solid lines in Fig. 2), we find a sharp increase in resistivity $\rho_{\perp}$ of about three orders of magnitude between 80 and 20 K. For the in-plane resistivity a more or less continuous increase was found with $\rho \propto T^{-3/2}$.

Figure 2: Normalized microwave resistance (35 GHz) of (BEDT-TTF)₂Cu[N(CN)₂]Cl as a function of temperature; the solid line represents the dc data for comparison. Upper panel: In-plane resistivity $\rho_{||}$. Lower panel: Resistivity perpendicular to the (*ac*)-plane $\rho_{\perp}$.

In both orientations we find a rapid drop of the resistivity at about 12.5 K; at this temperature the superconducting transition is reported if a moderate pressure of 300 bar is applied. Although we do not find evidence of superconductivity in our dc resistivity and ac susceptibility measurements, we interpret our findings as an indication that parts of the sample are superconducting, in accord with magnetization studies which show a direct transition from the semiconducting to the superconducting state [5]. Microwave measurements probe the integrated bulk, i.e. the data are the average over the entire sample. Small parts of the sample may be under internal stress and therefore superconductive.

Cooling down further, a second drop is seen at around 5 K. This is much more enhanced in the perpendicular direction, although indications can also be found for the in-plane resistivity. Since this cannot be explained by increasing internal stress, which would result in a gradual increase of the conducting fraction, these findings give evidence for a second superconducting phase not reported before.

In order to apply pressure, we coated the crystal with Apiezon N grease. The resistivity drop at 12 K becomes more enhanced, indicating that a larger volume fraction of the specimen is superconducting. No second step at 5 K is observed.

4 Conclusion

Even at ambient pressure, the microwave resistivity of κ -(BEDT-TTF)₂Cu[N(CN)₂]Cl shows a significant decrease at 12.5 K, and another drop at around 5 K. We conclude that there are superconducting domains present at ambient pressure, and there is a second superconducting phase.

References

- [1] J.M. Williams *et al.*, Inorg. Chem. 29 (1990) 3272
- [2] J.E. Schirber *et al.*, Phys. Rev. B 44 (1991) 4666
- [3] U. Welp *et al.*, Phys. Rev. Lett. 69 (1992) 840
- [4] V.A. Bondarenko *et al.*, Synth. Met. 56 (1993) 2386; V.A. Bondarenko *et al.*, Synth. Met. 56 (1993) 2391
- [5] Yu.V. Sushko, K. Andres, Phys. Rev. B 47 (1993) 330; Yu.V. Sushko, K. Andres, N.D. Kusch, E.B. Yagubskii, Solid State Commun. 87 (1993) 589; Yu.V. Sushko, H. Ito, T. Ishiguro, S. Horiuchi, G. Saito, J. Phys. Soc. Jpn. 62 (1993) 3372; Yu.V. Sushko, H. Ito, T. Ishiguro, S. Horiuchi, G. Saito, Solid State Commun. 87 (1993) 997
- [6] O. Klein, S. Donovan, M. Dressel, and G. Grüner, Int. J. Infrared and Millimeter Waves 14 (1993) 2423; S. Donovan, O. Klein, M. Dressel, K. Holczer, and G. Grüner, Int. J. Infrared and Millimeter Waves 14 (1993) 2459; M. Dressel, O. Klein, S. Donovan, and G. Grüner, Int. J. Infrared and Millimeter Waves 14 (1993) 2489