Molecular and Polymeric Ceramic Precursors

DOE/ER/13732--6

DE93 002841

Research Progress Report

Rose

NOV 12 1992

Larry G. Sneddon

The Trustees of the University of Pennsylvania
Philadelphia, Pennsylvania 19104

NOTICE

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the Department of Energy, nor any of their employees, make any warranty, express or implied, or assumes any legal liability of responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product or process disclosed or represents that its use would not infringe privately-owned rights.

June, 1992

Prepared for

The U.S. DEPARTMENT OF ENERGY

AGREEMENT NO. DE-FG02-87ER13732

MASTER

TECHNICAL REPORT

Grant No. DE-FGO2-87ER13732

Project Title

"Molecular and Polymeric Ceramic Precursors"

Abstract

The development of new methods for the production of complex materials is one of the most important problems in modern solid state chemistry and materials science. This project is attempting to apply the synthetic principles which have evolved in inorganic and organometallic chemistry to the production of technologically important non-oxide ceramics, such as boron nitride, boron carbide and metal borides. Our recent work has now resulted in the production of new polymer systems, including poly(B-vinylborazine), polyvinylpentaborane and polyborazylene, that have proven to be high yield precursors to boron-based ceramic materials. Current work is now directed toward the synthesis of new types of molecular and polymeric boron-containing species and an exploration of the solid state properties of the ceramics that have been produced in these studies.

Summary of Scientific Progress

As an alternative to high-temperature powder techniques, there has recently been great interest in the development of polymer precursors to ceramic materials. Such routes would appear to offer a number of potential advantages: (1) a suitable polymer could have a precisely controlled stoichiometry with a composition which could be systematically varied to optimize ceramic properties, (2) the polymer could be formed into a desired shape or thin-film and then converted to the ceramic with possible retention of form, and (4) the polymer could undergo decomposition at low temperatures, enabling ceramic formation under milder conditions than those used in conventional techniques.

Our work has concentrated on the syntheses and chemical properties of new boron containing molecular and polymeric systems that might serve as useful precursors to technologically important boron-based ceramics, including boron nitride, boron carbide and metal borides. Some of the most important results of our DOE sponsored research are briefly describe in the following sections.

A Polymer Precursor Route to TiB₂/TiN Nanocomposites.

Because of their high melting points, hardness and chemical resistance at high temperatures, metal borides and metal nitrides are two of the most important families of engineering ceramics. We have now developed a new polymer-based synthetic route by which nanophase titanium boride/titanium nitride composite materials may be produced in both high ceramic and high chemical yields.

We have previously reported the preparation of the new boron-nitrogen polymer, polyborazylene, (B₃N₃H₄)_x, and shown that this processable polymer can be converted to boron nitride in high ceramic and chemical yields (90-94%). We have also demonstrated a new, potentially general route to metal borides, such as TiB₂ and ZrB₂, involving the reduction of the corresponding metal oxide with a boron-carbon based polymer (decaborane-dinitrile). Taken together these two results suggested that the reactions of a metal with a boron-nitrogen polymer, such as polyborazylene, might lead to incorporation of both polymer boron and nitrogen atoms to produce new composite metal-nitride/metal-boride materials, which may have improved properties over individual metal borides or nitrides.

Such a titanium boride/titanium nitride precursor system was made by dispersing titanium powder into polyborazylene. Final ceramic materials were prepared by pyrolysis of either powders or shaped green bodies under inert atmosphere.

The shaped green bodies were made by isostatic pressing of polymer/titanium dispersions at room temperature at 75,000 psi. The green bodies were then heated under argon separately at 1000°, 1200° and 1450°C resulting in the production of ceramic bodies with ceramic yields of 96.0%, 95.5% and 94.9%, respectively. The

final ceramic bars showed excellent shape retention. The ceramic body prepared at 1000°C had a linear shrinkage of about 6%.

X-ray diffraction studies of the ceramic conversion reaction have shown that the product exhibits variations in composition and crystallinity as the processing temperature and/or time is increased. Thus, as shown in **Figure 1**, there is little reaction between the polymer and the titanium metal when the sample was heated at 800°C for 9.5 h. Elemental analyses of a sample at this point showed that the material still had a significant hydrogen content with the observed $B_{1.03}:N_{1.0}:H_{0.79}$ ratio suggesting that polymer crosslinking was still occurring. When the sample was heated at 1000°C for 2 h, the titanium metal is completely consumed by reaction with the polymer and crystalline titanium nitride is initially observed to form. The formation of crystalline TiB_2 is observed only upon heating of samples for either longer times (1000°, 3 days) or at higher temperatures (1200°, 1 h). TEM analysis of the ceramic body treated at 800°C for 9.5 h shows the presence of 20-100 nm spherical crystals embedded in an amorphous matrix. These crystals could be either unreacted titanium metal or nucleated titanium nitride. For the body treated at 1200°C, TEM shows angular grains on the order of 50-100 nm which have two contrast levels. The TEM of the 1450°C sample showed that the two types of grains are still evident, but that they have increased in size.

The preparations of TiB_2/TiN and $TiB_2/Ti(CN)$ composite materials by sintering TiB_2 and TiN or $TiCN$ powders at high temperatures have previously been reported. TiB_2/TiN composite coatings have also been achieved by CVD methods. The new polymer route discussed above is, however, the only direct chemical method that can be used to produce shaped titanium boride/nitride composites, consisting of intimately mixed polycrystals with grain sizes on the order of nanometers, in high ceramic and chemical yields. The dependence of the crystal size and distribution on the reaction/sinter temperature, the evolution of microstructure and the properties of the final composite material, such as conductivity and hardness, are currently under investigation. We are also exploring the reactions of polyborazylene with other metals and soluble metal complexes with the goal of developing a range of new metal boride/nitride precursor systems that will allow the formation of both shaped bodies and coatings.

New Synthetic Routes to Boron-Nitrogen Clusters:

(1) Synthesis and Structural Characterization of a Hybrid Triazene-Thiaborane Cluster: $\mu_2(4,exo-9)-(1-SiMe_3-3-H-N_3)-arachno-6-SB_9H_{10}$

Azide compounds have proven to be valuable building blocks for the synthesis of boron nitrogen compounds. Early investigations focused on the reaction of azides with compounds containing classically bonded borons, but recently azide reactions have also been employed for the synthesis of polyhedral azaborane clusters. For example, the reaction of HN_3 with $B_{10}H_{12}(SMe_2)_2$ was found to yield *nido*- $NB_{10}H_{13}$ by way of an azido- μ -amino-decaborane intermediate.

These previous results suggested that other classes of polyhedral boranes, and in particular the polyhedral thiaboranes, might also be susceptible to similar insertion reactions to yield previously unknown hybrid μ -amino-thiaboranes or thia-azaboranes. We have found that *nido*-6-SB₉H₁₁ reacts readily with an organic derivative of hydrazoic acid, trimethylsilyl azide, to give the first example of a new class of hybrid fused ring-cluster triazene-thiaborane compounds, $\mu_2(4,exo-9)-(1-SiMe_3-3-H-N_3)$ -*arachno*-6-SB₉H₁₀ (**1**).

In contrast to free triazenes, **1** exhibits both thermal and photolytic stability. The structure of $\mu_2(4,exo-9)-(1-SiMe_3-3-H-N_3)$ -*arachno*-6-SB₉H₁₀, as determined by a single crystal X-ray study, is shown in the ORTEP drawing in **Figure 2**. The triazene bridges the B4 and B9 atoms forming a planar exopolyhedral five-membered ring composed of the three azide nitrogens and the two cage boron atoms. Preliminary studies of the reactions of benzyl azide with *nido*-6-SB₉H₁₁ also indicate the formation of the benzyl analogue of **1**. In addition, the data obtained for minor products produced in both the trimethylsilyl- and benzyl azide reactions are consistent with the formation of new azathiaborane clusters. We are presently exploring the characterization of these products and the expansion of these azide reactions to the generation of new classes of aza-cage/ring complexes.

(2) Reactions of *nido*-6-SB₉H₁₁ with Imines. Structural Characterization of *endo*-9-((*t*-Bu)MeC=NH)-*arachno*-6-SB₉H₁₁.

Upon thermolysis or photolysis, amine-borane adducts, such as H₃B·NH₃, B₃H₇·NH₃ or B₉H₁₃·NH₃, have been shown to generate new boron-nitrogen compounds which may have higher boron-nitrogen bond orders (HB≡NH and B₃N₃H₆), bridging amino groups (μ -NH₂-B₂H₅), or NH-units incorporated into a borane cluster (*nido*-NB₉H₁₃). The latter result in particular has prompted new investigations of the reactions of polyhedral boranes with both saturated and unsaturated nitrogen ligands as possible routes to new hybrid boron-nitrogen clusters.

We have now found that the reaction of *nido*-6-SB₉H₁₁ with *N*-*t*-butylformaldimine results in the formation of the unique zwitterionic compound 9-((*t*-Bu)NH₂⁺-CH₂)-*nido*-6-SB₉H₉⁻ **2**. The formation of **2** is consistent with a reaction sequence involving hydroboration of the imine at the B-9 cage position accompanied by transfer of a proton from a cage-bridging site to the nitrogen atom. When **2** is then reacted with acetonitrile a rearrangement occurs and the adduct *exo*-9-(CH₃CN)-*endo*-9-((*t*-Bu)NHCH₂)-*arachno*-6-SB₉H₁₀ **3** is formed. The reaction of *nido*-6-SB₉H₁₁ with *t*-butylmethylketimine, gives the substituted imine product *endo*-9-((*t*-Bu)MeC=NH)-*arachno*-6-SB₉H₁₁ **4**. A single crystal X-ray study of **4** (**Figure 3**) confirmed that the imine adopts an *endo* position with regard to the *arachno*-6-SB₉H₁₁ framework. Furthermore, the observed imine-hydrogen to cage-sulfur distance (2.712 (28) Å) is less than the sum of the Van der Waals radii of hydrogen and sulfur suggesting that the observed *endo* configuration may be stabilized by N-H---S hydrogen-bonding interactions.

Figure 2.

Figure 3.

Recent Publications (1991-) resulting from this DOE sponsored project:

1. L. G. Sneddon, K. Su, P. J. Fazen, A. T. Lynch, E. E. Remsen and J. S. Beck "Polymeric Precursors to Boron Nitride Ceramics" in *Inorganic and Organometallic Oligomers and Polymers* R. M. Laine and J. F. Harrod eds., Kluwer: Dordrecht (Netherlands) 1991.
2. L. G. Sneddon, M. G. L. Mirabelli, A. T. Lynch, P. J. Fazen, K. Su and J. S. Beck "Polymeric Precursors to Boron Based Ceramics" *Pure and Applied Chemistry* 1991, 63, 407-410.
3. K. Su, E. E. Remsen, H. Thompson and L. G. Sneddon "Syntheses and Properties of Poly(vinylborazine) and Poly(vinylborazine/styrene) Copolymers" *Macromolecules* 1991, 24, 3760-3766.
4. K. Su and L. G. Sneddon "Polymer Precursor Routes to Metal Borides: Syntheses of TiB_2 and ZrB_2 " *Chem. Mater.* 1991, 3, 10-12.
5. K. Su, E. E. Remsen, H. M. Thompson and L. G. Sneddon "Synthesis of Poly(B-Vinylborazine) and Poly(Styrene-co-B-Vinylborazine) Copolymers" *Polymer Preprints*, 1991, 32, 481-482.
6. P. J. Fazen, E. E. Remsen and L. G. Sneddon "Synthesis and Ceramic Conversion Reactions of Polyborazylene" *Polymer Preprints*, 1991, 32, 544-545.
7. S. Kupper, P. J. Carroll and L. G. Sneddon "Synthesis and Structural Characterization of a Hybrid Triazene-Thiaborane Cluster: μ -(exo-9,4)-(1-SiMe₃-3-H-N₃)-*arachno*-6-SB₉H₁₀" *J. Am. Chem. Soc.* 1992, 114, 4914-5.
8. Kupper, S.; Carroll, P. J.; Sneddon, L. G. "Reactions of *nido*-6-SB₉H₁₁ with Imines. Structural Characterization of *endo*-9-((*t*-Bu)MeC=NH)-*arachno*-6-SB₉H₁₁." submitted.
9. K. Su, M. Nowakowski, D. Bonnell and L. G. Sneddon "A Polymer Precursor Route to TiB_2 /TiN Nanocomposites" submitted.
10. K. Su, G. Zank, E. Remsen and L. G. Sneddon "Synthesis, Characterization and Ceramic Conversion Reactions of Borazine-Modified Polysilazanes: New Polymeric Precursors to Silicon-Nitride/Boron-Nitride Composites." in preparation.

END

**DATE
FILMED**

12 / 29 / 92