O

f

Methodology for First Wall Design*

J. D. Galambos, D. L. Conner, P. L. Goranson, D. C. Lousteau,
D. E. Williamson, B. E. Nelson, F. C. Davis
Oak Ridge National Laboratory
P.O. Box 2009, Oak Ridge, Tennessee 37831-8218

ABSTRACT

An analytic parametric scoping tool has been developed for application to first wall (FW) design problems. Both thermal and disruption force effects are considered. For the high heat flux and high disruption load conditions expected in the International Thermonuclear Experimental Reactor (ITER) device, Vanadium alloy and dispersion-strengthened copper offer the best stress margins using a somewhat flattened plasma-facing configuration. Ferritic steels also appear to have an acceptable stress margin, whereas the conventional stainless steel 316 does not appear feasible. If a full semicircle shape FW is required, only the Vanadium and ferritic steel alloy have acceptable solutions.

INTRODUCTION

The FW design process involves consideration of competing effects; namely, disruption-induced forces (that favor thicker wall solutions) and thermal loads (that favor thinner walls). As an aid to finding an acceptable overall FW design, we have developed a systematic trade-off method. This method involves analytic modeling of the primary drivers in FW design and treats the FW components that a designer is free to pick as variables (subject to bounds). Standard optimization methods [1] may then be applied to analyze the design space and find a solution. The method discussed here simultaneously includes the effects of multiple stresses (thermal, fluid pressure, and disruption-induced), allows multiple FW parameters to vary, and includes configurational constraints. By automating the initial design procedure in this fashion, large parameter spaces can be examined to find a starting design point. This method is only meant to serve as an initial guide in the FW design process and is not meant to replace detailed design efforts.

Below we summarize the models used in this analysis. Cases are examined for coolant flowing through a channel, bounded by an arch that faces the plasma (see Fig. 1). Example cases are shown for different FW materials. For high heat fluxes ($> 50 \text{ W/cm}^2$), Vanadium (V15CR5Ti), ferritic steel (HT-9) and dispersion-strengthened copper (Cu15725) have feasible solutions. These solutions tend to result in thick FWs (from 6 mm for HT-9 to over 10 mm for Cu15725). Also, the FW tends more toward a flat plate (instead of a full semicircle arch) to minimize disruption-induced load.

II. MODEL

The model uses analytic methods [2] to calculate stresses in the FW. These stresses arise from three different

Fig. 1 Schematic of the FW geometry used in parametric analysis.

causes: thermal-induced stresses, coolant pressure-induced stresses, and plasma disruption-induced stresses. We use the equations for stress in an arch with fixed end and solve for the maximum stress that occurs at the fixed ends. This model is based on the current engineering design activity (EDA) concept that uses a thick ring to support the blanket and FW. This ring severely limits the radial (hence, circumferential) growth of the FW, which closely approximates the fixed end condition. The equations used in this model are described in detail in [3].

A. Thermal Stresses

We first consider stresses in the (x-y) plane shown in Fig. 1. We assume that the back plate and the inside surface of the FW are at the same temperature. The only temperature gradient is between the plasma-facing side of the FW and the inside (i.e., coolant-facing side) of the FW. We consider stresses from both (a) the bulk temperature rise T_0 of the plasma-facing arch, relative to the temperature of the radial plates (Case 5m, Table 18 of [1]) and (b) stress from a temperature gradient about T_0 (Case 5n, Table 18 of [1]). We denote the stress (in the x-y direction) from the uniform temperature rise as σ_{T1} . This tends to be small compared to the other thermal stresses and is primarily bending. The stress from the temperature gradient is denoted σ_{T2} and is entirely bending. The stress for this case is

$$\sigma_{T2} = (T_2 - T_1) \alpha E / \{ 2 (1 - \nu) \},$$

*Research sponsored by the Office of Fusion Energy, U.S. Department of Energy, under contract DE-AC05-84OR21400 with Martin Marietta Energy Systems, Inc.

where α is the coefficient of expansion, E is Young's modulus, and ν is Poisson's ratio. We have added the $(1 - \nu)$ factor in the denominator to account for the three-dimensional (3-D) effects. There is also a compressive thermal stress in the poloidal direction (σ_{T3}). In the model these properties are scaled with temperature using the formula from [3].

B. Stress from the Fluid Pressure

The stress arising from the fluid pressure is calculated using the equations of Case 5h in Table 18 of [2]; that is from a uniform outward force. Here we consider only the head pressure effects from the fluid and denote the stress arising from this force as σ_{fluid} .

C. Disruption-Induced Stresses

We consider here the stresses resulting from currents appearing in the FW structure during a plasma disruption. There are three components of these stresses. First, a radially outward force from the poloidal component of the halo currents crossed with the toroidal field (which adds to the fluid pressure stresses). We use the same equations from [2] as used in the fluid pressure case above to model this. We denote the stress from this effect as σ_{halo} . The radial force from the toroidal-induced current (crossed with the poloidal field) causes a stress that we denoted σ_{tor} . There is also a shear stress, τ_{yz} , caused by the radial component of disruption currents crossed with the toroidal field. This tends to be the largest of the disruption-induced stresses.

D. Stress Components

For the cases that use the formula from [2] (i.e., σ_{T1} , σ_{T2} , σ_{fluid} , σ_{halo} , and σ_{tor}), we resolve the forces into the stress components in the tensile, lateral, and vertical shear components. The solutions to the formulae from [1] provide the horizontal (H) and vertical (V) loads, and the angular moment (M). For each of these cases we calculate a bending stress:

$$\sigma_{\text{bend}} = M [\text{N-m}] / (t_{\text{fw}}^2 [\text{m}]); \quad (1)$$

a tensile stress (x direction) :

$$\sigma_{\text{tensile}} = (-H [\text{N}] \cos(\theta) + V [\text{N}] \sin(\theta)) / A [\text{m}^2]; \quad (2)$$

and a shear stress :

$$\tau_{zy} = (H [\text{N}] \sin(\theta) + V [\text{N}] \cos(\theta)) / A [\text{m}^2]; \quad (3)$$

where A is the FW cross-sectional area = $t_{\text{fw}} \times 1 \text{ m}$ (i.e., unit length) and θ = the FW arch half angle (see Fig. 1).

E. Stress Combinations and Limits

Three combinations of these stress components are constrained in this analysis. For each of these combinations we find the principal stresses (in three dimensions) s_1 , s_2 , and

s_3 and then take the maximum of $|s_1 - s_2|$, $|s_1 - s_3|$, $|s_2 - s_3|$.

The combination of only the primary membrane stresses (σ_P), including only the tensile and shear components arising from the disruption forces and the fluid pressure is constrained by

$$\sigma_P \leq S_m, \quad (4)$$

where S_m is presently calculated as two-thirds of the yield strength.

We also restrict the combination of primary and bending stresses from the fluid and disruption forces (including tensile, shear, and bending),

$$\sigma_{P+B} \leq 3/2 S_m. \quad (5)$$

Finally we restrict the combination of Primary plus Bending plus Secondary stresses (σ_{P+B+S}) to be

$$\sigma_{P+B+S} < 3 S_m. \quad (6)$$

This later combination includes thermal, fluid pressure, and disruption effects.

F. Configurational Limits

The number of FW segments in a toroidal sector is

$$N_{\text{seg}} = 2 \pi [R_{\text{fw}} - r_{\text{fw}} (1 - \cos(\theta))] / [24 \times 2 r_{\text{fw}} \sin(\theta) + t_{\text{fw}}], \quad (7)$$

where R_{fw} is the radius of the FW [= 4.8 m for the inboard side for all cases, r_{fw} is the radius of FW curvature (see Fig. 1) and 24 toroidal sectors have been assumed here]. The number of FW segments per sector impacts the calculated stress and can be varied parametrically.

G. Finite Element Model Comparison

The simple arch model equations employed previously assume fixed ends. In practice these ends are attached to long (~ 40-cm) radial arms connected to a rigid hardback, which may move. To test this fixed-end assumption, we compared the results from the arch equations to a finite element model analysis for a typical geometry expected in the ITER-EDA. This comparison shows the fixed end assumption to be good (see [3]).

H. Solution Method

We find solutions to the above stress constraints using existing mathematical techniques. In particular we use the equation-solving optimization packages in the SuperCode systems code [1]. The default problem is to find the minimum yield stress for which the stress combination equations (4, 5, 6) and the configuration constraint (equation 7) are satisfied. In this solution process we allow the FW thickness, radius of curvature, and the angle θ to vary. It is also possible to scan these quantities parametrically.

III RESULTS

The methodology just described is applied to the FW design for several representative calculations. First we examine the stress margin¹ for four structure materials: stainless steel (SS 316), HT-9, Vanadium (V15Cr5Ti), and Glidcop dispersion-strengthened copper (Cu15725). We consider a case with a 50-W/cm^2 heat load (corresponding to a 2-MW/m^2 wall load), a 12.5-MA/s disruption rate, and using six wall segments per sector. These conditions correspond to the worst expected conditions in the ITER EDA. Figure 2(a) shows the Margin of Safety (MOS = required yield strength/actual allowable yield strength - 1) vs the FW thickness. When the MOS > 0, the design is potentially feasible. (Note that for these conditions, with SS 316, there is no feasible case.) The Cu15725 case has a large MOS at wall thicknesses > 10 mm, but this may not be allowed due to the large toroidal electrical conductivity of this configuration, and resultant problems in providing poloidal flux to the plasma.

Fig. 2(a) Margin of Safety (i.e., the allowable yield strength/required stress - 1) vs the wall thickness for SS316, HT9, V15Cr5Ti, and Cu15725 FW materials (at 50-W/cm^2 heat load and 12.5-MA/s disruption rate).

The cases shown in Fig. 2 allow the FW angle (θ) to vary. This optimum half-angle tends to be near 40° for low thicknesses where the disruption stresses dominate and increases to its maximum possible value of 90° for large thicknesses, where the thermal stresses dominate. A primary reason this angle tends to decrease when disruption loads are significant is an effort to reduce the radial component of the current flowing in the FW. When this current is crossed with the toroidal field, a large shear stress is introduced where the FW joins the radial plates. If this angle is held fixed at 90° , the MOS tends to drop, and the V alloy is the only candidate with a MOS > 0.

Fig. 2(b) Thermal stress in poloidal direction corresponding to the cases in Fig 2(a).

Fig. 2(c) The disruption stress from $I_{\text{toroidal}} \times B_{\text{pol}}$ for the cases in Fig. 2(a).

Some typical stress component variations are shown in Figs. 2(a) and (c). As the wall thickness increases, the stresses from the disruption currents and from the fluid head pressure decrease [Fig. 2(b)]. The usual increase of the thermal stresses with increasing wall thickness is seen in Fig. 2(c). Near the optimum thickness (i.e., where the MOS is maximized), both the Primary membrane stress constraint and the (Primary + Bending + Secondary) stress constraint tend to be met. The combination of Primary plus Bending stresses is always below its limit. We note that as the FW thickness increases, the temperature gradient across it increases, and the allowable stress (at the peak temperature) tends to decrease.

A different parametric scan is shown in Fig. 3. Here we show the maximum permissible heat flux vs the wall thickness for the different candidate materials. These cases assume a 12.5-MA/ms disruption rate. At the maximum heat flux, the required yield strength is equal to the allowable yield stress. The Cu15725 has the highest permissible heat flux, but only at large thicknesses (which may not be feasible, as discussed). This large heat flux capability is due to the large thermal conductivity of Cu15725, relative to the other materials (the large conductivity means lower thermal stresses arise for a given heat flux). If we fix the FW angle θ at 90° , only the V and HT-9 materials have any solutions.

¹ Margin of safety is defined to be (allowable stress / required stress) - 1

Fig. 3 Maximum allowable surface heat load for various materials, with 12.5-MA/ms disruption rate.

IV SUMMARY

An analytic parametric scoping tool is developed for application to FW design problems. Both thermal and disruption force effects are considered. Also, a flexible numerical optimization package is included, which enhances the flexibility of the problem formulation.

For the high heat flux and high disruption load conditions expected in the ITER device, Vanadium alloy and dispersion-strengthened copper offer the best stress margins. Ferritic steels also appear to have an acceptable stress margin, whereas the conventional SS 316 does not appear feasible. These conclusions are based on the assumption that a flatter FW arrangement (than presently envisioned for the ITER-EDA) is acceptable. If a full semicircle shape FW is required, only the Vanadium and ferritic steel alloy have acceptable solutions.

ACKNOWLEDGMENTS

The authors take pleasure in thanking T. E. Shannon and S. Majumbar for useful discussions on stress modeling, C. Brimer for a careful review of the manuscript and methods, and A. Rowcliffe and J. Davis for providing material data.

REFERENCES

- [1] R. J. Roark and W. C. Young, "Formulas for Stress and Strain," McGraw-Hill Book Co., NY, NY, 1982.
- [2] S. W. Haney et al., "SuperCode for systems analysis of yokamak experiments and reactors," *Fusion Technology*, vol. 21, p. 1749, 1992.
- [3] *ITER Materials Design Databook*, prepared for the U.S. Department of Energy, under subcontract No. 87X43181, January 23, 1989.
- [4] D. E. Williamson, private communication.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

**DATE
FILMED**

12 / 29 / 93

END