Coal Liquefaction Process Streams Characterization and Evaluation

Characterization of Coal Liquefaction Resids Employing Thermogravimetric Analysis and Electron Spin Resonance Spectroscopy

Topical Report

Prepared by:

Department of Physics
West Virginia University
Morgantown, WV 26506

M. M. Ibrahim, M. S. Seehra

Prepared for:

CONSOL Inc.
Research & Development
4000 Brownsville Road
Liberty, PA 15129

F. P. Burke
R. A. Winschel
S. D. Brandes

October 1992

Under Contract to:

United States Department of Energy
Contract No. DE-AC22-89PC89883

U.S. DOE Patent Clearance was provided by
Chicago Operations Office on October 22, 1992.

PROJECT ASSESSMENT

Introduction

Under subcontract from CONSOL Inc. (DOE Contract No. DE-AC22-89PC89883), West Virginia University studied the use of temperature-programmed electron spin resonance (ESR) and thermogravimetric analysis (TGA) to analyze coal derived materials. The full report authored by the West Virginia University researchers is presented here. The following assessment briefly highlights the major findings of the project, and evaluates the potential of the method for application to coal derived materials. These results will be incorporated by CONSOL into a general overview of the application of novel analytical techniques to coal derived materials at the conclusion of this contract.

Summary

This study demonstrated the feasibility of using temperature-programmed ESR and TGA for the examination of tetrahydrofuran (THF)-soluble distillation resid materials derived from direct coal liquefaction. TGA is used to quantitate volatile losses in a temperature-programmed experiment. The TGA data are used to correct the free radical densities obtained by ESR as volatile material is evolved from the samples in the temperature-programmed ESR experiment. The techniques, when employed in tandem, can be used to determine the content and nature of the free radicals in the samples at temperatures approximating those used in the liquefaction process.

TGA and ESR experiments were performed in flowing nitrogen and hydrogen, at ambient pressure. No significant difference was observed in the ESR spectra in the different atmospheres, except in the case of low-rank coal-derived resids. The TGA results, however, were systematically different; mass loss in an H_2 atmosphere is consistently higher than that observed in an N_2 atmosphere. It was shown that temperature-programmed ESR, which can pinpoint conditions at which the free radical content is the highest, has potential to be a guide for the appropriate choice of conditions for optimum resid upgrading. Further development of these combined analytical methods as process development tools appears justified based on these results.

Program Description

This report describes the work performed at West Virginia University under a subcontract from CONSOL Inc., Research and Development. CONSOL's prime contract to the U.S. Department of Energy (Contract No. DE-AC22-89PC89883, "Coal Liquefaction Process Streams Characterization and Evaluation") established a program for the analysis of direct coal liquefaction derived materials. The program involves a number of participating organizations whose analytical expertise is being applied to these materials. This Participants Program has two main objectives. The broad objective is to improve our understanding of fundamental coal liquefaction chemistry to facilitate process improvement and new process development. The specific approach to achieving this objective is to provide a bridge between direct coal liquefaction process development and analytical chemistry by demonstrating the application of various advanced analytical methods to coal liquefaction materials. The methodologies (or techniques) of interest are those which are novel in their application for the support of coal liquefaction and those which have not been fully demonstrated in this application. CONSOL is providing well-documented samples from different direct coal liquefaction process development facilities to the program participants. The participants are required to interpret their analytical data in context to the processing conditions under which the samples were generated. The methodology employed is then evaluated for its usefulness in analyzing direct coal liquefaction derived materials.

Participant's Methodology

West Virginia used ESR and TGA as associated techniques to analyze the THF-soluble portion of 850°F distillation resid. The ten samples were produced at the Wilsonville pilot plant. Two major processing parameters were varied among the Wilsonville runs: feed coal and reactor configuration (thermal/catalytic vs catalytic/catalytic). Samples from Wilsonville were taken from three locations: between the reactors, after the second-stage reactor, and at the recycle oil tank. These samples are expected to represent different extents of coal liquefaction. Six of the ten Wilsonville samples were composites of samples taken over long periods of single runs. Four samples were obtained from single run periods and were chosen to represent thermal/catalytic vs

catalytic/thermal processing. The TGA and ESR experimental procedures are described on pages 2-3 of the attached report. Calculation of ESR parameters and an estimation of experimental error is offered on page 5 of the attached report.

Participant's Major Findings

The following principal observations for the application of TGA and ESR to coal liquefaction materials were reported by West Virginia University. An expanded discussion can be found in the attached report, pages 3-9.

Most of the observed weight loss in the TGA experiments for all samples occurred between 300 and 500°C and was greater in a flowing H₂ atmosphere than in N₂. This, it was speculated, may be the result of the suppression of retrograde reactions in the presence of H₂. The amount of material remaining (char) correlates with the aromaticity of the samples. A similar observation was noted previously by another program participant for a number of the THF-soluble samples, including six of the identical samples that were in the WVU sample set.¹ For all samples, weight loss began at a lower temperature in H₂ than in N₂.

An inverse relationship between the ESR free radical densities (N) and the H/C ratios of the samples was found. This was interpreted as indicating that the lower the free radical content is, the more hydrogenated the resid; thus, resids with low N values are more upgraded than resids with higher N values. Increases of an order of magnitude in N were observed for all resid samples at low temperatures (100 to 200°C), although there was no accompanying mass loss. This behavior, which is not found in coal samples, is apparently due to cleavage of weak bonds not accompanied by the evolution of volatile materials. At temperatures above 300°C, there is a fifty-fold increase in N corresponding to the evolution of volatile species that is associated with the rupture of bonds in the sample (thermal cracking).

N values for resids are smaller than those of the parent (bituminous) coals by more than an order of magnitude. The samples in the set derived from Illinois No. 6 coal produced the greatest yield of volatile materials. They also have the highest H/C ratio of the samples studied

and a slightly higher free radical density when measured in H_2 than in N_2 . In contrast, the samples derived from a subbituminous coal (Wyodak and Anderson seam) which have the lowest H/C values among the samples studied and yield lower N values in H_2 than in N_2 , are believed to be hydrogenated under the conditions of the ESR experiment.

Measured linewidths (ΔH) for all samples show a variation with temperature, but they are unaffected by atmosphere (H_2 or N_2). Linewidths for the resid samples increase from about 8 Gauss at room temperature to about 12 Gauss at about 200°C, corresponding to the ten-fold increase in free radical density (N), and then decrease to about 2 Gauss by 500°C. The decrease is associated with the fluid state of the samples at the elevated temperatures. The g-values of the samples fell within the range of 2.0015 and 2.0025 (± 0.0005). There was no influence of atmosphere on g-value. There was a slight decrease in the value with increasing temperature. This behavior is similar to that observed for neutral oxygen-containing species.

CONSOL Evaluation

The TGA and temperature-programmed ESR techniques were shown in this study to have potential for the analysis of direct coal liquefaction resid samples and for providing direction for process development. The free radical density (N) may prove to be a good indicator of resid reactivity. The lower the N value, the more hydrogenated and perhaps, therefore, more reactive the resid. This inference concerning reactivity is supported by the TGA data, which showed that samples with lower N values were more volatile.

The N values of the resids were observed to increase ten-fold at low temperature (100 to 200°C) with no corresponding volatilization. This behavior, which is not observed in the ESR of the parent coals, indicates that resid chemistry occurs at quite low temperatures. Thus, it may be possible to hydrogenate resids in this low temperature range if an appropriate catalyst can be found.

Definite identification of the free radicals could not be obtained, although their ESR behavior is most similar to the neutral oxygen-containing species.

Because there was almost no difference in the ESR spectra under H_2 and N_2 at ambient pressure, indicating that there was little or no interaction of the H_2 with the resid, it was not possible to determine a hydrogen donor ability (HDA) index for these samples. However, it may be possible to obtain an HDA index at elevated pressure.

The Mettler TA3000 TGA apparatus used in this work costs approximately \$40,000. The 9.4 GHz Varian ESR with the hot probe accessory costs about \$250,000. ESR experiments, including raw data conversion, require approximately two days per sample. TGA experiments require approximately four hours per sample. Data interpretation is not trivial and requires a professional trained in ESR methods. Expendable supplies (ESR tubes, TGA sample holders, and purge gases) for the analysis of the ten samples described in the appended report cost approximately \$1000.

Further Development

There are a number of avenues for further development of the ESR and TGA techniques for coal liquefaction derived resids. Suggested by the West Virginia University researchers is an expanded use of the TGA as a combined tool with proton nuclear magnetic resonance spectroscopy or Fourier transform infrared spectroscopy for analysis of the evolved volatile materials from the resids. Some utility of this latter combined technique has been previously demonstrated in this program.¹ It also was suggested, that in the temperature range in which the ESR indicates that there is an increase in free radical content with minimal weight loss, studies should be made of the usefulness of different hydrogenation catalysts. Also, expanding the experimental program to include high-pressure ESR experiments with and without catalysts would provide more insight into the behavior of the resids under direct coal liquefaction processing conditions. Another suggestion for further development of the technique includes establishment of a better correlation between feed coal and resid properties by use of the ESR technique.

Participant's Statement of Work

Electron spin resonance (ESR) spectroscopy has been used for the investigation of coal. It has not, however, been fully demonstrated for the characterization of coal liquefaction resids nor for its ability to support coal liquefaction process development. As such, it fits well within the scope of the participants program.

The application of ESR to a sample set of 10 samples will allow a demonstration of the value of this technique for the characterization of coal liquefaction-derived resids. These samples have been selected (see attached list) so that the utility of ESR for addressing the issue of resid reactivity can be evaluated. Each sample will be subjected to a temperature-programmed ESR experiment in both a flowing hydrogen atmosphere and a flowing nitrogen atmosphere. Each ESR experiment will be accompanied by a corresponding thermogravimetric analysis (TGA). The conditions of the TGA experiment will mimic those of the corresponding ESR experiment. Both the ESR and TGA experiments will be run at atmospheric pressure. The maximum temperature used in the temperature programs of the ESR and TGA experiments will be at least as high as the highest processing temperature achieved when the samples were produced. ESR spectra will be collected at intervals during the temperature program. The data collected by the ESR experiment will include intensity, g-value, and line shape and their evolution with temperature. Based on the maxima of free radical density, as a function of temperature, the hydrogen donor ability (HA) of each sample will be evaluated. The samples will be supplied to WVU with the following information, as available: elemental analyses, ash content, ash elemental analysis, phenolic -OH concentration, calorific value, hydrogen classes by ¹H-NMR, and the full history of the sample (plant, process conditions including maximum processing temperature, age, and storage conditions). The samples are the tetrahydrofuran-soluble portion of non-distillable residual materials. Sample size will be at least 1g. The ten soluble resid samples will be solid materials that will be supplied as approximately minus 60 mesh powders.

References

1. Serio, M. A.; Hsisheng, T.; Bassilakis, R.; Solomon, P. R. "Coal Liquefaction Process Streams Characterization and Evaluation; FT-IR Methods for Characterization of Coal Liquefaction Products, Topical Report", DOE/PC 89883-45, April 1992.

Characterization of Coal Liquefaction Resids employing
Thermogravimetric Analysis and Electron Spin Resonance
Spectroscopy

Technical Report

June 1992

M. M. Ibrahim and M. S. Sechra
Physics Department, West Virginia University
Morgantown, WV 26506

Prepared (under subcontract) for

CONSOL Inc.

Under U.S. Department of Energy Contract No. DE-AC-22-89PC89883

TABLE OF CONTENTS

	Page
EXECUTIVE SUMMARY	1
1. INTRODUCTION	2
2. EXPERIMENTAL SECTION	2
3. RESULTS AND DISCUSSION	3
3.1. TGA Results	4
3.2. ESR and Free Radical Densities	4
3.2.1. Calculation of ESR parameters and estimation of errors	5
3.2.2. General features	5
3.2.3. Sample to sample comparison	6
3.3. Free Radical Linewidths and g-Values	8
4. SUMMARY AND CONCLUSIONS	9
5. RECOMMENDATIONS	10
6. REFERENCES	10

LIST OF TABLES

Table

1	Parameters of the samples supplied by CONSOL	11
2	Percentage mass loss in H ₂ near 490°C for the CONSOL samples	12
3	Comparison of free radical density N at room temperature for the resids and a Blind Canyon coal, and atomic H/C values ...	13

LIST OF FIGURES

Figure

1	Plots of remaining W(%) and reaction rate (dm/dt)/m against temperature for sample C1 in N ₂ and H ₂ flow	14
2-10	Same as Fig. 1 except for samples C2-C10 respectively	15-23
11	Representative ESR spectra at several temperatures	24
12	Variation of N vs T for C10 and Blind Canyon Coal	25
13	Plots of N vs T for C1, in N ₂ and H ₂ flow, with and without mass correction	26
14-22	Same as Fig. 13 except for samples C2-C10 respectively	27-35
23	Comparison of N at RT, 200°C and 480°C and atomic C/H ratio for samples C1 through C10	36
24	Temperature dependence of the g-values and linewidth ΔH of the free radicals for C1, in N ₂ and H ₂ flow	37

25-33 Same as Fig. 24, except for samples C2-C10 respectively 38-46

LIST OF APPENDICES

1. Numerical data from TGA in N ₂ flow. The remaining weight (% of initial weight) is presented for resids C1-C10	47
2. Same as 1 except in H ₂ flow	52
3. Rate of weight loss in N ₂ flow from TGA	57
4. Same as 3 except in H ₂ flow	62
5. ESR parameters for sample C1-C10 in N ₂ flow and H ₂ flow respectively	67

EXECUTIVE SUMMARY

In this report, results on the characterization of ten resid samples using thermogravimetric analysis (TGA) and electron spin resonance (ESR) spectroscopy are presented. The resid samples are THF soluble fractions of solid coal liquefaction material (850° F+ resids) obtained from the liquefaction of three coals. TGA measurements of weight loss and reaction rate were carried out from room temperature (RT) to 600°C in flowing N₂ and H₂ gases. In ESR spectroscopy, where only a single line is observed, the free radical density N as well as the g -value and linewidths ΔH are reported from RT to 500°C, again in flowing N₂ and H₂ gases.

TGA measurements show that most of the weight loss occurs between 300 and 500°C, more weight is lost in H₂ than in N₂ and that weight loss begins to occur at lower temperatures in H₂ than in N₂. A strong correlation is observed between the remaining weight in H₂ at 500°C and the aromaticity of the resids.

The ESR results show that the RT free radical density N for resids is smaller by over an order of magnitude than N for bituminous coals. This is due to hydrogenation in liquefaction which lowers N by capping the free radicals. The variation of the RT N among resids bears an approximate proportionality to the atomic C/H ratio of resids. On heating the samples in N₂ and H₂, nearly an order of magnitude increase in N is observed between 100 and 200°C in all samples without significant weight loss, suggesting that this increase in N is due to thermolysis of the weaker bonds in resids. From 300° to 500°C, another increase in N by a factor of about 50 is observed. Since this region coincides with the massive evolution of volatiles in TGA, this increase in N is due to severe thermal cracking. The changes in g -values with temperature are not significant whereas the linewidth ΔH first increases reaching peak values of about 12 Gauss near 200°C and then decreases monotonically with increasing temperatures, reaching values of about 2 Gauss near 500°C. A tentative interpretation for this behavior is advanced.

Based on the above results, two suggestions for applications to coal liquefaction processes are immediately apparent: (i) Weight loss in H₂ flow in TGA experiments, when combined with ¹H NMR and possibly FTIR is likely to provide an excellent tool for characterizing resids; (ii) considerable thermal bond cleavage observed in ESR experiments in the 100 to 200°C range without

weight loss suggests that a suitable catalyst may promote hydrogenation of the resids at these temperatures.

1. INTRODUCTION

This is the final Technical Report for the project entitled "ESR/TGA Characterization of Liquefaction-Derived Resids" supported by a subcontract from CONSOL Inc. under DOE Contract DE-AC22-89PC89883. The objectives of this project were to employ the techniques of thermogravimetric analysis (TGA) and electron spin resonance (ESR) spectroscopy to characterize ten samples of resids obtained from the Wilsonville Liquefaction Plant. The samples, supplied by CONSOL Inc., consist of tetrahydrofuran (THF) soluble fractions of solid coal liquefaction materials (850° F+ resids) produced under variable conditions such as feed coal, reactor configuration and feed coal conversion (see Table 1).

In the TGA studies, samples were heated from room temperature (RT) to 600°C in flowing N₂ and H₂ and the data presented here include the remaining weight W(%) versus temperature and the rate of mass loss (dm/dt)/m versus temperature, where m is the mass at temperature T. In ESR experiments, we measured the free radical concentration N, their g-value and the linewidth ΔH as a function of temperature from RT to 500°C in flowing N₂ and H₂ gases. The data are presented for these parameters as a function of temperature, with and without the mass correction applied from the TGA experiments. Finally, we have provided an interpretation of these results taking into account other data available on these samples and included some suggestions for further studies and analysis.

2. EXPERIMENTAL SECTION

The TGA characterization of the samples was carried out with a Mettler TA3000 system in flowing N₂ and H₂ gases at a flow rate of 100 cm³/m. The experiments were carried out from RT to 600°C and the data obtained include the % weight loss relative to the original weight and the rate of mass loss (dm/dt)/m where m is the mass at a given temperature. In a typical experiment, 10 mg of the sample was heated at a rate of 10°C/minute.

The in-situ ESR spectroscopic studies were carried at x-band (≈ 9 GHz) frequencies employing a standard reflection type ESR spectrometer but a specially designed high temperature microwave cavity system allows measurements in vacuum, in flowing gases, and under pressures up to 800 psi. In a recent paper [1], we have described the details of this cavity system, although in this subcontract, experiments under flowing N_2 and H_2 gases only were carried out. The quantities reported here are the free radical density or spin concentration N/g , the g -values and linewidth ΔH (in Gauss) as a function of temperature from RT to $500^\circ C$. The data were taken in steps of $10^\circ C$ to $25^\circ C$ and the temperatures were stabilized at each temperature for about 10 minutes before data were taken. This is essential since it takes several minutes to scan the spectra. The microwave frequencies were accurately measured with a Hewlett Packard frequency counter and the resonance fields were accurately measured with an NMR (proton) probe. The free radical densities N were calculated using an on-line computer employing double-integration of the standard derivative ESR spectra and comparing with a standard [2,3]. Furthermore, the N values plotted are scaled by the factor $T(K)/RT(K)$ to take into account the Curie-variation of the intensity of the signal ($K =$ temperature in Kelvin). With this procedure, if no new free radicals are generated and if there is no quenching of the free radicals, then the plot of N vs T should be temperature-independent (horizontal line). The data are also compared with the recent measurements on a coal sample (Blind Canyon Coal).

3. RESULTS AND DISCUSSION

In Table 1, we have listed all the samples and some of their characteristic properties provided by CONSOL Inc. Samples C1, C2, C3 are derived from Illinois #6 coal (Burning Star No. 2), samples C4, C5 and C6 are from the Pittsburgh seam (Ireland Mine) and samples C7, C8, C9 and C10 are from Wyodak and Anderson Seam (Black Thunder). The C and H weight % listed in Table 1 are those of the resids and not of feed coals. The proton-type percentages H1 through H7 are determined by NMR and these data were also provided by CONSOL Inc. The information in Table 1 will be used in the interpretation of the data.

3.1 TGA Results:

In Figs. 1 through 10, we have plotted the results of the TGA studies for the ten samples of Table 1. In each Figure, the top graph represents remaining weight W as a percentage of the original weight at RT as the sample is heated from RT to 600°C in N_2 and H_2 (in two separate experiments). The bottom Figure is the rate $(dm/dt)/m$ plotted against temperature in which the peak value represents the temperature where the rate of mass loss becomes maximum. (The errors in $W\%$ and rate are within $\pm 1\%$.) This temperature is in the range 460-500°C. The numerical data for these plots are given in Appendices 1-4.

An examination of the data shows that in all cases the mass loss by 500°C is higher in H_2 flow than in N_2 flow. In addition, in N_2 flow, we see two or more steps in the case of samples C2, C4, and C7. Above about 500°C, the weight loss W in most cases becomes quite small and in many cases, the plot of remaining W vs T is nearly flat above about 500°C. So we may use the mass loss near 500°C as a measure of the property of the sample. In Table 2, we list % mass loss Δm near 500°C for the ten samples of Table 1, both in N_2 and H_2 flow. Also shown in Table 2, is the quantity 100-H1-H2 which represents the aliphatic component of the samples. There appears to be a good correlation between Δm in H_2 and 100-H1-H2.

In the TGA experiments, there is no noticeable weight loss below about 250°C and most of the weight loss occurs between about 300°C and 500°C. In all cases, we note that the weight loss begins to occur at a lower temperature in H_2 flow than in N_2 flow. These experiments show that the presence of H_2 facilitates the evolution of materials probably because H_2 is reducing retrograde reactions and promoting thermal cracking.

3.2 ESR and Free Radical Densities:

In Fig. 11, we show the typical ESR spectra of a sample at several temperatures. The spectra are taken by scanning the magnetic field H and obtaining first derivative of absorption dA/dH . The field sweep is normally -25 to +25 Gauss about the resonant field. The positions of resonant fields, H_0 and peak to peak linewidths, ΔH are also shown in Fig. 11. For all the resids, only one single line with ΔH of about 8 Gauss at room temperature was observed.

3.2.1 Calculation of ESR parameters and estimation of errors:

The free radical density N is determined from the area under the curve obtained by double integration of the spectra and comparing it with a standard [2,3]. The g -value is determined from the resonance field H_0 using the equation $g = 0.71448 f/H_0$ where f is the microwave frequency in GHz and H_0 is the resonance field in kiloGauss. The error in ΔH is primarily due to fixing the position of peaks, especially for broad peaks. The error in N at each temperature is calculated by including errors in the estimation of baseline, area under the absorption vs field curve and errors in the mass of the sample. In Figs. 13-22 for N vs T of all the resids and in Figs. 24-33 for ΔH vs T , the error bars shown at several representative temperatures indicate the uncertainties of these measurements.

The free radical density N is per unit gram. Since the mass of a sample changes with temperature, it is important to calculate $N/m(T)$, where $m(T)$ is the mass at each temperature T . We multiplied our measured mass at room temperature taken for ESR experiments with the percentage mass remaining at each temperature determined in the TGA experiments (Appendices 1 and 2) to determine $m(T)$. The absolute precision in g -values is estimated to be ± 0.0005 and that in N values to be within $\pm 10\%$. However, as the data presented here indicate, the relative precisions in N , g , and ΔH , from temperature to temperature in a given run, are better by a factor of two or so. As noted earlier, all the data on N are scaled by the factor $T(K)/298$ to correct for the Curie-law variation.

3.2.2 General features:

In order to consider the results presented here in proper perspective, we show in Fig. 12 a comparison of N vs T for a bituminous coal sample (Blind Canyon Coal) and a resid sample (C10). In previous studies [2,3], we have shown that the behavior of N vs T for many American bituminous coals is somewhat similar. The purpose of showing this comparison is to see how the free radical behavior in resids differ from that in a bituminous coal.

It is quite apparent that at RT, the free radical density N in resids is smaller (by 17 to 60 times) compared to N in the coal. In Table 3, we list the N values at RT for the coal and the resids, along with their atomic H/C ratio. We note that for C1, C2, C3 obtained from the Illinois #6 coal, the atomic H/C ratio is the highest (1.10) and N values are the lowest whereas for the other coals,

the atomic H/C ratios are less than one but N values are several fold higher. This inverse relationship between N and atomic H/C was noted in another process also viz. solvent extraction of coals [4] and reflects the ability of the hydrogen to quench the free radicals. Since coal liquefaction involves hydrogenation of coals, the lower the N values, better the product. These results suggest that samples C1, C2 and C3 represent better products. These conclusions are further confirmed by the TGA results presented earlier (see Table 2) which show considerably larger weight loss for C1, C2 and C3 than that for the remaining samples.

The behavior of N vs T in Fig. 12 for the resid samples is very different from that of the coal sample in that a substantial (several fold) increase in N occurs between 100 and 150°C for the resid sample whereas for coal, changes in N in this range are comparatively insignificant. The variation of N vs T for the coal sample shown here, is typical of American bituminous coal as shown in recent studies [2,3]. This behavior is observed in all the resid samples and consequently it constitutes a new finding. From 150° to about 350°C, changes in N for resid are quite insignificant whereas from 350° to 500°C, N increases by an order of magnitude. In the TGA experiments, there is no noticeable change in weight in the 100 to 150°C region so that changes in N observed in this temperature range probably reflect cleavage of weaker bonds resulting in an increase in free radicals but without evolution of any volatiles.

In Figs. 13 through 22, the data of N vs. T for the ten resid samples are presented, with and without the mass correction from the TGA experiments, and in N₂ and H₂ flow. In all cases there is a substantial increase in N between 100 and 150°C and then again between 350 and 500°C. In the intermediate region of 150°C and 350°C, the behavior of N vs T varies somewhat from sample to sample which is discussed in the next subsection. As regards to the differences between the data in N₂ and H₂ flow, there is no systematic trend in that in some cases N is lower in H₂ flow and in other cases N is higher in H₂ flow suggesting hydrogenolysis rather than hydrogenation. This is in contrast to the TGA experiments, where in all cases mass loss in H₂ flow is higher than that in N₂ flow.

3.2.3 Sample to sample comparison:

Resids C1, C2 and C3 are obtained from Illinois #6. These samples have the lowest C/H values (see Table 2). The TGA results of C2 in N₂ flow show an

additional stage in weight loss occurring beyond 500°C. By 600°C, the total weight loss in H₂ flow is more than in N₂ flow for these samples (Figs. 1 to 3). Also these samples have the largest total weight loss of all the resids. From Fig. 23 we also see that the free radical densities N are slightly higher in H₂ than in N₂ both at 200°C and at 480°C. These results from TGA and ESR directly correlate with the higher H content of these resids which on the one hand suppresses retrograde reactions and aid evolution of volatiles (TG) and on the other hand may inhibit further abstraction of hydrogen from other sources and reduces the possibility of quenching the free radicals (ESR).

Samples C4, C5, C6 are from a Pittsburgh coal with C/H values between 1.1 and 1.15. However in the ESR measurements, behavior of C4 stands out among these samples in that it has the largest N value at RT and between RT and 300°C, N values in H₂ are considerably lower than those in N₂ flow. Above about 300°C, the difference between the N values in N₂ and H₂ flow however are quite insignificant.

Samples C7, C8, C9 and C10 are from a Wyodak coal. However based on the atomic C/H values, C7 and C8 go together in that they have the highest C/H values of the then resids. Similarly C9 and C10 may be grouped together based on the C/H values. This grouping is fully justified by the TGA results as well as by the aromatic fractions of these samples (see Table 2). In the ESR experiments, only C7 and C8 give clear evidence of hydrogenation in that only for these samples, the N values are lower in H₂ than in N₂ as the samples are heated. The TGA results for C7 and C8 also show the largest difference in weight loss between N₂ and H₂ flow experiments. From these observations, we infer that the ability of a resid to absorb additional H₂ is related to its C/H value.

In a recent paper, Yokono et al [5] have studied the petroleum resids by high temperature ESR and ¹H NMR. These studies have shown that samples which have the highest hydrogen donor ability (as determined by ¹H NMR) have the lowest concentration of thermally generated free radicals at high temperatures (400-600°C), the explanation being that internally transferred hydrogen can more efficiently cap the thermally induced free radicals. In Fig. 23, we show a comparative plot of N for the ten samples at RT, 200°C and 480°C along with the atomic C/H ratio. The RT N values have a weak correlation (correlation coefficient = 0.53) with the atomic C/H ratio of the resid samples in that for samples with lower C/H ratio, the N values are lower.

At 200°C, the N values are not significantly affected by H₂ except for sample C4 which has the highest N values at RT and the effect of H₂ is to significantly lower the N values. For some of the samples, at 480°C, N values are higher in H₂ than in N₂, and the reverse is true for other samples. Consequently, at this stage of analysis, no significant correlation between the N values at higher temperatures and properties of the resids is yet evident.

In the Blind Canyon coal sample (Fig. 12), the effect of hydrogenation is evident only above 400°C in that above this temperature, presence of hydrogen lowers the N value as expected due to hydrogenation. For the resid samples, only two samples (samples C7 and C8) show clear evidence of hydrogenation at both 200°C and 400°C (Fig. 23) as noted earlier. These two samples also have the highest C/H atomic ratio (Fig. 23) (or the lowest H/C ratio).

3.3. Free Radical Linewidths and g-Values

The measured linewidths ΔH and the g-values at different temperatures, both in N₂ and H₂ flow, are plotted in Figs. 24 through Fig. 33 for the ten samples of Table 1. In some cases, the data near room temperature are missing because the signal intensity was too weak for accurate measurements of these quantities.

In most cases, the g-values are in the range of 2.0015 to 2.0025 (experimental uncertainty ± 0.0005) and with increasing temperature, the g-values decrease somewhat in most cases. These negative g-shifts (from the free electron value of $g = 2.0023$) of these free radicals are similar to those of neutral oxygen containing species [6]. For aliphatic hydrocarbons, the σ radicals have g-values near $g = 2.0025$ [6]. Since ESR cannot further resolve these free radicals, definite identification of the free radicals is difficult to obtain from these data. Any differences between the N₂ and H₂ flow results are within the experimental uncertainties.

In contrast to the g-values, the temperature dependent behavior of the linewidth ΔH has some very distinct features. In almost all cases, the linewidth increases with increasing temperatures, reaching a peak value of about 12 Gauss near 200°C and then with increasing temperatures, ΔH decreases monotonically, reaching a value of about 2 Gauss near 500°C. Results are somewhat similar in N₂ and H₂ flow. A speculative interpretation of these results is as follows. The initial increase in ΔH from RT to 200°C may be simply

related to the increase in the free radical concentration N observed in the same temperature range. The decrease observed in ΔH with increasing temperatures above 200°C may be possibly due to motional narrowing since in this temperature region, most of the mass of the samples is in the liquid state. (Motional narrowing of linewidth occurs in liquids because of cancellation of dipole-dipole interactions due to the mobility of molecules).

4. SUMMARY AND CONCLUSIONS

- The free radical concentration N at RT in the THF soluble resid samples is smaller by over an order of magnitude as compared to the N values in typical bituminous coals. Furthermore these N values appear proportional to the atomic C/H values for the resid. These observations are consistent with the idea that hydrogen present in the samples lowers N .
- The observations of weight loss in TGA experiments clearly show that more weight is lost in H_2 flow than in N_2 flow and weight loss begin to occur at lower temperatures in H_2 flow than in N_2 flow.
- In TGA experiments in H_2 flow, there is a strong correlation to suggest that the material remaining after heating the samples to 500°C consists primarily of aromatic components.
- Between 100°C and 200°C, there is nearly an order of magnitude increase in free radical density N in the ESR experiments, although in the TGA experiments, there is no weight loss in this temperature range. This suggests that many weaker bonds are being broken in this temperature range without evolution of material.
- From 300° to 500°C, there is a massive evolution of volatiles as seen in TGA and a factor of about 50 increase in the free radical concentration N . This is the result of thermal cracking of the resids.
- There appears to be no significant interaction of molecular hydrogen (without a catalyst) on the thermally generated free radicals in most of the samples yet in TGA experiments, enhanced evolution of volatiles occurs in H_2 flow (as compared to N_2 flow). It is possible that this difference in the TGA experiments is due to suppression of retrograde reactions by H_2 .
- Lack of significant interaction of the resids with H_2 in the ESR experiments made it difficult to extract any information on the hydrogen donor ability of the resids.

5. RECOMMENDATIONS

- In TGA, the weight loss in H₂ flow appears to correlate well with the components of the resids. This technique therefore has the potential of direct characterization of resids. In N₂ flow, several steps in weight loss are seen in some samples. These steps may relate to the evolution of different components. This needs to be investigated further.
- In ESR, the most interesting result appears to be the observed large change in the free radical density between 100 and 200°C, without mass loss. Different catalysts should be tried to see whether one can promote severe catalytic cracking of the resids at these low temperatures.
- The resids do not appear to hydrogenate well without a catalyst at near atmospheric pressures. ESR experiments on hydrogenation should be carried out at higher H₂ pressures, with and without, a catalyst.
- The type of feed coal has an effect on the properties of resids. Of the three feed coals, resids obtained from the Illinois #6 coal yields the best liquefaction product as indicated by the lowest free radical density and the largest weight loss in TGA experiments.

6. REFERENCES

1. M. M. Ibrahim and M. S. Seehra, ACS Div. Fuel Chem. Preprints (in press).
2. M. S. Seehra and B. Ghosh, J. Anal. Appl. Pyrolysis 13, 209 (1988).
3. M. S. Seehra, B. Ghosh and S. E. Mullins, Fuel 65, 1315 (1986).
4. M. S. Seehra, B. Ghosh, J. W. Zondlo, and E. A. Mintz, Fuel Proc. Technol. 18, 279 (1988).
5. T. Yokono, T. Obara, Y. Sanada, S. Shimomura and T. Imamura, Carbon 24, 29 (1986).
6. L. Petrakis and D. W. Grandy, "Free Radicals in Coals and Synthetic Fuels", Elsevier, Amsterdam, 1983.

Table 1. Parameters of the samples supplied by Consol

Sample	Run	Designator	Coal	C(%)	H(%)	H1	H2	H3	H4	H5	H6	H7
C1	257	V131B C/C	Illinois #6	88.75	8.15	16.7	4.4	17.9	9.4	18.6	20.4	12.5
C2	257	R1235 C/C	Illinois #6	88.41	8.04	17.8	4.9	18.6	9.2	18.1	19.7	11.7
C3	257	V1067 C/C	Illinois #6	88.32	8.16	17.7	3.0	18.9	9.3	19.5	19.6	11.9
C4	259	V131B C/C	Pittsburgh	90.54	6.74	26.1	5.4	18.9	9.4	14.8	14.6	10.8
C5	259	R1235 C/C	Pittsburgh	89.79	6.49	30.7	2.6	20.9	10.2	13.8	13.4	8.4
C6	259	V1067 C/C	Pittsburgh	89.8	6.8	28.6	3.6	21.7	9.1	14.8	13.5	8.7
C7	260C	R1235 T/C	Wyodak-Anderson	90.41	6.25	32.8	4.6	20.0	9.4	12.7	14.5	6.0
C8	260C	V1067 T/C	Wyodak-Anderson	89.74	6.46	30.5	4.7	20.8	9.4	13.8	13.0	7.8
C9	260D	R1235 C/T	Wyodak-Anderson	89.20	7.13	23.2	4.4	18.6	8.7	15.7	19.9	9.5
C10	260D	V1067 C/T	Wyodak-Anderson	89.10	6.95	24.7	3.8	19.3	9.3	15.8	18.8	8.2

H1 = condensed aromatics; H2 = uncondensed aromatics; H3 = cyclic alpha; H4 = alkyl alpha; H5 = cyclic beta;
H6 = alkyl beta; H7 = gamma

Table 2. Percentage mass loss Δm in H_2 near $490^\circ C$ for consol samples

Sample	Δm in N_2	Δm in H_2	100-H1-H2
C1	74	82	79
C2	52	76	77
C3	71	76	79
C4	44	68	69
C5	48	65	67
C6	50	62	68
C7	42	68	63
C8	42	69	65
C9	48	69	72
C10	46	68	72

Table 3. Comparison of free radical density N at room temperature for the coal resids and a Blind Canyon coal. Atomic H/C and C/H values are also listed

Sample	N ($10^{17}/g$) ($\pm 10\%$)	H/C (atomic)	C/H (atomic)
Blind canyon coal	80	0.90	1.11
C1	2.0	1.10	0.91
C2	1.9	1.09	0.92
C3	1.3	1.11	0.90
C4	4.6	0.89	1.12
C5	3.0	0.87	1.15
C6	3.0	0.91	1.10
C7	2.5	0.83	1.20
C8	2.0	0.86	1.16
C9	2.8	0.96	1.04
C10	3.1	0.94	1.06

Fig. 1. Plots of remaining $W(\%)$ and the reaction rate $(dm/dt)/m$ against temperature for sample C1 in N_2 flow and H_2 flow. m is the mass at T .

Fig. 2. Plots of remaining $W(\%)$ and the reaction rate $(dm/dt)/m$ against temperature for sample C2 in N_2 flow and H_2 flow. m is the mass at T .

Fig. 3. Plots of remaining $W(\%)$ and the reaction rate $(dm/dt)/m$ against temperature for sample C3 in N_2 flow and H_2 flow. m is the mass at T .

Fig. 4. Plots of remaining $W(\%)$ and the reaction rate $(dm/dt)/m$ against temperature for sample C4 in N_2 flow and H_2 flow. m is the mass at T .

Fig. 5. Plots of remaining $W(\%)$ and the reaction rate $(dm/dt)/m$ against temperature for sample C5 in N_2 flow and H_2 flow. m is the mass at T .

Fig. 6. Plots of remaining $W(\%)$ and the reaction rate $(dm/dt)/m$ against temperature for sample C6 in N_2 flow and H_2 flow. m is the mass at T .

Fig. 7. Plots of remaining $W(\%)$ and the reaction rate $(dm/dt)/m$ against temperature for sample C7 in N_2 flow and H_2 flow. m is the mass at T .

Fig. 8. Plots of remaining $W(\%)$ and the reaction rate $(dm/dt)/m$ against temperature for sample C8 in N_2 flow and H_2 flow. m is the mass at T .

Fig. 9. Plots of remaining $W(\%)$ and the reaction rate $(dm/dt)/m$ against temperature for sample C9 in N_2 flow and H_2 flow. m is the mass at T .

Fig. 10. Plots of remaining $W(\%)$ and the reaction rate $(dm/dt)/m$ against temperature for sample C10 in N_2 flow and H_2 flow. m is the mass at T .

Fig. 11. Representative esr spectra, derivative of absorbtion vs fiêld, H , at several temperatures for C5 in N₂ flow. The linewidths and the position of H_0 are marked. The cavity frequency shifts to lower frequencies with increase in temperature and this is taken into account in calculating the g -values.

Fig. 12. Variation of N vs T for C10 and Blind Canyon coal.

Fig. 13. Plots of N vs T for C1, in N_2 and H_2 flow, with and without mass correction. Error bars in this Fig. and for figs 14-45 are for representative temperatures.

Fig. 14. Plots of N vs T for C_2 , in N_2 and H_2 flow, with and without mass correction.

Fig. 15. Plots of N vs T for C_3 , in N_2 and H_2 flow, with and without mass correction.

Fig. 16. Plots of N vs T for C_4 , in N_2 and H_2 flow, with and without mass correction.

Fig. 17. Plots of N vs T for C5, in N_2 and H_2 flow, with and without mass correction.

Fig. 18. Plots of N vs T for C₆, in N₂ and H₂ flow, with and without mass correction.

Fig. 19. Plots of N vs T for C7, in N_2 and H_2 flow, with and without mass correction.

Fig. 20. Plots of N vs T for C8, in N_2 and H_2 flow, with and without mass correction.

Fig. 21. Plots of N vs T for C9, in N_2 and H_2 flow, with and without mass correction.

Fig. 22. Plots of N vs T for C10, in N_2 and H_2 flow, with and without mass correction.

Fig. 23. Comparison of N at 480°C, 200°C and RT and atomic C/H ratio for samples C1 through C10.

Fig. 24. Temperature dependence of the g-values and linewidth ΔH of the free radicals for C1, in N_2 and H_2 flow.

Fig. 25. Temperature dependence of the g-values and linewidth ΔH of the free radicals for C2, in N_2 and H_2 flow.

Fig. 26. Temperature dependence of the g -values and linewidth ΔH of the free radicals for C3, in N_2 and H_2 flow.

Fig. 27. Temperature dependence of the g -values and linewidth ΔH of the free radicals for C_4 , in N_2 and H_2 flow.

Fig. 28. Temperature dependence of the g-values and linewidth ΔH of the free radicals for C5, in N_2 and H_2 flow.

Fig. 29. Temperature dependence of the g -values and linewidth ΔH of the free radicals for C6, in N_2 and H_2 flow.

Fig. 30. Temperature dependence of the g-values and linewidth ΔH of the free radicals for C7, in N_2 and H_2 flow.

Fig. 31. Temperature dependence of the g-values and linewidth ΔH of the free radicals for C8, in N₂ and H₂ flow.

Fig. 32. Temperature dependence of the g-values and linewidth ΔH of the free radicals for C9, in N_2 and H_2 flow.

Fig. 33. Temperature dependence of the g-values and linewidth ΔH of the free radicals for C10, in N₂ and H₂ flow.

APPENDIX 1

Numerical data from TGA in N₂ flow.
The remaining weight (% of initial weight)
is presented for resids C1-C10.

	T (C)	W(%) C1	W(%) C2	W(%) C3	W(%) C4	W(%) C5	W(%) C6	W(%) C7	W(%) C8	W(%) C9	W(%) C10
1											
2	30	100.00	100.00	100.00	100.00	100.00	100.00	100.00	100.00	100.00	100.00
3	35	100.40	100.05	100.07	100.04	100.05	100.06	100.19	100.16	100.14	100.01
4	40	100.35	100.00	100.03	99.97	100.00	100.01	100.11	100.10	100.07	99.95
5	45	100.35	100.01	100.01	99.97	100.01	100.01	100.14	100.12	100.07	99.95
6	50	100.32	99.98	99.97	99.94	99.98	99.97	100.14	100.12	100.08	99.96
7											
8	55	100.29	99.96	99.96	99.92	99.95	99.97	100.16	100.12	100.05	99.94
9	60	100.27	99.92	99.94	99.89	99.93	99.92	100.16	100.10	100.05	99.93
10	65	100.24	99.91	99.91	99.88	99.93	99.91	100.17	100.10	100.04	99.92
11	70	100.23	99.87	99.89	99.85	99.91	99.88	100.17	100.09	100.03	99.92
12	75	100.21	99.83	99.88	99.81	99.86	99.85	100.18	100.08	100.03	99.92
13											
14	80	100.19	99.83	99.84	99.78	99.86	99.83	100.19	100.06	100.01	99.89
15	85	100.17	99.81	99.82	99.77	99.84	99.80	100.20	100.08	100.01	99.89
16	90	100.15	99.77	99.81	99.74	99.82	99.78	100.22	100.08	100.01	99.88
17	95	100.12	99.76	99.80	99.70	99.81	99.74	100.21	100.08	100.00	99.88
18	100	100.11	99.74	99.78	99.67	99.80	99.73	100.19	100.06	99.98	99.86
19											
20	105	100.10	99.70	99.77	99.63	99.77	99.70	100.19	100.07	99.95	99.86
21	110	100.09	99.70	99.74	99.60	99.75	99.66	100.19	100.04	99.95	99.85
22	115	100.06	99.66	99.73	99.58	99.73	99.63	100.18	100.05	99.94	99.84
23	120	100.05	99.66	99.74	99.56	99.72	99.61	100.18	100.01	99.93	99.83
24	125	100.03	99.63	99.73	99.55	99.70	99.60	100.19	99.97	99.94	99.83
25											
26	130	100.01	99.63	99.68	99.53	99.68	99.57	100.19	99.96	99.93	99.83
27	135	100.02	99.62	99.66	99.51	99.67	99.57	100.18	99.96	99.92	99.82
28	140	99.98	99.59	99.63	99.49	99.65	99.54	100.20	99.94	99.92	99.82
29	145	99.97	99.56	99.61	99.48	99.64	99.53	100.17	99.93	99.91	99.82
30	150	99.94	99.56	99.59	99.45	99.63	99.51	100.17	99.95	99.90	99.82
31											
32	155	99.94	99.54	99.56	99.44	99.63	99.50	100.15	99.93	99.89	99.82
33	160	99.89	99.50	99.54	99.42	99.60	99.49	100.16	99.92	99.88	99.82
34	165	99.89	99.47	99.49	99.41	99.59	99.47	100.15	99.91	99.86	99.82
35	170	99.86	99.47	99.47	99.37	99.58	99.46	100.13	99.92	99.85	99.82

	T (C)	W(%) C1	W(%) C2	W(%) C3	W(%) C4	W(%) C5	W(%) C6	W(%) C7	W(%) C8	W(%) C9	W(%) C10
36	175	99.86	99.44	99.44	99.37	99.56	99.43	100.13	99.92	99.84	99.82
37											
38	180	99.84	99.41	99.40	99.34	99.56	99.42	100.11	99.92	99.82	99.83
39	185	99.82	99.38	99.37	99.31	99.56	99.41	100.09	99.90	99.81	99.83
40	190	99.78	99.34	99.34	99.28	99.51	99.38	100.09	99.89	99.81	99.85
41	195	99.77	99.33	99.30	99.27	99.51	99.36	100.08	99.90	99.80	99.83
42	200	99.75	99.32	99.26	99.25	99.49	99.35	100.06	99.90	99.79	99.83
43											
44	205	99.73	99.28	99.22	99.23	99.46	99.32	100.07	99.89	99.80	99.83
45	210	99.69	99.25	99.19	99.19	99.44	99.31	100.05	99.88	99.78	99.83
46	215	99.68	99.21	99.15	99.18	99.43	99.29	100.03	99.88	99.78	99.85
47	220	99.66	99.18	99.11	99.14	99.42	99.27	99.98	99.88	99.77	99.83
48	225	99.64	99.16	99.05	99.11	99.39	99.25	99.98	99.88	99.76	99.83
49											
50	230	99.60	99.13	99.01	99.08	99.37	99.23	99.95	99.85	99.75	99.82
51	235	99.55	99.08	98.98	99.05	99.36	99.20	99.92	99.83	99.74	99.83
52	240	99.51	99.04	98.92	99.02	99.34	99.18	99.89	99.80	99.72	99.82
53	245	99.48	99.00	98.89	98.99	99.31	99.15	99.87	99.81	99.72	99.80
54	250	99.45	98.94	98.80	98.95	99.28	99.12	99.84	99.77	99.70	99.79
55											
56	255	99.40	98.89	98.75	98.93	99.25	99.09	99.80	99.73	99.68	99.76
57	260	99.34	98.84	98.68	98.88	99.22	99.06	99.77	99.68	99.66	99.75
58	265	99.28	98.78	98.60	98.83	99.19	99.02	99.73	99.62	99.64	99.72
59	270	99.20	98.69	98.51	98.77	99.14	98.97	99.68	99.55	99.62	99.69
60	275	99.12	98.63	98.44	98.74	99.11	98.93	99.63	99.47	99.56	99.64
61											
62	280	99.03	98.53	98.33	98.68	99.07	98.88	99.57	99.39	99.52	99.60
63	285	98.94	98.43	98.21	98.61	99.02	98.82	99.49	99.29	99.47	99.51
64	290	98.83	98.32	98.10	98.53	98.96	98.75	99.41	99.19	99.42	99.45
65	295	98.68	98.20	97.96	98.46	98.91	98.67	99.31	99.06	99.34	99.37
66	300	98.54	98.06	97.80	98.36	98.84	98.59	99.19	98.94	99.24	99.27
67											
68	305	98.38	97.91	97.60	98.28	98.76	98.49	99.06	98.81	99.16	99.16
69	310	98.19	97.73	97.39	98.15	98.66	98.37	98.91	98.65	99.03	99.02
70	315	97.99	97.54	97.15	98.02	98.56	98.25	98.72	98.47	98.89	98.87

	T (C)	W(%) C1	W(%) C2	W(%) C3	W(%) C4	W(%) C5	W(%) C6	W(%) C7	W(%) C8	W(%) C9	W(%) C10
71	320	97.75	97.29	96.88	97.87	98.43	98.10	98.51	98.29	98.73	98.69
72	325	97.49	97.03	96.60	97.70	98.30	97.92	98.28	98.09	98.55	98.49
73											
74	330	97.17	96.76	96.25	97.51	98.15	97.75	98.01	97.89	98.33	98.25
75	335	96.81	96.44	95.86	97.31	97.97	97.50	97.70	97.66	98.09	97.99
76	340	96.44	96.09	95.45	97.07	97.77	97.26	97.37	97.42	97.79	97.69
77	345	96.00	95.69	94.93	96.81	97.55	96.98	96.99	97.13	97.48	97.35
78	350	95.53	95.27	94.38	96.51	97.31	96.67	96.57	96.85	97.12	96.96
79											
80	355	94.98	94.82	93.78	96.18	97.01	96.32	96.10	96.50	96.75	96.53
81	360	94.37	94.36	93.10	95.83	96.69	95.93	95.58	96.15	96.31	96.05
82	365	93.71	93.91	92.35	95.44	96.34	95.49	95.00	95.77	95.77	95.51
83	370	92.99	93.46	91.51	95.02	95.96	95.00	94.37	95.35	95.20	94.92
84	375	92.16	93.06	90.60	94.61	95.51	94.47	93.69	94.88	94.63	94.27
85											
86	380	91.27	92.76	89.60	94.20	95.04	93.89	92.94	94.36	93.94	93.56
87	385	90.25	92.50	88.52	93.78	94.50	93.25	92.12	93.77	93.18	92.83
88	390	89.17	92.30	87.33	93.35	93.91	92.54	91.24	93.15	92.32	92.03
89	395	87.96	92.08	86.07	92.75	93.26	91.77	90.31	92.48	91.40	91.12
90	400	86.68	90.72	84.67	92.21	92.58	90.93	89.27	91.73	90.38	90.07
91											
92	405	85.27	91.58	83.20	91.73	91.81	90.01	88.18	90.91	89.27	88.91
93	410	83.75	91.24	81.58	91.29	90.93	89.03	87.02	90.03	88.05	87.64
94	415	82.11	90.82	79.88	90.88	89.99	87.95	85.78	89.07	86.70	86.28
95	420	80.31	90.26	78.03	90.51	88.92	86.77	84.49	88.03	85.20	84.80
96	425	78.37	89.59	76.09	90.12	87.74	85.49	83.20	86.88	83.63	83.21
97											
98	430	76.28	88.70	73.92	89.68	86.44	84.12	81.95	85.64	81.84	81.45
99	435	74.02	87.56	71.67	89.17	85.13	82.62	80.93	84.31	79.92	79.60
100	440	71.54	86.09	69.23	88.55	83.77	81.01	79.66	82.89	77.85	77.61
101	445	68.83	84.00	66.66	87.80	82.22	79.26	78.92	81.38	75.66	75.48
102	450	65.93	79.82	63.87	86.86	80.50	77.36	78.21	79.80	73.31	73.13
103											
104	455	62.80	72.61	60.90	85.68	78.51	75.33	77.31	78.10	70.87	70.73
105	460	59.48	68.94	57.77	84.23	76.27	73.15	76.52	76.35	68.42	67.18

	T (C)	W(%) C1	W(%) C2	W(%) C3	W(%) C4	W(%) C5	W(%) C6	W(%) C7	W(%) C8	W(%) C9	W(%) C10
106	465	55.99	64.25	54.48	82.47	73.88	70.85	75.52	74.49	65.97	64.25
107	470	52.91	60.37	51.09	79.57	71.23	68.51	74.44	72.64	62.75	62.35
108	475	49.83	57.08	47.71	76.75	68.90	66.09	72.36	70.81	60.00	60.85
109											
110	480	46.49	54.28	44.48	74.13	66.75	63.74	70.21	69.03	58.30	59.56
111	485	43.21	52.05	41.48	70.71	64.52	61.49	68.68	67.28	57.19	58.47
112	490	39.95	50.25	38.79	67.49	60.92	59.35	67.55	65.64	56.07	57.58
113	495	36.22	48.84	36.63	65.05	56.36	57.40	66.53	64.10	55.07	56.62
114	500	30.34	47.82	34.93	62.92	55.14	55.65	65.45	62.70	54.21	55.49
115											
116	505	29.29	46.98	33.51	61.44	54.27	54.09	64.55	61.46	53.40	55.09
117	510	28.61	46.28	32.33	60.17	53.43	52.75	63.74	60.36	52.72	54.48
118	515	28.04	45.76	31.40	59.09	52.81	51.68	63.01	59.46	52.14	53.97
119	520	27.59	45.27	30.60	58.17	52.28	51.15	62.38	58.99	51.63	53.52
120	525	27.22	44.74	29.96	57.41	51.82	50.78	61.85	58.58	51.21	53.17
121											
122	530	26.95	44.19	29.49	56.76	51.42	50.44	61.40	58.21	50.88	52.84
123	535	26.80	43.59	29.14	56.23	51.11	50.12	61.01	57.88	50.57	52.59
124	540	26.70	42.89	28.91	55.78	50.86	49.87	60.67	57.58	50.36	52.37
125	545	26.61	42.08	28.81	55.39	50.64	49.65	60.38	57.33	50.14	52.17
126	550	26.52	41.09	28.73	55.01	50.47	49.47	60.13	57.16	49.98	51.99
127											
128	555	26.44	39.90	28.64	54.61	50.32	49.32	59.92	57.04	49.83	51.81
129	560	26.36	38.65	28.59	54.16	50.20	49.22	59.74	56.89	49.69	51.64
130	565	26.30	36.97	28.59	53.56	50.06	49.11	59.58	56.76	49.54	51.47
131	570	26.22	35.19	28.48	52.82	49.97	49.03	59.42	56.63	49.39	51.28
132	575	26.12	33.26	28.42	51.88	49.86	48.94	59.26	56.50	49.23	51.09
133											
134	580	26.03	31.19	28.36	50.75	49.76	48.87	59.10	56.39	49.06	50.05
135	585	25.94	29.04	28.33	49.49	49.65	48.76	58.92	56.26	48.86	50.62
136	590	25.82	26.85	28.26	48.07	49.55	48.68	58.74	56.13	48.63	50.15
137	595	25.68	24.62	28.21	46.54	49.43	48.58	58.55	56.01	48.36	49.53

APPENDIX 2

Numerical data from TGA in H₂ flow.
The remaining weight (% of initial weight)
is presented for resids C1-C10.

	T (C)	W(%) C1	W(%) C2	W(%) C3	W(%) C4	W(%) C5	W(%) C6	W(%) C7	W(%) C8	W(%) C9	W(%) C10
1											
2	30	100.00	100.00	100.00	100.00	100.00	100.00	100.00	100.00	100.00	100.00
3	35	100.21	100.01	99.685	100.10	100.03	100.04	100.03	100.25	100.00	99.969
4	40	100.41	99.982	99.188	100.05	100.04	100.06	100.04	100.36	99.972	99.906
5	45	100.68	99.977	99.021	100.12	100.05	100.08	100.05	100.45	99.931	99.875
6	50	100.57	99.994	98.880	100.17	100.05	100.11	100.06	100.53	99.931	99.875
7											
8	55	100.84	99.977	98.792	100.14	100.06	100.13	100.08	100.58	99.903	99.843
9	60	101.11	99.977	98.752	100.18	100.06	100.14	100.09	100.61	99.889	99.828
10	65	100.69	99.988	98.685	100.19	100.08	100.15	100.10	100.62	99.861	99.812
11	70	101.04	99.977	98.625	100.15	100.07	100.16	100.12	100.64	99.833	99.781
12	75	101.44	99.965	98.571	100.17	100.08	100.16	100.13	100.64	99.805	99.781
13											
14	80	101.51	99.977	98.544	100.08	100.08	100.17	100.15	100.66	99.764	99.734
15	85	101.49	99.977	98.477	100.12	100.07	100.17	100.16	100.66	99.736	99.671
16	90	101.41	99.953	98.504	100.05	100.08	100.17	100.17	100.66	99.708	99.687
17	95	101.71	99.947	98.491	100.02	100.09	100.17	100.18	100.64	99.680	99.671
18	100	101.66	99.947	98.470	99.991	100.09	100.17	100.20	100.64	99.653	99.671
19											
20	105	101.82	99.953	98.484	100.01	100.09	100.17	100.22	100.64	99.625	99.593
21	110	101.81	99.953	98.457	99.955	100.10	100.18	100.23	100.64	99.611	99.593
22	115	101.83	99.959	98.437	100.00	100.11	100.19	100.25	100.64	99.583	99.577
23	120	101.74	99.947	98.397	99.937	100.09	100.20	100.26	100.64	99.555	99.546
24	125	102.01	99.947	98.397	99.982	100.10	100.21	100.27	100.62	99.528	99.546
25											
26	130	101.70	99.953	98.370	99.919	100.10	100.22	100.29	100.61	99.500	99.530
27	135	101.66	99.953	98.383	99.982	100.13	100.23	100.30	100.61	99.472	99.499
28	140	102.22	99.947	98.303	99.964	100.10	100.24	100.31	100.59	99.430	99.515
29	145	102.29	99.941	98.323	99.910	100.11	100.25	100.32	100.58	99.402	99.499
30	150	102.11	99.941	98.276	99.955	100.08	100.26	100.33	100.56	99.375	99.483
31											
32	155	102.06	99.924	98.215	99.883	100.06	100.26	100.34	100.55	99.347	99.421
33	160	102.28	99.900	98.162	99.928	100.09	100.27	100.36	100.53	99.319	99.405
34	165	102.31	99.883	98.155	99.919	100.06	100.27	100.35	100.52	99.291	99.389
35	170	102.25	99.871	98.088	99.855	100.05	100.28	100.36	100.48	99.250	99.374

	T (C)	W(%) C1	W(%) C2	W(%) C3	W(%) C4	W(%) C5	W(%) C6	W(%) C7	W(%) C8	W(%) C9	W(%) C10
36	175	102.34	99.865	98.068	99.855	100.05	100.28	100.37	100.47	99.222	99.311
37											
38	180	102.38	99.842	98.028	99.783	100.04	100.28	100.38	100.45	99.180	99.327
39	185	102.36	99.807	98.008	99.801	100.02	100.29	100.38	100.42	99.152	99.280
40	190	102.51	99.789	97.974	98.792	100.01	100.29	100.38	100.41	99.111	99.295
41	195	102.42	99.754	97.967	99.747	99.991	100.29	100.39	100.41	99.069	99.248
42	200	102.57	99.736	97.934	99.702	99.973	100.28	100.39	100.34	99.027	99.217
43											
44	205	102.19	99.684	97.893	99.729	99.946	100.29	100.39	100.31	98.986	99.233
45	210	101.12	99.660	97.880	99.684	99.928	100.28	100.39	100.27	98.944	99.217
46	215	101.11	99.637	97.847	99.602	99.910	100.28	100.38	100.20	98.888	99.201
47	220	101.12	99.602	97.793	99.657	99.883	100.27	100.38	100.16	98.833	99.201
48	225	101.16	99.572	97.746	99.648	99.847	100.26	100.37	100.08	98.777	99.155
49											
50	230	101.06	99.531	97.659	99.557	99.829	100.25	100.35	100.00	98.708	99.123
51	235	101.08	99.478	97.672	99.548	99.766	100.23	100.33	99.906	98.610	99.076
52	240	101.08	99.414	97.618	99.503	99.721	100.22	100.31	99.781	98.527	99.029
53	245	100.90	99.344	97.511	99.458	99.658	100.20	100.28	99.656	98.416	98.982
54	250	100.79	99.268	97.451	99.386	99.604	100.17	100.24	99.500	98.291	98.920
55											
56	255	100.86	99.197	97.350	99.259	99.514	100.14	100.20	99.313	98.138	98.841
57	260	100.66	99.057	97.296	99.232	99.460	100.11	100.13	99.094	97.985	98.763
58	265	100.42	98.934	97.202	99.142	99.343	100.06	100.06	98.860	97.804	98.622
59	270	100.32	98.775	97.068	98.961	99.226	100.01	99.984	98.579	97.596	98.497
60	275	100.13	98.617	96.941	98.871	99.100	99.947	99.882	98.266	97.360	98.325
61											
62	280	99.986	98.424	96.787	98.726	98.920	99.869	99.763	97.907	97.096	98.121
63	285	99.814	98.195	96.572	98.473	98.740	99.785	99.618	97.516	96.790	97.886
64	290	99.581	97.990	96.404	98.301	98.524	99.679	99.457	97.063	96.442	97.605
65	295	99.175	97.674	96.169	98.066	98.281	99.548	99.268	96.564	96.053	97.276
66	300	98.852	97.340	95.874	97.723	98.001	99.411	99.048	96.001	95.609	96.900
67											
68	305	98.502	96.976	95.572	97.425	97.695	99.243	98.795	95.376	95.122	96.493
69	310	97.980	96.590	95.244	97.073	97.326	99.049	98.499	94.705	94.566	95.961
70	315	97.306	96.068	94.814	96.585	96.930	98.823	98.160	93.939	93.941	95.428

	T (C)	W(%) C1	W(%) C2	W(%) C3	W(%) C4	W(%) C5	W(%) C6	W(%) C7	W(%) C8	W(%) C9	W(%) C10
71	320	96.797	95.570	94.398	96.160	96.507	98.560	97.784	93.112	93.260	94.802
72	325	96.069	95.008	93.882	95.618	95.967	98.261	97.348	92.206	92.496	94.129
73											
74	330	95.237	94.351	93.271	94.986	95.418	97.919	96.853	91.206	91.648	93.362
75	335	94.523	93.689	92.681	94.281	94.797	97.536	96.305	90.128	90.731	92.516
76	340	93.657	92.916	91.950	93.603	94.121	97.099	95.697	88.972	89.730	91.592
77	345	92.537	92.136	91.165	92.808	93.338	96.621	95.019	87.738	88.633	90.559
78	350	91.526	91.298	90.279	91.932	92.528	96.085	94.374	86.442	87.451	89.494
79											
80	355	90.289	90.461	89.313	91.001	91.637	95.497	93.438	85.052	86.201	88.320
81	360	88.729	89.494	88.300	89.899	90.673	94.845	92.550	83.615	84.867	87.052
82	365	87.389	88.562	87.113	88.851	89.989	94.131	91.566	82.084	83.449	85.705
83	370	85.829	87.525	85.918	87.667	88.594	93.369	90.517	80.490	81.976	84.281
84	375	84.173	86.406	84.550	86.438	87.468	92.533	89.382	78.897	80.420	82.762
85											
86	380	82.393	85.240	83.114	85.047	86.298	91.629	88.166	77.195	78.835	81.196
87	385	80.455	83.927	81.571	83.674	85.029	90.663	86.865	75.461	77.154	79.552
88	390	78.400	82.579	79.921	82.219	83.732	89.617	85.498	73.684	75.445	77.861
89	395	76.359	81.079	78.217	80.620	82.382	88.498	84.041	71.821	73.694	76.092
90	400	74.105	79.538	76.372	79.066	80.987	87.305	82.492	69.978	71.873	74.276
91											
92	405	71.823	77.810	74.433	77.403	79.519	86.033	80.856	68.104	69.997	72.381
93	410	69.590	76.017	72.394	75.714	77.998	84.693	79.135	66.198	68.038	70.393
94	415	67.178	74.106	70.247	73.943	76.314	83.269	77.317	64.339	66.064	68.358
95	420	64.635	71.974	68.040	72.073	74.658	81.782	75.402	62.418	64.036	66.338
96	425	62.147	69.841	65.705	70.257	72.911	80.216	73.412	60.481	61.993	64.240
97											
98	430	59.350	67.426	63.250	68.377	71.093	78.556	71.330	58.529	59.867	62.126
99	435	56.628	64.872	60.794	66.417	69.193	76.791	69.168	56.576	57.657	59.919
100	440	53.770	62.147	58.158	64.393	67.249	74.972	66.995	54.624	55.392	57.680
101	445	50.608	59.299	55.401	62.270	65.169	73.039	64.746	52.671	53.099	55.394
102	450	47.722	56.147	52.576	60.201	63.018	70.979	62.476	50.765	50.750	53.092
103											
104	455	44.719	52.168	49.698	57.996	60.776	68.814	60.164	48.860	48.430	50.744
105	460	41.626	47.949	46.706	55.674	58.606	66.581	57.797	47.001	46.123	48.442

	T (C)	W(%) C1	W(%) C2	W(%) C3	W(%) C4	W(%) C5	W(%) C6	W(%) C7	W(%) C8	W(%) C9	W(%) C10
106	465	38.465	43.572	43.808	53.406	53.961	64.053	55.409	45.158	43.899	46.188
107	470	35.743	39.318	41.024	51.075	49.145	61.479	53.122	43.377	41.829	44.246
108	475	33.448	35.603	38.508	48.771	46.237	58.536	50.535	41.659	39.897	42.383
109											
110	480	30.946	32.667	36.147	46.476	43.635	55.609	47.980	40.003	38.160	40.582
111	485	28.747	30.277	34.080	44.299	41.565	52.777	45.452	38.472	36.631	37.122
112	490	26.960	28.536	32.329	42.356	40.007	48.899	41.095	37.035	35.353	34.868
113	495	23.854	27.153	30.827	40.549	38.693	45.531	38.556	35.739	34.283	33.553
114	500	21.930	26.040	29.532	38.923	37.658	43.692	36.889	34.552	33.380	32.691
115											
116	505	20.555	25.149	28.552	37.477	36.901	42.158	35.496	33.521	32.615	32.018
117	510	19.648	24.399	27.653	36.194	36.289	40.828	34.253	32.599	31.976	31.533
118	515	18.906	23.796	27.009	35.173	35.785	39.909	33.452	31.787	31.462	31.188
119	520	18.370	23.374	26.439	34.189	35.380	39.225	32.925	31.162	31.045	30.907
120	525	18.026	23.052	26.043	33.583	35.038	38.705	32.559	30.709	30.725	30.719
121											
122	530	17.841	22.847	25.714	33.059	34.759	38.306	32.258	30.334	30.461	30.578
123	535	17.421	22.653	25.406	32.917	34.543	37.991	32.021	30.022	30.253	30.468
124	540	17.229	22.536	25.211	32.246	34.381	37.744	31.811	29.756	30.086	30.359
125	545	17.016	22.425	24.997	32.029	34.237	37.533	31.644	29.553	29.947	30.265
126	550	16.879	22.296	24.876	31.812	34.120	37.350	31.499	29.397	29.822	30.186
127											
128	555	16.796	22.225	24.782	31.641	34.012	37.208	31.381	29.272	29.725	30.139
129	560	16.796	22.143	24.641	31.442	33.903	37.092	31.268	29.163	29.628	30.045
130	565	16.721	22.079	24.567	31.370	33.804	36.998	31.182	29.085	29.544	30.014
131	570	16.473	22.032	24.480	31.270	33.714	36.919	31.101	29.007	29.461	29.920
132	575	16.631	21.974	24.386	31.108	33.624	36.850	31.031	28.928	29.364	29.842
133											
134	580	16.452	21.921	24.332	31.053	33.525	36.787	30.967	28.835	29.280	29.795
135	585	16.370	21.845	24.245	30.972	33.435	36.730	30.907	28.772	29.183	29.732
136	590	16.363	21.815	24.171	30.819	33.345	36.688	30.843	28.710	29.100	29.623
137	595	16.109	21.774	24.125	30.791	33.237	36.624	30.784	28.647	29.002	29.560

APPENDIX 3

Rate of weight loss in N₂ flow from TGA.

	T (C)	m/m C1	m/m C2	m/m C3	m/m C4	m/m C5	m/m C6	m/m C7	m/m C8	m/m C9	m/m C10
1											
2	30	-2.202e-04	-4.549e-05	4.336e-05	2.851e-05	3.341e-05	4.128e-05	-1.798e-05	5.825e-06	-1.080e-05	8.888e-05
3		-1.860e-05	-3.130e-05	-2.364e-05	-2.664e-05	-1.461e-05	-2.285e-05	-1.561e-06	-1.228e-05	-1.214e-05	-8.300e-06
4		-3.948e-06	-4.726e-06	-4.598e-06	-1.364e-05	-8.875e-06	-8.256e-06	-2.108e-05	-1.875e-05	-1.417e-05	-1.660e-05
5	45	-7.896e-06	-3.544e-06	-6.569e-07	-5.579e-06	-6.786e-06	-5.081e-06	1.483e-05	1.358e-05	6.748e-06	9.485e-06
6	50	-1.128e-05	-1.536e-05	-1.380e-05	-9.921e-06	-1.097e-05	-5.083e-06	2.342e-06	-4.525e-06	-8.097e-06	-1.779e-06
7											
8	55	-1.693e-06	-5.911e-07	-8.544e-06	2.481e-06	-1.254e-05	-6.353e-06	-2.342e-06	-6.465e-07	-2.025e-06	-1.779e-06
9	60	-5.080e-06	-1.005e-05	-5.916e-06	-7.445e-06	-8.359e-06	-8.263e-06	4.683e-06	-1.940e-06	-7.424e-06	-2.965e-06
10	65	-7.340e-06	-6.505e-06	-7.233e-06	-5.584e-06	-1.045e-06	-7.628e-06	-7.804e-06	-1.940e-06	-6.750e-06	-7.710e-06
11	70	-8.470e-06	-7.690e-06	-4.604e-06	-8.069e-06	-4.703e-06	-1.272e-05	5.463e-06	1.940e-06	-6.076e-06	-2.965e-06
12	75	-6.777e-06	-7.693e-06	-3.289e-06	-1.118e-05	-1.255e-05	-1.209e-05	3.121e-06	-2.587e-06	6.751e-07	-5.933e-06
13											
14	80	-7.344e-06	-1.184e-06	-1.053e-05	-8.074e-06	-1.411e-05	-6.998e-06	5.462e-06	1.293e-06	-6.077e-06	-5.933e-07
15	85	-6.780e-06	-1.243e-05	2.633e-06	-4.348e-06	3.137e-06	-7.637e-06	1.560e-06	0.000e+00	-1.350e-06	-1.780e-06
16	90	-7.911e-06	-5.330e-06	-1.316e-06	-8.699e-06	-9.937e-06	-9.548e-06	-2.340e-06	1.293e-06	-4.727e-06	-4.153e-06
17	95	-8.479e-06	-9.476e-06	-5.925e-06	-1.119e-05	-4.185e-06	-7.641e-06	-7.801e-06	-6.467e-06	-4.052e-06	-3.560e-06
18	100	-6.784e-06	-1.066e-05	-9.878e-06	-8.705e-06	-7.848e-06	-1.720e-05	-5.462e-06	-6.468e-07	-5.403e-06	-7.121e-06
19											
20	105	-1.131e-06	-1.778e-06	1.976e-06	-1.182e-05	-4.709e-06	-6.371e-06	-2.341e-06	3.234e-06	-6.080e-06	-2.967e-06
21	110	-5.089e-06	1.185e-06	-9.222e-06	-8.711e-06	-9.421e-06	-1.466e-05	-2.341e-06	3.882e-06	-7.431e-06	-4.155e-06
22	115	-1.697e-06	-6.521e-06	-8.564e-06	-1.168e-06	-6.805e-06	-5.738e-06	-1.561e-06	6.470e-07	2.703e-06	-2.374e-06
23	120	-9.051e-06	-7.708e-06	-7.905e-06	-1.867e-06	-1.571e-06	-1.403e-05	-7.803e-07	-1.877e-05	6.081e-06	-4.155e-06
24	125	-4.526e-06	-1.779e-06	-2.635e-06	-8.848e-06	-1.204e-05	-2.551e-06	-7.803e-07	-1.942e-06	-1.351e-06	-2.374e-06
25											
26	130	-2.829e-06	-1.067e-05	7.909e-06	-8.095e-06	-2.095e-06	-7.654e-06	-2.341e-06	-6.475e-07	-4.730e-06	0.000e+00
27	135	-1.132e-05	-1.186e-06	-1.516e-05	-8.719e-06	3.668e-06	-5.103e-06	-6.243e-06	-5.828e-06	-6.082e-06	-2.968e-06
28	140	-4.529e-06	-9.492e-06	-1.055e-05	-8.098e-06	-3.667e-06	-5.104e-06	1.560e-06	-3.886e-06	-2.027e-06	0.000e+00
29	145	-6.793e-06	-1.721e-05	-1.121e-05	1.246e-06	-9.431e-06	-4.467e-06	2.341e-06	-2.591e-06	0.000e+00	1.187e-06
30	150	-3.964e-06	-8.308e-06	-8.578e-06	-4.362e-06	1.048e-06	-6.362e-07	3.122e-06	-5.828e-06	-4.732e-06	0.000e+00
31											
32	155	-7.362e-06	-7.123e-06	-4.619e-06	-1.059e-05	-7.880e-06	-6.383e-07	-3.903e-06	-1.295e-06	-2.028e-06	1.781e-06
33	160	-1.417e-05	-3.563e-06	-1.320e-05	-5.610e-06	-2.097e-06	-8.299e-06	2.342e-06	-6.478e-07	-4.057e-06	5.936e-07
34	165	-7.365e-06	-5.345e-06	-1.981e-06	-6.858e-06	-4.194e-06	0.000e+00	-5.464e-06	1.296e-06	-6.762e-07	4.156e-06
35	170	-2.834e-06	-1.188e-05	-7.926e-06	-4.365e-06	-6.818e-06	-3.831e-06	-1.562e-06	-1.296e-06	-4.058e-06	-5.936e-07

	T (C)	m/m C1	m/m C2	m/m C3	m/m C4	m/m C5	m/m C6	m/m C7	m/m C8	m/m C9	m/m C10
36	175	-9.068e-06	-1.010e-05	-1.189e-05	-4.366e-06	-1.573e-06	-6.387e-06	-5.465e-06	1.943e-06	-5.411e-06	1.187e-06
37											
38	180	-5.669e-07	-1.664e-05	-1.190e-05	1.871e-06	5.244e-07	-7.027e-06	7.809e-07	-1.943e-06	-6.765e-06	-2.968e-06
39	185	-2.835e-06	-1.070e-05	-1.190e-05	-8.736e-06	-5.244e-07	-4.472e-06	-2.343e-06	3.239e-06	-2.706e-06	-5.935e-07
40	190	-6.235e-06	-9.516e-06	-1.720e-05	-1.873e-06	-5.771e-06	-1.214e-05	0.000e+00	6.480e-07	1.353e-06	4.155e-06
41	195	-1.305e-05	-3.569e-06	-1.059e-05	-1.373e-05	-3.148e-06	-5.753e-06	-2.343e-06	3.887e-06	-4.736e-06	1.187e-06
42	200	-1.589e-05	-1.904e-05	-1.324e-05	-6.869e-06	-7.346e-06	-4.475e-06	-5.469e-06	1.296e-06	-2.707e-06	5.342e-06
43											
44	205	-1.305e-05	-7.141e-06	-1.059e-05	-9.993e-06	-1.680e-05	-1.151e-05	2.344e-06	-8.424e-06	-6.766e-06	1.781e-06
45	210	-1.362e-05	-1.191e-06	-1.192e-05	-8.122e-06	-4.725e-06	-6.395e-07	-6.250e-06	-3.888e-06	-4.061e-06	2.374e-06
46	215	-1.760e-05	-1.251e-05	-1.590e-05	-1.125e-05	-6.301e-06	1.919e-06	-3.126e-06	-4.536e-06	-7.445e-06	-4.155e-06
47	220	-1.079e-05	-8.340e-06	-1.790e-05	-8.751e-06	-5.776e-06	-7.678e-06	-8.601e-06	-2.592e-06	-1.354e-06	-1.781e-06
48	225	-7.384e-06	-1.251e-05	-1.260e-05	-1.001e-05	-1.103e-05	-8.959e-06	-6.255e-06	-1.296e-06	-4.061e-06	-2.968e-06
49											
50	230	-1.250e-05	-1.252e-05	-2.190e-05	-1.001e-05	-1.313e-05	-5.761e-06	-6.257e-06	-5.834e-06	-2.708e-06	-2.968e-06
51	235	-9.665e-06	-1.550e-05	-7.302e-06	-1.126e-05	0.000e+00	-1.088e-05	-9.388e-06	-4.539e-06	1.354e-06	5.936e-07
52	240	-1.024e-05	-1.551e-05	-1.993e-05	-1.314e-05	-6.832e-06	-7.684e-06	-1.096e-05	-7.783e-06	0.000e+00	-1.781e-06
53	245	-2.048e-05	-1.850e-05	-2.060e-05	-1.816e-05	-1.104e-05	-8.327e-06	-8.610e-06	2.594e-06	-6.772e-06	-3.563e-06
54	250	-2.049e-05	-1.672e-05	-1.729e-05	-1.315e-05	-9.465e-06	-1.089e-05	-1.644e-05	-1.362e-05	-6.773e-06	-4.158e-06
55											
56	255	-1.765e-05	-1.255e-05	-1.996e-05	-1.253e-05	-1.157e-05	-6.409e-07	-1.253e-05	-1.428e-05	-8.129e-06	-5.941e-06
57	260	-1.595e-05	-1.136e-05	-1.465e-05	-1.629e-05	-1.052e-05	-1.667e-05	-1.097e-05	-2.078e-05	-9.486e-06	-1.189e-05
58	265	-2.622e-05	-2.093e-05	-3.198e-05	-1.944e-05	-1.211e-05	-1.347e-05	-1.646e-05	-2.274e-05	-1.084e-05	-1.189e-05
59	270	-2.738e-05	-2.155e-05	-3.135e-05	-1.318e-05	-1.632e-05	-1.348e-05	-1.490e-05	-2.406e-05	-9.490e-06	-5.352e-06
60	275	-2.455e-05	-2.576e-05	-3.604e-05	-2.260e-05	-1.159e-05	-1.733e-05	-1.805e-05	-2.668e-05	-1.560e-05	-1.666e-05
61											
62	280	-3.315e-05	-3.658e-05	-3.942e-05	-2.135e-05	-1.212e-05	-1.863e-05	-2.277e-05	-2.735e-05	-9.499e-06	-1.608e-05
63	285	-4.233e-05	-3.241e-05	-3.546e-05	-2.137e-05	-1.898e-05	-2.185e-05	-2.750e-05	-3.194e-05	-1.765e-05	-2.026e-05
64	290	-3.837e-05	-4.327e-05	-5.425e-05	-2.579e-05	-1.899e-05	-2.251e-05	-2.988e-05	-3.785e-05	-2.581e-05	-2.564e-05
65	295	-4.359e-05	-3.850e-05	-3.219e-05	-2.769e-05	-2.797e-05	-2.768e-05	-3.385e-05	-4.116e-05	-3.195e-05	-3.223e-05
66	300	-5.341e-05	-5.121e-05	-5.307e-05	-2.898e-05	-2.324e-05	-2.770e-05	-4.098e-05	-4.449e-05	-2.790e-05	-3.406e-05
67											
68	305	-5.811e-05	-5.612e-05	-6.462e-05	-3.847e-05	-3.066e-05	-3.611e-05	-4.893e-05	-5.109e-05	-3.541e-05	-4.249e-05
69	310	-6.974e-05	-6.227e-05	-8.365e-05	-4.167e-05	-3.492e-05	-4.132e-05	-5.454e-05	-5.052e-05	-4.227e-05	-4.435e-05
70	315	-7.162e-05	-7.087e-05	-1.021e-04	-5.121e-05	-3.655e-05	-4.460e-05	-6.573e-05	-5.916e-05	-4.780e-05	-5.344e-05

	T (C)	m³/m C1	m³/m C2	m³/m C3	m³/m C4	m³/m C5	m³/m C6	m³/m C7	m³/m C8	m³/m C9	m³/m C10
71	320	-9.148e-05	-8.076e-05	-9.291e-05	-5.509e-05	-3.925e-05	-5.050e-05	-7.538e-05	-6.387e-05	-5.745e-05	-6.438e-05
72	325	-9.811e-05	-9.498e-05	-1.095e-04	-5.836e-05	-4.727e-05	-5.902e-05	-8.511e-05	-6.269e-05	-6.784e-05	-6.996e-05
73											
74	330	-1.147e-04	-9.526e-05	-1.297e-04	-7.118e-05	-5.851e-05	-6.887e-05	-9.811e-05	-7.868e-05	-7.691e-05	-9.011e-05
75	335	-1.309e-04	-1.201e-04	-1.412e-04	-7.133e-05	-6.554e-05	-7.882e-05	-1.056e-04	-7.820e-05	-8.812e-05	-9.584e-05
76	340	-1.320e-04	-1.420e-04	-1.590e-04	-8.810e-05	-7.529e-05	-8.881e-05	-1.188e-04	-9.102e-05	-1.132e-04	-1.151e-04
77	345	-1.592e-04	-1.408e-04	-1.792e-04	-9.794e-05	-8.081e-05	-1.022e-04	-1.394e-04	-9.862e-05	-1.171e-04	-1.235e-04
78	350	-1.807e-04	-1.662e-04	-2.088e-04	-1.124e-04	-9.121e-05	-1.110e-04	-1.473e-04	-1.109e-04	-1.161e-04	-1.418e-04
79											
80	355	-2.050e-04	-1.576e-04	-2.270e-04	-1.141e-04	-1.028e-04	-1.312e-04	-1.741e-04	-1.234e-04	-1.445e-04	-1.561e-04
81	360	-2.297e-04	-1.653e-04	-2.555e-04	-1.365e-04	-1.123e-04	-1.410e-04	-1.873e-04	-1.252e-04	-1.662e-04	-1.719e-04
82	365	-2.404e-04	-1.592e-04	-2.867e-04	-1.416e-04	-2.460e-04	-1.583e-04	-2.115e-04	-1.338e-04	-1.847e-04	-1.985e-04
83	370	-2.714e-04	-1.505e-04	-3.274e-04	-1.428e-04	-2.073e-04	-1.798e-04	-2.336e-04	-1.575e-04	-2.050e-04	-2.206e-04
84	375	-3.089e-04	-1.244e-04	-3.611e-04	-1.428e-04	-1.684e-04	-2.071e-04	-2.545e-04	-1.733e-04	-2.262e-04	-2.476e-04
85											
86	380	-3.460e-04	-9.745e-05	-3.901e-04	-1.493e-04	-1.780e-04	-2.131e-04	-2.809e-04	-1.934e-04	-2.552e-04	-2.617e-04
87	385	-3.844e-04	-8.111e-05	-4.245e-04	-1.533e-04	-1.945e-04	-2.513e-04	-3.106e-04	-2.091e-04	-2.863e-04	-2.743e-04
88	390	-4.284e-04	-7.553e-05	-4.710e-04	-1.646e-04	-2.051e-04	-2.622e-04	-3.324e-04	-2.355e-04	-3.226e-04	-3.044e-04
89	395	-4.723e-04	-7.635e-05	-5.091e-04	-2.359e-04	-2.312e-04	-2.955e-04	-3.688e-04	-2.611e-04	-3.524e-04	-3.599e-04
90	400	-5.165e-04	-9.964e-05	-5.657e-04	-1.754e-04	-2.724e-04	-3.234e-04	-3.862e-04	-2.829e-04	-3.975e-04	-4.152e-04
91											
92	405	-5.668e-04	-1.090e-04	-6.183e-04	-1.635e-04	-2.854e-04	-3.563e-04	-4.335e-04	-3.012e-04	-4.349e-04	-4.463e-04
93	410	-6.231e-04	-1.392e-04	-6.797e-04	-1.609e-04	-3.410e-04	-3.895e-04	-4.654e-04	-3.408e-04	-4.878e-04	-5.158e-04
94	415	-6.879e-04	-1.750e-04	-7.369e-04	-1.384e-04	-3.736e-04	-4.304e-04	-4.903e-04	-3.728e-04	-5.506e-04	-5.709e-04
95	420	-7.745e-04	-2.134e-04	-8.234e-04	-1.315e-04	-4.245e-04	-4.641e-04	-5.015e-04	-4.176e-04	-6.047e-04	-6.118e-04
96	425	-8.601e-04	-2.862e-04	-8.885e-04	-1.527e-04	-4.713e-04	-5.252e-04	-5.140e-04	-4.567e-04	-6.782e-04	-6.824e-04
97											
98	430	-9.482e-04	-3.750e-04	-9.936e-04	-1.790e-04	-5.097e-04	-5.852e-04	-4.884e-04	-4.965e-04	-7.492e-04	-7.460e-04
99	435	-1.064e-03	-4.818e-04	-1.095e-03	-2.099e-04	-4.894e-04	-6.319e-04	-3.149e-04	-5.481e-04	-8.213e-04	-8.224e-04
100	440	-1.210e-03	-6.815e-04	-1.214e-03	-2.653e-04	-6.001e-04	-6.907e-04	-3.395e-04	-5.841e-04	-9.246e-04	-9.005e-04
101	445	-1.358e-03	-9.482e-04	-1.344e-03	-3.162e-04	-6.248e-04	-7.637e-04	-3.685e-04	-6.275e-04	-9.996e-04	-1.034e-03
102	450	-1.522e-03	-2.467e-03	-1.510e-03	-4.088e-04	-7.899e-04	-8.628e-04	-3.439e-04	-6.838e-04	-1.095e-03	-1.120e-03
103											
104	455	-1.720e-03	-2.859e-03	-1.663e-03	-5.092e-04	-8.704e-04	-9.291e-04	-3.691e-04	-7.351e-04	-1.184e-03	-1.241e-03
105	460	-1.916e-03	-2.006e-03	-1.858e-03	-6.254e-04	-9.905e-04	-1.013e-03	-3.841e-04	-7.859e-04	-1.212e-03	-1.939e-03

	T (C)	m³/m C1	m³/m C2	m³/m C3	m³/m C4	m³/m C5	m³/m C6	m³/m C7	m³/m C8	m³/m C9	m³/m C10
106	465	-2.018e-03	-2.148e-03	-2.073e-03	-8.514e-04	-1.190e-03	-1.100e-03	-4.534e-04	-8.428e-04	-1.118e-03	-1.171e-03
107	470	-1.861e-03	-1.979e-03	-2.224e-03	-1.230e-03	-1.170e-03	-1.157e-03	-4.893e-04	-8.429e-04	-2.224e-03	-6.661e-04
108	475	-2.173e-03	-1.765e-03	-2.333e-03	-1.205e-03	-1.050e-03	-1.197e-03	-5.677e-04	-8.501e-04	-1.049e-03	-7.770e-04
109											
110	480	-2.420e-03	-1.542e-03	-2.332e-03	-1.502e-03	-1.100e-03	-1.222e-03	-7.806e-04	-8.561e-04	-8.282e-04	-6.345e-04
111	485	-2.393e-03	-1.308e-03	-2.270e-03	-1.642e-03	-1.165e-03	-1.194e-03	-1.091e-03	-8.273e-04	-6.305e-04	-6.155e-04
112	490	-2.502e-03	-1.066e-03	-2.249e-03	-1.528e-03	-3.724e-03	-1.152e-03	-1.244e-03	-8.155e-04	-6.431e-04	-4.312e-04
113	495	-7.372e-03	-8.021e-04	-1.699e-03	-1.168e-03	-9.207e-04	-1.078e-03	-1.198e-03	-7.734e-04	-5.530e-04	-5.243e-04
114	500	-2.328e-03	-6.029e-04	-1.475e-03	-9.141e-04	-6.021e-04	-1.001e-03	-1.122e-03	-6.968e-04	-4.933e-04	-4.421e-04
115											
116	505	-9.217e-04	-6.024e-04	-1.267e-03	-7.444e-04	-5.416e-04	-8.936e-04	-9.882e-04	-6.434e-04	-4.565e-04	-4.090e-04
117	510	-7.240e-04	-4.008e-04	-1.103e-03	-6.499e-04	-4.104e-04	-7.537e-04	-1.043e-03	-5.609e-04	-4.009e-04	-3.865e-04
118	515	-6.115e-04	-3.783e-04	-9.353e-04	-5.632e-04	-3.578e-04	-5.493e-04	-1.002e-03	-3.712e-04	-3.471e-04	-3.000e-04
119	520	-5.170e-04	-3.433e-04	-7.365e-04	-4.922e-04	-3.065e-04	-2.421e-04	-8.830e-04	-2.447e-04	-2.864e-04	-2.474e-04
120	525	-4.075e-04	-3.975e-04	-6.118e-04	-4.081e-04	-2.811e-04	-2.339e-04	-7.331e-04	-2.221e-04	-2.598e-04	-2.243e-04
121											
122	530	-2.331e-04	-4.519e-04	-4.634e-04	-3.505e-04	-2.244e-04	-2.002e-04	-5.219e-04	-2.068e-04	-2.044e-04	-1.814e-04
123	535	-1.415e-04	-4.852e-04	-3.405e-04	-2.733e-04	-1.747e-04	-1.926e-04	-5.417e-04	-1.834e-04	-1.856e-04	-1.573e-04
124	540	-1.145e-04	-5.882e-04	-1.659e-04	-2.489e-04	-1.509e-04	-1.630e-04	-4.825e-04	-1.484e-04	-1.435e-04	-1.318e-04
125	545	-9.996e-05	-7.062e-04	-1.095e-04	-2.249e-04	-1.268e-04	-1.343e-04	-4.578e-04	-1.287e-04	-1.104e-04	-1.071e-04
126	550	-9.819e-05	-8.857e-04	-9.376e-05	-2.321e-04	-1.034e-04	-1.117e-04	-4.133e-04	-9.399e-05	-1.027e-04	-1.155e-04
127											
128	555	-1.049e-04	-1.038e-03	-6.194e-05	-2.599e-04	-8.818e-05	-6.241e-05	-3.759e-04	-7.376e-05	-9.622e-05	-1.079e-04
129	560	-6.870e-05	-1.267e-03	-9.423e-05	-3.135e-04	-7.696e-05	-7.485e-05	-2.970e-04	-7.737e-05	-9.240e-05	-1.151e-04
130	565	-7.747e-05	-1.504e-03	-9.651e-05	-4.131e-04	-6.466e-05	-6.336e-05	-2.654e-04	-8.097e-05	-1.050e-04	-1.156e-04
131	570	-9.281e-05	-1.748e-03	-4.152e-05	-5.256e-04	-7.209e-05	-4.663e-05	-2.279e-04	-7.658e-05	-1.094e-04	-1.357e-04
132	575	-1.235e-04	-2.002e-03	-5.548e-05	-6.582e-04	-6.492e-05	-6.619e-05	-1.960e-04	-6.987e-05	-1.152e-04	-1.255e-04
133											
134	580	-1.131e-04	-2.250e-03	-7.644e-05	-7.852e-04	-7.554e-05	-6.369e-05	-1.688e-04	-6.542e-05	-1.101e-04	-2.587e-04
135	585	-1.549e-04	-2.508e-03	-5.334e-05	-9.078e-04	-7.465e-05	-5.731e-05	-1.592e-04	-7.823e-05	-1.410e-04	-1.902e-04
136	590	-1.688e-04	-2.744e-03	-5.348e-05	-1.039e-03	-9.167e-05	-6.001e-05	-1.287e-04	-7.726e-05	-1.638e-04	
137	595	-1.939e-04	-2.981e-03	-7.219e-05	-1.116e-03	-8.871e-05	-6.929e-05	-1.070e-04	-7.281e-05	-1.927e-04	

APPENDIX 4

Rate of weight loss in H_2 flow from TGA.

	T (C)	m/m C1	m/m C2	m/m C3	m/m C4	m/m C5	m/m C6	m/m C7	m/m C8	m/m C9	m/m C10
1											
2	30	8.384e-05	-5.801e-05	-6.977e-05	-9.396e-05	-4.231e-05	-2.365e-05	-3.120e-05	-6.561e-05	-9.589e-05	-1.221e-04
3	35	3.155e-05	3.516e-06	-2.039e-04	1.083e-05	1.890e-05	1.838e-05	8.066e-06	5.921e-05	4.169e-06	1.566e-06
4	40	-5.202e-05	-1.231e-05	-9.943e-05	1.535e-05	-2.700e-06	4.201e-06	5.377e-07	2.490e-05	-2.502e-05	-2.194e-05
5	45	8.123e-05	4.103e-06	-3.997e-05	-9.024e-07	7.199e-06	1.103e-05	1.129e-05	3.576e-05	8.344e-06	-1.568e-06
6	50	6.355e-05	-1.758e-06	-4.207e-05	1.714e-05	1.800e-06	5.249e-06	4.838e-06	1.709e-05	-9.734e-06	-1.254e-05
7											
8	55	-4.021e-05	-2.344e-06	-1.969e-05	8.121e-08	8.997e-07	6.298e-06	4.300e-06	1.864e-05	-6.955e-06	-3.136e-06
9	60	-1.455e-04	-4.103e-06	-2.174e-05	-1.623e-05	-8.997e-07	4.722e-06	3.762e-06	9.315e-06	-8.347e-06	-1.098e-05
10	65	1.775e-05	4.102e-06	-1.700e-05	2.615e-05	4.498e-06	2.623e-06	4.299e-06	6.209e-06	-1.113e-05	-4.706e-06
11	70	4.693e-05	-1.172e-06	-1.633e-05	-2.797e-05	-8.996e-07	3.148e-06	4.298e-06	0.000e+00	-1.253e-05	-4.707e-06
12	75	-5.827e-05	5.862e-07	-1.497e-05	-1.173e-05	-8.995e-07	2.098e-06	4.835e-06	3.104e-06	-1.114e-05	-1.098e-05
13											
14	80	-6.364e-05	-1.758e-06	-1.974e-05	5.417e-06	3.598e-06	1.049e-06	4.297e-06	0.000e+00	-8.358e-06	-9.419e-06
15	85	-6.568e-05	-2.930e-06	-6.812e-07	-2.707e-06	-8.996e-07	1.574e-06	4.834e-06	0.000e+00	-1.254e-05	-1.414e-05
16	90	1.443e-04	-5.862e-07	-2.724e-06	-3.431e-05	-3.598e-06	1.049e-06	3.759e-06	0.000e+00	-1.254e-05	6.282e-06
17	95	-2.655e-04	-2.345e-06	-4.087e-06	-2.439e-05	-1.799e-06	-1.049e-06	4.832e-06	-4.656e-06	-8.365e-06	-4.713e-06
18	100	7.234e-05	-1.173e-06	-1.499e-05	-2.620e-05	0.000e+00	-5.245e-07	5.368e-06	0.000e+00	-6.973e-06	-6.283e-06
19											
20	105	-3.712e-05	2.345e-06	7.493e-06	2.078e-05	2.698e-06	1.049e-06	4.831e-06	0.000e+00	-1.116e-05	7.860e-06
21	110	-2.632e-05	-2.345e-06	-1.772e-05	-1.085e-05	0.000e+00	2.623e-06	5.903e-06	0.000e+00	-8.371e-06	-1.572e-06
22	115	1.134e-04	-2.345e-06	9.541e-06	-6.325e-06	-1.799e-06	3.147e-06	4.829e-06	3.104e-06	-5.582e-06	-1.572e-06
23	120	5.201e-05	-1.173e-06	-1.636e-05	-9.041e-07	0.000e+00	3.671e-06	4.828e-06	0.000e+00	-1.256e-05	-7.864e-06
24	125	4.918e-05	5.863e-07	-1.091e-05	-1.536e-05	0.000e+00	4.719e-06	5.364e-06	0.000e+00	-9.774e-06	-1.573e-06
25											
26	130	2.365e-05	2.345e-06	-2.455e-05	-1.085e-05	8.994e-07	5.243e-06	4.291e-06	-9.315e-06	-1.117e-05	-4.719e-06
27	135	8.653e-05	-5.862e-07	-6.819e-06	2.711e-06	2.697e-06	3.145e-06	3.754e-06	0.000e+00	-1.257e-05	-1.574e-06
28	140	6.723e-07	-5.863e-07	-8.189e-06	-2.350e-05	-1.799e-06	2.097e-06	3.217e-06	-7.764e-06	-8.386e-06	-1.573e-06
29	145	1.048e-04	-1.759e-06	-5.459e-06	2.713e-06	-2.698e-06	2.621e-06	1.072e-06	-4.659e-06	-1.258e-05	-4.721e-06
30	150	6.596e-05	-3.518e-06	-1.229e-05	-2.079e-05	8.995e-07	1.048e-06	3.217e-06	1.553e-06	-8.390e-06	-9.443e-06
31											
32	155	7.811e-05	-5.278e-06	-3.142e-05	-1.809e-06	-2.699e-06	1.572e-06	2.680e-06	-7.768e-06	-1.119e-05	-1.732e-05
33	160	1.142e-05	-5.865e-06	6.151e-06	-8.137e-06	-1.799e-06	3.144e-06	2.144e-06	-7.769e-06	-9.794e-06	0.000e+00
34	165	-3.493e-05	-4.693e-06	-1.572e-05	-2.532e-05	0.000e+00	2.096e-06	2.144e-06	-9.324e-06	-1.120e-05	-1.103e-05
35	170	2.823e-05	-3.520e-06	-8.891e-06	-1.448e-05	-3.599e-06	1.572e-06	2.144e-06	-6.218e-06	-1.260e-05	-9.453e-06

	T (C)	m/m C1	m/m C2	m/m C3	m/m C4	m/m C5	m/m C6	m/m C7	m/m C8	m/m C9	m/m C10
36	175	1.007e-05	-4.694e-06	-2.668e-05	-2.081e-05	-1.800e-06	1.572e-06	4.287e-06	-7.774e-06	-1.120e-05	-1.104e-05
37											
38	180	6.041e-06	-1.115e-05	1.574e-05	-1.901e-05	-1.800e-06	2.096e-06	4.287e-06	-9.330e-06	-1.261e-05	-1.261e-05
39	185	5.170e-05	-9.981e-06	-2.738e-06	-7.242e-06	-3.600e-06	5.239e-07	3.215e-06	-3.111e-06	-1.121e-05	-1.577e-06
40	190	2.011e-05	-9.982e-06	-2.260e-05	2.716e-06	-3.601e-06	5.239e-07	3.215e-06	-7.778e-06	-1.262e-05	-1.577e-06
41	195	-8.857e-05	-8.811e-06	1.096e-05	-2.264e-05	-4.502e-06	1.572e-06	1.072e-06	-1.089e-05	-1.262e-05	0.000e+00
42	200	1.199e-04	-5.288e-06	-4.110e-06	2.175e-05	-3.602e-06	5.240e-07	-1.607e-06	-9.340e-06	-1.123e-05	-6.312e-06
43											
44	205	6.120e-05	-9.993e-06	-2.124e-05	-3.624e-06	-7.206e-06	-1.572e-06	0.000e+00	-1.246e-05	-1.685e-05	-7.889e-06
45	210	9.515e-06	-4.116e-06	3.427e-06	-2.628e-05	-9.009e-07	0.000e+00	0.000e+00	-1.714e-05	-1.404e-05	-1.578e-06
46	215	-4.758e-06	-9.410e-06	-2.948e-05	1.270e-05	-7.209e-06	-1.572e-06	-2.679e-06	-2.027e-05	-1.686e-05	-3.157e-06
47	220	-2.718e-05	-9.413e-06	3.430e-06	-5.440e-06	-9.013e-06	-1.572e-06	-4.287e-06	-2.027e-05	-1.969e-05	-6.313e-06
48	225	6.793e-07	-1.471e-05	-2.608e-05	-2.085e-05	-1.443e-05	-3.669e-06	-2.144e-06	-2.653e-05	-2.392e-05	-4.737e-06
49											
50	230	-1.496e-05	-2.002e-05	-1.374e-06	-2.995e-05	-9.920e-06	-5.241e-06	-7.504e-06	-2.812e-05	-2.816e-05	-7.898e-06
51	235	-3.264e-05	-1.885e-05	-1.717e-05	-9.076e-07	-1.444e-05	-6.291e-06	-7.505e-06	-3.283e-05	-3.100e-05	-1.264e-05
52	240	-1.768e-05	-2.476e-05	-2.130e-05	-1.544e-05	-1.535e-05	-7.341e-06	-9.653e-06	-4.383e-05	-3.244e-05	-9.486e-06
53	245	-5.517e-05	-2.654e-05	-3.853e-05	-2.180e-05	-1.987e-05	-8.391e-06	-1.126e-05	-4.702e-05	-3.954e-05	-2.214e-05
54	250	-7.909e-05	-2.715e-05	-1.928e-05	-4.182e-05	-1.627e-05	-9.442e-06	-1.449e-05	-6.122e-05	-3.959e-05	-2.532e-05
55											
56	255	-2.521e-05	-4.017e-05	-4.204e-05	-2.731e-05	-2.533e-05	-9.970e-06	-1.772e-05	-6.606e-05	-5.381e-05	-2.851e-05
57	260	-7.305e-05	-4.259e-05	-1.103e-05	-3.460e-05	-3.077e-05	-1.312e-05	-2.095e-05	-7.881e-05	-5.815e-05	-3.646e-05
58	265	-6.844e-05	-4.679e-05	-2.968e-05	-3.919e-05	-4.169e-05	-1.575e-05	-2.526e-05	-8.532e-05	-6.536e-05	-4.763e-05
59	270	-5.001e-05	-5.458e-05	-5.529e-05	-6.208e-05	-4.355e-05	-1.944e-05	-3.228e-05	-1.062e-04	-7.262e-05	-4.610e-05
60	275	-3.638e-05	-6.477e-05	-2.699e-05	-3.290e-05	-5.360e-05	-2.313e-05	-3.824e-05	-1.144e-04	-8.421e-05	-5.255e-05
61											
62	280	-9.898e-05	-7.323e-05	-7.001e-05	-6.040e-05	-5.825e-05	-2.631e-05	-4.313e-05	-1.276e-04	-9.589e-05	-7.659e-05
63	285	-9.502e-05	-7.996e-05	-6.113e-05	-8.625e-05	-6.565e-05	-3.160e-05	-5.076e-05	-1.458e-04	-1.120e-04	-9.117e-05
64	290	-9.455e-05	-7.834e-05	-7.864e-05	-6.342e-05	-7.401e-05	-3.848e-05	-6.003e-05	-1.609e-04	-1.282e-04	-9.625e-05
65	295	-1.213e-04	-1.146e-04	-8.441e-05	-9.029e-05	-8.427e-05	-4.592e-05	-6.936e-05	-1.828e-04	-1.447e-04	-1.175e-04
66	300	-1.606e-04	-1.162e-04	-1.162e-04	-1.211e-04	-1.038e-04	-5.074e-05	-7.929e-05	-2.050e-04	-1.628e-04	-1.390e-04
67											
68	305	-9.210e-05	-1.311e-04	-9.687e-05	-1.020e-04	-1.115e-04	-5.930e-05	-9.256e-05	-2.260e-04	-1.870e-04	-1.574e-04
69	310	-1.796e-04	-1.644e-04	-1.296e-04	-1.443e-04	-1.304e-04	-7.003e-05	-1.076e-04	-2.556e-04	-2.087e-04	-1.762e-04
70	315	-2.627e-04	-1.775e-04	-1.584e-04	-1.712e-04	-1.477e-04	-8.135e-05	-1.217e-04	-2.777e-04	-2.322e-04	-1.952e-04

	T (C)	m/m C1	m/m C2	m/m C3	m/m C4	m/m C5	m/m C6	m/m C7	m/m C8	m/m C9	m/m C10
71	320	-1.825e-04	-1.704e-04	-1.585e-04	-1.625e-04	-1.623e-04	-9.436e-05	-1.397e-04	-3.120e-04	-2.623e-04	-2.180e-04
72	325	-1.982e-04	-2.208e-04	-2.022e-04	-1.918e-04	-1.867e-04	-1.096e-04	-1.569e-04	-3.439e-04	-2.855e-04	-2.545e-04
73											
74	330	-2.439e-04	-2.261e-04	-2.223e-04	-2.445e-04	-2.085e-04	-1.234e-04	-1.788e-04	-3.802e-04	-3.169e-04	-2.834e-04
75	335	-2.450e-04	-2.702e-04	-2.468e-04	-2.214e-04	-2.327e-04	-1.395e-04	-2.011e-04	-4.177e-04	-3.553e-04	-3.165e-04
76	340	-3.823e-04	-2.705e-04	-2.838e-04	-2.693e-04	-2.554e-04	-1.564e-04	-2.248e-04	-4.529e-04	-3.918e-04	-3.487e-04
77	345	-3.372e-04	-3.097e-04	-2.944e-04	-2.979e-04	-2.787e-04	-1.735e-04	-2.525e-04	-4.789e-04	-4.280e-04	-3.925e-04
78	350	-4.663e-04	-3.164e-04	-3.522e-04	-3.263e-04	-3.026e-04	-1.958e-04	-2.776e-04	-5.150e-04	-4.640e-04	-4.216e-04
79											
80	355	-5.191e-04	-3.219e-04	-3.523e-04	-3.723e-04	-3.311e-04	-2.151e-04	-3.074e-04	-5.565e-04	-5.030e-04	-4.645e-04
81	360	-5.778e-04	-3.640e-04	-4.186e-04	-4.111e-04	-3.604e-04	-2.388e-04	-3.371e-04	-5.847e-04	-5.387e-04	-5.018e-04
82	365	-5.552e-04	-3.487e-04	-4.652e-04	-4.159e-04	-3.862e-04	-2.590e-04	-3.689e-04	-6.242e-04	-5.779e-04	-5.462e-04
83	370	-6.358e-04	-4.164e-04	-4.966e-04	-4.576e-04	-4.187e-04	-2.842e-04	-4.035e-04	-6.734e-04	-6.137e-04	-5.815e-04
84	375	-6.630e-04	-4.232e-04	-5.618e-04	-5.090e-04	-4.415e-04	-3.140e-04	-4.351e-04	-6.929e-04	-6.549e-04	-6.281e-04
85											
86	380	-6.648e-04	-4.963e-04	-5.723e-04	-5.577e-04	-4.736e-04	-3.401e-04	-4.759e-04	-7.426e-04	-6.892e-04	-6.518e-04
87	385	-8.149e-04	-5.222e-04	-6.604e-04	-5.539e-04	-4.987e-04	-3.698e-04	-5.127e-04	-7.804e-04	-7.403e-04	-6.947e-04
88	390	-8.573e-04	-5.847e-04	-6.950e-04	-6.077e-04	-5.236e-04	-4.057e-04	-5.555e-04	-8.185e-04	-7.663e-04	-7.400e-04
89	395	-9.180e-04	-6.316e-04	-7.737e-04	-6.735e-04	-5.573e-04	-4.346e-04	-5.959e-04	-8.460e-04	-7.995e-04	-7.860e-04
90	400	-9.561e-04	-6.667e-04	-8.468e-04	-6.765e-04	-5.958e-04	-4.701e-04	-6.410e-04	-8.906e-04	-8.546e-04	-8.284e-04
91											
92	405	-1.115e-03	-7.591e-04	-8.689e-04	-7.284e-04	-6.295e-04	-5.039e-04	-6.879e-04	-9.174e-04	-9.053e-04	-8.934e-04
93	410	-1.050e-03	-7.916e-04	-9.656e-04	-7.709e-04	-6.787e-04	-5.447e-04	-7.518e-04	-9.179e-04	-9.579e-04	-9.542e-04
94	415	-1.245e-03	-8.998e-04	-1.060e-03	-8.370e-04	-7.302e-04	-5.818e-04	-8.049e-04	-9.857e-04	-1.018e-03	-9.918e-04
95	420	-1.294e-03	-9.884e-04	-1.096e-03	-8.487e-04	-7.621e-04	-6.258e-04	-8.639e-04	-1.031e-03	-1.057e-03	-1.043e-03
96	425	-1.413e-03	-1.101e-03	-1.224e-03	-8.951e-04	-7.976e-04	-6.708e-04	-9.261e-04	-1.077e-03	-1.119e-03	-1.092e-03
97											
98	430	-1.500e-03	-1.225e-03	-1.300e-03	-9.342e-04	-8.712e-04	-7.311e-04	-9.916e-04	-1.102e-03	-1.191e-03	-1.154e-03
99	435	-1.625e-03	-1.307e-03	-1.415e-03	-9.849e-04	-9.277e-04	-7.712e-04	-1.047e-03	-1.154e-03	-1.304e-03	-1.241e-03
100	440	-1.740e-03	-1.499e-03	-1.554e-03	-1.086e-03	-9.920e-04	-8.340e-04	-1.098e-03	-1.195e-03	-1.382e-03	-1.322e-03
101	445	-1.900e-03	-1.653e-03	-1.670e-03	-1.090e-03	-1.097e-03	-9.151e-04	-1.143e-03	-1.225e-03	-1.445e-03	-1.388e-03
102	450	-2.270e-03	-2.185e-03	-1.794e-03	-1.205e-03	-1.166e-03	-9.927e-04	-1.235e-03	-1.249e-03	-1.533e-03	-1.463e-03
103											
104	455	-2.207e-03	-2.698e-03	-1.942e-03	-1.315e-03	-1.219e-03	-1.066e-03	-1.293e-03	-1.292e-03	-1.624e-03	-1.540e-03
105	460	-2.277e-03	-2.987e-03	-2.152e-03	-1.417e-03	-1.654e-03	-1.140e-03	-1.383e-03	-1.316e-03	-1.642e-03	-1.587e-03

	T (C)	m/m C1	m/m C2	m/m C3	m/m C4	m/m C5	m/m C6	m/m C7	m/m C8	m/m C9	m/m C10
106	465	-2.307e-03	-3.374e-03	-2.145e-03	-1.377e-03	-3.088e-03	-1.346e-03	-1.439e-03	-1.339e-03	-1.640e-03	-1.536e-03
107	470	-2.376e-03	-3.404e-03	-2.209e-03	-1.512e-03	-2.500e-03	-1.397e-03	-1.546e-03	-1.372e-03	-1.595e-03	-1.426e-03
108	475	-2.379e-03	-3.219e-03	-2.138e-03	-1.573e-03	-1.974e-03	-1.976e-03	-1.679e-03	-1.354e-03	-1.515e-03	-1.367e-03
109											
110	480	-2.505e-03	-2.820e-03	-2.082e-03	-1.604e-03	-1.733e-03	-1.655e-03	-1.767e-03	-1.335e-03	-1.435e-03	-1.979e-03
111	485	-2.173e-03	-2.154e-03	-1.811e-03	-1.526e-03	-1.449e-03	-1.636e-03	-2.421e-03	-1.287e-03	-1.286e-03	-2.986e-03
112	490	-2.404e-03	-1.848e-03	-1.687e-03	-1.504e-03	-1.136e-03	-3.300e-03	-2.332e-03	-1.236e-03	-1.097e-03	-1.473e-03
113	495	-4.071e-03	-1.556e-03	-1.506e-03	-1.410e-03	-1.063e-03	-1.639e-03	-2.035e-03	-1.154e-03	-9.445e-04	-1.073e-03
114	500	-2.629e-03	-1.186e-03	-1.333e-03	-1.321e-03	-7.626e-04	-1.121e-03	-1.098e-03	-1.067e-03	-8.368e-04	-7.759e-04
115											
116	505	-2.173e-03	-1.072e-03	-1.109e-03	-1.234e-03	-6.148e-04	-1.160e-03	-1.249e-03	-9.739e-04	-7.073e-04	-5.819e-04
117	510	-1.497e-03	-8.718e-04	-9.437e-04	-1.056e-03	-5.011e-04	-9.511e-04	-1.018e-03	-8.816e-04	-5.910e-04	-4.568e-04
118	515	-7.306e-04	-7.732e-04	-7.849e-04	-1.012e-03	-4.226e-04	-6.215e-04	-6.175e-04	-8.010e-04	-4.814e-04	-3.313e-04
119	520	-9.353e-04	-4.262e-04	-5.354e-04	-7.822e-04	-3.562e-04	-5.251e-04	-4.476e-04	-5.263e-04	-3.939e-04	-2.482e-04
120	525	-5.528e-04	-4.169e-04	-5.584e-04	-5.838e-04	-2.903e-04	-3.896e-04	-3.370e-04	-4.527e-04	-3.930e-04	-1.682e-04
121											
122	530	-5.921e-04	-2.257e-04	-3.209e-04	-4.564e-04	-2.305e-04	-3.155e-04	-2.818e-04	-3.811e-04	-2.600e-04	-1.434e-04
123	535	-5.286e-04	-2.690e-04	-3.670e-04	-4.543e-04	-1.876e-04	-2.586e-04	-2.217e-04	-3.018e-04	-1.975e-04	-1.285e-04
124	540	-2.194e-04	-1.794e-04	-2.634e-04	-2.185e-04	-1.493e-04	-2.005e-04	-2.029e-04	-2.730e-04	-1.663e-04	-9.799e-05
125	545	1.454e-04	-1.672e-04	-1.691e-04	-2.398e-04	-1.262e-04	-1.778e-04	-1.598e-04	-2.008e-04	-1.531e-04	-9.829e-05
126	550	-3.705e-04	-1.367e-04	-2.238e-04	-2.073e-04	-1.214e-04	-1.365e-04	-1.434e-04	-1.647e-04	-1.305e-04	-9.336e-05
127											
128	555	-3.642e-04	-1.687e-04	-1.056e-04	-2.284e-04	-1.032e-04	-1.144e-04	-1.268e-04	-1.387e-04	-1.122e-04	-6.234e-05
129	560	-4.828e-04	-2.646e-05	-1.416e-04	-1.236e-04	-9.559e-05	-8.783e-05	-9.290e-05	-1.125e-04	-9.850e-05	-7.295e-05
130	565	-4.521e-05	-1.247e-04	-1.830e-04	-1.238e-04	-9.854e-05	-7.669e-05	-9.315e-05	-9.130e-05	-9.878e-05	-1.095e-04
131	570	-1.168e-04	-1.330e-05	-4.385e-05	-1.762e-04	-9.079e-05	-6.974e-05	-7.956e-05	-8.616e-05	-9.434e-05	-8.896e-05
132	575	9.091e-05	-5.600e-05	-1.403e-04	-1.249e-04	-7.764e-05	-5.846e-05	-7.107e-05	-9.179e-05	-1.088e-04	-8.395e-05
133											
134	580	6.683e-05	-4.544e-05	-1.406e-04	-1.077e-04	-8.861e-05	-5.999e-05	-6.774e-05	-9.209e-05	-1.044e-04	-9.459e-05
135	585	-2.813e-04	-1.288e-04	-2.214e-05	-1.663e-04	-8.885e-05	-4.721e-05	-8.528e-05	-6.515e-05	-1.048e-04	-8.425e-05
136	590	-5.040e-05	-9.938e-05	-1.388e-04	-9.968e-05	-9.179e-05	-5.156e-05	-6.453e-05	-7.073e-05	-1.051e-04	-1.004e-04
137	595	-2.176e-04	-7.804e-05	-1.140e-04	-8.509e-05	-9.751e-05	-6.169e-05	-5.941e-05	-8.724e-05	-1.054e-04	-9.004e-05

APPENDIX 5

ESR parameters for samples C1-C10 in N₂ flow
and H₂ flow respectively.

	T(°C)	N-no corr (/g)	m from TG	N-corr (/g)	del H (G)	g
1	25.0	2.000e+17	1.000	2.000e+17	6.50	2.00160
2	70.0	2.050e+17	1.000	2.050e+17	6.60	2.00165
3	92.0	2.080e+17	1.001	2.077e+17	6.73	2.00150
4	112.5	3.433e+17	1.001	3.431e+17	6.93	2.00150
5	155.0	8.700e+17	0.999	8.705e+17	8.60	2.00200
6						
7	177.0	9.680e+17	0.998	9.695e+17	10.13	2.00250
8	191.0	1.188e+18	0.998	1.191e+18	9.26	2.00250
9	206.0	1.724e+18	0.997	1.729e+18	10.73	2.00235
10	222.0	1.421e+18	0.997	1.426e+18	11.06	2.00214
11	233.0	1.835e+18	0.996	1.843e+18	11.33	2.00211
12						
13	251.0	2.414e+18	0.994	2.428e+18	10.93	2.00193
14	259.0	2.177e+18	0.993	2.191e+18	8.80	2.00192
15	271.0	2.616e+18	0.992	2.637e+18	8.27	2.00180
16	280.0	2.756e+18	0.990	2.783e+18	8.27	2.00177
17	296.0	3.025e+18	0.987	3.036e+18	7.26	2.00163
18						
19	311.0	3.169e+18	0.982	3.228e+18	7.27	2.00155
20	320.0	2.967e+18	0.978	3.035e+18	6.67	2.00150
21	341.0	2.857e+18	0.964	2.965e+18	6.87	2.00260
22	363.0	3.025e+18	0.940	3.219e+18	6.13	2.00250
23	374.0	2.805e+18	0.923	3.038e+18	5.93	2.00170
24						
25	388.0	2.947e+18	0.896	3.289e+18	5.67	2.00300
26	399.0	3.360e+18	0.869	3.864e+18	5.87	2.00300
27	411.0	5.160e+18	0.834	6.185e+18	4.60	2.00330
28	429.0	7.405e+18	0.767	9.655e+18	4.30	2.00250
29	444.0	8.783e+18	0.694	1.266e+19	4.73	2.00185
30						
31	459.0	1.169e+19	0.601	1.943e+19	4.20	2.00380
32	475.0	1.511e+19	0.498	3.033e+19	3.60	2.00270
33	492.0	1.999e+19	0.385	5.198e+19	2.60	2.00420
34	503.0	2.430e+19	0.297	8.179e+19	2.27	2.00330
35	518.0	2.642e+19	0.278	9.515e+19	1.73	2.00350

	T (°C)	N-no corr. (/g)	m from TG	N-corr (/g)	g	del H (G)
1	25.0	1.5700e+17	1.000	1.5700e+17	2.00154	7.13
2	68.0	1.0300e+17	1.009	1.0208e+17	2.00145	7.20
3	81.0	2.8230e+17	1.015	2.7813e+17	2.00230	8.06
4	100.0	2.9980e+17	1.017	2.9490e+17	2.00174	7.93
5	113.0	3.6600e+17	1.018	3.5946e+17	2.00196	7.73
6						
7	135.0	7.8540e+17	1.017	7.7258e+17	2.00230	8.86
8	153.0	1.0427e+18	1.021	1.0214e+18	2.00210	9.53
9	175.0	1.5070e+18	1.023	1.4725e+18	2.00230	9.80
10	190.0	1.5620e+18	1.025	1.5238e+18	2.00216	9.80
11						
12	200.0	1.6437e+18	1.026	1.6025e+18	2.00210	10.13
13	215.0	1.7793e+18	1.011	1.7598e+18	2.00197	9.70
14	232.0	1.8933e+18	1.011	1.8733e+18	2.00180	9.30
15	244.0	2.0584e+18	1.009	2.0392e+18	2.00190	8.30
16	251.0	2.4420e+18	1.008	2.4226e+18	2.00195	9.00
17						
18	277.0	2.6600e+18	1.002	2.6544e+18	2.00266	8.00
19	299.0	2.8800e+18	0.989	2.9115e+18	2.00205	8.00
20	313.0	3.0580e+18	0.976	3.1340e+18	2.00185	6.85
21	316.0	2.7340e+18	0.972	2.8126e+18	2.00180	6.86
22	329.0	2.2290e+18	0.954	2.3364e+18	2.00175	7.13
23						
24	341.0	2.1913e+18	0.934	2.3453e+18	2.00168	7.53
25	359.0	3.0122e+18	0.890	3.3829e+18	2.00155	6.30
26	370.0	2.7386e+18	0.858	3.1908e+18	2.00142	6.00
27	390.0	3.0152e+18	0.784	3.8459e+18	2.00174	6.00
28	405.0	4.2883e+18	0.718	5.9709e+18	2.00170	5.50
29						
30	415.0	5.2525e+18	0.672	7.8188e+18	2.00155	4.73
31	425.0	8.0223e+18	0.621	1.2909e+19	2.00181	4.40
32	441.0	7.9290e+18	0.531	1.4922e+19	2.00184	4.66
33	454.0	1.1367e+19	0.453	2.5082e+19	2.00173	3.60
34	467.0	1.3241e+19	0.374	3.5425e+19	2.00187	3.00
35						
36	476.0	1.7297e+19	0.329	5.2499e+19	2.00250	2.47
37	484.0	1.9591e+19	0.292	6.7123e+19	2.00240	2.27
38	495.0	1.9062e+19	0.239	7.9911e+19	2.00160	2.00
39	510.0	2.0780e+19	0.196	1.0576e+20	2.00380	2.13

	T(°)	N-no crr (/g)	m from TG	N-crr (/g)	g	del H (G)
1	25.0	3.300e+17	1.000	3.300e+17	2.00196	6.73
2	65.0	1.606e+17	0.999	1.607e+17	2.00186	6.13
3	84.0	2.810e+17	0.998	2.815e+17	2.00143	8.80
4	95.5	3.716e+17	0.998	3.725e+17	2.00215	7.20
5	107.0	5.263e+17	0.997	5.279e+17	2.00171	5.13
6						
7	125.0	1.135e+18	0.996	1.139e+18	2.00230	8.07
8	140.0	1.449e+18	0.996	1.455e+18	2.00217	9.20
9	156.0	1.064e+18	0.995	1.069e+18	2.00213	8.80
10	165.0	1.143e+18	0.995	1.149e+18	2.00212	9.40
11	173.0	1.011e+18	0.995	1.017e+18	2.00210	9.47
12						
13	184.0	1.053e+18	0.994	1.060e+18	2.00217	10.00
14	204.0	1.118e+18	0.993	1.126e+18	2.00220	9.87
15	219.0	1.373e+18	0.992	1.384e+18	2.00214	10.00
16	230.0	1.205e+18	0.991	1.216e+18	2.00206	8.80
17	246.0	1.943e+18	0.990	1.963e+18	2.00196	7.13
18						
19	256.0	2.036e+18	0.989	2.059e+18	2.00185	7.53
20	275.0	2.367e+18	0.986	2.400e+18	2.00175	7.06
21	291.5	2.335e+18	0.983	2.375e+18	2.00153	7.06
22	310.0	3.657e+18	0.977	3.742e+18	2.00123	6.07
23	322.0	4.111e+18	0.972	4.230e+18	2.00110	6.40
24						
25	339.0	3.652e+18	0.962	3.798e+18	2.00212	6.73
26	353.0	4.052e+18	0.945	4.286e+18	2.00197	5.33
27	364.0	5.822e+18	0.940	6.193e+18	2.00216	6.80
28	377.0	5.962e+18	0.929	6.415e+18	2.00180	6.00
29	388.0	5.465e+18	0.924	5.916e+18	2.00181	6.00
30						
31	401.0	6.266e+18	0.917	6.834e+18	2.00165	5.26
32	413.0	9.759e+18	0.910	1.073e+19	2.00160	4.93
33	426.0	1.167e+19	0.894	1.305e+19	2.00160	4.33
34	440.0	1.626e+19	0.861	1.888e+19	2.00157	4.93
35	456.0	1.527e+19	0.719	2.124e+19	2.00150	4.00
36						
37	470.0	2.319e+19	0.604	3.841e+19	2.00190	3.27
38	485.0	2.699e+19	0.521	5.185e+19	2.00300	2.53
39	503.0	3.010e+19	0.473	6.361e+19	2.00320	2.00

	T(°C)	N-no corr (kg)	m from TG	N corr (kg)	g	del H (G)
1	25.0	1.970e+17	1.000	1.9700e+17	2.00240	7.53
2	61.0	2.690e+17	1.000	2.6906e+17	2.00230	7.00
3	76.0	2.573e+17	1.000	2.5738e+17	2.00213	7.30
4	90.0	2.832e+17	1.000	2.8333e+17	2.00180	6.80
5	99.0	2.970e+17	0.999	2.9716e+17	2.00176	6.13
6						
7	115.0	4.903e+17	1.000	4.9050e+17	2.00141	8.00
8	132.0	4.820e+17	1.000	4.8223e+17	2.00126	7.67
9	153.0	1.041e+18	0.999	1.0419e+18	2.00153	9.99
10	164.0	1.275e+18	0.999	1.2764e+18	2.00153	10.20
11	177.0	1.312e+18	0.999	1.3143e+18	2.00178	8.67
12						
13	198.0	1.302e+18	0.997	1.3053e+18	2.00165	10.30
14	207.0	1.537e+18	0.997	1.5418e+18	2.00172	11.70
15	220.0	1.575e+18	0.996	1.5813e+18	2.00160	7.27
16	232.0	2.207e+18	0.995	2.2177e+18	2.00153	11.60
17	248.0	2.266e+18	0.993	2.2816e+18	2.00129	9.47
18						
19	264.0	2.625e+18	0.990	2.6526e+18	2.00159	6.13
20	293.0	3.288e+18	0.978	3.3620e+18	2.00142	7.00
21	306.0	3.979e+18	0.969	4.1063e+18	2.00167	8.00
22	323.0	3.556e+18	0.952	3.7340e+18	2.00156	6.53
23	341.0	4.182e+18	0.928	4.5084e+18	2.00146	7.26
24						
25	349.0	4.332e+18	0.915	4.7368e+18	2.00154	6.86
26	358.0	3.870e+18	0.917	4.2212e+18	2.00157	6.60
27	371.0	3.970e+18	0.873	4.5475e+18	2.00130	6.60
28	389.0	3.746e+18	0.867	4.3223e+18	2.00300	6.26
29	414.0	5.825e+18	0.745	7.8200e+18	2.00144	5.20
30						
31	429.0	8.930e+18	0.679	1.3150e+19	2.00140	4.47
32	440.0	1.191e+19	0.621	1.9169e+19	2.00129	4.20
33	455.0	1.570e+19	0.522	3.0101e+19	2.00126	4.40
34	471.0	1.483e+19	0.386	3.8445e+19	2.00121	3.93
35	483.0	2.049e+19	0.312	6.5604e+19	2.00110	3.13
36						
37	495.0	2.603e+19	0.272	9.5846e+19	2.00100	2.53
38	510.0	2.918e+19	0.244	1.1960e+20	2.00181	2.13

	T(°C)	N-no cr (g)	m from TG	N-cr (g)	g	del H (G)
1	25.0	1.237e+17	1.000	1.237e+17	2.00172	7.13
2	71.0	1.590e+17	0.999	1.591e+17	2.00068	7.13
3	98.0	2.640e+17	0.998	2.646e+17	2.00126	8.66
4	112.0	3.450e+17	0.997	3.459e+17	2.00120	8.67
5	143.0	9.760e+17	0.996	9.797e+17	2.00150	8.53
6						
7	156.0	7.342e+17	0.996	7.374e+17	2.00130	7.33
8	170.0	7.823e+17	0.995	7.865e+17	2.00210	8.46
9	193.0	6.223e+17	0.993	6.266e+17	2.00170	8.26
10	207.0	4.734e+17	0.992	4.772e+17	2.00210	10.98
11	226.0	4.956e+17	0.990	5.004e+17	2.00149	10.33
12						
13	238.0	5.499e+17	0.989	5.558e+17	2.00141	9.93
14	257.0	6.279e+17	0.987	6.361e+17	2.00130	8.73
15	267.0	6.720e+17	0.986	6.818e+17	2.00136	9.30
16	281.0	8.508e+17	0.983	8.654e+17	2.00153	9.33
17	293.0	7.730e+17	0.980	7.886e+17	2.00150	8.99
18						
19	311.0	1.150e+18	0.973	1.181e+18	2.00175	8.00
20	322.0	1.104e+18	0.968	1.141e+18	2.00166	7.80
21	342.0	1.093e+18	0.951	1.149e+18	2.00158	7.67
22	361.0	1.144e+18	0.929	1.231e+18	2.00139	7.33
23	371.0	1.152e+18	0.913	1.262e+18	2.00133	6.80
24						
25	387.0	1.145e+18	0.880	1.300e+18	2.00190	6.86
26	401.0	1.018e+18	0.844	1.207e+18	2.00180	6.20
27	412.0	1.258e+18	0.809	1.555e+18	2.00175	5.93
28	426.0	1.635e+18	0.757	2.162e+18	2.00156	5.47
29	448.0	2.224e+18	0.650	3.422e+18	2.00184	4.60
30						
31	467.0	3.193e+18	0.531	6.010e+18	2.00174	4.67
32	487.0	5.212e+18	0.404	1.290e+19	2.00180	4.46
33	501.0	6.672e+18	0.346	1.926e+19	2.00165	6.87
34	513.0	8.136e+18	0.318	2.561e+19	2.00200	2.87
35	528.0	1.104e+19	0.297	3.719e+19	2.00191	2.20

	T(°C)	N-no crr (g)	m from TG	N-crr (g)	g	del H (G)
1	25.0	3.230e+17	1.000	3.230e+17		5.72
2	64.0	2.329e+17	0.987	2.359e+17		9.30
3	99.0	2.754e+17	0.985	2.796e+17	2.00120	5.92
4	116.0	3.990e+17	0.984	4.054e+17	2.00179	8.72
5	133.0	5.670e+17	0.984	5.763e+17	2.00160	9.39
6						
7	152.0	8.559e+17	0.982	8.713e+17	2.00235	9.26
8	167.0	1.321e+18	0.981	1.346e+18	2.00185	8.53
9	184.0	9.223e+17	0.980	9.410e+17	2.00240	9.93
10	198.0	7.180e+17	0.979	7.330e+17	2.00200	8.40
11	208.0	5.177e+17	0.979	5.289e+17	2.00210	10.50
12						
13	226.0	7.101e+17	0.977	7.266e+17	2.00162	6.73
14	243.0	6.368e+17	0.975	6.540e+17	2.00157	7.40
15	253.0	6.950e+17	0.974	7.136e+17	2.00110	11.40
16	258.0	7.992e+17	0.973	8.212e+17	2.00100	6.53
17	283.0	1.077e+18	0.967	1.114e+18	2.00150	9.13
18						
19	291.0	1.323e+18	0.964	1.373e+18	2.00140	7.73
20	304.0	9.926e+17	0.956	1.038e+18	2.00140	6.87
21	315.0	1.183e+18	0.948	1.248e+18	2.00120	7.26
22	325.0	1.229e+18	0.939	1.309e+18	2.00175	7.00
23	342.0	1.400e+18	0.916	1.528e+18	2.00165	6.87
24						
25	363.0	1.423e+18	0.916	1.553e+18	2.00140	6.73
26	377.0	1.425e+18	0.837	1.703e+18	2.00130	9.07
27	395.0	1.529e+18	0.782	1.955e+18	2.00110	6.86
28	414.0	2.007e+18	0.707	2.839e+18	2.00095	5.13
29	428.0	2.699e+18	0.642	4.202e+18	2.00219	5.13
30						
31	442.0	2.641e+18	0.571	4.629e+18	2.00187	4.20
32	449.5	3.032e+18	0.526	5.767e+18	2.00072	5.26
33	467.0	4.852e+18	0.427	1.136e+19	2.00180	3.53
34	489.0	6.760e+18	0.327	2.069e+19	2.00165	2.67
35	499.0	8.013e+18	0.298	2.690e+19	2.00184	2.47
36						
37	508.0	8.755e+18	0.280	3.125e+19	2.00168	2.13
38	520.0	8.587e+18	0.264	3.248e+19	2.00160	2.07

	T(°C)	N-no crr (g)	m from TG	N-crr (g)	g	del H (G)
1	25.0	3.697e+17	1.000	3.697e+17		5.12
2	58.0	5.670e+17	0.999	5.676e+17		5.70
3	77.2	4.619e+17	0.998	4.628e+17	2.00250	10.80
4	91.0	1.124e+18	0.997	1.127e+18	2.00100	10.33
5	106.0	1.214e+18	0.996	1.219e+18	2.00182	9.80
6						
7	118.0	1.740e+18	0.996	1.747e+18	2.00175	10.72
8	135.0	2.253e+18	0.995	2.265e+18	2.00170	11.78
9	144.0	4.065e+18	0.995	4.086e+18	2.00220	9.45
10	164.0	4.810e+18	0.994	4.838e+18	2.00130	9.86
11	178.0	4.808e+18	0.994	4.839e+18	2.00210	9.85
12						
13	191.5	4.873e+18	0.993	4.909e+18	2.00200	10.26
14	201.0	4.987e+18	0.993	5.025e+18	2.00160	9.66
15	214.0	5.548e+18	0.992	5.594e+18	2.00160	8.86
16	231.0	5.798e+18	0.991	5.852e+18	2.00167	7.92
17	246.0	5.645e+18	0.990	5.703e+18	2.00140	7.06
18						
19	253.0	5.579e+18	0.989	5.639e+18	2.00170	6.67
20	267.5	5.713e+18	0.988	5.782e+18	2.00163	6.40
21	289.0	6.441e+18	0.985	6.536e+18	2.00147	6.80
22	310.0	4.847e+18	0.982	4.939e+18	2.00130	5.47
23	319.0	3.696e+18	0.978	3.778e+18	2.00128	5.33
24						
25	325.0	3.899e+18	0.977	3.991e+18	2.00120	6.67
26	337.0	4.324e+18	0.972	4.448e+18	2.00160	6.20
27	345.0	4.859e+18	0.968	5.019e+18	2.00150	5.73
28	360.0	5.510e+18	0.958	5.749e+18	2.00157	6.39
29	368.0	6.378e+18	0.952	6.701e+18	2.00155	5.73
30	381.0	8.764e+18	0.941	9.312e+18	2.00149	5.53
31						
32	391.0	1.408e+19	0.932	1.510e+19	2.00141	4.79
33	403.0	1.932e+19	0.919	2.102e+19	2.00130	4.59
34	415.0	2.207e+19	0.909	2.428e+19	2.00112	4.60
35	429.0	1.269e+19	0.898	1.413e+19	2.00190	4.06
36	440.0	2.047e+19	0.886	2.312e+19	2.00170	3.50
37						
38	450.0	2.654e+19	0.869	3.055e+19	2.00163	2.67
39	459.0	3.013e+19	0.845	3.565e+19	2.00150	2.53
40	473.0	4.041e+19	0.779	5.189e+19	2.00140	1.93
41	487.0	4.421e+19	0.688	6.427e+19	2.00130	1.79

	T(°C)	N-no crr (g)	m from TG	N-crr (g)	g	del H (G)
1	25.0	3.632e+17	1.000	3.632e+17	2.00030	8.20
2	83.0	5.148e+17	1.001	5.143e+17	2.00200	8.27
3	107.0	4.871e+17	1.000	4.871e+17	2.00110	8.40
4	126.0	7.418e+17	1.000	7.420e+17	2.00260	9.20
5	156.0	1.293e+18	0.999	1.294e+18	2.00175	8.30
6						
7	179.0	1.738e+18	0.998	1.741e+18	2.00190	12.80
8	188.0	1.315e+18	0.998	1.317e+18	2.00180	10.53
9	203.0	1.576e+18	0.997	1.580e+18	2.00180	12.20
10	206.0	1.887e+18	0.997	1.892e+18	2.00200	11.30
11	217.0	2.183e+18	0.996	2.191e+18	2.00170	11.00
12						
13	231.0	2.446e+18	0.996	2.457e+18	2.00160	10.50
14	244.0	2.760e+18	0.995	2.774e+18	2.00200	7.70
15	257.0	2.925e+18	0.992	2.948e+18	2.00160	8.13
16	267.0	2.853e+18	0.991	2.880e+18	2.00150	7.40
17	282.0	4.058e+18	0.986	4.115e+18	2.00140	6.70
18						
19	295.0	3.763e+18	0.981	3.837e+18	2.00170	6.53
20	306.0	4.864e+18	0.974	4.996e+18	2.00170	6.50
21	316.0	3.036e+18	0.965	3.146e+18	2.00160	6.00
22	332.0	3.946e+18	0.947	4.167e+18	2.00140	6.13
23	358.0	5.622e+18	0.903	6.223e+18	2.00130	5.73
24						
25	379.0	9.308e+18	0.853	1.091e+19	2.00120	5.20
26	390.0	1.124e+19	0.822	1.367e+19	2.00300	5.13
27	402.0	1.403e+19	0.784	1.789e+19	2.00110	4.93
28	420.0	1.540e+19	0.721	2.136e+19	2.00350	4.93
29	431.0	1.565e+19	0.680	2.301e+19	2.00350	4.13
30						
31	447.0	2.157e+19	0.614	3.510e+19	2.00330	3.53
32	458.0	3.090e+19	0.566	5.458e+19	2.00300	2.80
33	476.0	3.549e+19	0.483	7.347e+19	2.00250	2.50
34	495.0	4.095e+19	0.405	1.010e+20	2.00260	2.07

	T(°C)	N-no cr (g)	m from TG	N-cr (g)	g	del H (G)
1	25.0	2.018e+17	1	2.018e+17	2.00030	8.13
2	66.0	2.670e+17	0.999	2.672e+17	2.00170	7.20
3	85.5	4.480e+17	0.998	4.487e+17	2.00150	8.70
4	100.0	6.151e+17	0.998	6.163e+17	2.00219	9.99
5	126.0	6.860e+17	0.997	6.881e+17	2.00180	10.20
6						
7	144.0	5.503e+17	0.996	5.523e+17	2.00159	9.29
8	161.0	9.356e+17	0.996	9.394e+17	2.00200	10.13
9	173.0	1.154e+18	0.996	1.159e+18	2.00155	10.99
10	191.0	1.336e+18	0.995	1.343e+18	2.00185	10.70
11	205.0	1.575e+18	0.995	1.583e+18	2.00173	11.65
12	216.0	1.592e+18	0.994	1.601e+18	2.00190	10.53
13	231.0	1.817e+18	0.994	1.829e+18	2.00230	10.05
14	240.0	1.689e+18	0.993	1.700e+18	2.00220	9.90
15	253.0	1.765e+18	0.993	1.778e+18	2.00210	8.19
16	272.0	1.755e+18	0.991	1.770e+18	2.00179	7.80
17	283.0	1.727e+18	0.99	1.744e+18	2.00174	8.33
18	295.0	1.736e+18	0.989	1.755e+18	2.00170	7.00
19	309.0	2.009e+18	0.987	2.036e+18	2.00160	8.00
20	322.0	2.110e+18	0.984	2.144e+18	2.00140	7.33
21	336.0	2.044e+18	0.979	2.087e+18	2.00174	6.92
22	349.0	1.826e+18	0.974	1.876e+18	2.00182	6.13
23	360.0	1.867e+18	0.967	1.931e+18	2.00174	6.27
24	369.0	1.783e+18	0.96	1.857e+18	2.00184	6.19
25	379.0	1.923e+18	0.951	2.021e+18	2.00173	5.47
26	395.0	2.330e+18	0.933	2.499e+18	2.00160	5.93
27	405.0	3.006e+18	0.918	3.274e+18	2.00184	5.60
28	420.0	4.062e+18	0.889	4.568e+18	2.00173	5.13
29	436.0	5.952e+18	0.849	7.014e+18	2.00166	4.73
30	448.0	6.968e+18	0.812	8.583e+18	2.00166	4.87
31	460.0	6.771e+18	0.763	8.879e+18	2.00170	4.53
32	479.0	1.161e+19	0.672	1.728e+19	2.00170	3.27
33	497.0	1.559e+19	0.559	2.789e+19	2.00158	2.60
34	512.0	1.930e+19	0.532	3.629e+19	2.00184	2.73

	T(°C)	N-no crr (/g)	m from TG	N-crr (/g)	g	del H (G)
1	30.0	3.000e+17	1.000	3.000e+17	2.00260	7.00
2	66.0	2.929e+17	1.001	2.927e+17	2.00200	8.00
3	85.0	3.323e+17	1.001	3.321e+17	2.00190	9.20
4	105.0	4.575e+17	1.001	4.571e+17	2.00180	9.80
5	120.0	6.843e+17	1.001	6.837e+17	2.00230	9.40
6						
7	137.0	8.161e+17	1.001	8.152e+17	2.00255	10.90
8	149.0	1.066e+18	1.001	1.065e+18	2.00234	9.50
9	165.0	1.437e+18	1.001	1.436e+18	2.00240	12.05
10	181.5	1.328e+18	1.000	1.327e+18	2.00220	9.67
11	191.5	1.518e+18	1.000	1.518e+18	2.00210	6.80
12						
13	202.0	1.671e+18	1.000	1.672e+18	2.00210	10.50
14	216.0	1.765e+18	1.000	1.765e+18	2.00230	9.46
15	225.0	1.815e+18	0.998	1.817e+18	2.00220	9.53
16	245.0	1.909e+18	0.997	1.915e+18	2.00215	9.26
17	254.0	1.862e+18	0.995	1.870e+18	2.00200	8.73
18						
19	275.0	1.984e+18	0.989	2.006e+18	2.00190	7.80
20	291.0	2.127e+18	0.985	2.160e+18	2.00180	7.67
21	319.0	2.193e+18	0.966	2.270e+18	2.00194	6.26
22	326.0	1.953e+18	0.959	2.037e+18	2.00200	6.53
23	340.0	1.844e+18	0.941	1.959e+18	2.00190	6.73
24						
25	351.0	1.658e+18	0.953	1.738e+18	2.00216	5.67
26	363.0	1.761e+18	0.903	1.951e+18	2.00210	6.53
27	375.0	2.218e+18	0.875	2.536e+18	2.00199	6.00
28	394.0	2.841e+18	0.827	3.438e+18	2.00180	5.46
29	409.0	4.434e+18	0.783	5.663e+18	2.00188	5.20
30						
31	426.0	4.577e+18	0.725	6.309e+18	2.00197	5.07
32	443.0	4.104e+18	0.660	6.219e+18	2.00172	5.27
33	455.0	5.826e+18	0.608	9.586e+18	2.00240	4.53
34	467.0	9.036e+18	0.520	1.736e+19	2.00224	3.27
35	479.0	9.885e+18	0.442	2.239e+19	2.00215	3.40
36						
37	487.0	1.044e+19	0.409	2.550e+19	2.00210	2.53
38	497.0	1.056e+19	0.383	2.758e+19	2.00198	2.20
39	505.0	1.151e+19	0.369	3.120e+19	2.00180	2.00

	T(°C)	N-no crr (/g)	m from TG	N-crr (/g)	g	del H (G)
1	25.0	3.634e+17	1.000	3.634e+17		8.73
2	68.0	2.072e+17	0.999	2.074e+17		7.20
3	88.0	3.839e+17	0.998	3.847e+17		8.70
4	107.0	4.937e+17	0.997	4.953e+17		10.40
5	126.0	3.880e+17	0.996	3.895e+17		8.70
6						
7	142.0	4.757e+17	0.995	4.779e+17	2.00090	8.53
8	159.0	8.098e+17	0.995	8.140e+17	2.00080	9.45
9	167.5	1.068e+18	0.995	1.073e+18	2.00179	10.80
10	186.0	9.920e+17	0.994	9.979e+17	2.00150	9.13
11	200.0	1.172e+18	0.993	1.180e+18	2.00183	9.73
12						
13	214.0	1.158e+18	0.993	1.166e+18	2.00230	9.05
14	230.0	1.492e+18	0.991	1.505e+18	2.00240	9.06
15	250.0	1.227e+18	0.991	1.238e+18	2.00240	8.20
16	274.0	1.016e+18	0.989	1.027e+18	2.00210	8.06
17	291.0	8.699e+17	0.987	8.811e+17	2.00167	6.99
18						
19	306.0	7.725e+17	0.985	7.845e+17	2.00234	5.93
20	321.0	7.038e+17	0.986	7.138e+17	2.00215	7.60
21	341.0	7.059e+17	0.972	7.263e+17	2.00218	5.60
22	360.0	6.384e+17	0.959	6.655e+17	2.00189	5.53
23	372.0	6.733e+17	0.950	7.088e+17	2.00175	6.27
24						
25	394.0	6.028e+17	0.919	6.560e+17	2.00165	6.40
26	411.6	1.315e+18	0.887	1.483e+18	2.00129	6.59
27	437.0	2.489e+18	0.820	3.036e+18	2.00206	5.27
28	455.0	4.642e+18	0.753	6.162e+18	2.00220	4.33
29	468.0	6.095e+18	0.694	8.777e+18	2.00220	4.46
30						
31	483.0	7.187e+18	0.623	1.153e+19	2.00190	4.33
32	492.0	1.101e+19	0.586	1.881e+19	2.00225	3.46
33	506.0	1.373e+19	0.538	2.551e+19	2.00200	2.73
34	522.0	1.561e+19	0.510	3.061e+19	2.00190	2.13

	T(°C)	N-no cr (g)	m from TG	N-cr (g)	g H	del H (G)H
1	25	2.019e+17	1.000	2.019e+17	2.00230	9.27
2	59.3	4.152e+17	1.001	4.146e+17	2.00230	8.20
3	85	3.068e+17	1.002	3.063e+17	2.00175	9.73
4	101	4.123e+17	1.002	4.116e+17	2.00150	10.20
5	120	4.012e+17	1.002	4.004e+17	2.00194	7.40
6						
7	139	5.710e+17	1.002	5.696e+17	2.00080	9.20
8	157	1.037e+18	1.003	1.034e+18	2.00160	12.50
9	173	9.375e+17	1.003	9.349e+17	2.00265	9.73
10	190	1.186e+18	1.003	1.183e+18	2.00240	11.67
11	197	1.271e+18	1.003	1.267e+18	2.00196	10.00
12						
13	213	1.643e+18	1.003	1.639e+18	2.00237	9.60
14	227	1.544e+18	1.003	1.540e+18	2.00220	10.53
15	238	1.561e+18	1.002	1.558e+18	2.00214	10.40
16	249	1.678e+18	1.002	1.675e+18	2.00212	9.53
17	262	1.626e+18	1.001	1.624e+18	2.00222	9.47
18						
19	299	1.664e+18	0.9944	1.673e+18	2.00235	7.73
20	311.2	1.633e+18	0.9900	1.649e+18	2.00224	7.47
21	324	1.647e+18	0.9886	1.666e+18	2.00199	7.13
22	340	1.452e+18	0.9710	1.495e+18	2.00210	6.87
23	350	1.574e+18	0.9609	1.638e+18	2.00203	6.66
24						
25	360	1.585e+18	0.9485	1.671e+18	2.00198	5.73
26	375	1.490e+18	0.9253	1.610e+18	2.00184	6.86
27	386	1.678e+18	0.9045	1.855e+18	2.00178	5.80
28	406	1.562e+18	0.8576	1.821e+18	2.00161	5.47
29	417	1.896e+18	0.8267	2.293e+18	2.00203	6.13
30						
31	425	2.022e+18	0.7802	2.592e+18	2.00188	7.13
32	440	2.323e+18	0.7497	3.098e+18	2.00174	6.00
33	446	3.694e+18	0.7263	5.086e+18	2.00186	5.20
34	454	5.201e+18	0.6925	7.511e+18	2.00240	4.87
35	461	6.809e+18	0.6607	1.030e+19	2.00190	4.80
36						
37	482	7.567e+18	0.5448	1.389e+19	2.00199	4.87
38	502	8.620e+18	0.4308	2.001e+19	2.00198	4.00
39	519	1.204e+19	0.3936	3.060e+19	2.00190	3.13

	T(°C)	N-no crr (/g)	m from TG	N-crr (g)	g	del H (G)
1	25.0	3.700e+17	1.000	3.700e+17	2.00300	9.70
2	83.0	4.010e+17	1.002	4.002e+17	2.00242	10.40
3	100.3	4.425e+17	1.002	4.417e+17	2.00250	9.13
4	114.0	5.230e+17	1.002	5.221e+17	2.00180	10.30
5	137.4	8.390e+17	1.002	8.373e+17	2.00300	11.70
6						
7	148.0	1.416e+18	1.002	1.413e+18	2.00270	12.07
8	158.0	1.403e+18	1.001	1.401e+18	2.00280	12.90
9	172.0	1.908e+18	1.001	1.905e+18	2.00280	11.70
10	186.0	1.979e+18	1.001	1.977e+18	2.00290	11.20
11	199.0	2.180e+18	1.001	2.179e+18	2.00300	10.30
12						
13	209.0	2.042e+18	1.000	2.041e+18	2.00270	9.80
14	219.0	2.088e+18	0.9999	2.088e+18	2.00290	9.53
15	233.0	2.235e+18	0.9994	2.236e+18	2.00260	8.80
16	242.0	2.513e+18	0.9988	2.516e+18	2.00270	9.20
17	254.0	2.970e+18	0.9981	2.976e+18	2.00300	8.40
18						
19	275.0	2.370e+18	0.9963	2.379e+18	2.00290	7.13
20	289.0	2.658e+18	0.9942	2.673e+18	2.00270	6.80
21	303.0	2.568e+18	0.9912	2.591e+18	2.00270	6.60
22	317.0	2.755e+18	0.9864	2.793e+18	2.00280	7.80
23	345.0	2.730e+18	0.9699	2.815e+18	2.00290	6.13
24						
25	367.0	3.209e+18	0.9475	3.387e+18	2.00270	5.70
26	383.0	3.237e+18	0.9246	3.501e+18	2.00270	5.87
27	392.0	4.722e+18	0.9080	5.201e+18	2.00280	5.60
28	415.0	5.581e+18	0.8578	6.506e+18	2.00260	5.50
29	429.0	6.468e+18	0.8218	7.870e+18	2.00270	4.80
30						
31	442.0	8.370e+18	0.7954	1.052e+19	2.00270	4.40
32	452.0	7.601e+18	0.7785	9.764e+18	2.00289	4.73
33	461.0	1.010e+19	0.7634	1.323e+19	2.00270	4.09
34	481.0	1.272e+19	0.6989	1.821e+19	2.00270	4.73
35	501.0	1.568e+19	0.6525	2.402e+19	2.00290	3.80
36	524.0	1.662e+19	0.6195	2.683e+19	2.00270	2.93
37					2.00280	2.40

	T(°C)	N-no cr (/g)	m from TG	N-cr (/g)	g	del H (G)
1	25.0	1.880e+17	1.000	1.880e+17	2.00160	8.13
2	61.0	2.552e+17	1.001	2.550e+17	2.00210	7.80
3	73.0	3.310e+17	1.000	3.310e+17	2.00240	12.00
4	89.0	4.139e+17	1.002	4.132e+17	2.00300	10.00
5	116.0	6.139e+17	1.003	6.117e+17	2.00180	8.67
6						
7	133.0	1.093e+18	1.004	1.088e+18	2.00220	10.00
8	150.0	8.950e+17	1.003	8.921e+17	2.00240	10.78
9	167.0	1.628e+18	1.004	1.622e+18	2.00250	10.53
10	189.0	1.884e+18	1.004	1.877e+18	2.00240	10.40
11	205.0	1.583e+18	1.004	1.577e+18	2.00230	9.26
12						
13	221.0	1.357e+18	1.004	1.352e+18	2.00220	8.13
14	235.0	1.381e+18	1.003	1.376e+18	2.00220	7.33
15	251.0	1.369e+18	1.002	1.366e+18	2.00213	6.80
16	271.0	1.161e+18	0.9996	1.162e+18	2.00180	6.12
17	285.0	1.307e+18	0.9962	1.312e+18	2.00180	6.60
18						
19	308.0	1.463e+18	0.9862	1.484e+18	2.00220	6.13
20	322.0	1.624e+18	0.9761	1.664e+18	2.00200	6.53
21	333.0	1.612e+18	0.9652	1.670e+18	2.00162	6.73
22	350.0	1.391e+18	0.9437	1.474e+18	2.00172	6.73
23	366.0	1.609e+18	0.9136	1.761e+18	2.00166	5.67
24						
25	386.0	1.874e+18	0.8659	2.164e+18	2.00206	6.00
26	401.0	2.328e+18	0.8216	2.833e+18	2.00197	6.30
27	413.0	3.326e+18	0.7804	4.262e+18	2.00190	5.07
28	422.0	3.422e+18	0.7461	4.586e+18	2.00190	5.47
29	440.0	4.285e+18	0.6700	6.396e+18	2.00180	5.13
30						
31	457.0	4.152e+18	0.5874	7.067e+18	2.00170	4.47
32	473.0	4.651e+18	0.5157	9.020e+18	2.00187	3.87
33	488.0	6.339e+18	0.4284	1.480e+19	2.00200	3.33
34	500.0	6.711e+18	0.3689	1.819e+19	2.00180	2.93
35	511.0	7.499e+18	0.3409	2.200e+19	2.00170	2.60

	T(°C)	N-no crr (g)	m from TG	N-crr (g)	g	del H (G)
1	25.0	2.456e+17	1.000	2.456e+17	2.00320	7.87
2	56.0	1.998e+17	1.000	1.998e+17	2.00265	10.20
3	82.0	2.830e+17	1.001	2.828e+17	2.00300	7.93
4	94.0	3.145e+17	1.001	3.142e+17	2.00310	8.32
5	109.0	5.480e+17	1.000	5.477e+17	2.00295	8.27
6						
7	124.0	5.111e+17	1.000	5.112e+17	2.00280	9.12
8	140.0	7.670e+17	0.999	7.674e+17	2.00288	8.53
9	153.0	9.570e+17	0.999	9.576e+17	2.00281	10.80
10	172.0	9.850e+17	0.999	9.858e+17	2.00267	11.20
11	183.0	1.273e+18	0.999	1.274e+18	2.00298	10.50
12						
13	195.0	1.201e+18	0.999	1.202e+18	2.00290	9.93
14	205.0	1.425e+18	0.999	1.427e+18	2.00280	10.60
15	214.0	1.497e+18	0.999	1.499e+18	2.00270	10.30
16	227.0	1.936e+18	0.999	1.939e+18	2.00263	9.00
17	253.0	2.368e+18	0.997	2.374e+18	2.00244	9.40
18						
19	269.0	2.694e+18	0.996	2.706e+18	2.00248	8.06
20	287.0	2.959e+18	0.993	2.981e+18	2.00250	7.60
21	295.0	2.842e+18	0.991	2.869e+18	2.00246	7.47
22	310.0	2.924e+18	0.986	2.964e+18	2.00237	7.27
23	334.0	2.977e+18	0.977	3.046e+18	2.00254	6.53
24						
25	346.0	3.024e+18	0.971	3.115e+18	2.00244	6.20
26	363.0	3.394e+18	0.959	3.538e+18	2.00234	6.00
27	373.0	4.990e+18	0.951	5.249e+18	2.00250	5.07
28	385.0	6.687e+18	0.938	7.131e+18	2.00244	4.40
29	401.0	9.691e+18	0.916	1.058e+19	2.00233	4.33
30						
31	415.0	5.814e+18	0.891	6.527e+18	2.00220	4.67
32	427.0	7.421e+18	0.864	8.591e+18	2.00230	4.67
33	445.0	1.216e+19	0.814	1.494e+19	2.00230	3.53
34	460.0	1.547e+19	0.763	2.026e+19	2.00240	2.73

	T(°C)	N-no cr (g)	m from TG	N-cr (g)	g	del H (G)
1	25.0	2.830e+17	1.00	2.830e+17	2.00310	9.60
2	79.0	1.630e+17	1.01	1.619e+17	2.00330	6.60
3	91.6	2.950e+17	1.01	2.931e+17	2.00330	8.30
4	114.0	3.670e+17	1.01	3.647e+17	2.00360	8.73
5	127.0	6.160e+17	1.01	6.122e+17	2.00250	11.00
6						
7	147.0	4.911e+17	1.01	4.883e+17	2.00275	6.70
8	159.0	7.290e+17	1.01	7.252e+17	2.00289	8.70
9	178.0	1.043e+18	1.00	1.038e+18	2.00300	11.00
10	201.0	1.030e+18	1.00	1.027e+18	2.00286	10.70
11	212.5	1.047e+18	1.00	1.045e+18	2.00277	9.70
12						
13	232.0	1.796e+18	1.000	1.797e+18	2.00260	7.86
14	253.0	2.529e+18	0.994	2.545e+18	2.00280	9.46
15	269.0	1.930e+18	0.986	1.957e+18	2.00287	7.86
16	295.0	2.023e+18	0.966	2.095e+18	2.00293	7.70
17	307.0	2.378e+18	0.951	2.500e+18	2.00283	7.20
18						
19	315.0	2.714e+18	0.939	2.889e+18	2.00300	7.00
20	328.0	2.855e+18	0.916	3.117e+18	2.00290	6.13
21	338.0	2.361e+18	0.894	2.640e+18	2.00320	5.60
22	355.0	2.455e+18	0.851	2.886e+18	2.00320	6.20
23	372.0	2.164e+18	0.798	2.713e+18	2.00310	7.33
24						
25	389.0	2.755e+18	0.740	3.722e+18	2.00300	5.40
26	406.0	3.957e+18	0.677	5.845e+18	2.00310	6.33
27	432.0	4.078e+18	0.577	7.064e+18	2.00287	5.07
28	448.0	4.819e+18	0.520	9.275e+18	2.00260	5.13
29	484.0	4.580e+18	0.388	1.181e+19	2.00279	5.00
30						
31	495.0	5.118e+18	0.357	1.432e+19	2.00260	4.87
32	506.0	5.641e+18	0.332	1.700e+19	2.00257	4.20
33	517.0	6.159e+18	0.315	1.953e+19	2.00250	3.40
34	529.0	5.646e+18	0.310	1.824e+19	2.00280	3.00

	T(°C)	N-no cr (/g)	m from TG	N-cr (/g)	g	del H (G)
1	25.0	3.441e+17	1.000	3.441e+17	2.00370	8.66
2	50.0	2.540e+17	1.001	2.538e+17	2.00250	8.93
3	74.6	3.122e+17	1.000	3.121e+17	2.00243	7.93
4	90.0	4.416e+17	1.000	4.416e+17	2.00238	8.80
5	100.0	6.410e+17	0.9998	6.411e+17	2.00234	10.07
6						
7	115.0	7.263e+17	0.9994	7.267e+17	2.00224	8.47
8	143.0	9.149e+17	0.9991	9.157e+17	2.00249	9.39
9	153.0	9.377e+17	0.9989	9.388e+17	2.00296	8.86
10	171.0	9.682e+17	0.9985	9.697e+17	2.00254	8.99
11	183.0	7.099e+17	0.9982	7.112e+17	2.00249	4.93
12						
13	192.0	4.715e+17	0.9980	4.724e+17	2.00279	8.13
14	205.5	3.217e+17	0.9980	3.224e+17	2.00232	7.06
15	237.0	1.646e+17	0.9935	1.657e+17	2.00230	7.53
16	271.0	2.469e+17	0.9960	2.479e+17	2.00218	7.73
17	285.0	3.226e+17	0.9947	3.243e+17	2.00224	6.60
18						
19	299.0	4.376e+17	0.9926	4.408e+17	2.00209	6.27
20	309.0	5.201e+17	0.9906	5.250e+17	2.00243	6.41
21	320.0	7.757e+17	0.9873	7.857e+17	2.00230	5.60
22	328.0	8.609e+17	0.9842	8.747e+17	2.00220	6.07
23	337.0	1.456e+18	0.9797	1.486e+18	2.00215	5.27
24						
25	350.0	1.809e+18	0.9712	1.863e+18	2.00208	5.73
26	363.0	2.318e+18	0.9598	2.415e+18	2.00205	4.93
27	376.0	3.282e+18	0.9473	3.464e+18	2.00240	5.13
28	390.0	4.009e+18	0.9232	4.342e+18	2.00234	3.93
29	410.0	5.608e+18	0.8805	6.369e+18	2.00220	3.60
30						
31	424.0	7.408e+18	0.8395	8.825e+18	2.00218	2.60
32	432.0	8.050e+18	0.8263	9.742e+18	2.00215	2.47
33	440.0	8.330e+18	0.7785	1.070e+19	2.00220	2.42
34	456.0	8.452e+18	0.7037	1.201e+19	2.00202	2.13
35	473.5	7.656e+18	0.6083	1.259e+19	2.00210	2.13
36						
37	492.0	7.680e+18	0.5567	1.379e+19	2.00200	2.40
38	508.0	5.926e+18	0.5298	1.119e+19	2.00200	2.93
39	519.0	4.667e+18	0.5153	9.057e+18	2.00200	3.47

	T(°C)	N-no crr (/g)	m from TG	N-crr (/g)	g	del H (G)
1	25.0	2.530e+17	1.000	2.530e+17	2.00350	9.73
2	71.0	2.720e+17	0.9983	2.725e+17	2.00260	7.80
3	85.0	3.609e+17	0.9974	3.619e+17	2.00260	8.53
4	105.0	5.684e+17	0.9962	5.705e+17	2.00289	7.93
5	133.0	8.419e+17	0.9948	8.463e+17	2.00282	9.86
6						
7	152.0	8.317e+17	0.9937	8.370e+17	2.00271	8.40
8	164.0	7.623e+17	0.9930	7.677e+17	2.00261	8.99
9	174.0	5.962e+17	0.9923	6.008e+17	2.00252	8.27
10	190.0	4.848e+17	0.9911	4.891e+17	2.00246	8.46
11	200.0	3.835e+17	0.9903	3.873e+17	2.00231	8.26
12						
13	219.0	5.257e+17	0.9884	5.318e+17	2.00227	8.06
14	238.0	4.594e+17	0.9856	4.661e+17	2.00246	7.40
15	252.0	5.552e+17	0.9823	5.652e+17	2.00238	6.40
16	264.0	4.615e+17	0.9784	4.717e+17	2.00234	7.13
17	281.0	5.460e+17	0.9704	5.627e+17	2.00225	7.00
18						
19	311.0	1.174e+18	0.9444	1.244e+18	2.00199	6.66
20	329.0	1.268e+18	0.9182	1.381e+18	2.00192	6.47
21	343.0	1.266e+18	0.8907	1.421e+18	2.00227	5.99
22	356.0	1.443e+18	0.8593	1.679e+18	2.00213	5.87
23	367.0	1.547e+18	0.8285	1.867e+18	2.00199	5.47
24						
25	380.0	2.057e+18	0.7883	2.609e+18	2.00224	5.13
26	385.0	1.707e+18	0.7715	2.212e+18	2.00240	5.60
27	398.0	1.820e+18	0.7260	2.506e+18	2.00243	6.33
28	417.0	2.840e+18	0.6525	4.352e+18	2.00247	5.13
29	433.0	4.621e+18	0.5854	7.894e+18	2.00242	3.33
30						
31	449.0	5.406e+18	0.5028	1.075e+19	2.00240	3.00
32	467.0	5.583e+18	0.4307	1.296e+19	2.00220	2.53
33	473.0	5.504e+18	0.4070	1.352e+19	2.00210	2.33
34	511.0	5.417e+18	0.3187	1.699e+19	2.00230	2.20

8000491

2 OF 2

	T(°C)	N-no crr (/g)	m from TG	N-crr (/g)	g	del H (G)
1	25.0	3.076e+17	1.000	3.076e+17	2.00275	8.93
2	60.0	2.504e+17	0.9993	2.506e+17	2.00260	8.60
3	75.0	2.656e+17	0.9992	2.658e+17	2.00250	9.13
4	93.0	2.929e+17	0.9989	2.932e+17	2.00189	5.80
5	107.0	6.811e+17	0.9986	6.821e+17	2.00230	8.80
6						
7	126.0	6.422e+17	0.9983	6.433e+17	2.00247	10.10
8	132.0	8.220e+17	0.9982	8.234e+17	2.00230	8.86
9	151.0	1.124e+18	0.9982	1.126e+18	2.00230	9.33
10	161.0	1.321e+18	0.9982	1.324e+18	2.00230	9.73
11	175.0	1.712e+18	0.9982	1.715e+18	2.00210	9.46
12						
13	188.0	2.040e+18	0.9984	2.043e+18	2.00248	8.06
14	198.0	1.976e+18	0.9983	1.979e+18	2.00240	9.26
15	212.0	1.859e+18	0.9984	1.862e+18	2.00245	10.00
16	222.0	2.048e+18	0.9983	2.052e+18	2.00245	8.70
17	242.0	2.209e+18	0.9982	2.213e+18	2.00240	8.70
18						
19	259.0	2.472e+18	0.9975	2.478e+18	2.00190	8.26
20	280.0	2.565e+18	0.9951	2.578e+18	2.00240	7.00
21	291.0	2.582e+18	0.9935	2.599e+18	2.00230	7.33
22	304.0	2.414e+18	0.9918	2.434e+18	2.00220	7.33
23	317.0	1.931e+18	0.9880	1.954e+18	2.00214	7.19
24						
25	329.0	2.521e+18	0.9830	2.565e+18	2.00200	6.26
26	340.0	2.760e+18	0.9769	2.825e+18	2.00200	7.13
27	351.0	2.746e+18	0.9687	2.835e+18	2.00200	6.08
28	368.0	2.708e+18	0.9573	2.829e+18	2.00200	6.06
29	390.0	2.537e+18	0.9283	2.733e+18	2.00190	6.40
30						
31	399.0	2.411e+18	0.9130	2.640e+18	2.00180	5.80
32	416.0	2.936e+18	0.8737	3.361e+18	2.00170	5.27
33	435.0	3.611e+18	0.8145	4.434e+18	2.00173	5.40
34	451.0	5.154e+18	0.7265	7.094e+18	2.00171	4.70
35	464.0	6.095e+18	0.6483	9.401e+18	2.00171	4.20
36						
37	480.0	7.000e+18	0.5956	1.175e+19	2.00180	4.50
38	490.5	8.682e+18	0.5758	1.508e+19	2.00170	3.33

	T (°C)	N-no crr (/g)	m from TG	N-crr (/g)	g	del H
1	25.0	4.028e+17	1.000	4.028e+17	2.00280	7.60
2	59.0	3.530e+17	0.9983	3.536e+17	2.00180	8.67
3	76.0	3.520e+17	0.9977	3.528e+17	2.00130	7.93
4	100.0	6.086e+17	0.9967	6.106e+17	2.00215	8.87
5	112.0	8.749e+17	0.9959	8.785e+17	2.00203	9.53
6						
7	126.0	9.753e+17	0.9954	9.798e+17	2.00187	8.66
8	138.0	1.288e+18	0.9955	1.294e+18	2.00210	8.27
9	148.0	1.541e+18	0.9949	1.549e+18	2.00210	10.07
10	157.5	1.738e+18	0.9941	1.748e+18	2.00226	9.27
11	170.0	1.745e+18	0.9937	1.756e+18	2.00213	9.73
12						
13	184.0	1.656e+18	0.9938	1.666e+18	2.00220	8.93
14	201.0	1.645e+18	0.9922	1.658e+18	2.00226	9.27
15	213.4	1.599e+18	0.9920	1.612e+18	2.00200	7.87
16	226.0	1.649e+18	0.9915	1.663e+18	2.00226	8.00
17	243.0	1.611e+18	0.9901	1.628e+18	2.00187	7.67
18						
19	257.0	1.639e+18	0.9880	1.659e+18	2.00183	8.93
20	272.0	1.682e+18	0.9847	1.708e+18	2.00173	7.27
21	292.0	1.793e+18	0.9747	1.839e+18	2.00190	6.87
22	319.0	1.795e+18	0.9492	1.891e+18	2.00193	6.73
23	339.0	1.835e+18	0.9174	2.000e+18	2.00100	6.93
24						
25	350.0	1.736e+18	0.8949	1.940e+18	2.00184	6.13
26	357.0	1.669e+18	0.8651	1.929e+18	2.00179	6.13
27	367.0	1.925e+18	0.8514	2.261e+18	2.00180	6.53
28	379.0	1.909e+18	0.8151	2.342e+18	2.00162	6.07
29	391.0	2.197e+18	0.7751	2.835e+18	2.00175	5.60
30						
31	405.0	2.654e+18	0.7238	3.667e+18	2.00190	5.73
32	415.0	2.920e+18	0.6836	4.272e+18	2.00190	5.53
33	431.0	3.966e+18	0.6169	6.429e+18	2.00190	4.87
34	445.0	1.734e+18	0.5539	3.130e+18	2.00189	5.27
35	457.0	3.603e+18	0.4982	7.232e+18	2.00199	5.27
36						
37	470.0	5.290e+18	0.4425	1.196e+19	2.00196	4.93
38	482.0	6.996e+18	0.3920	1.785e+19	2.00184	3.67
39	493.0	8.229e+18	0.3408	2.415e+19	2.00206	3.07
40	505.0	8.831e+18	0.3202	2.758e+19	2.00200	2.73

**DATE
FILMED**

2/6/93