QUARTERLY PROGRESS REPORT

ON

CONFIGURATIONAL DIFFUSION OF ASPHALTENES IN FRESH AND AGED CATALYSTS EXTRUDATES

DOE/PC/91311--T4

DE93 004925

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Grant No. DE-FG22-91PC91311

6-20-92 to 9-20-92

James A. Guin
A Ray Tarrer

Chemical Engineering Department
Auburn University
Auburn, AL 36849

MASTER

Table of Contents

Objective and Work Statement.....	1
Summary of Progress.....	3
Planned Work.....	3
Detailed Progress—Numerical Solution for Intrapore Diffusional Model	
with Freundlich Adsorption Isotherm	
Intrapore Diffusional Model.....	4
Dimensionless Form of the Diffusion Model.....	7
Mathematical Methods For Numerical Solution of the Diffusional Model.....	9
Plots of the Solution in Terms of Different Parameters.....	13
Solution for Some Special Cases.....	15
Diffusion with Linear Adsorption Isotherm.....	16
Diffusion with Small Adsorption.....	17
Diffusion with Large Adsorption.....	17
Diffusion with Rectangular Adsorption Isotherm.....	18
Diffusion with Small Bath Volume.....	18
Diffusion with Large Bath Volume.....	19
Comparison of the Numerical Solution with	
an Approximate Analytical Solution.....	19
Conclusion.....	20
References	

Statement of Work

Configurational Diffusion of Asphaltenes in Fresh and Aged Porous Catalyst Extrudates

Objective: The objective of this research is to determine the relationship between the size and shape of coal and petroleum macromolecules and their diffusion rates i.e., effective diffusivities, in catalyst pore structures. That is, how do the effective intrapore diffusivities depend on molecule configuration and pore geometry.

Task 1. **Relationship Between Effective Intrapore Diffusion Coefficients, Molecular Size and Pore Geometry.**

Finite bath-type diffusion experiments will be performed using both coal and petroleum-derived macromolecular species, e.g. asphaltenes, as well as model compounds, e.g. porphyrins, polymers, of known molecular size. By monitoring the concentration of solute macromolecules in the bath, the effective intrapore diffusion coefficients will be determined through application of the appropriate diffusion equations. Macromolecular species concentrations will be monitored by size exclusion chromatography (SEC). Relationships will be sought between the size, and shape, e.g. planar, coil, of the diffusing solutes and the pore geometry (pore size distribution) of the catalyst support. The effects of molecule configuration and catalyst pore size distribution on the effective intrapore diffusivity will be examined. Specially prepared laboratory catalysts with very narrow pore size distributions and other model porous media, e.g. porous Vycor glass, will be utilized in the experiments. Pore structures of all catalysts and other porous media will be characterized by mercury porosimetry and surface area (BET) analysis.

Task 2. **Effects of Solvent Composition, Solute Concentration, and Temperature on the Molecular Configuration and Diffusion Rate of Coal and Petroleum Asphaltenes in Catalyst Pores.**

Diffusion experiments such as in Task 1 will be performed with varying solvent compositions, i.e., paraffinic-aromatic mixtures, to examine the effects of the state of molecular aggregation (self-assemblies) on the rates of diffusion of coal and petroleum asphaltenes in the catalyst pores. Similar experiments will be performed to study the effect of *temperature* and solute (macromolecule) *concentration* on the state of molecular configuration and aggregation on the resulting pore diffusivity.

Task 3.   Assessment of Diffusional Limitations in Aged Catalysts

Diffusivity measurements such as conducted in Task 1 will be performed with both model compound and coal-derived macromolecular species using extrudate-type aged catalysts from laboratory experiments as well as aged catalysts obtained from actual coal liquefaction pilot plants such as the Wilsonville, AL Advanced Coal Liquefaction R & D Facility. From the experimental diffusivities so obtained, an evaluation of effects of changes in catalyst pore structure, e.g. tortuosity, pore plugging, shall be made. The changes in pore diffusivities associated with the pore structural changes caused by coke and metals deposition will be investigated, as compared with the fresh catalysts. An assessment of the relationship of increased diffusional limitations to coke and metals deposition in the catalyst pores will be made based on the results of the diffusivity measurements. The degree to which pore diffusivities can be restored to their original values by carefully controlled oxidation and/or extractive catalyst regeneration techniques also will be explored. The practical importance of these findings to coal liquefaction technology will be evaluated.

Summary

This quarter we solved the intrapore diffusional model using a finite difference technique and made a parametric study by solving for several different cases of model parameters. A comparison with known exact and approximate analytical solutions was used to verify the accuracy of the model.

Planned Work

Experimental work will begin this quarter including both diffusional uptake and equilibrium adsorption experiments. A visiting scientist, Dr. C. Y. Chang has now joined the project and should be of great help in the coming year.

**NUMERICAL SOLUTION FOR INTRAPORE DIFFUSIONAL MODEL
WITH FREUNDLICH ADSORPTION ISOTHERM**

INTRAPORE DIFFUSIONAL MODEL

Consider a porous particle immersed in a finite bath containing solute "A" and solvent "B". The solute molecules "A" are diffusing into the porous particle. The following general assumptions will be used in this model:

1. Chemical reaction is not considered in this process;
2. The particle and the diffusing molecules are assumed to be perfect spheres;
3. Surface diffusion is neglected;
4. The solute is assumed to have both Brownian and hydrodynamic characteristics, the sizes of the diffusing molecules are larger than the sizes of solvent molecules, and the solvent is a continuum;
5. There are no particle-particle interactions;
6. Also, it is assumed that the stirring speed of the solution is so high that the concentration in the bath is dependent only on time, not on position, and the external mass transfer can be neglected.

Based on the above assumptions, the following mathematical diffusional model can be derived.

For mass transfer in the particle:

$$K_p \epsilon \frac{\partial C_a}{\partial t} + \rho_p \frac{\partial q}{\partial t} = \frac{D_e}{r^2} \frac{\partial}{\partial r} \left(r^2 \frac{\partial C_a}{\partial r} \right) \quad (1)$$

and

Boundary conditions:

$$t=0, \frac{\partial C_a}{\partial r}=0, \quad \frac{\partial q}{\partial r}=0 \quad (2)$$

$$r=R, C_a=C_b(t) \quad (3)$$

Initial condition:

$$t=0, C_a=0 \quad (4)$$

For mass transfer in the bath:

$$\frac{d(V_p C_b)}{dt} = -4\pi R^2 k D_o \left(\frac{\partial C_a}{\partial r} \right) \Big|_{r=R} \quad (5)$$

Initial condition:

$$t=0, C_b=C_{b0} \quad (6)$$

Also, the mass transfer in the bath can be expressed as:

$$V_b(C_{b0}-C_b) = 4\pi \int_0^R (K_p e C_a + \rho_p q) r^2 dr \quad (7)$$

where, q ---amount of adsorption, mol A/g(pellet)

$C_b(t)$ ---bath concentration at time t , mol/cc(fluid)

C_{b0} ---initial bath concentration at $t = 0$, mol/cc(fluid)

C_a ---available pore concentration, mol A/cc(available void)

V_b ---bath fluid volume, cc

r ---radius of the particle at any position, cm

R ---outer radius of the particle, cm

t ---immersing time, s

K_p ---partition factor

ρ_p ---bulk particle density, g/cc(total pellet volume)

ϵ ---porosity of the particle

L ---tortuosity of particle pore

k ---number of the particles

D_o ---effective diffusivity, cm^2/s

and

$$D_o = \frac{\epsilon K_p K_r}{L} D_m \quad (8)$$

where, D_m ---bulk molecular diffusivity, cm^2/s

K_r ---restriction factor

Equation (2) states that the concentration distribution in the spherical particle is symmetric, and equation (3) assumes that no external diffusion resistance exists around the particle.

For mass transfer between the particle and the bath at infinite time, we have:

$$q_\infty = \frac{V_b}{\rho_p V_p} (C_{b0} - C_{b\infty}) - \frac{K_p \epsilon C_{b\infty}}{\rho_p} \quad (9)$$

where, q_∞ ---amount of adsorption at infinite time, $\text{mol A/g}(\text{pellet})$

$C_{b\infty}$ ---bath concentration at infinite time, $\text{mol A/cc}(\text{fluid})$

V_p ---total particle pellet volume, cc

Equations (1-8) can be solved analytically or numerically according to the expression for the adsorption term q . In this quarterly report, we mainly consider the numerical solution for the Freundlich adsorption isotherm, and then extend the solution to some typical cases.

DIMENSIONLESS FORM OF THE DIFFUSIONAL MODEL

In equation (1), if one uses the Freundlich adsorption isotherm for the adsorption term q as described in the following equation

$$q = mC_a^{\frac{1}{n}} \quad (10)$$

where, m and n are constants,

then, equation (1) can be changed as follows:

$$K_p e \frac{\partial C_a}{\partial t} + \rho_p \frac{\partial}{\partial t} (mC_a^{\frac{1}{n}}) = \frac{D_o}{r^2} \frac{\partial}{\partial r} [r^2 \frac{\partial C_a}{\partial r}] \quad (11)$$

The following dimensionless parameters can be used to put the equation into dimensionless form:

$$\xi = \frac{r}{R} \quad (\text{dimensionless radius}) \quad (12)$$

$$\theta_a = \frac{C_a}{C_{bo}} \quad (\text{dimensionless pore concentration}) \quad (13)$$

$$\theta_b = \frac{C_b}{C_{bo}} \quad (\text{dimensionless bath concentration}) \quad (14)$$

$$\theta_q = \frac{\rho_p}{K_p e} \frac{q}{C_{bo}} = \frac{\rho_p}{K_p e} \frac{mC_a^{\frac{1}{n}}}{C_{bo}} \quad (\text{dimensionless adsorption}) \quad (15)$$

$$\tau = \frac{D_o}{R^2 K_p e} t \quad (\text{dimensionless time}) \quad (16)$$

$$E = \frac{\rho_p m (C_{b0})^{\frac{1}{n}-1}}{K_p e} \quad (\text{dimensionless constant}) \quad (17)$$

$$F = \frac{V_b}{V_p K_p e} \quad (\text{dimensionless constant}) \quad (18)$$

$$\theta = \theta_a + E \theta_a^{\frac{1}{n}} \quad (\text{com. of conc. and adsorp.}) \quad (19)$$

where,

$$E = \frac{\text{solute adsorbed on solid wall at equil bath conc } C_{b0}}{\text{solute accumulated in pore fluid at equil bath conc } C_{b0}} \quad (20)$$

$$F = \frac{\text{bath volume}}{\text{available pore volume}} \quad (21)$$

and θ is the dimensionless uptake, that is, the combination of accumulation in the pore and adsorption on the wall. Then, the diffusional model will have the following form:

for the particle:

$$\frac{\partial \theta_a}{\partial \tau} + \frac{\partial \theta_g}{\partial \tau} = \frac{1}{\xi^2} \frac{\partial}{\partial \xi} \left(\xi^2 \frac{\partial \theta_a}{\partial \xi} \right) \quad (22)$$

or

$$\frac{\partial \theta_a}{\partial \tau} + E \frac{\partial \theta_a^{\frac{1}{n}}}{\partial \tau} = \frac{1}{\xi^2} \frac{\partial}{\partial \xi} \left(\xi^2 \frac{\partial \theta_a}{\partial \xi} \right) \quad (23)$$

or

$$\frac{\partial \theta}{\partial \tau} = \frac{\partial^2 \theta_a}{\partial \xi^2} + \frac{2}{\xi} \frac{\partial \theta_a}{\partial \xi} \quad (24)$$

boundary conditions:

$$\xi=0, \frac{\partial \theta_a}{\partial \tau}=0 \quad (25)$$

$$\xi=1, \theta_a=\theta_b(\tau) \quad (26)$$

initial condition:

$$\tau=0, \theta_a=0 \quad (27)$$

for the bath:

$$\frac{d\theta_b}{d\tau} = -\frac{3}{F} \frac{\partial \theta_a}{\partial \xi} \Big|_{\xi=1} \quad (28)$$

initial condition:

$$\tau=0, \theta_b=1 \quad (29)$$

or

$$\theta_b = 1 - \frac{3}{F} \int_0^1 (\theta_a + E\theta_a^{\frac{1}{n}}) \xi^2 d\xi = 1 - \frac{3}{F} \int_0^1 \theta \xi^2 d\xi \quad (30)$$

The above PDEs and ODEs can be solved by numerical methods given constants E, F and n, and plots of fractional uptake M_t/M_∞ or dimensionless bath concentration θ_b vs. dimensionless time τ can be plotted.

MATHEMATICAL METHODS FOR NUMERICAL SOLUTION OF THE DIFFUSIONAL MODEL

Several methods can be used to solve the PDEs. In this report, we use the Method of Lines (MOL) to solve these equations. We will use a finite difference representation for the space

variables and a Runge-Kutta time integrator (IMSL program IVPK).

First, we set up a grid system of N lines in ξ direction. The distance between two lines is:

$$\Delta \xi = \frac{1}{N-1} \quad (31)$$

For each ξ_i , we have:

$$\xi_i = (i-1) \Delta \xi \quad (32)$$

where,

$$i=1, 2, 3, \dots, N \quad (33)$$

Using first and second order differences from grid points:

$$\left(\frac{\partial \theta_a}{\partial \xi} \right)_i = \frac{(\theta_a)_{i+1} - (\theta_a)_{i-1}}{2 \Delta \xi} \quad (34)$$

$$\left(\frac{\partial^2 \theta_a}{\partial \xi^2} \right)_i = \frac{(\theta_a)_{i+1} - 2(\theta_a)_i + (\theta_a)_{i-1}}{(\Delta \xi)^2} \quad (35)$$

Because of the nondifferential property of the adsorption term in equation (23) with respect to time at $C_a=0$, equation (23) can not be solved in terms of θ_a , but it can be solved in terms of θ as shown in equation (24). In the above equations, we can express θ_a in terms of θ by solving equation(19), e. g., by using a root finding program. By equation (19), we have:

$$(\theta_a)_i = f(\theta_i) \quad (36)$$

thus, for the first and second differences shown in equation(33-34):

$$\left(\frac{\partial \theta_a}{\partial \xi}\right)_1 = \frac{f(\theta)_{1+1} - f(\theta)_{1-1}}{2\Delta\xi} \quad (37)$$

$$\left(\frac{\partial^2 \theta_a}{\partial \xi^2}\right)_1 = \frac{f(\theta)_{1+1} - 2f(\theta)_1 + f(\theta)_{1-1}}{(\Delta\xi)^2} \quad (38)$$

For $i=1$, or $\xi=0$, we use L'Hopital's rule for the second term in equation(24):

$$\left(\frac{1}{\xi} \frac{\partial \theta_a}{\partial \xi}\right) \Big|_{\xi=0} = \frac{\partial^2 \theta_a}{\partial \xi^2} \quad (39)$$

thus:

$$\frac{d\theta_1}{d\tau} = 3 \left(\frac{(\theta_a)_0 - 2(\theta_a)_1 + (\theta_a)_2}{(\Delta\xi)^2} \right) \quad (40)$$

where $(\theta_a)_0$ is a fictional point. Because of the symmetry at $\xi=0$,

$$(\theta_a)_0 = (\theta_a)_2 \quad (41)$$

then:

$$\frac{d\theta_1}{d\tau} = \frac{6((\theta_a)_2 - (\theta_a)_1)}{(\Delta\xi)^2} \quad (42)$$

or

$$\frac{d\theta_1}{d\tau} = \frac{6(f(\theta_2) - f(\theta_1))}{(\Delta\xi)^2} \quad (43)$$

For $i=2, 3, \dots, N-1$, from equation(24), we have:

$$\frac{d\theta_i}{d\tau} = \frac{(\theta_a)_{i+1} - 2(\theta_a)_i + (\theta_a)_{i-1}}{(\Delta\xi)^2} + \frac{(\theta_a)_{i+1} - (\theta_a)_{i-1}}{(i-1)(\Delta\xi)^2} \quad (44)$$

or

$$\frac{d\theta_i}{d\tau} = \frac{f(\theta_{i+1}) - 2f(\theta_i) + f(\theta_{i-1}))}{(\Delta\xi)^2} + \frac{f(\theta_{i+1}) - f(\theta_{i-1}))}{(i-1)(\Delta\xi)^2} \quad (45)$$

For $i=N$, or $\xi=1$, $\theta_s=\theta_b$, and:

$$\frac{d\theta_b}{d\tau} = \frac{d(\theta_s)_N}{d\tau} = -\frac{3}{F} \left(\frac{\partial \theta_s}{\partial \xi} \right) \Big|_{\xi=1} \quad (46)$$

Using a five point formula to calculate the right hand side, the above equation can be expressed as:

$$\frac{d(\theta_s)_N}{d\tau} = \frac{1}{4F\Delta\xi} [-25(\theta_s)_N - 48(\theta_s)_{N-1} + 36(\theta_s)_{N-2} + 16(\theta_s)_{N-3} - 3(\theta_s)_{N-4}] \quad (47)$$

Since at $i=N$, the adsorption term is differentiable,

$$\frac{d\theta_N}{d\tau} = \frac{d}{d\tau} \left((\theta_s)_N + E(\theta_s)_N^{\frac{1}{n}} \right) = \left[1 + \frac{E}{n} (\theta_s)_N^{\frac{1}{n}-1} \right] \frac{d(\theta_s)_N}{d\xi} \quad (48)$$

thus

$$\frac{d\theta_N}{d\tau} = \frac{1 + \frac{E}{n} (f(\theta_N))^{\frac{1}{n}-1}}{4F\Delta\xi} [-25f(\theta_N) - 48f(\theta_{N-1}) + 36f(\theta_{N-2}) + 16f(\theta_{N-3}) - 3f(\theta_{N-4})] \quad (49)$$

Now there are N equations for $i=1, 2, 3, \dots, N$. They are:

for $i=1$:

$$\frac{d\theta_1}{d\tau} = \frac{6(f(\theta_2) - f(\theta_1))}{(\Delta\xi)^2} \quad (50)$$

for $i=2, 3, \dots, N-1$:

$$\frac{d\theta_i}{d\tau} = \frac{f(\theta_{i+1}) - 2f(\theta_i) + f(\theta_{i-1}))}{(\Delta\xi)^2} + \frac{f(\theta_{i+1}) - f(\theta_{i-1}))}{(i-1)(\Delta\xi)^2} \quad (51)$$

for $i=N$:

$$\frac{d\theta_N}{d\tau} = \frac{1 + \frac{E}{n} (f(\theta_N))^{\frac{1}{n}-1}}{4F\Delta\xi} [-25f(\theta_N) - 48f(\theta_{N-1}) + 36f(\theta_{N-2}) + 16f(\theta_{N-3}) - 3f(\theta_{N-4})] \quad (52)$$

The initial conditions are:

at $i=1, 2, 3, \dots, N-1$

$$\tau=0, \quad \theta_i=0 \quad (53)$$

at $i=N$

$$\tau=0, \quad \theta_N=1+E \quad (54)$$

We can solve these ODEs by using the IVP RK subprogram in the IMSL math package. As a check on the accuracy of the solution, we also use equation(30) evaluated by Simpson's rule.

PLOTS OF THE SOLUTION IN TERMS OF DIFFERENT PARAMETERS

Several methods can be employed to plot the results of the numerical solution for the diffusional model. In this report, we will plot either fractional uptake M_t/M_∞ , or dimensionless bath concentration $C_b(\tau)/C_{b0}$, vs. dimensionless time, τ .

For the fractional uptake in the particle, we have:

$$\frac{M_t}{M_\infty} = \frac{\text{uptake at time } \tau}{\text{uptake at infinite time}} \quad (55)$$

or

$$\frac{M_r}{M_\infty} = \frac{3 \int_0^1 (\theta_a + E\theta_a^{\frac{1}{n}}) \xi^2 d\xi}{\theta_{a\infty} + E\theta_{a\infty}^{\frac{1}{n}}} = \frac{3 \int_0^1 \theta \xi^2 d\xi}{\theta_{a\infty} + E\theta_{a\infty}^{\frac{1}{n}}} \quad (56)$$

where, $\theta_{a\infty}$ is the solution of:

$$E\theta_{a\infty}^{\frac{1}{n}} = F(1 - \theta_{a\infty}) - \theta_{a\infty} \quad (57)$$

which can be obtained from equation(9).

We use the Composite Simpson's rule for the integration in equation(56), or:

$$\int_0^1 \theta \xi^2 d\xi = \frac{\Delta \xi}{3} \left[2 \sum_{i=1}^{\frac{N}{2}-1} \theta_{2i} ((i-1)\Delta \xi)^2 + 4 \sum_{i=1}^{\frac{N}{2}} \theta_{2i-1} ((i-1)\Delta \xi)^2 + \theta_N \right] \quad (58)$$

For dimensionless bath concentration:

$$\theta_b = \theta_a|_{surface} = (\theta_a)_N \quad (59)$$

The relationship between fractional uptake and dimensionless bath concentration is:

$$\frac{M_r}{M_\infty} = \frac{F(1 - \theta_b)}{\theta_{a\infty} + E\theta_{a\infty}^{\frac{1}{n}}} \quad (60)$$

Thus, by solving the intrapore diffusional equations, we can plot either M_r/M_∞ or $C_b(\tau)/C_{b0}$ vs. τ .

Figures 1-10 plot the computed results of the diffusional model for different values of parameters E, F and n.

From Figures 1-4 it can be seen that for constant values of

E and F, respectively, the fractional uptake at same time will decrease as the value of n is decreased. But at larger n, e. g., n larger than 5, the fractional uptake does not change much as the value of n is increased. This is true since at larger values of n, the adsorption isotherm approaches a rectangular isotherm:

$$Q=Q_0 \quad (61)$$

where, q_0 ---saturated amount of solute adsorbed, mol/g

Figures 5 and 5-1 plot the fractional uptake and dimensionless bath concentration at different values of E, respectively. From Figure 5, for constant values of F and n, the fractional uptake decreases greatly with respect to time as the value of E increases from 1 to 100. From Figure 5-1 it can be seen that the decrease in dimensionless bath concentration for larger E is much greater than that for smaller E, and the equilibrium time needed for larger E is much longer than that for smaller E. This is because the larger the value of E, the greater the adsorption capacity of the particle.

The result in Figure 6 seems to show that at larger values of F, the effect of F on the fractional uptake is not very great, which means that at larger F, the sizes of bath volume and particle volume have little effect on the fractional uptake and the time needed to reach equilibrium, even though the dimensionless bath concentration may be greatly different, as shown in Figure 6-1.

SOLUTION FOR SOME SPECIAL CASES

As shown above, the numerical solution for diffusional model

with Freundlich adsorption isotherm can be extended to some special situations if one chooses suitable values for parameters E, F and n, respectively.

1. Diffusion with Linear Adsorption Isotherm

Instead of the Freundlich adsorption isotherm, if the adsorption can be expressed by linear isotherm, or

$$q = K_q C_a \quad (62)$$

where, K_q ---linear adsorption constant, cc/gram

then the diffusional model can be solved analytically⁽⁷⁾, and the solution is:

$$\theta_b = \frac{B}{1+B} + 6B \sum_{k=1}^{\infty} \frac{\exp(-b_k^2 \tau)}{B^2 b_k^2 + 9(1+B)} \quad (63)$$

where, the b_k 's are the non-zero roots of

$$\tan(b_k) = \frac{3b_k}{3+Bb_k^2} \quad (64)$$

and

$$\tau_L = \frac{t}{R^2} \frac{De}{K_p \epsilon + \rho_b K_q} \quad (\text{dimensionless time}) \quad (65)$$

$$B = \frac{V_b}{\frac{4}{3} k \pi R^3} \frac{1}{K_p \epsilon + \rho_p K_q} = \frac{V_b}{V_p} \frac{1}{K_p \epsilon + \rho_p K_q} \quad (\text{constant}) \quad (66)$$

Thus, given the value for B, we can plot either fractional uptake or dimensionless bath concentration vs. dimensionless time.

The relationship between dimensionless forms in the above two

$$B = \frac{F}{1+E} \quad (67)$$

$$\tau_L = \frac{\tau}{1+E} \quad (68)$$

The Freundlich isotherm, if n is 1, as shown in equation(10), becomes linear. Thus, the numerical solution for the Freundlich adsorption with $n=1$ should be the same as the analytical solution for the linear adsorption shown in equation (63).

Figure 7 compares the analytical solution with linear adsorption and the numerical solution with Freundlich adsorption for $n=1$. From this figure it can be seen that these two solutions are nearly the same, indicating that the result of the numerical solution is accurate.

2. Diffusion with Small Adsorption

If the adsorption on the surface of the particle is very small as compared with the accumulation in the pore, the adsorption term has little effect on pore diffusion, and can be neglected. Figure 8 shows the numerical solution for small E (E is 0.001). From this figure, we see that the changes for the parameter n have negligible effect on the fractional uptake, as expected.

3. Diffusion with Large Adsorption

If the adsorption term is much larger than the pore accumulation term, then the pore accumulation can be neglected. For this situation, the diffusional model can be solved numerically as shown by Hashimoto⁽¹⁾. Figure 9 shows the numerical solution obtained above for a larger value of E . For comparison, we also

show the solution from Hashimoto⁽¹⁾ in Figure 9-1. From these two figures we see that the solution shown above is nearly the same as that of Hashimoto⁽¹⁾ neglecting the pore accumulation term.

4. Diffusion with Rectangular Adsorption Isotherm

If the value of parameter n in the Freundlich isotherm is very large, e. g., n is 20, the adsorption isotherm approaches a constant (rectangular) adsorption as shown in equation (61). We can still use the above method to solve the diffusional model given a larger value of n . This approximates the numerical solution for the rectangular adsorption isotherm.

For rectangular adsorption, when the change in bath concentration is negligible, the diffusional model has the approximate analytical solution as shown by Moora⁽²⁾. The approximate solution is:

$$\tau = \frac{E}{6} \left[1 - 3 \left(1 - \frac{m_t}{m_\infty} \right)^{\frac{2}{3}} + 2 \left(1 - \frac{m_t}{m_\infty} \right) \right] \quad (69)$$

Figure 10 compares the approximate analytical solution with rectangular isotherm shown in equation (69) and the numerical solution with Freundlich isotherm for larger values of n . From this figure it can be seen that these two solutions are in good agreement except at larger value of fractional uptake.

5. Diffusion with Small Bath Volume

Diffusion with small bath volume is frequently used in some areas, such as in the preparation of supported catalysts, particularly in the impregnation of novel metal supported catalysts. Figure 11 shows the fractional uptake for small values

of F. From this figure it can be seen that at some value of E, the fractional uptake curves will intersect. This property of the uptake curve indicates that as long as a suitable value of E is chosen (which can be adjusted by choosing suitable solvent), the fractional uptake could still be larger at a limited immersing time.

6. Diffusion with Large Bath Volume

Figure 12 shows fractional uptake vs. dimensionless time at larger values of F, i. e., $F=1000000$, which means that the bath concentration would be nearly constant during the diffusion and adsorption process. The equilibrium time needed for larger values of E will be much greater than that for smaller values of E.

7. Comparison of the Numerical solution with an Approximate Analytical Solution

For diffusion with negligible pore accumulation, the diffusional model has a good approximate analytical solution up to 50% fractional uptake, as shown by D. D. Do⁽³⁾. The solution is:

$$\frac{m_t}{m_\infty} = 6 \left[\frac{n\lambda}{2(\lambda+1)} \right]^{\frac{1}{2}} \tau_d^{\frac{1}{2}} - \frac{4(1+n\lambda)}{\lambda+2} \tau_d \quad (70)$$

where

$$\lambda = \frac{4-n+(n^2+4n+12)^{\frac{1}{2}}}{2(3n-1)} \quad (71)$$

$$\tau_d = \frac{\tau}{1+E} \quad (72)$$

Figure 13 compares the numerical solution developed in this report with the approximate analytical solution shown in equation(70). We see that the numerical solution and the approximate analytical solution are in good agreement up to 50% fractional uptake.

CONCLUSION

Based on the above work, the following conclusions can be drawn:

1. The intrapore diffusional model can be set up mathematically based on certain assumptions, and the mathematical model can be solved numerically.
2. The numerical solution discussed in this quarterly report can be used for typical situations given suitable values for parameters E , F and n .
3. Comparison with known solutions for special cases shows the numerical solution to be accurate.

REFERENCES

1. Hashimoto, K., et al., J. Chem. Eng. Japan, 8(5), 367(1975)
2. Moora, M. W., M. S. Degree Thesis, University of Utah, 1977
3. Gray, P. G. and Do, D. D., Ind. Eng. Chem. Res., 31 1176(1992)

$E=1$
 $F=500$

Fig. 1 Fractional Uptake at different n

$E=5$
 $F=500$

Fig. 2 Fractional Uptake at different n

$E=20.0$
 $F=500$

Fig. 3 Fractional Uptake at different n

$E=100$
 $F=500$

Fig. 4 Fractional Uptake at different n

$n=2$
 $F=500$

Fig. 5 Fractional Uptake at different E

$n=2$
 $F=500$

Fig. 5-1 Bath Concentration at Different E

$n=2$
 $E=20$

Fig. 6 Fractional Uptake at different F

$n=2$
 $E=20$

Fig. 6-1 Bath Concentration for different F

**** analytical

upward

B=0.5

B=1.0

B=2.0

B=5.0

—

numerical

upward

E

F

n

100

50.5

1

100

101

1

100

202

1

100

505

1

Fig. 7 Solution for Linear adsorption

Fig. 8 Solution for Small Adsorption

$C(0)/C(\text{inf})=0.1$
 $\text{Beta}=0.4$
 $E=18000$

Figure 9 Fractional Uptake with Large Adsorption

Fig. 9.-1 Numerical Solution of Hashimoto⁽³⁾

Fig. 10 Comparison of Numerical Solution for Freundlich Isotherm with Analytical Solution for Rectangular Isotherm

$$n=2$$

$$F=3$$

Fig. 11 Solutoin for Small Bath Volume

$n=2$
 $F=10000000$

Fig. 12 Solution for Large Bath Volume

Fig. 13 Comparison of Numerical Solution with Aprox. Analytical Solution

**DATE
FILMED**

2 / 3 / 93