LA-6757

DR 1200

UC-25

Issued: June 1977

The Melting Point of Yttria

S. R. Skaggs

los alamos
scientific laboratory
of the University of California
LOS ALAMOS, NEW MEXICO 87545

An Affirmative Action/Equal Opportunity Employer

UNITED STATES
ENERGY RESEARCH AND DEVELOPMENT ADMINISTRATION
CONTRACT W-7405-ENG. 36

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

THE MELTING POINT OF YTTRIA

by

S. R. Skaggs

ABSTRACT

Fourteen samples of 99.999% Y_2O_3 were melted near the focus of a 250-W CO_2 laser. The average value of the observed melting point along the solid-liquid interface was $2462 \pm 19^\circ C$. Several of these same samples were then melted in ultrahigh-purity oxygen, nitrogen, helium, or argon and in water vapor. No change in the observed temperature was detected, with the exception of a $20^\circ C$ increase in temperature from air to helium gas. Posttest examination of the sample characteristics, clarity, sphericity, and density is presented, along with composition. It is suggested that yttria is superior to alumina as a secondary melting-point standard.

I. INTRODUCTION

Professor Marc Föex at the CNRS Laboratoire des Ultra-Refractaires, Odiello, France, undertook the organization of a worldwide measurement of the melting point of Y_2O_3 under the auspices of the International Union of Pure and Applied Chemistry (IUPAC).^{*} The primary purpose of this study was to obtain another secondary melting-point standard at a temperature somewhat higher than that for Al_2O_3 , which melts at $2053^\circ C$. Professor Föex and Dr. Jean-Pierre Coutures prepared 20-g quantities of 99.999% Y_2O_3 in a water-cooled crucible in the 1.7-kW vertical-axis solar furnace at Odiello. All samples were prepared in atmospheric air by fusing the surface of a cup of powder. After cooling, the fused product was removed to polyethylene containers so that there was very little chance for contamination. Analysis of the sample material by emission

spectrometry at Odiello showed the material contained very few impurities (see Table I, col. 2). Samples were supplied to investigators in Australia, France, Japan, Russia, and the United States.

A 10-g sample of this material was sent to Melvin Bowman at the Los Alamos Scientific Laboratory, who passed it on to me. Observation of the melting point is a logical extension of my work several years ago on the phase relationship of Y_2O_3 - ZrO_2 , using a 250-W CO_2 laser as a heat source.¹ It also naturally follows our 1970-71 measurements of alumina melting-point depression in various atmospheres.²

We have used the same containerless technique in the observation of yttria melting that we used earlier in the study of alumina melting.³ The apparent melting of a pendant droplet was observed by taking readings over the droplet surface in the vicinity of the melt-solid interface. These same droplets were later subjected to changing atmospheres of flowing gas at a constant laser power output to observe any change that might occur in the temperature. We report here the description of the apparatus, the

^{*}Union Internationale de Chimie Pure et Appliquée; Commission des Hautes Températures et des Matériaux Refractaires "Task Force" sur les Etalons Secondaires Pour les Mesures de Température-Recherches sur le Point de Fusion de l'oxyde d'yttrium (1972).

NOTICE
This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Energy Research and Development Administration, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

TABLE I

**IMPURITY CONTENT BY EMISSION
SPECTROGRAPHIC ANALYSIS OF
SAMPLE AND SUPPORT ROD MATERIALS**

Element	Sample 99.999% Y ₂ O ₃ (ppm)	Support Rod ^a 99.9% Y ₂ O ₃ (ppm)
Al	< 10	< 10
Si	10-20	5-50
Ca	< 3	30
Fe	< 2	< 10
Ge	NR	< 30
Sr	NR	< 30
Zr	NR	< 100
Nb	NR	< 300.
La	ND	< 10.
Ce	0.6	< 100
Pr	< 0.3	< 30.
Nd	< 0.9	< 50
Sm	< 1.6	< 10.
Eu	0.6	< 3.
Gd	< 2.9	< 10.
Tb	0.25	< 50
Dy	< 1	40.
Ho	< 0.3	< 10
Tm	< 0.9	< 10
Er	< 0.9	< 10
Yb	< 1	< 3
Lu	< 0.3	< 3
W	NR	< 500
Th	NR	< 1000

NR = not reported; ND = not detected.

^aMichigan Chemical keg No. 506A.

technique employed in the temperature observations, and the results of the measurements using the laser heat source.

A. Sample Materials

Rods of 99.9% Y₂O₃, 1 mm in diameter were extruded by the Los Alamos Scientific Laboratory (LASL) Group CMB-6 to suspend the samples in front of the laser. A typical analysis of the powder used for these rods is shown in Table I, col. 3.

Ultrahigh-purity (UHP) compressed gases for the controlled atmospheres were obtained from the Linde Division of Union Carbide Corporation. Typical impurity levels in these gases, with the exception of the rare gases, were <10 ppm.

B. Laser Heat Source

The power source for heating the samples was a nominal 250-W Coherent Radiation Laboratories Model 41 continuous-wave CO₂ laser. The beam exiting the laser window was ~1 cm in diameter and was focused through KCl and NaCl lenses to a beam diameter of ~1 mm, thus producing a heat flux of ~25 kW/cm². The laser was RF-excited and emitted power at a wavelength of 10.6 μm in a continuously variable range from 5 W to slightly over 300 W. About 85% of the beam was emitted in the TEM₀₀ mode. The infrared emission of the laser did not interfere with viewing, photographing, or temperature measurements, which were all performed in the visible region of the spectrum.

C. Pendant Drop Formation

A portion of the yttria rod was suspended in a fixture just above the focus of the laser beam ~50 mm in front of the exit lens. A small solid pellet of the previously fused sample material was raised into the laser beam, and the power was increased until some melt material was formed on the pellet surface. The rod and the pellet were brought into close proximity until liquid surface tension joined the two together. The pellet support was then removed, and the power from the laser was increased until the majority or all of the pellet was molten on the end of the rod. Figure 1 shows a typical droplet with the laser beam impinging on the surface from the left and the entire droplet molten.

D. Temperature Measurement

The apparent temperature of the sample in the laser beam was measured with a Pyro automatic photoelectric pyrometer (S/N A-127) placed ~1 m from the pendant drop. The pyrometer was calibrated by the standards laboratory at Sandia

Fig. 1.

Typical all-molten pendant droplet suspended on a support rod near the laser-beam focus. The plume is material boiling from the surface near where the beam strikes it. $\sim 12.5X$.

Laboratories, Albuquerque NM. The angle of observation was slightly to the rear of perpendicular (105 – 120°) from the incident infrared beam on the same horizontal plane. The power level was adjusted so that slightly more than half of the droplet was molten. A temperature profile over the entire droplet was taken for each sample. Temperatures at points along the liquid-solid interface that were not colinear with the incident beam were considered to be characteristic of the melt temperature. Figure 2 is a schematic of a typical temperature measurement on one of these droplets.

For measuring the temperature variation with variation of atmosphere, a surface location that had a very stable temperature with time in air was chosen. This stability could be observed visually, and it could be confirmed audibly because of the change in timbre of the chopper inside the automatic photoelectric pyrometer. This same spot was observed for as long as 15 min while the surrounding gas was changed.

Fig. 2.

Schematic of a typical observed temperature distribution on a partly molten pendant drop of Y_2O_3 in air at ~ 80 kPa (625 torr).

Noguchi⁸ measured the emittance of Y_2O_3 as 0.96 at the melting point of 2446°C for a wavelength of $0.65\text{ }\mu\text{m}$. If this emittance is applied in the radiation equation to correct the observed temperature, the correction is only 12 – 13°C , which is less than the standard deviation of all of the measurements taken here.

E. Atmospheric Control

For controlled-atmosphere measurements, the droplet was suspended above a laminar-flow column into which the various gases were metered. Figure 3 shows this schematically. The droplet was initially melted in normal room air, then the desired gas was admitted to the flow column by a metering system at the bottom and was passed vertically over the molten pendant drop. The gases used were water vapor, and ultrahigh-purity oxygen, nitrogen, helium, and argon. The flow rates varied from 0.08 to 0.25 l/s.

The water vapor was produced by boiling water in a flask on a hot plate. The vapor stream was piped through flexible plastic tubing from the flask to the immediate vicinity of the molten droplet.

Fig. 3.

Schematic diagram of apparatus used to produce pendant drops of molten yttria in controlled atmospheres.

F. Observation of the Solidified Droplets

The droplets were allowed to cool to room temperature while still suspended from the yttria support rods. This prevented contamination of the hot material by contact with a containment vessel. Upon cooling, they were examined for discoloration which might indicate substoichiometry, then they were examined for sphericity, clarity, and cracks. Pycnometric density measurements were taken on several of the droplets. A petrographic thin section was prepared of the sample (#10) heated in air, then oxygen, then argon, and another thin section was prepared of the sample (#12) heated in water vapor.

III. RESULTS AND DISCUSSION

A. Physical Characteristics

The results of the visual examinations are recorded in Table II. The color of the droplets after heating appeared to be the same as before heating. The feed material was white. The same material after heating with the laser was still white; however, it had become more clear and translucent, perhaps

containing fewer internal cracks and gas bubbles. An estimate was made of the amount of internal cracking that was a direct result of cooling the droplet from its molten state to room temperature in a very short time, typically 5-10 s.

Although the gases used in the alumina melting study³ had a strong influence on the morphology of the surface after cooling, these same gases had very little effect on the surface of yttria after cooling. All of the droplet surfaces, no matter what the gas, were smooth and glassy.

The sphericity of each droplet was obtained by measuring the length of the bead vertically along a line with the support rod and dividing that figure by the maximum dimension perpendicular to this line. This technique also measured the surface tension; however, the reduction of these data is beyond the scope of this work.

A physical characteristic that was originally thought to be of significance was the apparent density, which would give some measure of the defect structure frozen into each bead. The theoretical density of Y_2O_3 is 5.031 g/cm³, and some of the cooled spherules were near this value.⁴ We also thought that the apparent density would give some measure of the internal cracks and porosity. Upon visual examination of each frozen droplet, we found that most of the droplets were translucent to transparent, with very few internal voids and only a few internal cracks.

B. Melting Temperature Measurements

Fourteen samples were heated with the laser. Some were heated several times, and others were heated only enough to obtain preliminary data (the behavior to be expected in a particular gas). Table III lists the temperatures observed near the melt-solid interface out of the direct line of incoming radiation when the samples were heated in air.

C. Temperature Change with Environment

Several of the samples were melted in air then surrounded by another gas to determine if we could detect any change in the observed temperature in a different environment. In an earlier experiment on alumina³ we noted a distinct depression of the

TABLE II

PHYSICAL CHARACTERISTICS OF SOLIDIFIED Y_2O_3 PENDANT DROPLETS

Sample	Gas	Clarity	Cracks and voids ^a	Sphericity	Apparent	density
1	air	clear to white translucent	few internal cracks	1.13	4.40	87 %TD ^b
2	air	same	few; flat on side of incident beam	1.13	4.81	96
3	air	opalescent in room light	10%	1.29	4.40	87
4	air	clear to white translucent	few	1.32	4.73	94
5	air, O ₂	same	few	1.12	4.79	95
6	air, O ₂ , air	translucent to opaque, internal bubbles	10%	1.19	4.10	82
7	air, O ₂	clear to white translucent	apparently an internal bubble broke surface during cooling	1.11	4.29	85
8	air, O ₂ , air	same	some internal cracks	1.20	4.03	80
9	air, O ₂ , Ar	same	few	1.37	not measured	
10 ^c	air, O ₂ , He, O ₂					
11	air, O ₂ , He, O ₂	same	some internal cracks	1.19	4.24	84
12 ^c	air, H ₂ O(v), air					
13	air, H ₂ O(v), air	same	few	1.13	4.58	91
14	air, N ₂ , O ₂ , air	same	few	1.20	4.80	95

^aVisual estimate.^bTheoretical density of yttria = 5.031 g/cm³.^cSamples 10 and 12 were made into petrographic thin sections.

melting temperature in UHP oxygen relative to air or argon. We began the series of tests on yttria with oxygen gas to see if we could observe a similar phenomenon. The first trial with oxygen (#5) and all

subsequent trials showed no change in temperature from air to UHP oxygen within the precision of the measurements. Also, there was no observed change in position of the melt-solid interface with a change

TABLE III

OBSERVED MELTING TEMPERATURES OF
Y₂O₃ IN AIR

Sample	T _{obs} (°C)
3	2477 2486
5	2423 2447
6	2456 2448 2459
7	2431 2451
8	2474 2496
9	2461 2449
10	2475 2473
14	2473 2478
Average value:	2462 °C
Standard deviation:	19 °C

Lowest value = 2423; highest value = 2496.
Precision = ± 4°C.

in gas, which would have indicated a change in emittance of the yttria surface because the laser power was held constant.

To drive the system harder, we heated another droplet to the melting point in air, surrounded it with oxygen for several minutes, and then immersed it in argon. The history of this droplet is shown in Table IV. The pyrometer observed a temperature that was centrally located on the surface of the

TABLE IV

PENDANT DROPLET IN AIR,
OXYGEN, AND ARGON

Gas flow (l/s)	Time (min)	T _{obs} (°C)
Room air	---	2601
0.12 UHP O ₂	1 2	2603 2600
O ₂ off	1 2 3	2602 2604 2609
0.12 UHP Ar	1 2 3 4 5	2609 2609 2605 2610 2614

droplet, hence the temperatures shown are considerably above the melting temperature. No change in the location of the melt-solid interface position was observed.

Another pendant droplet was heated in UHP oxygen for 5 min and then was immersed in helium gas. After 5 min in helium, it was again immersed in oxygen. A visible change in the stability of the droplet occurred: in oxygen the droplet tended to be quite active, moving around in the laser beam while suspended from the rod. When helium gas displaced the oxygen, the droplet assumed a quiescent state but remained molten. Upon return to oxygen, the droplet resumed its motion.

Table V shows the temperature history of this droplet. There was a distinct change in temperature of about 17°C, increasing from oxygen into helium gas and then decreasing upon return to oxygen. This direction is the opposite of the expected temperature change in terms of the increased convection-cooling power of helium gas. A change may have occurred in the emittance of the molten yttria in helium gas; however, similar temperature changes were not observed in any of the other gases. This change may not be significant because the initial temperature of

TABLE V

PENDANT DROPLET IN AIR,
OXYGEN, AND HELIUM GAS

Gas flow (l/s)	Time (min)	T _{obs} (°C)
Room air	---	2583
0.12 UHP O ₂	1	2582
	2	2569
	3	2566
	4	2568
	5	2565
0.12 He	1	2581
	2	2581
	3	2585
	4	2586
	5	2589
0.12 UHP O ₂	1	2562
	2	2564
	3	2566
	4	2559
	5	2568

TABLE VI

PENDANT DROPLET IN WATER VAPOR

Atmosphere	Time (min)	T _{obs} (°C)
Room air	---	2569
Water vapor	1	2562
	2	2561
	3	2562
	4	2565
	5	2564
	6	2555
	7	2554
	8	2548
	9	2538
	10	2556
Vapor off; room air only	1	2564
	2	2564
	3	2547
	4	2547
	5	2554

the droplet was 2583°C, and it remained at this temperature for about 1 min after the introduction of the UHP oxygen before decreasing to 2569°C. The combined precision and error of the system is ~20°C, and it is questionable whether a 17°C change is significant when compared with this figure.

We then subjected a molten pendant droplet to a steady environment of water vapor from water boiling in a flask nearby. Table VI contains the results. There was considerable variation in the temperature with time for this droplet; however, after 10 min of immersion the temperature returned to what it was before the introduction of the water vapor, so the change was not considered significant.

The final gas introduced into the system was nitrogen. Table VII shows the history of the pendant droplet in nitrogen gas. There is no apparent change in the temperature of this droplet from nitrogen gas to room air over a long period of time.

D. Ceramography

Examination of petrographic thin sections shows very few voids or cracks in either sample that was prepared. There is some evidence of twin banding near the surface of one of the spherules. This banding is probably caused by severe residual thermal stress introduced by rapid cooling. Both sections are isotropic and exhibit complete extinction in transmitted polarized light.

IV. CONCLUSIONS

The results of 17 separate measurements of the melting temperature of yttria in air were $2452 \pm 19^\circ\text{C}$. Although this constitutes a wide variation in temperature, it is to be expected when blackbody conditions for temperature observation are not used. The emittance for Y₂O₃ at the melting point is reported to be 0.96.⁸ The correction to the observed temperature owing to this emittance was

TABLE VII

PENDANT DROPLET IN NITROGEN GAS

Gas flow (l/s)	Time (min)	T _{obs} (°C)
0.08 UHP N ₂	1	2609
	2	2610
	3	2633
	4	2630
	5	2628
N ₂ off; room air only	1	2635
	2	2631
	3	2631
	4	2631
	5	2626
	6	2633
	7	2648
	8	2633
	9	2640
	10	2643

so small that it was ignored in the data reported here.

The values obtained from the observations using the laser as a heat source agreed quite well with work performed by the author several years ago in studying the ZrO₂-Y₂O₃ phase relationships above 2000°C.¹ That study yielded a value of 2460°C for the melting temperature of Y₂O₃.

It was significant that the temperature did not change appreciably with a change in the surrounding environment. In addition, the samples appeared to retain their stoichiometry regardless of what gas they were melted in. For these reasons, yttria is an excellent candidate for use as a secondary melting standard. This conclusion is further supported by comparisons of the behavior of yttria in

several atmospheres with that of alumina in these same atmospheres.²

ACKNOWLEDGMENTS

I would like to acknowledge the valuable assistance provided by Norman L. Richardson and Mary Ann David in running the experiment. It was with kind permission of Lloyd S. Nelson that we were able to use the CO₂ laser facility at Sandia Laboratories, Albuquerque. The petrographic thin sections were prepared by Harry N. Planner of the Department of Geology at the University of New Mexico. And finally I am indebted to Frank Gac and George Hurley for their critical reviews of the manuscript.

REFERENCES

1. S. R. Skaggs, "The Zirconia-yttria System above 2000°C," Sandia Laboratories research report SC-RR-72 0031 (January 1972).
2. Lloyd S. Nelson, Norman L. Richardson, Klaus Keil, and S. R. Skaggs, "Effects of Oxygen and Argon Atmospheres on Pendant Drops of Aluminum Oxide Melted with Carbon Dioxide Laser Radiation," *High Temp. Sci.* 5, 138-154 (1973).
3. Tetsuo Noguchi, "High Temperature Phase Studies with a Solar Furnace," in *Advances in High Temperature Chemistry*, Vol. 2 (Academic Press, NY, 1969), p. 248.
4. Richard C. Anderson, "Thoria and Yttria," in *High Temperature Oxides. Part II. "Oxides of Rare Earths, Titanium, Zirconium, Hafnium, Niobium, and Tantalum"* (Academic Press, NY, 1970), p. 2.