WS RC-TR--92-260

DE93 001340

**INORGANIC ANALYSES OF VOLATILIZED AND CONDENSED
SPECIES WITHIN PROTOTYPIC DEFENSE WASTE PROCESSING
FACILITY (DWPF) CANISTERED WASTE (U)**

by

C. M. Jantzen

Westinghouse Savannah River Company
Savannah River Site
Aiken, South Carolina 29808

This report was prepared in connection with work done under Contract No. DE-AC09-89SR18035 with the U.S. Department of Energy. By acceptance of this report, the publisher and/or recipient acknowledges the U.S. Government's right to retain a nonexclusive, royalty-free license in and to any copyright covering this report, along with the right to reproduce and to authorize others to reproduce all or part of the copyrighted report.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

This report has been reproduced directly from the best available copy.

Available to DOE and DOE contractors from the Office of Scientific and Technical Information, P.O. Box 62, Oak Ridge, TN 37831; prices available from (615) 576-8401, FTS 626-8401.

Available to the public from the National Technical Information Service, U.S. Department of Commerce, 5285 Port Royal Rd., Springfield, VA 22161.

WSRC-TR-92-260, Rev. 0

Keywords: glass, inorganic
species, canisters, DWPF,
canistered waste forms,
volatilization, condensation

INORGANIC ANALYSES OF VOLATILIZED AND CONDENSED SPECIES WITHIN PROTOTYPIC DEFENSE WASTE PROCESSING FACILITY (DWPF) CANISTERED WASTE (U)

CAROL M. JANTZEN

Approved by

**E.W. Holtzscheiter, Research Manager
Defense Waste Processing Technology**

Publication Date: June 30, 1992

Authorized Derivative Classifier

**Westinghouse Savannah River Co.
Savannah River Site
Aiken, SC 29808**

**PREPARED FOR THE U.S. DEPARTMENT OF ENERGY UNDER
CONTRACT DE-AC09-89SR18035**

This page intentionally left blank.

ABSTRACT

The high-level radioactive waste currently stored in carbon steel tanks at the Savannah River Site (SRS) will be immobilized in a borosilicate glass in the Defense Waste Processing Facility (DWPF). The canistered waste will be sent to a geologic repository for final disposal. The Department of Energy has defined requirements which the canistered waste must meet to be acceptable for disposal in the repository. These requirements are the Waste Acceptance Preliminary Specifications (WAPS) which require the identification of any inorganic phases that may be present in the canister that may (1) lead to internal corrosion of the canister or (2) that could potentially adversely affect normal canister handling during storage and/or during an accident.

Borosilicate waste glass is poured into the canister at a temperature of about 1000°C and the canister is filled under a slight vacuum. Potentially volatile halide and sulfate species (NaCl , NaF , NaI , CaF_2 , Na_2SO_4 , CaSO_4 , BaSO_4) are present in the waste but concentrations are limited by process constraints. During vitrification, volatilization of mixed $(\text{Na}, \text{K}, \text{Cs})\text{Cl}$, $(\text{Na}, \text{K}, \text{Cs})_2\text{SO}_4$, $(\text{Na}, \text{K}, \text{Cs})\text{BF}_4$, $(\text{Na}, \text{K})_2\text{B}_4\text{O}_7$ and $(\text{Na}, \text{K})\text{CrO}_4$ species from the surface of the glass melt have been observed to condense in the melter off-gas line above the glass melt pool and in the cyclone separator which is installed on the canister pour spout vacuum line. The volatilization and vapor phase condensation of alkali halides and sulfates throughout the DWPF melter system, including the pour spout vacuum line above the canister, indicated that similar species could possibly condense on the interior of the canister.

A full-scale DWPF prototypic canister that had been filled during Campaign 10 of the SRS Scale Glass Melter was sectioned and examined. Mixed $(\text{Na}, \text{K})\text{Cl}$, $(\text{Na}, \text{K})_2\text{SO}_4$, (Na, K) borates, and a (Na, K) fluoride phase (either NaF or Na_2BF_4) were identified as inorganic species on the interior canister walls, neck, and shoulder above the melt pour surface. Similar deposits were found on the glass melt surface and on glass fracture surfaces. Chromates were not identified on the interior of the canister. Spinel crystals were found associated with the glass pour surface. Vaporization of species from the melt as it enters the canister and condensation on the interior canister shoulder and neck as the glass is poured is the most likely mechanism by which the halide and sulfate species are deposited. Reference amounts of the halides and sulfates were found retained in the glass and the glass chemistry, including the distribution of the halides and sulfates, was homogeneous.

Rust was visibly present and identified in the DWPF prototypic canister. In all cases where rust was observed, heavy metals (Zn , Ti , Sn) from the cutting blade/fluid were present indicating that the rust was a reaction product of the cutting fluid with the glass and with the heat sensitized canister or with carbon steel contamination on the canister interior which occurs during fabrication and handling. Measured relative humidity in sealed simulated waste glass canisters indicates that only minimal water vapor is present so that internal corrosion of the canister, as observed in this sectioned canister, will not occur.

This page intentionally left blank.

TABLE OF CONTENTS

	<u>Page</u>
Abstract	3
Introduction	7
Experimental	9
Glass and Deposit Sampling	9
Glass Composition Analyses	9
X-ray Diffraction and Scanning Electron Microscopy Analysis	12
Quality Assurance	12
Results and Discussion	13
Glass Composition Analyses	13
Deposit and Reaction Product Analyses	13
Conclusions	26
Acknowledgement	27
References	35
Appendix I	37

This page intentionally left blank.

INORGANIC ANALYSES OF VOLATILIZED AND CONDENSED SPECIES WITHIN PROTOTYPIC DEFENSE WASTE PROCESSING FACILITY (DWPF) CANISTERED WASTE (U)

INTRODUCTION

The high-level radioactive waste currently stored in carbon steel tanks at the Savannah River Site (SRS) will be immobilized in a borosilicate glass in the Defense Waste Processing Facility (DWPF). The canistered waste will be sent to a geologic repository for final disposal. The Department of Energy has defined requirements which the canistered waste must meet to be acceptable for disposal in the repository. These requirements are the Waste Acceptance Preliminary Specifications (WAPS).¹ Specification 3.9 of the WAPS is the chemical compatibility specification. Specification 3.9 requires the identification of any inorganic phases that may be present in the canister that may (1) lead to internal corrosion of the canister or (2) that could potentially adversely affect normal canister handling during storage and/or during an accident. Internal canister corrosion, chemical species, and any reaction products forming due to chemical interactions within the canistered waste after exposure to temperatures up to the glass transition temperature are to be identified.

The vitrification process operates at 1150°C at a nominal melter residence time of 65 hours.² The borosilicate waste glass is poured into a canister at a temperature of about 1000°C under a slight vacuum. Potentially volatile halide and sulfate species (NaCl, NaF, NaI, CaF₂, Na₂SO₄, CaSO₄, BaSO₄) are present in the waste.³⁻⁵ Process constraints limit the total amount of NaCl to <0.6 wt%, NaF to <0.1 wt%, and SO₄²⁻ species to <0.4 wt% of the glass.⁶ The seven projected DWPF glass compositions described in the DWPF Waste Form Compliance Plan (WCP)^{2, 4-5} have NaCl concentrations of 0.09 to 0.31 wt%, NaF concentrations of 0.04 to 0.08 wt%, NaI concentrations of <0.0009 wt%, CaF₂ concentrations of <0.008 wt%, and SO₄²⁻ concentrations (from Na₂SO₄ + CaSO₄ + BaSO₄) of 0.165 to 0.284 wt%. These waste species are melted with borosilicate glass frit chemicals and with other alkali borate waste stream species to form the borosilicate nuclear waste glass.

During vitrification, the species present in the waste, frit, and alkali borate waste stream are homogenized, and volatilization of chemical constituents with the highest vapor pressures occurs. Volatilization of mixed (Na, K, Cs)Cl, (Na, K, Cs)₂SO₄, (Na, K, Cs)BF₄, (Na, K)₂B₄O₇ and (Na,K)CrO₄ species from the surface of the glass melt have been observed to condense in the melter off-gas line above the glass melt pool.⁷⁻⁹ In addition, deposits highly enriched in NaCl, Na₂SO₄ and KBF₄ have been observed in the cyclone separator which is installed on the canister pour spout vacuum line.⁷ The volatilization and vapor phase condensation of alkali halides and sulfates throughout the DWPF melter system, including the pour spout vacuum line above the canister, indicated that similar species could possibly condense on the interior of the canister.

The presence of halides and fluorides on the canister interior is not of concern unless water vapor is present. Halides in the presence of water vapor could initiate internal stress corrosion cracking of the 304L canister. Since the glass enters the canister at $\sim 1000^{\circ}\text{C}$, and the canister is under a slight vacuum, free liquids will not enter the canister with the molten glass stream. Any liquids or moisture present in the canister prior to pouring are unlikely to remain due to the heat of the molten glass and the reduced pressure.² The only path by which water or water vapor could enter the canister is during the decontamination of the canister with a frit/water slurry. However, a shrink-fit seal has been developed to ensure that this slurry does not enter the canister.¹⁰ This temporary canister closure seal will be inserted into the canister neck after filling, and before canister decontamination, to prevent inleakage of the decontamination slurry. Every temporary canister closure will be tested to ensure that it is water tight.

The measured relative humidity in sealed simulated waste glass canisters ranged from 5.5 to 18.5%, consistent with the absence of water which would increase the relative humidity to 100%.¹¹ The measured relative humidity in the waste glass canisters agrees with previously calculated values.¹²⁻¹³ The only difference in the gas phases noted within the canister was a decreased CO_2 content relative to air. No other organics, pyrophorics, combustibles, or explosives have been identified in the gas phase of the canistered waste.¹¹

The present study was initiated to document the inorganic (non-waste glass) species, e.g. the waste glass volatiles, that might have condensed on the interior of the stainless steel waste canisters and any reaction products observed. The mechanism by which the reaction products formed was also to be determined.

EXPERIMENTAL

Glass and Deposit Sampling

A full-scale DWPF prototypic canister (~120" height) that had been filled during the SRS Scale Glass Melter (SGM) Campaign 10 was sectioned at 80" height with a band saw (Figure 1). The second canister of the SGM 10 Campaign, SGM 10-2 (Canister A-8), was chosen for sampling because the SGM 10 feed contained the reference amounts of halides and sulfates.¹⁴ Sectioning of the canister occurred about 6 months prior to sampling.

DWPF canisters are filled to a reference height of ~91" with glass. Sectioning canister 10-2 from 80 to 120" provided about 11" of glass for sampling (Figure 1). The glass was chiseled out of the canister in fist size pieces in order to ensure that the orientation of the melt surface was preserved for sampling of deposits. Glass samples were taken at the 80" sectioned surface near the edge and in the center of the canister (Figure 2) for determination of the glass composition. Samples of glass from the edge and center of the canister were also taken at 86" and 89" heights (Figure 2) to look for chemical variation of the glass and/or halide and sulfate content in the canister.

Forty four glass samples, including the melt surface, fracture surfaces, and glass adjacent to the canister walls were sampled for solids/deposit analysis. When the glass was completely removed from the canister, visible deposits on the shoulder and neck of the canister (Figure 3) were removed with scotch tape for solids/deposit analysis. Two additional samples of deposits were collected by flushing off the canister shoulder with deionized water. An eyedropper was used to transfer the liquid to a watch glass. One half of each liquid sample was dried at 90°C for solids analysis and one half sent for chemical analysis.

Glass Composition Analyses

The six glass samples were analyzed in duplicate by the following techniques:

- Dissolution by Na_2O_2 with an HCl uptake
 - ICP for Al, Ca, Fe, Mg, Mn, Li, Si, Cr, B, Sr, Ti, P, Ba, Pb, Mo, Zn, Cu, Ni, La, Cd
- Dissolution by HCl/HF microwave
 - ICP for Na, Zr, Sn
 - AA for Na, K, Si
- Dissolution by Na_2O_2 with a H_2O uptake
 - IC for SO_4 , NO_3 , and PO_4
 - ISE for Cl and F

where ICP is Inductively Coupled Plasma Spectroscopy, AA is Atomic Absorption analysis, IC is Ion Chromatography analysis, and ISE is Ion Selective Electrode analysis. The liquid water flush deposits were submitted for Cl and F analysis by ISE.

Figure 1 Schematic of full scale DWPF prototypic canister (Canister A-8, SGM 10-2) sectioned at 80 inch height for analysis of inorganic canister species.

Figure 2 Positions of six glass samples taken to examine the chemical homogeneity of the glass in Canister A-8 (SGM 10-2).

Figure 3 Position of eight deposit samples removed with tape for solids analysis in Canister A-8 (SGM 10-2).

X-ray Diffraction and Scanning Electron Microscopy Analyses

X-ray diffraction (XRD) and Scanning Electron Microscopy (SEM) analyses coupled with Energy Dispersive Analysis by X-ray (EDAX) were performed on the 44 glass samples and the 8 tape samples in order to determine the phase and chemical composition of any deposits and/or reaction products. Dried solids from the water flush were analyzed by XRD, SEM and EDAX as well.

QUALITY ASSURANCE

The SRTC Glass Technology Task Control Matrix for all the tasks in this study is given in Reference 15. All tasks were carried out in accordance with RW-0214 and NQA-1. Analytical Development Section (SRTC/ADS) procedures were followed for all chemical analyses.

Glass and deposit analyses are recorded in WSRC-NB-92-201.

RESULTS AND DISCUSSION

Glass Composition Analyses

The analyses of the twelve glass samples taken from the top of canister SGM 10-2 are given on a normalized oxide basis in Table I. The anion analyses for Cl, F, and SO_4 are given in element wt%. The detailed chemical analyses are given in Appendix I. The maximum standard deviations on the twelve glass samples is <1.0 with the analyses for Na_2O being the poorest, ± 0.94 wt% followed by the analyses for SiO_2 , ± 0.77 wt%.

The average oxide composition of the SGM 10-2 glass is similar to that analyzed at the end of the SGM-10 Campaign when the melter was drained (Table I).¹⁶ The target alkali oxide/ SiO_2 and $\text{B}_2\text{O}_3/\text{SiO}_2$ ratios for the feed for the SGM 10 Campaign were 0.23 and 0.43, respectively.¹⁷ The corresponding ratios for the glass in canister SGM 10-2 were 0.21 and 0.42. The ratios measured at the end of the SGM-10 Campaign were 0.23 and 0.37.

The reference amount of chlorides and halides added to SGM 10 were based on the process constraints of $\text{NaCl} < 0.6$ wt%, $\text{NaF} < 0.1$ wt% and $\text{SO}_4^{2-} < 0.4$ wt%. This is equivalent to $\text{Cl} < 0.364$ wt%, $\text{F} < 0.036$, and $\text{SO}_4^{2-} < 0.4$ wt%. Table I indicates that the average concentrations of these species in the canister 10-2 glass are 0.37 wt% Cl, 0.02 wt% F, and 0.16 wt% SO_4^{2-} .

The chemical analyses in Table I indicate that the SGM 10-2 canister glass was homogeneous. No chemical gradients in the oxides, halide, or sulfate compositions were observed when the compositions of the samples taken from the edge were compared to those taken from the center of the canister.

Deposit and Reaction Product Analyses

The analysis of the fifty two glass and deposit samples taken from canister SGM 10-2 are given in Table II. The small amounts of deposit material precluded any type of analysis but Scanning Electron Microscopy (SEM) coupled with quantitative elemental Energy Dispersive Analysis by X-ray (EDAX). The stoichiometry of the phases observed during SEM analysis was determined by the similarity of these smaller deposits to larger deposits of the same chemistry found in the off-gas lines and in the cyclone separator of several SRS scale glass melters.⁷⁻⁹

Three deposit samples had sufficient volume that comparative X-ray Diffraction (XRD) and SEM analysis could be performed. The speciation determined by SEM was similar to that observed during XRD analysis (Table III). The samples that had been flushed from the top shoulder and sides of the canister interior and dried were analyzed by XRD and SEM (Table IV). There was insufficient liquid from the flushing to enable quantitative Cl and F analyses.

Table 1. Composition of Glasses Sampled in Canister SGM-10-2

OXIDE WT%	2/3 + 0 EDGE-A #200038840	2/3 + 0 EDGE-B #200038841	2/3 + 0 CEN-A #200038842	2/3 + 0 CEN-B #200038843	2/3 + 6 EDGE-A #200038844	2/3 + 6 EDGE-B #200038845	2/3 + 6 CEN-A #200038846	2/3 + 6 CEN-B #200038847
Al ₂ O ₃	3.55	3.13	3.55	3.13	5.38	3.45	3.40	3.32
CaO	1.33	1.34	1.33	1.34	1.41	1.29	1.24	1.04
Fe ₂ O ₃	11.15	9.69	11.15	9.69	10.62	10.90	10.88	10.74
MgO	0.84	0.85	0.84	0.85	0.84	0.85	0.82	0.80
MnO	2.19	1.92	2.19	1.92	2.10	2.12	2.03	2.11
Na ₂ O	10.95	11.99	10.95	11.99	11.62	11.72	12.83	13.61
Li ₂ O	4.47	4.61	4.47	4.61	4.37	4.52	4.40	4.38
NiO	0.94	0.81	0.94	0.81	0.89	0.90	0.89	0.87
SiO ₂	50.84	51.65	50.84	51.65	49.54	50.61	49.98	49.59
Cr ₂ O ₃	0.15	0.11	0.15	0.11	0.11	0.10	0.11	0.12
B ₂ O ₃	12.07	12.35	12.07	12.35	11.67	12.04	11.94	11.73
SrO	0.04	0.05	0.04	0.05	0.05	0.04	0.04	0.04
ZrO ₂	0.68	0.71	0.68	0.71	0.64	0.70	0.69	0.73
TiO ₂	0.15	0.14	0.15	0.14	0.14	0.13	0.14	0.16
K ₂ O	0.43	0.45	0.43	0.45	0.36	0.43	0.44	0.48
P ₂ O ₅	0.10	0.07	0.10	0.07	0.14	0.05	0.03	0.04
BaO	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.01
ZnO	0.12	0.13	0.12	0.13	0.12	0.13	0.11	0.22
Cl	0.46	0.41	0.46	0.41	0.39	0.43	0.35	0.33
F	0.03	0.02	0.03	0.02	0.02	0.02	0.02	0.02
SO ₄	0.16	0.15	0.16	0.15	0.16	0.17	0.18	0.19
OXIDE SUMS	100.00	100.00	100.00	100.00	100.00	100.00	100.00	100.00
MOLAR BALANCE (M)								
SALTS	1.11	1.04	1.11	1.04	0.94	1.05	0.92	0.96
OXIDES	98.89	98.96	98.89	98.96	99.06	98.95	99.08	99.04
CALCULATED PARAMETERS								
ALK/SiO ₂	0.39	0.41	0.39	0.41	0.41	0.41	0.43	0.45
B ₂ O ₃ /SiO ₂	0.20	0.21	0.20	0.21	0.20	0.21	0.21	0.20
VISCOSITY (Poise at 1150°C)	43	38	43	38	45	37	31	27
LIQUIDUS (°C)	949	911	949	911	959	944	947	945

Table 1. Composition of Glasses Sampled in Canister SGM-10-2 (Cont'd)

OXIDE WT%	2/3 + 9 EDGE-A #200038848	2/3 + 9 EDGE-B #200038849	2/3 + 9 CEN-A #200038850	2/3 + 9 CEN-B #200038851	AVERAGE COMP	STD DEV	SGM-10 DRAIN GLASS
Al ₂ O ₃	3.47	3.36	3.35	3.36	3.54	0.60	4.22
CaO	1.06	1.01	0.96	1.27	1.22	0.15	1.41
Fe ₂ O ₃	10.89	10.79	10.77	10.75	10.67	0.48	13.45
MgO	0.84	0.80	0.77	0.83	0.83	0.02	0.60
MnO	2.18	2.11	2.12	2.09	2.09	0.09	1.72
Na ₂ O	11.54	13.31	13.31	12.96	12.23	0.94	12.85
Li ₂ O	4.48	4.40	4.37	4.42	4.46	0.09	4.02
NiO	0.91	0.90	0.90	0.88	0.89	0.04	1.21
SiO ₂	50.99	49.81	49.64	50.03	50.43	0.77	47.28
Cr ₂ O ₃	0.11	0.10	0.11	0.10	0.11	0.02	0.3
B ₂ O ₃	12.04	11.90	12.13	11.84	12.01	0.21	11.04
SrO	0.04	0.04	0.04	0.04	0.04	0.00	0.3
ZrO ₂	0.69	0.72	0.73	0.69	0.70	0.02	0.5
TiO ₂	0.13	0.13	0.14	0.13	0.14	0.01	0.3
K ₂ O	0.43	0.44	0.47	0.45	0.44	0.03	0.8
P ₂ O ₅	0.06	0.04	0.04	0.03	0.06	0.03	
BaO	0.01	0.01	0.01	0.00	0.01	0.00	
ZnO	0.13	0.14	0.13	0.13	0.14	0.03	
Cl	0.36	0.23	0.38	0.26	0.37	0.07	
F	0.02	N/A	N/A	N/A	0.02	0.00	
SO ₄	0.17	0.15	0.11	0.18	0.16	0.02	
OXIDE SUMS	100.00	100.00	100.00	100.00	100.00		100.00
MOLAR BALANCE (M)							
SALTS	0.97	0.67	0.87	0.74	0.95		
OXIDES	99.03	99.33	99.13	99.26	99.05		
CALCULATED PARAMETERS							
ALK/SiO ₂	0.40	0.44	0.44	0.43	0.42		0.37
B ₂ O ₃ /SiO ₂	0.20	0.21	0.21	0.20	0.21		0.23
VISCOSITY (Poise at 1150°C)	40	29	28	31	36		
LIQUIDUS (°C)	942	946	946	943	941		

Table II. Phase Identification of Canister Deposits.

<u>Sample ID</u>	<u>Sample Identification</u>	<u>SEM Analysis</u>
A	Top of neck of canister	spinel/rust (Fe, Ni, Cr) glass (Si, Al, Fe, Ca, etc) (Na,K)Cl (Na,K) ₂ SO ₄ NaF phase
B	Inside of Seal	spinel/rust (Fe, Ni, Cr) (Na,K)Cl (Na,K) ₂ SO ₄
C	Inside of Seal	spinel/rust (Fe, Ni, Cr) trace of glass (Si, Al, Fe, Ca, etc) trace of (Na,K)Cl trace of (Na,K) ₂ SO ₄
D	Top of neck of canister	spinel/rust (Fe, Ni, Cr) glass (Si, Al, Fe, Ca, etc) (Na,K)Cl (Na,K) ₂ SO ₄ NaF phase
E	Outside of Flange	(Na,K)Cl (Na,K) ₂ SO ₄ Sn, Ti, Zn from cutting fluid/blade
F	Inside Neck of canister "rust"	rust (high Fe, Ni, Cr) trace of B as Na ₂ B ₄ O ₇ trace of (Na,K)Cl trace of (Na,K) ₂ SO ₄ Ti from cutting fluid/blade
G	Side of canister above glass melt line	Sn, Ti, Zn from cutting fluid/blade spinel/rust (Fe, Ni, Cr) (Na,K)Cl (Na,K) ₂ SO ₄ NaF phase

Table II. Phase Identification of Canister Deposits (continued).

<u>Sample ID</u>	<u>Sample Identification</u>	<u>SEM Analysis</u>
H	White streaky deposit on side of canister above glass melt line	spinel/rust (Fe, Ni, Cr) Al, Si rich material Zn from cutting fluid/blade glass (Si, Al, Fe, Ca, etc) (Na,K)Cl (Na,K) ₂ SO ₄
I	Smear of bottom of inner canister closure plug	trace spinel/rust (Fe, Ni, Cr) trace of (Na,K)Cl trace of (Na,K) ₂ SO ₄
J	Gray powder from glass surface	W, Ti, Zn from cutting fluid/blade glass (Si, Al, Fe, Ca, etc) trace of (Na,K)Cl trace of (Na,K) ₂ SO ₄
K	White deposits near glass pour surface	glass (Si, Al, Fe, Ca, etc) (Na,K)Cl (Na,K) ₂ SO ₄ NaF phase Zn from cutting fluid/blade
L	Dark brown deposits near glass pour surface	glass (Si, Al, Fe, Ca, etc) (Na,K)Cl spinel/rust (Fe, Ni, Cr) W, Ti, Zn from cutting fluid/blade
M	Top of Pour Surface	glass (Si, Al, Fe, Ca, etc)
N	Top of Pour Surface	glass (Si, Al, Fe, Ca, etc) (Ca, K) ₂ SO ₄ Zn from cutting fluid/blade
O	Top of Pour Surface	glass (Si, Al, Fe, Ca, etc) spinel/rust (Fe, Ni, Cr)

Table II. Phase Identification of Canister Deposits (continued).

<u>Sample ID</u>	<u>Sample Identification</u>	<u>SEM Analysis</u>
P	Brown deposit on canister side below melt surface	glass (Si, Al, Fe, Ca, etc) (Na,K)Cl spinel/rust (Fe, Ni, Cr) B (either glass or Na ₂ B ₄ O ₇) Ti, Zn from cutting fluid/blade
Q	Glass with large bubbles	glass (Si, Al, Fe, Ca, etc) spinel/rust (Fe, Ni, Cr) Ti, Zn from cutting fluid/blade
R	"Pock" mark on side of canister below melt surface	Sn, Ti, Zn from cutting fluid/blade a lot of dendritic (Na,K)Cl trace of (Na,K) ₂ SO ₄ spinel/rust (Fe, Ni, Cr) spinel crystals (Fe, Ni, Cr)
S	"Blister" on side of canister below melt surface	glass (Si, Al, Fe, Ca, etc) (Na,K)Cl (Na,K) ₂ SO ₄
T	Deposits from "wet" glass	glass (Si, Al, Fe, Ca, etc) (Na,K)Cl (Na,K) ₂ SO ₄
U	Brown deposit on glass	glass (Si, Al, Fe, Ca, etc) (Na,K)Cl (Na,K) ₂ SO ₄ NaF phase
V, W	Deposits on glass	glass (Si, Al, Fe, Ca, etc) Zn from cutting fluid/blade
X	Deposits on top glass surface	glass (Si, Al, Fe, Ca, etc) (Na,K)Cl (Na,K) ₂ SO ₄ Ti from cutting fluid/blade

Table II. Phase Identification of Canister Deposits (continued).

<u>Sample ID</u>	<u>Sample Identification</u>	<u>SEM Analysis</u>
Y	Deposits on top glass surface	glass (Si, Al, Fe, Ca, etc) (Na,K)Cl (Na,K) ₂ SO ₄ spinel/rust (Fe, Ni, Cr) Sn,Ti from cutting fluid/blade
Z	Deposits on top glass surface	glass (Si, Al, Fe, Ca, etc) (Na,K)Cl (Na,K) ₂ SO ₄ spinel/rust (Fe, Ni, Cr)
AA	Deposits on top glass surface	glass (Si, Al, Fe, Ca, etc) dendritic (Na,K)Cl spinel/rust (Fe, Ni, Cr)
BB	Deposits on top glass surface with visible powdery deposits	glass (Si, Al, Fe, Ca, etc) spinel/rust (Fe, Ni, Cr)
CC	Melt pour surface	glass (Si, Al, Fe, Ca, etc) (Na,K)Cl (Na,K) ₂ SO ₄
DD	White deposit embedded in glass	Na aluminosilicate W from cutting fluid/blade
EE, FF	Melt pour surface	glass (Si, Al, Fe, Ca, etc) W,Ti, Zn from cutting fluid/blade (Na,K)Cl (Na,K) ₂ SO ₄
GG	Clean glass fracture surface at top of canister	glass (Si, Al, Fe, Ca, etc)
HH	Glass fracture surface with brown deposits	glass (Si, Al, Fe, Ca, etc) cubic (Na,K)Cl crystals (Na,K) ₂ SO ₄ NaF phase

Table II. Phase Identification of Canister Deposits (continued).

<u>Sample ID</u>	<u>Sample Identification</u>	<u>SEM Analysis</u>
II	Glass fracture surface at top of canister	glass (Si, Al, Fe, Ca, etc) (Na,K)Cl (Na,K) ₂ SO ₄ NaF phase
JJ	Opposite side of fracture surface in II	Sn, Ti from cutting fluid glass (Si, Al, Fe, Ca, etc) (Na,K)Cl (Na,K) ₂ SO ₄ NaF phase
KK	Glass fracture surface at top of canister	Sn, Ti, Ni, Cu, W from cutting fluid glass (Si, Al, Fe, Ca, etc) (Na,K)Cl (Na,K) ₂ SO ₄
LL	Glass fracture surface at top of canister	glass (Si, Al, Fe, Ca, etc) Sn from cutting fluid spinel/rust (Fe, Ni, Cr) (Na,K)Cl (Na,K) ₂ SO ₄
MM	Glass fracture surface at top of canister with brown deposits	W, Sn, Ti from cutting fluid/blade glass (Si, Al, Fe, Ca, etc) spinel/rust (Fe, Ni, Cr) (Na,K)Cl (Na,K) ₂ SO ₄
NN, OO	Glass fracture with "blister"	spinel crystals in small vugs (Fe, Ni, Cr) rust (Fe, Ni, Cr) glass (Si, Al, Fe, Ca, etc) trace (Na,K)Cl trace (Na,K) ₂ SO ₄
PP	Elliptical bubbles (vugs)	glass (Si, Al, Fe, Ca, etc) spinel/rust (Fe, Ni, Cr) (Na,K)Cl (Na,K) ₂ SO ₄

Table II. Phase Identification of Canister Deposits (continued).

<u>Sample ID</u>	<u>Sample Identification</u>	<u>SEM Analysis</u>
QQ	Tape smear of melt pour surface	spinel/rust (Fe, Ni, Cr) glass (Si, Al, Fe, Ca, etc) (Na,K)Cl (Na,K) ₂ SO ₄
RR	Miscellaneous deposits	Sn from cutting fluid/blade glass (Si, Al, Fe, Ca, etc) spinel/rust (Fe, Ni, Cr) (Na,K)Cl (Na,K) ₂ SO ₄
SS	Clean glass fracture surface at top of canister	glass (Si, Al, Fe, Ca, etc) spinel crystals (Fe, Ni, Cr) Sn from cutting fluid/blade (Na,K)Cl (Na,K) ₂ SO ₄
TT	Deposits on interior shoulder of canister	glass (Si, Al, Fe, Ca, etc) W, Cu from cutting fluid/blade (Na,K)Cl (immiscible in SO ₄ phase) (Na,K) ₂ SO ₄ (immiscible in Cl phase)
UU	Glass fracture surface at top of canister	glass (Si, Al, Fe, Ca, etc) W, Ti from cutting fluid/blade spinel/rust (Fe, Ni, Cr) (Na,K)Cl (immiscible in SO ₄ phase) (Na,K) ₂ SO ₄ (immiscible in Cl phase)
VV	White deposits on glass stringer near interior shoulder of canister	glass (Si, Al, Fe, Ca, etc) Sn from cutting fluid/blade large cubic (Na,K)Cl crystals (Na,K) ₂ SO ₄
WW	Glass fracture surface at top of canister	glass (Si, Al, Fe, Ca, etc) Sn,Ti from cutting fluid/blade spinel/rust (Fe, Ni, Cr) (Na,K)Cl (Na,K) ₂ SO ₄

Table II. Phase Identification of Canister Deposits (continued).

<u>Sample ID</u>	<u>Sample Identification</u>	<u>SEM Analysis</u>
XX	Fractured melt pour surface	glass (Si, Al, Fe, Ca, etc) Ti from cutting fluid/blade spinel/rust (Fe, Ni, Cr) (Na,K)Cl trace (Na,K) ₂ SO ₄
YY	Glass in contact with canister sidewall	glass (Si, Al, Fe, Ca, etc) spinel/rust (Fe, Ni, Cr) (Na,K)Cl trace (Na,K) ₂ SO ₄
ZZ	Bubbles (vugs) on melt surface	glass (Si, Al, Fe, Ca, etc) spinel crystals (Fe, Ni, Cr) (Na,K)Cl trace (Na,K) ₂ SO ₄

Table III Comparison of Scanning Electron Microscopy (SEM) and X-ray Diffraction (XRD) Deposit Identification.

<u>Sample ID</u>	<u>Sample Identification</u>	<u>SEM Analysis</u>	<u>XRD Analysis</u>
E	Outside of Flange	(Na,K)Cl (Na,K) ₂ SO ₄ Sn, Ti, Zn from cutting fluid/blade	Al ₂ Si ₂ O ₅ (OH) ₄ KB ₃ O ₅ ZnO, TiO ₂
F	Inside Neck of canister "rust"	rust (high Fe, Ni, Cr) trace of B as Na ₂ B ₄ O ₇ trace of (Na,K)Cl trace of (Na,K) ₂ SO ₄ Ti from cutting fluid/blade	Fe ₂ O ₃ KB ₃ O ₅
H	White streaky deposit on side of canister above glass melt line	spinel/rust (Fe, Ni, Cr) Al, Si rich material Zn from cutting fluid/blade glass (Si, Al, Fe, Ca, etc) (Na,K)Cl (Na,K) ₂ SO ₄	amorphous

Table IV Liquid Samples Flushed from Side Walls of Canister

<u>Sample Identification</u>	<u>SEM Analysis</u>	<u>XRD Analysis</u>
Flush Top Solid	glass (Si, Mn, Fe) (Na,K)Cl (Na,K)SO ₄	Insufficient Sample
Flush Side Solid	glass (Si, Fe, Mn, Ni, Cr) spinel/rust (Fe, Mn, Ni, Cr) (Na,K)Cl (Na,K)SO ₄	NaCl

The off-gas line and cyclone separator deposits of scale glass melters at SRS were shown to form by vapor phase transport and condensation.⁷⁻⁹ Vaporization of species from the melt as it enters the canister and condensation on the interior canister shoulder and neck as the glass is poured is the most likely mechanism by which halide and sulfate species could be deposited in these regions of the canister. The vapor phase transported phases observed in the off-gas line deposits were identified by XRD and include the following:

- Sodium/potassium/cesium salts
 $(\text{Na}, \text{K}, \text{Cs})_2\text{SO}_4$
 $(\text{Na}, \text{K}, \text{Cs})\text{Cl}$
 $(\text{Na}, \text{K}, \text{Cs})\text{BF}_4$
- Sodium/potassium borate
 $(\text{Na}, \text{K})_2\text{B}_4\text{O}_7$
- Sodium/potassium chromates
 $(\text{Na}, \text{K})_2\text{CrO}_4$

Similar $(\text{Na}, \text{K})_2\text{SO}_4$ and $(\text{Na}, \text{K})\text{Cl}$ deposits were identified on the samples of tape which had been used to remove deposits from the shoulder and side of the interior of canister SGM 10-2 above the glass fill line (Samples A through H; Table II, III, Figure 3). An NaF phase presumed to be $(\text{Na}, \text{K})_2\text{BF}_4$ was also identified in many of these samples. The positive identification of this phase is complicated by the fact that the conventional SEM/EDAX detector is not sensitive to elements as light in atomic weight as B. Hence, the EDAX spectra for NaF and Na_2BF_4 appear identical. Positive identification of a borate phase in Sample F from the inside neck of the canister was made by XRD (Table III). Reanalysis of sample F by EDAX with a wide angle detector indicated that B was, indeed, present (Table II). The phase was assumed to be $(\text{Na}, \text{K})_2\text{B}_4\text{O}_7$ as identified in the off-gas line deposits. Distribution of $(\text{Na}, \text{K})_2\text{B}_4\text{O}_7$ may be more ubiquitous but the presence of this phase is difficult to establish due to its amorphous nature upon condensation. The only other borate deposits noted on the interior walls of the canister above the melt line were traces of shards of glass.

Alkali chromates were not identified on the interior of the SGM 10-2 canister as they were in the SGM off-gas line deposits. The presence of alkali chromates in the off-gas line was complicated by evidence that the deposits were formed by reaction of the other alkali salts with chromium from the Inconel 690 off-gas pipe. Chromate deposits may, therefore not form when the other alkali salts interact with 304L stainless steel. The chromium rich phases that were detected during EDAX analysis of the SGM 10-2 canister deposits were primarily spinel crystals and/or Fe-Cr-Ni rich deposits of rust. However, the presence of alkali chromates as condensates in the canister interior can not be precluded.

Rust was visibly present on the shoulder and side of the interior of canister SGM 10-2 above the glass fill line (Samples A through H; Table II, III, Figure 3). The analysis of rust by SEM/EDAX is complicated by the fact that the EDAX spectra for rust and spinel appear the same, e.g. deposits enriched in Fe, Ni and Cr. If spinel crystals could not be identified morphologically the phase identification in Table II was given as spinel/rust. Positive identification of Fe_2O_3 rust was made in Sample F by XRD analysis (Table III). The bottom of the inner canister closure plug, sample I,

was not rusted and the identification of traces of rust, halides, and sulfates (Table II) is likely loose particulates from the neck of the canister that were deposited on the closure plug when the canister was lying on its side after sectioning and during sampling.

In almost all cases, when rust was identified as being present, Ti, W, Zn, Sn or aluminosilicate material from the cutting blade and fluid was also present, indicating that the cutting fluid had penetrated through or around the 11" of glass and come in contact with the halides and sulfates that had condensed on the interior shoulder and neck of the canister. The Ti, W, Zn and Sn are known to be embedded in the cutting blade of the band-saw used to section the canister, and significant amounts of them are not present in the glass (Table I). The aluminosilicate and rust deposits are, therefore, most likely reaction products of the cutting fluid with the glass and the heat sensitized canister or carbon steel contamination, which occurs on the canister interior during fabrication and handling. Samples of deposits on the glass pour surface, Samples J and K, indicated that a grey-white powder enriched in the W, Ti and Zn from the cutting blade/fluid was indeed present.

Glass pour surface samples L through Q indicated the same halide, sulfate, borate, rust and/or spinel deposits and Sn, Ti, Zn from the cutting blade/fluid (Table II). Deposits on glass fracture surfaces from the pour surface to the saw blade surface (L through ZZ) indicated the same types of deposits (Table II). Some of the samples were still wet (Sample T) although the canister had been sectioned several months before sampling.

Samples HH and II which were glass fracture surfaces from near the top of the canister exhibited cubic crystals of NaCl, molten globules of the NaF and Na₂SO₄ phases and dendritic growths of mixed (Na,K)Cl phase (Figure 4-7). Samples TT and UU indicated that the (Na,K)Cl and (Na,K)SO₄ phases were immiscible in each other as suggested during heat treatment studies of similar species in the off-gas deposits.⁷⁻⁹ Sample VV, which appeared as white deposits on a glass stringer near the interior shoulder of the canister also contained large cubic NaCl crystals. The solid dried samples flushed from the canister shoulder (Table IV) indicated that the NaCl had recrystallized to a dendritic form after flushing and drying the halide from the canister interior (Figure 8). Spinel crystals were often found associated with the glass pour surface (Figure 9).

CONCLUSIONS

Mixed (Na,K)Cl, (Na,K)₂SO₄, (Na,K) borates, and a (Na,K) fluoride phase (either NaF or Na₂BF₄) were identified as inorganic species on the interior canister walls, neck, and shoulder above the melt pour surface. Similar deposits were found on the glass melt surface and on glass fracture surfaces. Spinel crystals were only found associated with the glass pour surface.

The stoichiometry of these deposits is similar to the phases identified in scale glass melter off-gas systems. The off-gas deposits form by vapor-phase transport and condensation. Vaporization of species from the melt as it enters the canister and condensation on the interior canister shoulder and neck as the glass is poured is the most likely mechanism by which halide and sulfate species could be deposited in these regions of the canister. Reference amounts of the halides and sulfates were found to be retained in the glass and the glass chemistry, including the distribution of the halides and sulfates, was homogeneous.

Rust was visibly present and identified by both SEM and XRD analysis. In all cases where rust was observed, heavy metals (Zn, Ti, Sn) from the cutting blade/fluid were present indicating that the cutting fluid had penetrated through or around the 11 inches of glass to the interior walls of the top of the canister. The Ti, W, Zn and Sn are known to be embedded in the cutting blade of the band saw used to section the canister and significant amounts of these species are not present in the glass. Aluminosilicate and rust deposits identified are, therefore, reaction products of the cutting fluid with the glass and with the heat sensitized canister or with carbon steel contamination on the canister interior which occurs during fabrication and handling. Measured relative humidity in sealed simulated waste glass canisters indicates that only minimal water vapor is present so that internal corrosion of the canister, as observed in the SGM 10-2 sectioned canister, will not occur.

ACKNOWLEDGEMENT

Special thanks are due to W. G. Ramsey of Clemson University and John R. Harbour of the Glass Technology Group of the Savannah River Technology Center for their assistance in sampling of the canister glass.

Figure 4. Morphology of alkali halide and sulfate species in canister SGM 10-2 glass fracture surface (Sample HH).

Figure 5. Morphology of molten alkali halide (dark streaks) in canister SGM 10-2 glass fracture surface (Sample II).

Figure 6. Different morphologies of alkali halides in canister SGM 10-2 glass fracture surface (Sample II).

Figure 7. White alkali halide deposits in canister SGM 10-2 glass stringer near interior shoulder of canister (Sample VV). Very large cubic NaCl crystals visible at higher magnification.

Figure 8. Dendritic alkali chloride and globular mixed chloride and sulfate deposits in canister SGM 10-2 that were flushed from the canister shoulder and sides with deionized water and dried at 90°C for phase identification (Sample Flush Top Solid).

Figure 9. Morphology of isometric spinel crystals associated with the melt pour surface in Canister SGM 10-2 (Sample ZZ).

This page intentionally left blank.

REFERENCES

1. Office of Civilian Radioactive Waste Management, **Waste Acceptance Preliminary Specifications for Vitrified High-Level Waste Forms**, DRAFT, June 1991.
2. **Waste Form Compliance Plan for the Defense Waste Processing Facility**, Revision 0, USDOE Document WSRC-SW4-6, Westinghouse Savannah River Company, Aiken, SC, March 1990.
3. R.G. Baxter, **"Defense Waste Processing Facility Wasteform and Canister Description,"** USDOE Report DP-1606, Rev. 2, E.I. duPont deNemours & Co. Savannah River Plant, Aiken, SC (December, 1988).
4. J.R. Fowler, **"Projected Chemical Compositions of SRP Waste Glass for the Waste Acceptance Preliminary Specifications,"** USDOE Report DPST-87-713, E.I. duPont deNemours & Co. Savannah River Plant, Aiken, SC (March, 1988).
5. J.R. Fowler and M.J. Plodinec, **"Projected Compositions and Radiogenic Properties of DWPF Glasses,"** Proceedings of the Third International Conference on High Level Radioactive Waste Management, Vol. 1, 904-910 (1992).
6. D.F. Bickford, A.A. Ramsey, C.M. Jantzen, and K.G. Brown, **"Control of Radioactive Waste Glass Melters: I. Preliminary General Limits at Savannah River,"** J. Am. Ceram. Soc., 73 [10], 2896-2902 (1990).
7. C.M. Jantzen, **"Glass Melter Off-gas System Pluggages: Cause, Significance, and Remediation,"** USDOE Report WSRC-TR-90-205, Rev. 0, Westinghouse Savannah River Co., Savannah River Site, Aiken, SC (March, 1991).
8. C.M. Jantzen, **"Glass Melter Off-gas System Pluggages: Cause, Significance, and Remediation,"** Proceedings of the 5th International Symposium on Ceramics in Nuclear Waste Management, G.G. Wicks, D.F. Bickford, and R. Bunnell (Eds.), American Ceramic Society, Westerville, OH, 621-630 (1991).
9. C.M. Jantzen, A.S. Choi, and C.T. Randall, **"Remediation of Off-Gas System Deposits in a Radioactive Waste Glass Melter,"** High Level Radioactive Waste and Spent Fuel Management, Vol. 2, S.C. Slate, L.C. Oyen, K.J. Lee, and W.Z. Oh (Eds.), Korean Nuclear Society, Seoul, Korea, 21-32, (1991).
10. J.W. Kelker, **"Development of the DWPF Canister Temporary Shrink-Fit Seal,"** USDOE Report DP-1720, E.I. duPont deNemours & Co., Savannah River Laboratory, Aiken, SC (1986).
11. J.R. Harbour, T.J. Miller, and M.J. Whitaker, **"The Physical Properties and Chemical Composition of the Gas Within the Free Volume of Canistered Waste Forms,"** USDOE Report WSRC-TR-90-521, Westinghouse Savannah River Co., Savannah River Site, Aiken, SC (November, 1990).

12. J.R. Harbour, **"Qualification of Data by C.A. Langton on Internal Canister Environment,"** USDOE Report WSRC-RP-90-1199, Westinghouse Savannah River Co., Savannah River Site, Aiken, SC (October, 1990).
13. C.A. Langton, **"DWPF Canister Corrosion Studies Literature Review and Recommendations,"** USDOE Report DPST-82-978, E.I. duPont deNemours & Co., Savannah River Laboratory, Aiken, SC (1982).
14. M.E. Smith, M.R. Baron, S.L. Goudelock, G.F. Rabon, A.M. Wehner, **"DWPF Scale Glass Melter: Run Plan for SGM-10,"** USDOE Report DPST-88-355, E.I. duPont deNemours & Co., Savannah River Laboratory, Aiken, SC (1988).
15. J.R. Harbour and C.M. Jantzen, **"R/D Task Plan: Organic and Inorganic Analysis of Volatilized and Condensed Species Within SRL Canistered Waste Forms,"** USDOE Report WSRC-RP-90-179, Westinghouse Savannah River Co., Savannah River Laboratory, Aiken, SC (1990).
16. A.S. Choi, **"Freeze and Restart of the DWPF Scale Glass Melter,"** USDOE Report WSRC-RP-89-634, Westinghouse Savannah River Co., Savannah River Laboratory, Aiken, SC (1989).
17. A.S. Choi, M.E. Smith, K.R. Crow, M.R. Baron, G.F. Rabon, S.L. Goudelock, A.M. Wehner, **"Summary of Campaigns SGM-9 and SGM-10 of the DWPF Scale Glass Melter,"** USDOE Report DPST-88-626, E.I. duPont deNemours & Co., Savannah River Laboratory, Aiken, SC (1988).

APPENDIX I
DETAILS OF THE GLASS CHEMICAL ANALYSES

GLASS ID= 2/3 + 0 EDGE - A (ADS #200038840)

(SPREADSHEET REVISION 5.0, OCTOBER 23, 1990)

	ELEMENT	GRAV	OXIDE	NORM OXIDE	M.W.	MOLE	NORM OXIDE	COMPONENT	FREE ENERGY	NBO	KCAL/KG
	WT%	FACTOR	WT%	WT%		FRACTION	MOLE %	FREE ENERGY	HYDRATION		
Al2O3	1.9120	1.8895	3.6127	3.6342	101.9600	0.0354	2.2931	3.0400	0.0697	-0.0459	1.0772
CaO	0.8920	1.3992	1.2481	1.2555	56.0794	0.0223	1.4403	-16.1160	-0.2321	0.0288	-3.5867
Fe2O3	7.6060	1.4297	10.8743	10.9391	159.6922	0.0681	4.4069	15.5000	0.6831	-0.0881	10.5548
FeO	N/A	1.2865	0.0000	0.0000	71.8464	0.0000	0.0000	-14.6090	0.0000	0.0000	0.0000
MgO	0.4950	1.6583	0.8209	0.8257	40.3114	0.0204	1.3178	-13.8880	-0.1830	0.0264	-2.8280
MnO	1.6640	1.2912	2.1486	2.1614	70.9374	0.0303	1.9601	-14.8710	-0.2915	0.0392	-4.5041
Na2O	9.1440	1.3480	12.3261	12.3995	61.9790	0.1989	12.8705	-28.8150	-3.7086	0.2574	-57.3060
Li2O	2.0300	2.1525	4.3696	4.3956	29.8774	0.1463	9.4648	-22.7400	-2.1523	0.1893	-33.2573
NiO	0.7290	1.2726	0.9277	0.9333	74.7094	0.0124	0.8036	-14.3470	-0.1153	0.0161	-1.7816
SiO2	23.2530	2.1393	49.7451	50.0414	60.0848	0.8279	53.5796	5.5900	1.3655	0.0000	21.5633
Cr2O3	0.0810	1.4616	0.1184	0.1191	151.9974	0.0008	0.0504	37.3600	0.0188	-0.0010	0.2910
B2O3	3.6360	3.2201	11.7083	11.7780	69.6204	0.1682	10.8835	-9.9300	-1.0807	0.0000	-16.6996
UO2		1.1344	0.0000	0.0000	270.0388	0.0000	0.0000	-6.8000	0.0000	0.0000	0.0000
ThO2		1.1379	0.0000	0.0000	264.0400	0.0000	0.0000	-2.5330	0.0000	0.0000	0.0000
SrO	0.0380	1.1826	0.0449	0.0452	103.6194	0.0004	0.0281	-24.4000	-0.0068	0.0006	-0.1050
ZrO2	0.4930	1.3508	0.6659	0.6699	123.2188	0.0054	0.3498	45.1000	0.1577	0.0140	2.4375
TiO2	0.0910	1.6680	0.1518	0.1527	79.8988	0.0019	0.1229	15.9900	0.0197	0.0049	0.3038
K2O	0.3340	1.2046	0.4023	0.4047	94.2034	0.0043	0.2764	-41.7350	-0.1154	0.0055	-1.7825
Ca2O		1.0602	0.0000	0.0000	281.8094	0.0000	0.0000	-46.8200	0.0000	0.0000	0.0000
Sb2O3		1.1970	0.0000	0.0000	291.4982	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
P2O5	0.0460	2.2910	0.1054	0.1060	141.9370	0.0007	0.0481	-53.6200	-0.0258	0.0000	-0.3981
Nd2O3		1.1660	0.0000	0.0000	336.4782	0.0000	0.0000	-28.3200	0.0000	0.0000	0.0000
La2O3		1.1728	0.0000	0.0000	325.8100	0.0000	0.0000	-31.1400	0.0000	0.0000	0.0000
Y2O3		1.2699	0.0000	0.0000	225.8082	0.0000	0.0000	-12.9500	0.0000	0.0000	0.0000
BaO	0.0130	1.1165	0.0145	0.0146	153.3394	0.0001	0.0061	-30.5700	-0.0019	0.0001	-0.0289
PbO		1.0772	0.0000	0.0000	223.1900	0.0000	0.0000	-8.8100	0.0000	0.0000	0.0000
CeO2		1.2284	0.0000	0.0000	172.1200	0.0000	0.0000	11.3450	0.0000	0.0000	0.0000
MoO3		1.5003	0.0000	0.0000	143.9382	0.0000	0.0000	-21.7500	0.0000	0.0000	0.0000
ZnO	0.099	1.2447	0.1232	0.1240	81.3800	0.0015	0.0980	-2.4000	-0.0024	0.0020	-0.0363
QuO		1.2518	0.0000	0.0000	79.5454	0.0000	0.0000	1.7900	0.0000	0.0000	0.0000
Fe2+/Fe3+	0										
Cl	0.3971		0.3971	0.3971							
F	0.0253		0.0253	0.0253							
SO4	0.1633		0.1633	0.1633							

OXIDE SUMS	52.5560	99.4079	100.0000	1.5452	100.0000	-5.5713	0.4492	-86.0876
------------	---------	---------	----------	--------	----------	---------	--------	----------

MOLAR BALANCE (M)	MOLAR SUMS	MOLE %	NORMALIZED MOLE %	SUM + pH Si	-5.5713
				SUM + pH B	-5.5713
				pH =	

K ₂ SO ₄	0.2962	SALTS	1.1727	0.9537
KCl	0.8345	BORATES	22.1288	17.9965
KBF ₄	0.0419	CHROMATES	0.2523	0.2052
Na ₂ BO ₂	22.1288	OXIDES	99.4079	80.8446
Na ₂ CrO ₄	0.2523			
		TOTAL	122.9616	100.0000

K excess (M)	-0.01
Na excess (M)	0.06
SO ₄ excess (M)	0.00
Cl excess	0.00
F excess	0.00
B excess	0.00

ALK/SiO ₂ =	0.422	TEST=
ALK+ B ₂ O ₃ /SiO ₂ =	0.625	TIME=
B ₂ O ₃ /SiO ₂ =	0.203	
VISCOSITY @TEMP(°C)	34.482	SA/V=
LIQUIDUS RATIO =	0.079	
LIQUIDUS (°C) =	949.7677135	

NOTE LIQUIDUS AND VISCOSITY FORMULAS CHANGED TO CALCULATE ALL FE AS FE₂O₃ (OCTOBER 23, 1990)

GLASS ID= 2/3 + 0 EDGE - B (ADS #200038841)

(SPREADSHEET REVISION 5.0, OCTOBER 23, 1990)

ELEMENT	GRAV	OXIDE	NORM OXIDE	M.W.	MOLE	NORM OXIDE	COMPONENT	FREE ENERGY	NBO	KCAL/KG	
WT%	FACTOR	WT%	WT%		FRACTION	MOLE %	FREE ENERGY	HYDRATION			
Al2O3	1.4550	1.8895	2.7492	3.1276	101.9600	0.0270	1.9597	3.0400	0.0596	-0.0392	0.8197
CaO	0.7650	1.3992	1.0704	1.2177	56.0794	0.0191	1.3873	-16.1160	-0.2236	0.0277	-3.0761
Fe2O3	6.2390	1.4297	8.9199	10.1476	159.6922	0.0559	4.0597	15.5000	0.6293	-0.0812	8.6578
FeO	N/A	1.2865	0.0000	0.0000	71.8464	0.0000	0.0000	-14.6090	0.0000	0.0000	0.0000
MgO	0.4240	1.6583	0.7031	0.7999	40.3114	0.0174	1.2677	-13.8880	-0.1761	0.0254	-2.4224
MnO	1.4370	1.2912	1.8555	2.1108	70.9374	0.0262	1.9011	-14.8710	-0.2827	0.0380	-3.8897
Na2O	8.7880	1.3480	1.1193	13.4460	61.9790	0.1907	13.8600	-28.8150	-3.9938	0.2772	-54.9496
Li2O	1.8100	2.1525	3.8960	4.4322	29.8774	0.1304	9.4776	-22.7400	-2.1552	0.1896	-29.6531
NiO	0.5830	1.2726	0.7419	0.8440	74.7094	0.0099	0.7218	-14.3470	-0.1036	0.0144	-1.4248
SiO2	20.6360	2.1393	44.1466	50.2226	60.0848	0.7347	53.4012	5.5900	1.3382	0.0000	18.4120
Cr2O3	0.0790	1.4616	0.1155	0.1314	151.9974	0.0008	0.0552	37.3600	0.0206	-0.0011	0.2838
B2O3	3.2450	3.2201	10.4492	11.8874	69.6204	0.1501	10.9085	-9.9300	-1.0832	0.0000	-14.9038
UO2		1.1344	0.0000	0.0000	270.0388	0.0000	0.0000	-6.8000	0.0000	0.0000	0.0000
ThO2		1.1379	0.0000	0.0000	264.0400	0.0000	0.0000	-2.5330	0.0000	0.0000	0.0000
SrO	0.0330	1.1826	0.0390	0.0444	103.6194	0.0004	0.0274	-24.4000	-0.0067	0.0005	-0.0919
ZrO2	0.4790	1.3508	0.6470	0.7361	123.2188	0.0053	0.3817	45.1000	0.1721	0.0153	2.3682
TiO2	0.0780	1.6680	0.1301	0.1480	79.8988	0.0016	0.1184	15.9900	0.0189	0.0047	0.2604
K2O	0.3360	1.2046	0.4047	0.4605	94.2034	0.0043	0.3123	-41.7350	-0.1303	0.0062	-1.7931
Ca2O		1.0602	0.0000	0.0000	281.8094	0.0000	0.0000	-46.8200	0.0000	0.0000	0.0000
Sb2O3		1.1970	0.0600	0.0000	291.4882	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
P2O5	0.0300	2.2910	0.0687	0.0782	141.9370	0.0005	0.0352	-53.6200	-0.0189	0.0000	-0.2596
Nd2O3		1.1660	0.0000	0.0000	336.4782	0.0000	0.0000	-28.3200	0.0000	0.0000	0.0000
La2O3		1.1728	0.0000	0.0000	325.8100	0.0000	0.0000	-31.1400	0.0000	0.0000	0.0000
Y2O3		1.2698	0.0000	0.0000	225.8082	0.0000	0.0000	-12.9500	0.0000	0.0000	0.0000
BaO	0.0100	1.1165	0.0112	0.0127	153.3394	0.0001	0.0053	-30.5700	-0.0016	0.0001	-0.0223
PbO		1.0772	0.0000	0.0000	223.1900	0.0000	0.0000	-8.8100	0.0000	0.0000	0.0000
CeO2		1.2284	0.0000	0.0000	172.1200	0.0000	0.0000	11.3450	0.0000	0.0000	0.0000
MnO3		1.5003	0.0000	0.0000	143.9382	0.0000	0.0000	-21.7500	0.0000	0.0000	0.0000
ZnO	0.108	1.2447	0.1344	0.1529	81.3800	0.0017	0.1201	-2.4000	-0.0029	0.0024	-0.0396
CuO		1.2518	0.0000	0.0000	79.5454	0.0000	0.0000	1.7900	0.0000	0.0000	0.0000
Fe2+/Fe3+	0										
Cl	0.5004		0.5004	0.5004							
F	0.0328		0.0328	0.0328							
SO4	0.1838		0.1838	0.1838							
OXIDE SUMS	46.5150		87.9018	100.0000		1.3759	100.0000		-5.9397	0.4801	-81.7240
NORMALIZED											
MOLAR BALANCE (M)											
MOLAR SUMS											
MOLE %											
MOLE %											
SUM + pH Si											
SUM + pH B											
pH =											
K2SO4	0.3334			1.4394	1.3165						
KCl	1.0516			19.7492	18.0628						
KBF4	0.0543			0.2460	0.2250						
NaBO2	19.7492			87.9018	80.3957						
Na2CrO4	0.2460										
TOTAL											
109.3364											
100.0000											
K excess (M)	-0.01										
Na excess (M)	0.08										
SO4 excess (M)	0.00										
Cl excess	0.00										
F excess	0.00										
S excess	0.02										
ALK/SiO2 = 0.443 TEST=											
ALK+ B2O3/SiO2 = 0.647 TIME=											
B2O3/SiO2 = 0.204											
VISCOSITY @TEMP(°C) 29.358 SA/V=											
LIQUIDUS RATIO = 0.072											
LIQUIDUS (°C) = 927.3222662											
NOTE LIQUIDUS AND VISCOSITY FORMULAS CHANGED TO CALCULATE ALL FE AS FE2O3 (OCTOBER 23, 1990)											

NOTE LIQUIDUS AND VISCOSITY FORMULAS CHANGED TO CALCULATE ALL FE AS FE₂O₃ (OCTOBER 23, 1990)

GLASS ID= 2/3 + 0 CENTER - A (ADS #200036842)

(SPREADSHEET REVISION 5.0, OCTOBER 23, 1990)

ELEMENT	GRAV	OXIDE	NORM OXIDE	M.W.	MOLE	NORM OXIDE	COMPONENT	FREE ENERGY	NBO	KCAL/KG	
WT%	FACTOR	WT%	WT%		FRACTION	MOLE %	FREE ENERGY	HYDRATION			
Al2O3	1.7630	1.8895	3.3312	3.5450	101.9600	0.0327	2.2373	3.0400	0.0680	-0.0447	0.9932
CaO	0.8930	1.3992	1.2495	1.3297	56.0794	0.0223	1.5257	-16.1160	-0.2459	0.0305	-3.5907
Fe2O3	7.3280	1.4297	10.4768	11.1493	159.6922	0.0856	4.4926	15.5000	0.6963	-0.0899	10.1690
FeO	N/A	1.2865	0.0000	0.0000	71.8464	0.0000	0.0000	-14.6090	0.0000	0.0000	0.0000
MgO	0.4780	1.6583	0.7927	0.8435	40.3114	0.0197	1.3465	-13.8880	-0.1870	0.0269	-2.7309
MnO	1.5960	1.2912	2.0608	2.1930	70.9374	0.0291	1.9893	-14.8710	-0.2958	0.0398	-4.3201
Na2O	7.6330	1.3480	10.2893	10.9497	61.9790	0.1660	11.3681	-28.8150	-3.2757	0.2274	-47.8365
Li2O	1.9530	2.1525	4.2038	4.4737	29.8774	0.1407	9.6350	-22.7400	-2.1910	0.1927	-31.9958
NiO	0.6970	1.2726	0.8870	0.9439	74.7094	0.0119	0.8130	-14.3470	-0.1166	0.0163	-1.7034
SiO2	22.3300	2.1393	47.7706	50.8368	60.0848	0.7951	54.4431	5.5900	1.5090	0.0000	22.0360
Cr2O3	0.0940	1.4616	0.1374	0.1462	151.9974	0.0009	0.0619	37.3600	0.0231	-0.0012	0.3377
B2O3	3.5210	3.2201	11.3380	12.0657	69.6204	0.1629	11.1518	-9.9300	-1.1074	0.0000	-16.1714
UO2		1.1344	0.0000	0.0000	270.0388	0.0000	0.0000	-6.8000	0.0000	0.0000	0.0000
ThO2		1.1379	0.0000	0.0000	264.0400	0.0000	0.0000	-2.5330	0.0000	0.0000	0.0000
SnO	0.0340	1.1826	0.0402	0.0428	103.6194	0.0004	0.0266	-24.4000	-0.0065	0.0005	-0.0947
ZrO2	0.4700	1.3508	0.6349	0.6756	123.2188	0.0052	0.3528	45.1000	0.1591	0.0141	2.3237
TiO2	0.0840	1.6680	0.1401	0.1491	79.8988	0.0018	0.1201	15.9900	0.0192	0.0048	0.2804
K2O	0.3320	1.2046	0.3999	0.4256	94.2034	0.0042	0.2907	-41.7350	-0.1213	0.0058	-1.7718
Ca2O		1.0602	0.0000	0.0000	281.8094	0.0000	0.0000	-46.8200	0.0000	0.0000	0.0000
Sb2O3		1.1970	0.0000	0.0000	291.4982	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
P2O5	0.0400	2.2910	0.0916	0.0975	141.9370	0.0006	0.0442	-53.6200	-0.0237	0.0000	-0.3462
Na2O3		1.1660	0.0000	0.0000	336.4782	0.0000	0.0000	-28.3200	0.0000	0.0000	0.0000
La2O3		1.1728	0.0000	0.0000	325.8100	0.0000	0.0000	-31.1400	0.0000	0.0000	0.0000
Y2O3		1.2699	0.0000	0.0000	225.8082	0.0000	0.0000	-12.9500	0.0000	0.0000	0.0000
BaO	0.0080	1.1185	0.0089	0.0095	153.3394	0.0001	0.0040	-30.5700	-0.0012	0.0001	-0.0178
PbO		1.0772	0.0000	0.0000	223.1900	0.0000	0.0000	-8.8100	0.0000	0.0000	0.0000
CoO2		1.2284	0.0000	0.0000	172.1200	0.0000	0.0000	11.3450	0.0000	0.0000	0.0000
MnO3		1.5003	0.0000	0.0000	143.9382	0.0000	0.0000	-21.7500	0.0000	0.0000	0.0000
ZnO	0.093	1.2447	0.1158	0.1232	81.3800	0.0014	0.0974	-2.4000	-0.0023	0.0019	-0.0341
Q2O		1.2518	0.0000	0.0000	79.5454	0.0000	0.0000	1.7900	0.0000	0.0000	0.0000
Fe2+//Fe3+	0										
Cl	0.4591		0.4591	0.4591							
F	0.0259		0.0259	0.0259							
SO4	0.1601		0.1601	0.1601							
OXIDE SUMS	49.3470		93.9684	100.0000		1.4603	100.0000		-5.0997	0.4250	-74.4734
MOLAR BALANCE (M)		MOLAR SUMS	MOLE %	NORMALIZED MOLE %			SUM + pH Si		-5.0997		
							SUM + pH B		-5.0997		
							pH =				
K2SO4	0.2904	SALTS	1.2982	1.1097							
KCl	0.9648	BORATES	21.4289	18.3171							
KBF4	0.0429	CHROMATES	0.2928	0.2502							
NaBO2	21.4289	OXIDES	93.9684	80.3230							
Na2CrO4	0.2928										
		TOTAL	116.9883	100.0000							
K excess(M)	-0.01										
Na excess (M)	0.00										
SO4 excess (M)	0.00										
Cl excess	0.00										
F excess	0.00										
S excess	0.00										
ALK/SiO2 =	0.391	TEST=									
ALK+ B2O3/SiO2 =	0.596	TIME=									
B2O3/SiO2 =	0.205										
VISCOSITY @TEMP(°C)	42.626	SA/V=									
LIQUIDUS RATIO =	0.079										
LIQUIDUS (°C) =	949.4943159										
NOTE LIQUIDUS AND VISCOSITY FORMULAS CHANGED TO CALCULATE ALL FE AS FE2O3 (OCTOBER 23, 1990)											

NOTE LIQUIDUS AND VISCOSITY FORMULAS CHANGED TO CALCULATE ALL FE AS FE₂O₃ (OCTOBER 23, 1990)

GLASS ID= 2/3 + 0 CENTER - B (ADS #200038843)

(SPREADSHEET REVISION 5.0, OCTOBER 23, 1990)

	ELEMENT	GRAV	OXIDE	NORM OXIDE	M.W.	MOLE	NORM OXIDE	COMPONENT	FREE ENERGY	NBO	KCAL/KG
	WT%	FACTOR	WT%	WT%		FRACTION	MOLE %	FREE ENERGY	HYDRATION		
	Al2O3	1.4780	1.8895	2.7827	3.1264	101.9600	0.0274	1.9473	3.0400	0.0592	0.8327
	CaO	0.8550	1.3992	1.1963	1.3393	56.0794	0.0213	1.5166	-16.1160	-0.2444	-3.4380
	Fe2O3	6.0560	1.4297	8.6583	9.6930	159.6922	0.0542	3.8546	15.5000	0.5975	8.4039
	FeO	N/A	1.2865	0.0000	0.0000	71.8464	0.0000	0.0000	-14.6090	0.0000	0.0000
	MgO	0.4590	1.6583	0.7612	0.8521	40.3114	0.0189	1.3424	-13.8880	-0.1864	-2.6223
	MnO	1.3270	1.2912	1.7134	1.9182	70.9374	0.0242	1.7172	-14.8710	-0.2554	-3.5919
	Na2O (ICP)	7.9480	1.3480	10.7139	11.9944	61.9790	0.1729	12.2896	-28.8150	-3.5412	-49.8106
	Li2O	1.9150	2.1525	4.1220	4.6147	29.8774	0.1380	9.8085	-22.7400	-2.2305	-31.3733
	NaO	0.5690	1.2726	0.7241	0.8107	74.7094	0.0097	0.6891	-14.3470	-0.0989	-1.3906
	SiO2 (ICP)	21.5640	2.1393	46.1319	51.6453	60.0848	0.7678	54.5847	5.5900	1.4771	20.7763
	Cr2O3	0.0670	1.4616	0.0979	0.1096	151.9974	0.0006	0.0458	37.3600	0.0171	0.2407
	B2O3	3.4260	3.2201	11.0321	12.3505	69.6204	0.1585	11.2658	-9.9300	-1.1187	-15.7351
	UO2		1.1344	0.0000	0.0000	270.0388	0.0000	0.0000	-6.8000	0.0000	0.0000
	ThO2		1.1379	0.0000	0.0000	264.0400	0.0000	0.0000	-2.5330	0.0000	0.0000
	SnO	0.0350	1.1826	0.0414	0.0463	103.6194	0.0004	0.0284	-24.4000	-0.0069	-0.0975
	ZrO2	0.4670	1.3508	0.6308	0.7062	123.2188	0.0051	0.3640	45.1000	0.1642	2.3089
	TiO2	0.0740	1.6680	0.1234	0.1382	79.8988	0.0015	0.1098	15.9900	0.0176	0.2470
	K2O	0.3320	1.2046	0.3999	0.4477	94.2034	0.0042	0.3018	-41.7350	-0.1260	-1.7718
	Ce2O		1.0602	0.0000	0.0000	281.8094	0.0000	0.0000	-46.8200	0.0000	0.0000
	Sb2O3		1.1970	0.0000	0.0000	291.4982	0.0000	0.0000	0.0000	0.0000	0.0000
	P2O5	0.0270	2.2910	0.0619	0.0692	141.9370	0.0004	0.0310	-53.6200	-0.0166	-0.2337
	Nd2O3		1.1660	0.0000	0.0000	336.4782	0.0000	0.0000	-28.3200	0.0000	0.0000
	La2O3		1.1728	0.0000	0.0000	325.8100	0.0000	0.0000	-31.1400	0.0000	0.0000
	Y2O3		1.2699	0.0000	0.0000	225.8082	0.0000	0.0000	-12.9500	0.0000	0.0000
	BaO	0.0090	1.1165	0.0100	0.0112	153.3394	0.0001	0.0047	-30.5700	-0.0014	-0.0200
	PbO		1.0772	0.0000	0.0000	223.1900	0.0000	0.0000	-8.8100	0.0000	0.0000
	CeO2		1.2284	0.0000	0.0000	172.1200	0.0000	0.0000	11.3450	0.0000	0.0000
	MoO3		1.5003	0.0000	0.0000	143.9382	0.0000	0.0000	-21.7500	0.0000	0.0000
	ZrO	0.091	1.2447	0.1133	0.1268	81.3800	0.0014	0.0990	-2.4000	-0.0024	-0.0334
	ClO		1.2518	0.0000	0.0000	79.5454	0.0000	0.0000	1.7900	0.0000	0.0000
	Fe2+/Fe3+	0									
	Cl	0.4091		0.4091	0.4091						
	F	0.0187		0.0187	0.0187						
	SO4	0.1467		0.1467	0.1467						

OXIDE SUMS	46.6990	89.3245	100.0000		1.4066	100.0000		-5.4962	0.4579	-77.3087
------------	---------	---------	----------	--	--------	----------	--	---------	--------	----------

MOLAR BALANCE (M)		MOLAR SUMS	MOLE %	NORMALIZED			SUM + pH Si	-5.4962
				MOLE %			SUM + pH B	-5.4962
							pH =	

K2SO4	0.2661	SALTS	1.1568	1.0372
KCl	0.8597	BORATES	20.8507	18.6934
KBF4	0.0310	CHROMATES	0.2087	0.1871
NaBO2	20.8507	OXIDES	89.3245	80.0824
Na2CrO4	0.2087			
		TOTAL	111.5408	100.0000

K excess (M)	-0.01
Na excess (M)	0.03
SO4 excess (M)	0.00
Cl excess	0.00
F excess	0.00
B excess	0.00

ALK/SiO2 =	0.410	TEST=	
ALK+ B2O3/SiO2 =	0.617	TIME=	
B2O3/SiO2 =	0.206		
VISCOSITY @TEMP(°C)	38.481	SA/V=	
LIQUIDUS RATIO =	0.066		
LIQUIDUS (°C) =	910.6307776		

NOTE LIQUIDUS AND VISCOSITY FORMULAS CHANGED TO CALCULATE ALL FE AS FE2O3 (OCTOBER 23, 1990)

GLASS ID= 2/3 + 6 EDGE - A (ADS #200038844)

(SPREADSHEET REVISION 5.0, OCTOBER 23, 1990)

	ELEMENT	GRAV	OXIDE	NORM OXIDE	M.W.	MOLE	NORM OXIDE	COMPONENT	FREE ENERGY	NEO	KCAL/KG
	WT%	FACTOR	WT%	WT%		FRACTION	MOLE %	FREE ENERGY	HYDRATION		
Al2O3	2.8080	1.8895	5.3057	5.3766	101.9600	0.0520	3.4089	3.0400	0.1036	-0.0682	1.5819
CaO	0.9910	1.3992	1.3866	1.4051	56.0794	0.0247	1.6198	-16.1160	-0.2610	0.0324	-3.9848
Fe2O3	7.3330	1.4297	10.4840	10.6241	159.6922	0.0857	4.3008	15.5000	0.6666	-0.0860	10.1759
FeO	N/A	1.2865	0.0000	0.0000	71.8464	0.0000	0.0000	-14.6090	0.0000	0.0000	0.0000
MgO	0.5010	1.6583	0.8308	0.8419	40.3114	0.0206	1.3501	-13.8880	-0.1875	0.0270	-2.8623
MnO	1.6050	1.2912	2.0724	2.1001	70.9374	0.0292	1.9138	-14.8710	-0.2846	0.0383	-4.3444
Na2O	8.5030	1.3480	11.4620	11.6152	61.9790	0.1849	12.1150	-28.8150	-3.4909	0.2423	-53.2888
Li2O	2.0020	2.1525	4.3093	4.3669	29.8774	0.1442	9.4486	-22.7400	-2.1486	0.1890	-32.7986
NiO	0.6920	1.2726	0.8806	0.8924	74.7094	0.0118	0.7722	-14.3470	-0.1108	0.0154	-1.6912
SiO2	22.8500	2.1393	48.8830	49.5361	60.0848	0.8136	53.2964	5.5900	1.4177	0.0000	21.6411
Cr2O3	0.0760	1.4616	0.1111	0.1126	151.9974	0.0007	0.0479	37.3600	0.0179	-0.0010	0.2730
B2O3	3.5760	3.2201	11.5151	11.6689	69.6204	0.1654	10.8351	-9.9300	-1.0759	0.0000	-16.4240
UO2		1.1344	0.0000	0.0000	270.0388	0.0000	0.0000	-6.8000	0.0000	0.0000	0.0000
ThO2		1.1379	0.0000	0.0000	264.0400	0.0000	0.0000	-2.5330	0.0000	0.0000	0.0000
SnO	0.0390	1.1826	0.0461	0.0467	103.6194	0.0004	0.0292	-24.4000	-0.0071	0.0006	-0.1086
ZrO2	0.4710	1.3508	0.6362	0.6447	123.2188	0.0052	0.3383	45.1000	0.1526	0.0135	2.3287
TiO2	0.0830	1.6680	0.1384	0.1403	79.8988	0.0017	0.1135	15.9900	0.0182	0.0045	0.2771
K2O	0.2920	1.2046	0.3517	0.3564	94.2034	0.0037	0.2446	-41.7350	-0.1021	0.0049	-1.5583
Ca2O		1.0602	0.0000	0.0000	281.8094	0.0000	0.0000	-46.8200	0.0000	0.0000	0.0000
Sb2O3		1.1970	0.0000	0.0000	291.4982	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
P2O5	0.0590	2.2910	0.1352	0.1370	141.9370	0.0010	0.0624	-53.6200	-0.0335	0.0000	-0.5106
Nd2O3		1.1660	0.0000	0.0000	336.4782	0.0000	0.0000	-28.3200	0.0000	0.0000	0.0000
La2O3		1.1728	0.0000	0.0000	325.8100	0.0000	0.0000	-31.1400	0.0000	0.0000	0.0000
Y2O3		1.2699	0.0000	0.0000	225.8082	0.0000	0.0000	-12.9500	0.0000	0.0000	0.0000
BaO	0.0090	1.1165	0.0100	0.0102	153.3394	0.0001	0.0043	-30.5700	-0.0013	0.0001	-0.0200
PbO		1.0772	0.0000	0.0000	223.1900	0.0000	0.0000	-8.8100	0.0000	0.0000	0.0000
CeO2		1.2284	0.0000	0.0000	172.1200	0.0000	0.0000	11.3450	0.0000	0.0000	0.0000
MoO3		1.5003	0.0000	0.0000	143.9382	0.0000	0.0000	-21.7500	0.0000	0.0000	0.0000
ZnO	0.099	1.2447	0.1232	0.1249	81.3800	0.0015	0.0992	-2.4000	-0.0024	0.0020	-0.0363
CoO		1.2518	0.0000	0.0000	79.5454	0.0000	0.0000	1.7900	0.0000	0.0000	0.0000
Fe2+/Fe3+	0										
Cl	0.3914		0.3914	0.3914							
F	0.0229		0.0229	0.0229							
SO4	0.1597		0.1597	0.1597							

OXIDE SUMS	51.9890	98.6816	100.0000		1.5265	100.0000		-5.3292	0.4149	-81.3502
------------	---------	---------	----------	--	--------	----------	--	---------	--------	----------

MOLAR BALANCE (M)		MOLAR SUMS	MOLE %	NORMALIZED			SUM + pH Si	-5.3292
				MOLE %			SUM + pH B	-5.3292
							pH =	

K2SO4	0.2897	SALTS	1.1502	0.9441
KCl	0.8225	BORATES	21.7636	17.8638
KBF4	0.0379	CHROMATES	0.2367	0.1943
NaBO2	21.7636	OXIDES	98.6816	80.9980
Na2CrO4	0.2367			
		TOTAL	121.8322	100.0000

K excess(M)	-0.01
Na excess (M)	0.04
SO4 excess (M)	0.00
Cl excess	0.00
F excess	0.00
B excess	0.00

ALK/SiO2 =	0.409	TEST=	
ALK+ B2O3/SiO2 =	0.612	TIME=	
B2O3/SiO2 =	0.203		
VISCOSITY @TEMP(°C)	45.073	SA/V=	
LIQUIDUS RATIO =	0.082		
LIQUIDUS (°C) =	959.1188304		

NOTE LIQUIDUS AND VISCOSITY FORMULAS CHANGED TO CALCULATE ALL FE AS FE2O3 (OCTOBER 23, 1990)

GLASS ID= 2/3 + 6 EDGE - B (ADS #200038845)

(SPREADSHEET REVISION 5.0, OCTOBER 23, 1990)

	ELEMENT	GRAV	OXIDE	NORM OXIDE	M.W.	MOLE	NORM OXIDE	COMPONENT	FREE ENERGY	NBO	KCAL/KG	
	WT%	FACTOR	WT%	WT%		FRACTION	MOLE %	FREE ENERGY	HYDRATION			
	Al2O3	1.7430	1.8895	3.2934	3.4534	101.9600	0.0323	2.1729	3.0400	0.0661	-0.0435	0.9819
	CaO	0.8810	1.3992	1.2327	1.2926	56.0794	0.0220	1.4787	-16.1160	-0.2383	0.0296	-3.5425
	Fe2O3	7.2690	1.4297	10.3925	10.8973	159.6922	0.0651	4.3779	15.5000	0.6786	-0.0876	10.0871
	FeO	N/A	1.2865	0.0000	0.0000	71.8464	0.0000	0.0000	-14.6090	0.0000	0.0000	0.0000
	MgO	0.4860	1.6583	0.8059	0.8451	40.3114	0.0200	1.3449	-13.8880	-0.1868	0.0269	-2.7766
	MnO	1.5690	1.2912	2.0259	2.1243	70.9374	0.0286	1.9212	-14.8710	-0.2857	0.0384	-4.2470
	Na2O	8.2920	1.3480	11.1776	11.7206	61.9790	0.1803	12.1320	-28.8150	-3.4958	0.2426	-51.9665
	Li2O	2.0020	2.1525	4.3093	4.5186	29.8774	0.1442	9.7027	-22.7400	-2.2064	0.1941	-32.7986
	NaO	0.6740	1.2726	0.8577	0.8994	74.7094	0.0115	0.7723	-14.3470	-0.1108	0.0154	-1.6472
	SiO2	22.5620	2.1393	48.2669	50.6115	60.0848	0.8033	54.0397	5.5900	1.4476	0.0000	21.5192
	Cr2O3	0.0650	1.4616	0.0950	0.0998	151.9974	0.0006	0.0420	37.3600	0.0157	-0.0008	0.2335
	B2O3	3.5650	3.2201	11.4797	12.0373	69.6204	0.1649	11.0923	-9.9300	-1.1015	0.0000	-16.3735
	UO2		1.1344	0.0000	0.0000	270.0388	0.0000	0.0000	-6.8000	0.0000	0.0000	0.0000
	ThO2		1.1379	0.0000	0.0000	264.0400	0.0000	0.0000	-2.5330	0.0000	0.0000	0.0000
	SrO	0.0350	1.1826	0.0414	0.0434	103.6194	0.0004	0.0269	-24.4000	-0.0066	0.0005	-0.0975
	ZrO2	0.4950	1.3508	0.6886	0.7011	123.2188	0.0054	0.3650	45.1000	0.1846	0.0146	2.4473
	TiO2	0.0770	1.6680	0.1284	0.1347	79.8988	0.0016	0.1081	15.9900	0.0173	0.0043	0.2570
	K2O	0.3400	1.2046	0.4096	0.4295	94.2034	0.0043	0.2925	-41.7350	-0.1221	0.0058	-1.8145
	Ce2O		1.0602	0.0000	0.0000	281.8094	0.0000	0.0000	-46.8200	0.0000	0.0000	0.0000
	Sb2O3		1.1970	0.0000	0.0000	291.4982	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
	P2O5	0.0220	2.2910	0.0504	0.0529	141.9370	0.0004	0.0239	-53.6200	-0.0128	0.0000	-0.1904
	Nd2O3		1.1660	0.0000	0.0000	336.4782	0.0000	0.0000	-28.3200	0.0000	0.0000	0.0000
	La2O3		1.1728	0.0000	0.0000	325.8100	0.0000	0.0000	-31.1400	0.0000	0.0000	0.0000
	Y2O3		1.2699	0.0000	0.0000	225.8082	0.0000	0.0000	-12.9500	0.0000	0.0000	0.0000
	BaO	0.0080	1.1165	0.0067	0.0070	153.3394	0.0000	0.0029	-30.5700	-0.0009	0.0001	-0.0134
	PbO		1.0772	0.0000	0.0000	223.1900	0.0000	0.0000	-8.8100	0.0000	0.0000	0.0000
	CeO2		1.2284	0.0000	0.0000	172.1200	0.0000	0.0000	11.3450	0.0000	0.0000	0.0000
	MoO3		1.5003	0.0000	0.0000	143.9382	0.0000	0.0000	-21.7500	0.0000	0.0000	0.0000
	ZnO	0.101	1.2447	0.1257	0.1318	81.3800	0.0015	0.1039	-2.4000	-0.0025	0.0021	-0.0371
	ClO		1.2518	0.0000	0.0000	79.5454	0.0000	0.0000	1.7900	0.0000	0.0000	0.0000
	Fe2+/Fe3+	0										
	Cl	0.4284		0.4284	0.4284							
	F	0.0233		0.0233	0.0233							
	SO4	0.1698		0.1698	0.1698							

OXIDE SUMS	50.1840	95.3675	100.0000		1.4865	100.0000		-5.3802	0.4426	-79.9784
------------	---------	---------	----------	--	--------	----------	--	---------	--------	----------

MOLAR BALANCE (M)		MOLAR SUMS	MOLE %	NORMALIZED		SUM + pH Si	-5.3802
				MOLE %		SUM + pH B	-5.3802
						pH =	

K ₂ SO ₄	0.3080	SALTS	1.2469	1.0521
KCl	0.9003	BORATES	21.6967	18.3074
KBF ₄	0.0386	CHROMATES	0.2024	0.1708
NaBO ₂	21.6967	OXIDES	95.3675	80.4697
Na ₂ CrO ₄	0.2024			
		TOTAL	118.5135	100.0000

K excess (M)	-0.01
Na excess (M)	0.03
SO ₄ excess (M)	0.00
Cl excess	0.00
F excess	0.00
B excess	0.00

ALK/SiO ₂ =	0.409	TEST=
ALK+ B ₂ O ₃ /SiO ₂ =	0.615	TIME=
B ₂ O ₃ /SiO ₂ =	0.205	
VISCOSITY @TEMP(°C)	37.226	SA/V=
LIQUIDUS RATIO =	0.077	
LIQUIDUS (°C) =	944.3934019	

NOTE LIQUIDUS AND VISCOSITY FORMULAS CHANGED TO CALCULATE ALL FE AS FE₂O₃ (OCTOBER 23, 1990)

GLASS ID= 2/3 + 6 CENTER - A (ADS #200038846)

(SPREADSHEET REVISION 5.0, OCTOBER 23, 1990)

	ELEMENT	GRAV	OXIDE	NORM OXIDE	M.W.	MOLE	NORM OXIDE	COMPONENT	FREE ENERGY	NBO	KCAL/KG
	WT%	FACTOR	WT%	WT%		FRACTION	MOLE %	FREE ENERGY	HYDRATION		
Al2O3	1.7480	1.8895	3.3028	3.3983	101.9600	0.0324	2.1404	3.0400	0.0651	-0.0428	0.9848
CaO	0.8620	1.3992	1.2061	1.2410	56.0794	0.0215	1.4211	-16.1160	-0.2290	0.0284	-3.4661
Fe2O3	7.3990	1.4297	10.5784	10.8839	159.6922	0.0662	4.3770	15.5000	0.6784	-0.0875	10.2675
FeO	N/A	1.2865	0.0000	0.0000	71.8464	0.0000	0.0000	-14.6090	0.0000	0.0000	0.0000
MgO	0.4830	1.6583	0.8010	0.8241	40.3114	0.0199	1.3129	-13.8880	-0.1823	0.0263	-2.7594
MnO	1.5300	1.2912	1.9755	2.0326	70.9374	0.0278	1.8402	-14.8710	-0.2736	0.0368	-4.1414
Na2O	9.2490	1.3480	12.4677	12.8278	61.9790	0.2012	13.2918	-28.8150	-3.8300	0.2658	-57.9641
Li2O	1.9870	2.1525	4.2770	4.4006	29.8774	0.1432	9.4589	-22.7400	-2.1510	0.1892	-32.5528
NiO	0.6820	1.2726	0.8679	0.8930	74.7094	0.0116	0.7676	-14.3470	-0.1101	0.0154	-1.6667
SiO2	22.7080	2.1393	48.5792	49.9825	60.0848	0.8085	53.4233	5.5900	1.3724	0.0000	20.7704
Cr2O3	0.0730	1.4616	0.1067	0.1098	151.9974	0.0007	0.0464	37.3600	0.0173	-0.0009	0.2623
B2O3	3.6040	3.2201	11.6052	11.9405	69.6204	0.1667	11.0144	-9.9300	-1.0937	0.0000	-16.5526
UO2		1.1344	0.0000	0.0000	270.0388	0.0000	0.0000	-6.8000	0.0000	0.0000	0.0000
ThO2		1.1379	0.0000	0.0000	264.0400	0.0000	0.0000	-2.5330	0.0000	0.0000	0.0000
SrO	0.0340	1.1826	0.0402	0.0414	103.6194	0.0004	0.0256	-24.4000	-0.0063	0.0005	-0.0947
ZrO2	0.4960	1.3508	0.6700	0.6894	123.2188	0.0054	0.3593	45.1000	0.1620	0.0144	2.4523
TiO2	0.0810	1.6680	0.1351	0.1390	79.8988	0.0017	0.1117	15.9900	0.0179	0.0045	0.2704
K2O	0.3580	1.2046	0.4312	0.4437	94.2034	0.0046	0.3025	-41.7350	-0.1262	0.0060	-1.9106
Ca2O		1.0602	0.0000	0.0000	281.8094	0.0000	0.0000	-46.8200	0.0000	0.0000	0.0000
Sb2O3		1.1970	0.0000	0.0000	291.4982	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
P2O5	0.0140	2.2910	0.0321	0.0330	141.9370	0.0002	0.0149	-53.6200	-0.0080	0.0000	-0.1212
Nd2O3		1.1660	0.0000	0.0000	336.4782	0.0000	0.0000	-28.3200	0.0000	0.0000	0.0000
La2O3		1.1728	0.0000	0.0000	325.8100	0.0000	0.0000	-31.1400	0.0000	0.0000	0.0000
Y2O3		1.2699	0.0000	0.0000	225.8082	0.0000	0.0000	-12.9500	0.0000	0.0000	0.0000
BaO	0.0060	1.1165	0.0067	0.0069	153.3394	0.0000	0.0029	-30.5700	-0.0009	0.0001	-0.0134
RbO		1.0772	0.0000	0.0000	223.1900	0.0000	0.0000	-8.8100	0.0000	0.0000	0.0000
CeO2		1.2284	0.0000	0.0000	172.1200	0.0000	0.0000	11.3450	0.0000	0.0000	0.0000
MnO3		1.5003	0.0000	0.0000	143.9382	0.0000	0.0000	-21.7500	0.0000	0.0000	0.0000
ZnO	0.088	1.2447	0.1095	0.1127	81.3800	0.0013	0.0889	-2.4000	-0.0021	0.0018	-0.0323
ClO		1.2518	0.0000	0.0000	79.5454	0.0000	0.0000	1.7900	0.0000	0.0000	0.0000
Fe2+/Fe3+	0										
Cl	0.3502		0.3502	0.3502							
F	0.0237		0.0237	0.0237							
SO4	0.1815		0.1815	0.1815							

OXIDE SUMS	51.4020	97.1924	100.0000		1.5134	100.0000		-5.7002	0.4578	-86.2676
------------	---------	---------	----------	--	--------	----------	--	---------	--------	----------

MOLAR BALANCE (M)	MOLAR SUMS	MOLE %	NORMALIZED MOLE %	SUM + pH Si	SUM + pH B	pH =
				-5.7002	-5.7002	

K2SO4	0.3293	SALTS	1.1045	0.9169
KCl	0.7360	BORATES	21.9341	18.2088
KBF4	0.0393	CHROMATES	0.2274	0.1887
NaBO2	21.9341	OXIDES	97.1924	80.6855
Na2CrO4	0.2274			
		TOTAL	120.4583	100.0000

K excess (M)	0.00
Na excess (M)	0.07
SO4 excess (M)	0.00
Cl excess	0.00
F excess	0.00
B excess	0.00

ALK/SiO2 =	0.432	TEST=
ALK+ B2O3/SiO2 =	0.638	TIME=
B2O3/SiO2 =	0.206	
VISCOSITY @TEMP(°C)	31.154	SA/V=
LIQUIDUS RATIO =	0.078	
LIQUIDUS (°C) =	947.0715139	

NOTE LIQUIDUS AND VISCOSITY FORMULAS CHANGED TO CALCULATE ALL FE AS FE2O3 (OCTOBER 23, 1990)

GLASS ID= 2/3 + 6 CENTER - B (ADS #200038847)

(SPREADSHEET REVISION 5.0, OCTOBER 23, 1990)

ELEMENT	GRAV	OXIDE	NORM OXIDE	M.W.	MOLE	NORM OXIDE	COMPONENT	FREE ENERGY	NBO	KCAL/KG	
WT%	FACTOR	WT%	WT%		FRACTION	MOLE %	FREE ENERGY	HYDRATION			
Al2O3	1.5880	1.8895	3.0005	3.3181	101.9600	0.0294	2.0900	3.0400	0.0635	-0.0418	0.8946
CaO	0.6750	1.3992	0.9445	1.0444	56.0794	0.0168	1.1961	-16.1160	-0.1928	0.0239	-2.7142
Fe2O3	6.7940	1.4297	9.7134	10.7413	159.6922	0.0608	4.3198	15.5000	0.6696	-0.0864	9.4280
FeO	N/A	1.2865	0.0000	0.0000	71.8464	0.0000	0.0000	-14.6090	0.0000	0.0000	0.0000
MgO	0.4380	1.6583	0.7263	0.8032	40.3114	0.0180	1.2796	-13.8880	-0.1777	0.0256	-2.5024
MnO	1.4810	1.2912	1.9123	2.1146	70.9374	0.0270	1.9145	-14.8710	-0.2847	0.0383	-4.0088
Na2O	9.1270	1.3480	12.3032	13.6052	61.9790	0.1985	14.0978	-28.8150	-4.0623	0.2820	-57.1995
Li2O	1.8410	2.1525	3.9628	4.3821	29.8774	0.1326	9.4196	-22.7400	-2.1420	0.1884	-30.1609
NiO	0.6200	1.2726	0.7890	0.8725	74.7094	0.0106	0.7500	-14.3470	-0.1076	0.0150	-1.5152
SiO2	20.9600	2.1393	44.8397	49.5851	60.0848	0.7463	53.0002	5.5900	1.3098	0.0000	18.4423
Cr2O3	0.0730	1.4616	0.1067	0.1180	151.9974	0.0007	0.0499	37.3600	0.0186	-0.0010	0.2623
B2O3	3.2950	3.2201	10.6102	11.7331	69.6204	0.1524	10.8235	-9.9300	-1.0748	0.0000	-15.1334
UO2		1.1344	0.0000	0.0000	270.0388	0.0000	0.0000	-6.8000	0.0000	0.0000	0.0000
ThO2		1.1379	0.0000	0.0000	264.0400	0.0000	0.0000	-2.5330	0.0000	0.0000	0.0000
SnO	0.0310	1.1826	0.0367	0.0405	103.6194	0.0004	0.0251	-24.4000	-0.0061	0.0005	-0.0863
ZrO2	0.4870	1.3508	0.6578	0.7275	123.2188	0.0053	0.3792	45.1000	0.1710	0.0152	2.4078
TiO2	0.0860	1.6680	0.1434	0.1586	79.8988	0.0018	0.1275	15.9900	0.0204	0.0051	0.2871
K2O	0.3600	1.2046	0.4337	0.4795	94.2034	0.0046	0.3269	-41.7350	-0.1364	0.0065	-1.9212
Ca2O		1.0602	0.0000	0.0000	281.8094	0.0000	0.0000	-46.8200	0.0000	0.0000	0.0000
Sb2O3		1.1970	0.0000	0.0000	291.4982	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
P2O5	0.0170	2.2910	0.0389	0.0431	141.9370	0.0003	0.0195	-53.6200	-0.0104	0.0000	-0.1471
Nd2O3		1.1660	0.0000	0.0000	336.4782	0.0000	0.0000	-28.3200	0.0000	0.0000	0.0000
La2O3		1.1728	0.0000	0.0000	325.8100	0.0000	0.0000	-31.1400	0.0000	0.0000	0.0000
Y2O3		1.2699	0.0000	0.0000	225.8082	0.0000	0.0000	-12.9500	0.0000	0.0000	0.0000
BaO	0.0070	1.1165	0.0078	0.0086	153.3394	0.0001	0.0036	-30.5700	-0.0011	0.0001	-0.0156
PbO		1.0772	0.0000	0.0000	223.1900	0.0000	0.0000	-8.8100	0.0000	0.0000	0.0000
CoO2		1.2284	0.0000	0.0000	172.1200	0.0000	0.0000	11.3450	0.0000	0.0000	0.0000
MnO3		1.5003	0.0000	0.0000	143.9382	0.0000	0.0000	-21.7500	0.0000	0.0000	0.0000
ZnO	0.163	1.2447	0.2029	0.2244	81.3800	0.0025	0.1771	-2.4000	-0.0042	0.0035	-0.0598
CuO		1.2518	0.0000	0.0000	79.5454	0.0000	0.0000	1.7900	0.0000	0.0000	0.0000
Fe2+/Fe3+	0										
Cl	0.3277		0.3277	0.3277							
F	0.0227		0.0227	0.0227							
SO4	0.1906		0.1906	0.1906							
OXIDE SUMS	48.0430		90.4298	100.0000		1.4081	100.0000		-5.9474	0.4749	-83.7424
MOLAR BALANCE (M)		MOLAR SUMS		MOLE %	NORMALIZED MOLE %	SUM + pH Si		-5.9474			
						SUM + pH B		-5.9474			
						pH =					
K2SO4	0.3458	SALTS		1.0720	0.9590						
KCl	0.6887	BORATES		20.0535	17.9397						
KBF4	0.0376	CHROMATES		0.2274	0.2034						
NaBO2	20.0535	OXIDES		90.4298	80.8979						
Na2CrO4	0.2274										
		TOTAL		111.7827	100.0000						
K excess(M)	0.00										
Na excess (M)	0.09										
SO4 excess (M)	0.00										
Cl excess	0.00										
F excess	0.00										
B excess	0.00										
ALK/SiO2 =		0.450	TEST=								
ALK+ B2O3/SiO2 =		0.654	TIME=								
B2O3/SiO2 =		0.204									
VISCOSITY @TEMP(°C)		27.277	SA/V=								
LIQUIDUS RATIO =		0.077									
LIQUIDUS (°C) =		945.3955655									
NOTE LIQUIDUS AND VISCOSITY FORMULAS CHANGED TO CALCULATE ALL FE AS FE2O3 (OCTOBER 23, 1990)											

GLASS ID= 2/3 + 9 EDGE - A (ADS #200038948)

(SPREADSHEET REVISION 5.0, OCTOBER 23, 1990)

	ELEMENT	GRAV	OXIDE	NORM OXIDE	M.W.	MOLE	NORM OXIDE	COMPONENT	FREE ENERGY	NBO	KCAL/KG	
	WT%	FACTOR	WT%	WT%		FRACTION	MOLE %	FREE ENERGY	HYDRATION			
	Al2O3	1.6940	1.8895	3.2008	3.4686	101.9600	0.0314	2.1841	3.0400	0.0664	-0.0437	0.9543
	CaO	0.6960	1.3992	0.9738	1.0553	56.0794	0.0174	1.2082	-16.1160	-0.1947	0.0242	-2.7986
	Fe2O3	7.0280	1.4297	10.0479	10.8886	159.6922	0.0629	4.3776	15.5000	0.6785	-0.0876	9.7527
	FeO	N/A	1.2865	0.0000	0.0000	71.8464	0.0000	0.0000	-14.6090	0.0000	0.0000	0.0000
	MgO	0.4650	1.6583	0.7711	0.8356	40.3114	0.0191	1.3309	-13.8880	-0.1848	0.0266	-2.6566
	MnO	1.5580	1.2912	2.0117	2.1800	70.9374	0.0284	1.9730	-14.8710	-0.2934	0.0395	-4.2172
	Na2O	7.8990	1.3480	10.6479	11.5387	61.9790	0.1718	11.9525	-28.8150	-3.4441	0.2391	-49.5035
	Li2O	1.9220	2.1525	4.1371	4.4832	29.8774	0.1385	9.6338	-22.7400	-2.1907	0.1927	-31.4879
	NiO	0.6800	1.2726	0.8399	0.9102	74.7094	0.0112	0.7822	-14.3470	-0.1122	0.0156	-1.6130
	SiO2	21.9960	2.1393	47.0560	50.9931	60.0848	0.7832	54.4871	5.5900	1.4993	0.0000	21.5505
	Cr2O3	0.0710	1.4616	0.1038	0.1125	151.9974	0.0007	0.0475	37.3600	0.0177	-0.0010	0.2551
	B2O3	3.4510	3.2201	11.1126	12.0423	69.6204	0.1596	11.1051	-9.9300	-1.1027	0.0000	-15.8499
	UO2		1.1344	0.0000	0.0000	270.0388	0.0000	0.0000	-6.8000	0.0000	0.0000	0.0000
	ThO2		1.1379	0.0000	0.0000	284.0400	0.0000	0.0000	-2.5330	0.0000	0.0000	0.0000
	SrO	0.0320	1.1826	0.0378	0.0410	103.6194	0.0004	0.0254	-24.4000	-0.0062	0.0005	-0.0891
	ZrO2	0.4730	1.3508	0.6389	0.6924	123.2188	0.0052	0.3608	45.1000	0.1627	0.0144	2.3386
	TiO2	0.0740	1.6680	0.1234	0.1338	79.8988	0.0015	0.1075	15.9900	0.0172	0.0043	0.2470
	K2O	0.3310	1.2046	0.3987	0.4321	94.2034	0.0042	0.2945	-41.7350	-0.1229	0.0059	-1.7665
	Ce2O		1.0602	0.0000	0.0000	281.8094	0.0000	0.0000	-46.8200	0.0000	0.0000	0.0000
	Sb2O3		1.1970	0.0000	0.0000	291.4982	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
	P2O5	0.0230	2.2910	0.0527	0.0571	141.9370	0.0004	0.0258	-53.6200	-0.0138	0.0000	-0.1991
	Nd2O3		1.1660	0.0000	0.0000	336.4782	0.0000	0.0000	-28.3200	0.0000	0.0000	0.0000
	La2O3		1.1728	0.0000	0.0000	325.8100	0.0000	0.0000	-31.1400	0.0000	0.0000	0.0000
	Y2O3		1.2699	0.0000	0.0000	225.8082	0.0000	0.0000	-12.9500	0.0000	0.0000	0.0000
	BaO	0.0060	1.1165	0.0067	0.0073	153.3394	0.0000	0.0030	-30.5700	-0.0009	0.0001	-0.0134
	PbO		1.0772	0.0000	0.0000	223.1900	0.0000	0.0000	-8.8100	0.0000	0.0000	0.0000
	CeO2		1.2284	0.0000	0.0000	172.1200	0.0000	0.0000	11.3450	0.0000	0.0000	0.0000
	MoO3		1.5003	0.0000	0.0000	143.9382	0.0000	0.0000	-21.7500	0.0000	0.0000	0.0000
	ZnO	0.095	1.2447	0.1182	0.1281	81.3800	0.0015	0.1011	-2.4000	-0.0024	0.0020	-0.0349
	QuO		1.2518	0.0000	0.0000	79.5454	0.0000	0.0000	1.7900	0.0000	0.0000	0.0000
	Fe2+/Fe3+	0										
	Cl	0.3627		0.3627	0.3627							
	F	0.023		0.0230	0.0230							
	SO4	0.1744		0.1744	0.1744							
	OXIDE SUMS	48.4740		92.2792	100.0000		1.4373	100.0000		-5.2271	0.4326	-75.1315
	MOLAR BALANCE (M)			MOLAR SUMS	MOLE %	NORMALIZED			SUM + pH Si			
						MOLE %			SUM + pH B			
									pH =			
	K2SO4	0.3164		SALTS	1.1167	0.9743						
	KCl	0.7622		BORATES	21.0029	18.3239						
	KBF4	0.0381		CHROMATES	0.2211	0.1929						
	NaBO2	21.0029		OXIDES	92.2792	80.5089						
	Na2CrO4	0.2211										
				TOTAL	114.6199	100.0000						
	K excess(M)	-0.01										
	Na excess (M)	0.02										
	SO4 excess (M)	0.00										
	Cl excess	0.00										
	F excess	0.00										
	B excess	0.00										
	ALK/SiO2 =	0.402		TEST=								
	ALK+ B2O3/SiO2 =	0.605		TIME=								
	B2O3/SiO2 =	0.204										
	VISCOSITY @TEMP(°C)	39.892		SA/V=								
	LIQUIDUS RATIO =	0.076										
	LIQUIDUS (°C) =	942.2957817										
	NOTE LIQUIDUS AND VISCOSITY FORMULAS CHANGED TO CALCULATE ALL FE AS FE2O3 (OCTOBER 23, 1990)											

GLASS ID= 2/1 + 9 EDGE - B (ADS #200038049)

(SPREADSHEET REVISION 5.0, OCTOBER 23, 1990)

	ELEMENT	GRAV	OXIDE	NORM OXIDE	M.W.	MOLE	NORM OXIDE	COMPONENT	FREE ENERGY		KCAL/KG	
	WT%	FACTOR	WT%	WT%		FRACTION	MOLE %	FREE ENERGY	HYDRATION	NBO		
	Al2O3	1.6140	1.8895	3.0497	3.3605	101.9600	0.0299	2.1166	3.0400	0.0643	-0.0423	0.9093
	CaO	0.6570	1.3992	0.9193	1.0130	56.0794	0.0164	1.1600	-16.1160	-0.1869	0.0232	-2.6418
	Fe2O3	6.8500	1.4297	9.7934	10.7915	159.6922	0.0613	4.3398	15.5000	0.6727	-0.0868	9.5057
	FeO	N/A	1.2865	0.0000	0.0000	71.8464	0.0000	0.0000	-14.6090	0.0000	0.0000	0.0000
	MgO	0.4360	1.6583	0.7230	0.7967	40.3114	0.0179	1.2692	-13.8880	-0.1763	0.0254	-2.4909
	MnO	1.4840	1.2912	1.9161	2.1114	70.9374	0.0270	1.9115	-14.8710	-0.2843	0.0382	-4.0169
	Na2O	8.9640	1.3480	12.0835	13.3149	61.9790	0.1950	13.7962	-28.8150	-3.9754	0.2759	-56.1779
	Li2O	1.8530	2.1525	3.9886	4.3951	29.8774	0.1335	9.4469	-22.7400	-2.1482	0.1889	-30.3575
	NaO	0.6430	1.2726	0.8183	0.9017	74.7094	0.0110	0.7751	-14.3470	-0.1112	0.0155	-1.5714
	SiO2	21.1280	2.1393	45.1991	49.8055	60.0848	0.7523	53.2328	5.5900	1.3451	0.0000	19.0080
	Cr2O3	0.0620	1.4616	0.0906	0.0999	151.9974	0.0006	0.0422	37.3600	0.0158	-0.0008	0.2227
	B2O3	3.3530	3.2201	10.7970	11.8973	69.6204	0.1551	10.9744	-9.9300	-1.0898	0.0000	-15.3998
	UO2		1.1344	0.0000	0.0000	270.0388	0.0000	0.0000	-6.8000	0.0000	0.0000	0.0000
	ThO2		1.1379	0.0000	0.0000	264.0400	0.0000	0.0000	-2.5330	0.0000	0.0000	0.0000
	SrO	0.0290	1.1826	0.0343	0.0378	103.6194	0.0003	0.0234	-24.4000	-0.0057	0.0005	-0.0808
	ZrO2	0.4810	1.3508	0.6497	0.7160	123.2188	0.0053	0.3731	45.1000	0.1683	0.0149	2.3781
	TiO2	0.0730	1.6680	0.1218	0.1342	79.8988	0.0015	0.1078	15.9900	0.0172	0.0043	0.2437
	K2O	0.3350	1.2046	0.4035	0.4447	94.2034	0.0043	0.3031	-41.7350	-0.1265	0.0061	-1.7878
	Ca2O		1.0602	0.0000	0.0000	281.8094	0.0000	0.0000	-46.8200	0.0000	0.0000	0.0000
	Sb2O3		1.1970	0.0000	0.0000	291.4982	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
	P2O5	0.0140	2.2910	0.0321	0.0353	141.9370	0.0002	0.0160	-53.6200	-0.0086	0.0000	-0.1212
	Nd2O3		1.1660	0.0000	0.0000	336.4782	0.0000	0.0000	-28.3200	0.0000	0.0000	0.0000
	La2O3		1.1728	0.0000	0.0000	325.8100	0.0000	0.0000	-31.1400	0.0000	0.0000	0.0000
	Y2O3		1.2699	0.0000	0.0000	225.8082	0.0000	0.0000	-12.9500	0.0000	0.0000	0.0000
	BaO	0.0050	1.1165	0.0056	0.0062	153.3394	0.0000	0.0026	-30.5700	-0.0008	0.0001	-0.0111
	PbO		1.0772	0.0000	0.0000	223.1900	0.0000	0.0000	-8.8100	0.0000	0.0000	0.0000
	CeO2		1.2284	0.0000	0.0000	172.1200	0.0000	0.0000	11.3450	0.0000	0.0000	0.0000
	MoO3		1.5003	0.0000	0.0000	143.9382	0.0000	0.0000	-21.7500	0.0000	0.0000	0.0000
	ZnO	0.101	1.2447	0.1257	0.1385	81.3800	0.0015	0.1093	-2.4000	-0.0026	0.0022	-0.0371
	CoO		1.2518	0.0000	0.0000	79.5454	0.0000	0.0000	1.7900	0.0000	0.0000	0.0000
	Fe2+Fe3+	0										
	Cl	0.2272		0.2272	0.2272							
	F	N/A		N/A	N/A							
	SO4	0.1485		0.1485	0.1485							

OXIDE SUMS	48.0820	90.7513	100.0000	1.4131	100.0000	-5.8329	0.4652	-82.4268
------------	---------	---------	----------	--------	----------	---------	--------	----------

MOLAR BALANCE (M)	MOLAR SUMS	MOLE %	NORMALIZED	MOLE %	SUM + pH Si	SUM + pH B	pH =
-------------------	------------	--------	------------	--------	-------------	------------	------

K ₂ SO ₄	0.2694	SALTS	0.7469	0.6663			
KCl	0.4775	BORATES	20.4065	18.2042			
KBF ₄		CHROMATES	0.1931	0.1723			
NaBO ₂	20.4065	OXIDES	90.7513	80.9573			
Na ₂ CrO ₄	0.1931						
		TOTAL	112.0977	100.0000			

K excess (M)	0.00
Na excess (M)	0.08
SO ₄ excess (M)	0.00
Cl excess	0.00
F excess	
B excess	0.00

ALK/SiO ₂ =	0.442	TEST=	
ALK+ B ₂ O ₃ /SiO ₂ =	0.648	TIME=	
B ₂ O ₃ /SiO ₂ =	0.206		
VISCOSITY @TEMP(°C)	28.736	SA/V=	
LIQUIDUS RATIO =	0.077		
LIQUIDUS (°C) =	945.6550561		

NOTE LIQUIDUS AND VISCOSITY FORMULAS CHANGED TO CALCULATE ALL FE AS FE₂O₃ (OCTOBER 23, 1990)

GLASS ID= 2/3 + 9 CENTER - A (ADS #200038850)

(SPREADSHEET REVISION 5.0, OCTOBER 23, 1990)

	ELEMENT	GRAV	OXIDE	NORM OXIDE	M.W.	MOLE	NORM OXIDE	COMPONENT	FREE ENERGY	NBO	KCAL/KG
	WT%	FACTOR	WT%	WT%		FRACTION	MOLE %	FREE ENERGY	HYDRATION		
Al2O3	1.6170	1.8895	3.0553	3.3476	101.9600	0.0300	2.1102	3.0400	0.0641	-0.0422	0.9110
CaO	0.6250	1.3992	0.8745	0.9581	56.0794	0.0156	1.0981	-16.1160	-0.1770	0.0220	-2.5131
Fe2O3	6.8750	1.4297	9.8292	10.7693	159.6922	0.0616	4.3344	15.5000	0.6718	-0.0867	9.5404
FeO	N/A	1.2865	0.0000	0.0000	71.8464	0.0000	0.0000	-14.6090	0.0000	0.0000	0.0000
MgO	0.4260	1.6583	0.7064	0.7740	40.3114	0.0175	1.2341	-13.8880	-0.1714	0.0247	-2.4338
MnO	1.5000	1.2912	1.9368	2.1221	70.9374	0.0273	1.9227	-14.8710	-0.2859	0.0385	-4.0602
Na2O	9.0120	1.3480	12.1482	13.3101	61.9790	0.1960	13.8025	-28.3150	-3.9772	0.2761	-58.4788
Li2O	1.8550	2.1525	3.9929	4.3748	29.8774	0.1336	9.4110	-22.7400	-2.1401	0.1882	-30.3903
NiO	0.6430	1.2726	0.8183	0.8965	74.7094	0.0110	0.7713	-14.3470	-0.1107	0.0154	-1.5714
SiO2	21.1790	2.1393	45.3082	49.6419	60.0848	0.7541	53.1013	5.5900	1.3430	0.0000	19.0715
Cr2O3	0.0690	1.4616	0.1009	0.1105	151.9974	0.0007	0.0467	37.3600	0.0175	-0.0009	0.2479
B2O3	3.4390	3.2201	11.0739	12.1331	69.6204	0.1591	11.2010	-9.9300	-1.1123	0.0000	-15.7948
UO2		1.1344	0.0000	0.0000	270.0388	0.0000	0.0000	-6.8000	0.0000	0.0000	0.0000
ThO2		1.1379	0.0000	0.0000	264.0400	0.0000	0.0000	-2.5330	0.0000	0.0000	0.0000
SrO	0.0320	1.1826	0.0378	0.0415	103.6194	0.0004	0.0257	-24.4000	-0.0063	0.0005	-0.0891
ZrO2	0.4940	1.3508	0.6673	0.7311	123.2188	0.0054	0.3814	45.1000	0.1720	0.0153	2.4424
TiO2	0.0770	1.6680	0.1284	0.1407	79.8988	0.0016	0.1132	15.9900	0.0181	0.0045	0.2570
K2O	0.3580	1.2046	0.4312	0.4725	94.2034	0.0046	0.3224	-41.7350	-0.1345	0.0064	-1.9106
Ca2O		1.0602	0.0000	0.0000	281.8094	0.0000	0.0000	-46.8200	0.0000	0.0000	0.0000
Sb2O3		1.1970	0.0000	0.0000	291.4982	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
P2O5	0.0150	2.2910	0.0344	0.0377	141.9370	0.0002	0.0170	-53.6200	-0.0091	0.0000	-0.1298
Nd2O3		1.1660	0.0000	0.0000	336.4782	0.0000	0.0000	-28.3200	0.0000	0.0000	0.0000
La2O3		1.1728	0.0000	0.0000	325.8100	0.0000	0.0000	-31.1400	0.0000	0.0000	0.0000
Y2O3		1.2699	0.0000	0.0000	225.8082	0.0000	0.0000	-12.9500	0.0000	0.0000	0.0000
BaO	0.0050	1.1165	0.0056	0.0061	153.3394	0.0000	0.0026	-30.5700	-0.0008	0.0001	-0.0111
PbO		1.0772	0.0000	0.0000	223.1900	0.0000	0.0000	-8.8100	0.0000	0.0000	0.0000
CeO2		1.2284	0.0000	0.0000	172.1200	0.0000	0.0000	11.3450	0.0000	0.0000	0.0000
MoO3		1.5003	0.0000	0.0000	143.9382	0.0000	0.0000	-21.7500	0.0000	0.0000	0.0000
ZnO	0.097	1.2447	0.1207	0.1323	81.3800	0.0015	0.1045	-2.4000	-0.0025	0.0021	-0.0356
Q.O		1.2518	0.0000	0.0000	79.5454	0.0000	0.0000	1.7900	0.0000	0.0000	0.0000
Fe2+/Fe3+	0										
Cl	0.3768		0.3768	0.3768							
F	N/A		N/A	N/A							
SO4	0.1098		0.1098	0.1098							

OXIDE SUMS	48.3180	91.2701	100.0000		1.4201	100.0000		-5.8412	0.4639	-82.9485
------------	---------	---------	----------	--	--------	----------	--	---------	--------	----------

MOLAR BALANCE (M)	MOLAR SUMS	MOLE %	NORMALIZED MOLE %	SUM + pH Si	-5.8412
				SUM + pH B	-5.8412
				pH =	

K2SO4	0.1992	SALTS	0.9910	0.8739
KCl	0.7919	BORATES	20.9299	18.4557
KBF4		CHROMATES	0.2149	0.1895
NaBO2	20.9299	OXIDES	91.2701	80.4809
Na2CrO4	0.2149			
		TOTAL	113.4059	100.0000

K excess (M)
 Na excess (M) 0.07
 SO4 excess (M) 0.00
 Cl excess 0.00
 F excess
 B excess 0.00

ALK/SiO2 =	0.443	TEST=	
ALK+ B2O3/SiO2 =	0.654	TIME=	
B2O3/SiO2 =	0.211		
VISCOSITY @TEMP(°C)	28.005	SA/V=	
LIQUIDUS RATIO =	0.077		
LIQUIDUS (°C) =	945.943831		

NOTE LIQUIDUS AND VISCOSITY FORMULAS CHANGED TO CALCULATE ALL FE AS FE2O3 (OCTOBER 23, 1990)

GLASS ID= 2/3 + 9 CENTER - B (ADS #200038851)

(SPREADSHEET REVISION 5.0, OCTOBER 23, 1990)

	ELEMENT	GRAV	OXIDE	NORM OXIDE	M.W.	MOLE	NORM OXIDE	COMPONENT	FREE ENERGY	NBO	KCAL/KG
	WT%	FACTOR	WT%	WT%		FRACTION	MOLE %	FREE ENERGY	HYDRATION		
Al2O3	1.6900	1.8895	3.1933	3.3600	101.9600	0.0313	2.1133	3.0400	0.0642	-0.0423	0.9521
CaO	0.8610	1.3992	1.2047	1.2676	56.0794	0.0215	1.4496	-16.1160	-0.2336	0.0290	-3.4621
Fe2O3	7.1430	1.4297	10.2123	10.7455	159.6922	0.0640	4.3153	15.5000	0.6689	-0.0863	9.9123
FeO	N/A	1.2865	0.0000	0.0000	71.8464	0.0000	0.0000	-14.6090	0.0000	0.0000	0.0000
MgO	0.4740	1.6583	0.7860	0.8271	40.3114	0.0195	1.3158	-13.8880	-0.1827	0.0263	-2.7080
MnO	1.5360	1.2912	1.9833	2.0868	70.9374	0.0280	1.8866	-14.8710	-0.2806	0.0377	-4.1577
Na2O	9.1380	1.3480	12.3180	12.9611	61.9790	0.1987	13.4111	-28.8150	-3.8644	0.2682	-57.2684
Li2O	1.9510	2.1525	4.1995	4.4188	29.8774	0.1406	9.4847	-22.7400	-2.1568	0.1897	-31.9630
NiO	0.6580	1.2726	0.8374	0.8811	74.7094	0.0112	0.7563	-14.3470	-0.1085	0.0151	-1.6081
SiO2	22.2260	2.1393	47.5481	50.0305	60.0848	0.7913	53.3993	5.5900	1.3582	0.0000	20.1275
Cr2O3	0.0650	1.4616	0.0950	0.1000	151.9974	0.0006	0.0422	37.3600	0.0158	-0.0008	0.2335
B2O3	3.4950	3.2201	11.2542	11.8418	69.6204	0.1617	10.9081	-9.9300	-1.0832	0.0000	-16.0520
UO2		1.1344	0.0000	0.0000	270.0388	0.0000	0.0000	-6.8000	0.0000	0.0000	0.0000
ThO2		1.1379	0.0000	0.0000	264.0400	0.0000	0.0000	-2.5330	0.0000	0.0000	0.0000
SrO	0.0340	1.1826	0.0402	0.0423	103.6194	0.0004	0.0262	-24.4000	-0.0064	0.0005	-0.0947
ZrO2	0.4840	1.3508	0.6538	0.6879	123.2188	0.0053	0.3580	45.1000	0.1615	0.0143	2.3930
TiO2	0.0760	1.6680	0.1268	0.1334	79.8988	0.0016	0.1071	15.9900	0.0171	0.0043	0.2537
K2O	0.3560	1.2046	0.4288	0.4512	94.2034	0.0046	0.3072	-41.7350	-0.1282	0.0061	-1.8999
Ca2O		1.0602	0.0000	0.0000	281.8094	0.0000	0.0000	-46.8200	0.0000	0.0000	0.0000
Sb2O3		1.1970	0.0000	0.0000	291.4982	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
P2O5	0.0110	2.2910	0.0252	0.0265	141.9370	0.0002	0.0120	-53.6200	-0.0064	0.0000	-0.0952
Nd2O3		1.1660	0.0000	0.0000	336.4782	0.0000	0.0000	-28.3200	0.0000	0.0000	0.0000
La2O3		1.1728	0.0000	0.0000	325.8100	0.0000	0.0000	-31.1400	0.0000	0.0000	0.0000
Y2O3		1.2699	0.0000	0.0000	225.8082	0.0000	0.0000	-12.9500	0.0000	0.0000	0.0000
BaO	0.0040	1.1165	0.0045	0.0047	153.3394	0.0000	0.0020	-30.5700	-0.0006	0.0000	-0.0089
PbO		1.0772	0.0000	0.0000	223.1900	0.0000	0.0000	-8.8100	0.0000	0.0000	0.0000
CeO2		1.2284	0.0000	0.0000	172.1200	0.0000	0.0000	11.3450	0.0000	0.0000	0.0000
MnO3		1.5003	0.0000	0.0000	143.9382	0.0000	0.0000	-21.7500	0.0000	0.0000	0.0000
ZnO	0.102	1.2447	0.1270	0.1336	81.3800	0.0016	0.1053	-2.4000	-0.0025	0.0021	-0.0374
Q2O		1.2518	0.0000	0.0000	79.5454	0.0000	0.0000	1.7900	0.0000	0.0000	0.0000
Fe2+//Fe3+	0										
Cl	0.2573		0.2573	0.2573							
F	N/A		N/A	N/A							
SO4	0.1804		0.1804	0.1804							
SUMS	50.3040		95.0381	100.0000		1.4819	100.0000		-5.7683	0.4641	-85.4834
MOLAR BALANCE (M)			MOLAR SUMS	MOLE %	NORMALIZED			SUM + pH Si	-5.7683		
					MOLE %			SUM + pH B	-5.7683		
								pH =			
K2SO4	0.3273		SALTS	0.8680	0.7395						
KCl	0.5407		BORATES	21.2707	18.1213						
KBF4			CHROMATES	0.2024	0.1725						
NaBO2	21.2707		OXIDES	95.0381	80.9667						
Na2CrO4	0.2024										
			TOTAL	117.3792	100.0000						
K excess(M)											
Na excess (M)	0.07										
SO4 excess (M)	0.00										
Cl excess											
F excess											
B excess	0.00										
ALK/SiO2 =	0.435		TEST=								
ALK+ B2O3/SiO2 =	0.639		TIME=								
B2O3/SiO2 =	0.204										
VISCOSITY @TEMP(°C)	30.822		SA/V=								
LIQUIDUS RATIO =	0.077										
LIQUIDUS (°C) =	943.3955774										
NOTE LIQUIDUS AND VISCOSITY FORMULAS CHANGED TO CALCULATE ALL FE AS FE2O3 (OCTOBER 23, 1990)											

This page intentionally left blank.

DISTRIBUTION WSRC-TR-92-260

cc: L.M. Papouchado, 773-A
E. W. Holtzscheiter, 773-A
M.J. Plodinec, 773-A
W.T. Goldston, 704-S
J. T. Carter, 704-1T
C. T. Randall, 704-1T
L. F. Landon, 704-1T
N. E. Bibler, 773-A
C.M. Jantzen, 773-A
G. G. Wicks, 773-A
A. A. Ramsey, 704-15S
W. G. Ramsey, 773-A
M. K. Andrews, 773-62A
B. C. Ha, 773-A
K. E. Mottell, 773-43A
R. F. Schumacher, 773-42A
D. C. Beam, 773-A
D. F. Bickford, 773-A
S. L. Marra, 704-15S
C. A. Cicero, 773-62A
D. M. Ferrara, 773-62A
J. R. Harbour, 773-43A
J. F. Sproull, 704-S
M.E. Smith, 704-1T
N.D. Hutson, 704-1T
D.H. Miller, 704-1T
A.S. Choi, 704-1T
L. O. Westphal, 704-S
SRL Records, 773-A

END

**DATE
FILMED**

12 / 14 / 92