DOE/PC/90167--T6

"MULLED COAL - A BENEFICIATED COAL FORM
FOR USE AS A FUEL OR FUEL INTERMEDIATE"

DOE/PC/90167---T6

DE92 019663

Contract No. DE-AC22-90PC90167

Technical Progress Report No. 6
For the Period July 1, 1991 through September 30, 1991

Prepared By:

ENERGY INTERNATIONAL CORPORATION
135 William Pitt Way
Pittsburgh, PA 15238
Report No. 90167-007

Submitted: November 1991

FINAL

Prepared For:

PETC Project Manager: Anthony E. Mayne

Pittsburgh Energy Technology Center
U.S. Department of Energy
P. O. Box 10940
Pittsburgh, PA 15236

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

TABLE OF CONTENTS

	<u>Page No.</u>
I. EXECUTIVE SUMMARY	1
II. INTRODUCTION.	1
III. PROJECT DESCRIPTION	3
IV. PROJECT STATUS.	3
1.0 Phase I - Technology Development	3
1.1 Feedstock Procurement	3
1.2 Feasibility Study	4
1.3 Lab Scale Tests	4
2.0 Phase II - System Demonstration.	4
2.1 Component Development	4
V. PLANNED ACTIVITIES.	16
VI. SUMMARY	16

LISTS OF TABLES

	<u>Page No.</u>
Table I Continuous Processor Tests.	5
Table II Milled Coal Samples Submitted for Flowability Tests	9
Table III Basic Hopper Design Criteria.	10
Table IV Basic Hopper Design Criteria.	11
Table V Basic Hopper Design Criteria.	12
Table VI Aging Study Matrix.	17

LIST OF FIGURES

	<u>Page No.</u>
Figure 1 Continuous Processing System for Making MC/CWF.	7
Figure 2 Arching Diameter vs Moisture Content for. Various NPA Concentrations	13
Figure 3 Stable Rathole Diameter vs Moisture Content for Various NPA Concentrations	14
Figure 4 Product Flow Illustrations.	15

I. EXECUTIVE SUMMARY

Energy International Corporation has been awarded a contract by DOE-PETC (DE-AC22-90PC90167) to evaluate a new concept for utilization of the fine coal wet cake produced by many of the physical beneficiation processes now under development. The project started with the selection of coal feedstocks on May 15, 1990. This report covers activities from July 1, 1991 through September 30, 1991.

II. INTRODUCTION

Under the auspices of the Department of Energy and private industry, considerable progress has been made in:

- o preparation of coal-water fuels
- o combustion of low-ash coal-based fuel forms
- o processes to provide deeply-cleaned coal

These technology advances are compatible with the national objective to increase the environmentally responsive use of readily available and abundant coal resources, and to reduce oil and gas fuel consumption.

As these technical developments move toward commercial application, the need for coordinated efforts and integrated requirements has become increasingly apparent. Systems are vitally needed to integrate energy delivery systems from the raw resource through processing to application and end use. Problems have been encountered in the preparation of conventional coal-water fuels that mutually satisfy the requirements for storage stability, handling, preparation, atomization, combustion, and economics. Experience has been slow in evolving generic technologies or products and coal-specific requirements and specifications continue to dominate the development. Thus, prospects for commercialization remain highly specific to the coal, the processor, and the end use.

Developments in advanced beneficiation of coal to meet stringent requirements for low ash and low sulfur can be anticipated to further complicate the problem areas. This is attributable to the beneficiated coal being procured in very fine particles with high surface areas, modified surface characteristics, reduced particle size distribution range, and high inherent moisture. Experience in the storage, handling, and transport of highly beneficiated coal has been limited. This is understandable, as quantities of such product are only now becoming available in meaningful quantities.

Since the inception of the project, we have:

- o Developed formulations for stabilizing wet filter cake into a granular free flowing material (Mulled Coal).
- o Applied the formulation to wet cake from a variety of coal sources ranging from anthracite to subbituminous coal.
- o Evaluated effects of moisture loss on mull properties.
- o Developed design concepts for equipment for preparing the Mulled Coal and converting it into Coal Water Fuel.

This report covers activities from July 1, 1991 to September 30, 1991. During this period we have:

- o Obtained storage and handling system design data for the granular coal.
- o Begun the 75-day aging study on various mull formulations to determine the effects of time and exposure on mull properties.
- o Demonstrated the continuous production of mulled coal from wet filter cake.

During the next quarter we will:

- o Complete the 75-day aging studies on various mull formulations.
- o Demonstrate continuous production of mull from wet cake.
- o Demonstrate the continuous production of CWF from mull.
- o Perform atomization studies on Mulled Coal and CWF prepared from Mulled Coal.

Much of the existing work and experience with advanced coal-based fuels such as CWF has been built on the premise that the fuel should, and will, be capable of being compatible with use in the existing storage, handling, and transport equipment as a "one-to-one" replacement for conventional oil fuels. Expensive additives, additional processing, equipment, and system modifications will be needed to provide effective and versatile fuel delivery systems. This will be even more significant for fine particle highly beneficiated coal fuels.

The conventional approach for formulation of CWF would be to develop a single formulation that meets the requirements of the total fuel system. At best, the resultant material will have properties that represent a compromise.

Energy International is developing a technology that will create a staged formulation with the first coal form (Mulled Coal) that can be stored, transported, and pumped. Just prior to combustion, the Mulled Coal (MC) will be modified to provide the properties needed for proper atomization. This concept is an alternative to the expensive and energy intensive thermal drying processing of fine coal wet cake. The material is suitable for both direct feed use in conventional and fluid bed combustors as well as on-site conversion to combustible slurries. By maintaining the coal form relatively close to the feed wet cake, only minor processing with low additive levels and low energy blending is needed at the point of production. Its conversion to slurry or other use-feed form is made near the time of use and thus the requirements for stability, climatic control, storage, transport, and handling requirements are much less severe.

III. PROJECT DESCRIPTION

The Mulled Coal project is divided into a series of tasks designed to produce formulations and system designs suitable to convert fine coal "wet cakes" into materials that can be stored, handled, and transported to a site where it can be utilized as a fuel in existing and developing combustion devices.

The work is divided into two phases:

Phase I will provide the technology base and establish the technical feasibility of the concept of stabilizing the fine coal "wet cake" in a form that can be readily stored and moved to the location where it can either be combusted "as is" or converted into a desired fuel form at the combustion site. The information developed during Phase I should provide a basis for design and implementation of a demonstration program (Phase III).

Phase II will demonstrate the ability to utilize the Mulled Coal to improve the ability to store and move fine coal products as a stable "wet cake". Tasks in this phase will first test components of the fine coals and subsequently demonstrate operations of an integrated system for storing, handling, and combustion of the highly beneficiated fine coal products.

Phase I - Once the feed coals are selected, basic technical information for formulations of Mulled Coal will be developed through bench studies. Some base assumptions for the process concept are:

1. Chemical formulations will have to consider end use as well as the chemistry involved with the beneficiation processes.
2. If any changes in particle sizes are required for the combustor, they should be made before formulation of the Mulled Coal.
3. Conversion from Mulled Coal to the final fuel form should require minimal equipment and relatively moderate conditions such as dilution, addition of small quantities of reagents, mild agitation, and little heating. Grinding, high temperatures, corrosive or hazardous materials, etc. should be minimized.

Phase II - Phase II will comprise the design, acquisition, and testing of the system components required to simulate the storage, transportation and combustion of the "mulled coal" formulation(s). The "mulled coal" will be prepared in sufficient quantities to perform a full system test of the preferred formulations.

IV. PROJECT STATUS

1.0 Phase I - Technology Development

1.1 Feedstock Procurement

Sufficient raw coal has been procured to satisfy project requirements.

1.2 Feasibility Study

Evaluation of reagents and various mull formulations have been completed.

1.3 Laboratory Scale Tests

Lab scale testing of the mull and slurry components is complete. The final task activity was completion of the Phase I Technical Report during this quarter.

2.0 Phase II - System Demonstration

2.1 Component Development

2.1.1 Mulled Coal Preparation

Four tons of deep-cleaned Upper Elkhorn #3 coal were sent to Virginia Tech to be ground to approximately 20 micron average particle size and centrifuged to approximately 40-45 wt. % moisture content. Three tons of this wet cake will be sent back to EI and made into mulled coal product using the 2-inch continuous processor currently being tested at EI. One to two tons of mulled coal will then be sent to Grand Forks, North Dakota (UNDEERC) for the full system test scheduled for late October.

2.1.2 Component Fabrication

A 2-inch continuous processor has been leased from Teledyne Readco and installed at EI for testing in July. An Accurate Volumetric Screw Feeder (Model No. 602) has also been leased and installed. Approximately 500 pounds of deep-cleaned Upper Elkhorn No. 3 coal was ground in our 20 in. x 30 in. batch ball mill to 20 micron average particle size, and then filtered and dried to 1% moisture content to be used for testing the processor. Several tests were made in which wet cake, mulled coal, and coal-water slurry were produced in the continuous processor, see Table I and Figure 1.

Tests TCP-1, TCP-7, and TCP-16 were made feeding dry, powdered coal plus water to make a 35% wet cake. A satisfactory wet cake was made at the following conditions: 50 lb/hr coal feed, 25.2 lb/hr water feed, 100 RPM agitator speed, and 1.0 mesh outlet weir opening.

The 35% wet cake was fed to the processor at 50 lb/hr and 25 lb/hr with a non-polar additive (NPA) to determine the optimum mull production rate for this processor (see tests TCP-2 and 3). The mull product at 50 lb/hr feed rate (1.2 minute residence time) was fairly lumpy and was considered to be marginal at this NPA concentration. The mull product at 25 lb/hr wet cake feed rate (2.4 minutes residence time) contained only a few small lumps and was considered to be satisfactory.

The product mull was then fed to the processor with dispersant addition to make coal-water slurry. The dispersant was fed as a 25 wt. % solution in water for metering convenience. Good coal-water slurry was made at 50 lb/hr and 100 lb/hr mull feed rates with 1 wt. % dispersant (see tests TCP-4, 5, and 6).

Table I

TESTS RUN IN TELEDYNE TWO-INCH CONTINUOUS PROCESSOR

Test No.	Solids Charge			Agent			Weir In.	Motor RPM	Comments
	Feed	Rate Lb/Hr	Set	Feed	Rate Lb/Hr	Set			
TCP-1	Coal (1)	50	150	H ₂ O	25.2	8.2	1.0	150	Wetcake not too good - chunky
TCP-1A	Coal (1)	50	150	H ₂ O	25.2	8.2	1.0	100	Wetcake OK - 35% H ₂ O
TCP-2	Wetcake	50	225	NPA (2)	0.99	3.7	3/4	310	Mull OK - fairly lumpy - 3% NPA
TCP-3	Wetcake	25.9	170	NPA	0.50	2.7	3/4	310	Mull better - smaller lumps - 3% NPA
TCP-4	Mull (3)	52.3	200	Disper. (4)	0.33	3.7	3/4	310	Good slurry
TCP-5	Mull	102.2	350	Disper.	0.66	4.3	3/4	310	Good slurry
TCP-6	Mull	102.2	350	Disper.	0.66	4.3	3/4	160	Good slurry
TCP-7	Coal	53.7	150	H ₂ O	25.6	8.3	1.0	100	Wetcake OK - lots of small lumps
TCP-8	Wetcake	30.25	165	NPA	0.60	2.7	1/2	310	Mull OK - 3% NPA
TCP-9	Wetcake	30.25	165	NPA	0.42	2.5	3/4	310	Mull marginal - 2% NPA
TCP-10	Wetcake	30.25	165	NPA	0.22	2.3	3/4	310	Mull no good - 1% NPA
TCP-11	Wetcake	30.25	165	NPA	0.60	2.7	3/4	310	Make mull for Beard Oil - 3% NPA
TCP-12	Mull	52.3	200	Disper. - 1% NPA	0.33	3.0	3/4	310	Good C-W-S Viscosity 218 cp @ 100 Particle Size 18.15 μ m HV 281 cp @ 200 1.200 PLF
TCP-13	Wetcake	31.3	164	NPA	0.22	2.3	3/4	310	Mull wet and chunky - 1% NPA
TCP-14	Mull	50	200	Disper. 0.5% NPA	0.16	2.5	3/4	310	Good C-W-S 515 cp @ 200 s ⁻¹ 357 cp @ 100 s ⁻¹ PLF - 1.344
TCP-15	Mull	50	200	Disper. 1.0% NPA	0.33	3.0	3/4	310	Good C-W-S 265 cp @ 200 s ⁻¹ 235 cp @ 100 s ⁻¹ 1.039 PLF

Table I (Cont'd)

TESTS RUN IN TELEDYNE TWO-INCH CONTINUOUS PROCESSOR

Test No.	Solids Charge			Agent			Weir In.	Motor RPM	Comments
	Feed	Rate Lb/Hr	Set	Feed	Rate Lb/Hr	Set			
TCP-16	Coal	50	150	H ₂ O	25.2	8.2	1.0	100	Wetcake OK - same as TCP-LA
TCP-17A	Wetcake	40	160	NPA	0.80	2.7	3/4	310	Mull chunky - marginal - 3% NPA
TCP-17B	Wetcake	40	160	NPA	0.80	2.7	1/2	310	Weir opening showed no effect
TCP-18	Wetcake	50	200	NPA	1.01	3.0	3/4	310	Mull chunky and feels wet. It flows but not a very good mull at 3% NPA.

(1) Deep-cleaned Upper Elkhorn No. 3 coal ground to 20 μ m MV, dried to 1% moisture.

(2) Non-polar additive - weight % of dry coal.

(3) Wetcake product from run TCP-3.

(4) Dispersing agent - weight % of dry coal, 25% in water solution.

Figure 1
 CONTINUOUS PROCESSING SYSTEM FOR
 MAKING MULLED COAL AND/OR COAL-WATER-SLURRY

Three tests were made to determine the effects on the mull of lowering the NPA concentration. The mull was marginal or unsatisfactory at 1 and 2 wt. % NPA (see tests TCP-8, 9, and 10) even at the low wet cake feed rate of 30 lb/hr.

Two tests were made to evaluate the coal-water slurry viscosity at 0.5 and 1.0 wt. % dispersant levels (see tests TCP-14 and 15). The higher dispersant amount lowered the viscosity and power law factor to acceptable levels.

Three additional tests were made to see whether the outlet weir opening had any effect on the mull product (see tests TCP-17A, 17B, and 18). The weir opening showed no apparent effect on the product. Closing the weir opening increases the product holdup in the processor.

After reviewing the data from the above tests, we concluded that:

1. The 2-inch Continuous Processor can make satisfactory mulled coal product feeding 35% moisture wet cake (20 um MV particle size) at 30 lb/hr with 3 wt. % NPA. Higher feed rates produce a lumpy and sticky mulled product. The throughput is limited by the low residence time (<2 minutes) in this mixer. Other types of mixers such as pug mill or a Simpson Multi-Muller should be tested for commercial mull production.
2. A satisfactory coal-water slurry can be produced at a mulled coal feed rate up to 100 lb/hr with a 1.0 wt. % dispersant. This would meet the requirements for the full test system to be used at Grand Forks, North Dakota (UNDEERC) for the slurry atomization study.

2.1.3 ESTL Testing

Solids Flow Testing

Sufficient quantities of ground, deep-cleaned Upper Elkhorn #3 coal were ground to 12, 20, and 70 micron average particle sizes for the solids flow tests. Ten samples with varying amounts of dried coal, water, and NPA were prepared in the batch Sigma Blade mixer and submitted to Henk Colijn and Associates for the storage and handling studies (see Table II). In Tables III, IV, and V, the critical arching dimensions for mass flow and the stable rathole diameters are given for the first seven samples, both at instantaneous steady flow and after three days consolidation.

The critical arching dimension is the outlet size below which the material will not flow. The critical arching diameter vs moisture and oil content is shown in Figure 2. As can be seen, this dimension increases at the moisture content is increased and decreases as the oil content as increased. Also, time consolidation greatly increases the critical arching diameter.

The stable rathole diameters are mainly for funnel flow applications. The stable rathole diameter vs moisture and oil content is shown in Figure 3. Mass flow can be obtained by expanding the outlet opening of the bin above the stable rathole diameter (see Figure 4). The stable rathole diameter increases almost threefold after time consolidation.

Table II

SAMPLES OF MULLED COAL SUBMITTED TO
HENK COLIJN FOR FLOWABILITY TESTING

<u>Sample No.</u>	<u>Ave. Particle Size</u> <u>Microns</u>	<u>Moisture</u> <u>Wt %</u>	<u>NPA</u> <u>Wt % of Coal</u>
005-87A	20	20	0.5
005-88A	20	20	1
005-89A	20	30	1
005-90A	20	30	2
005-91A	20	30	3
005-92A	20	40	1
005-93A	20	40	3
005-114-1	20	30	0
005-114-A	12	30	2
005-114-B	70	30	2

Table III

H. Colijn and Assoc. Basic Hopper Design Criteria

Company: ENERGY INTERNATIONAL CORP.

Material: Coal - NPA Mixture

Moisture

18.8%

19.4%

NPA

0.5%

1.0%

	005-87A	005-88A
Critical Arching Dimension for mass-flow:		
Steady flow:		
round outlet diameter	0.3'	0.7'
slot outlet dimension	0.15'x0.5'	0.35'x1.1'
Time Consolidation:		
round outlet diameter	0.8'	2.1'
slot outlet dimension	0.4'x1.2'	1'x3'
Stable rathole diameters:		
Steady flow	0.6'	1.6'
Time Consolidation	1.8'	3.5'
Minimum hopper slope angles (with horizontal) for mass flow (deg):		
Cone:		
UHMP	90	90
304-2B stainless steel	90	90
Wedge:		
UHMP	80	80
304-2B stainless steel	90	90
Self-cleaning hopper and chute angle (with horizontal) (deg):		
UHMP	60	60
304-2B stainless steel	73	76
Rusted carbon steel	73	76

Table IV

H. Colijn and Assoc.

Basic Hopper Design Criteria

Company: ENERGY INTERNATIONAL CORP.

Material: Coal-NPA Mixture

Moisture	29.3%	29.6%	29.7%
NPA	1.0%	2.0%	3.0%

	005-89A	005-90A	005-91A
Critical Arching Dimension for mass-flow:			
Steady flow:			
round outlet diameter	2.2'	1.3'	0.7'
slot outlet dimension	1'x3'	0.6'x1.8'	0.35'x1.1'
Time Consolidation:			
round outlet diameter	4.7'	3.4'	2.5'
slot outlet dimension	2.2'x6.6'	1.6'x4.8'	1.1'x3.3'
Stable rathole diameters:			
Steady flow	5.5'	2.8'	1.6'
Time Consolidation	11'	7.0'	4.1'
Minimum hopper slope angles (with horizontal) for mass flow (deg):			
Cone:			
UHMP	85	85	85
304-2B stainless steel	85	83	80
Wedge:			
UHMP	75	75	75
304-2B stainless steel	75	73	70
Self-cleaning hopper and chute angle (with horizontal) (deg):			
UHMP	72	72	72
304-2B stainless steel	68	68	68
Rusted carbon steel	84	84	84

Table V.

H. Colijn and Assoc. Basic Hopper Design Criteria

Company: ENERGY INTERNATIONAL CORP.

Material: Coal-NPA Mixture

Moisture

40.3%

39.9%

NPA

1.0%

3.0%

	005-92A	005-93A
Critical Arching Dimension. for mass-flow:		
Steady flow:		
round outlet diameter	5.9'	2.2'
slot outlet dimension	2.8"x8.4'	1"x3'
Time Consolidation:		
round outlet diameter	16.7'	6.4"
slot outlet dimension	8"x24'	3"x9'
Stable rathole diameters:		
Steady flow	16.5'	6.4'
Time Consolidation	*	10'
Minimum hopper slope angles (with horizontal) for mass flow (deg):		
Cone:		
UHMP	85	90
304-2B stainless steel	85	90
Wedge:		
UHMP	75	85
304-2B stainless steel	75	85
Self-cleaning hopper and chute angle (with horizontal) (deg):		
UHMP	67	70
304-2B stainless steel	67	67
Rusted carbon steel	80	80

H. COLIJN

CONSULTING ENGINEER

Figure 3

TRANSPORTATION & MATERIAL SOLING SYSTEMS

423 FRANKLIN HTE. DRIVE

MONROEVILLE, PA. 15146

DATE 8/25/91

SUBJECT: COAL-NPA MIXTURE

K&E IN X.10 TO 1 INCH 7 1/2 IN X 10 IN MS
KEUFFEL & ESSER CO. MADE IN U.S.A.

Figure 4

FLOW PATTERNS

As can be seen from the steep hopper slope angles, this material will not readily flow out of a conical bottom vessel. The material is very sticky and compacts easily. Also, the hopper surface should be lined with a very smooth material such as UHMP polyethylene to improve the solids flow. Based on these preliminary results Mr. Henk Colijn concluded that a special bottom tank with a chute design containing a screw feeder or belt feeder may be necessary to obtain good solids flow. Also, the flowability of the solids can be improved by decreasing the moisture content and/or increasing the NPA amount for a given particle size.

Aging Studies

Approximately 270 lb (30 gals) of granular mull were prepared for aging studies. The Upper Elkhorn #3 feedstock coal was ground to a +/- micron particle size with +/- 30% moisture. Twelve three-gallon mull samples were prepared with varying NPA concentrations on August 6, 1991. The aging process will evaluate weather and/or time effects on samples stored in an open bin, closed bin, nitrogen inerted bin and shallow ("skin effect") tray for 75 days. Table VI provides a matrix of the study. The samples will be riffled, sampled and measured for moisture content, oxidation levels and flowability tests every two weeks. This simulation will provide information on how different storage techniques may affect the handling and transportation characteristics of the granular mulls.

V. PLANNED ACTIVITIES

1. One to two tons of mulled coal will be prepared at EI to be used for the full system testing of the solid mull and CWF at Grand Forks, North Dakota (UNDEERC).
2. The 75-day aging test program of various coal formulations will be completed.
3. The "in-line" system which includes the 2-inch continuous processor will be assembled and shipped to UNDEERC at Grand Forks, North Dakota for the coal-water fuel atomization testing.
4. The final selection of mull coal formulations from the aging test program will be submitted to the consulting engineers on transportation and material handling systems to perform flow and storage tests.
5. The Final Project Report will be prepared.

VI. SUMMARY

Four tons of precleaned coal have been sent to Virginia Tech Coal and Mineral Research Lab at Blacksburg, VA to be ground to 20 microns average particle size and centrifuged to 40 to 45 wt. % moisture.

A 2-inch continuous processor, leased by EI from Teledyne Readco Corporation, has been installed and tested for making wet cake, mulled products, and coal-water slurry.

TABLE VI

MULLED COAL AGING STUDIES

(8-6-91)

MULL ADDITIVE PRODUCT	ADDITIVE (% wt.)	OPEN BIN STORAGE	CLOSED BIN STORAGE	INERTED BIN STORAGE	EXPOSED		CUMULATIVE VOLUME (Gals.)	CUMULATIVE VOLUME (Lbs.)
					TRAY TEST (Skin Effect)			
NPA2	2%	A1			A2		6	45
NPA1	1%	B1	B2	B3			15	112.5
	2%	B4	B5	B6	B7		27	202.5
	3%	B8	B9	B10			36	270

NOTES:

1. All samples will be +/- 3gal. (22.5 lb.)
2. Samples will have a +/- 20 micron particle size and +/- 30% moisture content.
3. Samples will be aged 75 days and monitored for moisture content, oxidation levels and flowability tests.
4. Representative samples will be subjected to freeze/thaw cycles before and after the aging process. The samples will be checked for effects on mull integrity.

Ten samples of selected mull coal formulations have been prepared in the six-quart Sigma Mixer and submitted to the consulting engineers to perform flow and storage testing.

Twelve samples of mulled coal formulations have been prepared to evaluate aging effects of storage methods on handling and transportation characteristics.

Preparations are being made to produce one ton of mulled coal from the wet cake obtained from Virginia Tech. This mulled coal product will be shipped with the skid-mounted test unit to Grand Forks, North Dakota (UNDEERC) for the full system testing of the solid mull and CWF.

END

DATE
FILMED

10 / 21 / 92