Fermi National Accelerator Laboratory

TM-1662

Guidelines for Structural Bolting in Accordance with the AISC Eighth Edition "Manual of Steel Construction"

Jeffrey L. Western and David M. Johns
*Fermi National Accelerator Laboratory
P.O. Box 500
Batavia, Illinois 60510*

May 11, 1990

Operated by Universities Research Association Inc. under contract with the United States Department of Energy

**Guidelines for Structural Bolting
in accordance with AISC Eighth Edition
"Manual of Steel Construction"**

by: Jeffrey L. Western and David M. Johns

1. INTRODUCTION

This paper specifies the usage of structural bolts in terms of their design, selection and application, in accordance with the the American Institute of Steel Construction (AISC) Eighth Edition. " Manual of Steel Construction ".

2. GENERAL GUIDELINES

2.1 All bolts used shall have identification or grade marks as specified by the American Society for Testing and Materials (ASTM), the Society of Automotive Engineers (SAE), or the International Organization for Standardization (ISO), as identified by Industrial Fasteners Institute (IFI) guidelines. See the attached table "Properties of Steel Fasteners" for common fasteners.

2.2 All structural bolting shall conform to the standard specifications as specified in AISC " Manual of Steel Construction ".

2.3 Bolts not having identification shall not be used, unless material verification has been obtained.

2.4 Preventative steps to alleviate corrosion shall be taken when bolts are exposed to corrosive environments.

2.5 All bolts subjected to a fatigue loading shall be designed for such loads.

2.6 Washers and nuts shall be of the same material as the bolting material, unless compatibility of different materials can be demonstrated.

3. STRUCTURAL BOLTING GUIDELINES

3.1 All structural bolting shall conform to the standard specifications as stated in AISC.

3.2 All bolts that are designated for support application shall follow AISC provisions for allowable, minimum, and maximum stresses.

3.3 All bolts subjected to a fatigue loading shall be in accordance with AISC Appendix B Section B3; p. 5-86 thru p. 5-91.

3.4 The minimum end distance from center of bolt hole shall be in accordance with AISC 1.16.5; p. 5-50 thru 5-52.

3.5 The maximum edge distance shall not exceed provisions set in AISC Section 1.16.6; p. 5-52.

3.6 All bolts shall be spaced in accordance with AISC 1.16.4; p. 5-50.

3.7 The maximum size of fastener holes shall be specified by AISC 1.23.4; p. 5-58.

3.8 A325 or A490 bolts, that are to be used within a friction or bearing type connection, shall have a minimum pretensioning force of $.7F_y$ applied to them. See AISC Table 1.23.5; p. 5-59 and Section 1.23.5; p. 5-149.

3.9 Bolts that encounter extraneous loads or stresses such as eccentric shear, prying action, connection bearing stress, or block shear shall be designed under AISC guidelines.

3.10 Bolts that are subjected to **tension** shall follow the following AISC code provisions. See AISC Table 1-B; p. 4-3.

3.10.1 $F_t = P / A_g \leq .33F_u$ for allowable tensile stress in threaded fasteners and:

3.10.2 $F_t = P / A_g \leq .60F_y$ for the allowable tensile capacity on the gross area of the bolt.

3.10.3 Reference Tables / Sections;

- a) AISC Table 1; p. 5-72. Allowable stresses in terms of F_y .
- b) AISC Table 2; p. 5-73. Allowable stresses in terms of F_u .
- c) AISC Section 1.5.2; p. 5-24. Allowable stresses on fasteners.
- d) AISC Table 1-A & 1-B; p. 4-3. Allowable stresses and loads on bolts and threaded fasteners.

3.11 Bolts that are subjected to **shear** with a **bearing-type connection** shall follow AISC guidelines. See AISC Table 1-D; p. 4-5.

3.11.1 $F_v = V / A_g \leq .17 F_u$ where bolts create a bearing-type connection and threads are in the shear plane.

3.11.2 $F_v = V / A_g \leq .22 F_u$ where bolts create a bearing-type connection and threads are excluded from the shear plane.

3.11.3 Reference Table / Sections;

- a) AISC Table 1-D; p. 4-5. Allowable shear.
- b) AISC Section 1.5.2; p. 5-23, 24. Allowable stresses on Fasteners.
- c) AISC Table 2 Appendix A; p. 5-73. Allowable stresses as a function of F_u .

3.12 Bolts that are subjected to **shear** with a **friction-type connection** shall follow AISC "Structural Joints Using ASTM A325 or A490 Bolts" p. 5-209 thru p. 5-229.

3.12.1 Reference Tables / Sections:

- a) AISC Appendix E; p. 5-101 to 5-103. Allowable shear stress in friction-type connections.
- b) AISC Section 1.5.2; p. 5-23, 24. Allowable stress on bolts.
- c) AISC Section 1.23.5; p. 5-59. High strength bolt construction assembly.

3.13 Bolts that are subjected to **combined tension and shear** shall follow AISC Section 1.6.3; p. 5-27, 28. Bolts that are not identified in AISC Table 1.6.3; p. 5-28 shall adhere to the following:

- 3.13.1** $F_t \leq .43F_u - 1.8F_v \leq .33F_u$; for a connection where threads are in the shear plane.
- 3.13.2** $F_t \leq .43F_u - 1.4F_v \leq .33F_u$; for a connection where threads are excluded from the shear plane.

3.14 Nomenclature

- T** - denotes the tension force (lbs or kips) on the bolt.
- V** - denotes the shear force (lbs or kips) on the bolt.
- A_g** - denotes the gross area (in²) of the bolt based on the nominal diameter of the bolt.
- F_u** - denotes the specified minimum tensile stress (psi or ksi) of the type of steel or fastener being used.
- F_y** - denotes the specified minimum yield stress (psi or ksi) of the type of steel being used.
- F_v** - denotes the shear stress (psi or ksi) applied to the bolt.
- F_t** - denotes the tensile axial stress (psi or ksi) applied to the bolt.

4. INTENDED USAGE

This paper is intended to give the engineer an understanding of structural bolting as specified by the AISC code. This paper is not intended to be a substitute for the AISC code, but rather a guide to locate specific requirements in the code.

PROPERTIES OF STEEL FASTENERS

IDENTIFICATION GRADE MARK	SPECIFICATION	FASTENER DESCRIPTION	NOMINAL SIZE RANGE (IN)	MECHANICAL PROPERTIES		
				PROOF LOAD (psi)	YIELD STRENGTH MIN (psi)	TENSILE STRENGTH MIN (psi)
NO GRADE MARK	ASTM A307 Grades A&B	BOLTS, SCREWS, STUDS	1/4 THRU 4			60,000
SAE J429 Grade 5	BOLTS, SCREWS, STUDS	1/4 THRU 1 OVER 1 THRU 1-1/2	85,000 74,000	92,000 81,000	120,000 105,000
	ASTM A449		1/4 THRU 1 OVER 1 THRU 1-1/2 OVER 1-1/2 THRU 3	85,000 74,000 55,000	92,000 81,000 58,000	120,000 105,000 90,000
SAE J429 Grade 5.1	SEMS	NO. 6 THRU 3/8	85,000		120,000
SAE J429 Grade 5.2	BOLTS, SCREWS, STUDS	1/4 THRU 1	85,000	92,000	120,000
ASTM A325 Type 1	HIGH STRENGTH STRUCTURAL BOLTS	1/2 THRU 1 1-1/8 THRU 1-1/2	85,000 74,000	92,000 81,000	120,000 105,000
ASTM A325 Type 2		1/2 THRU 1	85,000	92,000	120,000
ASTM A325 Type 3		1/2 THRU 1 1-1/8 THRU 1-1/2	85,000 74,000	92,000 81,000	120,000 105,000
SAE J429 Grade 7	BOLTS, SCREWS	1/4 THRU 1-1/2	105,000	115,000	133,000
SAE J429 Grade 8	BOLTS, SCREWS, STUDS	1/4 THRU 1-1/2	120,000	130,000	150,000
	ASTM A354 Grade BD
NO GRADE MARK	SAE J429 Grade 8.1	STUDS	1/4 THRU 1-1/2	120,000	130,000	150,000
ASTM A490	HIGH STRENGTH STRUCTURAL BOLTS	1/2 THRU 1-1/2	120,000	130,000	150,000 MIN 170,000 MAX