DOE/PC/89762--T17

DOE/PC/89762--T17

DE93 009698

QUARTERLY

TECHNICAL PROGRESS REPORT

Submitted to U. S. Department of Energy

GRANT TITLE: NQR-NMR Studies of Higher Alcohol
Synthesis Cu-Co Catalysts

GRANT NO: DE-FG22 89PC89762 (GSU: 5-5374)

STARTING DATE: 09-15-89

ENDING DATE: 09-14-91 (Under No Cost Extension
till 6-30-93)

PROJECT DIRECTOR: A. N. Murty
Physics Department

INSTITUTION: Grambling State University
Grambling, Louisiana 71245

RECEIVED

MAR 24 1993

OSTI

*U.S./DOE Patent Clearance is not required prior to the publication of this document.

DISCLAIMER

A. N. Murty
Project Director

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

1-25-93
Date

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

Quarterly Technical Progress Report

(Period Sept. 15th to Dec. 15th, 92)

During this quarter we have investigated a series of Cu/Co catalysts supported on Titanium Dioxide. The primary objective of the study has been to examine and compare the nature and effect of the supports Chromia and Titania (Cr_2O_3 , and TiO_2) on the magnetic character of the Cu-Co-Cr and Cu-Co- TiO_2 catalysts.

EXPERIMENTAL:

Sample preparation: starting with one molar nitrate solutions of the metals, they were mixed in the desired ratio and precipitated as carbonates by reacting with sodium carbonate. The precipitate is thoroughly washed and dried at 80°C and calcined at 350°C for 18 hours. The oxidic composite is then reduced for 18 hours in a following stream of hydrogen. This procedure is followed for the preparation of Cu/Co and Cu/Co/Cr catalysts with different intermetallic ratios. The NMR and Magnetization results of these samples were reported in our earlier reports [1].

In the preparation of the titania supported catalysts, a slightly different procedure had to be adopted. The necessary amount of Titanium dioxide, to produce a 20% loading of the Cu/Co catalyst, is suspended in a 7 pH solution of sodium hydroxide. As in the earlier procedure, the mixed solution of the Cu/Co nitrates is precipitated on the suspension by slow drop wise addition while

continuously stirring the suspension at 80° C. The resulting precipitate is washed, dried, calcined and reduced as in the preparation of Cu/Co/Cr composites.

RESULTS AND DISCUSSION:

The magnetization results for Cu/Co, Cu/Co/Cr, Cu/Co/TiO₂ system are presented in Table I. The magnetization data for the unsupported Cu/Co catalysts is shown in column 2, while columns 3 and 4 show similar data for supported catalysts. Pure cobalt metal has a magnetic moment of 161 emu/g. The measured emu values and the corresponding reduction percentages are given in table I for the various catalysts investigated. The VSM (Vibration Sample Magnetometer) determines S_s, the saturation magnetization, emu per gram of the composite sample. The magnetization values reported are emu per gram of cobalt in the composite. (emu/gram sample * grams of sample/grams of cobalt loaded). As such the data normally reflects the proportion of cobalt metal that is reduced to metallic form (percent reduction). However, if electronic exchanges occur between cobalt and other elements in the system, the magnetic moment itself differs from the assumed value of 161 emu/g Co. Then the emu value observed will be the resultant due to the electronic charge density modifications in Co as well as reduction to metallic state. Our earlier NMR studies [2,3] reveal such electronic structural modifications occur for Cobalt in Cu-Co and Co-TiO₂ systems. The magnetization data in column 3 for Cu-Co-TiO₂ systems unambiguously shows such electron exchanges do occur between cobalt and titania. We find more than 100% reduction, or magnetization

values greater than 161 emu/g, in almost all samples with Cu/Co > 1. The average emu value turns out to be 176 emu/g for beyond the experimental uncertainty, which is found to be less than 5%. It is known that copper promotes the reduction of cobalt and accordingly we find that as copper content increases, the percent reduction also improves. The increase in percent reduction being far more than the loaded amount of cobalt in Cu-Co-TiO₂ system leads us to believe that there occurs an enhancement in the magnetic moment of Co due to charge transfer from Co to Cu and TiO₂. The magnetic moments of the three ferromagnetic metals Fe ((Ar)3d⁶ 4s²), Co ((Ar) 3d⁷ 4s²) and Ni ((Ar) 3d⁸ 4s²) are respectively 218 emu/g, 161 emu/g and 54 emu/g. It seems a decrease in the electronic charge density of Co could lead to a higher magnetic moment of Co. Though the increase in magnetic moment beyond the expected value of 161 emu/g is not apparent in Cu/Co systems the NMR spectra (Fig. I) of cobalt reveal that the hyperfine field at the Co nuclear site increases in catalysts with Cu/Co > 1 causing a shift of the NMR spectrum to higher frequencies. These results lend further support to our view that both in Cu-Co and Cu-Co-TiO₂ catalysts charge transfers occur from Co to Cu and TiO₂. We have not yet been able to observe such shifts in the Cu-Co-TiO₂ catalysts. Perhaps due to the miniscular cobalt content or large frequency shifts in Cu-Co-TiO₂, the NMR lines seem to escape detection in the range 200-230 MHz. Presently, we are in the process of scanning the range 200 to 250 MHz with enhanced sensitivity.

In contrast to these catalysts, the percent reduction is far lower in the Cu-Co-Cr system (table I-Column iv data). It seems a

IT'S GREAT TO BE A LION

"WE SERVE"

proportion of loaded cobalt remains locked in spinel
phases (AB_2O_4) with Cu and Cr. However as copper content
increases in the range $1.5 < Cu/Cr < 5$, there occurs a significant
drop in the percent metal reduced, and again drops for Cu/Cr
above 5. When copper content is very high, it is likely that cobalt might
get into a solid solution of Cu. The NMR Spectra of Co in the Cu-
CO-Cr catalysts (Fig.2) show no significant deviations from the
normal Co spectrum indicating that unlike in the Cu-Co and Cu-Co-
TiO₂ systems cobalt ~~essentially loses~~ ^{Grambling, LA 71245} its identity with no
noticeable charge perturbations. It seems chromia inhibits
intermetallic interactions, while Titania promotes metal support
interactions.

These results are being prepared for presentation at the
67th Annual Louisiana Academy of Science meeting (Abstract enclosed)

REFERENCES

1. Murty A. N., DOE Technical Progress reports 12/15/91 to 3/15/92;
3/15/92 to 6/15/92; Abstracts of University Coal
Research projects 6/92
2. Murty A. N., M. Seamster, A. N. Thorpe, R. T. Obermyer, and
V. U. S. Rao., J. Appl. Phys., 67, 5847 (1990)
3. Washington J., and A. N. Murty., Research Abstracts #116 - NSF
conference on Diversity in the Scientific and
Technological work force Sept. (1992)

TABLE I
MAGNETIZATION EMU/GRAM OF Co LOADED

Cu/Co Ratio	Cu-Co	Cu-Co-TiO ₂ (20% loading on Titania)	Cu-Co-Cr	Inter-metallic Ratio
0.15			(54%) 87	(10/70/20)
0.2	(81%) 131	(93%) 149		
0.3			(10%) 16	(5/15/80)
0.4	(43%) 69	(90%) 145		
0.6	(35%) 57	(71%) 115		
0.7			(3%) 5	(40/55/5)
0.8	(35%) 56	(111%) 179		
1.0		(101%) 163		
1.3			(1.2%) 2	(40/30/30)
1.5	(80%) 129	(120%) 193		
1.7			(30%) 48	(50/30/20)
2.0	(89%) 144			
2.5	(82%) 132	(96%) 155*		
3.0	(80%) 129	(117%) 188		
3.3			(53%) 85	(50/15/35)
3.5	(78%) 125			
4.0	(77%) 124			
4.6			(50%) 97	(70/15/15)
7.0			(7%) 11	(70/10/20)
8.0			(9%) 14	(40/5/55)

(*Sample may need to be prepared again and reexamined)

NMR SPECTRA OF COBALT IN Cu/Co CATALYSTS

NMR SPECTRA OF COBALT IN Cu/Co/Cr CATALYSTS

IG. IIA

LOUISIANA ACADEMY OF SCIENCES

Call for Paper Titles & Abstracts

ANNUAL MEETING - FIRST THURSDAY, FRIDAY AND SATURDAY OF FEBRUARY

READ ALL INSTRUCTIONS BEFORE TYPING. MAIL THIS FORM AND ONE COPY OF THIS FORM TO YOUR SECTION CHAIRPERSON BY NOVEMBER 1st FOR INCLUSION IN THE PROGRAM.

PLEASE NOTE: At least one of the paper's authors MUST be an Academy member.

MURTY, A.N., CHARLES REED, JARVIS WASHINGTON, URSULA DONATTO, AND S.V. NAIDU. Physics Department, Grambling State University, Grambling, LA. - X-Ray powder spectra of Cu-Co-Cr Catalysts*. -

The French Institute IFP has extensively investigated the Catalytic character of Cu-Co-Cr System for the conversion of synthesis gas to methanols/mixed alcohols/hydrocarbons. The method of preparation and the intermetallic ratio is reported to govern the product selectivity. Our studies on the magnetic character revealed similarities between the catalytic and magnetic properties of the system. This study examines the changes in the X-ray powder patterns of the same catalysts. The sample powders were prepared with different inter-metallic ratios by a rigorously controlled Co-precipitation procedure, and the powder spectra indicate significant correlation to the magnetization character.

*Work supported by DOE, NSF and ONR.

1. Compose an abstract that will fit within this area. The abstract must be double-spaced and typed with elite size type. Type clean: use carbon ribbon.
2. FOLLOW THE EXAMPLE ON THE REVERSE SIDE OF THIS SHEET.
3. Author(s): first or single author put last name first, others first name first. Give full first and last names. CAPITALIZE AUTHOR'S NAME(S). If multiple authors underline the name of person presenting the paper. End with a period
4. Follow author(s) immediately with address(es) including zip code. End with a period.
5. Type a dash (-) before title of abstract. Capitalize only first letter of first word in title except for proper nouns, etc. Type a dash (-) at end of title of abstract.
6. Start text on next line without indentation using entire width of box. Type entire abstract within rectangular box and do not type on or beyond bottom of the box. The abstract will appear as you submit it.

"to encourage research in the sciences and disseminate scientific knowledge"

END

DATE
FILMED

4 / 28 / 93