WSRC-RP-91-1227, Rev 0

Keywords: glass, glass durability,
crystallization, Product
Consistency Test (PCT)

DURABILITY OF GLASSES FROM PACIFIC NORTHWEST LABORATORY COMPOSITIONAL VARIABILITY STUDY-II (CVS-II) (U)

WSRC-RP--91-1227

DE92 018536

CAROL M. JANTZEN

Approved by

**E.W. Holtzscheiter, Research Manager
Defense Waste Processing Technology**

Publication Date: May 10, 1992

Authorized Derivative Classifier

**Westinghouse Savannah River Co.
Savannah River Site
Aiken, SC 29808**

**PREPARED FOR THE U.S. DEPARTMENT OF ENERGY UNDER
CONTRACT DE-AC09-89SR18035**

This page intentionally left blank.

ABSTRACT

Pacific Northwest Laboratory (PNL) is developing a borosilicate glass as a solid, stable medium for the disposal of high-level radioactive waste at the Hanford site. They are optimizing the glass forming region and developing process models to be used in the Hanford Waste Vitrification Project (HWVP). Their experimentally-based statistical approach for optimizing the glass composition for HWVP has been designated the Composition Variability Study (CVS).

In Part I of the CVS study PNL tested wide ranges of composition, developed first-order empirical models, and provided input for planning CVS-II. In part II, they are generating glass property data for a number of compositions in order to develop second-order empirical models which will be used to identify the composition region that simultaneously satisfies all quality and processability requirements of HWVP.

Westinghouse Savannah River Company (WSRC) was requested to assist in the CVS-II study by verifying the glass durability properties. The durability of five glasses plus a standard glass was examined using the Product Consistency Test (PCT) developed at WSRC for DWPF and using the monolithic durability test developed by the Materials Characterization Center (MCC-1). The data were examined for internal consistency and analytic bias. The raw analytic data are tabulated. The PCT durability is expressed as grams of glass (Na, B, Li, Si, and K) dissolved per liter of leachate (g/L) and as grams of glass dissolved per square meter (m^2) of glass surface area exposed (g/m^2). The MCC-1 durability is expressed as grams of glass in the leachate per square meter of glass surface area exposed (g/m^2). The total chemical analyses of the glasses and the crystalline phases identified are reported.

This page intentionally left blank.

Table of Contents

	<u>Page</u>
Abstract	3
Introduction	7
Experimental	8
Quality Assurance	9
Results and Discussion	9
PCT Analyses	
Multielement Standard Analyses	9
Standard Glass Analysis	9
CVS-II Glass Analysis.	9
MCC-1 Analyses	
Multielement Standard Analyses	17
Standard Glass Analysis	17
CVS-II Glass Analysis.	17
Target Glass Compositions	17
X-ray Analyses and Scanning Electron Microscopy	21
Conclusions	21
References	23
Appendix I : Task Control Matrix	25
Appendix II: Target and Analyzed Glass Compositions	27

This page intentionally left blank.

DURABILITY OF GLASSES FROM PACIFIC NORTHWEST LABORATORY COMPOSITIONAL VARIABILITY STUDY-II (U)

INTRODUCTION

Waste form producers at the Savannah River Site (SRS), West Valley Nuclear Fuel Services (WVNFS), and Hanford Waste Vittrification Project (HWVP) will immobilize high-level radioactive liquid waste in borosilicate glass. The glass will be poured into stainless steel canisters for eventual disposal in a geologic repository. The Department of Energy has defined a set of requirements for the canistered waste form which must be met in order to assure compatibility with, and acceptance by, the repository. These requirements are the Waste Acceptance Preliminary Specifications (WAPS).¹

The current Waste Acceptance Preliminary Specification (WAPS) 1.3 requires the waste form producers to demonstrate control of the consistency of the final waste form using the Product Consistency Test.²⁻³ The PCT is a crushed glass durability test which is (1) sensitive to glass composition and homogeneity, and (2) may have the potential to be related to repository site-specific release tests. It is a glass dominated production test which rapidly and reliably can be used to test glasses during production, even in the remote environments necessitated by highly radioactive glasses.⁴⁻⁶ Therefore, the PCT has been substituted for the MCC-1 test in the current WAPS 1.3 specification. The acceptance criterion for a production glass has been changed to a glass production criterion: the glass being tested during production must have a release which is better than the 131 Stage 2 glass that was qualified in the DWPF Environmental Assessment (EA).⁷

Pacific Northwest Laboratory (PNL) is generating glass property data for a number of glass compositions in order to develop process/product models which will be used to identify the composition region that simultaneously satisfies all durability and processability requirements for HWVP. This includes PCT testing and adherence to the current version of the WAPS. The Savannah River Laboratory (SRL) of Westinghouse Savannah River Company (WSRC) was requested to assist PNL by verifying the glass durability properties of the HWVP glasses by testing with both the Product Consistency Test (PCT) and the monolithic MCC-1 test.

This study reports the durability of five glasses designed for HWVP by PNL. These five glasses are part of the PNL's Composition Variability Study - Part II. The contract deliverables include the following :

- leachate concentration data file printout
- leachate conversion/calculation printout
- leachate concentration summary sheet and pH values

EXPERIMENTAL

The durability of the five glasses from CVS-II were examined using Version 3.0 of the PCT³ (PCT-GTOP-3-025, Rev.0, see Appendix 1). In the PCT analysis crushed glass of 100-200 mesh is immersed in ASTM Type I water for 7 days at 90°C. The surface area of the glass exposed in 100-200 mesh glass can be calculated using an assumed waste glass density (~2.76 g/cc for average SRS glasses) and by assuming a Gaussian distribution of particle sizes. Since the volume of leachant solution (V) is maintained at 10 mL per gram of glass the ratio of the glass surface area (SA) to the volume (V) of leachant is 19.55 cm⁻¹. PCT leachates were filtered to remove colloids and/or particulates. The leachates were analyzed for pH and the elemental concentration of the glass species of interest.

A standard glass, ARM-1 was used to ascertain if long term bias in the experimental analysis and in the analytical data of these glasses had occurred compared to previous glasses tested at SRS. Triplicate analyses and triplicate glass standards were run simultaneously.

A multi-element solution standard was used to ensure that instrumental drift in the Inductively Coupled Plasma (ICP) Spectroscopy and/or Atomic Absorption (AA) analyses did not significantly bias the short term leachate analyses. Durability tests containing ASTM Type I water but no glass samples were run simultaneously as "blanks." The use of blanks ensure that test vessel preparation was adequate and that the sample leachates can be corrected for elemental variation occurring independently of the glass-solution interactions.

The durability of the five glasses from CVS-II were also examined using PNL's MCC-1P, Rev. 1.0 (PSL-417-LCH, Rev.0, see Appendix 1). In the MCC-1 analysis a monolith of glass is immersed in ASTM Type I water for 28 days at 90°C. The ratio of the specimen surface area (SA) in m² to volume of solution (V) used was in m³ was the recommended 0.1 cm⁻¹. The leachates were analyzed for pH and the elemental concentration of the glass species of interest. A standard glass, ARM-1 was also analyzed. Duplicate analyses and duplicate glass standards were run simultaneously. Durability tests containing ASTM Type I water but no glass samples were run simultaneously as "blanks." The use of blanks ensure that test vessel preparation was adequate and that the sample leachates can be corrected for elemental variation occurring independently of the glass-solution interactions.

The target compositions of the five glasses, in oxide wt%, were provided by G. F. Piepel of PNL. Although not a contract deliverable, portions of the glasses were dissolved and analyzed using DWPF analysis methods⁸ in order to verify the target compositions. A standard glass was dissolved and analyzed simultaneously to ensure that instrumental bias in the analytic equipment could adequately be evaluated. After these analyses were completed, P. Hrma of PNL noted that two of the CVS-II glasses supplied to SRS (CVS-II-16 and 18) had the composition of the PNL Internal Standard glass and may have been erroneously labeled before being shipped.

X-ray diffraction (XRD) and Scanning Electron Microscopy (SEM) analyses coupled with Energy Dispersive Analysis by X-ray (EDAX) were performed on the CVS-II glasses in order to determine the crystallinity and/or homogeneity of the five glasses and the chemical composition of

the crystalline phases. These analyses were also not contract deliverables but were included because of the large impact that crystallinity or inhomogeneity can have on glass durability.

QUALITY ASSURANCE

The PCT Version 3.0 is a Glass Technology Category 1 Procedure requiring experimenter data input and signoff at every step (GTOP-3-025 in The Glass Technology Procedures Manual, DPSTM-88-700-5, L 13-1). All the ovens, balances, and water purification systems used for the PCT and the MCC-1 testing are M&TE Category 1. The SRL Glass Technology Task Control Matrix is given in Appendix I. All tasks were carried out in accordance with OGR-14 and NQA-1.

Analytic Development Services (SRL/ADS) procedures were followed for all chemical, X-ray and SEM/EDAX analyses. All the data for this study are recorded in DPSTN-4507 (E-48203) on pages 126-153 and in WSRC-NB-90-271 on pages 64 to 111.

RESULTS AND DISCUSSION

PCT ANALYSES

Multielement Standard Analysis

During PCT analysis, a multielement solution standard was used to ensure that instrumental drift did not significantly bias the short term analysis of the leachates. The multielement solution standard was run before leachate analysis began and after every 5 leachate samples (Appendix II). Analysis of the solution standard data indicated that there was less than 0.5 ppm bias in the ICP analyses for Na, Li, Al, Fe, and Si and less than 0.6 ppm bias in the Atomic Absorption (AA) analyses for K. The data also indicated that there was about a 2 ppm "low" bias in the Na determinations made by AA compared to the Na determinations by ICP analysis (Table 1).

Standard Glass Analysis

Historical control charting using PNL's Approved Reference Material (ARM-1) as the standard glass as the PCT standard glass did not indicate any significant bias in the elemental releases (in ppm) for all elements since May 1989. All the standard glass elemental releases used in this study fell within one-sigma of the average elemental release for ARM-1 glass since May, 1989. Hence, no long term bias corrections were made to the CVS-II data set.

CVS-II Glass Analysis

The leachate concentrations are reported as normalized elemental concentrations, NC_i , released from the glass in grams of glass per L of leachant and as NL_i , the normalized elemental mass losses released from the glass in grams of glass per L of leachant and per glass surface area exposed. In both cases the leachate concentrations for a given element are normalized by the

Table 1 Multielement Solution Standard Analysis

Element	Concentration of Multielement Standard ug/mL	Run before Samples-1 ug/mL	Run before Samples-2 ug/mL	Run after 5 Samples-1 ug/mL	Run after 5 Samples-2 ug/mL	Run after 10 Samples-1 ug/mL	Run after 10 Samples-2 ug/mL	Run after 15 Samples-1 ug/mL	Run after 15 Samples-2 ug/mL
Na (ICP)	50.00	49.89	49.65	50.01	50.22	50.41	50.19	50.56	50.26
Na (AA)		48.58	48.51	48.35	49.01	48.35	48.20	50.00	47.35
Si	50.00	49.48	49.28	50.06	49.93	50.42	49.78	50.62	50.39
B	120.00	120.59	119.93	120.52	121.00	121.06	120.27	122.43	122.10
K	10.00	9.53	9.49	9.41	9.49	9.30	9.23	9.41	9.39
Li	10.00	9.99	9.96	10.13	10.05	10.08	10.04	10.12	10.07
Al	4.40	4.24	4.25	4.27	4.28	4.37	4.34	4.23	4.20
Fe	4.10	4.01	4.00	4.01	4.04	4.06	4.04	4.05	4.04

Element	Concentration of Multielement Standard ug/mL	Average Bias before Leachate Analysis ug/mL	Average Bias after 5 Leachate Analyses ug/mL	Average Bias after 10 Leachate Analyses ug/mL	Average Bias after 15 Leachate Analyses ug/mL
Na (ICP)	50.00	-0.23	0.11	0.30	0.41
Na (AA)		-1.46	-1.32	-2.73	-1.32
Si	50.00	-0.62	-0.01	0.10	0.51
B	120.00	0.26	0.76	0.66	2.27
K	10.00	-0.49	-0.55	-0.74	-0.60
Li	10.00	-0.03	0.09	0.06	0.09
Al	4.40	-0.16	-0.12	-0.04	-0.18
Fe	4.10	-0.10	-0.07	-0.05	-0.06

ELEMENT	TOTAL AVERAGE BIAS ug/mL
Na (ICP)	0.15
Na (AA)	-1.71
Si	0.00
B	0.99
K	-0.59
Li	0.05
Al	-0.13
Fe	-0.07

weight fraction of that element in the glass. The normalized mass loss, NL_i , is a function of (1) the mass fraction of that element in the glass, (2) the exposed surface area of the glass, and (3) the leachate volume, as given below:

$$NL_i = \frac{C_i}{F_i \cdot (SA/V)} \quad (1)$$

where

$$\begin{aligned} NL_i &= \text{normalized elemental mass loss (g}_{\text{glass}}/\text{m}^2) \\ C_i &= \text{mass of element "i" in the solution corrected for the average mass} \\ &\quad \text{of element "i" in the blanks (g}_i/\text{m}^3) \\ F_i &= \text{fraction of element "i" in the glass (g}_i/\text{g}_{\text{glass}}) \\ SA &= \text{specimen surface area (m}^2) \\ V &= \text{solution volume (m}^3) \end{aligned}$$

Equation 1 provides leachate concentrations in grams of glass per m^2 of glass surface area exposed. Since the SA/V term in Equation 1 is constant during PCT analyses the alternative expression given below is used preferentially in this study.

$$NC_i = \frac{C_i}{F_i} \quad (2)$$

The units of NC_i are, therefore, expressed as grams of glass per L of leachant. The leachate pH and leachate concentrations, expressed as ppm, NL_i , and NC_i , are given in Table 2.

Boron and lithium releases from glass are considered to be the most accurate indicators of glass durability since these elements are leached from glass more rapidly than other elements. In addition, boron is considered to be the best indicator of glass durability because boron does not saturate in the leachate and does not participate in precipitation reactions caused by solution supersaturation. Therefore, the elemental releases measured in the leachates were checked for internal consistency by plotting the releases in ppm for Li, Si, Na, and K against the normalized releases of B (Figure 1). The plots of Li and K versus B were consistent, e.g. if a given glass released a great deal of B it, likewise, released a great deal of Li or K. The trends for Si versus B and Na versus B are not as consistent because the data for CVS 2-7 appears suspect. Figure 1 also demonstrates the consistently low bias in the Na analyses by AA over the Na analyses by ICP.

The normalized releases were calculated using the analyzed glass compositions given in Table 3 and Appendix II. The normalized releases were calculated in grams of glass (grams of B, Li, Si, Na, and K) leached per liter of leachate (g/L) as given in Equations 1 and 2. The calculation of NL_i , NC_i , $\log NL_i$, and $\log NC_i$ are given in Tables 4 and 5.

Table 2. PCT Leachate Concentrations for CVS-II Glasses

Sample	ADS SAMPLE #	LEACHATE pH @ 25°C	B IN LEACHATE (PPM)	SI IN LEACHATE (PPM)	K IN LEACHATE (PPM)	Na IN LEACHATE BY ICP (PPM)	Na IN LEACHATE BY AA (PPM)	LI IN LEACHATE (PPM)
CVS2-5-7-1	200059596	9.57	30.210	43.257	<0.1	38.780	38.592	6.363
CVS2-5-7-2	200059597	9.57	29.935	43.362	<0.1	38.882	38.261	6.352
CVS2-5-7-3	200059598	9.58	30.915	43.998	<0.1	39.695	37.254	6.521
AVERAGE		9.57	30.353	43.539	<0.1	39.052	38.702	6.412
% STD DEV		0.00	0.41	0.33		0.46	0.41	0.08
CVS2-7-7-1	200059588	9.77	78.042	75.771	<0.1	39.446	39.572	37.574
CVS2-7-7-2	200059589	9.78	88.699	73.008	<0.1	34.377	34.274	33.239
CVS2-7-7-3	200059590	9.78	72.769	73.220	<0.1	36.582	35.433	35.001
AVERAGE		9.78	73.137	74.000	<0.1	36.802	36.426	35.271
% STD DEV		0.00	3.66	1.26		2.08	2.27	1.78
CVS2-16-7-1	200059591	10.24	69.867	157.380	1.610	141.130	141.030	30.932
CVS2-16-7-2	200059592	10.24	71.277	158.200	1.524	143.710	137.406	31.562
CVS2-16-7-3	200059593	10.24	70.533	158.540	1.599	143.150	142.877	31.404
AVERAGE		10.24	70.559	158.040	1.578	142.663	140.371	31.299
% STD DEV		0.00	0.58	0.49	0.04	1.11	2.20	0.27
CVS2-17-7-1	200059583	10.17	28.473	64.188	0.245	48.543	45.698	14.082
CVS2-17-7-2	200059584	10.17	27.338	62.504	0.256	46.700	45.864	13.538
CVS2-17-7-3	200059585	10.16	27.739	63.338	0.235	47.289	46.867	13.658
AVERAGE		10.17	27.850	63.337	0.245	47.504	46.140	13.753
% STD DEV		0.00	0.47	0.88	0.01	0.77	0.61	0.22
CVS-18-7-1	200059580	10.32	100.160	187.900	1.716	197.170	190.785	42.552
CVS-18-7-2	200059581	10.32	97.759	187.890	1.578	192.600	186.502	41.805
CVS-18-7-3	200059582	10.32	100.340	189.370	1.663	196.880	188.808	42.501
AVERAGE		10.32	99.420	188.387	1.652	195.543	188.698	42.286
% STD DEV		0.00	1.18	0.70	0.06	2.09	1.75	0.34
ARM-1-7-1	200059609	10.42	18.906	64.859	0.213	39.239	37.254	14.963
ARM-1-7-2	200059600	10.42	19.501	64.226	0.171	39.855	39.407	15.102
ARM-1-7-3	200059601	10.42	18.128	62.053	0.213	37.751	36.095	14.302
AVERAGE		10.42	18.845	63.713	0.199	38.948	37.585	14.789
% STD DEV		0.00	0.56	1.20	0.02	0.88	1.37	0.35
BLANK-7-1	200059604	5.92	<0.004	0.131	0.362	<0.010	0.070	<0.001
BLANK-7-2	200059605	5.83	<0.004	0.411	<0.1	<0.010	0.060	<0.001
AVERAGE		5.88	<0.004	0.271	0.181	<0.010	0.065	<0.001
% STD DEV		0.05		0.14	0.00		0.01	

Notebook WSRC-NB-90-271

Figure 1. Internal Consistency of PCT and MCC-1 Leachate Data.

Table 3. Elemental Concentrations of Analyzed CVS-II Glasses (see Appendix II)

Sample	B wt% in glass	Si wt% in glass	K wt% in glass	Na wt% in glass	Li wt% in glass
CVS2-5-28-1	4.554	21.019		7.770	0.891
CVS2-5-28-2	4.554	21.019		7.770	0.891
AVERAGE	4.554	21.019		7.770	0.891
CVS2-7-28-1	4.713	21.510		5.875	2.548
CVS2-7-28-2	4.713	21.510		5.875	2.548
AVERAGE	4.713	21.510		5.875	2.548
CVS2-16-28-	3.332	22.292	0.250	8.185	1.580
CVS2-16-28-	3.332	22.292	0.250	8.185	1.580
AVERAGE	3.332	22.292	0.250	8.185	1.580
CVS2-17-28-	3.188	20.067	0.024	7.245	1.742
CVS2-17-28-	3.188	20.067	0.024	7.245	1.742
AVERAGE	3.188	20.067	0.024	7.245	1.742
CVS-18-28-1	2.910	22.504	0.230	7.980	1.568
CVS-18-28-2	2.910	22.504	0.230	7.980	1.568
AVERAGE	2.910	22.504	0.230	7.980	1.568
ARM-1-28-1	3.665	21.547		7.295	2.360
ARM-1-28-2	3.665	21.547		7.295	2.360
AVERAGE	3.665	21.547		7.295	2.360

Table 4. PCT Normalized Releases for CVS-II Glasses (Corrected for Blank Analyses)

Sample	ADS SAMPLE #	LEACHATE pH	NLI(B) (g/L)	NLI(Si) (g/L)	NLI(K) (g/L)	NLI(Na)ICP (g/L)	NLI(Na)AA (g/L)	NLI(L)JAA (g/L)	NLI(B) (g/m2)	NLI(Si) (g/m2)	NLI(K) (g/m2)	NLI(Na)ICP (g/m2)	NLI(Na)AA (g/m2)	NLI(L)JAA (g/m2)
CVS2-5-7-1	200059596	9.57	0.663	0.205		0.498	0.470	0.715	33.932	10.461	0.000	25.529	24.046	36.549
CVS2-5-7-2	200059597	9.57	0.657	0.205		0.498	0.466	0.713	33.623	10.486	0.000	25.465	23.828	36.486
CVS2-5-7-3	200059598	9.56	0.679	0.208		0.511	0.479	0.732	34.724	10.641	0.000	26.132	24.482	37.457
AVERAGE		9.57	0.667	0.206		0.503	0.472	0.720	34.093	10.530	0.000	25.709	24.119	36.831
% STD DEV		0.00												
CVS2-7-7-1	200059588	9.77	1.656	0.351		0.671	0.672	1.476	84.700	17.954	0.000	34.344	34.397	75.489
CVS2-7-7-2	200059589	9.76	1.456	0.336		0.585	0.582	1.306	74.452	17.297	0.000	29.930	29.784	66.779
CVS2-7-7-3	200059590	9.78	1.544	0.339		0.623	0.602	1.375	78.977	17.346	0.000	31.850	30.793	70.319
AVERAGE		9.76	1.552	0.343		0.626	0.619	1.365	79.376	17.533	0.000	32.042	31.658	70.863
% STD DEV		0.00												
CVS2-16-7-1	200059591	10.24	2.097	0.705	0.572	1.724	1.722	1.958	107.256	36.050	29.236	88.197	88.094	100.139
CVS2-16-7-2	200059592	10.24	2.139	0.708	0.537	1.756	1.678	1.998	109.420	36.238	27.478	89.809	85.829	102.179
CVS2-16-7-3	200059593	10.24	2.117	0.710	0.567	1.749	1.742	1.988	108.278	36.316	29.013	89.459	89.123	101.667
AVERAGE		10.24	2.116	0.708	0.559	1.743	1.714	1.981	108.318	36.201	28.576	89.155	87.682	101.328
% STD DEV		0.00												
CVS2-17-7-1	200059583	10.17	0.893	0.318	0.272	0.670	0.630	0.807	45.684	16.287	13.930	34.272	32.216	41.303
CVS2-17-7-2	200059584	10.17	0.858	0.310	0.319	0.645	0.632	0.777	43.863	15.863	16.303	32.971	32.335	36.763
CVS2-17-7-3	200059585	10.16	0.870	0.314	0.228	0.652	0.646	0.784	41.507	16.076	11.645	33.373	33.036	40.116
AVERAGE		10.17	0.874	0.314	0.273	0.656	0.636	0.790	44.685	16.075	13.956	33.539	32.529	40.394
% STD DEV		0.00												
CVS-18-7-1	200059580	10.32	3.442	0.834	0.869	2.471	2.390	2.715	176.058	42.647	34.212	126.384	122.249	138.856
CVS-18-7-2	200059581	10.32	3.358	0.834	0.809	2.414	2.336	2.667	171.837	42.645	31.136	123.454	119.504	136.419
CVS-18-7-3	200059582	10.32	3.448	0.840	0.846	2.467	2.365	2.711	176.374	42.982	33.031	126.185	120.982	138.690
AVERAGE		10.32	3.416	0.836	0.841	2.450	2.364	2.698	174.756	42.758	32.783	125.341	120.912	137.988
% STD DEV		0.00												
ARM-1-7-1	200059599	10.42	0.516	0.300		0.539	0.510	0.834	26.386	15.333	0.000	27.551	26.112	32.431
ARM-1-7-2	200059600	10.42	0.532	0.297		0.547	0.540	0.840	27.217	15.182	0.000	27.984	27.624	32.732
ARM-1-7-3	200059601	10.42	0.495	0.287		0.518	0.495	0.806	25.301	14.667	0.000	26.506	25.298	30.998
AVERAGE		10.42	0.514	0.294		0.535	0.515	0.827	26.301	15.061	0.000	27.347	26.345	32.054
% STD DEV		0.00												

Table 5. Logarithm of the PCT Normalized Releases for CVS-II Glasses (Corrected for Blank Analyses)

Sample	ADS SAMPLE #	LEACHATE pH	log NL(B) (g/L)	log NL(Si) (g/L)	log NL(K)og NL(Na)ICPog NL(Na)AA (g/L)	log NL(Li) (g/L)	log NL(B) (g/m2)	log NL(Si) (g/m2)	log NL(K)og NL(Na)ICPog NL(Na)AA (g/m2)	log NL(Li) (g/m2)
CVS2-5-7-1	200059596	9.57	-0.178	-0.689	-0.302	-0.328	1.531	1.020	1.407	1.381
CVS2-5-7-2	200059597	9.57	-0.182	-0.688	-0.303	-0.332	1.527	1.021	1.406	1.377
CVS2-5-7-3	200059598	9.56	-0.168	-0.682	-0.292	-0.320	1.541	1.027	1.417	1.389
AVERAGE		9.57	-0.176	-0.686	-0.299	-0.326	1.533	1.022	1.410	1.382
%STD DEV		0.00								1.566
CVS2-7-7-1	200059588	9.77	0.219	-0.455	-0.173	-0.172	1.928	1.254	1.536	1.537
CVS2-7-7-2	200059589	9.76	0.163	-0.471	-0.233	-0.235	1.872	1.238	1.476	1.474
CVS2-7-7-3	200059590	9.78	0.189	-0.470	-0.206	-0.220	1.898	1.239	1.503	1.488
AVERAGE		9.78	0.191	-0.465	-0.203	-0.208	1.900	1.244	1.506	1.500
%STD DEV		0.00								1.850
CVS2-16-7-1	200059591	10.24	0.322	-0.152	-0.243	0.236	2.030	1.557	1.466	1.945
CVS2-16-7-2	200059592	10.24	0.330	-0.150	-0.270	0.244	2.039	1.559	1.439	1.934
CVS2-16-7-3	200059593	10.24	0.326	-0.149	-0.248	0.241	2.035	1.560	1.463	1.950
AVERAGE		10.24	0.326	-0.150	-0.253	0.241	2.035	1.559	1.456	1.943
%STD DEV		0.00								2.006
CVS2-17-7-1	200059583	10.17	-0.049	-0.497	-0.565	-0.174	1.660	1.212	1.144	1.535
CVS2-17-7-2	200059584	10.17	-0.067	-0.508	-0.497	-0.199	1.642	1.200	1.212	1.518
CVS2-17-7-3	200059585	10.16	-0.060	-0.503	-0.643	-0.190	1.649	1.208	1.066	1.523
AVERAGE		10.17	-0.059	-0.503	-0.564	-0.197	1.650	1.206	1.145	1.528
%STD DEV		0.00								1.606
CVS-18-7-1	200059580	10.32	0.537	-0.079	-0.175	0.393	2.246	1.830	1.534	2.102
CVS-18-7-2	200059581	10.32	0.526	-0.078	-0.216	0.383	2.235	1.830	1.493	2.092
CVS-18-7-3	200059582	10.32	0.538	-0.078	-0.190	0.392	2.246	1.833	1.519	2.101
AVERAGE		10.32	0.534	-0.078	-0.193	0.389	2.242	1.831	1.516	2.098
%STD DEV		0.00								2.140
ARM-1-7-1	200059599	10.42	-0.297	-0.523	-0.269	-0.282	1.421	1.186	1.440	1.417
ARM-1-7-2	200059600	10.42	-0.274	-0.528	-0.262	-0.268	1.435	1.181	1.447	1.441
ARM-1-7-3	200059601	10.42	-0.306	-0.543	-0.286	-0.306	1.403	1.166	1.423	1.403
AVERAGE		10.42	-0.289	-0.531	-0.272	-0.289	1.420	1.178	1.437	1.421
%STD DEV		0.00								1.506

MCC-1 ANALYSES

Multielement Standard Analysis

The MCC-1 procedure provided by PNL does not require the use of a multielement standard.

Standard Glass Analysis

The MCC-1 procedure provided by PNL does not require the use of a standard glass. Although PNL's Approved Reference Material (ARM-1) was leached as a standard glass along with the CVS-II glasses, there was no historical data base for MCC-1 testing with this glass. No statement could be made about the analytic bias. The standard glass analytic results are given in Table 6.

CVS-II Glass Analysis

The raw data used to convert the leachate concentrations to NL_i is given in Table 6. The elemental releases measured in the leachates were checked for internal consistency by simultaneously plotting the releases in ppm for Li, Si, Na, and K against the normalized releases of B along with the data from the PCT analysis (Figure 1). The MCC-1 data also shows the consistently low bias in the Na analyses by AA compared to the Na analyses by ICP.

The normalized releases were calculated using the analyzed glass compositions in Table 3 and Appendix II. The normalized releases, NL_i and $\log NL_i$, were calculated in grams B, Li, Si, Na, and K leached per glass surface area exposed (g/m^2) as given in Equation 1 (Tables 7 and 8).

TARGET GLASS COMPOSITIONS

The CVS-II glasses were analyzed chemically (Appendix II) in duplicate along with a standard SRS glass from the Waste Compliance Plan, e.g. WCP Purex glass. The analysis included a redox measurement. The analysis did not include analysis of Ce, Nd, and Y. Therefore, the target values for these elements were used and are indicated in bold in the oxide wt% columns in Appendix II.

Comparison of the analyzed compositions with the target compositions is good except for the presence of minor constituents which were found during chemical analysis. This included MnO , ZnO , TiO_2 , and K_2O as well as FeO indicated by the redox state measured. The analytic values for Al, Si, and B were biased low compared to the standard Purex glass analysis. All three of these analyses are measured from a Na_2O_2 dissolution rather than the microwave dissolution used for the remainder of the analysis. Once a 7% bias correction was applied to the 3 elements from the Na_2O_2 dissolution, the analyzed and target values were in excellent agreement (Appendix II).

Table 6. MCC-1 Leachate Concentration Data for CVS-II Glasses

Sample	ADS SAMPLE #	LEACHATE pH @ 25°C	B IN LEACHATE (PPM)	SI IN LEACHATE (PPM)	K IN LEACHATE (PPM)	Na IN LEACHATE BY ICP (PPM)	Na IN LEACHATE BY AA (PPM)	LI IN LEACHATE (PPM)
CVS2-5-28-1	200062210	8.98	4.965	18.008	<0.1	7.668	7.480	0.921
CVS2-5-28-2	200062211	9.01	5.081	18.358	<0.1	7.578	7.593	0.933
AVERAGE		9.00	5.023	18.183	<0.1	7.623	7.535	0.927
% STD DEV		0.01	0.08	0.17		0.05	0.06	0.01
CVS2-7-28-1	200062212	9.90	2.581	19.940	<0.1	15.286	16.200	1.148
CVS2-7-28-2	200062213	9.90	2.585	19.586	<0.1	15.012	15.800	1.128
AVERAGE		9.90	2.583	19.763	<0.1	15.149	15.900	1.137
% STD DEV		0.00	0.00	0.18		0.14	0.30	0.01
CVS2-16-28-1	200062214	9.59	5.343	30.854	<0.1	13.827	14.400	2.598
CVS2-16-28-2	200062215	9.50	5.571	32.059	<0.1	14.513	15.210	2.713
AVERAGE		9.55	5.457	31.507	<0.1	14.170	14.805	2.656
% STD DEV		0.05	0.11	0.55		0.34	0.41	0.06
CVS2-17-28-1	200062216	9.46	4.809	20.333	<0.1	9.812	10.370	2.252
CVS2-17-28-2	200062217	9.42	4.799	20.819	<0.1	9.770	10.460	2.252
AVERAGE		9.44	4.804	20.475	<0.1	9.791	10.415	2.252
% STD DEV		0.02	0.01	0.14		0.02	0.05	0.00
CVS-18-28-1	200062218	9.59	5.002	29.266	0.143	13.064	13.930	2.433
CVS-18-28-2	200062219	9.59	5.106	29.864	0.208	13.244	14.180	2.488
AVERAGE		9.59	5.051	29.565	0.176	13.154	14.055	2.461
% STD DEV		0.00	0.05	0.30	0.03	0.09	0.13	0.03
ARM-1-28-1	200062220	9.55	4.838	22.618	<0.1	9.597	10.460	2.871
ARM-1-28-2	200062221	9.50	4.847	22.189	<0.1	9.509	9.720	2.900
AVERAGE		9.53	4.843	22.404	<0.1	9.553	10.090	2.886
% STD DEV		0.02	0.00	0.21		0.04	0.37	0.01
BLANK-28-1	200062222	6.86	0.100	0.169	<0.1	0.166	0.106	<0.01
BLANK-28-2	200062223	6.92	0.020	0.230	<0.1	0.147	0.082	0.007
AVERAGE		6.89	0.06	0.20		0.16	0.09	0.00
% STD DEV		0.03	0.04	0.63		0.01	0.01	

Notebook DPSTN-4507 (E48203)

Table 7. MCC-1 Normalized Releases for CVS-II Glasses (Corrected for Blank Analyses)

Sample	ADS SAMPLE #	LEACHATE pH	NLI(B) (g/m ²)	NLI(Si) (g/m ²)	NLI(K) (g/m ²)	NLI(Na)ICP (g/m ²)	NLI(Na)AA (g/m ²)	NLI(Li)AA (g/m ²)
CVS2-5-28-1	200062210	9.98	10.771	8.473		9.667	9.508	10.303
CVS2-5-28-2	200062211	9.01	11.025	8.639		9.551	9.647	10.438
AVERAGE		9.00	10.898	8.556		9.609	9.577	10.371
CVS2-7-28-1	200062212	9.90	5.349	9.178		25.752	27.414	4.495
CVS2-7-28-2	200062213	9.90	5.358	9.013		25.286	28.393	4.409
AVERAGE		9.90	5.353	9.095		25.519	26.904	4.452
CVS2-16-28-1	200062214	9.59	15.855	13.796		16.702	17.478	16.421
CVS2-16-28-2	200062215	9.50	16.540	14.292		17.540	18.468	17.149
AVERAGE		9.55	16.197	14.044		17.121	17.973	16.785
CVS2-17-28-1	200062216	9.46	14.896	10.033		13.327	14.184	12.911
CVS2-17-28-2	200062217	9.42	14.865	10.174		13.269	14.308	12.911
AVERAGE		9.44	14.881	10.104		13.298	14.246	12.911
CVS-18-28-1	200062218	9.59	16.983	12.916	6.231	16.175	17.338	15.499
CVS-18-28-2	200062219	9.59	17.320	13.182	9.063	16.400	17.652	15.850
AVERAGE		9.59	17.151	13.049	7.647	16.288	17.495	15.675
ARM-1-28-1	200062220	9.55	13.037	10.404		12.959	14.229	12.150
ARM-1-28-2	200062221	9.50	13.061	10.205		12.838	13.213	12.273
AVERAGE		9.53	13.049	10.305		12.898	13.721	12.212

Table 8. Logarithm of the MCC-1 Normalized Releases for CVS-II Glasses (Corrected for Blank Analyses)

Sample	ADS SAMPLE #	LEACHATE pH	log NLI(B) (g/m ²)	log NLI(Si) (g/m ²)	log NLI(K) (g/m ²)	log NLI(Na)ICP (g/m ²)	log NLI(Na)AA (g/m ²)	log NLI(Li) (g/m ²)
CVS2-5-28-1	200062210	8.98	1.032	0.928		0.985	0.978	1.013
CVS2-5-28-2	200062211	9.01	1.042	0.936		0.980	0.984	1.019
AVERAGE		9.00	1.037	0.932		0.983	0.981	1.016
CVS2-7-28-1	200062212	9.90	0.728	0.963		1.411	1.438	0.853
CVS2-7-28-2	200062213	9.90	0.729	0.955		1.403	1.421	0.844
AVERAGE		9.90	0.729	0.959		1.407	1.430	0.849
CVS2-16-28-1	200062214	9.59	1.200	1.140		1.223	1.242	1.215
CVS2-16-28-2	200062215	9.50	1.219	1.155		1.244	1.268	1.234
AVERAGE		9.55	1.209	1.147		1.234	1.255	1.225
CVS2-17-28-1	200062216	9.46	1.173	1.001		1.125	1.152	1.111
CVS2-17-28-2	200062217	9.42	1.172	1.007		1.123	1.156	1.111
AVERAGE		9.44	1.173	1.004		1.124	1.154	1.111
CVS-18-28-1	200062218	9.59	1.230	1.111	0.795	1.209	1.239	1.190
CVS-18-28-2	200062219	9.59	1.239	1.120	0.957	1.215	1.247	1.200
AVERAGE		9.59	1.234	1.116	0.883	1.212	1.243	1.195
ARM-1-28-1	200062220	9.55	1.115	1.017		1.113	1.153	1.085
ARM-1-28-2	200062221	9.50	1.116	1.009		1.108	1.121	1.089
AVERAGE		9.53	1.116	1.013		1.111	1.137	1.087

Notebook DPSTN-4507 (E48203)

X-RAY ANALYSIS AND SCANNING ELECTRON MICROSCOPY

Ruthenium dioxide was identified in all the CVS-II glasses by X-ray diffraction analysis (Table 9). In CVS-16 and CVS-17 small amounts of irregularly distributed Cu-Ni alloy were detected during SEM/EDAX analysis. In CVS-5 and CVS-17 a Ca-Zr-Al-Fe silicate containing La and Nd or two phases (a Ca-Zr-Al-Fe silicate and a rare earth oxide) were detected. In CVS-5 there was sufficient amounts of this phase to yield a strong x-ray diffraction pattern. However, positive phase identification was not possible from the complex pattern. In CVS-18 a mixed chloride phase, (Na,K)Cl, was observed.

During SEM analysis it was noted that all of the surfaces of a crushed grain did not have the same surface texture. Many grains had one dull flat textured surface indicating that before grinding the samples for the PCT, the original glass specimen was not free of melt cast surfaces. Textural differences in glass surfaces can impart variation to the PCT response to a glass composition.

CONCLUSIONS

The PCT leachate data of the CVS-II glasses appears to be internally consistent except for the Si and Na analyses of the CVS2-7 glass. No long term or short term instrumental analytic bias was observed. The chemical analysis of the target compositions indicate that they are approximately correct. RuO₂ was detected in all of the glasses by x-ray diffraction. Small amounts of other phases were detected during the scanning electron microscopy analysis in four out of the five glasses examined. All of the glasses exhibited irregular surface texture indicating that the original samples contained melt cast surfaces as well as fracture surfaces.

Table 9. Crystalline Phases Identified in CVS-II Glasses

<u>Glass</u>	<u>Phases Identified by XRD</u>	<u>Phases Identified by SEM</u>
CVS-5	RuO_2 + Unknown	RhO_2 + Ca-Zr-Al-Fe silicate + RE oxide
CVS-7	RuO_2	None
CVS-16	RuO_2	RuO_2 + Cu-Ni alloy
CVS-17	RuO_2	Cu-Ni alloy + Ca-Zr-Al-Fe silicate + RE oxide
CVS-18	RuO_2	RuO_2 + (Na,K)Cl

REFERENCES

1. **Waste Acceptance Preliminary Specifications for the Defense Waste Processing Facility High-Level Waste Form**, U. S. Department of Energy, Office of Civilian Radioactive Waste Management, USDOE Document OGR/B-8, Washington, DC (1988).
2. C. M. Jantzen and N. E. Bibler, **"Product Consistency Test (PCT) and Test Protocol,"** USDOE Report DPST-87-575, Savannah River Laboratory, Aiken, SC (1987).
3. C. M. Jantzen and N. E. Bibler, **"Nuclear Waste Product Consistency Test (PCT) -Version 3.0,"** WSRC-TR-90-539, Rev. 1 (November, 1990).
4. C. M. Jantzen and N. E. Bibler, **"Product Consistency Test (PCT) and Test Protocol,"** USDOE Report DPST-87-575, Savannah River Laboratory, Aiken, SC (1987).
5. G. F. Piepel, T. E. Jones, D. L. Eggett, G. B. Mellinger, **"Product Consistency Test Round Robin Conducted by the Materials Characterization Center - Summary Report,"** USDOE Report PNL-6967, Materials Characterization Center, Battelle Pacific Northwest Laboratories, Richland, WA (1989).
6. N. E. Bibler and J. K. Bates, **"Product Consistency Leach Tests of Savannah River Site Radioactive Waste Glasses,"** Scientific Basis for Nuclear Waste Management, XIII, V. M. Oversby and P. W. Brown (Eds.), Materials Research Society, Pittsburgh, PA, 327-338 (1990).
7. U.S. Department of Energy, **"Environmental Assessment Waste Form Selection for SRP High-Level Waste,"** U.S. DOE Report DOE-EA-0179 (July, 1982).
8. C.J. Coleman, **"DWPF Analytical Procedures,"** DPST-88-270 (March 21, 1988).

This page intentionally left blank

Appendix I
Savannah River Laboratory Glass Technology Task Control Matrix

**SAVANNAH RIVER LABORATORY
GLASS TECHNOLOGY TASK CONTROL MATRIX**

KEY ELEMENTS	OTHER	SOFTWARE, Section 20 of 10	OPERATING STATUS - GT-QA-14-1	HANDLING / STORAGE - GT-QA-13-1	M & TE - GT-QA-12-1	TEST CONTROL - GT-QA-11-1	INSPECTION - GT-QA-10-1	SPECIAL PROCESSES - GT-QA-9-1	ITEMS - GT-QA-8-1	PROCEDURES - GT-QA-5-1	PROCUREMENTS - GT-QA-4-1 & 4-2	DESIGN - GT-QA-3-1, 3-2, 3-3, 3-4	QUALIFICATION OF DATA - GT-QA-2-10	PERSONNEL TRAINING - GT-QA-2-9	LAB NOTEBOOKS - GT-QA-2-7	ANALYTICAL SUPPORT - GT-QA-2-6	PEER REVIEWS - GT-QA-2-4
PCT-GTOP-3-025, REV. 0			X	X	X					X	X			X	X	X	
PNL-MCC-1P, TEST, REV. 1.0			X	X	X					X	X			X	X	X	

All activities are subject to the requirements of GT-QA-1-1, 1-2, 6-1, 6-2, 15-1, 16-1, 17-1, 17-2, & 17-3.

APPROVED BY: *Patricia J. ...* 4/14/91
QUALITY SECTION/Date

W. H. ... 4/29/91
MANAGER, DWPT/Date

Carol M. Jantzen 4/16/91
TASK LEADER/ Date

Appendix II
Comparison of Target and Analyzed Glass Composition for CVS-II Glasses

GLASS ID = CV52-5A

(SPREADSHEET REVISION 5.0, OCTOBER 23, 1990)

ELEMENT	GRAV	OXIDE	PNL NOMINAL	M.W.	MOLE	NORM OXIDE	COMPONENT	FREE ENERGY	KCAL/KG
WT%	FACTOR	WT%	OXIDE WT%		FRACTION	MOLE %	FREE ENERGY	HYDRATION	
Al2O3*	3.9370	1.8895	7.9597	101.9600	0.0781	5.3473	3.0400	0.1626	2.3732
CaO	2.3890	1.3992	3.3427	56.0794	0.0596	4.0828	-16.1160	-0.6580	-9.6062
Fe2O3	3.0370	1.4297	4.1195	159.6922	0.0258	1.7670	15.5000	0.2739	3.9985
FeO	SEE FEOX	1.2965	0.2002	71.8464	0.0028	0.1908	-14.6090	-0.0279	-0.4070
MgO	0.0010	1.6583	0.0017	40.3114	0.0000	0.0028	-13.8880	-0.0004	-0.0057
MnO	0.1330	1.2912	0.1717	70.9374	0.0724	0.1658	-14.8710	-0.0247	-0.3600
Na2O (NA)	7.7700	1.3480	10.4740	61.9790	0.1690	11.5754	-28.8150	-3.3354	-48.6951
Li2O	0.9060	2.1525	1.9502	29.8774	0.0653	4.4709	-22.7400	-1.0167	-14.8429
NiO	0.6540	1.2726	0.8323	74.7094	0.0111	0.7631	-14.3470	-0.1095	-1.5983
SiO2*	20.8300	2.1393	47.6809	60.0848	0.7936	54.3562	5.5900	1.8062	26.3696
Cr2O3	0.1760	1.4616	0.2572	151.9974	0.0017	0.1159	37.3600	0.0433	0.6323
B2O3*	4.5240	3.2201	15.5875	69.6204	0.2239	15.3359	-9.9300	-1.5229	-22.2325
UO2	NA	1.1344		270.0388	0.0000	0.0000	-6.8000	0.0000	0.0000
ThO2	NA	1.1379		264.0400	0.0000	0.0000	-2.5330	0.0000	0.0000
SrO	0.1100	1.1826	0.1301	103.6194	0.0013	0.0860	-24.4000	-0.0210	-0.3063
ZrO2	0.6430	1.3508	0.8686	123.2188	0.0070	0.4828	45.1000	0.2178	3.1791
TiO2	BDL	1.6680		79.8988	0.0000	0.0000	15.9900	0.0000	0.0000
K2O (AA)	BDL	1.2046		94.2034	0.0000	0.0000	-41.7350	0.0000	0.0000
Cs2O	NA	1.0602	0.2150	281.8094	0.0008	0.0523	-46.8200	-0.0245	-0.3572
Sr2O3	NA	1.1970		201.4982	0.0000	0.0000	0.0000	0.0000	0.0000
P2O5	0.0610	2.2910	0.1398	141.9370	0.0010	0.0674	-53.6200	-0.0362	-0.5279
Na2O3	NA	1.1660	1.7600	336.4782	0.0052	0.3583	-28.3200	-0.1015	-1.4813
La2O3	0.5400	1.1728	0.8950	325.8100	0.0019	0.1331	-31.1400	0.0415	-0.6353
Y2O3	NA	1.2699	0.0720	225.8082	0.0003	0.0218	-12.9500	-0.0028	-0.0413
BaO	0.1090	1.1165	0.1430	153.3394	0.0008	0.0544	-30.5700	-0.0166	-0.2426
PbO	BDL	1.0772		223.1900	0.0000	0.0000	-8.8100	0.0000	0.0000
CaO2	NA	1.2284	0.2150	172.1200	0.0012	0.0856	11.3450	0.0097	0.1417
MoO3	0.258	1.5003	0.4021	143.9382	0.0028	0.1913	-21.7500	-0.0416	-0.6076
ZnO	0.112	1.2447	0.1394	81.3800	0.0017	0.1173	-2.4000	-0.0028	-0.0411
CdO	0.684	1.1423	1.0098						
QzO	0.163	1.2518	0.2040	79.5454	0.0026	0.1757	1.7900	0.0031	0.0459
Fe2+/Fe3+	0.054								
SUMS	47.2470	98.4883	98.2980		1.4599	100.0000		-4.4672	-65.2181
							SUM + pH Si	-4.6556	
							SUM + pH B	-5.3920	
							pH (PCT) =	9.57	

NA = NOT ANALYZED

BDL = LOW DETECTION LEVEL

GLASS ID = CVS2-58

(SPREADSHEET REVISION 5.0, OCTOBER 23, 1990)

ELEMENT	GRAV FACTOR	OXIDE WT%	PIN NOMINAL OXIDE WT%	M.W.	MOLE FRACTION	NORM OXIDE MOLE %	COMPONENT FREE ENERGY	FREE ENERGY HYDRATION	KCAL/KG
Al ₂ O ₃ *	3.8600	7.8040	8.0000	101.9600	0.0765	5.2061	3.0400	0.1583	2.3268
CaO	2.3080	3.2294	3.4800	56.0794	0.0576	3.9168	-16.1160	-0.6312	-9.2805
Fe ₂ O ₃	2.9170	3.8651	4.0000	159.6922	0.0242	1.6463	15.5000	0.2552	3.7515
FeO	1.2865	0.2748		71.8464	0.0038	0.2601	-14.6090	-0.0380	-0.5587
MgO	1.6583			40.3114	0.0000	0.0000	-13.8880	0.0000	0.0000
MnO	1.2912	0.1666		70.9374	0.0023	0.1597	-14.8710	-0.0238	-0.3492
Na ₂ O (AA)	1.3480	10.4740	10.1000	61.9790	0.1690	11.4944	-28.8150	-3.3121	-48.6951
Li ₂ O	2.1525	1.8834	2.0000	29.8774	0.0630	4.2877	-22.7400	-0.9750	-14.3350
NiO	1.2726	0.9196	0.8240	74.7084	0.0110	0.7461	-14.3470	-0.1070	-1.5739
SiO ₂ *	2.1393	49.5462	47.5100	60.0848	0.8080	54.9555	5.5900	1.8636	27.3988
Cr ₂ O ₃	1.4616	0.2455	0.1790	151.9974	0.0016	0.1099	37.3600	0.0411	0.6035
B ₂ O ₃ *	4.5640	15.7942	15.9000	69.6204	0.2269	15.4306	-9.9300	-1.5323	-22.5274
UO ₂	1.1344			270.0388	0.0000	0.0000	-6.8000	0.0000	0.0000
ThO ₂	1.1379			264.0400	0.0000	0.0000	-2.5330	0.0000	0.0000
SnO	1.1826	0.1301	0.1430	103.6194	0.0013	0.0854	-24.4000	-0.0208	-0.3063
ZrO ₂	1.3508	0.8605	1.0000	123.2198	0.0070	0.4750	45.1000	0.2142	3.1494
TiO ₂	1.6680			79.8988	0.0000	0.0000	15.9900	0.0000	0.0000
K ₂ O (AA)	1.2046			94.2034	0.0000	0.0000	-41.7350	0.0000	0.0000
CaO	1.0602	0.2150	0.2150	281.8094	0.0008	0.0519	-46.8200	-0.0243	-0.3572
SiO ₂ O ₃	1.1970			291.4982	0.0000	0.0000	0.0000	0.0000	0.0000
P ₂ O ₅	2.2910	0.1168	0.1430	141.9370	0.0008	0.0560	-53.6200	-0.0300	-0.4414
Na ₂ O ₃	1.1660	1.7600	1.7600	336.4782	0.0052	0.3556	-28.3200	-0.1008	-1.4813
Li ₂ O ₃	1.1728	0.7271	0.8950	325.8100	0.0022	0.1518	-31.1400	-0.0473	-0.6950
Y ₂ O ₃	1.2699	0.0720	0.0720	225.8082	0.0003	0.0217	-12.9500	-0.0028	-0.0413
B ₂ O	1.1165	0.1262	0.1430	153.3394	0.0008	0.0560	-30.5700	-0.0171	-0.2515
P ₂ O	1.0772			223.1900	0.0000	0.0000	-8.8100	0.0000	0.0000
CaO ₂	1.2284	0.2150	0.2150	172.1200	0.0012	0.0850	11.3450	0.0096	0.1417
MnO ₃	1.5003	0.3946	0.4300	143.9382	0.0027	0.1885	-21.7500	-0.0406	-0.5962
ZnO	1.2447	0.1908		81.3600	0.0012	0.0843	-2.4000	-0.0020	-0.0297
CdO	1.1423	0.9755	1.0740						
Q ₂ O	1.2518	0.2078	0.2150	79.5454	0.0026	0.1777	1.7900	0.0032	0.0468
Fe ₂ +Fe ₃ +	0.079								
SUMS	47.3580	99.2041	98.2980		1.4702	100.0000			
NA = NOT ANALYZED							SUM + pH Si	-4.3600	-64.1011
BDL = BELOW DETECTION LEVEL							SUM + pH B	-4.5484	
							pH (PCT) =	-5.2848	9.57

GLASS ID = CVS2-7A

(SPREADSHEET REVISION 5.0, OCTOBER 23, 1990)

ELEMENT	GRAV FACTOR	OXIDE WT%	FWL NOMINAL OXIDE WT%	M.W.	MOLE FRACTION	NORM OXIDE MOLE %	COMPONENT FREE ENERGY	FREE ENERGY HYDRATION	KCAL/KG
Al2O3*	4.5240	1.8895	9.1465	101.9600	0.0897	5.8376	3.0400	0.1775	2.7271
CaO	0.8110	1.3992	1.1348	56.0794	0.0202	1.3168	-16.1160	-0.2122	-3.2610
Fe2O3	2.9850	1.4297	4.0567	159.6922	0.0254	1.6531	15.5000	0.2562	3.9375
FeO	1.2865	0.1898	0.1898	71.8464	0.0026	0.1719	-14.6090	-0.0251	-0.3860
MgO	0.0080	0.0133	0.0133	40.3114	0.0003	0.0214	-13.8880	-0.0030	-0.0457
MnO	0.1160	0.1498	0.1498	70.9374	0.0021	0.1374	-14.8710	-0.0204	-0.3140
Na2O (AA)	5.8700	1.3480	7.9128	61.9780	0.1277	8.3080	-28.8150	-2.3939	-36.7877
Li2O	2.5390	2.1525	5.4652	29.8774	0.1829	11.9035	-22.7400	-2.7069	-41.5962
NiO	0.5360	1.2726	0.6821	74.7094	0.0091	0.5941	-14.3470	-0.0852	-1.3099
SiO2*	21.4900	2.1393	49.1917	60.0848	0.8187	53.2770	5.5900	1.6835	25.8710
Cr2O3	0.1470	1.4616	0.2149	151.9974	0.0014	0.0920	37.3600	0.0344	0.5281
B2O3*	4.7010	3.2201	16.1973	69.6204	0.2327	15.1398	-9.9300	-1.5034	-23.1023
UO2	NA	1.1344		270.0398	0.0000	0.0000	-6.8000	0.0000	0.0000
ThO2	NA	1.1379		264.0400	0.0000	0.0000	-2.5330	0.0000	0.0000
SrO	0.0920	1.1826	0.1088	103.6194	0.0010	0.0683	-24.4000	-0.0167	-0.2562
ZrO2	0.6590	1.3508	0.8902	123.2188	0.0072	0.4701	45.1000	0.2120	3.2582
TiO2	0.6100	1.6680		79.8988	0.0000	0.0000	15.9900	0.0000	0.0000
K2O (AA)	BDL	1.2046		94.2034	0.0000	0.0000	-41.7350	0.0000	0.0000
CaO	NA	1.0602	6.1740	281.3084	0.0006	0.0402	-46.8200	-0.0188	-0.2891
SiO2O3	NA	1.1979		291.4982	0.0000	0.0000	0.0000	0.0000	0.0000
P2O5	0.0280	2.2910	0.0641	141.9370	0.0005	0.0294	-53.6200	-0.0158	-0.2423
Na2O3	NA	1.1660	1.4310	336.4782	0.0043	0.2768	-28.3200	-0.0784	-1.2044
La2O3	0.5500	1.1728	0.6450	325.8100	0.0020	0.1288	-31.1400	-0.0401	-0.6165
Y2O3	NA	1.2699	0.0580	225.8082	0.0003	0.0167	-12.9500	-0.0022	-0.0333
BaO	0.0980	1.1165	0.1094	153.3394	0.0007	0.0464	-30.5700	-0.0142	-0.2181
PbO	BDL	1.0772		223.1900	0.0000	0.0000	-8.8100	0.0000	0.0000
CaO2	NA	1.2284	0.2150	172.1200	0.0012	0.0813	11.3450	0.0092	0.1417
MnO3	0.221	1.5003	0.3316	143.9382	0.0023	0.1499	-21.7500	-0.0326	-0.5010
ZnO	0.082	1.2447	0.1021	81.3800	0.0013	0.0816	-2.4000	-0.0020	-0.0301
CdO	0.703	1.1423	0.8030						
CuO	0.154	1.2518	0.1928	79.5454	0.0024	0.1577	1.7900	0.0028	0.0434
Fe2+/Fe3+	0.052								
SUMS	46.3240	99.4798	98.6340		1.5367	100.0000		-4.7952	-73.6869
							SUM + pH Si	-5.0768	
							SUM + pH B	-6.0304	
							pH (PCT) =	9.78	

NA = NOT ANALYZED

BDL = BELOW DETECTION LEVEL

GLASS ID = CVS2-7B

	ELEMENT WT%	GRAV FACTOR	OXIDE WT%	PINL NOMINAL OXIDE WT%	M.W.	MOLE FRACTION	NORM OXIDE MOLE %	COMPONENT FREE ENERGY	FREE ENERGY HYDRATION	KCAL/KG
Al ₂ O ₃ *	4.5450	1.8895	9.1889	9.5300	101.9600	0.0901	5.8468	3.0400	0.1777	2.7397
CaO	0.8000	1.3992	1.1194	0.9400	56.0794	0.0200	1.2949	-16.1160	-0.2087	-3.2168
Fe ₂ O ₃	3.0020	1.4297	4.0759	4.0000	159.6922	0.0255	1.6559	15.5000	0.2567	3.9562
FeO	SEE REDOX	1.2865	0.1944		71.8464	0.0027	0.1755	-14.6090	-0.0256	-0.3953
MgO	0.0060	1.6583	0.0099		40.3114	0.0002	0.0160	-13.8880	-0.0022	-0.0343
MnO	0.1160	1.2912	0.1498		70.9374	0.0021	0.1370	-14.8710	-0.0204	-0.3140
Na ₂ O (AA)	5.9800	1.3480	7.9262	7.0000	61.9790	0.1279	8.2966	-28.8150	-2.3907	-36.8503
Li ₂ O	2.5530	2.1525	5.4953	5.9100	29.8774	0.1839	11.9325	-22.7400	-2.7134	-41.8255
NiO	0.5440	1.2728	0.6923	0.6670	74.7094	0.0093	0.6012	-14.3470	-0.0862	-1.3295
SiO ₂ *	21.5290	2.1393	49.2610	48.1400	60.0848	0.8202	53.2102	5.5900	1.6791	25.8816
Cr ₂ O ₃	0.1490	1.4616	0.2178	0.1450	151.9974	0.0014	0.0930	37.3600	0.0347	0.5353
B ₂ O ₃ *	4.7250	3.2201	16.2800	17.0000	69.6204	0.2338	15.1705	-9.9300	-1.5064	-23.2203
UO ₂	NA	1.1344			270.0388	0.0000	0.0000	-6.8000	0.0000	0.0000
ThO ₂	NA	1.1379			264.0400	0.0000	0.0000	-2.5330	0.0000	0.0000
SO	0.0930	1.1826	0.1100	0.1160	103.6194	0.0011	0.0589	-24.4000	-0.0168	-0.2590
ZrO ₂	0.6640	1.3508	0.8969	1.0050	123.2188	0.0073	0.4722	45.1000	0.2130	3.2829
TiO ₂	0.0100	1.6680			79.8988	0.0000	0.0000	15.9900	0.0000	0.0000
K ₂ O (AA)	BDL	1.2046	0.1740	0.1740	94.2034	0.0000	0.0000	-41.7350	0.0000	0.0000
CaO	NA	1.0602			281.8094	0.0006	0.0401	-46.8200	-0.0188	-0.2891
SiO ₂ O ₃	NA	1.1970			291.4982	0.0000	0.0000	0.0000	0.0000	0.0000
F ₂ O ₅	0.0330	2.2910	0.0756	0.1160	141.9370	0.0005	0.0346	-53.6200	-0.0185	-0.2856
Na ₂ O ₃	NA	1.1660	1.4310	1.4310	336.4782	0.0043	0.2759	-28.3200	-0.0781	-1.2044
La ₂ O ₃	0.5590	1.1728	0.6556	0.7250	325.8100	0.0020	0.1305	-31.1400	-0.0407	-0.6266
Y ₂ O ₃	NA	1.2699	0.0580	0.0580	225.8082	0.0003	0.0167	-12.9500	-0.0022	-0.0333
BaO	0.0990	1.1165	0.1105	0.1160	153.3394	0.0007	0.0468	-30.5700	-0.0143	-0.2204
PbO	BDL	1.0772			223.1900	0.0000	0.0000	-8.8100	0.0000	0.0000
CeO ₂	NA	1.2284	0.2150	0.1740	172.1200	0.0012	0.0810	11.3450	0.0092	0.1417
MnO ₃	0.22	1.5003	0.3301	0.3480	143.9382	0.0023	0.1488	-21.7500	-0.0324	-0.4988
ZnO	0.092	1.2447	0.1145		81.3800	0.0014	0.0913	-2.4000	-0.0022	-0.0338
CdO	0.708	1.1423	0.8087	0.8700						
ClO	0.16	1.2518	0.2003	0.1740	79.5454	0.0025	0.1634	1.7900	0.0029	0.0451
Fe ₂ -/Fe ₃ +	0.053									
SUMS	46.4870		99.6112	98.6340		1.5414	100.0000		-4.8043	-74.0543
								SUM + pH Si	-5.0859	
								SUM + pH B	-6.0396	
								pH (PCT) =	9.78	

NA = NOT ANALYZED

BDL = BELOW DETECTION LEVEL

GLASS ID = CVS2-16A

(SPREADSHEET REVISION 5.0, OCTOBER 23, 1990)

ELEMENT	GRAV FACTOR	OXIDE WT%	P/NL NOMINAL OXIDE WT%	M.W.	MOLE FRACTION	NORM OXIDE MOLE %	COMPONENT FREE ENERGY	FREE ENERGY HYDRATION	KCAL/KG
Al2O3*	1.3480	1.8695	2.3100	101.9600	0.0267	1.8557	3.0400	0.0564	0.8126
CaO	0.7790	1.3992	0.8300	56.0794	0.0194	1.3494	-16.1160	-0.2175	-3.1324
Fe2O3	4.5430	1.4297	7.1900	159.6922	0.0365	2.5370	15.5000	0.3932	5.6642
FeO	1.2865	0.5934		71.8464	0.0083	0.5734	-14.6090	-0.0838	-1.2066
SEE REDOX									
MgO	0.5060	1.6583	0.8400	40.3114	0.0208	1.4451	-13.8880	-0.2007	-2.8908
MnO	0.1590	1.2912		70.9374	0.0029	0.2009	-14.8710	-0.0299	-0.4304
Na2O (AA)	3.2400	1.3480	11.2500	61.9790	0.1792	12.4418	-28.8150	-3.5851	-51.6406
Li2O	1.5790	2.1525	3.7500	29.8774	0.1138	7.8976	-22.7400	-1.7959	-25.8686
NbO	0.5260	1.2726	0.6100	74.7094	0.0090	0.6220	-14.3470	-0.0892	-1.2955
SiO2*	21.2920	2.1393	53.5300	60.0848	0.8112	56.3143	5.5900	1.6075	23.1553
Cr2O3	0.1260	1.4616	0.1330	151.9974	0.0012	0.0841	37.3600	0.0314	0.4527
B2O3*	3.1140	3.2201	10.5300	69.6204	0.1541	10.6991	-9.9300	-1.0624	-15.3033
UO2	NA	1.1344		270.0388	0.0000	0.0000	-6.8000	0.0000	0.0000
ThO2	NA	1.1379		264.0400	0.0000	0.0000	-2.5330	0.0000	0.0000
SO	0.0050	1.1826	0.1060	103.6194	0.0001	0.0040	-24.4000	-0.0010	-0.0139
ZrO2	2.8060	1.3508	3.8500	123.2188	0.0319	2.2117	45.1000	0.9975	14.3677
TiO2	0.0650	1.6680		79.8988	0.0000	0.0000	15.9900	0.0000	0.0000
K2O (AA)	0.2480	1.2046		94.2034	0.0032	0.2202	-41.7350	-0.0919	-1.3235
Ca2O	NA	1.0602	0.1590	281.8094	0.0006	0.0392	-46.8200	-0.0183	-0.2642
Na2O3	NA	1.1970		291.4982	0.0000	0.0000	0.0000	0.0000	0.0000
P2O5	0.0750	2.2910	0.1060	141.9370	0.0012	0.0840	-53.6200	-0.0451	-0.6491
Nb2O3	NA	1.1660	1.3080	336.4782	0.0039	0.2699	-28.3200	-0.0764	-1.1009
La2O3	0.8080	1.1728	0.6620	325.8100	0.0029	0.2019	-31.1400	-0.0629	-0.9057
Y2O3	NA	1.2699	0.0530	225.8082	0.0002	0.0163	-12.9500	-0.0021	-0.0304
BaO	0.0980	1.1165	0.1094	153.3394	0.0007	0.0495	-30.5700	-0.0151	-0.2181
PbO	BDL	1.0772		223.1900	0.0000	0.0000	-8.8100	0.0000	0.0000
CaO2	NA	1.2284	0.1590	172.1200	0.0009	0.0641	11.3450	0.0073	0.1048
MnO3	0.193	1.5003	0.3180	143.9382	0.0020	0.1397	-21.7500	-0.0304	-0.4375
ZrO	0.473	1.2447	0.5887	91.3600	0.0072	0.5022	-2.4000	-0.0121	-0.1736
CaO	0.542	1.1423	0.6191						
CaO	0.182	1.2518	0.2028	79.5454	0.0025	0.1770	1.7900	0.0032	0.0456
Fe2+/Fe3+	0.113								
SUMS	47.7870	94.9546	98.7548		1.4404	100.0000		-4.3232	-62.2723
							SUM + pH Si	-4.9280	
							SUM + pH B	-6.4275	
							pH (PCT) =	10.24	

NA = NOT ANALYZED

BDL = BELOW DETECTION LEVEL

GLASS ID = CVS2-16B

ELEMENT	GRAV	OXIDE	PHIL NOMINAL	M.W.	MOLE	NORM OXIDE	COMPONENT	FREE ENERGY	KCAL/KG
WT%	FACTOR	WT%	OXIDE WT%		FRACTION	MOLE %	FREE ENERGY	HYDRATION	
Al ₂ O ₃ *	1.5520	3.1378	2.3100	101.9600	0.0308	1.9855	3.0400	0.0604	0.9355
CaO	1.3992	1.0732	0.8300	56.0794	0.0191	1.2347	-16.1160	-0.1990	-3.0841
Fe ₂ O ₃	1.4297	5.6184	7.1900	159.6922	0.0352	2.2699	15.5000	0.3518	5.4533
FeO	1.2865	0.7735		71.8464	0.0108	0.6946	-14.6090	-0.1015	-1.5728
SEE REDOX									
MgO	1.6583	0.8374	0.8400	40.3114	0.0208	1.3403	-13.8880	-0.1861	-2.8851
MnO	1.2912	0.2040		70.9374	0.0029	0.1855	-14.8710	-0.0276	-0.4277
Na ₂ O (AA)	1.3480	10.9592	11.2500	61.9790	0.1768	11.4080	-28.8150	-3.2872	-50.9512
Li ₂ O	2.1525	3.4031	3.7500	29.8774	0.1139	7.3486	-22.7400	-1.6711	-25.9014
NbO	1.2726	0.6745	0.6100	74.7094	0.0090	0.5825	-14.3470	-0.0836	-1.2953
SiO ₂ *	2.1393	53.3212	53.5300	60.0848	0.8874	57.2543	5.5900	1.7643	27.3470
Cr ₂ O ₃	1.4616	0.1812	0.1330	151.9974	0.0012	0.0769	37.3600	0.0287	0.4455
B ₂ O ₃ *	3.2201	12.2315	10.5300	69.6204	0.1757	11.3349	-9.9300	-1.1256	-17.4459
UO ₂	1.1344			270.0388	0.0000	0.0000	-6.8000	0.0000	0.0000
ThO ₂	1.1379			264.0400	0.0000	0.0000	-2.5330	0.0000	0.0000
SnO	1.1826	0.0071	0.1060	103.6194	0.0001	0.0044	-24.4000	-0.0011	-0.0167
ZrO ₂	1.3508	3.9700	3.8500	123.2188	0.0322	2.0787	45.1000	0.9375	14.5308
TiO ₂	1.6680			79.8988	0.0000	0.0000	15.9900	0.0000	0.0000
K ₂ O (AA)	1.2046	0.3036		94.2034	0.0032	0.2079	-41.7350	-0.0868	-1.3449
CaO	1.0602	0.1590	0.1590	281.8034	0.0006	0.0364	-46.8200	-0.0170	-0.2642
Na ₂ O ₃	1.1970			291.4982	0.0000	0.0000	0.0000	0.0000	0.0000
P ₂ O ₅	2.2910	0.1650	0.1060	141.9370	0.0012	0.0750	-53.6200	-0.0402	-0.6231
Na ₂ O ₃	1.1660	1.3080	1.3080	336.4782	0.0039	0.2508	-28.3200	-0.0710	-1.1009
La ₂ O ₃	1.1728	3.4844	0.6620	325.8100	0.0107	0.6900	-31.1400	-0.2149	-3.3303
Y ₂ O ₃	1.2699	0.0530	0.0530	225.8092	0.0002	0.0151	-12.9500	-0.0021	-0.0304
BaO	1.1165	0.2389	0.1060	153.3394	0.0016	0.1005	-30.5700	-0.0307	-0.4763
PbO	1.0772			223.1900	0.0000	0.0000	-8.8100	0.0000	0.0000
CaO ₂	1.2284	0.1590	0.1590	172.1200	0.0009	0.0596	11.3450	0.0068	0.1048
MnO ₃	1.5003	0.2851	0.3180	143.9382	0.0020	0.1278	-21.7500	-0.0278	-0.4307
ZnO	1.2447	0.5925		81.3800	0.0073	0.4697	-2.4000	-0.0113	-0.1747
CdO	1.1423	0.6180	0.7850						
CuO	1.2518	0.2078	0.1598	78.5454	0.0026	0.1685	1.7900	0.0030	0.0468
Fe ₂ +Fe ₃ +									
SUMS	52.6140	103.9663	98.7548		1.5500	100.0000			
							SUM + pH Si	-4.0318	-62.4920
							SUM + pH B	-4.6366	
							pH (PCT) =	-6.1361	
								10.24	

NA = NOT ANALYZED

BDL = BELOW DETECTION LEVEL

ELEMENT	GRAV	OXIDE	PNL NOMINAL	M.W.	MOLE	NORM OXIDE	COMPONENT	FREE ENERGY	KCAL/KG
WT%	FACTOR	WT%	OXIDE WT%		FRACTION	MOLE %	FREE ENERGY	HYDRATION	
Al ₂ O ₃ *	2.9200	1.8895	5.9036	101.9600	0.0579	3.8455	3.0400	0.1169	1.7602
CaO	2.0240	1.3992	2.8320	56.0784	0.0505	3.3539	-16.1160	-0.5405	-8.1385
Fe ₂ O ₃	4.2640	1.4297	5.7566	159.6922	0.0360	2.3941	15.5000	0.3711	5.5875
FeO	1.2865	1.2865	0.3056	71.8464	0.0043	0.2825	-14.6090	-0.0413	-0.6214
SEE PEROX									
MgO	2.0590	1.6583	3.4144	40.3114	0.0847	5.6255	-13.8880	-0.7813	-11.7634
MnO	0.0730	1.2912	0.0943	70.9374	0.0013	0.0882	-14.8710	-0.0131	-0.1976
Na ₂ O (AA)	7.2900	1.3480	9.8269	61.9790	0.1586	10.5303	-28.8150	-3.0343	-45.6869
Li ₂ O	1.7260	2.1525	3.7152	29.8774	0.1243	8.2587	-22.7400	-1.8780	-28.2769
NaO	0.3730	1.2726	0.4747	74.7094	0.0064	0.4220	-14.3470	-0.0605	-0.9116
SiO ₂ *	20.3150	2.1393	46.5021	60.0848	0.7739	51.4016	5.5900	1.1405	17.1718
Cr ₂ O ₃	0.1460	1.4616	0.2134	151.9974	0.0014	0.0932	37.3600	0.0348	0.5245
B ₂ O ₃ *	3.2520	3.2201	11.2048	68.6204	0.1609	10.6890	-9.9300	-1.0614	-15.9815
UO ₂	NA	1.1344		270.0388	0.0000	0.0000	-6.8000	0.0000	0.0000
ThO ₂	NA	1.1379		264.0400	0.0000	0.0000	-2.5330	0.0000	0.0000
SiO	0.0580	1.1826	0.0686	103.6194	0.0007	0.0440	-24.4000	-0.0107	-0.1615
ZrO ₂	3.0310	1.3508	4.0943	123.2188	0.0332	2.2068	45.1000	0.9953	14.9857
TiO ₂	0.0070	1.6680		79.8988	0.0000	0.0000	15.9900	0.0000	0.0000
K ₂ O (AA)	0.0220	1.2046	0.0265	94.2034	0.0003	0.0187	-41.7350	-0.0078	-0.1174
CaO	NA	1.0602	0.1090	281.8094	0.0004	0.0257	-46.8290	-0.0120	-0.1811
SiO ₂ O ₃	NA	1.1970		291.4982	0.0000	0.0000	0.0000	0.0000	0.0000
P ₂ O ₅	0.0290	2.2910	0.0664	141.9370	0.0005	0.0311	-53.6200	-0.0167	-0.2510
Na ₂ O ₃	NA	1.1660	0.8990	336.4782	0.0027	0.1774	-28.3200	-0.0503	-0.7567
La ₂ O ₃	0.4960	1.1728	0.4550	325.8100	0.0018	0.1186	-31.1400	-0.0369	-0.5560
Y ₂ O ₃	NA	1.2699	0.0370	225.8082	0.0002	0.0109	-12.9500	-0.0014	-0.0212
BaO	0.0610	1.1165	0.0681	153.3394	0.0004	0.0295	-30.5700	-0.0090	-0.1358
PbO	BDL	1.0772		223.1900	0.0000	0.0000	-8.8100	0.0000	0.0000
CaO ₂	NA	1.2284	0.1090	172.1200	0.0006	0.0421	11.3450	0.0048	0.0718
Mn ₂ O ₃	0.144	1.5003	0.2160	143.9382	0.0015	0.0987	-21.7500	-0.0217	-0.3265
ZnO	0.112	1.2447	0.1394	81.3800	0.0017	0.1139	-2.4000	-0.0027	-0.0411
CaO	0.452	1.1423	0.5163						
UO	0.093	1.2518	0.1164	79.5454	0.0015	0.0972	1.7900	0.0017	0.0262
Fe ₂ +Fe ₃ +	0.059								
SUMS	48.9470	97.2913	99.1430		1.5057	100.0000		-4.9146	-73.9982
							SUM + pH Si	-5.4592	
							SUM + pH B	-6.8711	
							pH (PCT) =	10.17	

NA = NOT ANALYZED
BDL = BELOW DETECTION LEVEL

ELEMENT	GRAV FACTOR	OXIDE WT%	PIN NOMINAL OXIDE WT%	M.W.	MOLE FRACTION	NORM OXIDE MOLE %	COMPONENT FREE ENERGY	FREE ENERGY HYDRATION	KCAL/KG
Al ₂ O ₃ *	2.5100	5.0746	6.3600	101.9600	0.0498	3.3746	3.0400	0.1026	1.5130
CaO	1.3992	2.8012	2.7500	56.0794	0.0500	3.3868	-16.1160	-0.5458	-8.0500
Fe ₂ O ₃	1.4297	5.8209	5.6800	159.6922	0.0365	2.4715	15.5000	0.3831	5.6499
FeO	1.2865	0.3352		71.8464	0.0047	0.3164	-14.6090	-0.0462	-0.6816
SEE REDOX									
MgO	1.6583	3.4542	3.6300	40.3114	0.0857	5.8100	-13.8880	-0.8069	-11.9005
MnO	1.2912	0.1136		70.9374	0.0016	0.1086	-14.8710	-0.0162	-0.2382
Na ₂ O (AA)	1.3480	9.7056	10.0300	61.9790	0.1566	10.6176	-28.8150	-3.0595	-45.1228
Li ₂ O	2.1525	3.7819	3.7600	29.8774	0.1266	8.5827	-22.7400	-1.9517	-28.7848
NO	1.2726	0.4823	0.4190	74.7094	0.0065	0.4377	-14.3470	-0.0628	-0.9262
SiO ₂ *	2.1393	45.3667	48.0100	60.0848	0.7550	51.1944	5.5900	1.0851	16.0033
Cr ₂ O ₃	1.4616	0.2251	0.0910	151.9974	0.0015	0.1004	37.3600	0.0375	0.5532
B ₂ O ₃ *	3.2201	10.7638	11.4200	69.6204	0.1546	10.4828	-9.9300	-1.0409	-15.3524
UO ₂	1.1344			270.0388	0.0000	0.0000	-6.8000	0.0000	0.0000
ThO ₂	1.1379			264.0400	0.0000	0.0000	-2.5330	0.0000	0.0000
SiO	1.1826	0.0745	0.0730	103.6194	0.0007	0.0488	-24.4000	-0.0119	-0.1754
ZrO ₂	1.3508	4.1780	4.2900	123.2188	0.0339	2.2990	45.1000	1.0369	15.2922
TiO ₂	1.6680			79.8988	0.0000	0.0000	15.9900	0.0000	0.0000
K ₂ O (AA)	1.2046	0.0301		94.2034	0.0003	0.0217	-41.7350	-0.0090	-0.1334
Ce ₂ O	1.0602	0.1090	0.1090	281.8094	0.0004	0.0262	-46.8200	-0.0123	-0.1811
Sn ₂ O ₃	1.1970			291.4982	0.0000	0.0000	0.0000	0.0000	0.0000
P ₂ O ₅	2.2910	0.1306	0.0730	141.9370	0.0009	0.0624	-53.6200	-0.0334	-0.4933
Ni ₂ O ₃	1.1660	0.8990	0.8990	336.4782	0.0027	0.1812	-28.3200	-0.0513	-0.7567
La ₂ O ₃	1.1728	0.4034	0.4550	325.8100	0.0012	0.0840	-31.1400	-0.0261	-0.3856
Y ₂ O ₃	1.2699	0.9370	0.0370	225.8082	0.0002	0.0111	-12.9500	-0.0014	-0.0212
B ₂ O	1.1165	0.0759	0.0730	153.3394	0.0005	0.0336	-30.5700	-0.0103	-0.1514
P ₂ O	1.0772			223.1900	0.0000	0.0000	-8.8100	0.0000	0.0000
Ce ₂ O	1.2284	0.1090	0.1090	172.1200	0.0006	0.0429	11.3450	0.0049	0.0718
Mo ₂ O ₃	1.5003	0.2220	0.2190	143.9382	0.0015	0.1046	-21.7500	-0.0227	-0.3355
ZnO	1.2447	0.1133		81.3800	0.0014	0.0944	-2.4000	-0.0023	-0.0334
CdO	1.1423	0.5266	0.5470						
Q ₂ O	1.2518	0.1252	0.1090	79.5454	0.0016	0.1067	1.7900	0.0019	0.0282
Fe ₂ +/Fe ₃ +	0.064								
SUMS	47.9110	94.9589	99.1430		1.4749	100.0000			
							SUM + pH Si	-5.0589	-74.6119
							SUM + pH B	-5.6035	
							pH (PCT) =	-7.0154	
								10.17	

NA = NOT ANALYZED

BDL = BELOW DETECTION LEVEL

ELEMENT	GRAV	OXIDE	PUL NOMINAL	M.W.	MOLE	NORM OXIDE	COMPONENT	FREE ENERGY	FREE ENERGY	KCAL/KG
WT%	FACTOR	WT%	OXIDE WT%		FRACTION	MOLE %	FREE ENERGY	HYDRATION		
Al ₂ O ₃ *	1.4670	2.9659	2.3100	101.9600	0.0291	1.9850	3.0400	0.0603	0.8843	
CaO	1.3992	1.0816	0.8300	56.0794	0.0193	1.3161	-16.1160	-0.2121	-3.1082	
Fe ₂ O ₃	1.4297	5.5069	7.1900	159.6922	0.0345	2.3532	15.5000	0.3647	5.3450	
FeO	1.2865	0.8275		71.8464	0.0115	0.7860	-14.6090	-0.1148	-1.6827	
SEE REDOX										
MgO	1.6583	0.8275	0.8400	40.3114	0.0205	1.4008	-13.8980	-0.1945	-2.8509	
MnO	1.2912	0.2105		70.9374	0.0030	0.2025	-14.8710	-0.0301	-0.4412	
Na ₂ O (AA)	1.3480	10.7570	11.2500	61.9790	0.1736	11.8436	-28.8150	-3.4127	-50.0112	
Li ₂ O	2.1525	3.3837	3.7500	29.8774	0.1133	7.7284	-22.7400	-1.7574	-25.7539	
NbO	1.2726	0.6770	0.6100	74.7094	0.0091	0.6184	-14.3470	-0.0887	-1.3001	
SiO ₂ *	2.1393	50.8581	53.5300	60.0848	0.8464	57.7605	5.5900	1.7242	25.2665	
Cr ₂ O ₃	1.4616	0.2032	0.1330	151.9974	0.0013	0.0912	37.3600	0.0341	0.4994	
B ₂ O ₃ *	3.2201	9.9610	10.5300	69.6204	0.1431	9.7934	-9.9300	-0.9695	-14.2074	
UO ₂	1.1344			270.0388	0.0000	0.0000	-6.8000	0.0000	0.0000	
ThO ₂	1.1379			264.0400	0.0000	0.0000	-2.5330	0.0000	0.0000	
SO	1.1825	0.0106	0.1060	103.6194	0.0001	0.0070	-24.4000	-0.0017	-0.0251	
ZrO ₂	1.3508	3.9389	3.8500	123.2188	0.0320	2.1814	45.1000	0.9838	14.4171	
TiO ₂	1.6680			79.8988	0.0000	0.0000	15.9900	0.0000	0.0000	
K ₂ O (AA)	1.2046	0.2771		94.2034	0.0029	0.2007	-41.7350	-0.0838	-1.2275	
CaO	1.0602	0.1590	0.1590	281.8094	0.0006	0.0385	-46.8200	-0.0180	-0.2642	
SiO ₂ O ₃	1.1970			291.4982	0.0000	0.0000	0.0000	0.0000	0.0000	
P ₂ O ₅	2.2910	0.2131	0.1060	141.9370	0.0015	0.1024	-53.6200	-0.0549	-0.8049	
N ₂ O ₃	1.1660	1.3080	1.3080	336.4782	0.0039	0.2853	-28.3200	-0.0751	-1.1009	
La ₂ O ₃	1.1728	1.8014	0.6620	325.8100	0.0055	0.3773	-31.1400	-0.1175	-1.7217	
Y ₂ O ₃	1.2699	0.9530	0.0530	225.8082	0.0002	0.0160	-12.9500	-0.0021	-0.0304	
B ₂ O	1.1165	0.2311	0.1060	153.3394	0.0015	0.1029	-30.5700	-0.0314	-0.4608	
P ₂ O	1.0772			223.1900	0.0000	0.0000	-8.9100	0.0000	0.0000	
CaO ₂	1.2284	9.1590	0.1590	172.1200	0.0009	0.0830	11.3450	0.0072	0.1048	
MnO ₃	1.5003	0.2851	0.3180	143.9382	0.0020	0.1351	-21.7500	-0.0294	-0.4307	
ZrO	1.2447	0.5850		81.3800	0.0072	0.4905	-2.4000	-0.0118	-0.1725	
CaO	1.1423	0.6203	0.7950							
CaO	1.2518	0.1990	0.1598	79.5454	0.0025	0.1707	1.7900	0.0031	0.0448	
Fe ₂ +/Fe ₃ +	0.167									
SUMS	49.1510	97.1005	98.7548		1.4654	100.0000		-4.0283	-59.0323	
							SUM + pH Si	-4.7067		
							SUM + pH B	-6.3077		
							pH (PCT) =	10.32		

NA = NOT ANALYZED
BDL = BELOW DETECTION LEVEL

GLASS ID = CVS2-18B

ELEMENT	GRAV	OXIDE	PNIL NOMINAL	M.W.	MOLE	NORM OXIDE	COMPONENT	FREE ENERGY	FREE ENERGY	KCAL/KG
WT%	FACTOR	WT%	OXIDE WT%		FRACTION	MOLE %	FREE ENERGY	HYDRATION		
Al2O3	1.4540	2.7473	2.3100	101.9600	0.0269	1.8147	3.0400	0.0552	0.8191	
CaO	0.7610	1.0648	0.8300	56.0794	0.0190	1.2787	-16.1160	-0.2061	-3.0600	
Fe2O3	4.4650	5.5126	7.1800	159.6922	0.0345	2.3248	15.5000	0.3603	5.3506	
FeO	1.2865	0.7838	0.8400	71.8464	0.0109	0.7347	-14.6090	-0.1073	-1.5937	
MgO	1.6583	0.8242	0.8400	40.3114	0.0204	1.3769	-13.8880	-0.1912	-2.8394	
MnO	0.1620	0.2092		70.9374	0.0029	0.1936	-14.8710	-0.0295	-0.4385	
Na2O (AA)	7.9800	10.7570	11.2500	61.9790	0.1736	11.6886	-28.8150	-3.3681	-50.0112	
Li2O	1.5630	3.3644	3.7500	29.8774	0.1126	7.5836	-22.7400	-1.7245	-25.6065	
NiO	1.2726	0.6668	0.6100	74.7094	0.0089	0.6011	-14.3470	-0.0862	-1.2806	
SiO2*	22.7900	52.1675	53.5300	60.0648	0.8682	59.4721	5.5900	1.7910	26.5935	
Cr2O3	1.4616	0.1988	0.1330	151.9974	0.0013	0.0881	37.3600	0.0329	0.4886	
B2O3*	2.9300	10.0953	10.5300	69.6204	0.1450	5.7656	-9.9300	-0.9697	-14.3990	
UO2	1.1344			270.0388	0.0000	0.0500	-6.8000	0.0000	0.0000	
ThO2	1.1379			264.0400	0.0000	0.0000	-2.5330	0.0000	0.0000	
SnO	1.1826	0.0106	0.1060	103.6194	0.0001	0.0069	-24.4000	-0.0017	-0.0251	
ZrO2	1.3508	3.9281	3.8500	123.2188	0.0318	2.1470	45.1000	0.9683	14.3776	
TiO2	1.6680			79.8988	0.0000	0.0000	15.9900	0.0000	0.0000	
K2O (AA)	1.2046	0.2759		94.2034	0.0029	0.1672	-41.7350	-0.0823	-1.2221	
Cs2O	1.0602	0.1590	0.1590	281.8094	0.0006	0.0380	-46.8200	-0.0178	-0.2642	
Sr2O3	1.1970			291.4982	0.0000	0.0000	0.0000	0.0000	0.0000	
P2O5	2.2910	0.1741	0.1060	141.9370	0.0012	0.0826	-53.6200	-0.0443	-0.6578	
Nb2O3	1.1660	1.3080	1.3080	336.4782	0.0039	0.2618	-28.3200	-0.0741	-1.1009	
La2O3	1.1728	1.8214	0.6620	325.8100	0.0056	0.3765	-31.1400	-0.1172	-1.7408	
Y2O3	1.2699	0.0530	0.0530	225.8082	0.0002	0.0158	-12.9500	-0.0020	-0.0304	
BaO	1.1165	0.2322	0.1060	153.3394	0.0015	0.1020	-30.5700	-0.0312	-0.4630	
PbO	1.0772			223.1900	0.0000	0.0000	-8.8100	0.0000	0.0000	
CeO2	1.2284	0.1590	0.1590	172.1200	0.0009	0.0622	11.3450	0.0071	0.1042	
MoO3	1.5003	0.2821	0.3180	143.9382	0.0020	0.1320	-21.7500	-0.0287	-0.4262	
ZnO	1.2447	0.5800		81.3800	0.0071	0.4800	-2.4000	-0.0115	-0.1711	
CdO	1.1423	0.6180	0.7950							
QzO	1.2518	0.2015	0.1598	79.5454	0.0025	0.1706	1.7900	0.0031	0.0454	
Fe2+/Fe3+										
SLMS	49.6710	98.1946	98.7548		1.4849	100.0000		-3.8758	-57.5507	
							SUM + pH Si	-4.5542		
							SUM + pH B	-6.1552		
							pH (PCT) =	10.32		

NA = NOT ANALYZED

BDL = BELOW DETECTION LEVEL

GLASS ID = PUREX STANDARD-A

(SPREADSHEET REVISION 5.0, OCTOBER 23, 1990)

ELEMENT	GRAV	OXIDE	CGW NOMINAL	M.W.	MOLE	NORM OXIDE	COMPONENT	FREE ENERGY	FREE ENERGY	KCAL/KG
WT%	FACTOR	WT%	OXIDE WT%		FRACTION	MOLE %	FREE ENERGY	HYDRATION		
Al2O3*	1.3120	2.6526	2.9900	101.9600	0.0260	1.7471	3.0400	0.0531	0.7909	
CaO	1.8895	1.1292	1.0900	56.0784	0.0201	1.3522	-16.1160	-0.2179	-3.2449	
Fe2O3	1.4297	12.4702	13.2500	159.6922	0.0781	5.2440	15.5000	0.8128	12.1038	
FeO	1.2865	0.8977		71.8464	0.0125	0.8391	-14.6090	-0.1226	-1.8253	
SEEDED										
MgO	1.6583	1.4046	1.4100	40.3114	0.0348	2.3399	-13.8880	-0.3250	-4.8390	
MnO	1.2912	1.6899	1.6891	70.9374	0.0238	1.5988	-14.8710	-0.2378	-3.5405	
Na2O (AA)	1.3480	12.2533	12.6200	61.9790	0.1977	13.2765	-28.8150	-3.8256	-56.9676	
Li2O	2.1525	3.2460	3.2200	29.8774	0.1086	7.2959	-22.7400	-1.6591	-24.7054	
NiO	1.2726	1.2242	1.1900	74.7094	0.0164	1.1004	-14.3470	-0.1579	-2.3510	
SiO2*	2.1393	46.3487	46.5000	60.0848	0.7714	51.8022	5.5900	1.1864	17.6668	
Cr2O3	1.4616	0.1842	0.1500	151.9974	0.0012	0.0814	37.3600	0.0304	0.4527	
B2O3*	3.2201	9.9093	10.3300	69.6204	0.1423	9.5583	-9.9300	-0.9491	-14.1337	
UO2	1.1344			270.0388	0.0000	0.0000	-6.8000	0.0000	0.0000	
ThO2	1.1379			264.0400	0.0000	0.0000	-2.5330	0.0000	0.0000	
SnO	1.1826	0.0047		103.6194	0.0000	0.0031	-24.4000	-0.0007	-0.0111	
ZrO2	1.3508	0.0419	0.0450	123.2188	0.0003	0.0228	45.1000	0.0103	0.1533	
TiO2	1.6680	0.6822	0.6800	79.8988	0.0085	0.5734	15.9900	0.0917	1.3653	
K2O (AA)	1.2046	3.5777	3.4100	94.2034	0.0380	2.5504	-41.7350	-1.0644	-15.8501	
Cs2O	1.0502	0.0600	0.0600	281.8094	0.0002	0.0143	-46.8200	-0.0067	-0.0997	
Sn2O3	1.1970			291.4982	0.0000	0.0000	0.0000	0.0000	0.0000	
P2O5	2.2910	0.0321		141.9370	0.0002	0.0152	-53.6200	-0.0081	-0.1212	
Nd2O3	1.1660	0.0600	0.0600	336.4782	0.0002	0.0120	-28.3200	-0.0034	-0.0505	
La2O3	1.1728	0.0188		325.8100	0.0001	0.0039	-31.1400	-0.0012	-0.0179	
Y2O3	1.2699			225.8082	0.0000	0.0000	-12.9500	0.0000	0.0000	
BaO	1.1165	0.1976	0.2000	153.3394	0.0013	0.0865	-30.5700	-0.0265	-0.3940	
PbO	1.0772			223.1900	0.0000	0.0000	-8.8100	0.0000	0.0000	
CeO2	1.2284			172.1200	0.0000	0.0000	11.3450	0.0000	0.0000	
Mn2O3	1.5003	0.0825	0.0800	143.9382	0.0006	0.0385	-21.7500	-0.0084	-0.1247	
ZnO	1.2447	0.1195		81.3800	0.0015	0.0886	-2.4000	-0.0024	-0.0352	
CoO	1.1423									
QO	1.2518	0.4093	0.4200	79.5454	0.0051	0.3456	1.7900	0.0062	0.0921	
Fe2+/Fe3+	0.08									
SUMS	52.6030	98.6950	99.3941		1.4891	100.0000				
							SUM + pH Si	-6.4258	-95.6872	
							SUM + pH B	-6.4258		
							pH (PCT) =			

NA = NOT ANALYZED

BDL = BELOW DETECTION LEVEL

GLASS ID = PUREX STANDARD-B

(SPREADSHEET REVISION 5.0, OCTOBER 23, 1990)

ELEMENT	GRAV	OXIDE	CGW/NOMINAL	M.W.	MOLE	NORM OXIDE	COMPONENT	FREE ENERGY	FREE ENERGY	KCAL/KG
WT%	FACTOR	WT%	OXIDE WT%		FRACTION	MOLE %	FREE ENERGY	HYDRATION		
Al2O3*	1.4930	3.0185	2.9900	101.9600	0.0296	1.9769	3.0400	0.0601	0.9000	
CaO	1.3992	1.0662	1.0900	56.0794	0.0180	1.2696	-16.1160	-0.2046	-3.0640	
Fe2O3	1.4297	12.3590	13.2500	159.6922	0.0774	5.1681	15.5000	0.8011	11.9958	
FeO	1.2865	0.8897		71.8464	0.0124	0.9269	-14.6090	-0.1208	-1.8091	
MgO	1.6583	1.3681	1.4100	40.3114	0.0339	2.2663	-13.8880	-0.3147	-4.7133	
MnO	1.2912	1.6540	1.6891	70.9374	0.0233	1.5570	-14.8710	-0.2315	-3.4674	
Na2O (AA)	1.3480	12.3881	12.6200	61.9790	0.1999	13.3474	-28.8150	-3.8460	-57.5943	
Li2O	2.1525	3.2180	3.2200	29.8774	0.1077	7.1924	-22.7400	-1.6356	-24.4924	
NbO	1.2728	1.2141	1.1900	74.7094	0.0163	1.0852	-14.3470	-0.1557	-2.3315	
SiO2*	2.1393	46.3533	46.5000	60.0848	0.7715	51.5170	5.5900	1.1607	17.6810	
Cr2O3	1.4616	0.2105	0.1500	151.9974	0.0014	0.0925	37.3600	0.0345	0.5173	
B2O3*	3.2201	10.2986	10.3300	69.6204	0.1479	9.8782	-9.9300	-0.9809	-14.6890	
UO2	1.1344			270.0388	0.0000	0.0000	-6.8000	0.0000	0.0000	
ThO2	1.1379			264.0400	0.0000	0.0000	-2.5330	0.0000	0.0000	
SiO	1.1926	0.0012		103.6194	0.0000	0.0008	-24.4000	-0.0002	-0.0028	
ZrO2	1.3508	0.0365	0.0450	123.2188	0.0003	0.0198	45.1000	0.0089	0.1335	
TiO2	1.6680	0.6739	0.6800	79.8988	0.0084	0.5632	15.9900	0.0901	1.3486	
K2O (AA)	1.2046	3.6740	3.4100	94.2034	0.0390	2.6044	-41.7350	-1.0870	-16.2771	
CaO	1.0602	0.0600	0.0600	281.8094	0.0002	0.0142	-46.8200	-0.0067	-0.0997	
SiO2O3	1.1970			291.4882	0.0000	0.0000	0.0000	0.0000	0.0000	
P2O5	2.2910	0.0619		141.9370	0.0004	0.0291	-53.6200	-0.0156	-0.2337	
Na2O3	1.1660	0.0600	0.0600	336.4782	0.0002	0.0119	-28.3200	-0.0034	-0.0505	
La2O3	1.1728	0.0059		325.8100	0.0000	0.0012	-31.1400	-0.0004	-0.0056	
Y2O3	1.2699			225.8082	0.0000	0.0000	-12.9500	0.0000	0.0000	
B2O	1.1165	0.1965	0.2000	153.3394	0.0013	0.0856	-30.5700	-0.0262	-0.3918	
PbO	1.0772			223.1900	0.0000	0.0000	-8.8100	0.0000	0.0000	
CaO2	1.2284			172.1200	0.0000	0.0000	11.3450	0.0000	0.0000	
MnO3	1.5003	0.0765	0.0800	143.9382	0.0005	0.0355	-21.7500	-0.0077	-0.1156	
ZrO	1.2447	0.1531		81.3800	0.0019	0.1256	-2.4000	-0.0030	-0.0452	
CoO	1.1423									
UO	1.2518	0.3943	0.4200	79.5454	0.0050	0.3310	1.7900	0.0059	0.0887	
Fe2+/Fe3+										
SUMS	52.8980	99.4317	99.3941		1.4975	100.0000				
							SUM + pH Si	-6.4587	-96.7179	
							SUM + pH B	-6.4587		
							pH (PCT) =	-6.4587		

NA = NOT ANALYZED

BDL = BELOW DETECTION LEVEL

This page intentionally left blank.

END

**DATE
FILMED
9 / 3 / 92**