1st Quarter
88

Do

DOE/PC/79812--T9

DE92 018422

CONTRACT IDENTIFICATION: THE DEVELOPMENT OF PRECIPITATED IRON CATALYSTS WITH IMPROVED STABILITY	REPORTING PERIOD: 12/16/87 - 3/16/88	CONTRACT NUMBER: DE-AC22-87PC79812
CONTRACTOR: Signal Research Center Inc. 50 E. Algonquin Rd., Box 5016 Des Plaines, IL 60017-5016	REPORT SUBMITTED BY: Mayim Abrevaya, Principal Investigator	CONTRACT START DATE: September 16, 1987
		CONTRACT COMPLETION DATE: September 16, 1989

TECHNICAL PROGRESS REPORT

ABSTRACT

This program has the objective of developing a precipitated iron Fischer-Tropsch catalyst with improved stability. During this second quarter of the program most of the work was done under Task 3 which involves the development of a baseline iron catalyst. Under this task, several Fe/Cu catalysts were prepared by precipitation at different pH levels between 3 and 10. These catalysts were characterized by STEM, XRD, DSC, TGA, TPR and N₂ adsorption in order to examine precipitation pH, copper level, calcination and reduction temperature requirements for the baseline iron catalyst. Work during the next quarter will focus on the design of the slurry reactor system for testing the precipitated iron catalysts.

OBJECTIVE

The objective of this program is to develop a precipitated iron Fischer-Tropsch catalyst with improved stability suitable for slurry reactors.

ENTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

INTRODUCTION

Precipitated iron catalysts are expected to be used in next generation slurry reactors for large scale production of transportation fuels from synthesis gas. These reactors are expected to operate at higher temperatures and lower $H_2:CO$ ratios relative to the Sasol Arge reactor. Iron catalysts' feasibility has been demonstrated under relatively mild Arge-type conditions but not under more severe slurry conditions. It is expected that a major improvement in catalytic stability will be needed to make iron catalysts suitable for slurry operation.

This program is aimed at identifying the chemical principles governing the deactivation of precipitated iron catalysts during Fischer-Tropsch synthesis and to use these chemical principles in the design of more stable catalysts.

The program has been divided into five major tasks to be conducted over a two-year period. The description of these tasks are described below:

Task 1: Upgrade the existing fixed-bed pilot plant with slurry and Berty reactor testing capabilities.

Task 2: Establish the stability of a state-of-the-art reference precipitated iron catalyst.

Task 3: Construct an iron catalyst preparation plant and develop a baseline iron catalyst.

Task 4: Elucidate the deactivation chemistry for iron catalysts.

Task 5: Modify the catalyst chemistry to improve its stability.

Work has been initiated in Tasks 1 and 3. Most of the work was done under Task 3 and this is going to be described later in the report.

EXPERIMENTAL

Under Task 3, preliminary catalyst preparation equipment was built in the laboratory for determining the significance of various catalyst preparation parameters. This data will then be used for final design of the catalyst preparation equipment.

Several Fe/Cu catalysts were prepared at different pH levels by co-precipitation of the nitrates of iron and copper with Na_2CO_3 solution. The precipitates were washed with water, dried and then calcined. The catalysts were examined by STEM (scanning transmission electron microscopy), XRD (x-ray diffraction), DCS (differential scanning calorimetry), TGA (thermogravimetric analysis) TPR (temperature programmed reduction) and nitrogen adsorption.

RESULTS AND DISCUSSION

1. Determination of pH's for Precipitating Iron and Copper

An $\text{Fe}(\text{NO}_3)_3$ solution with 5.0 wt.% Fe was titrated against 1N solutions of Na_2CO_3 and NH_4OH at room temperature (Figures 1 and 2). In both cases, it was determined that precipitation of iron started to occur at a pH of about 2. Similarly, a solution of $\text{Cu}(\text{NO}_3)_2$ with 0.5 wt.% Cu started to precipitate at a pH of about 5 (Figures 3 and 4). However, it was also determined that in the presence of $\text{Fe}(\text{NO}_3)_3$, $\text{Cu}(\text{NO}_3)_2$ precipitated at lower pH's.

2. Description of DSC and TGA Experiments

Catalyst 5685-61 was prepared by co-precipitation of $\text{Fe}(\text{NO}_3)_3$ and $\text{Cu}(\text{NO}_3)_2$ solutions with a Na_2CO_3 solution (100 Fe:1Cu, by wt.) at a pH of 3.5. According to STEM examination of the catalyst after drying at 110°C , the catalyst was made up 2-4nm amorphous Fe-Cu particles. Another catalyst 5685-53 (100 Fe:1Cu) precipitated with Na_2CO_3 at a pH of 4.3 showed similar morphology to catalyst 5685-61. These two catalysts were used for establishing reproducibility of DSC (differential scanning calorimetry) experiments which are useful for determining the calcination temperature requirement of Fe-Cu catalysts.

In DSC experiments, the uncalcined catalyst is heated from room temperature to 600°C at $5^\circ\text{C}/\text{min}$ under air flow and the heat flow to or from the catalyst is measured. The results obtained with catalyst 5685-53 in two separate runs are described in Figure 5. A minimum in the DSC curve indicates the occurrence of an endothermic reaction. The minimum at $40\text{-}50^\circ\text{C}$ is probably related to water evolution from the catalyst. A maximum in the DSC curve indicates the occurrence of an exothermic reaction. The maximum observed at about 390°C is probably related to the formation of Fe_2O_3 from Goethite, $\alpha\text{-FeO}(\text{OH})$, which apparently illustrates the calcination temperature requirement for the catalyst. There appears to be a secondary maxima at about 200°C . It is not presently clear whether the presence of multiple maxima indicates the presence of catalyst particles with different calcination temperature requirements or whether it indicates that calcination is a multi-step process.

The results summarized in Figure 5 also indicate that the DSC experiments were quite reproducible with no more than 5°C difference between the calcination temperature requirements measured in two separate runs with the same catalyst.

Catalyst 5685-53 was also evaluated in a TGA (thermogravimetric analysis) experiment which involves measuring the percent weight loss as the catalyst is heated

up to 600°C at 5°C/min under air flow (Figure 6). The TGA experiment also provides the derivative of the catalyst weight loss with respect to time. A maximum in the derivative curve illustrates the temperature at which the rate of weight loss becomes maximum. Three maximas, at 56°C, 217°C and 360°C, were observed which may correspond to the minimum and maxima observed in the DSC experiments at 40-50°C, 200°C and 390°C. It is not presently clear why the high temperature maxima (or minimum) differ by 20-50°C between the DSC and TGA experiments.

During the TGA experiment, catalyst 5685-53 lost about 12% weight between 100°C, the temperature at which significant fraction of the free water should have evolved and 600°C. It is important to note that 12.4% weight loss would occur for $2\text{FeO}(\text{OH}) \rightarrow \text{Fe}_2\text{O}_3 + \text{H}_2\text{O}$ reaction, which presumably is the major calcination reaction.

The DSC results obtained with catalyst 5685-61 in two separate runs and the TGA results are described in Figures 7 and 8. For this catalyst, the secondary maximum at about 250°C is less apparent. Also the high temperature maximum occurs at a lower temperature. These DSC results again indicate that these experiments are quite reproducible, but this time the high temperature maxima for duplicate measurements on the same catalyst were 12°C apart.

3. Description of TPR Experiments

Catalyst 5685-145 with 100Fe:1Cu (by wt.) was prepared by co-precipitation of $\text{Fe}(\text{NO}_3)_3$ and $\text{Cu}(\text{NO}_3)_2$ with a Na_2CO_3 solution at a pH of 6.5, followed by drying at 110°C and calcining at 410°C. Based on XRD (x-ray diffraction) measurements on a similar catalyst, we expect the Fe-Cu crystallite size in this catalyst to be between 60Å and 110Å. Catalyst 5685-145 was used for establishing reproducibility of TPR (temperature programmed reduction) experiments, which are useful for determining the reduction temperature requirement of Fe-Cu catalysts.

In TPR experiments, the calcined catalyst is heated from room temperature to 800°C at 2°C/min under 5% H₂ in Argon flow and the uptake of H₂ is measured. The results obtained with catalyst 5685-145 in two separate runs are described in Figure 9.

The first major TPR peak occurs between 140°C and 160°C. In an attempt to identify the crystalline phases present at 150°C another portion of catalyst 5685-145 was heated from room temperature to 150°C in 2 hours under 5% H₂ in Argon flow, maintained at 150°C for 1 more hour and then analyzed by XRD (Figure 10). Magnetite (Fe₃O₄) phase was observed to be present along with Maghemite (γ-Fe₂O₃) phase.

It is important to mention that the peak between 140°C and 160°C was equivalent to about 0.15 mmole H₂/g catalyst. Since this catalyst contains 0.11 mmole Cu/g catalyst, the TPR peak at 140-160°C may be partly attributed to the reduction of copper.

The second major TPR peak occurs between 160°C and 200°C. A portion of catalyst 5685-145 heated to 250°C under 5% H₂ in Argon flow in 4 hours and maintained there for 1 more hour showed only Magnetite phase, but no Fe₂O₃ (Figure 11).

The third major TPR peak occurs between 200°C and 680°C. At higher temperatures further H₂ uptake occurs. A portion of catalyst 5685-145 was heated to 800°C under 5% H₂ in Argon flow in 6.5 hours and held there for 1 more hour. This catalyst showed metallic iron (α-Fe) along with Wustite (α-FeO). (Figure 12).

These results suggest that reduction of Fe-Cu catalyst may be occurring, at least, in three steps at specified temperature ranges.

It is not presently clear why there may be two peaks associated with Fe_3O_4 formation from Fe_2O_3 .

The results summarized in Figure 9 indicate that duplicate TPR results obtained with the same catalyst are quite reproducible with no more than 10°C difference between the position of each corresponding TPR maxima.

TPR results show that complete reduction of Fe-Cu catalysts require temperatures in excess of 800°C . However, it is well established that temperatures higher than 300°C are not typically required to generate active catalysts. This suggests that reduction of the catalyst surface relative to the bulk occurs at much lower temperatures, as also discussed by M. P. Rosynek et al. from Texas A & M University under the work done in Contract DE-AC22-85PC8001 (Quarterly Technical Progress Report for January 1, 1988 to March 31, 1988). TPR experiments are nevertheless useful for monitoring differences between different Fe-Cu catalysts since reduction behavior of these catalysts, as examined by TPR, is expected to vary sensitively with their chemical and morphological properties.

4. Use of DSC for Determining Calcination Temperature Requirement for Fe-Cu Catalysts.

It was previously described that DSC measurements on 100Fe: 1Cu catalyst 5685-53 precipitated at pH = 4.3 showed a high temperature maximum peak at about 390°C . Another catalyst precipitated at the same pH of 4.3 was calcined at 275°C for 2 hours. XRD measurements showed this catalyst to have 37.8% crystalline $\alpha\text{-Fe}_2\text{O}_3$ only. A portion of catalyst 5685-53 calcined at 380°C and another portion calcined at 450°C showed 79% and 80% $\alpha\text{-Fe}_2\text{O}_3$, which was the only detected crystalline phase. These results indicate that essentially maximum crystalline $\alpha\text{-Fe}_2\text{O}_3$ is obtained when calcination is done at the temperature which corresponds to the high temperature maximum in the DSC measurement and that the amount of $\alpha\text{-Fe}_2\text{O}_3$ does not significantly

increase at higher calcination temperatures. Since neither according to DSC, nor according to XRD measurements, any phase transformation seems to take place in the Fe-Cu catalyst at temperatures higher than that which corresponds to the high temperature maximum in the DSC experiment ($=T_c$) there may not be a need to choose a calcination temperature higher than T_c .

Catalyst 5685-75 (100Fe:1Cu, by wt.), on the other hand, was prepared by co-precipitation of $\text{Fe}(\text{NO}_3)_3$ and $\text{Cu}(\text{NO}_3)_2$ with a solution of Na_2CO_3 at a pH = 9.7. DSC measurement on this catalyst showed a high temperature maximum at 443°C (Figure 13). A portion of this catalyst was calcined at 380°C and another portion at 450°C, each for 2 hours. XRD measurements showed the catalyst calcined at 380°C to be 77% $\alpha\text{-Fe}_2\text{O}_3$, and the catalyst calcined at 450°C to be 87% $\alpha\text{-Fe}_2\text{O}_3$. These results again indicate that the amount of $\alpha\text{-Fe}_2\text{O}_3$ is maximized when calcination is done at the high temperature DSC maximum.

Experiments were later conducted with catalysts 5685-111 and 5685-61 to determine whether an extended low temperature calcination would lower the final calcination temperature requirement. Catalyst 5685-111 was prepared by co-precipitating $\text{Fe}(\text{NO}_3)_3$ and $\text{Cu}(\text{NO}_3)_2$ (100 Fe:1 Cu) at a pH = 9.5 with ammonia solution. For this catalyst, the high temperature DSC maximum occurred at 458°C (Figure 14). During another DSC experiment, this catalyst was brought to 347°C at 5°C/min, and then maintained isothermally for 1.5 more hours (Figure 15). The catalyst was then subjected to a standard DSC experiment, which indicated the high temperature DSC peak position and shape had not essentially changed (Figure 16).

Catalyst 5685-61, however, which had a maximum DSC peak at about 380°C was brought to 350°C during the DSC experiment and then maintained isothermally for 2 more hours (Figure 17). A subsequent standard DSC experiment did not show the 380°C peak anymore (Figure 18).

These two sets of results show that a low temperature calcination may lower the final calcination temperature requirement when the first calcination temperature is 30°C lower but not when it is 100°C lower than the temperature at which the maximum in the DSC curve appears.

5. Effect of Calcination Temperature

Two separate portions each of 100 Fe:1Cu catalysts 5685-53 and 5685-75 prepared at pH=4.3 and 9.7, respectively, were calcined at 380°C and 450°C, and later examined by STEM, TPR and N₂ adsorption in order to determine the effect of calcination temperature on Fe-Cu catalysts.

Catalyst prepared at pH=4.3 and calcined at 380°C showed 4-6 nm Fe-Cu particles in the STEM examination, while the particle size was much larger, i.e., 5-20 nm, for the catalyst calcined at 450°C. Similarly, the particle size increased from 5-40 nm to 10-40 nm when the calcination temperature was increased from 380°C to 450°C with catalyst prepared at pH=9.7.

N₂ adsorption measurements on pH=4.3 catalyst calcined at 380°C and 450°C are summarized in Figures 19-21. The results indicate that higher temperature calcination decreases the total pore volume from 0.22 to 0.17cc/g, increases the average pore radius from 52 to 62Å and decreases the total surface area from 83 to 53 m²/g. Similarly for pH=9.7 catalysts, it was determined that higher temperature calcination decreases the total pore volume from 0.19 to 0.18cc/g, increases the average pore radius from 52 to 89Å and decreases the total surface area from 74 to 41m²/g. (Figures 22-24)

Results of TPR experiments with two different portions of catalyst 5685-53 precipitated at pH=4.3 are summarized in Figure 25. The following differences were found with the portion calcined at 450°C relative to the portion calcined at 380°C.

1. The low temperature TPR peak which seems to be related to the $\text{Fe}_2\text{O}_3 \rightarrow \text{Fe}_3\text{O}_4$ reaction increased in magnitude and also shifted to 20°C lower temperature.
2. The TPR peak between 350 and 700°C expanded by 20°C to higher temperature and increased in magnitude.

These results indicate that selection of suitable calcination temperatures for Fe-Cu catalysts is very important since morphological properties of iron catalysts, as determined by STEM and N_2 adsorption, are influenced significantly by the calcination temperature. Furthermore, variations in TPR spectra also were observed with changes in calcination temperature, which suggest that chemical properties of catalysts may also have been influenced by calcination temperature.

6. Effect of pH

Six catalysts were prepared by precipitation of solutions containing $\text{Fe}(\text{NO}_3)_3$ and $\text{Cu}(\text{NO}_3)_2$ (100 Fe:1Cu) with Na_2CO_3 solution at pH = 3.5, 4.3, 5.5, 6.5, 7.9 and 9.7, respectively. These catalysts were characterized by DSC, TGA, STEM, TPR and XRD in order to evaluate the effect of pH of precipitation on Fe/Cu catalysts.

Catalysts 5685-61, 5685-53, 5709-73 and 5709-49 precipitated at pH = 3.5, 4.3, 5.5 and 6.5, respectively, and dried at 110°C showed amorphous looking Fe-Cu particles of 2-4nm in the STEM examination (Figures 26 and 27). Catalyst 5685-69 precipitated at pH=7.9, on the other hand, had 20-35% crystalline material with 10-20nm Fe-Cu particles (Figure 28). The rest of the catalyst was amorphous with 2-4nm particles. Catalyst 5685-75 precipitated at a higher pH of 9.7 was 35-45% crystalline with 10-40nm Fe-Cu particles (Figure 28). In order to identify the nature of the crystalline material catalyst 5685-75 was also analyzed by XRD which indicated 30.1% of the catalyst to be crystalline $\alpha\text{-Fe}_2\text{O}_3$. A minor amount of Goethite phase was also detected in XRD (Figure 29).

Since high pH catalysts showed increased amounts of crystalline Fe_2O_3 with large iron particles, a low pH and a high pH catalyst were calcined, and then analyzed by STEM in order to determine whether differences in catalyst morphology observed after the 110°C drying step still existed after calcination. The STEM micrographs for pH=4.3 and pH=9.7 catalysts after calcination at 380°C and 450°C are in Figures 30 and 31. Low pH catalyst was composed of 4-6nm Fe-Cu particles after calcination at 380°C, while the high pH catalyst was composed of 5-40nm particles. Similarly after 450°C calcination the low pH catalyst had 5-20nm particles, while the high pH catalyst had 10-40nm particles. These results indicate that the Fe-Cu particle size increases with increase in pH of precipitation and these differences persist through the calcination step.

Catalysts precipitated at pH=3.5, 4.3, 7.9 and 9.7 were also examined by DSC, after the drying step at 110°C (Figure 32). The minima observed at 40-50°C are probably related to water evolution. The high temperature DSC maximum peak decreases in magnitude and shifts to higher temperature from 367°C to 444°C with increase in pH from 3.5 to 9.7. All catalysts, regardless of pH, have a secondary maximum at about 250°C. Catalysts with pH=7.9 and 9.7 have also a low temperature maximum at about 100°C, but catalysts with pH=3.5 and 4.3 don't. It appears that the DSC maximum at about 100°C is related to the formation of large iron oxide particles that are observed during STEM examination of the high pH catalysts which were dried at 110°C.

It is important to indicate that high pH catalysts that were dried at 110°C lost less weight during the TGA experiment between 100°C and 600°C, relative to low pH catalysts :5.3% for pH=7.9 catalyst and 4.0% for pH=9.7 catalyst relative to 12% for pH=3.5 and 4.3 catalysts (Figures 6, 8, 33 and 34). Less weight loss during the TGA experiments with high pH catalysts that were dried at 110°C relative to low pH catalysts that were dried at 110°C is expected since significant fraction of $2\text{FeO}(\text{OH})$ ---> $\text{Fe}_2\text{O}_3 + \text{H}_2\text{O}$ reaction with high pH catalysts seems to occur during the 110°C drying step before the TGA experiments.

DSC and TGA experiments show distinct features for catalysts precipitated at different pH's, indicating that the properties of iron catalysts are significantly influenced by pH of precipitation. We, therefore, suggest that DSC and TGA techniques may play a key role, in the future, for characterization of Fe-Cu catalysts.

The effect of pH of precipitation on the properties of Fe-Cu catalysts was further demonstrated by the TPR experiments (Figures 35 and 36). TPR experiments show that pH=9.7 catalysts could be reduced at lower temperatures relative to pH=4.5 catalysts, regardless of the calcination temperature. It is not presently clear whether these differences in reducibility of Fe-Cu catalysts precipitated at different pH's are mainly caused by differences in the catalyst particle sizes that were previously discussed.

7. Effect Of Cu Level

Three catalysts were prepared by co-precipitation of solutions containing different ratios of $\text{Fe}(\text{NO}_3)_3$ and $\text{Cu}(\text{NO}_3)_2$ (100 Fe:0.5 Cu, 100 Fe:1 Cu, 100 Fe:5 Cu, by wt.) with Na_2CO_3 solution at a pH=6.1-6.5. A fourth catalyst with 100 Fe:5 Cu was precipitated at pH=9.5. These catalysts were characterized by DSC, TGA, STEM, XRD and TPR in order to evaluate the effect of copper level.

Catalyst 5685-139 with 100 Fe:0.5 Cu showed, in the STEM examination, partly crystalline morphology with 2-6nm particles after the 110°C drying step (Figure 37). XRD analysis of the same catalyst indicated these crystallites to be Goethite (Figure 38). It is interesting to note that, as explained above, crystallites observed with high pH catalysts (7.9 and 9.5) after 110°C drying were Hematite ($\alpha\text{-Fe}_2\text{O}_3$) and not Goethite ($\alpha\text{-FeO}(\text{OH})$).

Catalysts 5709-49 and 5685-135 with 100 Fe:1 Cu and 100 Fe:5 Cu, respectively, did not show crystallites and had amorphous looking 2-4nm particles (Figure 37 and 39). These results indicate that copper may suppress the formation of Goethite at 110°C.

Since large Hematite particles would result from large Goethite particles during calcination, the copper level may be a key variable to control Fe-Cu particle size in the finished catalyst.

Since large Hematite particles were formed at 110°C with high pH catalysts and copper suppressed the formation of large Goethite particles at the same temperature, a high pH catalyst was prepared to determine whether formation of large Hematite particles could be prevented by the use of a high copper level. Catalyst 5709-37 with 100 Fe:5 Cu was prepared at pH=9.5. This catalyst was amorphous which indicates that high copper level, indeed, suppressed the formation of large Hematite particles at 110°C (Figure 39).

The high and low Cu catalysts 5685-139 (100 Fe:0.5 Cu) and 5685-135 (100 Fe:5 Cu) precipitated at pH=6.1-6.5 showed also different features in the DSC and TGA experiments (Figures 40 and 41). The significance of these features are going to be evaluated in the future. It is important to note that the weight loss between 100°C and 600°C with the low copper catalyst which did not have Hematite (α -Fe₂O₃), but only Goethite (α -FeO(OH)), crystallites was about 12%, which is similar to the weight loss observed with low pH samples with no Hematite crystallites. These two sets of results are consistent since the weight loss during the TGA experiments between 100°C and 600°C probably is attributed to the formation of Hematite from FeO(OH). It is not presently clear why the weight loss is less with the high copper catalyst since that catalyst did not show Hematite formation at 110°C.

Catalysts 5685-139, 5685-61 and 5685-135 with 100 Fe:0.5 Cu, 100 Fe:1 Cu and 100 Fe:5 Cu, respectively, were all calcined at 410°C, and then examined by TPR (Figure 42). The low temperature peaks between 100°C and 180°C are probably related to the onset of Fe₃O₄ formation or to the reduction of copper, as discussed above. The position of the low temperature peak decreased in temperature as the copper level increased.

The higher temperature peaks between 180°C and 210°C are apparently related to Fe_3O_4 formation reaction. These peak positions were similar for catalysts with 100 Fe:5 Cu and 100 Fe:1 Cu, but occurred at a higher temperature with catalyst having 100 Fe:0.5 Cu. These results are consistent with those obtained by other investigators and suggest that copper may enhance the reduction of Fe_2O_3 to Fe_3O_4 .

The portions of the TPR experiments at temperatures higher than 250°C, which involve reduction of Fe_3O_4 to metallic iron via FeO formation were different with the three catalysts containing different levels of copper. However, no obvious trend in the ease of reduction to metallic iron with copper level was observed.

8. Effect Of Potassium

Catalysts 5685-139 with 100 Fe:0.5 Cu and catalyst 5685-135 with 100 Fe:5 Cu were impregnated with 0.2% and 0.4% K (in the form of K_2CO_3) respectively. The TPR behavior of these catalysts were compared before and after K impregnation. Results summarized in Figures 43 and 44 indicate that, while potassium may inhibit the reduction of Fe_2O_3 to Fe_3O_4 , it certainly enhances reduction of Fe_3O_4 to metallic Fe.

9. Catalysts Precipitated With NH_4OH

Different DSC features of 100Fe:1 Cu catalysts 5685-75 and 5685-111 prepared by precipitation at pH=9.5-9.7 using Na_2CO_3 and NH_4OH solutions, respectively, were previously described (Figures 13 and 14). STEM examination of these catalysts after 110°C drying indicated that while Na_2CO_3 - derived catalyst was partly crystalline with 10-40nm Fe-Cu particles, NH_4OH derived catalyst had only amorphous looking particles, no larger than 2-4nm. These two catalysts were later calcined at 450°C, and further characterized in order to determine whether differences between these two catalysts would continue to exist through the catalyst finishing steps. STEM examination

indicated that, while the average Fe-Cu particle size was approximately the same with both catalysts, the particle size distribution was wider with Na_2CO_3 -derived catalyst (100-400 Å) relative to NH_4OH -derived catalyst (250-300 Å) (Figure 55). According to TPR experiments, while Fe_3O_4 formation seems to have shifted to about 20°C higher temperature, reduction to metallic iron seems to have been enhanced with the NH_4OH -derived catalyst (Figure 45).

SUMMARY

1. A pH of at least 2 is required to precipitate an iron nitrate solution by using sodium carbonate or ammonia solutions, while a pH of at least 5 is required to precipitate copper nitrate solution. However, in the presence of iron nitrate, precipitation of copper occurs at lower pH's.
2. Increase in calcination temperature decreases the surface area and pore volume of precipitated Fe-Cu catalysts. Therefore, the calcination temperature should be no higher than that required for forming Fe_2O_3 from $\text{FeO}(\text{OH})$.
3. Amount of crystalline Fe_2O_3 in a precipitated Fe-Cu catalyst is maximized when calcination is conducted at the high temperature maximum in the DSC curve. This suggests that DSC experiments may be useful for determining the calcination temperature requirement for Fe-Cu catalysts.
4. According to DSC measurements, the calcination temperature requirement for precipitated 100 Fe:1 Cu catalysts prepared from Na_2CO_3 increased from about 380°C to about 450°C as the pH of precipitation increased from 3.5 to 9.5.

5. Na_2CO_3 -derived Fe-Cu catalysts prepared at $\text{pH} \leq 6.5$ had small amorphous particles while catalysts prepared at $\text{pH} \geq 7.9$ were increasingly crystalline with large Hematite ($\alpha\text{-Fe}_2\text{O}_3$) particles, after 110°C drying. These morphological differences remained through the calcination step. This indicates that pH of precipitation is the key variable for controlling the Fe-Cu particle size.
6. Na_2CO_3 -derived 100 Fe:0.5 Cu catalyst prepared at $\text{pH}=6.5$ had large Goethite ($\alpha\text{-FeO(OH)}$) particles, while 100Fe:1 Cu and 100 Fe:5 Cu catalysts prepared at same pH had small amorphous particles. Since large Goethite particles would lead to large Hematite particles during calcination the copper level may also be a key variable for controlling the Fe-Cu particle size.
7. Formation of Fe_3O_4 from Fe_2O_3 occurred at a lower temperatures with Na_2CO_3 -derived 100 Fe:5 Cu and 100 Fe:1 Cu catalysts relative to 100 Fe:0.5 Cu catalyst prepared at $\text{pH}=6.1\text{-}6.5$. This indicates that copper enhances reduction of Fe_2O_3 to Fe_3O_4 .
8. Formation of Fe_3O_4 from Fe_2O_3 occurred at a higher temperature while formation of metallic iron from Fe_3O_4 occurred at a lower temperature after K_2CO_3 impregnation of Na_2CO_3 -derived catalysts prepared at $\text{pH}=6.1\text{-}6.5$. This indicates that, while K may inhibit the reduction of Fe_2O_3 to Fe_3O_4 , it may enhance the reduction of Fe_3O_4 to metallic Fe.
9. NH_4OH -derived 100 Fe:1 Cu catalyst precipitated at $\text{pH}=9.5$ had small amorphous particles, while Na_2CO_3 -derived catalyst prepared at the same pH had large Hematite particles after 110°C drying. However, after 450°C calcination the average particle sizes were similar for both catalysts. This indicates that the use of NH_4OH relative to Na_2CO_3 does not provide an obvious advantage.

10. Complete reduction of precipitated Fe-Cu catalysts require temperatures in excess of 800°C. Since it is fairly well established that reduction temperatures no higher than 300°C can lead to very active catalysts, the reduction of Fe-Cu catalyst surface must be occurring at much lower temperatures than temperatures required for bulk reduction.

FUTURE PLAN

Work during the next quarter will focus on the design of the slurry reactor system for testing the precipitated iron catalysts

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

FIGURE 1: TITRATION OF $\text{Fe}(\text{NO}_3)_3$ SOLUTION (5 WT.% Fe^{3+} WITH 1N Na_2CO_3 SOLUTION

FIGURE 2: TITRATION OF $\text{Fe}(\text{NO}_3)_3$ SOLUTION (5 WT.% Fe) WITH 1N NH_4OH SOLUTION

FIGURE 3: TITRATION OF $\text{Cu}(\text{NO}_3)_2$ SOLUTION (0.5 WT.%) WITH 1N Na_2CO_3 SOLUTION

FIGURE 4: TITRATION $\text{Cu}(\text{NO}_3)_2$ SOLUTION (0.5 WT. % Cu) WITH 1N NH_4OH SOLUTION

FIGURE 5: REPRODUCIBILITY OF DSC EXPERIMENTS WITH pH=4.3 CATALYST 5685-53

FIGURE 6: TGA OF pH=4.3 CATALYST 5685-53

FIGURE 7: REPRODUCIBILITY OF DSC EXPERIMENTS WITH pH=3.5 CATALYST 5685-61

FIGURE 8: TGA OF pH=3.5 CATALYST 5685-6i

FIGURE 9: REPRODUCIBILITY OF TPR FOR Fe/Cu CATALYSTS (5685-145)

FIGURE 10: XRD OF PH-6.5 CATALYST 5685-145 AFTER H₂ TREATMENT AT 150°C

FIGURE 11: XRD OF pH=6.5 CATALYST 5685-145 AFTER H₂ TREATMENT AT 250°C

FIGURE 12: XRD OF PH=6.5 CATALYST 5685-145 AFTER H₂ TREATMENT AT 800°C

FIGURE 13: DSC OF pH=9.7 CATALYST 5685-75 PRECIPITATED BY Na_2CO_3

FIGURE 14: DSC OF pH=9.5 CATALYST 5685-111 PRECIPITATED BY NH_4OH

General V2.2A DuPont 9900

FIGURE 15: ISOTHERMAL DSC AT 350°C OF pH=9.5 CATALYST 5685-111 PRECIPITATED BY NH_4OH

FIGURE 16: STANDARD DSC AFTER ISOTHERMAL DSC OF pH=9.5 CATALYST 5685-111 PRECIPITATED
BY NH_4OH

FIGURE 17: ISOTHERMAL DSC AT 350°C OF pH=3.5 CATALYST 5685-61

FIGURE 18: STANDARD DSC AFTER ISOTHERMAL DSC OF pH=3.5 CATALYST 5685-61

QUANTA CHROME

FIGURE 19: CUMULATIVE PORE VOLUME WITH PH-4.3 CATALYSTS CALCINED AT 380°C AND 450°C

FIGURE 20: PORE SIZE DISTRIBUTION WITH pH=4.3 CATALYSTS CALCINED AT 380°C AND 450°C

.1000E-01

$D_v(r) - A \text{ (cc/g-Å)}$

- #5685-137A, 450°C
- ◇ #5885-129A, 380°C

FIGURE 21: CUMULATIVE SURFACE AREA WITH pH=4.3 ACATALYSTS CALCINED AT 380°C AND 450°C

FIGURE 22: CUMULATIVE PORE VOLUME WITH pH=9.7 CATALYSTS CALCINED AT 380°C AND 450°C

AUTOSORB

FIGURE 23: PORE SIZE DISTRIBUTION WITH pH-9.7 CATALYSTS CALCINED AT 380°C AND 450°C

DERIVATIVE OF PORE VOLUME WITH RESPECT TO PORE RADIUS

.1888E-01

$DV(r)-A \text{ (cc/g-A)}$

○ #5685-137B, 450°C
◇ #5685-1298, 380°C

FIGURE 24: CUMULATIVE SURFACE AREA WITH pH-9.7 CATALYSTS CALCINED AT 380°C AD 450°C

FIGURE 25: EFFECT OF CALCINATION TEMPERATURE ON TPR OF Fe/Cu CATALYSTS
PRECIPITATED AT PH 4.3

FIGURE 26: STEM MICROGRAPHS OF pH=3.5 AND pH=4.3 CATALYSTS AFTER 110°C DRYING

pH=4.3

pH=3.5

FIGURE 27: STEM MICROGRAPHS OF pH=5.5 AND pH=6.5 CATALYSTS AFTER 110°C DRYING

pH=5.5

pH=6.5

FIGURE 28: STEM MICROGRAPHS OF pH-7.9 AND pH-9.7 CATALYSTS AFTER 110°C DRYING

pH-7.9

pH-9.7

FIGURE 29: XRD OF pH=9.7 CATALYST AFTER 110°C DRYING

FIGURE 30: STEM MICROGRAPHS OF pH=4.3 AND pH=9.7 CATALYSTS AFTER 380°C CALCINATION

pH=4.3

pH=9.7

FIGURE 31: STEM MICROGRAPHS OF pH-4.3 AND pH-9.7 CATALYSTS AFTER 450°C CALCINATION

DIFFERENTIAL SCANNING CALORIMETRY

FIGURE 32:

Fe/Cu CATALYSTS PRECIPITATED AT DIFFERENT pH'S

FIGURE 33: TGA OF pH=7.9 CATALYST 5685--69

FIGURE 34: TGA OF pH=9.7 CATALYST 5685-75

FIGURE 35: EFFECT OF pH OF PRECIPITATION ON TPR OF Fe/Cu CATALYSTS
CALCINED AT 380C

FIGURE 36: EFFECT OF pH OF PRECIPITATION ON TPR OF Fe/Cu CATALYSTS
CALCINED AT 450C

FIGURE 37: STEM MICROGRAPHS OF 100 Fe:0.5 Cu AND 100 Fe:5Cu CATALYSTS AFTER 110°C

DRYING

Cu LEVEL EFFECT ON PRECIPITATED Fe/Cu CATALYST MORPHOLOGY (110°C DRIED)

5% Cu

100 Fe:5.0 Cu

0.5% Cu

100 Fe:0.5 Cu

FIGURE 38: XRD OF 100 Fe:0.5 Cu CATALYST 5685-139 AFTER 110°C DRYING

FIGURE 39: STEM MICROGRAPH OF 100 Fe:5 Cu CATALYST

FIGURE 40: DSC OF 100 Fe:0.5 Cu AND 100 Fe:5 Cu CATALYSTS

FIGURE 41: TGA OF 100 Fe:0.5 AND 100 Fe:5 Cu CATALYSTS

FIGURE 42: COPPER LEVEL EFFECT ON TPR OF Fe/Cu CATALYSTS
PRECIPITATED AT pH 6.1-6.5

FIGURE 43: EFFECT OF K₂CO₃ IMPREGNATION ON TPR OF Fe/Cu CATALYSTS

Fe TO Cu RATIO 100:1

FIGURE 44: EFFECT OF K₂CO₃ IMPREGNATION ON TPR OF Fe/Cu CATALYSTS
FE TO CU RATIO 100:5

FIGURE 45: STEM MICROGRAPHS OF NH_4OH AND Na_2CO_3 -DERIVED pH=9.5-9.7 CATALYSTS AFTER 110°C DRYING

FIGURE 46: EFFECT OF PRECIPITATION BASE ON TPR OF Fe/Cu CATALYSTS

END

**DATE
FILMED**

9 / 18 / 92