PROGRESS REPORT

**DEPARTMENT OF ENERGY
DE-FG02-84ER45153**

**"Magnetic Properties and Critical Behavior of the
Conductivity Near the M-I Transition"**

For the Period 11/30/91-7/31/92

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

July 1992

**Prepared by:
Professor Myriam Sarachik
Principal Investigator
Department of Physics
The City College of CUNY
Convent Avenue @ 138th Street
New York, NY 10031**

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

PROGRESS REPORT - July 1992

Work continues on both sides of the Metal-Insulator transition. We report the following accomplishments:

Metallic Phase:

(1) A paper appeared in the February 15 issue of Physical Review,¹ and another is scheduled to be published September 15. These contain detailed discussions of the work done for his thesis by Peihua Dai on the transport of metallic Si:B. The first paper is concerned largely with the temperature dependence of the resistivity, and also summarizes the results published in two Physical Review Letter articles^{2,3} of 1991 on the critical conductivity exponent in zero field and in a magnetic field of 7.5T. The second paper is a detailed discussion of the field dependence, and the temperature dependence of the phase breaking lengths derived from these measurements.

(2) We have just completed measurements of the Hall coefficient of metallic Si:B. We find that unlike the n-type materials Si:P and Si:As, where Castner and co-workers claim to have observed a non-diverging Hall coefficient, the Hall coefficient of p-type Si:B appears to diverge as the critical concentration is approached. This is an important experimental finding in an area that has been plagued by controversy. Theoretically, the Hall coefficient is expected to diverge in systems where the metal-insulator transition is driven by electron-electron interactions while, based on work of Shapiro and Abrahams,⁴ it was expected to remain finite when the transition is due to electron localization. However, Wang, Wang, Kotliar and Castellani⁵ have recently claimed that the Hall coefficient should diverge even at a localization

transition, in which case one would expect it to diverge under any circumstances. The experimental situation is, if anything, even murkier. Both diverging and finite Hall coefficients have been observed. In particular, Field and Rosenbaum⁶ found a diverging Hall coefficient in Ge:Sb, while Koon and Castner⁷ claim that it stays finite in Si:P and Si:As. Castner⁸ has suggested that the origin of the difference may be with whether the spin-orbit scattering is strong (diverging R_H) or weak (finite R_H). Our recent results may support this view, since spin-orbit effects are known to be strong in Si:B. Since other comparisons between Si:B and Si:P have failed to reveal any differences associated with strong spin-orbit effects in the former, this would be a most interesting result. An alternative possibility is that, due to the high fields ($>2T$) and high temperatures ($>0.5K$) of Castner's measurements, the Hall coefficient has not been correctly determined. We are planning to measure the coefficient of Si:P at much lower fields and down to $0.05K$ to check these results.

(3) A pressure cell has been designed and built, and will be tested within the next month. This is in connection with the proposed work to investigate the effect of uniaxial stress in Si:B.

(4) We are currently reanalyzing the field and temperature dependence of the conductivity of Si:B near the metal-insulator transition. This is motivated by the realization that, although the data in zero field does not scale, the data in magnetic fields of 7 or 8T can be expressed in terms of a single universal scaling function.

Insulating Phase:

(1) The results of our study of the Hall coefficient of CdSe in the hopping regime were published in Rapid Communications⁹ earlier this year.

We find a Hall coefficient which exhibits unexpectedly rich and unanticipated dependence on magnetic field, and suggest an empirical relation which describes the dependence of the Hall coefficient on magnetic field and temperature. There has not been any theoretical progress in understanding this behavior, and it remains a puzzle at this time.

(2) Another Rapid Communication,¹⁰ also published a few months ago, contains our experimental observations of the magnetoconductance of CdSe in the hopping regime. We find a positive magnetoconductance whose field dependence is consistent in detail with theoretical expectations for a component due to quantum interference between different hopping paths. More specifically, we observe an initial quadratic behavior, following by a quasilinear regime, followed by saturation, and the magnetic field ranges where these occur are entirely consistent with theory.

(3) With Amnon Aharony of Tel Aviv University, we have proposed a universal scaling which describes our earlier experimental observation¹¹ of a cross-over from Mott variable-range hopping to variable-range hopping in the presence of a Coulomb gap. A paper describing this work¹² just appeared in the June 29 issue of Physical Review Letters.

(4) With Mark Azbel of Tel Aviv University, we have found a universal empirical relation between the transverse (Hall) and longitudinal conductivity in CdSe. This is potentially a major contribution in the field of hopping conductivity. We are still trying to understand all its implications.

(5) In Si:B at very low temperatures, we have found a hopping conductivity whose temperature dependence changes from simply activated in the absence of a magnetic field to variable range hopping with a

Coulomb gap in the presence of a field. We have interpreted this as evidence for correlations between electrons due to exchange. An article has been submitted to Physical Review Letters.

(6) We have studied the magnetoconductance of Si:P, Si:As and Si:B above 1K, and find them to all be negative. This is somewhat puzzling, and signals the apparent absence of a measurable component due to quantum interference which normally contributes a positive magnetoconductance. The absence of this term may be associated in these materials with the effect of the spins, which destroy the phase coherence necessary for quantum interference. Work is continuing on this.

(7) Recent measurements on a CdSe sample with smaller dopant concentration than we've measured to date reveal a second maximum in the magnetoconductance at approximately 7 to 8.5T. A similar feature has been observed by Raikh et al. in δ -doped GaAs, which they attributed to an increase in the density of states associated with reduced impurity bandwidth due to decreased wavefunction overlap in a magnetic field. To our knowledge, this is the second observation of this feature, and the first in a 3-dimensional material.

References:

1. Peihua Dai, Youzhu Zhang and M.P. Sarachik, Phys. Rev. B**45**, 3984 (1992).
2. Peihua Dai, Youzhou Zhang and M. P. Sarachik, Phys. Rev. Lett. **66**, 1914 (1991).
3. Peihua Dai, Youzhou Zhang and M. P. Sarachik, Phys. Rev. Lett. **67**, 136 (1991).
4. S. Shapiro and E. Abrahams, Phys. Rev. B**24**, 4025 (1981).
5. X. Wang, Z. Wang, G. Kotliar, and C. Castellani, Phys. Rev. Lett. **68**, 2504 (1992).
6. S.B. Field and T.F. Rosenbaum, Phys. Rev. Lett. **55**, 522 (1985).
7. D.W. Koon and T.G. Castner, Phys. Rev. Lett. **60**, 1755 (1988).
8. T.G. Castner, Phys. Rev. B**42**, 5317 (1990).
9. Youzhou Zhang, Peihua Dai and M. P. Sarachik, Phys. Rev. (Rapid Communications) B**45**, 6301 (1992).
10. Youzhou Zhang, Peihua Dai and M.P. Sarachik, Phys. Rev. (Rapid Communications) B**45**, 9473 (1992).
11. Youzhu Zhang, Peihua Dai, Miguel Levy and M. P. Sarachik, Phys. Rev. Lett. 64, 2687 (1990).
12. Amnon Aharony, Youzhu Zhang and M. P. Sarachik, Phys. Rev. Lett.**68**, 3900 (1992).

PUBLICATIONS - 1991-1992

"A Calibration Curve for Room Temperature Resistivity versus Carrier Concentration in n-Type CdSe," Miguel Levy and M. P. Sarachik, J. Appl. Phys. **69**, 2703 (1991).

"Negative Magnetoresistance in the Variable Range Hopping Regime in n-Type CdSe," Youzhu Zhang and M. P. Sarachik, Phys. Rev. **B43**, 7212 (1991).

"The Critical Conductivity Exponent for Si:B," Peihua Dai, Youzhou Zhang and M. P. Sarachik, Phys. Rev. Lett. **66**, 1914 (1991).

"The Effect of a Magnetic Field on the Critical Conductivity Exponent near the Metal-Insulator Transition," Peihua Dai, Youzhou Zhang and M. P. Sarachik, Phys. Rev. Lett. **67**, 136 (1991).

"Non Linear Hall Voltage in the Hopping Regime," Youzhou Zhang, Peihua Dai and M. P. Sarachik, Phys. Rev. (Rapid Communications) **B45**, 6301 (1992).

"Electrical Conductivity of Metallic Si:B near the Metal-Insulator Transition," Peihua Dai, Youzhu Zhang and M.P. Sarachik, Phys. Rev. **B45**, 3984 (1992).

"Magnetococonductance of CdSe in the Hopping Regime: The Effect of Quantum Interference," Youzhou Zhang, Peihua Dai and M.P. Sarachik, Phys. Rev. (Rapid Communications) **B45**, 9473 (1992).

"Universal Crossover in Variable Range Hopping with Coulomb Interactions," Amnon Aharony, Youzhu Zhang and M. P. Sarachik, Phys. Rev. Lett. **68**, 3900 (1992).

"Low Temperature Transport in the Hopping Regime: Evidence for Correlations due to Exchange," Peihua Dai, Youzhu Zhang and M. P. Sarachik, submitted to Phys. Rev. Letters.

"Magnetococonductance of metallic Si:B near the Metal-Insulator Transition," Peihua Dai, Youzhu Zhang and M. P. Sarachik, to be published in Phys. Rev. B, Sept. 15, 1992.

"Hopping Magnetococonductance of n-type CdSe," Youzhu Zhang, Peihua Dai and M. P. Sarachik, 21st International Conference on the Physics of Semiconductors, 10-14 August, 1992, Beijing, China.

"An Empirical Scaling in Longitudinal and Transverse Transport in n-type CdSe", M. P. Sarachik, Youzhu Zhang, Peihua Dai and M. Ya. Azbel, to be submitted to Physical Review Letters.

"Critical Behavior of the Hall coefficient of Si:B", Peihua Dai, Youzhu Zhang and M. P. Sarachik, to be submitted to Physical Review Letters.

"The Apparent Absence of Quantum Interference in the Hopping
Magneconductance of doped Si" Peihua Dai, Jonathan Friedman and M.P.
Sarachik, in preparation.

"The Resistivity of n-type CdSe," Youzhu Zhang and M. P. Sarachik, in
preparation.

END

**DATE
FILMED**

9 / 15 / 92