2
DOE/PC/91283--T5

FEB 24 1993

Liquid Chromatographic Analysis of Coal Surface Properties

RECEIVED

DOE/PC/91283--T5

DE93 009657

Quarterly Progress Report
For the Period October-December 1992

K. C. Kwon and Ricardo Rigby
Chemical Engineering Department
School of Engineering and Architecture
Tuskegee University
Tuskegee, Alabama 36088

US/DOE Patent Clearance is
not required prior to the
publication of this document.

Prepared for the United States
Department of Energy under
the Contract No. DE-FG22-91PC91283

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

CONTENTS

	Page
I. ABSTRACT.....	1
II. INTRODUCTION.....	1
III. PROJECT STATUS.....	2
IV. FUTURE EXPERIMENTAL PLANS.....	5
V. PRESENTATIONS.....	5

TABLES

1. Equilibrium adsorption of isopropanol,.....	6
1-propanol, 1-butanol, 2-butanol, isobutanol, and t-butanol on 60-200 mesh Illinois #6 coal, and their equilibrium concentrations in aqueous solutions at 25°C.	
2. Equilibrium adsorption of cyclohexanol, phenol,....	7
o-cresol and 2-naphthol on 60-200 mesh Illinois #6 coal, and their equilibrium concentrations in aqueous solutions at 25°C.	

FIGURES

1. Equilibrium adsorption of normal alcohols.....	8
2. Equilibrium adsorption of propanols.....	9
3. Equilibrium adsorption of butanols.....	10
4. Equilibrium adsorption of 6-ring compounds.....	11

I. ABSTRACT

Experiments on equilibrium adsorption loadings of various additives on 60 - 200 mesh Illinois #6 coal (DECS-2; Randolph county) were performed during the October - December period. The additives include n-propanol, n-butanol, 2-butanol, phenol, 2-naphthol, o-cresol and cyclohexanol.

Equilibrium adsorption loadings of normal alcohols on 60 - 200 mesh Illinois #6 coal increase with increased numbers of carbons in their molecular formulas. Normal alcohols are more adsorbed on the coal than their branched alcohols. Adsorption loadings of single-ring compound phenol on the coal is higher than that of cyclohexanol. Adsorption loadings of double-ring compound 2-naphthol on the coal is much higher than that of single-ring compound phenol.

II. INTRODUCTION

The main objectives of this proposed research are to refine further the inverse liquid chromatography technique for the study of surface properties of raw coals, treated coals and coal minerals in water, to evaluate relatively surface properties of raw coals, treated coals and coal minerals by inverse liquid chromatography, and to evaluate floatability of various treated coals in conjunction with surface properties of coals.

Coals such as Pittsburgh seam coal, Illinois #6 coal, Wyodak coal are chosen as representatives of high-rank bituminous coal, high volatile bituminous coal and subbituminous coal, respectively. Coal minerals such as pyrite and dolomite are chosen as representative coal minerals.

Alcohols such as methanol, ethanol, isopropanol, isobutanol, tert-butanol, heptanol, 1-hexadecanol, 2-methyl-1-pentanol, 4-methyl-2-pentanol (methylisobutyl carbinol), n-octanol, s-octanol, and cyclohexanol as probe compounds are utilized to evaluate hydrophilicity of coals and coal minerals.

N-alkanes such as hexane, heptane and octane are employed as probe compounds to evaluate hydrophobicity of coals and coal minerals. Aromatic compounds such as benzene and toluene as probe compounds are used to examine aromaticity of coal surface. Aromatic acids such as o-cresol, m-cresol, p-cresol, phenol and β -naphthol are used to detect aromatic acidic sites of coal surface.

Hydrophilicity, hydrophobicity and aromaticity of surfaces for either raw coals or treated coals in water are relatively determined by evaluating equilibrium physical/chemical adsorption loadings of probe compounds on various raw coals and treated coals to compare affinities of coals for water.

III. PROJECT STATUS

1. Experiments

Experiments on equilibrium adsorption loadings of various alcohols on Illinois #6 coal were performed in aqueous solutions at 25°C. Illinois #6 coal (DECS-2; Randolph county) were pulverized and sieved to obtain 60-200 mesh coal particles. Sieved 60-200 mesh Illinois #6 coal particles were washed with distilled water (DW) to get rid of any water-soluble organic compounds on the surfaces of the coal particles. Coal particles

were submerged under water overnight, and then filtered next day to remove organic-dissolved water from surfaces of coal particles. These washing processes continued for 3 weeks. Washed coal particles were dried at 110°C for 4 hours.

Dry coal particles of 0.75 - 2.5-g were introduced into an empty column. The coal particles packed in the column were washed with DW for 10 hours to eliminate any water-soluble contaminants introduced in the coal-packed column during the process of packing dry coal particles into the column.

The alcohols include n-propanol, n-butanol, s-butanol, and cyclohexanol for equilibrium adsorption experiments. Equilibrium adsorption loadings of ring compounds such as phenol, 2-naphthol and o-cresol on Illinois #6 coal were investigated during this quarter.

Equilibrium adsorption loadings of n-heptanol, n-octanol, p-cresol and m-cresol on Illinois #6 coal were investigated. Their reproducibilities of adsorption data were poor in comparison with butanols and propanols. These data are not included in this quarter report.

Mr. Ricardo Rigby, a senior chemical engineering students, worked as research assistants for this project during the October - December period.

2. Experimental Results

Experimental data on equilibrium adsorption loadings of alcohols and ring compounds on 60 -200 mesh Illinois #6 coal were shown in Tables 1 and 2, and Figures 1 through 4.

Equilibrium adsorption loadings of normal alcohols on Illinois #6 coal are compared with their equilibrium concentrations of 3 - 40 ppm (see Figure 1). Equilibrium adsorption loadings of ethanol on the coal are $5 - 20 \times 10^{-6}$ mg/g-coal. Equilibrium adsorption loadings of propanols on the coal are $1 - 100 \times 10^{-6}$ mg/g-coal, while equilibrium adsorption loadings of butanols on the coal are $2 - 190 \times 10^{-6}$ mg/g-coal. Equilibrium adsorption loadings of normal alcohols on the coal increase with increased numbers of carbons in their molecular formulas.

Equilibrium adsorption loadings of n-propanol on the coal are $9 - 100 \times 10^{-6}$ mg/g-coal, whereas equilibrium adsorption loadings of isopropanol on the coal are $1 - 38 \times 10^{-6}$ mg/g-coal (see Figure 2). These observations suggest that the branched alcohol isopropanol is less active than the straight-chain alcohol n-propanol with Illinois #6 coal.

Equilibrium adsorption loadings of butanols on 60 - 200 mesh Illinois #6 coal are $2 - 190 \times 10^{-6}$ mg/g-coal (see Figure 3). Equilibrium adsorption loadings of n-butanol on the coal are $17 - 184 \times 10^{-6}$ mg/g-coal, while equilibrium adsorption loadings of s-butanol are $14 - 103 \times 10^{-6}$ mg/g-coal. Equilibrium adsorption loadings of isobutanol on the coal are $3 - 55 \times 10^{-6}$ mg/g-coal, whereas equilibrium adsorption loadings of t-butanol on the coal are $2 - 8 \times 10^{-6}$ mg/g-coal. These data suggest that the straight-chain butanols such as n-butanol and s-butanol are more active than the branched butanols such as isobutanol and t-butanol with

Illinois #6 coal. These facts also reveal that equilibrium adsorption loadings of butanols on the coal increase with reactivities of OH group in butanols.

Equilibrium adsorption loadings of ring compounds such as cyclohexanol, phenol, o-cresol and 2-naphthol on the coal are $17 - 1200 \times 10^{-6}$ mg/g-coal (see Figure 4). Equilibrium adsorption loadings of double-ring compound 2-naphthol on the coal are $200 - 1200 \times 10^{-6}$ mg/g-coal, whereas equilibrium adsorption loadings of single-ring compound phenol on the coal are $32 - 276 \times 10^{-6}$ mg/g-coal. Equilibrium adsorption loadings of o-cresol on the coal are $64 - 166 \times 10^{-6}$ mg/g-coal. Equilibrium adsorption loadings of cyclohexanol on the coal are $17 - 115 \times 10^{-6}$ mg/g-coal.

IV. FUTURE EXPERIMENTAL PLANS

Experiments on equilibrium adsorption of selected alcohols on Pittsburgh coal and Wyodak coal Illinois #6 coal will be conducted to investigate surface properties of these coals in comparison with those of Illinois #6 coal.

V. PRESENTATIONS

A research paper, entitled "Analysis of Surface Properties of Coal by Inverse Liquid Chromatography", was accepted for presentation at the 18th International Technical Conference on Coal Utilization & Fuel Systems, Clearwater, Florida, April 26-29, 1993. An annual report on equilibrium adsorption loadings of alcohols will be prepared with experimental data obtained during the past four quarters.

Table 1. Equilibrium adsorption of isopropanol, 1-propanol, 1-butanol, 2-butanol, isobutanol, and t-butanol on 60-200 mesh Illinois #6 coal, and their equilibrium concentrations in aqueous solutions at 25°C.

Run #	Alcohols	Equilibrium Concentrations Alcohols, ppm	Equilibrium Adsorption on Coal, 10^{-6} mg/g-coal
1	isopropanol	3.00	1.36
2	isopropanol	5.01	4.41
3	isopropanol	7.02	6.17
4	isopropanol	10.16	4.36
404	isopropanol	10.16	8.82
5	isopropanol	16.01	13.38
6	isopropanol	20.33	17.20
1001	isopropanol	40.02	37.98
83	isopropanol	5.00	3.28
82	isopropanol	9.99	5.27
81	isopropanol	20.01	8.89
86	isopropanol	30.01	21.26
84	isopropanol	40.05	20.65
137	1-propanol	5.01	8.80
138	1-propanol	10.01	18.18
136	1-propanol	20.00	45.64
135	1-propanol	30.03	76.79
134	1-propanol	40.33	99.85
99	1-butanol	4.98	16.99
98	1-butanol	10.01	30.63
97	1-butanol	19.99	89.62
89	1-butanol	30.00	131.17
88	1-butanol	39.97	184.38
104	2-butanol	5.01	13.67
103	2-butanol	10.01	30.84
102	2-butanol	19.97	54.64
101	2-butanol	30.04	88.38
100	2-butanol	40.10	102.98
20	isobutanol	4.88	2.57
8	isobutanol	5.02	3.10
63	isobutanol	4.99	4.45
14	isobutanol	10.01	9.86
57	isobutanol	10.01	12.32
56	isobutanol	19.99	19.21
61	isobutanol	19.99	22.97
65	isobutanol	29.94	42.09
101	isobutanol	40.02	52.16
64	isobutanol	39.97	55.44
62	t-butanol	10.00	4.16
70	t-butanol	19.97	3.59
69	t-butanol	29.89	1.74
68	t-butanol	39.72	8.08

Table 2. Equilibrium adsorption loadings of cyclohexanol, phenol, o-cresol and 2-naphthol on 60-200 mesh Illinois #6 coal, and their equilibrium concentrations in aqueous solutions at 25°C.

Run #	Alcohols	Equilibrium Concentrations Alcohols, ppm	Equilibrium Adsorption on Coal, 10^{-6} mg/g-coal
133	cyclohexanol	5.00	16.62
132	cyclohexanol	10.00	29.39
131	cyclohexanol	19.98	64.94
130	cyclohexanol	29.91	79.73
129	cyclohexanol	39.90	115.00
71	phenol	4.99	54.00
66	phenol	9.99	31.80
72	phenol	9.99	68.43
75	phenol	20.02	153.99
74	phenol	29.97	210.32
73	phenol	39.98	275.76
80	o-cresol	5.07	63.99
76	o-cresol	10.04	94.36
85	o-cresol	20.10	104.01
79	o-cresol	30.11	143.84
78	o-cresol	40.03	166.35
163	2-naphthol	5.01	203.67
161	2-naphthol	9.99	527.73
164	2-naphthol	19.98	697.25
159	2-naphthol	29.98	982.01
158	2-naphthol	39.96	1202.01

Figure 1. Equilibrium concentration of n-alcohols (n-ALCO) and their adsorption on 2.5-9 60-200 mesh Illinois #6 coal in aqueous solutions at 25°C.

Figure 2. Equilibrium concentrations of propanols (PROL) and their adsorption on 2.5-g 60-200 mesh Illinois #6 coal in aqueous solutions at 25°C.

Figure 3. Equilibrium concentration of butanols (BUTL) and adsorption of BUTL on 2.5-g 60-200 mesh Illinois #6 coal in aqueous solutions at 25°C.

Figure 4. Equilibrium concentration of various ring-containing compounds (RCC) and adsorption of RCC on 2.5-9 60-200 mesh Illinois #6 coal in aqueous solutions at 25°C.

END

DATE
FILMED

4/1/1/93