190
U-22-77
LA-6583

UC-21 *Dr 437*

Issued: April 1977

Electroless or Autocatalytic Coating of Microparticles for Laser Fusion Targets

by

**Anton Mayer
Duane S. Catlett**

los alamos
scientific laboratory
of the University of California
LOS ALAMOS, NEW MEXICO 87545

An Affirmative Action/Equal Opportunity Employer

MASTER

UNITED STATES
ENERGY RESEARCH AND DEVELOPMENT ADMINISTRATION
CONTRACT W-7405-ENG. 36

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

Work supported by the US Energy Research and Development Administration, Division of Laser Fusion.

**Printed in the United States of America. Available from
National Technical Information Service
U.S. Department of Commerce
5285 Port Royal Road
Springfield, VA 22161
Price: Printed Copy \$3.50 Microfiche \$3.00**

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Energy Research and Development Administration, nor any of their employees, nor any of their contractors, subcontractors, or their employees, make any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights.

ELECTROLESS OR AUTOCATALYTIC COATING OF MICROPARTICLES FOR LASER FUSION TARGETS

by

Anton Mayer and Duane S. Catlett

ABSTRACT

Use of a novel device for applying uniform metallic coatings to spherical microparticles is described. The apparatus deposits electroless metal coatings on hollow, thin-walled metal or sensitized nonmetallic microman-drels. The apparatus and process were developed for fabrication of microsphere pressure vessels for use as targets in laser-initiated fusion research.

NOTICE
This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Energy Research and Development Administration, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights.

I. INTRODUCTION

In research on laser-initiated pure fusion, target design has been limited severely by the lack of sufficiently energetic lasers. The most difficult constraint is that of size. Present laser fusion targets range from 50 to 500 μm in diameter.

Figure 1 shows a hypothetical target.¹ The inner shell is generally obtained from a commercial source, and in many designs it is considered to be an inert layer, whose sole purpose is to serve as a mandrel upon which to deposit the design layers. Regardless of the coating technique, during the deposition process, the microparticles must be forced to move individually and randomly in the coating medium to ensure wall thickness uniformity and homogeneity of the deposit.

Several techniques for applying metal shells to microspheres¹⁻⁴ have been evaluated. They include physical vapor deposition (PVD), chemical vapor deposition (CVD), sputter deposition, and electro- and electroless plating. An apparatus developed to electroplate microspheres for laser fusion targets has been reported.⁵ Here, we describe an apparatus developed to electrolessly plate such microspheres.

Fig. 1.

A hypothetical structured, multilayered laser fusion target.

204

II. APPARATUS

Electroless, or autocatalytic, plating has extensive decorative and engineering applications in the metal-finishing industry. Large parts are plated on racks; small parts are efficiently processed in bulk in screen baskets or perforated barrels. Applying thick, uniform coatings to hollow microparticles presented a challenge, because existing techniques could not be applied directly.

The initial approach to coating thin-walled metal or metal-coated glass shells, at both LASL and Bendix Kansas City, was to suspend the particles in the solution vortex or in a vigorously stirred electroless plating solution until the desired coating thickness was obtained. In theory, the particles would ride in the solution vortex and thus be plated uniformly. In practice, however, some particles were drawn into the solution meniscus where their motion and the deposition essentially ceased. As the plating progressed, other particles became denser than the solution medium, sank to the bottom of the plating tank, and agglomerated. A new apparatus⁹ makes it practical to electrolessly plate discrete microparticles with uniformly thick deposits.

The electroless plating apparatus is shown in Fig. 2. The microparticles are confined in a cylindrical reaction chamber by fine mesh screens at top and bottom. The cylinder wall extends beyond both screens. The top extension serves as a solution overflow and intake cavity. The bottom extension is fitted over a stationary piston. The plating apparatus is immersed vertically in the electroless plating solution, and the extension rod is attached to a mechanical or pneumatic direction-reversing drive mechanism. The reaction chamber is forced intermittently up and down over the stationary piston. The reaction-reversing cycle time is variable from 1 to 10 s. The moving chamber's stroke length is adjusted to purge the reaction chamber with fresh solution continually.

The solution movement through the reaction chamber moves the particles randomly during metal deposition. When the motion is downward, plating solution forced through the bottom screen into the reaction chamber lifts and disperses the particles that are denser than the solution. When the motion is upward, solution drawn into the cavity by suction through the top screen disperses the particles that

Fig. 2.

An apparatus for autocatalytic plating of discrete microparticles.

float. Evolved hydrogen, which normally accompanies electroless deposition, is forced out of the reaction chamber during the downward stroke, thereby keeping the cavity filled with plating solution.

III. RESULTS

Uniform, fully dense deposits with excellent surface smoothness have been applied to 50- to 200- μ m-diam spherical mandrels. The agglomeration inherent in previous techniques has been virtually eliminated. Metal distribution from particle to particle within the same batch is excellent.

Figure 3, a metallurgical cross section of an experimental laser-fusion target, shows a uniform coating of $16\text{ }\mu\text{m}$ of electroless nickel over the thin-walled ($2\text{-}\mu\text{m}$) spherical glass mandrel.

Figure 4 is a scanning electron micrograph of an electroless nickel coated laser target. The surface

Fig. 3.
Metallographic cross section of $16\text{ }\mu\text{m}$ of electroless nickel plated on a thin-walled glass mandrel. (500X)

Fig. 4.
Scanning electron micrograph of an electroless nickel-coated laser target. (550X)

finish of particles coated in this apparatus is as good as, or better than, that of the starting substrate.

We have thus far applied electroless nickel coatings to both metal and metallized-glass spheres, 2 to $22\text{ }\mu\text{m}$ thick. Proprietary baths from the Shipley Company and the Sel Rex Corporation were used as plating solutions. Exceedingly fine-grained, smooth coatings have been deposited from the Shipley "Nicoloy 22" bath and the Sel Rex "Electroless Ni" process. The Shipley bath deposits a nickel-phosphorous-copper alloy that is typically about 12 wt% P, 1 wt% Cu, and 87 wt% Ni. The Sel Rex solution deposits a nickel-phosphorous alloy whose phosphorous content is $<2\text{ wt}\%$. Batch sizes range from only a few spheres to over 100 000.

IV. SUMMARY

We have developed a method and apparatus for applying very uniform coatings to discrete microparticles by electroless techniques. Agglomeration or bridging of the particles is prevented by moving them randomly during deposition. The microparticle density is not critical and may be less than, equal to, or more than that of the plating solution. Although all particles coated thus far have been hollow spheres, the method is applicable to discrete irregular microparticles.

ACKNOWLEDGMENTS

Grateful acknowledgments are extended to C. A. Javorsky and J. R. Bradberry, who were responsible for the metallography, and to R. R. Bryant, for fabricating the apparatus.

REFERENCES

1. R. J. Fries and E. H. Farnum, "Laser Fusion Target Fabrication," Los Alamos Scientific Laboratory report LA-5703-Rev. (1974).
2. J. W. Havenhill, "1973 Laser Target Activities," Los Alamos Scientific Laboratory unpublished data.

3. W. J. McCreary, "Microspherical Laser Targets by CVD," Proc. Conf. Chemical Vapor Deposition, Electrochemical Society, Princeton, New Jersey (1975), p. 714.
4. Gary A. Simonsic and Billy W. Powell, "Vapor Phase Coatings of Metals and Organics for Laser Fusion Target Applications," Los Alamos Scientific Laboratory unpublished data.
5. Anton Mayer and Duane S. Catlett, "Electrolytic Coating of Microparticles for Laser Fusion Targets," Los Alamos Scientific Laboratory report LA-6584 (1976).
6. Anton Mayer, U.S. Patent Application No. SN 613849