CONF-760631--1

The Solubility of Hydrogen Isotopes in Lithium*

F. J. Smith, A. M. Batistoni,** G. M. Begun, and J. F. Land
Oak Ridge National Laboratory
Oak Ridge, Tennessee 37830, USA

Summary

The individual solubilities of hydrogen, deuterium and tritium in lithium have been measured as a function of temperature (700 to 1000°C) and pressure (0.1 to 760 torr). The individual solubilities decrease with increasing temperature, and, for the same hydrogen isotope concentration in the molten lithium, the equilibrium gas pressures for the isotopes are of the order $P_{T_2} > P_{D_2} > P_{H_2}$. When the mole fraction of LiH, LiD, or LiT is less than about 0.1, the temperature dependence of the individual solubilities can be expressed as $\ln(N_{LiH}^{-1} P_{H_2}^{1/2}) = 9.842 - 6242/T(^{\circ}K)$, $\ln(N_{LiD}^{-1} P_{D_2}^{1/2}) = 9.515 - 5644/T(^{\circ}K)$, and $\ln(N_{LiT}^{-1} P_{T_2}^{1/2}) = 9.226 - 5085/T(^{\circ}K)$. In these equations, N is the mole fraction in the liquid phase, P is the equilibrium pressure of the gaseous hydrogen isotope (torr), and T is temperature ($^{\circ}K$).

The mutual solubilities of hydrogen and deuterium in lithium have been measured for the plateau region at 800°C. Both the total pressure and the individual partial pressures of H_2 , HD, and D_2 have been determined as a function of the mole fraction of LiH and LiD in the lithium solution with varying hydrogen-to-deuterium ratios. The total pressure and the partial pressures of hydrogen and deuterium in the plateau region at 800°C may be expressed as $P_{total}^{1/2}$ (torr) = $-3 N_{LiH}/(N_{LiH} + N_{LiD}) + 15.9$, $P_{H_2}^{1/2}$ (torr) = $12.9 N_{LiH}/(N_{LiH} + N_{LiD})$, and $P_{D_2}^{1/2}$ (torr) = $15.9 N_{LiD}/(N_{LiH} + N_{LiD})$.

The individual solubilities of hydrogen, deuterium and tritium in lithium have been measured as a function of temperature (700 to 1000°C) and pressure (0.1 to 760 torr). The individual solubilities decrease with increasing temperature, and, for the same hydrogen isotope concentration in the molten lithium, the equilibrium gas pressures for the isotopes are of the order $P_T > P_D > P_H$. When the mole fraction of LiH, LiD, or LiT is less than about 0.1, the temperature dependence of the individual solubilities can be expressed as $\ln(N_{LiH}^{-1} P_{H_2}^{1/2}) = 9.842 - 6242/T(^{\circ}K)$, $\ln(N_{LiD}^{-1} P_D^{1/2}) = 9.515 - 5644/T(^{\circ}K)$, and $\ln(N_{LiT}^{-1} P_T^{1/2}) = 9.226 - 5055/T(^{\circ}K)$. In these equations, N is the mole fraction in the liquid phase, P is the equilibrium pressure of the gaseous hydrogen isotope (torr), and T is temperature ($^{\circ}K$).

The mutual solubilities of hydrogen and deuterium in lithium have been measured for the plateau region at 800°C. Both the total pressure and the individual partial pressures of H_2 , HD, and D_2 have been determined as a function of the mole fraction of LiH and LiD in the lithium solution with varying hydrogen-to-deuterium ratios. The total pressure and the partial pressures of hydrogen and deuterium in the plateau region at 800°C may be expressed as $P_{total}^{1/2}$ (torr) = $-3 N_{LiH}/(N_{LiH} + N_{LiD}) + 15.9$, $P_{H_2}^{1/2}$ (torr) = $12.9 N_{LiH}/(N_{LiH} + N_{LiD})$, and $P_{D_2}^{1/2}$ (torr) = $15.9 N_{LiD}/(N_{LiH} + N_{LiD})$.

2

*Research sponsored by the Energy Research and Development Administration under contract with Union Carbide Corporation.

**International Atomic Energy Agency Fellow, Address after September 1976: Comisión Nacional de Energía Atómica, Argentina.

By acceptance of this article, the publisher or recipient acknowledges the U. S. Government's right to retain a non-exclusive, royalty-free license in and to any copyright covering the article.

NOTICE
This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Energy Research and Development Administration, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

Adequate tritium management schemes for controlled thermonuclear reactions (CTR) with lithium blankets will require detailed information on the solid-liquid equilibria for the hydrogen isotope-lithium system. Phase equilibrium studies are needed to define the tritium pressures that will exist in a CTR system. This information also aids in the prediction of permeation of hydrogen isotopes through the system. All of this information will be needed in the design of a process to maximize recovery of the bred tritium and minimize the loss of tritium to the environment.

The individual equilibrium pressures of the hydrogen isotopes in Li-LiH, Li-LiD, and Li-LiT-T₂ systems were measured between 700°C and 1000°C using a modified Sieverts apparatus. Samples of lithium were encapsulated in iron, which is highly permeable to the hydrogen isotopes, and the equilibrium pressure was established inside and outside the capsule which was held at constant temperature. Utilizing the measured equilibrium pressures and a mass balance on the system, the experimental data were considered in terms of the equilibria

in which (g) and (s) indicate the gas and the solid Li-LiH phases, respectively, and H represents the hydrogen isotope. The experimental results for solubility of pure H₂, deuterium, and tritium in lithium as a function of pressure at 800°C are shown in Fig. 1. The tritium measurements were limited to 150 ci total which, in our system, was about 50% of equilibrium pressure. The first rising portion of the plot ($x_{\text{LiH}} = 2 \times 10^{-4}$) represents a solid solution of lithium hydride dissolved in lithium, and the second rising portion ($x_{\text{LiH}} = 2 \times 10^{-2}$) represents lithium dissolved in the Li₂ lithium hydride. The constant-pressure plateau between the two portions defines the two-phase coexistence region. When the mole fraction, x , of LiH, LiD, or LiT was less than 0.1, the Sieverts relation [1]

$$\sqrt{P_{\text{H}_2}(g)} = K_1 \cdot x_{\text{LiH}(s)} \quad (2)$$

was obeyed by each isotope. The temperature dependence of the solubility is given by the equation:

$$\begin{array}{l} \text{hydrogen} \\ \ln K_1 (\text{atm}^{1/2}/\text{mole fraction}) = 9.041 - 6147/T(^{\circ}\text{K}), \end{array} \quad (3)$$

$$\begin{array}{l} \text{deuterium} \\ \ln K_1 (\text{atm}^{1/2}/\text{mole fraction}) = 9.515 - 5634/T(^{\circ}\text{K}), \end{array} \quad (4)$$

$$\begin{array}{l} \text{tritium} \\ \ln K_1 (\text{atm}^{1/2}/\text{mole fraction}) = 9.216 - 5054/T(^{\circ}\text{K}), \end{array} \quad (5)$$

The solubilities decrease with increasing temperature and, for the same hydrogen isotope concentration in the molten lithium, the equilibrium pressures for the isotopes are in the order $P_{\text{T}_2} > P_{\text{D}_2} > P_{\text{H}_2}$.

The mutual solubilities and isotopic exchange of hydrogen and deuterium in lithium have been measured for the plateau region at 800°C. A Sieverts apparatus was modified for these measurements by the addition of a gas port to circulate and mix the gases (H₂, HD, and D₂) and a sampling station to permit sampling and analysis.

hydrogen (or deuterium) was added to the liquid to produce a solid (HD , (or HD-D_2)) system in the plateau region, then deuterium (or hydrogen) was added in a second process. The results are shown in Fig. 2. The results were independent of whether the initial gas phase was hydrogen or deuterium, and did not depend on the relative amounts of the two coexisting liquid phases. The equilibrium pressure depended only on the relative amount of the liquid phase present. The total equilibrium pressure in the solid hydrogenic two-phase region is given by the relationship

$$P_{\text{total}}^{1/2} (\text{atm}^{1/2}) = \left(\frac{N_{\text{HD}}}{N_{\text{HD}} + N_{\text{HD-D}_2}} \right) \cdot 15.9 \quad (6)$$

Partial pressures of hydrogen and deuterium are represented by

$$P_{\text{H}_2}^{1/2} (\text{atm}^{1/2}) = 15.9 \left(\frac{N_{\text{HD}}}{N_{\text{HD}} + N_{\text{HD-D}_2}} \right), \quad (7)$$

$$P_{\text{D}_2}^{1/2} (\text{atm}^{1/2}) = 15.9 \left(\frac{N_{\text{D}_2} + N_{\text{HD-D}_2}}{N_{\text{HD}} + N_{\text{HD-D}_2}} \right), \quad (8)$$

respectively. The equilibrium partial pressure of HD is defined by the pressures of H_2 , D_2 , and the gas phase equilibrium constant which at 400°C is [3]

$$K(p) = 1.0 = \frac{P_{\text{HD}}^2}{P_{\text{H}_2} P_{\text{D}_2}}. \quad (9)$$

The results of the two phase region (single isotope present) were similar to the data for hydrogen and deuterium (Fig. 1). The data (Fig. 1) are in excellent agreement with those of Volante [3]. The two curves in Fig. 1 for the solid hydrogen-deuterium effect are also identical to those for a single isotope and are independent of the ratio of gas to liquid deuterium. They are given by the relationships $N_{\text{HD}} + N_{\text{HD-D}_2} = 2N_{\text{H}_2}$ and $N_{\text{HD}} + N_{\text{HD-D}_2} = 2N_{\text{D}_2}$.

The equilibrium constant effect measured in the solid solubility work at 400°C is obtained by dividing N_{H_2} (6) by N_{D_2} (8).

$$\frac{P_{\text{H}_2}^{1/2}}{P_{\text{D}_2}^{1/2}} = 1.0 = \frac{N_{\text{H}_2}}{N_{\text{D}_2}} \quad (10)$$

Details of the experimental procedure, equilibrium pressure effects and the extension of other temperatures, to the deuterium region, and to the hydrogen-deuterium system.

REFERENCES

- [1] STEWART, A., *Z. Physik. Chem.* **92**, 179 (1937).
- [2] STEWART, H. L., LEST, H.A., *J. Chem. Phys.* **2**, 399 (1934).
- [3] VOLANTE, E., Chemical Engineering Division Technical Research Chemical Atomic Energy, 1971-74, ORNL Report 6060-74, p. 5.

Fig. 1 Solubility of Individual Hydrogen Isotopes In Lithium at 800°C.

Fig. 2. Mutual Solubility of Hydrogen and Deuterium in Lithium for the Plateau Region at 800°C.