2. 1.
JUN 08 1993

5-3
1

DEPARTMENT OF ENERGY

Quarterly Technical Progress Report

Due date April 30, 1993

Period of report 1/1/93 to 3/30/93

Project DE-FG22-92PC92529

**Transient Studies of Low Temperature Catalysts for
Methane Conversion**

directed by

Eduardo E. Wolf

Professor

Chemical engineering Department

University of Notre Dame

Notre Dame, IN 46556

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

APR 29 1993

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

BRIEF SUMMARY OF PROGRESS

This report summarizes studies conducted during the past quarter on the partial oxidation of methane on the following catalysts: vanadium phosphate, unsupported and supported on silica, and on the silica (SiO_2) support. It was found that the unsupported vanadium phosphate catalyst exhibits some selectivity towards formaldehyde at relatively low methane conversions (up to 5% conversion). The selectivity decreases even further on the silica supported VPO catalyst without a significant increase in conversion. In the case of silica, the reaction temperature decreases, and the formaldehyde selectivity is higher than in the case of the VPO catalyst.

SUMMARY OF PROGRESS

The objective of this project is to use a combination of transient and steady state techniques to study the factors determining the conversion of methane to higher hydrocarbons on low temperature metallo-oxide catalysts, which are made of a combination of an oxide and a metal. The oxide can provide the pathway for participation of lattice oxygen, which is related to the hydrocarbon selectivity, and the metal function can interact with methane.

Our previous report dealt with the results obtained in the absence of catalysts whereas in this report we present new catalytic results. Among the various catalyst systems considered, vanadium phosphate (VOPO_4) referred as VPO, was thought as a good candidate because a metal can be inserted (pillared) into that structure, and because it contains phosphorous which was shown to be beneficial to the selectivity in the case of Mo/Sn/P catalysts (1).

Studies of the activity and selectivity of VPO catalysts are presented in Figs. 1 a,b. The results were obtained in a flow quartz reactor at the operating conditions shown in the figures captions. Fig.1 indicates that this catalyst has some formaldehyde selectivity, with the other oxidation products being mainly CO whereas CO_2 forms to a less extent than formaldehyde.

Given the low conversion obtained on the unsupported VPO catalysts, it was supported on silica to increase its surface area. The results are presented in Fig. 2 a,b indicating an even lower selectivity towards formaldehyde but also a dramatic increase in CO_2 production. This results suggest that the silica support could have selective sites but

also unselective sites which oxidize some of the formaldehyde to form CO_2 , since silica alone have no activity towards CO oxidation. Alternatively, it can form CO_2 directly from methane. These results lead to studies of the activity and selectivity of the silica support alone, which are shown in Fig. 3 . It can be seen that silica shows the highest formaldehyde selectivity of all the catalysts studied and at a much lower temperature (540-600°C) than the unsupported VPO (600-700°C). CO_2 production is still high on silica and it is not clear whether is coming from the sequential oxidation of formaldehyde or from sites that are capable of oxidizing methane on silica. The formaldehyde selectivity decreases as the temperature reaches about 580°C.

In order to answer the above questions, it is necessary to conduct the proposed transient experiments to determine the nature of the oxygen insertion into the methane molecule. Work will also be conducted in parallel to explore the effect of adding Sn into the VPO catalyst to increase its activity and selectivity as it was done in the case of a Mo/Sn/P catalysts (1).

- 1) T. Weng and E.E. Wolf, Appl. Catal. A, 96, 383 (1993).

0.2 g $\text{VOPO}_4 \cdot 2\text{H}_2\text{O}$.
Total flow = 24.01 cc/m.
 $P' = 0.03$, $\text{CH}_4/\text{O}_2 = 4.74$

Fig. 1a

Fig. 1b

0.2 g VPO(5%)/SiO₂.
 Total flow= 25 cc/m.
 P'=0.63, CH₄/O₂=4.74

Fig. 2a

Fig. 2b

0.2 g SiO₂.
 Total flow= 24.1 cc/m.
 P'=0.66, CH₄/O₂=4.35.

Fig. 3a

Fig. 3b

END

**DATE
FILMED**

8 / 26 / 93