Annual Technical Progress Report, DOE Grant No. DE-FG02-84-ER13289

for the period

Dec. 1, 1991-Nov. 30, 1992

MODEL STUDIES OF HYDRODESULFURIZATION BY Mo

DOE/ER/13289--6

DE93 002774

Cynthia M. Friend

Department of Chemistry, Harvard University

Cambridge, MA 02138

The study of the effects of surface modifiers, namely cobalt and sulfur, on the activity and selectivity of Mo(110) for desulfurization processes has been the focus of our recent work. In addition, spectroscopic methods for identifying surface intermediates and characterizing their structure have been refined in our laboratories.

The effect of cobalt and sulfur on the reactivity of Mo(110) is of specific interest because they are both components of commercial catalysts used in hydrodesulfurization. Furthermore, modified surfaces may exhibit unusual reactivity compared to clean surfaces. Thin metal films have particular promise as novel materials because of the fact that strained and "flexible" structures may be formed for films of a few layers or less.

Sulfur generally increases the selectivity for desulfurization processes while decreasing the overall reactivity. For the case of 2,5-dihydrothiophene, for example, the selectivity for butadiene elimination over nonselective decomposition is ~83% on Mo(110)-p(4x1)-S compared to ~70% on clean Mo(110) (Figure 1).

Cobalt promotes C-H activation processes on Mo(110). Several ordered phases of cobalt have been prepared on Mo(110). The structure of the Co overlayer depends on its coverage. New reaction pathways are opened on Co-covered Mo(110) and reaction selectivity is dramatically changed for the two cases investigated to date - 2,5-dihydrothiophene and methanethiol desulfurization. The Mo(110)-(9x2)-Co overlayer exhibits particularly interesting chemistry and has been the main focus of our work.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

Figure 1: Reaction scheme for 2,5-dihydrothiophene on Mo(110)-p(4x1)-S.

Figure 2: Temperature programmed reaction data for methanethiol adsorbed on Mo(110) and Mo(110)-(9 $\times$ 2)-Co at 120 K.

A new reaction channel, butadiene hydrogenation to butene, is observed for 2,5-dihydrothiophene desulfurization on Mo(110)-(9x2)-Co. Interestingly, the overall selectivity for 2,5-dihydrothiophene desulfurization is lower on the Co-covered surface than on clean Mo(110) itself. This is attributed to the C-H bond activation induced by the cobalt. On clean Mo(110), butadiene is formed via intramolecular elimination without any hydrogenation or dehydrogenation. The low barrier for elimination on the clean surface leads to the high selectivity.

The Mo(110)-(9x2)-Co surface exhibits unique chemical properties in the desulfurization of methanethiol. Specifically, the rate of methane formation from methyl thiolate hydrogenolysis is increased as sulfur is deposited during the course of reaction. The increased rate is apparent from a comparison of the line-shapes of the methane peaks in temperature programmed reaction spectra of methanethiol on initially clean Mo(110) and the Mo(110)-(9x2)-Co surfaces (Figure 2). The sharp line shape is indicative of an autocatalytic process. The broad line shape for clean Mo(110) indicates a decline in the hydrogenolysis rate as sulfur is deposited; the more usual behavior. The acceleration of methane production as sulfur is deposited on the Mo(110)-(9x2)-Co surface is tentatively attributed to a structural transition in the cobalt layer induced by sulfur. Low energy electron diffraction data obtained prior to and following methanethiol reaction indicate a disordering of the cobalt overlayer after temperature programmed reaction. More detailed studies of the cobalt overlayer structures are planned to test this hypothesis. These preliminary results suggest that there is a rich chemistry associated with complex modified surfaces that can be exploited as a means of developing an understanding of the role that changes in surface structure may play in determining reactivity.

We have also been developing methods for exploiting vibrational spectroscopy as a means of determining molecular orientation. Knowledge of the molecular orientation is important input for semiempirical electronic structure calculations which provide qualitative descriptions of adsorbate-surface bonding. Intramolecular vibrational coupling must be taken into account in the analysis of vibrational data for adsorbed species; assignments do not always follow directly from gas-phase assignments due to changes in the coupling induced by bonding to the surface. As part of this effort, we have performed *ab initio* valence force field calculations which model the interaction of 2-propoxide with Mo as a means of making reliable

vibrational assignments. We have obtained excellent agreement between theory and experiment for the case of four different isotopically-labeled 2-propoxide isomers (Fig. 3). The shifts in the peaks shown, which have a significant component of the C-O stretch, are due to changes in the coupling of $\nu(\text{C-O})$ to other vibrational modes. Accordingly, we have been able to determine that the C-O bond of 2-propoxide is oriented perpendicularly to the Mo(110) plane based on an intensity analysis of the vibrational data. Similar approaches have been adopted in order to estimate the orientations of methyl thiolate on Mo(110) and 2,5-dihydrothiophene on Mo(110)-p(4x1)-S.

During the next grant period, we plan to focus on structural and reactivity studies of the modified surfaces and are particularly interested in mixed phases of Co and S on Mo(110).

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Figure 3: Electron energy loss spectra for four different isotopomers of 2-propoxide on Mo(110). Only the C-O stretch region is shown. The bars are the calculated vibrational frequencies.

Publications, 1991-92, Cynthia M. Friend

★Support by DOE grant, No. DE-FGO2-84-ER13289

- 1.) X. Xu and C. M. Friend, "Partial Oxidation Without Allylic C-H Bond Activation: The Conversion of Propene to Acetone on Rh(111)-p(2×2)-O". *J. Am. Chem. Soc.*, 113 (18), 6779-85, 1991.
- 2.) C. M. Friend and X. Xu, "Reactions on Transition Metal Surfaces". *Ann. Rev. of Phys. Chem.*, 42, 251-278, 1991.
- ★3.) B. C. Wiegand, P. E. Uvdal, J. G. Serafin, and C. M. Friend, "Selective γ C-H Bond Cleavage in Alkoxides: 2-Propanol on Mo(110)". *J. Am. Chem. Soc.*, 113 (17), 6686-6687, 1991.
- 4.) X. Xu and C. M. Friend, "Selective β -Elimination in the Reaction of 2-Propanol to Acetone on Rh(111)-p(2×1)-O". *Surf. Sci.*, 260, 14-22, 1992.
- 5.) X. Xu and C. M. Friend, "Partial Oxidation of Olefins: Conversion of Isobutene to *tert*-Butanol on Oxygen-Covered Rh(111)". *J. Phys. Chem.*, 95(26), 10753-10759, 1991.
- 6.) X. Xu and C. M. Friend, "Enhanced Kinetic Stability of γ -C-H Bonds in Surface Alkoxides: The Reactions of *tert*-Butanol on Clean and Oxygen-Covered Rh(111)". *Langmuir*, 8(4), 1103-1111, 1992.
- 7.) X. Xu and C. M. Friend, "The Effect of Rhodium Environment on Oxidation Mechanism: Conversion of Norbornene to Norbornanone on Rh(111)-p(2×1)-O". *J. Am. Chem. Soc.*, 113, 8572-8573, 1991.
- ★8.) B. C. Wiegand, P. Uvdal, and C. M. Friend, "Probing the Kinetics for Thiol Desulfurization: The Reactions of *tert*-Butanethiol on Mo(110)", *J. Phys. Chem.*, 96(11), 4527-4533, 1992.

Publications, 1991-92, Cynthia M. Friend

★Support by DOE grant, No. DE-FGO2-84-ER13289

- ★9). P. Uvdal, B. C. Wiegand, J. G. Serafin and C. M. Friend, "Isotopic Labeling as a Tool to Establish Intramolecular Vibrational Coupling: The Reaction of 2-Propanol on Mo(110)", *J. Chem. Phys.*, *Submitted*, 1992.
- ★10). B. C. Wiegand, P.C. Uvdal, J. G. Serafin, "Competition Between C-O and 1-C-H Bond Scission During Deoxygenation: The Reactions of 1-Propanol on Mo(110)", *J. Phys. Chem.*, 96(12), 5063-5069, 1992.
- ★11). C. M. Friend, "Desulfurization Reactions Induced by Transition Metal Surfaces", *Surface Chemistry*, (R. J. Madix (ed.), Springer-Verlag), *Submitted*, 1991.
- ★12). B. C. Wiegand and C. M. Friend, "Model Studies of Desulfurization Reactions on Metal Surfaces and in Organometallic Complexes, *Chem. Reviews*, 92(4), 1992.
- ★13). B. C. Wiegand, P.C. Uvdal, and C. M. Friend, "The Local Structure of Adsorbed Methyl Thiolate Intermediate: The Reactions of Methanethiol on Mo(110)", *Surface Science*, *Submitted*, 1992.
- ★14.) H. Xu and C.M. Friend, "The Acceleration of Desulfurization by Sulfur Deposition: The Reactions of Methanethiol on Cobalt-Covered Mo(110)." *J. Am. Chem. Soc.*, *Submitted*, 1992.
- ★15.) H. Xu and C.M. Friend, "The Effect of Sulfur on Desulfurization Kinetics and Selectivity: 2,5-Dihydrothiophene on Mo(110)-p(4x1)-S." *J. Phys. Chem.*, *Submitted*.

*budget reviewed.
ds*

END

**DATE
FILMED**

12 / 16 / 92