Lawrence Berkeley Laboratory

UNIVERSITY OF CALIFORNIA

Accelerator & Fusion Research Division

Received by OSTI

NOV 25 1986

Presented at the Applied Superconductivity Conference,
Baltimore, MD, September 29-October 3, 1986

EVALUATION OF VARIOUS FABRICATION TECHNIQUES FOR FABRICATION OF FINE FILAMENT NbTi SUPERCONDUCTORS

R.M. Scanlan, J. Royet, and R. Hannaford

September 1986

LEGAL NOTICE

This book was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

LBL-21230
SSC- MAG 76
SSC- N- 249

LBL--21230

DE87 002571

EVALUATION OF VARIOUS FABRICATION TECHNIQUES FOR FABRICATION
OF FINE FILAMENT NbTi SUPERCONDUCTORS*

R.M. Scanlan, J. Royet, and R. Hannaford

Lawrence Berkeley Laboratory
University of California
Berkeley, CA 94720, USA

Presented at the 1986 Applied Superconductivity Conference, Baltimore, MD
September 29-October 3, 1986

*This work is supported by the Director, Office of Energy Research, Office of High Energy and Nuclear Physics, High Energy Physics Division, U.S. Department of Energy, under Contract No. DE-AC03-76SF00098.

MASTER
DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

R.M. Scanlan, John Royet and R. Hannaford

Lawrence Berkeley Laboratory
University of California
Berkeley, CA 94720**Abstract**

The successful fabrication of a fine filament high current density NbTi superconductor can have a significant impact on the cost of the Superconducting Supercollider. Consequently, we have been exploring various approaches for fabricating this type of superconductor, in collaboration with several superconductor wire manufacturers. The techniques investigated include double conventional hot extrusion, large single stack conventional hot extrusion, and warm hydrostatic extrusion. The important conductor properties (critical current density, piece length, yield, and cost) will be compared for the various approaches. Finally, the feasibility of manufacturing production quantities of a fine filament conductor will be assessed.

Introduction

In September, 1986, the Magnet Selection Advisory Panel chose a high field magnet design for the Superconducting Super Collider (SSC) dipole magnets. The conductor specified for these magnets is NbTi with a filament diameter of 5 μm and minimum critical current density (J_c , 4.2 K) of 2750 A/mm² at 5T and a J_c (4.2 K) of 1100 A/mm² at 8 T. These values are considerably higher than those specified for existing dipoles in the Tevatron or those under construction for the HERA project (see Table I.). Consequently, a conductor development program is underway to insure that superconducting cable can be made to these specifications in a cost effective manner. The initial goal for this development program was to produce industrial-size billets of multifilamentary NbTi with a filament size of 18-20 μm and a J_c (4.2 K, 5T) greater than 2400 A/mm². This goal was met in 1984¹ and the results were confirmed by the fabrication of 12 additional billets². However, if strands with 20 μm filaments are used in the SSC dipoles, powerful correction coils are necessary in order to correct the field distortion produced at the accelerator injection field (0.3T). This field distortion is produced by magnetization effects which are proportional to the size of the superconductor filaments and hence can be reduced by reducing the filament diameter. Consequently, a second phase conductor development program was initiated in 1984 with the goal of producing strands with high J_c (> 2750 A/mm² at 5T) and a fine filament diameter (< 5 μm).

Experimental Details of the Strand Development Program

Initial experimental results^{3,4} and a review of the published literature on fine filament NbTi conductors^{6,7} indicated that conventional fabrication techniques would not produce fine filaments with acceptable properties. One problem is the formation of a brittle intermetallic compound layer between the Cu matrix and the NbTi filaments as a

Table I. Wire and Cable Specifications for Accelerator Dipole Magnets

Dimensional Tolerances	Tevatron/CBA	HERA	SSC
Strand	± 0.0076 mm	± 0.01 mm	± 0.0025 mm
Surface	Sn/Ag Coating	Sn/Ag Coating	Bare
Fil.Diam.	8 μm	< 20 μm	5 μm
Twist Pitch	13 mm	25 mm	25 mm
		+0.2	
Cu:SC	1.8/1	1.8	$\pm 2\%$
		-0.1	
Keystone Angle	2.05°	2.2°	1.68°
Cable	+0.000	± 0.02	± 0.0127
Mid-thickness (mm)	outer edge		
	-0.025		
	+0.000		
	inner edge		
	-0.025		
Width (mm)	+0.000	± 0.025	± 0.025
	-0.025		
Cable Edge	-		-
Radius		> .25 mm	
Min.Length			
Strand (m)	305	400	764
Min. Length	-	385 outer	675 outer
Cable (m)	-	600 inner	542 inner
Dim. Q.C.	10-stack	10-stack	10-stack
RRR	45	60	70
J_c	1800 A/mm ²	2400 A/mm ²	2750 A/mm ²
	5T	5T	5T
			1100 A/mm ²
			8T

result of the interdiffusion which occurs during the thermomechanical processing of the composite. Another problem is the progressive deterioration of the uniform filament cross section, described as "sausaging", which becomes much more pronounced as the filament diameter is reduced. Sausaging behavior is caused by the intermetallic formation, but can also result from other causes and be present in the absence of intermetallic compound formation, as described below.

Fine filament fabrication problems have also been studied in detail for the case of multifilamentary Nb₃Sn, since, in this case, Nb₃Sn is produced by the diffusion and reaction between Nb filaments and Sn in the bronze matrix. In order to limit reaction temperature and time, the Nb filament size must be maintained at 5 μm or less. The results of several fabrication studies^{8,9,10} on Nb₃Sn have been reported, and these studies provided useful direction for resolving the problems associated with the fabrication of fine filament NbTi.

Several potential processes for the fabrication of fine filament NbTi were identified, and a matrix of experiments (Table II.) were begun in order to evaluate both technical feasibility and cost. Two

*This work was supported by the Director, Office of Energy Research, Office of High Energy and Nuclear Physics, High Energy Physics Division, U.S. Dept. of Energy under Contract DE-AC03-76SF00098.

approaches for eliminating the problem of intermetallic compound formation were investigated. First, a diffusion barrier was applied around each NbTi filament in order to prevent the interdiffusion of Cu and Ti. This approach was investigated in research and development billets, processed at Supercon^{11,12} and Intermagnetics General Corp. (IGC)^{11,13}. Although the use of diffusion barriers had been described^{5,7} or alluded to⁶ previously, it was necessary to demonstrate that this approach could be used in large scale fabrication and in a cost effective manner.

**Table II. Billets Fabricated in SSC Phase I
Fine Filament R&D Program**

<u>Designation</u> (Subcon- tractor)	<u>Filament Size</u> at Final <u>Wire Diam.</u>	<u>Extrusion</u> <u>Technique</u>	<u>Experimental</u> <u>Goals</u>
LBL-1 (Supercon)	8 μ m	Lg. single stack	High J _c , diffusion barrier
LBL-2 (Supercon)	6 μ m	Lg. single stack	demo, eco- nomics, fil. spacing
5914-12 (IGC)	5 μ m	Dbl. hot extrusion	
5914-221 (IGC)	2.7 μ m	Dbl. hot extrusion	Fine fil., diffusion barrier
5914-222	2.7 μ m	Dbl. hot extrusion	demo, eco- nomics, fil. spacing
5940-21 (IGC)	5 μ m	Lg. single stack	Production experience
5940-22 (IGC)	5 μ m	Lg. single stack	Production experience
5941-1 (IGC)	5 μ m	Lg. single stack	Alt. μ m source eval.
Hydrostatic-1 (Nat'l Standard)	2.7 μ m	Warm hydrost.	Hydrostatic extrusion eval., fil. spacing
Hydrostatic-2 (Nat'l Standard)	2.7 μ m	Warm hydrost.	Hydrostatic extrusion eval., fil. spacing
Hydrostatic-3 (Nat'l Standard)	2.7 μ m	Warm hydrost.	Hydrostatic extrusion eval., fil. spacing

The large single stack billets (LBL-1 and LBL-2) showed the best critical current results. Samples with optimized heat treatments yielded J_c values

In the first phase of the fine filament program, Supercon constructed two production-size billets (305 mm diameter); one was designed for SSC inner layer cable and the other for SSC outer layer cable. Likewise, IGC constructed two billets, 254 mm in diameter, one with a copper to superconductor ratio of 1.3:1, and the other with a ratio of 1.8:1 (see Table II for additional details). Finally, the feasibility of using reduced temperature processing in order to reduce intermetallic formation without the use of a diffusion barrier was investigated by use of warm hydrostatic extrusion and short time intermediate heat treatments. This option was explored with three billets, 165 mm in diameter, extruded at the National Standards production facility in Perth, Scotland.

In order to reach the requisite large number of filaments in the composite strands, two billet assembly approaches were investigated. Billets LBL-1 and LBL-2 were stacked at Supercon by assembling approximately 4,165 Cu-clad monofilament NbTi rods. The advantages of this large single stack approach include (1) a uniform environment which is

Fig. 1. SEM Micrographs of Extracted Filaments From The Hydrostatic Extrusion Billet Which Was Processed with 10 hr., 375°C Heat Treatments.

over 3100 A/mm² at 5T and over 1170 A/mm² at 8T. The n-values (for a discussion of the relationship between n-values, J_c and filament quality, see paper MF-7, these proceedings) for these strands were quite high - approximately 30 for 8T and 50-60 for 5T measurements. The double stack billets yielded J_c values in the range of 2300-2500 A/mm² at 5T and n-values of about 25. The hydrostatic extrusion billets yielded low J_c values and low n values even in the absence of any appreciable intermetallic compound formation. For example, one sample was processed with minimal heat treatments (three at 375°C for 10 hrs.). SEM analysis (Fig. 1) showed little intermetallic compound formation, but considerable sausaging; this result was confirmed by critical current measurements which yielded n-values of approximately 25.

The results for the hydrostatic extrusion billets were dominated by filament sausaging behavior and can be explained by examining the inter-filament spacing compared with the spacing used in the other billets (Table III.). Billets LBL-1 and LBL-2 had uniformly spaced filaments and showed no tendency toward sausaging (Fig. 2). Billets 5914 had bundles of closely spaced filaments separated by thick copper layers. The filaments within the bundles were uniform, but those at the edges exhibited sausaging (Fig. 3). The hydrostatic extrusion billets, with comparatively wide spacing within the

Table III.
Filament Spacing in Fine Filament Material

Material	Fil. Diam.	Spacing/ Fil. Diam.	Spacing at Final Wire Size	Fil. Quality
LBL-1	8 μm	0.11	0.9 μm	Excellent n = 60
LBL-2	6 μm	0.17	1.0 μm	Excellent n = 50
5914-12	5 μm	0.2	1.0 μm	Sausaging at edge of 7X bundle n = 25 at 5 μm fil. diam. n = 13 at 2 μm fil. diam.
5914-221	2.7 μm	0.14	0.36 μm	Sausaging at edge of 19X bundle n = 25
Hydrostatic	2.7 μm	0.4	1.0 μm	Sausaging at edge and interior of 19X bundle n = 10-25

[10μ]

XBB 866-4560

Fig. 2. LBL-1 - Fine Filament NbTi Made by Large Single Stack Approach at Supercon, Inc.

bundles, showed sausaging, both at the edges and within the filament bundles.

From these results, we conclude that filament spacing must be maintained uniform and close together. However, for this application in SSC dipoles, a minimum spacing requirement has also been identified. Ghosh and Sampson¹⁴ have shown that a filament spacing of about 0.4-0.5 μm is required to avoid electrical coupling of the filaments at the SSC injection field of 0.3T. This coupling is believed to originate from a proximity effect and may be enhanced in this case due to the high purity copper matrix (the high purity is maintained by the diffusion barrier). Thus, filament spacing must be chosen to satisfy both the mechanical stability and the electrical requirements; we conclude from this study that a value of spacing to filament diameter of about 0.15 is appropriate.

Fig. 3. Micrograph of Billet 5914-221 Showing Filament Sausaging at Edge of 19 Filament Bundles.

With regard to the evaluation of drawability, initial samples from all billets, except the 5940-5941 series, showed some problems. Several different sources for these drawing problems have been identified and eliminated in subsequent processing. Copper-to-copper bonding problems were present in portions of billets 5914-221, 5914-222, LBL-1, and the hydrostatic extrusion billets. The problem is due to a combination of the large interfacial surface area present in these billets, and low extrusion temperatures employed. The problem was most severe for the hydrostatic billets which were heated to 200°C and extruded at a rather low ratio area reduction of 10 (exit temperature was about 450-500°C). An attempt was made to remove these defects by hot isostatic pressing the extruded rods at a 25 mm diameter; results showed a partial improvement, but some unbonded areas remained. Subsequent attempts to draw material with these defects resulted in wire breakage at the fine wire sizes. These studies confirm that a high extrusion temperature, or a pre-extrusion bonding step, is desirable for achieving high product yields.

After the portions of the billets showing bonding problems were set aside, additional drawing

problems were encountered. Experiments were performed in which the drawing die parameters were changed and drawability improved dramatically. The tentative conclusion is that the high J_c fine filament composites develop a high tensile strength and thus require somewhat different processing than more conventional NbTi composites. After the die changes were made, both billet LBL-2 and billet 5914-221 yielded over 80% of the material in lengths greater than 3,000 m; billet 5940-21, produced after these problems were identified and corrected, yielded one length over 12,000 m length and over 85% of the material in lengths over 3,000 m.

Cable Produced from Fine Filament NbTi

A series of 23-strand and 30-strand cables were made to SSC specifications from the strands described above. When compared with cables made to the same specifications from strands with 18-20 μm filament size, these cables showed two primary differences. First, the amount of degradation in critical current which occurred during cabling was reduced from typically 10-15% for the large filament material to 0-8% from the fine filament material. Second, the strands were more difficult to cable and showed some tendency to protrude from the cable when the cable was bent around a small diameter under light tension. In order to present this information in a more quantitative manner, we have developed a springback test for assessing the cabling ease of various strands. Results indicate that the high J_c fine filament strands have a relatively high springback value. Several experiments are underway to reduce this springback. First, we find that cold-worked strands exhibit less springback than strands in which the Cu matrix is annealed, so we are making cables with cold worked strands for evaluation. Second, we are studying a modified heat treatment sequence with less cold work in the final stage to see if such processing will produce a high J_c strand with less springback.

Conclusions

1. The use of diffusion barriers appears to be a reliable and cost effective modification to conventional fabrication for applications where fine filaments are required.

2. The large single stack approach to billet assembly yields the best product for the SSC specification of 5 μm filaments in 0.6 to 0.8 mm diameter wires. For finer filaments or other applications requiring a larger number of filaments, it may be necessary to use a double stacking approach. If so, the largest feasible number of elements should be stacked together in order to minimize the number of sausaged filaments which occur at the perimeter of the stack.

3. Fine filament strands can be produced to the SSC specification of 2750 A/mm² in a reliable and cost effective manner.

4. Cable made from high J_c fine filament strands shows decreased degradation, but a greater springback tendency, than cable made from strands with 20 μm diameter filaments and $J_c = 2400$ A/mm² at 5T.

Acknowledgements

We acknowledge the excellent work and enthusiastic participation of the groups at Supercon, Inc. and Intermagnetics General Corp. in this program. Prof. D. LaBalestier (Univ. of Wisconsin) made many useful suggestions and measurements during

the course of these experiments. W. B. Sampson, M. Garber, and A. Ghosh of Brookhaven National Laboratory made many useful measurements and provided the explanation of proximity effect coupling to account for the magnetization behavior of closely spaced fine filaments.

References

1. D. C. Larbalestier, A. W. West, W. Starch, W. Warnes, P. Lee, W. K. McDonald, P. O'Larey, K. Hemachalam, B. Zeitlin, R. Scanlan, and C. Taylor, "High Critical Current Densities in Industrial Scale Composites Made from High Homogeneity Nb 46.5 Ti," IEEE Trans. on Magnetics, MAG 21, 265 (1985).
2. R. M. Scanlan, A. F. Greene, and M. Suenaga, ICFA Workshop on Superconducting Magnets and Cryogenics, Brookhaven National Laboratory (May, 1986).
3. M. Garber, M. Suenaga, W. B. Sampson, and R. L. Sabatini, "Effect of CuTi compound formation on the characteristics of NbTi accelerator magnet wire," in Proc. 1985 Particle Accelerator Conf., Vancouver (May, 1985).
4. D. C. Larbalestier, L. Chengren, W. Starch, P. J. Lee, "Limitation of Critical Current Density by Intermetallic Formation in Fine Filament Nb-Ti Superconductors," IEEE Trans. on Magnetics, MAG 21, 39 (1985).
5. M. T. Taylor, C. Graeme-Barber, A. C. Barber, and R. B. Reed, Cryogenics 11, 224-226 (1971).
6. E. Gregory, "Manufacture of Superconducting Materials," R. W. Meyerhoff, ed., American Society of Metals, Metals Park, Ohio, 1-16 (1977).
7. P. Dubots, et al., in Proc. ICEC 8, 505 (1980).
8. P. A. Sanger 9th Symp. on Eng. Prob. of Fusion Research, IEEE Publ. 81 CH 1715, 1333 (1981).
9. R. M. Scanlan, D. W. Cornish, C. R. Spencer, E. Gregory, and E. Adam, *ibid*, 1317.
10. D. B. Smathers, K. R. Marken, D. C. Larbalestier, and R. M. Scanlan, IEEE Trans. on Magnetics MAG 19, 1417 (1983).
11. R. M. Scanlan, J. Royet, and C. E. Taylor, "Superconducting Materials for the SSC," paper CZ-1, in Proc. Int. Cryo. Materials Conf., M.I.T., Cambridge, MA, August, 1985, LBL-19394 (1985).
12. T. S. Kreilick, E. Gregory, J. Wong, paper CZ-6, *ibid*.
13. K. Hemachalam, C. G. King, B. A. Zeitlin, and R. M. Scanlan, paper CZ-5, *ibid*.
14. A. K. Ghosh and W. B. Sampson, paper MI-2, elsewhere in these proceedings.

This report was done with support from the Department of Energy. Any conclusions or opinions expressed in this report represent solely those of the author(s) and not necessarily those of The Regents of the University of California, the Lawrence Berkeley Laboratory or the Department of Energy.

Reference to a company or product name does not imply approval or recommendation of the product by the University of California or the U.S. Department of Energy to the exclusion of others that may be suitable.