DOE/PC/88935 - T12

College of Earth and Mineral Sciences

PENNSTATE

Received OSTI

AUG 24 1992

INHIBITION OF RETROGRESSIVE REACTIONS IN COAL/PETROLEUM CO-PROCESSING

Reporting Period: September 1 - November 30, 1988

Harold H. Schobert
Jasna Tomic

December 1988
Contract No. DE-FG22-88PC88935

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

ab
DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

PENN STATE

College of Earth and Mineral Sciences

DOE/PC/88935--T12

DE92 019730

Undergraduate Majors

Ceramic Science and Engineering, Fuel Science, Metals Science and Engineering, Polymer Science; Mineral Economics; Mining Engineering, Petroleum and Natural Gas Engineering; Earth Sciences, Geosciences; Geography; Meteorology.

Graduate Programs and Fields of Research

Ceramic Science and Engineering, Fuel Science, Metals Science and Engineering, Polymer Science; Mineral Economics; Mining Engineering, Mineral Processing, Petroleum and Natural Gas Engineering; Geochemistry and Mineralogy, Geology, Geophysics; Geography; Meteorology.

Universitywide Interdisciplinary Graduate Programs Involving EMS Faculty and Students

Earth Sciences, Ecology, Environmental Pollution Control Engineering, Mineral Engineering Management, Solid State Science.

Associate Degree Programs

Metallurgical Engineering Technology (Shenango Valley Campus).

Interdisciplinary Research Groups Centered in the College

C. Drew Stahl Center for Advanced Oil Recovery, Center for Advanced Materials, Coal Research Section, Earth System Science Center, Mining and Mineral Resources Research Institute, Ore Deposits Research Group.

Analytical and Characterization Laboratories (Mineral Constitution Laboratories)

Services available include: classical chemical analysis of metals and silicate and carbonate rocks; X-ray diffraction and fluorescence; electron microscopy and diffraction; electron microprobe analysis; atomic absorption analysis; spectrochemical analysis; surface analysis by secondary ion mass spectrometry (SIMS); and scanning electron microscopy (SEM).

The Pennsylvania State University, in compliance with federal and state laws, is committed to the policy that all persons shall have equal access to programs, admission, and employment without regard to race, religion, sex, national origin, handicap, age, or status as a disabled or Vietnam-era veteran. Direct all affirmative action inquiries to the Affirmative Action Officer, Suzanne Brooks, 201 Willard Building, University Park, PA 16802; (814) 863-0471.
U. Ed. 87-1027

Produced by the Penn State Department of Publications

INHIBITION OF RETROGRESSIVE REACTIONS
IN COAL/PETROLEUM CO-PROCESSING

Reporting Period: September 1 - November 30, 1988

Harold H. Schobert
Jasna Tomic

December 1988
Contract No. DE-FG22-88PC88935

TABLE OF CONTENTS

	<u>Page</u>
OBJECTIVE	1
SUMMARY	1
TASK 1. Selection of Feedstocks	1
TASK 2. Identification of Solvation and Dispersion Relationships	3
APPENDIX Analytical Data on Coal Samples	4

OBJECTIVE

The overall objective of this project is to develop a fundamental understanding of the reactions occurring at the onset of coke formation during the co-processing of coals with petroleum residua. The specific objectives include the examination of chemical components, or groups of components, in coals and petroleum feedstocks to quantify and rank the effects of these components on retardation or enhancement of coke formation. The work involves bench scale reactions in microautoclaves supplemented by optical microscopy of carbonaceous residues and instrumental analyses such as FTIR and ^{13}C NMR.

SUMMARY

During this reporting period the candidate coals have been selected, samples of the coals have been obtained, and a wealth of analytical data on the coals has also been obtained. Coal samples have been submitted for characterization by solid state ^{13}C NMR, but the spectra have not yet been run. The necessary apparatus and solvents for performing sequential elution by solvents chromatographic separation of petroleum materials has been obtained and is in the process of being set up.

TASK 1. SELECTION OF FEEDSTOCKS

Five coals have been selected for use in this project. The coals range in rank from subbituminous B through high volatile A

bituminous, and range in carbon content from 76.56% to 85.20% (dmmf basis). The samples were obtained from the Penn State/DOE Coal Sample Bank, complete with a full set of analytical data. All of the relevant data obtained from the Sample Bank is provided as an appendix to this report. For convenience, a few relevant parameters are summarized in the table below (on a dmmf basis).

Table 1. Properties of Coal Feedstocks

<u>Sample No.</u>	<u>Seam Name</u>	<u>Rank</u>	<u>Carbon</u>	<u>Vitrinite</u>	<u>FSI</u>
PSOC-1488	Dietz	subB	76.56	88.6	0.0
PSOC-1498	Wadge	hvc	78.24	89.2	0.5
PSOC-1501	Juanita C	hvb	81.17	92.4	2.0
PSOC-1504	Upper Sunnyside	hva	82.88	86.9	5.5
PSOC-1448	York Canyon	hva	85.20	83.7	8.0

In addition to wanting to obtain a suite of samples having a range of ranks, carbon contents, and free swelling indices, some of these coals were also selected because they have been used in collateral research on direct liquefaction at Penn State. Consequently, some data on the behavior of these coals in a hydrogen atmosphere is already available at no cost to this project.

These coal samples have been submitted to the NMR center maintained by the Penn State Chemistry Department for solid state ^{13}C NMR spectroscopy. Results have not yet been obtained, due to lengthy down-time of the instrument. If this problem persists into the next reporting period, arrangements will be made to obtain the spectra off campus.

The work forecast for the coming quarter is a) to obtain the NMR spectra of the coal samples, b) to obtain the FTIR spectra of the coals, and c) to select and obtain samples of the petroleum materials.

TASK 2. IDENTIFICATION OF SOLVATION AND DISPERSION RELATIONSHIPS

This task is intended to test the hypothesis that coking can be retarded by having as much as possible of the reacting material in a single homogeneous liquid phase. Therefore experiments will be conducted by reacting coals with model compounds and with fractions of the petroleum materials. The petroleum fractions will be obtained by the sequential elution by solvents chromatography procedure. During this reporting period, most of the necessary glassware, apparatus, and solvents for SESC have been ordered and the apparatus is being assembled. To expedite this phase of the work and to keep costs at a reasonable level, the SESC systems are being shared with a collateral DOE project (Thermal Stability of Jet Fuels) now underway in our laboratory.

The work forecast for the coming quarter is to begin SESC separation of the petroleum materials once the appropriate samples have been obtained.

APPENDIX

The Appendix contains the full suite of analytical data on the five coals selected for this project.

SAMPLE LOCATION:

COUNTRY -> USA
STATE -> MONTANA
COUNTY -> BIGHORN
TOWNSHIP ->
CITY -> DECKER

COAL PROVINCE -> NORTHERN GREAT PLAINS
REGION -> FORT UNION

MAP REFERENCE: LATITUDE -> 45 D 6 M 41 S
LONGITUDE -> 106 D 53 M 53 S
QUADRANGLE -> PEARL SCHOOL (7.5')

SAMPLE IDENTIFICATION:

PSU NUMBER -> PSOC-1488
SEAM NAME -> DIETZ
ALTERNATE SEAM NAME ->
APPARENT RANK -> SUBBIT B

SAMPLE HISTORY:

SAMPLING DATE & AGENCY -> 7/17/85 ; PSU

SAMPLE TYPE -> CHANNEL-BENCH

ADDITIONAL INFORMATION ->

MINE INFORMATION:

RESERVES ->
ANNUAL PRODUCTION ->
LIFE EXPECTANCY ->
MINING METHOD -> STRIP

SEAM INFORMATION:

AGE OF SEAM -> PALEO.
GROUP -> FORT UNION
FORMATION ->
SEAM THICKNESS -> 40 FT. 0 IN.

PSU NUMBER
SEAM NAME
ALTERNATE SEAM NAME
APPARENT RANK

COUNTRY
STATE

PSOC-1488
DIETZ
SUBBIT B

PSOC-1488
DIETZ
SUBBIT B

PSOC-1488
DIETZ
SUBBIT B

*** CHEMICAL DATA ***

PROXIMATE ANALYSIS		AS REC'D	DRY	DAF	DMMF(PARR)
% MOISTURE	23.66				
% ASH	4.08	5.35			
% VOLATILE	31.95	41.85		44.22	43.88
% FIXED CARBON	40.31	52.80		55.78	56.12

% EQUILIBRIUM MOISTURE = 24.05
MM-FREE = 25.22

ULTIMATE ANALYSIS		AS REC'D	DRY	DAF	DMMF(PARR)	ELEMENTAL ANALYSIS		DRY	DMMF(MOD.P.)	DMMF(DIR.)
% ASH	4.08	5.35				(6.05%MM)			(6.09%MM)	(%MM)
% CARBON	54.91	71.93		76.00	76.56	% CARBON		71.91	76.57	
% HYDROGEN	3.78 (*)	4.95		5.23	5.27	% HYDROGEN		4.88	5.20	
% NITROGEN	0.68	0.89		0.94	0.95	% NITROGEN		0.89	0.95	
% TOTAL SULFUR	0.38	0.50		0.53		% ORGANIC SULFUR		0.48	0.51	
% OXYGEN(DIFF)	12.50 (*)	16.38		17.31	17.22	% OXYGEN(DIFF)		15.75	16.78	

(*)-EXCLUDES MOISTURE

SULFUR FORMS		% PYRITIC	% SULFATIC	% ORGANIC	% TOTAL	DRY % CHLORINE =	DRY % CO2 =
DRY	0.02	0.00	0.48	0.50	0.50	0.07	0.09
DAF	0.02	0.00	0.51	0.53	0.53	MOTT-SPOONER DIFFERENCE = 91.	

CALORIFIC VALUE (GROSS, BTU/LB)		AS REC'D MOIST.	EQUIL. MOIST.	ATOM RATIOS (DMMF)	PARR	MOD. PARR	DIRECT
MM-CONTAINING	12519.	9557.	9508.	ATOMIC H/C	0.8266	0.8153	
MM-FREE (PARR)	13299.	10000.	9946.	ATOMIC O/C	0.1688	0.1645	
MM-FREE (MOD. P)	13330.	10022.	9968.				
NET CV, DMMF BTU/LB	12841.						

PSU NUMBER
SEAM NAME
ALTERNATE SEAM NAME
APPARENT RANK

SAMPLE IDENTIFICATION:

PSU NUMBER
SEAM NAME
ALTERNATE SEAM NAME
APPARENT RANK

-> PSOC-1488
-> DIETZ
-> SUBBIT B

SAMPLE LOCATION:

COUNTRY -> USA
STATE -> MONTANA

** PENN STATE COAL DATA BASE **
**
** PSOC-1488
**
** 09/22/88
** PAGE 3
**

***** RANK CALCULATIONS *****

APPARENT RANK (AS REC'D MOIST.) -> SUBBIT B
ASTM RANK (EQUIL. MOIST.) -> SUBBIT B
REFLECTANCE RANK CATEGORY -> REPORTED RANK : ->

***** PETROGRAPHIC DATA *****

MACERAL COMPOSITION (WHITE LIGHT ANALYSIS)

-----	TEXT- INITE	ULM- INITE	HUMO- DETRINITE	GEL- INITE	CORPO- HUMINITE	SPOR- INITE	CUT- INITE	RES- INITE	ALG- INITE	FUS- INITE	SEMI- FUSINITE	MAC- RINITE	SCLERO- TINITE
DMMF VOL. %	0.0	81.7	1.2	5.1	0.6	2.9	0.0	0.6	0.0	2.5	3.0	1.9	0.5
DRY WT. %	0.0	76.8	1.1	4.8	0.6	2.7	0.0	0.6	0.0	2.3	2.8	1.8	0.5
DMMF VOL % HUMINITE =	88.6												
	6.1 % MM.												

ULMINITE REFLECTANCE DATA:

HIGH: 0.56 LOW: 0.40 MEAN-MAX: 0.47

***** C A K I N G A N D M E C H A N I C A L P R O P E R T I E S *****

GIESELER COAL PLASTOMETER:

GRAY-KING COKE TYPE

INIT. SOFTENING TEMP
TEMP. MAX. FLUIDITY
SOLIDIFICATION TEMP.
FLUID TEMP. RANGE

42.1

0.0

VICKERS HARDNESS NUMBER

MAXIMUM FLUIDITY
WASHABILITY DATA AVAILABLE? NO

** PENN STATE COAL DATA BASE **
 ** PSOC-1488 **
 ** 09/22/88 **
 ** PAGE 4 **

SAMPLE LOCATION:

COUNTRY -> USA
 STATE -> MONTANA

SAMPLE IDENTIFICATION:

PSU NUMBER -> PSOC-1488
 SEAM NAME -> DIETZ
 ALTERNATE SEAM NAME ->
 APPARENT RANK -> SUBBIT B

% HTA = 4.53

MAJOR ELEMENT ANALYSIS

	SI02	AL203	T102	FE203	MGO	CAO	NA2O	K2O	P2O5	S03
OXIDE % OF HTA	32.5	19.6	1.46	5.33	5.62	16.2	3.17	0.37	0.24	12.5
ELEMENT % OF TOTAL DRY COAL	SI	AL	TI	FE	MG	CA	NA	K	P	S
	0.7	0.5	0.04	0.17	0.15	0.5	0.11	0.01	0.005	0.5

% HTA = 4.53

TRACE ELEMENT ANALYSIS

	PPM HTA	PPM TOTAL COAL	PPM HTA	PPM TOTAL COAL	PPM HTA	PPM TOTAL COAL	VOLATILES	PPM TOTAL COAL
AG							AS	
B							BR	
BA	8010.	363.					CD	
BE	7.0	0.3					CL	700.
BI							F	
CE							HG	
CO							SB	
CR	95.	4.					SE	
CU	190.	9.						
GA								

** PENN STATE COAL DATA BASE **
 **
 ** PSOC-1488 **
 **
 ** 09/22/88 **
 ** PAGE 5 **

SAMPLE LOCATION:

 COUNTRY -> USA
 STATE -> MONTANA

SAMPLE IDENTIFICATION:

 PSU NUMBER -> PSOC-1488
 SEAM NAME -> DIETZ
 ALTERNATE SEAM NAME ->
 APPARENT RANK -> SUBBIT B

ASH FUSION TEMPERATURES (ALL TEMPERATURES IN DEGREES F)

	REDUCING	OXIDIZING
INITIAL DEFORMATION	2085.	2190.
SOFTENING	2115.	2320.
HEMISPHERICAL	2175.	2460.
FLUID	2235.	2470.

SAMPLE LOCATION:

COUNTRY -> USA
STATE -> COLORADO
COUNTY -> ROUTT
TOWNSHIP ->
CITY -> HAYDEN
COAL PROVINCE -> ROCKY MOUNTAIN
REGION -> GREEN RIVER
MAP REFERENCE: LATITUDE -> 40 D 25 M 59 S
LONGITUDE -> 107 D 7 M 21 S
QUADRANGLE -> MILNER (7.5')

SAMPLE IDENTIFICATION:

PSU NUMBER -> PSOC-1498
SEAM NAME -> WADGE
ALTERNATE SEAM NAME ->
APPARENT RANK -> HVC

SAMPLE HISTORY:

SAMPLING DATE & AGENCY -> 9/24/85 : PSU

SAMPLE TYPE -> CHANNEL-WHOLE SEAM

ADDITIONAL INFORMATION ->

MINE INFORMATION:

RESERVES ->
ANNUAL PRODUCTION ->

LIFE EXPECTANCY -> 20 YEARS

MINING METHOD -> STRIP

SEAM INFORMATION:

AGE OF SEAM -> U. CRET.
GROUP -> MESAVERDE
FORMATION -> WILLIAMS FORB
SEAM THICKNESS -> 10 FT 3 IN

** PENN STATE COAL DATA BASE **
 **
 ** PSOC-1498
 **
 ** 09/22/88
 ** PAGE 2
 **

SAMPLE LOCATION:

COUNTRY -> USA
 STATE -> COLORADO

SAMPLE IDENTIFICATION:

PSU NUMBER -> PSOC-1498
 SEAM NAME -> WADGE
 ALTERNATE SEAM NAME ->
 APPARENT RANK -> HVC

*** CHEMICAL DATA ***

PROXIMATE ANALYSIS				DMMF(PARR)	
	AS REC'D	DAE	DRY		
% MOISTURE	9.45				
% ASH	6.43		7.10		
% VOLATILE	38.04	45.22	42.01	44.80	
% FIXED CARBON	46.08	54.78	50.89	55.20	

% EQUILIBRIUM MOISTURE = 10.85
 MM-FREE = 11.69

ULTIMATE ANALYSIS				DMMF(PARR)		DMMF(MOD. P)		DMMF(DIR.)	
	AS REC'D	DAE	DRY						
% ASH	6.43		7.10	(7.95%MM)		(8.04%MM)		(%MM)	
% CARBON	65.21	77.52	72.02	78.24		71.97		78.26	
% HYDROGEN	4.58 (*)	5.45	5.06	5.50		4.97		5.40	
% NITROGEN	1.52	1.81	1.68	1.83		1.68		1.83	
% TOTAL SULFUR	0.47	0.56	0.52			0.49		0.53	
% OXYGEN(DIFF)	12.33 (*)	14.66	13.62	14.43		12.85		13.97	
(*)-EXCLUDES MOISTURE									
						% MINERAL MATTER		8.04	
						(INCL. 0.06% FES2)			

DRY % CHLORINE = 0.01 DRY % CO2 = 0.18
 MOTT-SPOONER DIFFERENCE = 121.

SULFUR FORMS				DMMF(PARR)		DMMF(MOD. P)		DMMF(DIR.)	
	AS REC'D	DAE	DRY						
DRY	0.03	0.49	0.00	0.52		0.01		0.18	
DAF	0.03	0.53	0.00	0.56					

CALORIFIC VALUE (GROSS, BTU/LB)				DMMF(PARR)		DMMF(MOD. P)		DMMF(DIR.)	
	AS REC'D	DAE	DRY						
MM-CONTAINING	12762.	11377.	11556.	0.8439		0.8291			
MM-FREE (PARR)	13837.	12221.	12428.	0.1385		0.1340			
MM-FREE (MOD. P)	13876.	12254.	12462.						
NET CV, DMF BTU/LB	13366.								

SAMPLE IDENTIFICATION:-----
PSU NUMBER -> PSOC-1498
SEAM NAME -> WADGE
ALTERNATE SEAM NAME ->
APPARENT RANK -> HVC
SAMPLE LOCATION:-----
COUNTRY -> USA
STATE -> COLORADO
** PENN STATE COAL DATA BASE **
**
** PSOC-1498
**
** 09/22/88
** PAGE 3
**

***** RANK CALCULATIONS *****

APPARENT RANK (AS REC'D MOIST.) -> HVC INTERNATIONAL RANK : ->
AS REC'D MOIST. ->
ASTM RANK (EQUIL. MOIST.) -> HVC EQUIL. MOIST. ->
REFLECTANCE RANK CATEGORY -> HVB REPORTED RANK : ->

***** PETROGRAPHIC DATA *****

MACERAL COMPOSITION (WHITE LIGHT ANALYSIS)

	VITRINITE	PSEUDO-VITRINITE	FUSINITE	SEMI-FUSINITE	MACRINITE	MICRINITE	SCLERO-INITE	SPOR-INITE	RESINITE	ALGINITE	CUTINITE
DMF VOL. %	89.2	0.0	3.1	2.4	1.0	2.2	0.0	1.8	0.3	0.0	0.0
DRY VOL. %	85.6	0.0	3.0	2.3	1.0	2.1	0.0	1.7	0.3	0.0	0.0
DRY WT. %	81.7	0.0	3.2	2.4	1.0	2.2	0.0	1.4	0.2	0.0	0.0

REFLECTANCE DATA
VITRINITE : HIGH: 0.69 LOW: 0.49 MEAN-MAX: 0.60

VITRINITE TYPES V 5 V 6 V 7
PERCENT 1.0 45.0 54.0

***** C A K I N G A N D M E C H A N I C A L P R O P E R T I E S *****

GIESELER COAL PLASTOMETER:

GRAY-KING COKE TYPE
HARDGROVE GRINDABILITY 44.2
FREE SWELLING INDEX 0.5
VICKERS HARDNESS NUMBER

INIT. SOFTENING TEMP

TEMP. MAX. FLUIDITY

SOLIDIFICATION TEMP.

FLUID TEMP. RANGE

MAXIMUM FLUIDITY
WASHABILITY DATA AVAILABLE? NO

** PENN STATE COAL DATA BASE **
 **
 ** PSOC-1498 **
 **
 ** 09/22/88 **
 ** PAGE 4 **

SAMPLE LOCATION:

 COUNTRY -> USA
 STATE -> COLORADO

SAMPLE IDENTIFICATION:

 PSU NUMBER -> PSOC-1498
 SEAM NAME -> WADGE
 ALTERNATE SEAM NAME ->
 APPARENT RANK -> HVC

% HTA = 7.96

MAJOR ELEMENT ANALYSIS

	SI02	AL203	T102	FE203	MG0	CA0	NA20	K20	P205	S03
OXIDE % OF HTA	48.7	31.1	0.92	3.60	1.47	6.22	0.92	0.84	1.03	3.90
ELEMENT % OF TOTAL DRY COAL	SI	AL	TI	FE	MG	CA	NA	K	P	S
	1.8	1.3	0.04	0.20	0.07	0.35	0.05	0.06	0.04	0.52

% HTA = 7.96

TRACE ELEMENT ANALYSIS

	PPM HTA	PPM TOTAL COAL	PPM HTA	PPM TOTAL COAL	PPM HTA	PPM TOTAL COAL	VOLATILES	PPM TOTAL COAL
AG							AS	
B							BR	
BA	3330.	265.					CD	
BE	9.0	0.7		16.			CL	100.
BI							F	
CE							HG	
CO			< 25.	< 2.			SB	
CR	50.	4.					SE	
CU	85.	7.		2.				
GA								

** PENN STATE COAL DATA BASE **
 **
 ** PSOC-1498 **
 **
 ** 09/22/88 **
 ** PAGE 5 **

SAMPLE LOCATION:

COUNTRY -> USA
 STATE -> COLORADO

SAMPLE IDENTIFICATION:

PSU NUMBER -> PSOC-1498
 SEAM NAME -> WADGE
 ALTERNATE SEAM NAME ->
 APPARENT RANK -> HVC

ASH FUSION TEMPERATURES (ALL TEMPERATURES IN DEGREES F)

	REDUCING	OXIDIZING
INITIAL DEFORMATION	2700.+	2700.+
SOFTENING	2700.+	2700.+
HEMISPHERICAL	2700.+	2700.+
FLUID	2700.+	2700.+

SAMPLE IDENTIFICATION:

PSU NUMBER
SEAM NAME
ALTERNATE SEAM NAME
APPARENT RANK

-> PSOC-1501
-> JUANITA C
->
-> HVB

SAMPLE HISTORY:

SAMPLING DATE & AGENCY -> 9/27/85 ; PSU

SAMPLE TYPE -> CHANNEL-WORKING SECTION
ADDITIONAL INFORMATION ->

MINE INFORMATION:

RESERVES ->
ANNUAL PRODUCTION ->

SEAM INFORMATION:

AGE OF SEAM -> U. CRET.
GROUP -> MESAVERDE
FORMATION -> WILLIAMS FORK
SEAM THICKNESS -> 7 FT. 0 IN.

SAMPLE LOCATION:

COUNTRY -> USA
STATE -> COLORADO
COUNTY -> GUNNISON
TOWNSHIP ->
CITY -> SOMERSET
COAL PROVINCE-> ROCKY MOUNTAIN
REGION -> UINTA

MAP REFERENCE: LATITUDE -> 38 D 54 M 50 S
LONGITUDE -> 107 D 27 M 32 S
QUADRANGLE-> SOMERSET (7.5')

LIFE EXPECTANCY ->
MINING METHOD -> UNDERGROUND

** PENN STATE COAL DATA BASE **
**
** PSOC-1501
**
**
** 09/22/88
** PAGE 1
**

PSU NUMBER
SEAM NAME
ALTERNATE SEAM NAME
APPARENT RANK

COUNTRY
STATE

PSOC-1501
JUANITA C
HVB

USA
COLORADO

PENN STATE COAL DATA BASE
PSOC-1501
09/22/88
PAGE 2

C H E M I C A L D A T A

PROXIMATE ANALYSIS		AS REC'D	DRY	DAF	DMMF(PARR)
% MOISTURE	5.80				
% ASH	5.23		5.55		
% VOLATILE	38.32		40.68	43.07	42.69
% FIXED CARBON	50.65		53.77	56.93	57.31

% EQUILIBRIUM MOISTURE = 6.86
MM-FREE = 7.29

U L T I M A T E A N A L Y S I S

ULTIMATE ANALYSIS		AS REC'D	DRY	DAF	DMMF(PARR)	ELEMENTAL ANALYSIS	DRY	DMMF(MOD.P)	DMMF(DIR.)
% ASH	5.23		5.55		(6.35%MM)			(6.30%MM)	(%MM)
% CARBON	71.61		76.02	80.49	81.17	% CARBON	75.96	81.06	
% HYDROGEN	4.69 (*)		4.98	5.27	5.32	% HYDROGEN	4.91	5.24	
% NITROGEN	1.38		1.46	1.55	1.56	% NITROGEN	1.46	1.56	
% TOTAL SULFUR	0.60		0.64	0.68		% ORGANIC SULFUR	0.62	0.66	
% OXYGEN(DIFF)	10.69 (*)		11.35	12.02	11.95	% OXYGEN(DIFF)	10.76	11.48	

(*)-EXCLUDES MOISTURE

SULFUR FORMS		% PYRITIC	% SULFATIC	% ORGANIC	% TOTAL
DRY	0.02	0.00	0.62	0.64	
DAF	0.02	0.00	0.66	0.68	

DRY % CHLORINE = 0.03 DRY % CO2 = 0.22
MOTT-SPOONER DIFFERENCE = 270.

CALORIFIC VALUE (GROSS, BTU/LB)		AS REC'D MOIST.	EQUIL. MOIST.
MM-CONTAINING	13579.	12791.	12647.
MM-FREE (PARR)	14465.	13573.	13410.
MM-FREE (MOD. P)	14490.	13597.	13434.
NET CV, DMMF BTU/LB	13998.		

ATOM RATIOS (DMMF)
PARR MOD.PARR DIRECT
ATOMIC H/C 0.7868 0.7761
ATOMIC O/C 0.1105 0.1063

SAMPLE IDENTIFICATION:-----
PSU NUMBER -> PSOC-1501
SEAM NAME -> JUANITA C
ALTERNATE SEAM NAME ->
APPARENT RANK -> HVB
SAMPLE LOCATION:-----
COUNTRY -> USA
STATE -> COLORADO
** PENN STATE COAL DATA BASE **
** PSOC-1501
** 09/22/88
** PAGE 3

***** RANK CALCULATIONS *****

APPARENT RANK (AS REC'D MOIST.) -> HVB INTERNATIONAL RANK : ->
ASTM RANK (EQUIL. MOIST.) -> HVB AS REC'D MOIST. ->
REFLECTANCE RANK CATEGORY -> HVA REPORTED RANK : ->
EQUIL. MOIST. ->

***** PETROGRAPHIC DATA *****

MACERAL COMPOSITION (WHITE LIGHT ANALYSIS)

	VITRINITE	PSEUDO-VITRINITE	FUSINITE	SEMI-FUSINITE	MACRINITE	MICRINITE	SCLERO-TINITE	SPOR-INITE	RESINITE	ALGINITE	CUTINITE
DMMF VOL. %	92.4	0.0	1.9	2.4	0.5	1.2	0.1	1.4	0.1	0.0	0.0
DRY VOL. %	89.5	0.0	1.8	2.3	0.5	1.2	0.1	1.4	0.1	0.0	3.2 % MM
DRY WT. %	86.1	0.0	2.0	2.4	0.5	1.2	0.1	1.2	0.1	0.0	6.3 % MM

REFLECTANCE DATA
VITRINITE : HIGH: 0.82 LOW: 0.64 MEAN-MAX: 0.73

VITRINITE TYPES V 6 V 7 V 8
PERCENT 19.0 78.0 3.0

***** C A K I N G A N D M E C H A N I C A L P R O P E R T I E S *****

GIESELER COAL PLASTOMETER:

INIT. SOFTENING TEMP	412	GRAY-KING COKE TYPE	
TEMP. MAX. FLUIDITY	421	HARDGROVE GRINDABILITY	56.7
SOLIDIFICATION TEMP.	436	FREE SWELLING INDEX	2.0
FLUID TEMP. RANGE	24	VICKERS HARDNESS NUMBER	

MAXIMUM FLUIDITY 1
WASHABILITY DATA AVAILABLE? NO

** PENN STATE COAL DATA BASE **
 ** PSOC-1501 **
 ** 09/22/88 **
 ** PAGE 4 **

SAMPLE LOCATION:

 COUNTRY -> USA
 STATE -> COLORADO

-> PSOC-1501
 -> JUANITA C
 -> /
 -> HVB

SAMPLE IDENTIFICATION:

 PSU NUMBER
 SEAM NAME
 ALTERNATE SEAM NAME
 APPARENT RANK

% HTA = 5.37

MAJOR ELEMENT ANALYSIS

	SI02	AL203	TI02	FE203	MG0	CA0	NA20	K20	P205	S03
OXIDE % OF HTA	51.1	29.9	0.86	6.17	1.09	3.63	1.94	0.75	1.22	1.60
ELEMENT % OF TOTAL DRY COAL	SI	AL	TI	FE	MG	CA	NA	K	P	S
	1.3	0.8	0.03	0.23	0.04	0.14	0.08	0.03	0.03	0.64

% HTA = 5.37

TRACE ELEMENT ANALYSIS

	PPM HTA	PPM TOTAL COAL	PPM HTA	PPM TOTAL COAL	PPM HTA	PPM TOTAL COAL	VOLATILES	PPM TOTAL COAL
AG					SN		AS	
B			GE		SR	2790.	BR	
BA	3060.	164.	LI		TH		CD	
BE	9.0	0.5	MN	100.	U		CL	300.
BI			MO		V	130.	F	
CE			NB		Y		HG	
CO			NI	30.	YB		SB	
CR	45.	2.	PB		ZN	130.	SE	
CU	130.	7.	RB	30.	ZR	340.		
GA			SC					

** PENN STATE COAL DATA BASE **
 **
 ** PSOC-1501 **
 ** 09/22/88 **
 ** PAGE 5 **

SAMPLE LOCATION:

 COUNTRY -> USA
 STATE -> COLORADO

SAMPLE IDENTIFICATION:

 PSU NUMBER -> PSOC-1501
 SEAM NAME -> JUANITA C
 ALTERNATE SEAM NAME ->
 APPARENT RANK -> HVB

ASH FUSION TEMPERATURES (ALL TEMPERATURES IN DEGREES F)

	REDUCING	OXIDIZING
INITIAL DEFORMATION	2700.+	2700.+
SOFTENING	2700.+	2700.+
HEMISPHERICAL	2700.+	2700.+
FLUID	2700.+	2700.+

SAMPLE IDENTIFICATION:

PSU NUMBER
SEAM NAME
ALTERNATE SEAM NAME
APPARENT RANK

-> PSOC-1504
-> UPPER SUNNYSIDE
->
-> HVA

SAMPLE HISTORY:

SAMPLING DATE & AGENCY

-> 10/ 2/85 ; PSU

SAMPLE TYPE

-> CHANNEL-WHOLE SEAM

ADDITIONAL INFORMATION

->

MINE INFORMATION:

RESERVES

->

ANNUAL PRODUCTION

->

SEAM INFORMATION:

AGE OF SEAM

-> U. CRET.

GROUP

-> MESAVERDE

FORMATION

-> BLACKHAWK

SEAM THICKNESS

-> 6 FT. 5 IN.

SAMPLE LOCATION:

COUNTRY

-> USA

STATE

-> UTAH

COUNTY

-> CARBON

TOWNSHIP

->

CITY

-> SUNNYSIDE

COAL PROVINCE->

ROCKY MOUNTAIN

REGION ->

UINTA

MAP REFERENCE: LATITUDE ->

39 D 34 M 22 S

LONGITUDE ->

110 D 20 M 20 S

QUADRANGLE-> SUNNYSIDE (15')

LIFE EXPECTANCY

->

MINING METHOD

-> UNDERGROUND

** PENN STATE COAL DATA BASE **
**
** PSOC-1504
**
** 09/22/88
** PAGE 1
**

SAMPLE IDENTIFICATION:
PSU NUMBER
SEAM NAME
ALTERNATE SEAM NAME
APPARENT RANK

SAMPLE LOCATION:
COUNTRY
STATE

PSOC-1504
UPPER SUNNYSIDE
HVA

PSOC-1504
UPPER SUNNYSIDE
HVA

*** CHEMICAL DATA ***

PROXIMATE ANALYSIS
AS REC'D DRY DAF DMME(PARR)
% MOISTURE 3.38
% ASH 7.29
% VOLATILE 37.49
% FIXED CARBON 51.85

% EQUILIBRIUM MOISTURE = 5.42
MM-FREE = 5.90

ULTIMATE ANALYSIS
AS REC'D DRY DAF DAF DMME(PARR) DMME(MOD.P) DMME(DIR.)
% ASH 7.29 7.54 7.54 82.88 (8.57%MM)
% CARBON 73.22 75.78 81.96 75.74 82.89
% HYDROGEN 5.18 (*) 5.36 5.80 5.26 5.76
% NITROGEN 1.57 1.62 1.75 1.62 1.77
% TOTAL SULFUR 0.74 0.77 0.83 0.71 0.78
% OXYGEN(DIFF) 8.63 (*) 8.93 9.66 8.04 8.80

(*)-EXCLUDES MOISTURE
SULFUR FORMS
% PYRITIC % SULFATIC % TOTAL
DRY 0.04 0.02 0.77
DAF 0.04 0.02 0.83

CALORIFIC VALUE
(GROSS, BTU/LB)
MM-CONTAINING 13640.
MM-FREE (PARR) 14876.
MM-FREE (MOD. P) 14926.
NET CV, DMME BTU/LB 14382.

** PENN STATE COA' DATA BASE **
 **
 ** PSOC-1504
 **
 ** 09/22/88
 ** PAGE 3
 **

SAMPLE IDENTIFICATION:

 PSU NUMBER
 SEAM NAME
 ALTERNATE SEAM NAME
 APPARENT RANK

-> PSOC-1504
 -> UPPER SUNNYSIDE
 ->
 -> HVA

SAMPLE LOCATION:

 COUNTRY
 STATE

-> USA
 -> UTAH

APPARENT RANK (AS REC'D MOIST.)
 ASTM RANK (EQUIL. MOIST.)
 REFLECTANCE RANK CATEGORY

-> HVA
 -> HVB
 -> HVA

INTERNATIONAL RANK :
 AS REC'D MOIST. ->
 EQUIL. MOIST. ->
 REPORTED RANK : ->

***** RANK CALCULATIONS *****
 ***** PETROGRAPHIC DATA *****

MACERAL COMPOSITION (WHITE LIGHT ANALYSIS)

	VITRINITE	PSEUDO-VITRINITE	FUSINITE	SEMI-FUSINITE	MACRINITE	MICRINITE	SCLERO-TINITE	SPOR-INITE	RESINITE	ALGINITE	CUTINITE
DMHF VOL. %	86.9	0.0	3.3	2.9	1.4	2.2	0.0	2.5	0.8	0.0	0.0
DRY VOL. %	83.1	0.0	3.2	2.8	1.3	2.1	0.0	2.4	0.8	0.0	4.3 % MM
DRY WT. %	78.8	0.0	3.5	2.8	1.4	2.1	0.0	2.1	0.7	0.0	8.6 % MM

REFLECTANCE DATA

 VITRINITE : HIGH: 0.90 LOW: 0.69 MEAN-MAX: 0.80

VITRINITE TYPES V 6 V 7 V 8 V 9

 PERCENT 1.0 49.0 47.0 3.0

***** C A K I N G A N D M E C H A N I C A L P R O P E R T I E S *****

GIESELER COAL PLASTOMETER:

INIT. SOFTENING TEMP 400
 TEMP. MAX. FLUIDITY 433
 SOLIDIFICATION TEMP. 451
 FLUID TEMP. RANGE 51
 HARDGROVE GRINDABILITY 60.8
 FREE SWELLING INDEX 5.5
 VICKERS HARDNESS NUMBER

MAXIMUM FLUIDITY 17
 WASHABILITY DATA AVAILABLE? NO

** PENN STATE COAL DATA BASE **
 **
 ** PSOC-1504
 **
 ** 09/22/88
 ** PAGE 4
 **

SAMPLE LOCATION:

COUNTRY -> USA
 STATE -> UTAH

SAMPLE IDENTIFICATION:

PSU NUMBER -> PSOC-1504
 SEAM NAME -> UPPER SUNNYSIDE
 ALTERNATE SEAM NAME ->
 APPARENT RANK -> HVA

% HTA = 7.10

MAJOR ELEMENT ANALYSIS

	SI02	AL203	TI02	FE203	MG0	CA0	NA20	K20	P205	S03
OXIDE % OF HTA	71.1	21.6	1.09	2.58	0.52	1.02	0.64	0.83	0.38	0.30
ELEMENT % OF TOTAL DRY COAL	SI	AL	TI	FE	MG	CA	NA	K	P	S
	2.4	0.8	0.05	0.13	0.02	0.05	0.03	0.05	0.01	0.77

% HTA = 7.10

TRACE ELEMENT ANALYSIS

	PPM HTA	PPM TOTAL COAL	PPM HTA	PPM TOTAL COAL	PPM HTA	PPM TOTAL COAL	VOLATILES	PPM TOTAL COAL
AG			GE		SN		AS	
B			LA		SR	250.	BR	
BA	270.	19.	LI		TH		CD	
BE	10.	1.	MN	150.	U		CL	1800.
BI			MO		V	130.	F	
CE			NB		Y		HG	
CO			NI	35.	YB		SB	
CR	95.	7.	PB		ZN	250.	SE	
CU	170.	12.	RB	30.	ZR	470.		
GA			SC					

** PENN STATE COAL DATA BASE **
 **
 ** PSOC-1504 **
 **
 ** 09/22/88 **
 ** PAGE 5 **

SAMPLE LOCATION:

 COUNTRY -> USA
 STATE -> UTAH

SAMPLE IDENTIFICATION:

 PSU NUMBER -> PSOC-1504
 SEAM NAME -> UPPER SUNNYSIDE
 ALTERNATE SEAM NAME ->
 APPARENT RANK -> HVA

ASH FUSION TEMPERATURES (ALL TEMPERATURES IN DEGREES F)

 INITIAL DEFORMATION REDUCING OXIDIZING
 2700.+ 2700.+ 2700.+
 SOFTENING 2700.+ 2700.+
 HEMISPHERICAL 2700.+ 2700.+
 FLUID 2700.+ 2700.+

SAMPLE IDENTIFICATION:

PSU NUMBER
SEAM NAME
ALTERNATE SEAM NAME
APPARENT RANK

-> PSOC-1448
-> YORK CANYON
->
-> HVA

SAMPLE HISTORY:

SAMPLING DATE & AGENCY

-> 4/ 8/85 ; PSU

SAMPLE TYPE
ADDITIONAL INFORMATION

-> CHANNEL-WHOLE SEAM

MINE INFORMATION:

RESERVES
ANNUAL PRODUCTION

->
-> 1500 THOUSAND TONS

SEAM INFORMATION:

AGE OF SEAM
GROUP
FORMATION
SEAM THICKNESS

-> PALEO.
->
-> RATON
-> 6 FT. 9 IN.

SAMPLE LOCATION:

COUNTRY -> USA
STATE -> NEW MEXICO
COUNTY -> COLFAX
TOWNSHIP ->
CITY -> RATON

COAL PROVINCE-> NORTHERN GREAT PLAINS
REGION -> RATON MOUNTAIN

MAP REFERENCE: LATITUDE -> 36 D 53 M 0 S
LONGITUDE -> 104 D 55 M 0 S
QUADRANGLE-> CASA GRANDE (15')

LIFE EXPECTANCY -> 7 YEARS

MINING METHOD -> STRIP

** PENN STATE COAL DATA BASE **
**
** PSOC-1448
**
** 07/12/88
** PAGE 1
**

SAMPLE IDENTIFICATION:
PSU NUMBER
SEAM NAME
ALTERNATE SEAM NAME
APPARENT RANK

SAMPLE LOCATION:
COUNTRY
STATE

PSOC-1448
YORK CANYON
HVA

PENN STATE COAL DATA BASE
PSOC-1448
07/12/88
PAGE 2

C H E M I C A L D A T A

PROXIMATE ANALYSIS
AS REC'D DRY DAF DMF(PARR)
% MOISTURE 1.45
% ASH 11.25 11.42
% VOLATILE 36.25 36.78 41.52 40.82
% FIXED CARBON 51.05 51.80 58.48 59.18
% EQUILIBRIUM MOISTURE = 1.64
MM-FREE = 1.88

ULTIMATE ANALYSIS
AS REC'D DRY DAF DMF(PARR) DMF(MOD.P) DRY DMF(DIR.)
(12.59%MM) (12.95%MM) (%MM)
% ASH 11.25 11.42 84.08 85.20 74.27 85.32
% CARBON 73.40 74.48 6.04 6.12 5.20 5.98
% HYDROGEN 5.27 (*) 5.35 1.84 1.86 1.63 1.87
% NITROGEN 1.61 1.63 0.52 6.81 0.41 0.47
% TOTAL SULFUR 0.45 6.66 7.52
% OXYGEN(DIFF) 6.56 (*) 6.66 12.95
% MINERAL MATTER (INCL. 0.07% FES2)
(*)-EXCLUDES MOISTURE

SULFUR FORMS
% PYRITIC % SULFATIC % TOTAL
DRY 0.04 0.01 0.46
DAF 0.05 0.01 0.52
DRY % CHLORINE = 0.05 DRY % CO2 = 0.76
MOTT-SPOONER DIFFERENCE = -130.

CALORIFIC VALUE (GROSS, BTU/LB)
MM-CONTAINING 13467. 13272. 13246. ATOMIC H/C 0.8628 0.8413
MM-FREE (PARR) 15380. 15125. 15092. ATOMIC O/C 0.0600 0.0560
MM-FREE (MOD. P) 15468. 15211. 15177.
NET CV, DMF 8TU/LB 14898.

SAMPLE IDENTIFICATION:
PSU NUMBER
SEAM NAME
ALTERNATE SEAM NAME
APPARENT RANK
PSOC-1448
YORK CANYON
HVA
COUNTRY
STATE
USA
NEW MEXICO
PENN STATE COAL DATA BASE
PSOC-1448
07/12/88
PAGE 3

APPARENT RANK (AS REC'D MOIST.)
ASTM RANK (EQUIL. MOIST.)
REFLECTANCE RANK CATEGORY
INTERNATIONAL RANK :
AS REC'D MOIST. ->
EQUIL. MOIST. ->
REPORTED RANK : ->

PETROGRAPHIC DATA

Table with 10 columns: DMF VOL. %, DRY VOL. %, DRY WT. %, VITRINITE, PSEUDO-VITRINITE, FUSINITE, SEMI-FUSINITE, MACRINITE, MICRINITE, SCLERO-TINITE, SPOR-INITE, RESINITE, ALGINITE, CUTINITE. Rows show data for DMF, DRY, and VITRINITE percentages and types.

REFLECTANCE DATA
VITRINITE :
HIGH: 0.83 LOW: 0.61 MEAN-MAX: 0.71

VITRINITE TYPES
PERCENT
V 6 V 7 V 8
37.0 59.0 4.0

GIESSELER COAL PLASTOMETER:
INIT. SOFTENING TEMP
TEMP. MAX. FLUIDITY
SOLIDIFICATION TEMP.
FLUID TEMP. RANGE
MAXIMUM FLUIDITY
WASHABILITY DATA AVAILABLE?

SAMPLE IDENTIFICATION: PSU NUMBER PSOC-1448
 SEAM NAME SEAM NAME
 ALTERNATE SEAM NAME
 APPARENT RANK
 SAMPLE LOCATION: COUNTRY -> USA
 STATE -> NEW MEXICO
 ** PENN STATE COAL DATA BASE **
 ** PSOC-1448 **
 ** 07/12/88 **
 ** PAGE 4 **

% HTA = 10.69

MAJOR ELEMENT ANALYSIS

OXIDE % OF HTA	SI02	AL203	TI02	FE203	MGO	CAO	NA20	K20	P205	S03
	40.8	24.5	1.14	7.21	2.08	14.9	1.17	0.51	1.54	4.70
ELEMENT % OF TOTAL DRY COAL	SI	AL	TI	FE	MG	CA	NA	K	P	S
	2.0	1.4	0.07	0.54	0.13	1.1	0.09	0.05	0.07	0.46

% HTA = 10.69

TRACE ELEMENT ANALYSIS

	PPM HTA	PPM TOTAL COAL	PPM HTA	PPM TOTAL COAL	PPM HTA	PPM TOTAL COAL	VOLATILES	PPM TOTAL COAL
AG							AS	
B							BR	
BA	5130.	548.					CD	
BE	7.0	0.7	108.	12.			CL	500.
BI							F	
CE							HG	
CO							SB	
CR	70.	7.					SE	
CU	210.	22.	30.	3.				
GA								

** PENN STATE COAL DATA BASE **
 **
 ** PSOC-1448
 **
 ** 07/12/88
 ** PAGE 5
 **

SAMPLE LOCATION:

 COUNTRY
 STATE
 -> USA
 -> NEW MEXICO

SAMPLE IDENTIFICATION:

 PSU NUMBER
 SEAM NAME
 ALTERNATE SEAM NAME
 APPARENT RANK
 -> PSOC-1448
 -> YORK CANYON
 ->
 -> HVA

ASH FUSION TEMPERATURES (ALL TEMPERATURES IN DEGREES F)

	REDUCING	OXIDIZING
INITIAL DEFORMATION	2355.	2420.
SOFTENING	2395.	2505.
HEMISPHERICAL	2470.	2540.
FLUID	2505.	2565.

END

**DATE
FILMED**

10 / 14 / 92