DOE/ER/45401-3

DOE/ER/45401--3

DE92 019744

TECHNICAL PROGRESS REPORT
TO THE DEPARTMENT OF ENERGY

Title: Measurements of Crystal Growth Kinetics at Extreme Deviations
from Equilibrium

Award #: DE-FG02-89ER45401

Period of Award: 1 September 1990 - 31 August 1991

Grantee: President & Fellows of Harvard College
Office for Sponsored Research
Holyoke Center, Room 440
1350 Massachusetts Avenue
Cambridge MA 02138

P.I.: Michael J. Aziz
Associate Professor of Materials Science
Division of Applied Sciences
Harvard University
29 Oxford St.
Cambridge MA 02138
(617) 495-9884

Date: July 14, 1992

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MAJ:ER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

ABSTRACT

We have measured solute trapping of several solutes in Al during rapid solidification. We have also made preliminary measurements of solute trapping of As in Si, trapped 20 atomic percent As in Si, and made a preliminary measurement of the T_0 curve in Si-As.

1. RESEARCH PROGRESS FOR 1991-92

We have managed to solute-trap up to 20 *atomic percent arsenic* onto substitutional lattice sites in Si, resulting in highly concentrated solutions. In addition, the $k(v)$ function, which we are in the process of measuring for dilute solutions, undergoes a transition from equilibrium partitioning to complete solute trapping over a velocity range that appears to be experimentally measurable, as shown in Figs. 1-3. Arsenic is the only dopant in Si (that we have found so far) that is sluggish enough to be completely trapped at "routine laser-annealing" velocities of 1-5 m/s. As shown in Fig. 2, we can slow down the velocities enough to observe the effects of significant partitioning at the interface — a "spike" of arsenic that has been zone-refined out to the surface during solidification. Obviously, the $k(v)$ data in Fig. 3 are preliminary, but k appears to rise too steeply with v to fit the continuous growth model. More accurate measurements are in progress to resolve this issue.

The thermodynamics of supersaturated Si-As are important as input to the kinetic models for the velocity-undercooling function. We expect to be able to model the thermodynamics to sufficient accuracy if we know the T_0 curve (the temperature, as a function of composition, at

Figure 1. Measured melt depth vs. time for pulsed-laser-melted dilute Si-As alloy thin film on SiO₂. Sample was heated from back by C-W CO₂ laser immediately prior to pulsed laser melting in order to reduce solidification velocity. Measured velocity of approximately 0.34 m/s is determined from slope of curve. Spike at peak of trace is artifact of electromagnetic interference from laser firing, which disappears soon after solidification begins.

Figure 2. Arsenic depth profiles measured by RBS before and after pulsed laser melting and solidification at 0.34 m/s. Solid curve is simulation using measured time-dependence of melt depth, measured initial profile, and best-fit partition coefficient of $k \approx 0.5$.

which solid and liquid solutions of identical composition have the same Gibbs free energy) for the Si-As alloy. We made a measurement of the T_0 curve in collaboration with J.A. Knapp at Sandia Laboratories. He uses a scanned pulsed line-source e-beam to melt thin films on sapphire. The heating rate is too rapid for precipitation to occur before the T_0 temperature is crossed, at which point melting occurs quite rapidly. The peak temperature vs. distance from the center of the line is carefully calibrated, and the width of the melted region is used to determine the peak temperature at the melting threshold. The advantages of the e-beam source are that the reflectivity for both solid and liquid is known (it's zero) and for any thin film on sapphire, on the time scale of the experiment, the known thermal properties of the sapphire substrate completely dominate the unknown properties of the film. As shown in Fig. 4, the T_0 curve we obtained for Si-As is different than the T_0 curve obtained by Pietro Baeri and his graduate student, Riccardo Reitano,

Figure 3. $k(v)$ function for As in Si. Point at 0.34 m/s measured on Si-on-SiO₂ with CO₂ heating; points at 4 and 5 m/s measured on Si-on-sapphire with no heating. Curve, fit of continuous growth model with $v_D = 0.82$ m/s, may not rise steeply enough to account for experiment. More thorough measurements will settle the issue.

Figure 4. Measured T_0 temperatures and calculated phase boundaries and T_0 curve in Si-As alloys. Solid and broken curves are calculated phase boundaries and T_0 curves using two different assumptions about the thermodynamic parameters.

who used pulsed laser melting techniques. It also differs from another measurement by Percy *et al.*. Dr. Reitano, supported by an Italian National Postdoctoral Fellowship, recently joined our group after obtaining his Ph.D. and is resolving the differences between the T_0 curves.

3.3 Solute Trapping in Metals

We are now making the world's first measurements of solute trapping in metallic systems. This is much more difficult than our earlier experiments that led to a pretty thorough understanding of the solute trapping process in silicon. But it is quite important to get data in metals. In contrast to silicon, where the change in structure from a covalent solid to a metallic melt is a theorist's nightmare, in metals we are getting to the point where first-principles calculations of the structure and properties of the crystal-melt interface are possible. Such calculations can already be done in

fcc and hcp metals with the embedded-atom method (though it is not first-principles, it is less phenomenological than the simple "continuous growth model").

At present, we have managed to obtain nonequilibrium partition coefficients at a single velocity for Sn, Ge, and Cu in Al and a couple of solutes in Ni, as shown in Fig. 10, and over a small velocity range for Ge in Al. We have had to work hard to control post-solidification solid-phase diffusion, which was altering our Al-Sn and Al-Ge depth profiles in some cases when the samples were preheated with a CO₂ laser.

Figure 5. RBS depth profiles of ²⁰⁸Pb in 1800 Å Ni film before and after pulsed laser melting and solidification. Lines show computer simulations used to determine partition coefficient. Best fit is $k(1.2 \text{ m/s}) = 0.12$ and $D_{\text{liq}} = 4.0 \times 10^{-5} \text{ cm}^2/\text{sec}$.

2. PUBLICATIONS SUPPORTED BY GRANT

D.E. Hoglund, M.J. Aziz, S.R. Stiffler, M.O. Thompson, J.Y. Tsao and P.S. Peercy, "Effect of Nonequilibrium Interface Kinetics on Cellular Breakdown of Planar Interface During Rapid Solidification of Si-Sn," *Journal of Crystal Growth* **109**, 107-112 (1991).

D. Hoglund, M.J. Aziz, "Interface Stability During Rapid Directional Solidification," to appear in Materials Research Society Symposia Proceedings **205**, 325-9 (1992).

P.M. Smith, J.A. West, M.J. Aziz, "Solute Trapping of Ge in Al," to appear in Materials Research Society Symposia Proceedings **205**, 331-6 (1992).

3. PERSONNEL SUPPORTED BY GRANT

Patrick M. Smith, fifth year Ph.D. student; graduation summer 1992.

David E. Hoglund, third year Ph.D. student; expected graduation summer 1993.

Michael J. Aziz, associate professor (part-time summer salary).

END

**DATE
FILMED
9/29/92**