DOE/PC/89908--T22

DOE/PC/89908--T22

DE92 040661

QUARTERLY TECHNICAL PROGRESS REPORT NO. 11

APRIL - JUNE 1992

**ENGINEERING DESIGN AND ANALYSIS OF ADVANCED PHYSICAL
FINE COAL CLEANING TECHNOLOGIES**

for

**U.S. DEPARTMENT OF ENERGY
PITTSBURGH ENERGY TECHNOLOGY CENTER
PITTSBURGH, PA**

CONTRACT NO. DE-AC22-89PC89908

SUBMITTED BY

**P.W. GALLIER
PROJECT MANAGER**

**ASPEN TECHNOLOGY, INC.
251 VASSAR STREET
CAMBRIDGE, MA 02139**

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

JULY 20, 1992

for
Received OSTI
SEP 08 1992

TABLE OF CONTENTS

	Page
1.0 INTRODUCTION	1
2.0 ADMINISTRATIVE ITEMS	2
3.0 TASK 1.2 - Engineering Analysis of Conventional Coarse Coal Cleaning	3
3.1 Planned Scope of Work	3
3.2 Technical Status	3
3.2.1 Updates, and Testing of Task 2 Models	3
3.2.2 Additional Task 2 Model Discussions	8
3.2.3 ASPEN PLUS Implementations	9
3.2.4 Task 2 Topical Reports	11
3.2.5 Task 2 Model Validation Reports	11
4.0 TASK 1.3 - Engineering Analysis of Unit Operations for Processing Fine and Ultrafine Coals	12
TASK 1.4 - Engineering Analysis of Advanced Technologies for Physical Cleaning of Fine and Ultrafine Coals	12
4.1 Planned Scope of Work	12
4.2 Technical Status	12
5.0 TASK 1.6 -Laboratory Testing	13
5.1 Planned Scope of Work	13
5.2 Technical Status	13
5.2.1 Froth Flotation	13
5.2.2 Other Advanced Processes	14
6.0 QUARTER NO. 12 WORK PLAN	18

1.0 INTRODUCTION

This project is sponsored by the United States Department of Energy (DOE) for the "Engineering Design and Analysis of Advanced Physical Fine Coal Cleaning Technologies". The major goal is to provide the simulation tools for modeling both conventional and advanced coal cleaning technologies. This DOE project is part of a major research initiative by the Pittsburgh Energy Technology Center (PETC) aimed at advancing three advanced coal cleaning technologies- heavy-liquid cycloning, selective agglomeration, and advanced froth flotation through the proof-of-concept (POC) level.

The commercially available ASPEN PLUS process simulation package will be extended to handle coal cleaning applications. Algorithms for predicting the process performance, equipment size, and flowsheet economics of commercial coal cleaning devices and related ancillary equipment will be incorporated into the coal cleaning simulator.

This report is submitted to document the progress of Aspen Technology, Inc. (AspenTech), its contractor, ICF Kaiser Engineers, Inc., (ICF KE) and CQ Inc., a subcontractor to ICF KE, for the period of March through June 1992. ICF KE is providing coal preparation consulting and processing engineering services in this work and they are responsible for recommending the design of models to represent conventional coal cleaning equipment and costing of these models.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

2.0 ADMINISTRATIVE ITEMS

AspenTech, and CQ Inc attended a kickoff meeting for Task 6 on April 2, 1992 at Penn State University. The discussion focused on froth flotation modeling and the Task 6 experimental program. The participants at that meeting also included representatives from DOE, DOE project consultants, and members of the Penn State Project team.

A project review meeting was held at DOE PETC on May 19, 1992. The goals for this meeting were to follow up on the froth flotation discussion begun at the Task 6 kickoff meeting, and to discuss model validation.

An internal project team meeting was held between AspenTech, ICF KE, and CQ Inc. on June 30 1992. The discussion focused on manpower assignments and scheduling for the remainder of the project. The project team agreed to hold weekly conference call meetings on Friday afternoon until the completion of the project.

3.0 TASK 1.2 - ENGINEERING ANALYSIS OF CONVENTIONAL COARSE COAL CLEANING

3.1 Planned Scope of Work

The work plan for the period called for the completion of all Task 2 items including model documentation, testing, and validation.

3.2 Technical Status

The technical status of all Task 2 items are discussed below in the following sections.

3.2.1 Updates, and Testing of Task 2 Models

Screens and Centrifuges

Model validation procedures were discussed at a meeting between the project team and DOE-PETC on May 19, 1992. It became apparent at the meeting that one of the problems occurring was the inability of some of the screen models to give a continuous relationship between tons per hour oversize and screen cut size. In the original deslime screen model, the input to the model was both separation size and screen efficiency. The efficiency value was used in the calculation to place 100 minus the efficiency value as a fractional recovery for all size intervals less than the screen size into the screen oversize. These calculations reveal that step functions occur in tons per hour oversize flow, when the screen opening is varied. Another algorithm was developed during the work period to allow a continuous function to result from the deslime screen model when performing sensitivity between screen opening. The model was developed from several sets of data collected from deslime screening operations at 0.5mm size. Primarily, the sharpness index was calculated for subsequent use in the model. Then, the logistic equation was used to create a set of fractional recovery values from the d50 and sharpness index parameters. The resulting calculations give a more realistic separation of the screen feed as compared to the old algorithm. If the user of the model wishes to use this approach, he should enter the d50 value and an efficiency value of 0. If an efficiency value greater than zero is entered, the calculations will follow the path of the old algorithm. The double-deck deslime screen was also updated to include this algorithm. A similar approach is utilized in the inclined screen models (wet, double-deck wet, dry, and double-deck dry inclined screens).

Both screen and centrifuge models rely on the calculation of average particle size to predict the moisture content of the screen oversize and centrifuge discharge products (cake). When a selectivity curve approach is used to calculate screen performance, reasonable values for moisture can be obtained by setting the dewatered product film thickness to a value of approximately 0.008 mm. In the screen

algorithms, where efficiency is an input parameter by the user, the model uses the efficiency to determine the recovery of all size fractions finer than the separation size. If the efficiency is 80 percent, then the recovery of the fines to the oversize stream is 20 percent. This approach recovers a considerable amount of fines to the oversize, resulting in erroneously high values for predicted product moisture content. In order to be able to make both approaches to modeling screens compatible with the algorithm to predict moisture content of the screen oversize, further modifications will need to be made to the screen algorithm. The preferred changes were discussed with AspenTech at the meeting on June 30, 1992, and will be discussed in the monthly progress report for July 1992. When the screen algorithms have been finalized, the centrifuges will be tested again and final model parameters adjusted to result in moisture contents comparable to centrifuge manufacturer data.

Gravity-based Devices

As part of additional testing for the gravity-based device models (primarily heavy-media cyclones, concentration tables, and water-only cyclones), data from three coal cleanability characterization test programs conducted at the Coal Quality Development Center are being used to compare calculated versus actual probable error and specific gravity of separation by particle size. These three test programs used these three devices in various combinations, giving a total of fourteen different flowsheets to test. These flowsheets have been set up as ASPEN PLUS input files. Comparisons between model results and actual operating results will be available in July. The flowsheets are configured for Kentucky No. 11, Illinois No. 6, and the Stockton-Lewiston Coal Seams. A wide range of separating gravities and particle sizes will be covered in this testing.

Roll Crusher

The roll crusher model was tested using EPRI Coal Quality Information System (CQIS™) washability data for two coals (Meigs Creek and Mary Lee Seams). These tests compared actual crushed size distributions to those predicted by the roll crusher model. It was found that the model uses the 20 percent retained size as the definition of topsize of the crusher product. If a 3/4 in. product topsize is required and the user inputs 3/4 in. size for the crusher gap setting, the model gives a product size distribution with about 20 percent retained on 3/4 in. size. For example, Figure 1 shows the actual size distribution for the Mary Lee seam coal crushed to 95 percent passing 3/4 in. This gives a 20 percent retained size value of slightly greater than 3/8 in. (approximately 11.2 mm). When SET = 11.1mm (SET is the parameter for crusher gap size), the resulting size distribution approximates that of the actual CQIS crushed to 3/4 in. coal sample. When 3/4 in. (19.05mm) is used for

SET the distribution is much coarser, resulting in a 20 percent retained size of about 3/4 in.

Roll crushers are typically used to minimize the amount of fines generated by crushing. The model appears to do this as well, but tends to underestimate the amount of fines, giving values slightly greater than the feed sample for the finest sizes. This is illustrated in Figure 2. While the model gives progressively finer size distributions with decreasing values of SET for the Mary Lee seam coal in the coarser size ranges, the size distribution in the fine size range tends to merge. This is in contrast to the size distributions given for the various crushed products as shown in Figure 3.

Figure 1. Mary Lee Seam Crushed to 3/4" Topsizes Model vs Sample Comparison

Figure 2. Crusher Model Results for Mary Lee Seam Coal

Figure 3. CQIS Crushed Coal Size Distributions for Mary Lee Seam Coal

3.2.2 Additional Task 2 Model Discussions

Froth Flotation

Several items regarding the conventional froth flotation model were discussed at a project review meeting at DOE PETC on May 19, 1992. These included:

- Determining how to get data in time to meet the overall project schedule.
- Proposing a simplified model to be delivered if data is not received in time.
- Calibrating the model for coal rank with only three coals represented.
- Addressing batch to continuous scale-up.

A review of work already completed to generate the equations for the rank/reagent correlations that are in the present model was presented. The data used in these correlations were from nine coal cleanability characterizations conducted at the Coal Quality Development Center covering a range in coal ranks from high volatile B bituminous to low volatile bituminous. Good correlations between recovery and rank (percent carbon on a dry mineral matter free basis) and reagents were found. These correlations can be found in the froth flotation topical report draft.

Concern exists for completing all models and documentation in time for inclusion in the final package. A simplified model was proposed to take the place of the kinetics model should time be a consideration. This model would be based on partition curves (separating gravity and probable error) generated by the Task 6 test program.

A review of the rate and residence time distributions in froth flotation scale-up was presented. In testing various combinations of two residence time equations and two rate equations, it was found that the froth factor documented by WEMCO is the most important variable in scaling from batch to continuous flotation. This factor accounts for differences in pulp level and froth removal rate between laboratory and plant froth flotation cells.

In plant surveys, WEMCO found the ratio of batch rate constant to plant rate constant to vary as the percent of froth height over the lip of the cell in the plant (froth factor) varied. When a high pulp level of high froth factor was maintained in the plant, the ratio between laboratory and plant kinetics decreased. Most laboratory tests were run with a high pulp level. During this analysis, the froth factor was applied successfully to results from two test programs conducted by Arnold (Ph.D. Thesis, 1989). These results will be documented in the final froth flotation topical report.

From this analysis, it was proposed that a perfect-mixers-in-series equation be used with the classical first-order rate equation modified for froth factor for scale-up from batch to continuous.

Rotary Breaker

The rotary breaker model currently in the DOE Coal Preparation Simulator developed by Austin, Luckie, and Klima of Penn State University still represents the most advanced modeling effort of this unit operation. As such, this model is currently being incorporated into an ASPEN PLUS system model and should be available for use in July.

ICF KE is investigating several alternatives to make the model more accurate and understandable to the user.

3.2.3 ASPEN PLUS Implementations

The changes made to the Coal Cleaning Simulator during this period were mostly aimed at correcting problems found during the flowsheet validations. One modification was made to the washability interpolation. Prior to interpolation, the feed size distribution is preprocessed by a subroutine which resets the size intervals. That subroutine was changed to ensure that standard screen sizes be used for the size intervals, with only the topsize being the actual user specified size limit. This should prevent problems such as the size range being much wider than that provided by the user (previously, this subroutine would add fine size intervals to the input size range, in some cases).

Another change made was the modification of the heavy media cyclone water balance algorithm. Because of the internal calculations of both the amount of media and makeup water required, the water balance was not being made correctly in the case where a feed that was too dilute. The report writer for this model was also modified in order to correctly label the material balances reported.

Other changes made were the addition of fifteen coals to the Coal Property Databank (Table 3), and the referencing of utilities in the screen cost models for operating cost calculations.

Finally, a number of problems had been reported for CCS cost models. These were related to discrepancies between UOS block sizing calculations and cost block sizing calculations, and utilities (horsepower requirement) calculations. The corrections were applied to the latest CCS version.

Changes were also made to the CCS documentation. The documentation format is being totally revised to provide more model descriptions and better compatibility with the ModelManager interface.

Table 3. Coals in Coal Property Databank

Coal Name	Databank Name	Coal Rank
Illinois No. 6	ILLINOIS-NO-6	High volatile B bituminous
Meigs Creek	MEIGS-CREEK	High volatile B bituminous
Pittsburgh	PITTSBURGH	High volatile A bituminous
Indiana No. 5	INDIANA-NO-5	High volatile C bituminous
Kentucky No. 9	KENTUCKY-NO-9	High volatile B bituminous
Kentucky No. 11	KENTUCKY-NO-11	High volatile C bituminous
Robinson	ROBINSON	Subbituminous C
Anthracite Culm	ANTHRACITE-CULM	Semi anthracite
Lower Freeport (50%), Upper Freeport (50%)	LFREE50-UFREE50	High volatile bituminous
Upper Freeport	UPPER-FREEPORT	High volatile A bituminous
Upper Freeport (20%), Lower Kittanning (80%)	UFREE20-UFREE80	Medium volatile bituminous
Upper Kittanning	UPPER-KITTANNING	High volatile A bituminous
Lower Kittanning	LOWER-KITTANNING	Low volatile bituminous
Wilcox Group, Upper Calvert Bluff formation	WILCOX-UCALVERT	Lignite A
Stockton-Lewiston	STOCKTON-LEWISTON	High volatile B bituminous

3.2.4 Task 2 Topical Reports

AspenTech reviewed an updated gravity model topical report during the work period. This report will be forwarded to DOE and DOE project consultants. The classification topical report completion is being delayed to allow the incorporation of algorithm changes now being made to the screen models.

3.2.5 Task 2 Model Validation Reports

Comments on all six flowsheet validation reports were received during the work period. After a meeting on May 19, 1992, with DOE PETC and their consultants, it was concluded that the AspenTech team should consider alternate approaches to the model validation process. One suggested alternative is to consider the use of equipment manufacturers as an independent source for individual model validation. AspenTech agreed to explore the alternatives and submit their findings to DOE at a later date.

4.0 TASK 1.3 - Engineering Analysis of Unit Operations for Processing Fine and Ultrafine Coals

TASK 1.4 - Engineering Analysis of Advanced Technologies for Physical Cleaning of Fine and Ultrafine Coals

4.1 Planned Scope of Work

Progress was to be made in Tasks 3, and 4.

4.2 Technical Status

A fine sizing screen and a wet ball mill model will be the first models delivered in Task 1.3. The fine sizing screen model will be the formulation developed by Rogers and Brame of Kennedy Van Saun Corporation for sizing fine coal at various pulp densities on inclined high-frequency vibrating screens (Derrick type). The wet ball mill will use a population balance approach typical of those developed at the University of Utah and Penn State University.

The column flotation model developed at the Virginia Polytechnic Institute and State University (VPI) will be used as the model for advanced froth flotation in the ASPEN PLUS simulator. Relationships between probability of adhesion and various rank, size/specific gravity, and reagent factors still need to be determined.

The advanced cycloning model will be developed from data collected from DOE PETC's micro-Mag process development program. Relationships between particle size and relative separating density and probable error will be regressed from the available data. A functional form will be utilized to generate separation curves for individual size fractions, similar to the approach utilized for the conventional gravity separation models.

To date, no acceptable formulation has been found for modeling selective agglomeration.

5.0 TASK 1.6 - Laboratory Testing

5.1 Planned Scope of Work

The preliminary froth flotation tests were scheduled to begin. Feed sample characterizations were to be performed for Upper Freeport and Pittsburgh seam coals. The necessary data reduction was to begin.

5.2 Technical Status

5.2.1 Froth Flotation

The Upper Freeport seam froth flotation feed samples have been characterized by size and specific gravity. Preliminary froth flotation tests investigating frother and collector dosage and percent solids have been conducted for the crushed to 28 mesh topsize Upper Freeport seam coal. For these tests, three reagent conditions giving results over a range of flotation rate and recovery have been selected as the conditions for complete size and gravity analyses. These conditions are

Test 1 0.16 lb/T MIBC	
Test 1 0.65 lb/T MIBC	
Test 1 0.65 lb/T MIBC	0.65 lb/T Dodecane

For these tests, the feed sample is at 10 percent solids. Kinetic parameters, rate constant and ultimate recovery, were calculated for total yield for each test. For these tests, ultimate recovery values for the yield of the total coal sample ranged from 72 to 82 percent. Values for the rate constant k more than tripled.

Eight different rate equations are being evaluated for use in the final model. These equations are

- Classical first-order
- First-order with rectangular distribution of flotabilities
- fully-mixed reactor (exponential distribution of flotabilities)
- Arbiter second-order equation
- Klimpel second-order equation
- First-order with sine wave
- Classical first-order with time lag (Agar)
- Natural law equation (Lai)

As additional rate data is obtained for the Upper Freeport and Pittsburgh seam coals, each set of data will be fitted to the equations listed above. Comparisons between actual recovery and ultimate recovery will be made for each equation. The equation with

the best overall estimates of ultimate recovery and the lowest standard errors will be selected for use in the final model. All data obtained through August 1992 will be used in the final model equation selection. This data will cover all size and specific gravity fractions to be tested.

Kinetic parameters were calculated for the total yield and the yield of plus and minus 400 mesh fractions for each of the preliminary tests. Some of these results are plotted in the attached graphs, using values calculated for the classical first-order equation. While the exact numeric values for the rate constants and ultimate recovery are different for the other equations, the same trends are observed overall. Figure 4 shows the variation of the rate constant with increasing collector (dodecane) dosage, and Figure 5 shows the variation of ultimate recovery. These tests were conducted at 10 percent solids and with 100 μ l (0.65 lb/T) MIBC. Note that the fine fraction floats at a lower rate than the coarse fraction, but to an overall higher recovery. As expected, flotation rate increases with increasing collector dosage. Ultimate recovery remains about constant as all of these tests give high overall recoveries. Figures 6 and 7 illustrate similar patterns for increasing frother dosage. No collector was added to these tests and the solids content was 10 percent by weight.

The results in Figures 8 and 9 for increasing percent solids show quite interesting trends. The rate constants decrease with increasing solids content for the coarse fraction, while showing a minimum at 10 percent solids for the fines. Ultimate recovery, on the other hand increases with increasing percent solids for the coarse fraction while going through a maximum at 10 percent solids for the fines. These tests were conducted with 100 μ l MIBC; the concentration in the slurry was the same but the dosage on a lb/T basis decreased with increasing percent solids.

A sample of Pittsburgh seam coal has also been obtained for testing. Feed sample characterization and preliminary froth flotation testing has begun.

5.2.2 Other Advanced Processes

A request for proposal for modeling liberation under Task 6 was prepared and submitted to Penn State University. A proposal was obtained from PSU in response. Approval of the liberation work as a subcontract to Penn State University was requested to DOE PETC's contracting office.

Figure 4. Flotation Rate Constant vs Collector Dosage (Upper Freeport)

Figure 5. Ultimate Recovery vs Collector Dosage (Upper Freeport)

Figure 6. Flotation Rate Constant vs Frother Dosage (Upper Freeport)

Figure 7. Ultimate Recovery vs Frother Dosage (Upper Freeport)

Figure 8. Flotation Rate Constant vs Percent Solids (Upper Freeport)

Figure 5. Ultimate Recovery vs Percent Solids (Upper Freeport)

6.0 QUARTER NO. 11 - WORK PLAN

- In Task 2, complete models, complete model documentation, complete testing and validation.
- Continue Tasks 3 and 4.
- In Task 5 complete Upper Freeport seam testing. Continue Pittsburgh seam testing. Begin Illinois No. 6 seam testing.
- Conduct data reduction on Task 6 results for final model rate equation selection.

END

**DATE
FILMED**

10 / 30 / 92