Trip Report Marshall Space Center Computed Tomography ^(U)

by

J. R. Harbour and M. K. Andrews

Westinghouse Savannah River Company
Savannah River Laboratory
Aiken, SC 29808

Received 6/30/92
JUL 24 1992

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

This report was prepared in connection with work done under Contract No. DE-AC09-89SR18035 with the U.S. Department of Energy. By acceptance of this paper, the publisher and/or recipient acknowledges the U.S. Government's right to retain a nonexclusive, royalty-free license in and to any copyright covering this paper, along with the right to reproduce, and to authorize others to reproduce all or part of the copyrighted paper.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

Trip Report Marshall Space Flight Center Computed Tomography ^(U)

BIR Inc. is a small company out of the Chicago area which sells equipment for producing images by tomography. They have built a relatively large instrument, called ACTIS, for NASA at the Marshall Space Center in Huntsville, Alabama and still have access to this instrument. Dick Bernardi of BIR has a grant from Henry Walter of the DOE to determine the utility of computed tomography (CT) for characterization of nuclear and hazardous waste within the DOE complex. As part of this effort, we have been investigating the potential of this technique for obtaining images of canistered waste forms. Funding for data acquisition was provided through this grant. This was our second trip to Huntsville.

Two canistered waste forms were sent to Huntsville for this set of experiments. The first was an IDMS canister filled during the noble metal campaign. No glass sample had been taken from this canister; thus, the waste form was characterized in the "as is" state after the pour. A digital radiograph (DR) of the top of the canister revealed a relatively large void beneath the top of the glass line. A second DR showed the region between the two pours. Several CT scans at various heights of the canister were then taken which detail numerous cracks and some small voids (see Figures 1 and 2). These images are of slices which are 2 mm in height and parallel to the base of the canister. They are consistent with the types of cracks observed in the stainless steel beakers characterized during the first trip.

The second canistered waste form to be analyzed was the bottom, 2-ft high, section of the WIPP canistered waste form. This is the canister which had been filled at TNX back in 1984, overpacked, and then emplaced within WIPP for three years. For two of those years, the waste form was heated to ~ 100°C. This section weighed ~ 1000 pounds and was 2 ft in diameter (normal size for DWPF canisters). Several images were obtained at the region of the dished bottom. However, at the higher levels on the canister, attenuation of the x-rays by this waste form was very high and only faint images were obtained.

A solution to this problem is to use a 6 or 9 MeV electron accelerator as an x-ray source, but shielding problems make this approach impractical. An alternate solution is to use a

wedge in front of the source, which will cut down on the amount of x-rays reaching the detector by air. This will increase the count number for x-rays transmitted through the waste form before detector saturation, which in turn increases the signal to noise ratio. BIR said this approach is standard procedure in the industry, and that they will consider this particular experiment in more detail. Provided it is a feasible approach, and the cost of the wedge is not too high, BIR will fabricate the wedge and we will try the experiment again in January. Consequently, the WIPP canistered waste form was left at Marshall Space Flight Center. Hanford (Jim Weber) will also have samples characterized by CT at this time.

Dick Bernardi is applying for a grant through the DOE's Program Research and Development Announcement (PRDA) for "Research and Development for Environmental Restoration and Waste Management Technologies". BIR's goal is to develop a mobile 2 MeV CT scanner for transport to various DOE sites for waste characterization. The shielding for this source on the truck would weigh ~ 60,000 pounds. Rocky Flats is interested in this unit for characterization of 55-gallon drums. An opportunity exists here for us as well. We will be sectioning a number of the canistered waste forms produced during the DWPF Startup Test Program. These sections will be of a size that can be analyzed in the mobile unit at TNX (provided, of course, the wedge solves the problem discussed above). We could, therefore, develop a database on the nature and amount of voids, crack density, and the nature of the stainless steel/glass interface in prototypically filled canisters with varying glass composition. The cost of this effort is expected to be covered by the DOE grant. Although the WAPS does not require this sort of data, it would provide us with a better basis for discussion of these issues, when raised by interveners. This is a one-time opportunity for this type of data acquisition, as the canistered waste forms will be destructively analyzed during cold-run testing.

As we previously discussed, a letter of support to DOE for this proposal will be drafted. We propose that this letter be expanded to show a willingness on our part to obtain CT data on selected cold-run canisters at TNX using the mobile scanner.

Finally, we offer a timely quotation for DWPF and DWPT, that was observed during our visit to NASA, which was popular during the tenure of Werner Von Braun. In light of the current emphasis on schedule, it is equally important to remember that our goal is also to provide a quality product.

The quotation is:

"THE BITTERNESS OF POOR QUALITY LASTS LONG AFTER THE SWEETNESS OF MEETING THE SCHEDULE".

Figure 1. A CT scan below the surface of the IDMS canister

Figure 2. A CT scan at the interface between the two pours in the IDMS canister

END

**DATE
FILMED**

9 / 14 / 92