27
8-13-76
5 to ATIS

BDX-613-1392

GEAR CUTTING

PDO 6984391, Final Report

R. W. Stiles, Project Leader

Project Team:
G. E. Volkland
L. K. Gillespie
C. P. Rome

Published August 1976

Prepared for the United States Energy
Research and Development Administration
Under Contract Number E(29-1)-613 USERDA

**Kansas City
Division**

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

NOTICE

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Energy Research and Development Administration, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

Printed in the United States of America

Available From the National Technical Information Service, U. S. Department of Commerce, 5285 Port Royal Road, Springfield, Virginia 22161.

Price: Microfiche \$2.25
Paper Copy \$5.45

BDX-613-1392
Distribution Category UC-38

GEAR CUTTING

Published August 1976

Project Leader:
R. W. Stiles
Department 822

Project Team:
G. E. Volkland
L. K. Gillespie
C. P. Rome

PDO 6984391
Final Report

NOTICE
This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Energy Research and Development Administration, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

Technical Communications

**Kansas City
Division**

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

GEAR CUTTING

BDX-613-1392, UNCLASSIFIED Final Report, Published August 1976

Prepared by R. W. Stiles, D/822, under PDO 6984391

This study of gear cutting techniques was divided into three areas: grinding fine pitch pinion gears, generation shaping ratchet teeth, and shaping fine pitch internal gears. Bendix and the Fellows Gear Shaping Company developed the process for grinding 120 pitch, 12 tooth pinion gears. This process repeatably produced an AGMA Class 11 gear, maintaining a 16AA surface finish with minimum burrs.

A study of shaping ratchet teeth resulted in the development of a mathematical model and computer program of the generation shaping process. This computer program provides specific data on contours that can be generated and designs the shaper cutter tooth form. Cutting tests performed on fine pitch internal gears established Bendix tolerance capabilities for total composite error, pitch diameter, and minimum gear tooth relief.

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Energy Research and Development Administration, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

THE BENDIX CORPORATION
KANSAS CITY DIVISION
P.O. BOX 1159
KANSAS CITY, MISSOURI 64141

A prime contractor for the United
States Energy Research and
Development Administration
Contract Number E(29-1)-613 USERDA

CONTENTS

Section	Page
SUMMARY	7
DISCUSSION	9
SCOPE AND PURPOSE.	9
<u>Pinion Gears</u>	9
<u>Ratchet Wheels</u>	10
<u>Internal Gears</u>	12
ACTIVITY	12
<u>Grinding Miniature Pinion Gears.</u>	12
<u>Shaping Ratchet Wheel Teeth.</u>	21
<u>Shaping Internal Gears</u>	36
ACCOMPLISHMENTS.	44
REFERENCES	45
BIBLIOGRAPHY	46
APPENDICES	
A. PINION GEAR BLANK.	47
B. WHEEL TRUING MECHANISM	50
C. COMPOSITE CHARTS FROM FELLOWS NO. 4 REDLINER GEAR CHECKING MACHINE AND INVOLUTE PROFILE CHARTS FROM FELLOWS 12-M INVOLUTE MACHINE.	56
D. MACHINING AND GAGING REQUIREMENTS FOR INTERNAL GEARS	60
E. REPEATABILITY DATA FOR SHAPING INTERNAL GEARS.	68
DISTRIBUTION	78

ILLUSTRATIONS

Figure		Page
1	Pinion Gear Used in Study (P-64633)	10
2	Generation of Involute Profiles.	11
3	Samples of Bendix-Made Ratchet Wheels.	11
4	Gear Shaping Operation	13
5	Unit Dollar Cost Versus Production Quantity for Making Ratchet Teeth on a 20-Tooth Stainless Steel Ratchet Wheel.	14
6	Composite Reading on Fellows No. 4 "Redliner Gear Checker.	20
7	Profile Recording on Fellows 12-M Involute Machine	21
8	Photographs of Tooth Profile (P-64921)	22
9	Comparison of Burrs Produced by Grinding and Hobbing (P-74710).	23
10	Ratchet Wheel Selected for Study	24
11	Fellows 712 Gear Shaper, Showing Recipro- cating Cutter and Ratchet Wheel (P-74631).	25
12	Generated Tooth Profile.	26
13	Shaper Cutter Tooth Action During Ratchet Tooth Generation	27
14	Three Types of Ratchet Teeth	28
15	Three Types of Epicycloidal Curves	29
16	Locus of Negative Rake Ratchet Tooth	30
17	Epicycloidal Curve	32
18	Prolate or Curtate Epicycloidal Curve.	32
19	Computer Generated Ratchet Wheel	34

20	Typical Radial Ratchet Wheel Manufactured at Bendix	35
21	Computer Generated Radial Ratchet Wheel . . .	36
22	Single Position Hob Applications.	37
23	Internal Gear Blank	38
24	Clearance Groove Required for Cutting Blind Internal Teeth.	42
A-1	Pinion Gear Blank	48
A-2	Graphic Gear, Pinion.	49
B-1	Full Form Diamond Dressing Tool	52
B-2	Wheel Truing Attachment (P-64631)	53
B-3	Wheel Truing Device	54
B-4	Diamond Dresser and Grinding Wheel (P-64635)	55
C-1	Master Gear and Staging Fixture for Redliner Gear Checker (P-64636)	57
C-2	Composite Readings Obtained at BKC on Fellows No. 4 Redliner Gear Checker. . .	58
C-3	Typical Involute Profile Recorded on Fellows 12-M Involute Machine	59
D-1	Internal Gear Characteristics	62
D-2	Shaper Cutter	66
D-3	Master Gear for Internal Gear Cutting	67
E-1	Pitch Diameter Variations	70
E-2	Total Composite Error Variations.	71
E-3	High and Low Pitch Diameters, Setup Contributions	72
E-4	High and Low Pitch Diameters, Run Contributions	73

E-5	Total Composite Error Readings, Setup Contributions.	74
E-6	Total Composite Error Readings, Run Contributions.	75

TABLES

Number		Page
1	Inspection Data for Parts Ground in Support of Development Contract.	16
2	Averages and Standard Deviations for Internal Ring Gear	40
3	TCE Percent Defective by Gear Class.	40
4	Minimum Width or Clearance Groove and Excess Travel of Cutter Slide.	43
E-1	Handling Sequence.	69
E-2	Operator/Setup Averages and Bias for Gage Study	76
E-3	Standard Deviations for Gage Study	77

SUMMARY

The activity on this project was divided into three sections: grinding 120 pitch, 12 tooth pinion gears; shaping ratchet wheel teeth; and shaping fine pitch internal gear teeth. These activities were carried to provide new knowledge in the areas of gear cutting for Bendix engineers.

The first activity involved grinding a miniature pinion gear. Although grinding inherently produces a better involute form and finer surface finish than other basic gear fabrication methods, equipment and experience in grinding 120-pitch gears with 0.100-inch (2.54 mm) pitch diameters were not available when Bendix Kansas City placed a process development contract with the Fellows Company. Bendix had been producing a functional miniature gear by hobbing, but the required surface finish was borderline and burrs on the part were difficult to remove. As a result of this project, a repeatable process was developed for grinding the tooth form and maintaining a 16 μ in. AA (0.41 μ m) surface finish with minimum burrs. An experimental machine was used in this process development; production equipment is not yet available in U. S. industry for this process but could be developed.

The second area investigated was generation shaping ratchet wheel teeth. Bendix manufactures a wide variety of ratchet wheels for electromechanical devices: hobbing, blanking, and form milling are most commonly used. But because of disadvantages associated with each, gear shaping was studied as an alternate, more versatile method of making ratchet teeth. In gear cutting, the reciprocating action of the cutter permits cutting internal teeth and features that are closely banked against obstructions. In addition, irregular, segmented, noncircular, or interrupted configurations can be produced.

Initial investigations, using the trial-and-error layout cutter design technique, were found to be too inaccurate for Bendix purposes. Therefore, a mathematical model and computer program were created that will accurately predict whether a desired ratchet tooth geometry can be produced, and will also design the cutting tool.

The final activity was shaping internal gear teeth. A 120 pitch, 80 tooth internal gear was selected for cutting tests on the Fellows No. 3 Fine Pitch Gear Shaper. The intent of the study was to cut an internal gear that would meet an AGMA Class 10a requirement. A secondary objective was to determine the minimum permissible gear tooth relief.

The test data showed that the standard deviations for the high and low pitch diameters were 0.00036 and 0.00056 inch (9.1 and 14 μm) respectively and that the total composite error (TCE) had a standard deviation of 0.00051 inch (13 μm). Based on these estimates, with 95 percent confidence 95 percent of the high low pitch diameters would fall within an interval 0.00327 inch (83.1 μm) wide. Also, with 95 percent confidence 95 percent of the TCE readings will be less than 0.00239 inch (60.1 μm). Since the TCE on a Class 10 gear is 0.0010 inch (25.4 μm), the study showed that 67.4 percent of the gears could be expected to be defective.

The parts used to estimate tool relief were shaped oversize so the shaper cutter would penetrate into the undercut. The parts were sectioned and checked on a toolmaker's microscope. The average cutting depth below the tooth was 0.0035 inch (89 μm), with a standard deviation of 0.00075 inch (19 μm). Based on this standard deviation, the minimum tool relief necessary to contain 95 percent of the readings 95 percent of the time was 0.0065 inch (165 μm).

DISCUSSION

SCOPE AND PURPOSE

Pinion Gears

A 120-pitch, 12-tooth pinion gear (Figure 1) is one of a family of similar gears used in escapement assemblies. The timing repeatability of the escapement assemblies is influenced by the accuracy and surface finish on the gearing. Consequently this pinion and the other gears in the escapement assemblies require a 16 microinch ($0.41\ \mu\text{m}$) AA surface finish on the working surfaces of the teeth and a precision tooth form to AGMA quality class 11b+. Small commercial pinions of this pitch and size are fabricated by hobbing and are generally made of soft material such as brass or mild steel. For this reason, little effort had been made by industry to develop grinding equipment for this size gear. The blank for 120 diametral pitch (DP) gear is extremely small (0.100 inch [$2.54\ \mu\text{m}$] pitch diameter) and is made from 17-4 PH stainless steel heat treated to a hardness of Rockwell C (RC) 41 minimum, which places it at the upper limits of machinability.

Bendix was producing this gear by hobbing, using a Class AAA hob. Although a functional gear was being produced when the hobs were sharp, the required surface finish was borderline and deburring had become a major problem. Therefore, the most logical step for improvement of the process was to grind the tooth form. A process development contract was placed with the Fellows Company (formerly the Fellows Gear Shaper Company) to develop a repeatable process for grinding the tooth form and maintaining a 16 microinch (AA) surface finish with minimum burrs. Fellows was to develop any tooling necessary for an experimental grinder in their shop and produce 50 pinions to print tolerances.

Gear grinding is one of the first methods used to finish gears.¹ Grinding inherently produces a better involute form, a better tooth-to-tooth error (TTE), a better total composite error (TCE), and finer surface finishes than other basic gear fabrication methods. Gear grinding is used when the need for any or all of the above conditions exists. As the material in a blank becomes harder, grinding may be the only method available to produce the gear teeth form. Although grinding can be performed at any hardness range, optimum hardness for grindability is from RC 40 to 55.² Coarse pitch gears (up to 48 DP) require prefinishing operations such as hobbing or shaping preparatory to grinding, but fine pitch gears (48 DP and finer) are ground from solid blanks.

Figure 1. Pinion Gear Used in Study

Generation grinding using a threaded grinding wheel (Figure 2) is especially adaptable to high-volume production work. This process operates on the same principle as hobbing in that the threaded grinding wheel acts like a rack with the lead in the thread form allowing continuous grinding action without indexing.

Ratchet Wheels

Bendix manufactures a wide variety of ratchet wheels for electro-mechanical mechanisms (Figure 3). The ratchet wheel teeth are produced by hobbing, blanking, or by form milling one tooth at a time on a vertical or horizontal milling machine. The last is the most common process but all have some limitations or disadvantages. Hobbing at Bendix is presently limited to a 0.625 inch (15.8 mm) diameter blank because of machine capacity, and the teeth must be equally spaced about the entire periphery of the blank. Dies for blanking ratchet teeth are expensive and production quantities must be high to justify the initial tooling costs. Material selection is another important factor in blanking: 6061 aluminum, for example, tears when blanked. Form

Figure 2. Generation of Involute Profiles

Figure 3. Samples of Bendix-Made Ratchet Wheels

milling is slow, requires large numbers of cutting tools, and does not have the accuracy or repeatability of the other two processes. None of these processes can produce banked or internal ratchet teeth.

This study was undertaken to develop gear shaping (Figure 4) as a method of producing ratchet teeth. Gear shaping offers considerable flexibility as a metal cutting process: the cutter, which has suitable relief to provide cutting edge clearances, rotates in timed relationship with the workpiece and cuts by reciprocating. The reciprocating action permits internal teeth and cutting features that are closely banked against obstructions. Irregular, segmented, noncircular, or interrupted configurations can also be produced.

In comparing gear shaping to the other ratchet teeth manufacturing processes, the cost of the process has to be taken into consideration (Figure 5). In production quantities in excess of 2000, fine edge blanking is the most economical process. Hobbing is the most economical at any production run size and form milling is the most expensive. Cost, however, is not the only consideration in process selection. Gear shaping offers the greatest versatility of the four.

Bendix obtained two gear shapers in 1969: a Fellows Number 3 Gear Shaper for fine pitch gear teeth (40 DP and finer) up to 3 inches (76.2 mm) pitch diameter, and a Fellows Number 712 Gear Shaper for coarse pitch (7 DP maximum) gear teeth up to 7 inches (177.8 mm) external and 5.5 inches (139.7 mm) internal pitch diameter.

Internal Gears

The study on shaping internal gear teeth was carried out to provide Bendix engineers with data on tolerance capabilities related to functional internal gear characteristics and to define the limitations of the gear shaping process. Machining tests were carried out to establish a process standard deviation on pitch diameter, total composite error, and minimum permissible gear tooth relief.

ACTIVITY

Grinding Miniature Pinion Gears

Equipment and Technique

Grinding 120-pitch gears presented no problem to the Fellows Company since they grind master gears and shaper cutters of this pitch for their customers. This was the first attempt by anyone,

Figure 4. Gear Shaping Operation

however, to grind a gear with a 0.100-inch pitch diameter. The part presented unique problems with respect to grinding because of its minute size (Appendix A). The blank had to be located and driven off two 0.0261-inch-diameter (0.663 mm) journals. The proportion of the grinding wheel diameter to the part diameter created problems in the design and fabrication of the workholding centers. To grind to full depth with the wheel, the outside diameter on the workholding centers had to be thinned to 0.075-inch (1.9 mm) diameter for 0.25-inch (6.35 mm) length; there was also an apparent danger that both the centers and the work piece might spring away from the grinding wheel due to grinding pressure. Further complicating this operation was the difficulty of applying sufficient holding pressure from the machine's tailstock to drive the gear during the machining cycle.

Figure 5. Unit Dollar Cost Versus Production Quantity for Making Ratchet Teeth on a 20-Tooth Stainless Steel Ratchet Wheel

The machine used in this project was an experimental fine pitch gear grinder. The grinding wheel selected (Norton 38A400-J9VG) was 400-grit aluminum oxide. The diameter of the wheel is 4 inches (102 mm). A rack form (two times the pressure angle, or 40 degrees) was threaded into the wheel at a precalculated lead angle (see Appendix B for a description of wheel truing and dressing operation). The workholding device was mounted in two female centers; the device consists of a driving center mounted in the headstock and a driven center mounted in the tailstock. The gear blank was placed in the female centers and pressure was applied from the tailstock to keep the blank from rotating during grinding. The work holding centers were horizontally mounted on the machine and the grinding wheel spindle rotates, strokes

axially across the part, and feeds in at a controlled amount at the end of each stroke. This action continues until full depth of the gear tooth is reached, at which time the wheel head automatically retracts. The lead angle on the grinding wheel allows continuous action without indexing. Only a small portion of the grinding wheel is used at a time. As the wheel dulls, the wheel head is shifted vertically (tangential about 0.050 inch [1.27 mm]) to a new area.

The surface speed was 3769 feet per minute (19.15 m/s). The workpiece rotated at 300 rpm and the grinding wheel at 3600 rpm. The wheel head slide speed was 0.0029 inch (74 μm) per revolution of the workpiece and the infeed rate was 0.0008 inch (20 μm) per stroke.

The actual grinding of the pinions from setup to completion took place in a 3-week period. In first setting up the job the originally calculated wheelhead speed of 2 seconds per 0.175 inch (4.45 mm) stroke was too fast and the wheelhead was feeding in the middle of the stroke. The speed was changed to 9 seconds per stroke which corrected the problem. Drag in the tailstock live center and insufficient drive pressure was hindering the rotation of the pinion gear during the machining cycle. The tailstock center had to be lapped four times before it ran free enough to allow the pinion to rotate with the driving headstock center.

About twenty-five pinions were required to debug the process and tooling. Once the initial setup problems had been corrected, however, little trouble was encountered in grinding the tooth form.

Results

A total of 91 gears were ground during the course of this project; 61 were within print tolerance and 30 were scrapped. Of the 30 scrapped parts, 15 were lost during setup. Seventy-four percent of the 50 good parts required by the contract fell within a range of 0.00020 to 0.00040 inch (5.1 to 10 μm) on the TCE with only 12 percent exceeding 0.0004 inch (10 μm). Seventy-six percent of the 50 parts fell within a range of +0.00020 to -0.00030 inch (+5.1 to -7.6 μm) from the nominal on the over pin measurement of the pitch diameter. See Table 1.

Cycle Time. When the machining time of the grinding operation was compared to hobbing, only the actual machine cycle time was compared since all other functions would have been similar for both methods. The cycle time for hobbing after engaging the machine is 2.4 minutes and the average cycle time established during the course of this project for grinding was 5.6 minutes at the feed rates used. The grinding feed rates used were conservative; by increasing the wheelhead slide speed and the infeed

Table 1. Inspection Data for Parts Ground in Support of Development Contract

Part* Number	TCE** (Inch)† Limit 0.00055 Inch	DOP*** (Inch)† 0.1233 to 0.1219 Inch	Good
1	Did not rotate		
2	Did not rotate		
3	Did not rotate		
4	0.00040	0.12240	X
5	0.00060	0.12190	
6	0.00040	0.12160	
7	0.00040	0.12170	
8	Did not rotate	Did not rotate	
9	0.00035	0.12320	X
10	0.00040	0.12320	X
11	Machine malfunction	Machine malfunction	
12	Ground flat	Ground flat	
13	0.00056	0.12080	
14	0.00015	0.12580	
15	Not checked	0.12400	
16	0.00065	0.12290	
17	Not checked	0.12800	
18	Machine malfunction	Machine malfunction	
19	0.00060	Not checked	
20	0.00035	0.12230	X
21	0.00055	0.12190	X
22	Machine malfunction	Machine malfunction	
23	0.00030	0.12150	
24	0.00055	0.12180	
25	0.00080	0.12280	
26	0.00018	0.12200	X
27	0.00018	0.12260	X
28	0.00045	0.12174	
29	0.00015	0.12250	X
30	0.00050	0.12160	
31	0.00040	0.12280	X
32	0.00020	0.12280	X
33	0.00025	0.12260	X
34	0.00030	0.12260	X
35	0.00040	0.12265	X
36	0.00040	0.12260	X
37	0.00025	0.12250	X
38	0.00028	0.12240	X
39	0.00030	0.12260	X
40	0.00025	0.12250	X
41	0.00040	0.12240	X
42	0.00040	0.12240	X
43	0.00020	0.12260	X

Table 1 continued. Inspection Data for Parts Ground in
Support of Development Contract

Part* Number	TCE** (Inch)† Limit 0.00055 Inch	DOP*** (Inch)† 0.1233 to 0.1219 Inch	Good
44	0.00015	0.12260	X
45	0.00018	0.12240	X
46	0.00030	0.12250	X
47	0.00035	0.12190	X
48	0.00045	0.12190	X
49	0.00020	0.12214	X
50	0.00025	0.12234	X
51	0.00030	0.12255	X
52	0.00030	0.12255	X
53	0.00030	0.12260	X
54	0.00025	0.12260	X
55	0.00045	0.12260	X
56	0.00030	0.12267	X
57	0.00020	0.12267	X
58	0.00030	0.12260	X
59	0.00040	0.12260	X
60	0.00025	0.12260	X
61	0.00035	0.12260	X
62	0.00015	0.12260	X
63	No teeth	No teeth	
64	Machine malfunction	Machine malfunction	
65	Machine malfunction	Machine malfunction	
66	0.00025	0.12230	X
67	0.00020	0.12220	X
68	0.00020	0.12200	X
69	Machine malfunction	Machine malfunction	
70	0.00015	0.12240	X
71	0.00050	0.12240	X
72	0.00025	0.12240	X
73	0.00020	0.12300	X
74	0.00040	0.12260	X
75	0.00035	0.12260	X
76	Machine malfunction	Machine malfunction	
77	0.00045	0.12160	
78	0.00035	0.12260	X
79	0.00035	0.12330	X
80	0.00050	0.12342	
81	0.00025	0.12330	X
82	0.00035	0.12260	X
83	0.00035	0.12300	X
84	0.00025	0.12330	X
85	0.00035	0.12260	X
86	0.00040	0.12260	X

Table 1 continued. Inspection Data for Parts Ground in
Support of Development Contract

Part* Number	TCE** (Inch)† Limit 0.00055 Inch	DOP*** (Inch)† 0.1233 to 0.1219 Inch	Good
87	0.00020	0.12290	X
88	0.00050	0.12290	X
89††	0.00035	0.12160	
90††	0.00030	0.12260	X
91††	0.00040	0.12285	X

*Parts are listed in the order that they were ground.

**The composite check was made on a No. 4 Fellows Redliner
Gear Checker at 800 to 1 amplification.

***The over pin measurements were made using 0.015-inch-diameter
(0.38 mm) pins and a super-micrometer.

†1 inch = 25.4 mm.

††Ground at an infeed rate of 0.0012 inch (30 μ m) per stroke.

rate, the cycle time could be reduced by as much as 40 percent. To verify this, the last three gears were ground at an infeed rate of 0.0012 inch (30 μ m) per stroke. The greater infeed rate had no effect on surface finish, TCE, or pitch diameter.

Inspection Data. The two basic checks required on the pinion gears consisted of a composite check and a pitch diameter check. The total composite error (TCE) and tooth-to-tooth error (TTE) were checked on a Fellows No. 4 Red Liner at 800 to 1 amplification (Figure 6). The part was held in a special V-block fixture and rolled with a 120 DP, 1.500-inch (38.10 mm) pitch diameter master gear. The pressure was set at 4 ounces (1.1 N). One of the pinions (Number 7) was selected as a master for both the Red Liner check and pitch diameter check. The No. 7 master pinion and at least two other pinions were checked each day to maintain the sizing on the Red Liner and to ensure that the machine setup was not disturbed during the night shift hours.

The pitch diameter of the pinions was checked over 0.0150-inch-diameter (0.381 mm) pins on a super-micrometer. The anvil pressure was set at 2 to 2.5 ounces (0.56 to 0.69 N). The required pitch diameter limits were 0.1233 to 0.1219 inch (3.132 to 3.096 mm). This gave a tooth thickness at the pitch diameter of 0.01399 to 0.01327 inch (0.3553 to 0.3371 mm).

The tooth profiles were checked on a Fellows 12-M Involute Machine in 3-degree increments at 5000 to 1 magnification. The involute profile measuring instrument duplicates the generation of an involute curve from the base circle. The probe contacts the tooth profile and measures a deviation from true involute on a roll tape. Profile variations are measured in the traverse plane.

The check was made by holding the pinion in a small drill chuck on one journal. The drill chuck was fitted to a tapered adaptor that would replace the bottom center in the 12-M Machine. The drill chuck was lined up in the adaptor first by setting the tapered adaptor in a precision V-block with a ball bearing in the end against a plate. A 0.0350-inch (0.889 mm) pin was set in the chuck and was lined up with a high magnification indicator to run 0.00008 inch (2.0 μ m) total indicator reading (TIR). Then with the drill chuck lined up in the adaptor, a pinion was inserted in chuck and the other journal was indicated to run a TIR of 0.00040-inch (10 μ m) or better.

After the pinion had been aligned in the chuck, the adaptor was set in the bottom center position in the machine. The machine was set by blocks figured from the base circle. The involute profile was rolled from 0 degree or radial (Figure 7). A standard stylus was thinned by hand for the pointer. On the first pinion

Figure 6. Composite Reading on
Fellows No. 4 Redliner
Gear Checker

rolled, the base circle was changed by only 0.0001 inch ($2.5 \mu\text{m}$) to keep the involute itself within 0.0001. This accuracy indicated that the pressure angle on the grinding wheel was good. The charts from radial showed approximately 48 to 50 degrees of roll. Appendix C shows some actual charts obtained.

Because of the part's minute size, it was impossible to obtain a quantitative inspection of the tooth surface finish. Three approaches were taken to qualify the surface finish produced.

- A random sample of parts was checked on an involute checking machine at Fellows' plant using 5000 to 1 amplification. Charts were made on five of the best 50 pinions ground. These charts were made for the purpose of estimating surface finish only. The part print called for a 16 μinch ($0.41 \mu\text{m}$) AA surface finish on the working surface of the tooth. Since the stylus traced the involute form perpendicular to the lay lines in the tooth and because of the high magnification used, surface roughness can be seen in the chart recording.
- A random sample of five good parts was visually compared to a known standard by Bendix inspection personnel for an interpretation of surface finish.
- Three ground and three hobbed gears were photographed on a scanning electron microscope to compare the surface finish at high magnification. Typical results are shown in Figure 8.

All of the techniques used indicated that better than a 16 μinch AA surface finish was obtained.

Figure 7. Profile Recording on Fellows 12-M Involute Machine

Deburring. Figure 9 shows a comparison of the burrs generated by hobbing and grinding. The burrs produced at the end, where the cutter exits, and at the crest of the tooth are the most difficult to remove. The burrs in these areas on the hobbed gears are larger, better attached to the parent metal, and much more difficult to remove than the burrs on the ground part.

A sample of ten ground gears were vibratory deburred for one hour in N8 media (fused Al_2O_3) and PC-12B burnishing compound. All of the grinding burrs were removed from the parts with no apparent damage to the surface finish when examined under 25X magnification.

Shaping Ratchet Wheel Teeth

Initial Gear Shaping Attempts

A ratchet wheel (Figure 10) used in a production part was selected to study generation shaping using Fellows tooling. This part is a positive rake ratchet wheel with a large radius at the root of the tooth.

← CREST OF TOOTH

GROUND GEAR

HOBBED GEAR, NEW HOB

HOBBED GEAR, USED HOB

Figure 8. Photographs of Tooth Profile (200X)

The first efforts were too inaccurate. Test specimens were cut on the Fellows Number 712 Gear Shaper (Figure 11) and the tooth form inspected on an optical comparator with an overlay chart. The back side of the tooth was within the required 0.004-inch

Figure 9. Comparison of Burrs Produced by Grinding and Hobbing (17-4 PH Stainless Steel, H900 Condition)

Figure 10. Ratchet Wheel Selected for Study

(0.1 mm) tolerance band, but the face was about 0.008 inch (0.2 mm) too large (Figure 12). When the cutter was fed deeper into the blank to remove the excess material, the total tooth thickness was reduced, creating an undersized back side of the tooth.

Fellows could not determine how the cutter could be altered to eliminate the unwanted material; in their judgement, no further refinements could be made because they had already optimized the cutter's design.

Figure 11. Fellows 712 Gear Shaper, Showing Reciprocating Cutter and Ratchet Wheel

Figure 12. Generated Tooth Profile

Bendix Engineers discovered that Fellows used layout techniques for cutter design on non-involute applications. Layout, a trial-and-error technique, depends on the experience of the layout draftsman and can only approximate the ratchet tooth and cutter tooth geometry. Therefore, the scope of Bendix's study was expanded to develop a mathematical model and computer program for generation shaping.

Development of Mathematical Model

Theory of Gear Shaping. To create a profile on a gear shaper, both members (cutter and workpiece) must have pitch line movement: two pitch circles rolling together, or a combination of a pitch circle and a pitch line movement, as in cutting a rack. The cutter's tooth curve is driven in unison with a mating blank, generating a tooth profile in the blank that will mesh with itself as shown earlier in Figure 4. In shaping involute gear teeth, the cutter tooth is also an involute form of the same pressure angle and pitch. In the case of a ratchet tooth, however, the cutter tooth must be an arcuate contour that will roll with the straight sides of the ratchet tooth (Figure 13).

Figure 13. Shaper Cutter Tooth Action During Ratchet Tooth Generation

Ratchet wheel tooth geometry is divided into these three classes (Figure 14):

- A radial tooth form in which the tooth face lies on a radial plane from the centerline;
- A positive rake tooth form in which the tooth face lies from radial to below radial; and
- A negative rake tooth form in which the tooth form lies from below radial to radial.

Figure 14. Three Types of Ratchet Teeth

As the pitch circles of the cutter and the workpiece are rolled together, the cutter's locus is an infinite number of cycloidal curves (Figure 15): an epicycloidal curve, a curtate epicycloidal curve, or a prolate epicycloidal curve. Therefore, the cutter tooth's path as it generates the mating ratchet tooth will be made up of one, two, or a combination of all cycloidal curves.

The cycloidal curve(s) describing the cutter tooth loci will depend upon where the pitch circles intersect the ratchet tooth; the ratchet tooth geometry is in turn determined by the loci the cutter follows. A direct relationship therefore exists between the tooth geometry and the pitch circles.

Figure 16 shows the locus of each of nine points selected along each side of a negative rake ratchet tooth as the two pitch circles roll together. The envelope formed by these loci define the cutter tooth profile that will produce this ratchet tooth.

Figure 15. Three Types of Epicycloidal Curves

These manipulations can be made to the pitch circles to influence the ratchet tooth geometry.

- The workpiece's pitch circle will intersect the ratchet tooth's root diameter. The resultant pitch circle of the shaper cutter will intersect the major diameter, or crest, of the cutter tooth. The locus of the cutter tooth's leading edge will follow an epicycloidal curve and the loci of all other surfaces on the cutter tooth will follow curtate epicycloidal curves. With this type of cutting action, the point at the cutter's tip on the ratchet wheel tooth can be reproduced and thereby produce a "sharp" fillet radius. The only ratchet tooth applicable to this type of cutting action is the negative rake tooth shown earlier in Figure 14.
- The workpiece's pitch circle will pass through a plane somewhere between the crest and root of the ratchet tooth. The shaper cutter's pitch circle will pass through a corresponding plane on the cutter tooth. The cutter's loci will be a series of epicycloidal, curtate epicycloidal, and prolate epicycloidal curves. This type of cutting action will produce a radial, negative, or positive rake tooth with a large fillet radius at the root.

Figure 16. Locus of Negative Rake Ratchet Tooth

- The workpiece's pitch circle will be extended beyond the crest of the ratchet tooth. All of the cutting edges will move in a plane below the cutter's pitch diameter. The locus of all points on the cutter will be a prolate epicycloidal curve. This looping action will undercut the face of the ratchet tooth and create a positive rake tooth as shown earlier in Figure 14.

Using this gear shaping theory, a mathematical model of generation shaping was developed to provide precise data on cutter tooth design and ratchet tooth geometry obtainable with this cutter.

These mathematical formulas calculate the locus of the cutter tooth:

- Epicycloidal Curve (Figure 17):

$$X = (R + r) \cos \theta - r \cos \frac{R + r\theta}{r}$$

$$Y = (R + r) \sin \theta - r \sin \frac{R + r\theta}{r}$$

- Prolate Epicycloidal Curve (Figure 18):

$$X = (R + r) \cos \theta - r' \cos \frac{(R + r\theta + \ell)}{r}$$

$$Y = (R + r) \sin \theta - r' \sin \frac{(R + r\theta + \ell)}{r}$$

$$r < r'$$

- Curtate Epicycloidal Curve (Figure 18):

$$X = (R + r) \cos \theta - r' \cos \frac{(R + r\theta + \ell)}{r}$$

$$Y = (R + r) \sin \theta - r' \sin \frac{(R + r\theta + \ell)}{r}$$

$$r > r'$$

Data Input. To use this mathematical model for a specific application, a sufficient number of points (radial distance and angle from the ratchet wheel centerline) on the ratchet tooth must be described so that when these points are connected with straight lines, a complete tooth is defined. These points are entered in the data deck of the computer program. The pitch radius of both the ratchet wheel and the cutter are also entered in the data

Figure 17. Epicycloidal Curve

Figure 18. Prolate or Curtate Epicycloidal Curve

deck along with the total angle selected to roll the pitch circles through angle θ and the number of divisions that θ will be divided into $\Delta\theta$.

Data Output. The computer calculates the X and Y coordinates defining the cutter tooth and then draws the profile on the plotter. The plotted cutter tooth is then rolled through angle θ and redrawn every 2 degrees ($\Delta\theta$) over the previously drawn ratchet wheel. The generated envelope will show any departures in tooth definition from the input tooth. By manipulating the pitch (rolling) circles, the best condition that can be generated on a gear shaper can be created.

The plotter will also draw a two-dimensional line definition of the cutter tooth at any desired magnification for manufacturing and inspection of the cutter.

The tooth form on the previously selected production part ratchet wheel was entered in the computer program and the plot (Figure 19) showed that this tooth profile could have been created by gear shaping, and that incorrect cutter design (and not process limitations) prevented it.

A radial ratchet tooth (Figure 20) was also entered into the program to determine if it could be generated on a gear shaper. This ratchet tooth is typical of those manufactured at Bendix for use in several electromechanical assemblies. The computer plot in Figure 21 shows the optimum tooth form that can be produced by generation shaping. The face of the tooth can be held on the radial for approximately half its total depth and the smallest fillet radius obtainable in this particular case is a 0.015-inch (0.4 mm) radius, about twice that required.

Results

The creation of a mathematical model and computer program has advanced gear shaping from trial-and-error to mathematical precision.

From the study, some general observations can be made about generation shaping ratchet wheel teeth.

- A "sharp" fillet radius can only be generated on a negative rake tooth.
- A radial tooth can be shaped if sufficient fillet radius is allowed. Only a third to a half of tooth depth can be held radial.
- To produce a positive rake (undercut face) tooth, the pitch circles must be in a plane at or beyond the crest of the ratchet tooth.

Figure 19. Computer Generated Ratchet Wheel

Figure 20. Typical Radial Ratchet Wheel Manufactured at Bendix

- The cutter's pitch circle should be made as large as possible. Enlarging the cutter increases the generating pressure angle allowing the cutter tooth to enter and withdraw from the blank at a steeper angle, reducing the undercutting and topping effect. The cutter used to shape the Coded Enable Switch ratchet wheel was four times larger than the ratchet wheel blank.
- The relative position of the theoretical pitch circles can be manipulated to influence the ratchet tooth geometry.

A radial tooth form like that shown in Figure 20 can be produced by hobbing if the teeth are not obstructed and are equally spaced about the periphery of the ratchet wheel. A single position hob can be used for these applications with the hob offset from the ratchet wheel centerline (Figure 22).

The computer program developed is a useful tool to the process engineer investigating gear shaping as a metal cutting process. The program will tell if a desired geometry can be generated on a

Figure 21. Computer Generated Radial Ratchet Wheel

gear shaper, and will also design the cutting tool. An optical comparator overlay of the cutter tooth at any desired magnification can be obtained through the Calcomp plotter. The overlay can be used to both manufacture and inspect the cutting tool. Although the study was directed toward ratchet teeth, the theory and computer program are applicable to any geometry.

Shaping Internal Gears

Machining Test Samples

The study part was a 20 degree full depth, 120 pitch, 80 tooth internal gear. The blanks, shown in Figure 23, were made from free machining brass.

Fifty test gears were shaped to provide statistical data on the PD and TCE. To establish data for depth repeatability, 20 gears were shaped 0.010 inch (0.254 mm) oversize on the PD so the cutter tooth would bottom approximately 0.005 inch (0.127 mm) deep into the clearance groove. Appendix D shows machining and gaging requirements for the gears.

PARTS HAVING SPECIAL FORMS

Figure 22. Single Position Hob Applications

INTERNAL SPUR GEAR TOOTH DATA

- I. NO. OF TEETH: 80
- II. DIAMETRAL PITCH: 120
- III. PRESSURE ANGLE: 20°
- IV. STD. PITCH DIA: 0.6667 IN. (16.934 mm)
- V. TOOTH FORM: STD. ADD. PER AGMA STD. 207.04
- VI. AGMA CLASS: 10A (SEE NOTE 2) PER AGMA STD. 290.02 AND 236.05
- VII. BACKLASH ALLOWANCE TO BE: 1/2 ON EACH GEAR
- VIII. MATING GEAR DWG.: 1443703 REF.
- IX. OPERATING CENTER DISTANCE: 0.2124 TO 0.2044 IN. (5.395 TO 5.090 mm)

Figure 23. Internal Gear Blank

Shaper Operation

All of the study gears were machined on a Fellows No. 3 Gear Shaper utilizing a 52-tooth shank type cutter and a three-cut depth feed cam. The cutting rate was set at 2000 strokes per minute at a rotary feed of 0.0006 inch (15 μ m) per stroke or 2268 strokes per revolution of the cutter. The cutter made about 1.6 revolutions to each revolution of the gear blank and 3 revolutions of the blank were required to finish the teeth. The gear was rerun through the cycle to help reduce the burrs on the teeth. The cutting time calculated for one cycle was 5.1 minutes.

Since the shaper cutter is essentially a pinion gear with cutting clearances, the same problems of interference that can exist between a pinion and internal gear also apply to the cutter. As a general rule, the smallest permissible difference between the number of teeth in an internal gear and in a cutter is ten teeth for a 20 degree full length and eight teeth for a 20-degree stub tooth form.³

Gaging Gear Characteristics

The TCE and PD on the study gears were checked on a No. 4 Fellows Redliner gear checking machine. The master gear used had 60 teeth and the study gear 80 teeth. Since the ratio of the number of teeth on the study gear to the number of teeth on the master is 4 to 3, four revolutions of the master results in three revolutions of the internal gear. The master gear checked within 0.000050 inch (1.27 μm), so its contribution is considered negligible.

Thirty-six parts were selected from the 50 test gears to study. The TCE (difference between the high and low pitch diameter readings) was computed using the second revolution on each run, and the high and low pitch diameters were recorded. The results of this data are summarized in Table 2. The standard deviations for the high and low pitch diameters are 0.00036 and 0.00056 inch (9.144 and 12.7 μm) respectively, and the TCE has a standard deviation of 0.00051 inch (12.954 μm). Using these estimates, with 95 percent confidence, 95 percent of the high and low pitch diameters would be contained in an interval 0.00327 inch (83.058 μm) wide. Similarly, with 95 percent confidence, 95 percent of the TCE readings would be less than 0.00239 inch (60.706 μm).

The intent of the study was to make internal gears that would meet Class 10 gear requirements. This class gear has a TCE tolerance of 0.0010 inch (25.4 μm). Since the interval that would contain 95 percent of the TCE readings 95 percent of the time is 0.00239 inch (60.706 μm), the study gears would not meet the Class 10 requirement, with 67.4 percent of the gears expected to be defective. Table 3 shows the percent defective that could be expected for four classes of gears (Classes 7, 8, 9, and 10).

A gage study was performed which consisted of two operators each making two complete setups and three runs within each setup. A setup consisted of tearing down the previous setup, recentering the arbors, and mastering the distance between centers. A run is removing the gear from its locating pin and repositioning it each time. Since each run consists of three revolutions of the ring gear, three estimates of the high and low pitch diameters were obtained.

Table 2. Averages and Standard Deviations for Internal Ring Gear

		Pitch Diameter		
		High in. (mm)	Low in. (mm)	TCE in. (mm)
Average		0.66746 (16.953)	0.66618 (16.921)	0.00128 (0.0325)
Standard Deviation		0.00036 (0.0091)	0.00056 (0.0142)	0.00051 (0.0129)
Confidence Statements*	Upper Limit	0.66824 (16.973)	---	0.00239 (0.0607)
	Lower Limit	---	0.66497 (16.890)	---
	Total Interval	0.00327 (0.0831)		0.00239 (0.0607)

*With 95 percent confidence, 95 percent of the readings will either be below (above) the upper (lower) limits or contained in the total interval.

Table 3. TCE Percent Defective by Gear Class

Class	Allowed Tolerance Inch	(μ m)	Percent Defective
7	0.0027	(68.6)	2.3
8	0.0019	(48.3)	10.5
9	0.0014	(35.6)	33.6
10	0.0010	(25.4)	67.4

The gage study data was analyzed using analysis of variance techniques to test for differences between operators, setups, and runs. The analysis showed no significant difference between operators for either the high or low pitch diameters. There were significant differences between setups within operators and between runs within setups within operators for both the high and low pitch diameters. Appendix E gives data on the study.

Table E-2 illustrates the average for the high and low pitch diameters and the average bias between setups within an operator. The maximum operator/setup bias was 0.00100 and 0.00078 inch (25.4 and 19.8 μm) for the high and low readings respectively. The operator/setup effects represent approximately 90 percent of the total variation.

Figures E-3 and E-4 illustrate the contribution of runs within setups within operators. Even though this treatment is significant, it represents less than 4 percent of the total gaging variation.

There was a relatively large bias between the operator setups, indicating a need for care in the setup and the technique used to locate the part on the gage. The setup and operator contributions result in approximately 90 percent of the total variation. The gage repeatability (± 2 standard deviations) is estimated to be ± 0.00016 and ± 0.00018 inch (± 4.06 and ± 4.57 μm) for the high and low pitch diameters respectively, and ± 0.00028 inch (± 7.11 μm) for the TCE measurements.

The 20 special parts used to estimate tool relief were sectioned and the depth of penetration of the cutter was measured on a toolmaker's microscope. The average cutting depth was 0.12250 inch (3.1115 mm) with a standard deviation of 0.00075 inch (19.05 μm). Using this standard deviation, the minimum tool relief necessary to contain 95 percent of the readings 95 percent of the time was 0.0065 inch (0.165 mm).

Clearance Grooves for Blind Internal Gears

To cut blind internal gear teeth it is necessary to provide a clearance groove for the cutter to pass into at the end of the stroke (Figure 24). The groove must be sufficiently wide to allow for some excess cutter stroke and chip clearance on coarse pitch gears.

The width of the groove will depend upon the face width of the gear being cut and the type of gear shaping machine used.⁴ The stroking mechanism on a gear shaper operates through an eccentric crankshaft in which the amount of eccentric offset controls the stroke length. On coarse pitch shaping machines, such as the Fellows No. 712, the long length of the crank arm causes a certain amount of uncontrollable overshoot at the end of the stroke. The

Figure 24. Clearance Groove Required for Cutting Blind Internal Teeth

overshoot and chip clearance allowance create certain minimum groove widths for coarse pitch banked gears. These minimum requirements are shown in Table 4.

For fine pitch gears such as the 120 DP study gear, chip clearance is not a problem since the chips are small and will disperse throughout the bottom of the groove. In addition, the crank arm on the Fellows No. 3 Gear Shaper is short and overshoot is not a significant factor. Fellows recommends a maximum of a 0.0937-inch-wide (2.381 mm) groove for a fine pitch gear with a 0.75-inch-wide (19.050 mm) gear face (maximum stroke length on the

Table 4. Minimum Width of Clearance Groove and Excess Travel of Cutter Slide⁵

Diametral Pitch of Gear to Cut	Width of Groove w for Spur Cutter	
	Inch	(mm)
4	9/32	(7.14)
5	17/64	(6.75)
6	1/4	(6.35)
7	1/4	(6.35)
8	15/64	(5.95)
10	7/32	(5.55)
12	7/32	(5.55)
14	13/64	(5.16)
18	13/64	(5.16)
24	3/16	(4.76)

No. 3 Shaper is 1 inch [25.4 mm]). The study gear had a 0.312-inch-wide (0.794 mm) face and Fellows recommended⁴ a 0.469-inch (1.260 mm) clearance groove. The study indicated exceptionally good repeatability on the stroking mechanism and that a relief as small as 0.0065 inch (0.165 mm) would have been sufficient on the study gear.

Results

Analysis of the inspection data indicates that a minimum pitch diameter tolerance of 0.00327 inch (83.06 μm) would be required. The values obtained on the high and low pitch diameters are probably not representative of the true averages of the shaping process because of the number of times the parts were deburred, cleaned, and gaged. The variation in these diameters, however, was used to estimate the repeatability of the shaping process. The minimum tolerance required for the total composite error is 0.00239 inch (60.71 μm). The intent was to make a Class 10 gear, but it is estimated that 67.4 percent of the gears would be defective because of the TCE requirement for a Class 10 gear.

The material selected for the study gear (FM brass) presented problems in burr removal and tooth wear from the running contact with the master gear. The length of the locating inside diameter (ID) also created problems in checking the gear on the Redliner. Because of the short length of engagement, the parts would cock on the checking mandrel. Before repeatable data could be obtained from the Redliner, two gears had to be bonded together to increase the engagement length of the hole. During gaging, dirt and foreign material in the gear teeth influenced the readings on the Redliner because of the light gaging pressure used (4 oz. [1.1 n]). For this reason the gears had to be thoroughly cleaned and checked for cleanliness several times before gaging.

ACCOMPLISHMENTS

When this project was begun, equipment and experience in grinding 120-pitch gears with 0.100-inch (2.54 mm) pitch diameters were not available. A repeatable process was developed for grinding the tooth form and maintaining a 16 μ in. AA (0.41 μ m) surface finish with minimum burrs. An experimental machine was used in this process development; production equipment is not available in U.S. industry for this process but could be developed.

In initial investigations of the gear shaping technique for making ratchet teeth, the trial-and-error layout cutter design method was found to be too inaccurate for Bendix purposes. Therefore, a mathematical model and computer program were created that will accurately predict whether a desired ratchet tooth geometry can be produced and will also design the cutting tool.

The intent of a study on shaping internal gear teeth was to cut an internal gear that would meet an AGMA Class 10a requirement. A secondary objective was to determine the minimum permissible gear tooth relief. The study showed that 67.4 percent of the gears produced using available equipment and techniques could be expected to fall short of the Class 10a requirement. The minimum tool relief required to obtain 95 percent in-tolerance readings 95 percent of the time was found to be 0.0065 inch (165 μ m).

REFERENCES

¹*Tool Engineers Handbook*, 2nd Edition, American Society of Tool and Manufacturing Engineers, McGraw-Hill, 1959, pp 44-87.

²George W. Michalec, *Precision Gearing, Theory and Practice*. John Wiley and Sons, 1966, p 481.

³*The Internal Gear*, The Fellows Gear Shaper Co., 5th Edition, 1967, p 12.

⁴*Ibid.*, p 20.

⁵*7 and 7a Type High Speed Gear Shapers*, The Fellows Gear Shaper Co., 10th Edition, 1964, p 66.

BIBLIOGRAPHY

- Davis, W. O., *Gears for Small Mechanisms*. 2nd Edition. London: N.A.G. Press, Ltd., 1970.
- Dudley, Darle W., *Practical Gear Design*. 1st Edition, McGraw-Hill Book Company, 1954.
- Metal Cutting Tool Handbook*, The Metal Cutting Tool Institute, 1965.
- Michalec, George W., *Precision Gearing, Theory and Practice*. John Wiley and Sons, 1966.
- Read, L. C., "The Gear Shaping Process - Some Special Applications." *Machinery and Production Engineering*, December 1, 1965, pp 1208-1211.
- Scoles, C. A. and Kirk, R., *Gear Metrology*. London: MacDonald Technical and Scientific, 1969.
- The Art of Generating with a Reciprocating Tool*, 5th Edition, The Fellows Gear Shaper Company, 1963.
- The Internal Gear, Design and Application*, 5th Edition, The Fellows Gear Shaper Company, 1967.
- The Involute Curve and Involute Gearing*, 5th Edition, The Fellows Gear Shaper Company, 1964.
- Tool Engineers Handbook*, 2nd Edition, American Society of Tool and Manufacturing Engineers, McGraw-Hill, 1959.
- 7 and 7a Type High Speed Gear Shapers*, The Fellows Gear Shaper Co., 10th Edition, 1964.

Appendix A

PINION GEAR BLANK

Figure A-1. Pinion Gear Blank

Figure A-2. Graphic Gear, Pinion

Appendix B

WHEEL TRUING MECHANISM.

Appendix B

WHEEL TRUING MECHANISM

WHEEL TRUING

A rack form is threaded into the grinding wheel prior to the grinding operation. Since the Fellows No. 4 grinding machine has a separate self-contained truing mechanism, the wheel has to be removed from the grinding machine and mounted on the wheel truing spindle. The diamond dressing tool shown in Figure B-1 has the full form of the rack on it.

The diamond tool is placed in the left-hand holder as shown in Figure B-2. The angle α (which sets the angle of the diamond in the proper attitude to the grinding wheel) is established by setting a spacing block between the dresser and the stop shown. The 0.9481 inch (24.08 mm) value for M is derived by using the formula

$$M = 3.937 \sin (40^\circ - \text{pressure angle}) - 0.3937.$$

The following set of change gears establishes the proper lead angle on the wheel. The lead angle is equal to the circular pitch of the gear to be ground

$$\left(\text{or } \frac{\pi}{120} = 0.0261 \text{ inch [0.663 mm] per revolution of the wheel}\right).$$

The travel of the truing slide is set to overtravel the grinding wheel by about 0.25 inch (6.35 mm) on each end.

The whole depth of the tooth form plus clearance is calculated by the following formula:

$$\frac{3.558}{DP} - 1.374 \times \text{flat on diamond}.$$

The truing mechanism (Figure B-3) is turned on, which starts the grinding wheel rotation at the proper speed and the traverse of the truing slide. While the truing slide is traveling from right to left on its dressing stroke, the hand wheel is fed in until it touches the grinding wheel (Figure B-4). This is the starting point for the threads on the grinding wheel and the dial setting on the micrometer drum is noted. The hand wheel is fed in 0.0005 inch (13 μm) during the return stroke of the truing slide until the 0.0255-inch (0.648 mm) full depth is obtained.

The grinding wheel is then removed from the truing mechanism and placed on the wheel head spindle of the machine.

Figure B-1. Full Form Diamond Dressing Tool

Figure B-2. Wheel Truing Attachment

Figure B-3. Wheel Truing Device

Figure B-4. Diamond Dresser and Grinding Wheel

Appendix C

COMPOSITE CHARTS FROM FELLOWS NO. 4
REDLINER GEAR CHECKING MACHINE AND
INVOLUTE PROFILE CHARTS FROM FELLOWS 12-M
INVOLUTE MACHINE

Figure C-1. Master Gear and Staging Fixture for Redliner Gear Checker

Figure C-2. Composite Readings Obtained at BKC on Fellows No. 4 Redliner Gear Checker

Figure C-3. Typical Involute Profile Recorded on Fellows 12-M Involute Machine

Appendix D

MACHINING AND GAGING REQUIREMENTS FOR INTERNAL GEARS

Appendix D

MACHINING AND GAGING REQUIREMENTS FOR INTERNAL GEARS

DIMENSIONAL REQUIREMENTS

The study gear has 80 teeth and the master gear has 60 teeth. Known data for study gear is as follows:

- Basic configuration = 20° involute internal spur gear, diametral pitch 120, 80 teeth;
- Circular pitch = 0.02618 inch (0.665 mm);
- Standard circular thickness = 0.01309 inch (0.332 mm);
- Standard addendum = 0.0083 inch (0.211 mm);
- Working depth = 0.0167 inch (0.424 mm);
- Standard Dedendum = 0.0120 inch (0.305 mm);
- Whole depth = 0.0203 inch (0.516 mm); and
- Pitch diameter = 0.6667 inch (16.934 mm).

The pitch diameter can be determined directly from the center distance and the numbers of teeth by proportionality.

$$\text{Pitch diameter} = \frac{\text{Number of internal teeth}}{\text{Diametral pitch}}$$

$$\text{PD} = \frac{\text{Number of teeth (circular pitch)}}{\pi}$$

$$\text{PD} = \frac{80}{120} = \frac{80 (0.02618)}{3.1416} = 0.6667 \text{ inch (16.934 mm)}$$

An internal gear may be proportioned like a standard spur gear turned "outside in" or with addendum and dedendum in reverse positions (Figure D-1); however, to avoid interference or improve the tooth form and action, the internal diameter of the gear should be increased and the outside diameter of the mating pinion made larger than the size based upon standard or conventional tooth proportions.

Figure D-1. Internal Gear Characteristics

Internal Diameter (based upon spur gear reversed):

$$ID = \frac{\text{Number of Teeth} - 2}{\text{Diametral Pitch}} = \frac{80 - 2}{120} = 0.6500 \text{ inch (16.51 mm)}$$

Internal diameter enlarged to avoid interference:

- For internal gears to mesh with pinions having 16 teeth or more, subtract 1.2 from the number of teeth and divide the remainder by the diametral pitch--

$$ID = \frac{\text{Number of Teeth} - 1.2}{\text{Diametral Pitch}} = \frac{80 - 1.2}{120}$$

$$= 0.6567 \text{ inch (16.68 mm);}$$

- If circular pitch is used

$$ID = \frac{(\text{Number of Teeth} - 1.2) \times \text{Circular Pitch}}{\pi}$$

$$= \frac{80 - 1.2 (0.02618)}{3.1416} = 0.6567 \text{ inch (16.68 mm).}$$

Major Diameter (MD) = ID + 2(whole depth):

MD = ID + 2(whole depth), or

MD = 0.6500 + 2(0.0203) = 0.6906 inch (17.541 mm).

Clearance Diameter (CD) = ID + 2(working depth):

CD = 0.6500 + 2(0.0167) = 0.6834 inch (17.358 mm).

Gear Tolerances (AGMA):

- TCT (total composite tolerance) = 0.0010 inch (25.4 μ m);
- TTE (tooth-to-tooth tolerance) = 0.0005 inch (12.7 μ m);
- $\text{Cot } \phi = \text{Cot (pressure angle)} = \text{Cot } 20^\circ = 2.74748$ inch (69.786 mm);
- BT (backlash tolerance) = 0.00075 inch (19.05 μ m);
- Maximum Indicator Reading = 0; and
- Minimum Indicator Reading (IR) =
$$\left[\frac{-BT}{2} (\text{Cot } \phi) + TCT \right]$$
$$= \left[\frac{-0.00075}{2} (2.74748) + 0.001 \right]$$
$$= -0.00203 \text{ (-51.562 } \mu\text{m)}.$$

(For internal gears a minimum indicator reading corresponds to a larger PD; therefore, the tolerance on the PD is 0.0 to +0.00203 inch [51.562 μ m]).

REDLINER SETUP

Four ounces of checking pressure is recommended.

The following information can be used to calculate the center distance.

For standard gears the tooth thickness t of mating gears is equal where

$$t = \frac{P}{2} = \frac{\pi}{2P_d},$$

$$t = \frac{\text{Circular pitch}}{2}, \text{ or}$$

$$t = \frac{\pi}{2 (\text{diametral pitch})}$$

measured linearly along the arc of the pitch circle. The pitch (circle) diameter equals

$$PD = \frac{N}{P_d} = \frac{NP}{\pi},$$

$$PD = \frac{\text{Number of teeth}}{\text{Diametral pitch}}, \text{ or}$$

$$PD = \frac{\text{Number of teeth (circular pitch)}}{\pi}.$$

The circular pitch = $2t = 2(0.0148)$ per data supplied by the manufacturer of the master gear. The PD of the master gear is

$$PD = \frac{\text{Number of teeth (2) (0.0148)}}{\pi} = \frac{60 (2) (0.0148)}{3.1416}$$

$$= 0.506503 \text{ inch (12.865 mm)}.$$

The PD of the study gear = 0.6667 inch (16.934 mm). The center distance (CD) is

$$CD = \frac{PD \text{ study gear} - PD \text{ master}}{2}$$

$$= \frac{0.6667 - 0.5065}{2} = 0.0801 \text{ inch (2.034 mm)}.$$

The following information can be used to calculate the gage block set distance. The Redliner arbor diameter = 0.4998 inch (12.695 mm), and the study gear arbor = 0.49975 inch (12.694 mm). Thus the set distance (SD) is

$$SD = CD + \frac{0.4998 - 0.49975}{2}$$

$$= 0.0801 + 0.000025$$

$$= 0.080125 \text{ inch (2.035 mm)}.$$

The Redliner arbor is set 0.0801 inch (2.034 mm) higher than the study gear arbor. Thus, the SD may also be gaged from the top of the Redliner arbor to the bottom of the study gear arbor:

$$\begin{aligned} \text{SD} &= \frac{\text{Arbor}_m + \text{Arbor}_g}{2} + 0.080125 \\ &= \frac{0.4998 - 0.49975}{2} + 0.080125 = 0.5799 \text{ inch (14.729 mm)}. \end{aligned}$$

In chart analysis, it should be remembered that four revolutions of the master gear equal three revolutions of the study gear.

NO. T.	80
I.D.	0.650
T.	0.0122
D+F	0.0203
H.	AT P.D.
DP	120
PA	20°
No. T.	52
PITCH DIA.	0.4333
BASE DIA.	0.4069
(NOMINAL)	
OUTSIDE DIA.	0.4573
SCA	1.50°
OD ANGLE	3°8'
T. (CHORD)	0.0102
H. (CHORD)	0.0071
BRUSH	0.001/0.003
(BEFORE COR.)	
MIN. ANG. INV.	16.64°
MIN. GRD.	
DEPTH	0.022
INV. TOLERANCE	0.00015
MAX. RUNOUT	
(CONE)	0.0004
CP SPACING	
MAX.	0.0002
CP SPACING	
T. TO T.	0.0001
7/16" TAPER SHANK	
PRECISION-FINISHING	

1 INCH = 25.4 mm

Figure D-2. Shaper Cutter

SIZE OD TO FINAL DIA. OVER PINS WITHIN 0.001
FINAL OD = DOP - Y
* ETCH DIAM. ARC T (AT PD) CORRESPONDING TO FINAL DOP
1 INCH = 25.4 mm

Figure D-3. Master Gear for Internal Gear Cutting

Appendix E

REPEATABILITY DATA FOR SHAPING INTERNAL GEARS

Table E-1. Handling Sequence.

1. Parts shaped (36 parts).
2. Parts gaged--charts indicated deburring and cleaning was necessary.
3. Hand deburr.
4. Ultrasonic clean.
5. Parts gaged--charts indicated more deburring and cleaning was necessary.
6. Hand deburr.
7. Ultrasonic clean.
8. Parts gaged--problem found in the technique used to hold the parts for gaging.
9. A second part was bonded to the part to be gaged to reduce the holding problem.
10. Ultrasonic clean.
11. Final gaging.

Figure E-1. Pitch Diameter Variations

Figure E-2. Total Composite Error Variations

Figure E-3. High and Low Pitch Diameters, Setup Contributions

Figure E-4. High and Low Pitch Diameters, Run Contributions

Figure E-5. Total Composite Error Readings, Setup Contributions

Figure E-6. Total Composite Error Readings, Setup Contributions

Table E-2. Operator Setup Averages and Bias for Gage Study

		Pitch Diameter, Inch (mm)				Total Composite Error, Inch (μm)	
		High		Low			
Operator	Setup	Average	Setup Bias	Average	Setup Bias	Average	Setup Bias
01	S1	0.66731 (16.950)	0.00078 (0.0198)	0.66596 (16.915)	0.00074 (0.0188)	0.00136 (34.54)	0.00003 (0.762)
	S2	0.66809 (16.969)		0.66670 (16.934)		0.00139 (35.31)	
02	S1	0.66831 (16.975)	0.00009 (0.0023)	0.66674 (16.935)	0.00006 (0.0015)	0.00157 (39.88)	0.00003 (0.762)
	S2	0.66822 (16.973)		0.66668 (16.934)		0.00154 (39.12)	
Maximum Bias (01S1 - 02S1)		0.00100 (0.0254)		0.00078 (0.0198)		0.00021 (5.334)	

Table E-3. Standard Deviations for Gage Study

Operator	Setup	Pitch Diameter Inch (μm)		TCE Inch (μm)
		High	Low	
01	S1	0.00009 (2.286)	0.00011 (2.794)	0.00017 (4.318)
	S2	0.00008 (2.032)	0.00011 (2.794)	0.00014 (3.556)
02	S1	0.00015 (3.810)	0.00011 (2.794)	0.00010 (2.540)
	S2	0.00013 (3.302)	0.00011 (2.794)	0.00005 (1.270)
Gage Standard Deviation		0.00008 (2.032)	0.00009 (2.286)	0.00014 (3.556)
Gage Repeatability (± 2 Standard Deviations)		± 0.00016 (± 4.064)	± 0.00018 (± 4.572)	± 0.00028 (± 7.112)

DISTRIBUTION

	Copy
R. Bulcock, ERDA-KCAO	1
V. C. Vespe, ERDA-ALO	2
J. A. Freed, LASL	3
S. J. Buginas, LLL	4
H. M. Brinkmeier, Monsanto	5
J. P. Ford, SLA	6
L. K. Gillespie, SLA	7
R. S. Pinkham, SLA	8
A. L. Thornton, SLA	9
A. G. Erny, D/261, FU34	10
E. L. Young, Jr., D/261, FU34	11
J. D. Corey, D/554, BD50	12-13
L. Stratton, D/554, 2C44	14-16
R. F. Pippert, D/700, 1A42	17
R. P. Frohmberg, D/800, 2A39	18
J. A. Morrison, D/800, 2A40	19
W. G. Cooper, D/821, 2A36	20
J. L. Couchman, D/821, 2A36	21
J. P. Dycus, D/822, 2A36	22
L. K. Gillespie, D/822, 2A36	23
G. E. Klement, D/822, 2A36	24
D. D. Oswald, D/822, 2A36	25
C. P. Rome, D/822, 2A36	26
D. R. Wachter, D/822, 2A36	27
D. P. Roberts, D/823, 1A27	28
R. E. Kessler, D/865, 2C40	29