Lawrence Livermore Laboratory

DT FUSION NEUTRON IRRADIATION OF LLL Nb_3Sn AND LLL SUPERCONDUCTOR WIRES AT 4.2°K

S. C. MacLean

May 17, 1977

This is an informal report intended primarily for internal or limited external distribution. The opinions and conclusions stated are those of the author and may or may not be those of the laboratory.

Prepared for U.S. Energy Research & Development Administration under contract No. W-7405-Eng-48.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

ABSTRACT

The DT fusion neutron irradiation of one LLL superconductor wire and one LLL Nb₃Sn foil at 4.2°K is described. The sample position, beam — on time, and neutron dose record are given. The results from two "profile" dosimetry foils measuring the lateral variation in neutron flux are included.

NOTICE
This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Energy Research and Development Administration, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

DT FUSION NEUTRON IRRADIATION OF LLL Nb₃Sn AND LLL
SUPERCONDUCTOR WIRE AT 4.2°K

The Rotating Target Neutron Source (RTNS) irradiation during the week of September 13-17, 1976 was scheduled for Dr. Ronald M. Scanlon of LLL. During the irradiation his samples were held at liquid helium temperature. The samples were one superconductor wire and one piece of Nb₃Sn foil.

Two niobium dosimetry wires of approximately 10 mm in length and 0.25 mm in diameter were parallel to the sample wire. The dosimetry wire closer to the superconductor sample was designated Nb-RS-4 and the second dosimetry wire, farther from the sample, was Nb-RS-5.

A niobium dosimetry foil, 0.14 mm thick and 24 mm square, was scribed into 36 squares, 4 × 4 mm each, labeled and taped to the front of the Helitran containing R. Scanlon's samples. The niobium "profile" foil was included in order to measure the lateral variation in the neutron flux. Each square on the foil was labeled with a two digit figure. The first number indicated the horizontal row, top to bottom 1 to 6. The second number designated the vertical rows, left to right, 1 to 6.

The line between the fourth and fifth horizontal rows on the niobium profile foil was over the position of the superconductor wire sample inside the Helitran. Autoradiographs of a copper foil (with a 6 mm diameter hole in it) following a few minutes of irradiation were used to align the sample position with the neutron beam.

The irradiation was carried out by the E Division Accelerator Staff. Neutron production was monitored continuously with a proton recoil counter and recorded each hour. The irradiation was interrupted the third day so that the experimental apparatus could be moved back from the target and measurements could be taken. Before repositioning the Helitran and continuing the irradiation a new niobium profile foil replaced the first one. The foil was labeled in the same manner except that the vertical rows were designated A to F, left to right. Total beam-on time was 69.52 hours. The dose record is attached.

The center of the neutron beam had been within 1 mm of the sample wire on the first portion of the irradiation. However, an autoradiograph of the second profile foil showed the beam spot to have been considerably off center.

The niobium profile foils were cut along the scribed lines and each of the sections weighed. These along with the niobium dosimetry wires were delivered to Ruth Anderson in the LLL Radiochemistry Division. She carried out the gamma ray counting.

The average fluence of each dosimeter was calculated using the method described in UCRL-51393, Rev. 1. However, the cross section used for the activation of the 10.16 day isomer of niobium by 14.8 MeV neutrons was changed to 458 millibarns. The fluences of the first profile foil sections are given in Figures II and III and the fluences of the second profile foil pieces are shown in Figures IV and V.

During the first portion of the irradiation, the sample wire and dosimetry wires were parallel with the horizontal lines on the profile foil. However, during the second part of the irradiation the profile foil was rotated 30° in relationship to the sample. This correction of the dose record was taken into account when calculating the fluence on the dosimetry wires.

<u>Dosimetry Wire</u>	<u>Fluence (neutrons/cm²)</u>
Nb-RS-4	4.24×10^{16}
Nb-RS-5	5.04×10^{16}

The estimated overall uncertainty of these results is ±20%. The relative uncertainty between any two values is about ±5%. The values given here represent average fluences over the volume of each dosimetry wire or foil.

RTNS IRRADIATION OF SEPTEMBER 13 AND 17, 1976

07 DEC 76

09:53:35

11 1.00×10^{16}	12 1.35×10^{16}	13 1.53×10^{16}	14 1.40×10^{16}	15 1.13×10^{16}	16 8.44×10^{15}
21 1.51×10^{16}	22 2.43×10^{16}	23 3.04×10^{16}	24 2.71×10^{16}	25 1.87×10^{16}	26 1.25×10^{16}
31 2.12×10^{16}	32 3.98×10^{16}	33 5.48×10^{16}	34 4.77×10^{16}	35 2.94×10^{16}	36 1.73×10^{16}
41 2.23×10^{16}	42 4.47×10^{16}	43 7.04×10^{16}	44 7.01×10^{16}	45 4.31×10^{16}	46 2.24×10^{16}
51 1.88×10^{16}	52 3.68×10^{16}	53 6.33×10^{16}	54 7.36×10^{16}	55 4.88×10^{16}	56 2.37×10^{16}
61 1.38×10^{16}	62 2.45×10^{16}	63 4.05×10^{16}	64 5.03×10^{16}	65 3.59×10^{16}	66 1.94×10^{16}

Figure II. Fluence Results for First Niobium Profile Foil (neutrons/cm²).

Figure III NIOBIUM PROFILE FOIL I - SEPTEMBER 13-14, 1976

1A	1B	1C	1D	1E	1F
1.10×10^{16}	2.02×10^{16}	4.35×10^{16}	7.94×10^{16}	8.01×10^{16}	4.47×10^{16}
2A	2B	2C	2D	2E	2F
1.18×10^{16}	2.27×10^{16}	4.97×10^{16}	1.00×10^{17}	1.14×10^{17}	6.53×10^{16}
3A	3B	3C	3D	3E	3F
1.08×10^{16}	1.89×10^{16}	3.94×10^{16}	7.97×10^{16}	1.08×10^{17}	7.09×10^{16}
4A	4B	4C	4D	4E	4F
9.02×10^{15}	1.45×10^{16}	2.62×10^{16}	4.98×10^{16}	6.83×10^{16}	5.10×10^{16}
5A	5B	5C	5D	5E	5F
6.97×10^{15}	1.02×10^{16}	1.60×10^{16}	2.34×10^{16}	2.86×10^{16}	2.55×10^{16}
6A	6B	6C	6D	6E	6F
5.43×10^{15}	7.17×10^{15}	1.02×10^{16}	1.28×10^{16}	1.39×10^{16}	1.26×10^{16}

Figure IV. Fluence Results for Second Niobium Profile Foil (neutron/cm²).

2: I

NIOBIUM PROFILE FOIL II - September 15-17, 76

NOTICE

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Energy Research & Development Administration, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately-owned rights.

NOTICE

Reference to a company or product name does not imply approval or recommendation of the product by the University of California or the U.S. Energy Research & Development Administration to the exclusion of others that may be suitable.

Technical Information Department

LAWRENCE LIVERMORE LABORATORY

University of California | Livermore, California | 94550