Rep...

Report
Grant DOE/PC/89771--10
TENTH DE92 018437
January

1577

MECHANISM OF HYDRODENITROGENATION (Part 10)

ADSORPTION OF PIPERIDINE ON REDUCED MOLYBDENUM CATALYSTS

Raul Miranda
Department of Chemical Engineering
University of Louisville
Louisville, KY 40292, USA

contents

Abstract	2
Introduction	2
Experimental	4
Results and Discussion	5
Conclusions	8
Acknowledgements	8
References	9
Figures	10

MASTER

DISCLAIMER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

JUN 10 1992

Report DOE/PC/89771-10

ABSTRACT

Diffuse reflectance ir spectroscopy of adsorbed piperidine was done to study the interaction of highly basic cyclic amines with OH on various surfaces. The silanol groups on pure silica do not interact strongly with piperidine, as shown by their inability to promote the exchange of deuterium from OD with hydrogen from piperidine. After supporting molybdena on such silica, however, the silanol groups associated with interfacial sites become more acidic and are able to exchange D with piperidine, which is also adsorbed more strongly. The OH groups on pure alumina do not interact with adsorbed piperidine because of their high basicity. Upon supporting molybdena, however, new acidity and probably new OH groups are generated that interact and exchange D with piperidine.

INTRODUCTION

Efficient nitrogen removal from heterocyclic aromatics in liquid fuels calls for the development of catalysts with better HDN activity than is available with the traditional HDS catalysts, such as CoMo/ γ -Al₂O₃ and NiMo/ γ -Al₂O₃. Over these catalysts, the first step is the partial or total hydrogenation of the heterocyclic ring -- at equilibrium at normal operating conditions -- and the rate-limiting step is the scission of the C-N-C bonds. Therefore an increase in the rate of C-N-C scission should produce an overall increase in the HDN yield.

In this project it is proposed that the selectivity of the HDN reaction can be affected by an alteration of the catalyst acidity since it is possible that an acidic Hofmann-like deamination pathway is operative [1] in parallel with the hydrogenolysis of saturated C-N-C bonds. Such was the conclusion from the study done of the denitrogenation of piperidine [3], where it was demonstrated that Bronsted acid sites are active for the denitrogenation of N-heterocycles, whereas Lewis sites are not.

To understand better the role of acidic sites in the presence of hydrogenation and hydrogenolysis sites, molybdena was supported on a series of acidic aluminas, and the resulting new acidity and molybdenic phases were characterized [4]. The oxidized catalysts supported on silica-aluminas showed increases from 3 to 150% of weak, medium and strong acid sites, which were produced by the molybdena phases.

Recently [9-10] we utilized DRIFT of deuterium-exchanged catalysts to follow the depletion of OH on the support and the simultaneous regeneration of OH due to molybdena addition. It was found that silica hydroxyls react partially with deposited molybdena. The new species formed do not lead to regeneration of hydroxyls on the catalyst. On the other hand, the interaction of molybdena with alumina or silica-alumina leads to the generation of interfacial OH groups, that compensate for the hydroxyls lost to reaction.

The HDN reaction of pyridine was utilized to assess the variation in activity and selectivity produced by the nature of the support [7]. The results revealed that for silica-alumina supports (>50 wt% silica) the optimum loading of molybdena is 4 wt%. At this loading, the selectivity for denitrogenation was maximum, in coincidence with a substantial portion of the support (containing acidic sites) being exposed. The possible role of Lewis acid sites produced on the molybdena surface by coordinative unsaturation is the strong adsorption of aromatic and saturated cyclic amines, while the weak-strong acidic Bronsted sites, present on the support as well as on the molybdena, interact with those amines. It is not clear at this point the nature of such interaction. In principle, H^+ would add to NH to form a stable quaternary N^+ ion, as is known to occur in solution chemistry.

To answer the question of the nature of the interaction between adsorbed cyclic amines and supported reduced molybdena phases, we used the deuterium-exchange technique we have utilized in previous quarters [9-10]. Exchange of surface OH with deuterium produces an isotopic shift in the IR spectra of the OH region, placing the new bands in a more sensitive IR region. Adsorption of piperidine on the exchanged catalysts leads to a perturbation of the spectra in a manner that is characteristic of the interaction of cyclic saturated amine with surface OH.

EXPERIMENTAL

Synthesis of Supports and Supported Molybdena

Pure silica and gamma-alumina were synthesized as described before [2]. The supports were characterized by BET surface area, ammonia chemisorption and TPD, and IR of adsorbed pyridine.

Supported molybdena (8 wt%) was prepared by incipient impregnation method from ammonium heptamolybdate, and was dried and calcined according to the technique described previously [4]. The oxidic catalysts were prereduced in 50 ml/min H_2 at 400°C for 4 hours in a fixed-bed microreactor. Subsequently the powder was lightly compressed into a 13 mm pellet and rereduced in situ in the DRIFT cell, by flowing H_2 at 400°C for 1 hour.

Deuterium Exchange

The exchange was effected with D_2 inside the DRIFTS cell equipped with environmental chamber and described before [5]. A catalyst pellet was made with 100 mg of powder compressed at about 200-500 psig for about 5 min. No additive was used in these pellets. The pellet was rereduced as described above. Finally, the sample was evacuated at 400°C during 1 hour (10^{-5} Torr) to remove gas phase hydrogen.

For the exchange using D_2 , 2 atm of gas was kept in the cell maintained at 400°C during 1 hour. The temperature was reduced to 150°C under pressure, followed by evacuation at 150°C during 1 hour. DRIFT spectra were recorded under H_2 and D_2 atmospheres and under vacuum at 150 and 400°C.

Piperidine Adsorption and Desorption

Piperidine was purified by distillation and was kept dry on a bed of molecular sieves and KOH. A 0.5 microl pulse of piperidine was injected over the catalyst held under vacuum at 150°C. Infrared peaks of the adsorbed species appeared immediately. After 30-60 min under vacuum at 150°C the spectrum was recorded. Then the temperature was raised quickly to 400°C, and kept for 1 h before recording another spectrum. In some experiments (see figures) H_2 was then flown over the catalyst at 400°C.

RESULTS AND DISCUSSION

Fig. 1 shows the result of piperidine adsorption and desorption on pure silica support. The bands observed were previously assigned [9] following Baumgarten et al. [11]: the band at 3744 cm^{-1} belongs to the terminal isolated silanol groups Si-OH and the broad band between 3700 and 3300 cm^{-1} belongs to the H-bonded silanols on the silica surface. After exchange, new bands at 2757 cm^{-1} and $2720\text{-}2400\text{ cm}^{-1}$ appear, and they correspond to the isolated and deuterium-bonded OD groups, respectively (Fig. 2).

The silanol groups remain unperturbed during H_2 treatment at 400°C , 150°C and under vacuum at 150°C , as seen in Fig. 1. Upon injection, and after removal of gas phase piperidine, new bands corresponding to adsorbed species appear. The observed bands are in agreement with previous experiments of Hirokawa et al. [12], who made most of the assignments given in Table 1.

Table 1
Adsorbed Piperidine

W-number (cm^{-1})	Assignment	Ref.
2430 (w)	N-D str.	12
2760 (w) *	OH-piperidine	13
2864 (m)	CH_2 asym. str.	12
2944 (s)	CH_2 sym. str.	12
3290 (w)	N-H str.	12

Our spectra (Fig. 1) show the presence of the 3290 , 2944 , 2864 and 2760 cm^{-1} bands. The 2760 cm^{-1} band is really originating from the 3740 cm^{-1} band after a frequency shift of 980 cm^{-1} that occurs upon interaction of piperidine with OH on silica, according to Pukshtis et al. [13]. Observe that the intensity of the 3744 cm^{-1} band suffered a reduction after adsorption of piperidine, as a result of the interaction of OH with the amine. Also observe that a temperature increase to 400°C produces the complete desorption of piperidine and the regain of intensity of the 3744 cm^{-1} band. A feasible conclusion at this point is that the interaction of the adsorbed piperidine with silanols on silica is weak, as expected from the basicity of such silanols.

Fig. 2 includes the exchange of some of the isolated silanols with deuterium, and the adsorption of piperidine on the deuterated surface. It must be observed that deuterium exchange occurs mainly with the isolated silanols and not the H-bonded ones, and that piperidine interacts mainly with the exchangeable groups, and not with the unexchanged ones. This latter observation is derived from the relatively large reduction in intensity suffered by the 2757 cm^{-1} band, in comparison to the 3744 cm^{-1} band. After desorption of piperidine at 400°C , both OH and OD isolated groups are restored. Thus, the extent of exchange of D with piperidine seems to be limited by the weak interaction with the support.

Similar experiments were performed with supported molybdena. Figs. 3-4 shows the 8 wt% molybdena results. As pointed out earlier [10] molybdena loading on silica causes the loss of isolated OH groups from the support, without regeneration of new OH groups related to the molybdena phases, as seen by comparing Figs. 1 and 3. The remaining silanol band (3744 cm^{-1}) is reduced further upon adsorption of piperidine (fourth spectrum in Fig. 3 and fifth in Fig. 4).

On supported molybdena catalyst, and in contrast to pure silica support, increase of temperature to 400°C is not enough to provoke the complete desorption of piperidine and the restoration of the 3744 cm^{-1} band. After flowing H_2 at 150°C most or all of the 3744 cm^{-1} band is restored, although some piperidine still remains adsorbed. Only after flowing H_2 at 400°C is the complete desorption possible. The immediate conclusions from this experiment are that piperidine now interacts with both OH groups from the support and with the molybdena phases. The molybdena interaction is probably through coordinated unsaturated sites (cus) since no new OH are formed on molybdena. Both adsorbed species (OH..piperidine) and (cus..piperidine) are stronger than the original OH..piperidine interaction on pure silica support.

An observation that is more clearly seen with the deuterated surface (Fig. 4) is that desorption of piperidine under vacuum, with no H_2 flowing, is accompanied by the lack of substantial regeneration of OD (last spectrum, Fig. 4). It does appear that the piperidine that remains adsorbed (i.e. the strongly adsorbed piperidine) is interacting with both OD and cus, i.e. forming a OD..piperidine..cus species, which can only be desorbed by hydrogenolysis at 400°C . Another explanation to the lack of OD 2757 cm^{-1} restoration after partial desorption of piperidine is that molybdena induces enough lability (acidity) on the D of OD that D is able to exchange with piperidine H and leave the surface together with piperidine. This point will be clarified a posteriori with mass spectrometry of the desorbed species.

Similar experiments were run with alumina support (Fig. 5), reduced molybdena on alumina (Fig. 6) and deuterated reduced molybdena on alumina (Fig. 7). The broadness of the bands observed for these materials is due to the existence of several types of surface hydroxyl groups on alumina, as shown by Knozinger and Ratnasamy [16] and others [14-15]. Isolated OH bands lie in the region of about 3700 to 3800 cm^{-1} , while the H-bonded bands lie between 3200 to 3600 cm^{-1} . Corresponding bands appear in the 2600-2800 cm^{-1} region upon deuterium exchange (Fig. 5), and typical CH_2 stretching bands in the 2800-3000 cm^{-1} after adsorption of piperidine. In contrast to the silica OH, the alumina OH seem not to interact at all with the adsorbed piperidine. Adsorption, however, is strong, as shown by the amount of residual piperidine not desorbing at 400°C.

When molybdena is supported on alumina (Fig. 6), as noticed before [10], new OH are generated, probably as Al-OH-Mo, i.e. interfacial, groups. Fig. 7 shows that the extent of deuteration of the new OH groups is better than that of the bare alumina groups (Fig. 5), because of their reduced basicity (increased H lability). Likewise, the adsorption of piperidine affects now the OD bands more than before. Desorption of piperidine does not reconstitute the OD bands to their original levels, meaning that as in the case of silica-supported molybdena, D has probably exchanged or reacted with the desorbing piperidine. Also as in the case of silica-supported molybdena, the strongly chemisorbed remaining piperidine may be the one interacting with the OD groups.

CONCLUSIONS

The adsorption of piperidine on silica, alumina and supported molybdena occurs on various types of sites. It is apparent that the high basicity of OH groups on alumina prevents their interaction with the strongly basic piperidine, even though adsorption on alumina is strong. Thus the most probable sites of adsorption on alumina are the Lewis acid sites (Al cus). The lack of interaction of piperidine with OH (OD) groups leads to little exchange of surface D with piperidine H. As molybdena is supported on alumina, new, more acidic OH (OD) groups are generated which now are able to interact and exchange D with piperidine. Thus piperidine seems to be adsorbed on Mo cus, Al cus and near Al-OH-Mo interfacial sites. The aliphatic ring vibrations, however, are not affected by the difference in adsorption modes. Differences of this type have not been reported in the literature.

Silica adsorbs piperidine weakly and the basic OH (OD) groups do not interact strongly with piperidine. On the other hand, when molybdena is adsorbed on silica, the acidity of the same silanols is greatly increased, so that interaction and exchange with piperidine now occurs. Piperidine seems to be adsorbed on Mo cus, which are also responsible for the higher acidity (and H lability) of Si-OH-Mo groups.

ACKNOWLEDGEMENTS

Funding

This work was carried out with funds from DOE (Grant DE-FG22-89PC89771), partial support from NSF (Grant No. RII-8610671) and from the Commonwealth of Kentucky (EPSCoR Program).

Personnel

Jorge Marzari, PhD student

REFERENCES

1. N. Nelson and R. B. Levy, J. Catal. 58(1979)485
2. R. Miranda, "Mechanism of Hydrodenitrogenation. Part I: Preparation and Characterization of Acidic Supports", DOE Report DOE/PC/89771-1, January 1990.
3. R. Miranda, "Mechanism of Hydrodenitrogenation. Part II: Piperidine Denitrogenation over Silica-Aluminas", DOE Report DOE/PC/89771-2, April 1990.
4. R. Miranda, "Mechanism of Hydrodenitrogenation. Part III: Preparation and Characterization of Acidic Molybdena Catalysts", DOE Report DOE/PC/89771-3, July 1990.
5. R. Miranda, "Mechanism of Hydrodenitrogenation. Part IV: Infrared Spectroscopy of Acidic Molybdena Catalysts", DOE Report DOE/PC/89771-4, October 1990.
6. R. Miranda, "Mechanism of Hydrodenitrogenation. Part V: X-Ray Diffraction of Supported Molybdena Catalysts", DOE Report DOE/PC/89771-5, January 1991.
7. R. Miranda, "Mechanism of Hydrodenitrogenation. Part VI: HDN of Pyridine over Acidic Molybdena Catalysts", DOE Report DOE/PC/89771-6, April 1991.
8. R. Miranda, "Mechanism of Hydrodenitrogenation. Part VII: Low Temperature Oxygen Chemisorption of Acidic Molybdena Catalysts", DOE Report DOE/PC/89771-7, June 1991.
9. R. Miranda, "Mechanism of Hydrodenitrogenation. Part VIII: H₂-D₂ Exchange in Non-Acidic and Acidic Supports", DOE Report DOE/PC/89771-8, September 1991.
10. R. Miranda, "Mechanism of Hydrodenitrogenation. Part IX: H₂-D₂ Exchange in Reduced Mo Catalysts", DOE Report DOE/PC/89771-9, December 1991.

11. E. Baumgarten, C. Lentjes-Wagner, R. Wagner, *J. Molec. Catal.* 50, 153-65 (1989)
12. T. Hirokawa, T. Kimura, K. Ohno, H. Murata, *Spectrochimica Acta*, 36A, 329-32 (1980)
13. E.A. Paukshtis, E.N. Yurchenko, *Russ. Chemical Rev.*, 52, 242-58 (1983)
14. J.L. Carter, P.J. Lucchesi, P. Corneil, D.J.C. Yates, J.H. Sinfelt, *J. Phys. Chem.* 69, 3070-4 (1965)
15. Y. Amenomiya, *J. Catal.* 22, 109-22 (1971)
16. H. Knozinger, P. Ratnasamy, *Catal. Rev. Sci. Eng.* 17, 31 (1978)

FIGURES

- Fig. 1 Diffuse reflectance IR spectra of piperidine adsorbed on silica. See text for conditions.
- Fig. 2 Diffuse reflectance IR spectra of piperidine adsorbed on deuterium-exchanged silica. See text for conditions.
- Fig. 3 Diffuse reflectance IR spectra of piperidine adsorbed on reduced 8 wt% molybdena/silica catalyst. See text for conditions.
- Fig. 4 Diffuse reflectance IR spectra of piperidine adsorbed on 8 wt% molybdena/silica reduced and deuterium-exchanged catalyst. See text for conditions.
- Fig. 5 Diffuse reflectance IR spectra of piperidine adsorbed on deuterium-exchanged alumina. See text for conditions.
- Fig. 6 Diffuse reflectance IR spectra of piperidine adsorbed on reduced 8 wt% molybdena/alumina. See text for conditions.
- Fig. 7 Diffuse reflectance IR spectra of piperidine adsorbed on reduced and deuterium-exchanged 8 wt% molybdena/alumina. See text for conditions.

DRIFTS of chemisorbed piperidine on SiO_2

DRIFTS of D_2 exchanged SiO_2 and
chemisorbed piperidine.

DRIFTS of reduced 8% Mo/SiO_2
and chemisorbed piperidine.

DRIFTS of D₂ exchanged 8% Mo/SiO₂
and chemisorbed piperidine.

DRIFTS of D_2 exchanged Al_2O_3 and
and chemisorbed piperidine.

DRIFTS of reduced 8% $\text{Mo}/\text{Al}_2\text{O}_3$ and
chemisorbed piperidine

DRIFTS of D_2 exchanged 8% $\text{Mo}/\text{Al}_2\text{O}_3$
and chemisorbed piperidine

END

**DATE
FILMED**

9 / 9 / 92