27/
7-13-77
250 NTS

BDX-613-1480 (Rev.)

SYNTHESIS OF POLYAMINOBISMALEIMIDE

MASTER

PDO 6989254, Final Report

D. R. Jamieson, Project Leader

Project Team:
J. E. Adams
G. W. Griffith
C. L. Long
J. M. Walker

Published November 1975

Prepared for the United States Energy Research and Development
Administration Under Contract Number EY-76-C-04-0613 USERDA

**Kansas City
Division**

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

NOTICE

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Energy Research and Development Administration, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

Printed in the United States of America

Available From the National Technical Information Service, U.S. Department of Commerce, 5285 Port Royal Road, Springfield, Virginia 22161.

Price: Microfiche \$2.25
Paper Copy \$4.50

BDX-613-1480
Distribution Category UC-25

SYNTHESIS OF POLYAMINOBISMALEIMIDE

Published November 1975

Project Leader:
D. R. Jamieson
Department 814

Project Team:
J. E. Adams
G. W. Griffith
C. L. Long
J. M. Walker

PDO 6989254
Final Report

NOTICE

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Energy Research and Development Administration, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

Communications Services

**Kansas City
Division**

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

SYNTHESIS OF POLYAMINOBISMALEIMIDE (Rev.)

BDX-613-1480, UNCLASSIFIED Final Report, Published November 1975

Prepared by D. R. Jamieson, D/814, under PDO 6989254

Studies were conducted on a laboratory scale to determine chemical routes required to reproduce the commercial resin system, Kerimid 601. The resin was identified as polyaminobismaleimide. Reaction variables, pertinent to the synthesis of the resin precursor, were studied and formulations resembling the commercial resin were prepared for evaluation. Results indicate technical feasibility for producing this resin.

WPC-bj1

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Energy Research and Development Administration, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

The Bendix Corporation
Kansas City Division
P.O. Box 1159
Kansas City, Missouri 64141

A prime contractor with the United States
Energy Research and Development
Administration under Contract
Number EY-76-C-04-0613 USERDA

CONTENTS

Section	Page
SUMMARY.	5
DISCUSSION	6
SCOPE AND PURPOSE.	6
ACTIVITY	6
<u>Composition and Structure of Commercial Resin. . . .</u>	6
<u>Preparation of 4,4'-Bismaleimidodiphenylmethane</u> <u>(BMI).</u>	9
<u>Preparation of Polyaminobismaleimide Resin System. .</u>	15
ACCOMPLISHMENTS.	23
FUTURE WORK.	26
DISTRIBUTION	27

ILLUSTRATIONS

Figure		Page
1	Particle Size Distribution Curve for Kerimid 601 Resin.	10
2	Infrared Spectrum of Kerimid 601 Resin	11
3	GPC Chromatogram of Kerimid 601 Resin.	13
4	Infrared Spectrum of BMI Batch 17.	16
5	Infrared Spectrum of Impure BMI.	17
6	Infrared Spectrum of 6.7/1 BMI/MDA Melt Blend.	19
7	Infrared Spectrum of 3.25/1 BMI/MDA Melt Blend.	20
8	Infrared Spectrum of Melt Blend Prepared From Impure BMI.	21
9	GPC Chromatogram of BMI/MDA Melt-Blend Batch 6A	23
10	GPC Chromatogram of Replicate BMI/MDA Melt Blend	24
11	GPC Chromatogram of BMI/MDA Melt-Blend Prepared With Impure BMI	24
12	Temperature Versus Dissipation of Kerimid 601 and Bendix Blends.	25

TABLES

Number		Page
1	Summary of Physical and Chemical Properties of Kerimid 601 Resin	12
2	Carbon, Hydrogen, and Nitrogen Content of Experimental Batches of BMI.	18

SUMMARY

Studies were conducted on a laboratory scale for duplicating Kerimid 601 (Rhodia Incorporated, France), a commercial resin system. Since the only commercial source of this material is a foreign supplier, work was undertaken to establish technical feasibility for producing the resin on an emergency basis should the resin become unavailable, and to provide process data for scale-up, if the capability for producing pilot plant or production quantities becomes necessary.

Kerimid 601 is a finely divided bright yellow powder, and upon quantitative and qualitative analysis, was found to be composed of a mixture of 6.7 parts 4,4'-bismaleimidodiphenylmethane (BMI) and 1.0 part methylenedianiline (MDA). About 10 percent of the MDA is free and 90 percent is bound to BMI.

Synthesis of BMI was accomplished in a two-step procedure involving first the formation of maleamic acid by reacting maleic anhydride with methylenedianiline followed by the dehydration of maleamic acid with acetic anhydride. Both reactions were carried out in a dimethylformamide solution, with the latter reaction catalyzed by anhydrous sodium acetate.

A reaction variable study was conducted to optimize the process, and the pertinent physical and chemical properties of pure BMI were determined so that the purity of BMI produced in the process could be assessed. The variable study indicated the reaction temperature must be held below 60°C to prevent the formation of undesirable by-products.

Attempts to duplicate the Kerimid 601 resin system were carried out by melt-blending appropriate proportions of BMI and MDA under various conditions and comparing physical and chemical properties of the samples with those of the Kerimid system. It was determined that the elapsed time at the blending temperature was the most critical variable associated with the blending operation and lack of control of this parameter caused wide deviation from target specifications.

Larger scale production of this resin system will require additional studies of the melt-blending operation to insure consistency in the final product.

DISCUSSION

SCOPE AND PURPOSE

The project was undertaken to develop the capability for duplicating Kerimid 601 polyimide resin since the only source of this resin is a foreign supplier, the need exists for the capability for producing the material in-house on an emergency basis, or as a back-up to commercial suppliers should the material become unavailable. Pursuant to this objective, the chemical composition and chemical structure of the commercial resin were characterized and procedures for synthesizing the resin and resin precursor were developed.

ACTIVITY

Composition and Structure of Commercial Resin

The Kerimid 601 polyimide resin system in the uncured state is composed of a mixture of 4,4'-bismaleimidodiphenylmethane and methylenedianiline as determined by mass spectroscopy and gel permeation chromatography (GPC). Structural formulae for these compounds are shown in structural diagrams (1) and (2).

These two compounds are present in the weight ratio of 6.7 parts of BMI to 1 part MDA, as determined by carbon-hydrogen analysis.

The resin system may cure by two different reaction paths, each being an addition reaction, to form a cross-linked thermoset structure. The first reaction involves the addition of MDA to BMI according to structural diagram (3).

In like manner, the unreacted primary amino group may react with another mole of BMI to chain extend the molecule. This reaction occurs at relatively low temperatures, in the neighborhood of 100°C, and can go to near completion in much less than 1 hour.

Approximately 90 percent of the amine is bound to the imide in the commercial material so that the resin is largely composed of the molecular species shown in structural diagrams (4) and (5).

The second reaction path effecting cure involves homopolymerization of the olefin group present in the imide ring. The reaction is thermally initiated around 150°C and proceeds as shown in structural diagram (6).

The commercial resin melts around 104°C although the vendor indicates their internal product specification is 100° ± 2°C.

4,4'-BISMALEIMIDODIPHENYLMETHANE (BMI)

METHYLENEDIANILINE (MDA)

where:

(4)

(5)

The resin is a bright yellow powder which has an average particle size of about 13 microns (micrometers). The distribution curve (Figure 1) does not appear to be log-normal, but instead shows some skewing toward the lower end of the curve.

The infrared spectrum of the resin (Figure 2) shows a characteristic strong absorption of the imide group in the 5.9 to 6.2 micron region, and more importantly shows little in the way of primary amine absorption. The infrared appears to be a good qualitative tool for characterizing this material, but is not particularly sensitive for estimating the relative amounts of bismaleimide and methylenedianiline present in the resin system.

Table 1 summarizes important properties of this material obtained thus far.

Of the characterization studies carried out, the GPC proved to be particularly valuable because the array of molecular species present in this product was elucidated. In the GPC curve (Figure 3) the peak centered on 24 eV corresponds to BMI, and the peak at about 25.4 eV results from unreacted MDA. The peaks between 16 eV and 22 eV are due to adducts resulting from the reactions of BMI and MDA. The molecular weight of each species decreases with increasing elution volume. About 18 percent of the sample was insoluble in tetrahydrofuran (THF), the elution solvent, indicating the presence in the product of adducts whose molecular weights are higher than those shown in the curve.

Preparation of 4,4'-Bismaleimidodiphenylmethane (BMI)

The synthesis of BMI was accomplished in large measure by utilizing the procedures developed by Cole and others¹ with some

¹U. S. Patent 3,127,414, H. N. Cole, C. Gruber, W. F. Gruber, Preparation of m-Phenylenedimaleimide

Figure 1. Particle Size Distribution Curve for Kerimid 601 Resin

modifications. These procedures involve a two-step synthesis route, each step being carried out in solution. The first step involves the formation of methylene bis (N-phenyl) maleamic acid by treating maleic anhydride with methylenedianiline in dimethylformamide solution. The reaction proceeds according to structural diagram (7).

The reaction proceeds readily at room temperature and characteristically causes a slight rise in temperature of the reaction mixture. The reaction goes to completion in about an hour, but to insure reaction completion the mixture was allowed to stir for 2 hours before the next step in the synthesis procedure was

Figure 2. Infrared Spectrum of Kerimid 601 Resin

Table 1. Summary of Physical and Chemical Properties of Kerimid 601 Resin

Property	Value
Melting Point	100 to 104°C
Carbon	71.35 Percent
Hydrogen	4.45 Percent
Nitrogen	8.49 Percent
Free MDA	~1.3 Weight Percent
Theoretical BMI to MDA Ratio (based upon C, H, N analysis)	6.7 to 1

initiated. The product is soluble in dimethylformamide and remains in solution even after the reaction mixture cools down to room temperature.

The next step in the synthesis of BMI involves the imidization reaction which can be initiated immediately after completion of the first step in the same reaction mixture without the need for isolation of maleamic acid.

Imidization or cyclization is accomplished by the reaction of acetic anhydride with maleamic acid and is catalyzed by sodium acetate. The reaction proceeds according to structural diagram (8).

This reaction is a dehydration reaction in which two moles of water are split out of maleamic acid. The reaction is run at 55 to 60°C in a nitrogen atmosphere and is essentially complete in about 2 hours. The temperature must be kept in the range mentioned above to minimize the formation of undesirable byproducts formed at higher temperature. A nitrogen blanket over the reaction mixture minimizes oxidation of methylenedianiline. After the reaction is complete, the reaction mixture is added drop-wise to 4 volumes of water, and BMI precipitates as bright yellow crystals. The crude BMI is filtered and washed several times with distilled water and finally vacuum dried overnight at 60°C. The product at this point is a finely divided bright yellow powder.

A typical recipe for the imidization reaction utilizing the quantity of maleamic acid contained in the first step previously

Figure 3. GPC Chromatogram of Kerimid 601 Resin

described includes the use of a two-fold excess of acetic anhydride to drive the reaction to completion. Literature sources² indicate potassium acetate is a better catalyst than sodium acetate but the potassium salt was not evaluated in this process. The procedure involves dissolving the requisite quantity of sodium acetate in 90 milliliters of acetic anhydride and adding the resulting solution to the reaction mixture from step one. The temperature of the reaction mixture is raised to 55 to 60°C and maintained in this range for 2 hours. A nitrogen blanket is maintained over the reaction mixture until reaction is complete and cooled to room temperature.

²"Macromolecular Synthesis," Volume 2, John Wiley and Sons Incorporated, 1966, p 111.

Numerous runs were made at elevated temperatures (in the neighborhood of 80 to 90°C) in the attempt to accelerate the imidization reaction, but in each attempt, the higher temperatures led to an excessive amount of undesirable byproducts which interfere with the cure mechanism in the subsequent resin formulations.

The melting point of pure BMI is 150°C and laboratory batches having low amounts of impurities typically melt in the range of 147 to 150°C. Impure BMI characteristically has a melting range of 135 to 140°C or lower.

Gross differences between pure and impure BMI appear in their respective infrared spectra. The infrared spectrum of a good

batch of BMI, shown in Figure 4, compares favorably with a standard spectrum.³ The spectrum of impure material (Figure 5) is substantially different from the standard especially in the fingerprint region of the spectrum around 12.6 micrometers. The nature or structure of the impurities is not apparent from the spectrum but band broadening seen in the region from 6.0 to 6.5 micrometers suggests the presence of significant quantities of free amide in the sample. The presence of amide indicates some of the impurities may be caused by incomplete cyclization or imidization in the second step of the process.

Samples of BMI produced in the laboratory were also analyzed for carbon, hydrogen, and nitrogen and the results are tabulated (Table 2). The data clearly show impure BMI is consistently low in carbon and support the concept that some of the impurities may result from incomplete imidization. Low carbon may also result from oxidation of methylenedianiline which could occur during the imidization reaction. The relative ease of oxidation of aromatic amines is well established in the literature.

During development efforts leading to a laboratory procedure for the synthesis of BMI, it became apparent that appropriate analytical data was necessary to insure the product was sufficiently pure. Generally, good material exhibits a bright yellow color, while bad material tends to be brown or tan in color. Some lots, however, showed an acceptable color but proved to be bad and were found to exhibit a low melting point. It is suggested, therefore, that during subsequent development efforts involving the synthesis of BMI at least two criteria be used to determine acceptability of these products. These are that the melting point must be in the range of 147 to 150°C and that the infrared spectrum be identical to that of the standard.

Although C, H, and N analysis is quite informative as to the purity of this product, the analysis itself is time-consuming and does not enhance the sensitivity of the previously mentioned tests.

Preparation of Polyaminobismaleimide Resin System

As previously indicated, analysis of Kerimid 601 indicated the resin system was basically composed of 6.7 parts BMI to 1 part methylenedianiline with about 90 percent of the methylenedianiline bonded to the BMI through an addition reaction. Such a

³"Infrared Spectra File," Spectrum Number 47360, Sadtler Research Laboratories, Incorporated, 1975

Figure 4. Infrared Spectrum of BMI Batch 17

Figure 5. Infrared Spectrum of Impure BMI

Table 2. Carbon, Hydrogen, and Nitrogen Content of Experimental Batches of BMI

Batch Number	Carbon (Percent)	Hydrogen (Percent)	Nitrogen (Percent)	Quality of Batch
14	69.48	3.91	7.51	Bad
15	69.36	4.05	7.45	Bad
16	69.91	4.03	7.57	Good
17	70.13	4.02	7.69	Good

system may be prepared by melt-blending the appropriate quantities of BMI and MDA. During the melt-blending process the addition reaction between MDA and the double-bond in BMI takes place. Since the addition reaction proceeds readily at temperatures slightly above the melting point of MDA (92°C), time and temperature of the melt-blending process are the most important variables involved in this process. The melt-blending procedure suggested by the patent literature¹ calls for heating MDA to 120°C, at which point MDA is quite fluid, and adding the appropriate quantity of BMI with stirring until the mixture appears homogeneous. Stirring is continued for 10 minutes, at which time, the mixture is quenched and forms a brittle glassy solid, which can be ground to a fine powder.

A series of melt-blends was prepared and the resulting samples were analyzed by GPC, infrared spectroscopy, and dielectric analysis. The resulting analytical data were then compared with similar data obtained from the Kerimid system.

The infrared spectrum of a melt-blend containing 6.7 parts BMI and 1 part MDA is shown in Figure 6 and is comparable to the spectrum of the Kerimid resin (Figure 2). The spectrum of a sample composed of 3.25 parts BMI to 1 part MDA (Figure 7) was prepared to determine the effects of a gross change in composition on the relative intensities of the bands in the fingerprint region of the spectrum. A comparison of respective spectra shows only subtle differences. A comparison of the spectrum of a melt-blend made from a bad batch of BMI, Figure 8, with Figures 6 or 7 reveals gross differences, particularly in the region around 8.7 microns where the shape of the bands from bad material is substantially different from the bands produced by good material. It appears, therefore, infrared analysis is useful to characterize the qualitative nature of the system but is relatively insensitive to the quantitative nature. A more intensive study of the infrared behavior during future development efforts, however, may yield more information.

Figure 6. Infrared Spectrum of 6.7/1 BMI/MDA Melt-Blend

Figure 7. Infrared Spectrum of 3.25/1 BMI/MDA Melt-Blend

Figure 8. Infrared Spectrum of Melt-Blend Prepared From Impure BMI

GPC chromatograms were obtained for several melt-blends to characterize the molecular species present in the blends. Figure 9 is the GPC curve obtained for melt-blend Batch 6A (100 gram batch) and is comparable to the curve obtained for the Kerimid system (Figure 3). The peak centered on 24 elution counts is due to BMI, while the earlier peaks are due to the array of adducts formed from BMI and MDA.

A GPC chromatogram (Figure 10) of a small batch made in the attempt to duplicate Batch 6A shows the same molecular species but slightly different relative quantities. This difference illustrates the point that close control of time and temperature are necessary to reproduce exactly the array of molecular species present in the Kerimid system.

During the preparation of another melt-blend (Batch 7) temperature control was lost and the temperature reached 130°C during blending operations. The resulting resin had a high melting point and, more importantly, no free MDA remained in mixture as evidenced by the absence of a MDA peak in the mass spectra of the system. This latter result again shows the necessity for good temperature control during the melt-blending operation.

The GPC chromatogram of a melt-blend made from a lot of BMI which was known to be bad (Figure 11) shows an array of molecular species, quite different from that of the commercial resin. Particularly noticeable is the absence of a strong peak at 24 eV due to BMI.

Dielectric analysis of three melt-blends was performed using the Audrey II dielectrometer and dissipation was measured as a function of temperature and time at frequencies between 100 and 1000 Hz. Dissipation plots for the commercial material were obtained for reference purposes. Figure 12 summarizes the data obtained and indicates, of the three batches analyzed, only Batch 6A is similar in response to the commercial resin with respect to dissipation. The dissipation curve for Melt Blend Batch 7 is shifted toward higher temperatures, as seen in Figure 12. As previously mentioned, Batch 7 was over-cooked because of a loss of temperature control during the blending operation and the effect on the dissipation curve is well illustrated. The two Kerimid curves in Figure 12 were obtained from two different lots of the material.

Changes in dielectric properties are usually attributed to changes in structure but it is possible that small amounts of impurities can mask the true nature of the dissipation curve. At this point, not enough is known about the nature of the changes in dissipation resulting from these two effects to draw any firm conclusions for this system; the data, however, does infer that Batch 6A is close to, but not identical to, the Kerimid 601 resin system.

Figure 9. GPC Chromatogram of BMI/MDA
Melt-Blend Batch 6A

As the data shows, only one batch (6A) came close to duplicating the Kerimid 601 resin in all respects, and a sample of this batch was molded using a simulated production process. The molded part appeared to be similar to parts molded with Kerimid 601, based upon preliminary examination.

ACCOMPLISHMENTS

A chemical process for producing BMI, a precursor to a polyamino-bismaleimide resin system, was developed. The reaction conditions and purification techniques required to produce good quality BMI were established, and analytical procedures necessary to assure the requisite purity of BMI were worked out.

Figure 10. GPC Chromatogram of Replicate BMI/MDA Melt-Blend

Figure 11. GPC Chromatogram of BMI/MDA Melt-Blend Prepared With Impure BMI

Figure 12. Temperature Versus Dissipation of Kerimid 601 and Bendix Blends

A technical feasibility for producing a polyaminobismaleimide resin system similar to Kerimid 601 was established. Although the ultimate goal to duplicate this commercial resin was not fully realized, enough information was gathered during this project regarding the composition and cure mechanism to assure us that complete duplication is a reasonable goal in subsequent development efforts.

FUTURE WORK

To provide a back-up capability for producing this material on a production scale, two areas in the process will require further development. The most important is development of the technique for melt blending BMI and MDA. Close control of the temperature during the blending operation is required since the array of molecular species in the blend depends upon the proper degree of cure attained during the blending operation. If the present blending technique was used during production scale operations, an undesirable number of rejected batches would probably result.

The procedure for grinding the solidified melt blend to the appropriate particle size should be improved. The present procedure, grinding with a mortar and pestle, is only adequate at best and is not amenable to a production scale process. To prove the capability for producing this material on large scale, the process should, of course, be scaled up, and pilot plant quantities, on the order of 10 pounds (4.5 kg) per batch, should be produced and evaluated. Scale-up may require the acquisition of some equipment presently not among the complement of our pilot plant equipment. A successful pilot project will establish both a back-up and in-house capability for producing this material.

DISTRIBUTION

	Copy
R. Bulcock, ERDA-KCAO	1
V. C. Vespe, ERDA-ALO	2
F. B. Baker, LASL	3
F. Dubois, LASL	4
J. A. Freed, LASL	5
R. S. Gauler, LASL	6
S. J. Buginas, LLL	7
W. E. Cady, LLL	8
J. K. Lepper, LLL	9
H. M. Brinkmeier, Monsanto	10
P. B. Rand, SLA	11
J. M. Brierly, SLL	12
H. R. Sheppard, SLL	13
J. D. Corey, D/554, BD50	14-15
L. Stratton, D/554, 2C44	16-18
R. F. Pippert, D/700, 1A42	19
R. P. Frohmberg, D/800, 2A39	20
J. C. Culver, D/812, 2A27	21
W. H. Deterding, D/814, 2C43	22
D. R. Jamieson, D/814, 2C43	23
H. M. McIlroy, D/814, 2C43	24
C. H. Smith, D/814, 2C43	25
D. M. Cowan, D/816, SG3	26
R. A. Daniel, D/861, 2A31	27
R. H. Graham, D/861, 2A31	28
R. E. Kessler, D/865, 2C40	29