217
11/11/76

Q1-500

Y-2063

**FRACTURE CHARACTERISTICS OF URANIUM
ALLOYS BY SCANNING ELECTRON
MICROSCOPY**

J. W. Koger
R. K. Bennett, Jr

October 1976

NOTICE

PORTIONS OF THIS REPORT ARE ILLEGIBLE. It
has been reproduced from the best available
copy to permit the broadest possible avail-
ability.

**UNION
CARBIDE**

OAK RIDGE Y-12 PLANT
OAK RIDGE, TENNESSEE

*prepared for the U.S. ENERGY RESEARCH AND DEVELOPMENT ADMINISTRATION
under U.S. GOVERNMENT Contract W-7405 eng 26*

NOTICE

PORTIONS OF THIS REPORT ARE ILLEGIBLE. It
has been reproduced from the best available
copy to permit the broadest possible avail-
ability.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

Printed in the United States of America. Available from
National Technical Information Service
U.S. Department of Commerce
5285 Port Royal Road, Springfield, Virginia 22161
Price: Printed Copy \$4.00; Microfiche \$2.25

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the Energy Research and Development Administration/United States Nuclear Regulatory Commission, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

Date of Issue: October 28, 1976
Distribution Category: UC-25

Report Number: Y-2063

FRACTURE CHARACTERISTICS OF URANIUM ALLOYS BY SCANNING ELECTRON MICROSCOPY

J. W. Koger
Metallurgical Development Department

R. K. Bennett, Jr
Laboratory Development Department
Y-12 Development Division

NOTICE
This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Energy Research and Development Administration, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

Oak Ridge Y-12 Plant
P. O. Box Y, Oak Ridge, Tennessee 37830

Prepared for the US Energy Research
and Development Administration
Under US Government Contract W-7405-eng-26

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

ABSTRACT

The fracture characteristics of uranium alloys were determined by scanning electron microscopy. The fracture mode of stress-corrosion cracking (SCC) of uranium-7.5 weight percent niobium-2.5 weight percent zirconium (Mulberry) alloy, uranium-niobium alloys, and uranium-molybdenum alloys in aqueous chloride solutions is intergranular. The SCC fracture surface of the Mulberry alloy is characterized by very clean and smooth grain facets. The tensile-overload fracture surfaces of these alloys are characteristically ductile dimple. Hydrogen-embrittlement failures of the uranium alloys are brittle and the fracture mode is transgranular. Fracture surfaces of the uranium-0.75 weight percent titanium alloys are quasi cleavage.

CONTENTS

SUMMARY	4
INTRODUCTION	5
FRACTURE CHARACTERISTICS OF URANIUM ALLOYS	6
Experimental Procedure	6
Fractography with the Scanning Electron Microscope	6
Specimen Preparation	6
Scanning Electron Microscope Examination	7
Results and Discussion	7
Uranium-7.5 Niobium-2.5 Zirconium Alloy (Mulberry)	7
Uranium-Niobium Alloys	8
Uranium-Molybdenum Alloys	9
Uranium-Titanium Alloys	9
Conclusions	10
REFERENCES	11
APPENDIX	13
Micrographs of Alloy Specimens	13

MASTER

SUMMARY

The purpose of this study was to contrast and compare various fracture surfaces of uranium alloys by using the scanning electron microscope (SEM). Aqueous chloride stress-corrosion-cracking (SCC) failures, tensile-overload failures, and hydrogen-embrittlement failures were studied in uranium-7.5 weight percent niobium-2.5 weight percent zirconium alloy (Mulberry), uranium-niobium alloys, uranium-molybdenum alloys, and uranium-titanium alloys. The fracture mode of SCC was intergranular for all but the uranium-titanium alloys, and the fracture mode of tensile overload was ductile dimple. Hydrogen-embrittlement failures are brittle and the fracture mode is transgranular. Fracture surfaces of the uranium-titanium alloys are quasi cleavage.

INTRODUCTION

Unalloyed uranium has rather poor mechanical properties and corrodes readily when exposed to the atmosphere. A desirable solution is to alloy the uranium with such elements as molybdenum and niobium which, in amounts over 4 wt %, stabilize the high-temperature gamma phase at room temperature. Such binary alloys possess improved strength, ductility, and corrosion resistance. In addition, their physical properties can be altered by heat treatment.

Ternary systems involving the three elements of note have also been considered and the uranium-7.5 niobium-2.5 zirconium (Mulberry) ternary alloy was found to have several improved properties, compared to uranium, and has been substituted for uranium on a production scale for certain applications.

For some applications, dilution of the uranium must be minimized. Studies have shown significant increases in the mechanical properties and oxidation resistance with very small additions (<3 wt %) of elements such as titanium, molybdenum, niobium, and zirconium. These alloys transform to a martensitic structure on water quenching from above 800° C.

One objective of this report is to contrast and compare the fracture surfaces of various uranium-based alloys, like those mentioned, caused by SCC, hydrogen embrittlement, and a tensile-force overload. Saxton has an excellent review of the fracture behavior of several uranium alloys.⁽¹⁾ Characterization of the various fracture surfaces will prove helpful when failures occur in these alloys during service. Correlation of optical microstructures with these fracture surfaces is also of interest. The stress-corrosion failures occurred on exposure of stressed specimens to aqueous chloride solutions. Hydrogen-embrittlement specimens were made by charging hydrogen into the specimens at high temperature, followed by a rapid quench. The specimens were then subjected to a tensile test.

The work described in this report was performed at the Oak Ridge Y-12 Plant.^(a)

(a) Operated by the Union Carbide Corporation's Nuclear Division for the US Energy Research and Development Administration.

FRACTURE CHARACTERISTICS OF URANIUM ALLOYS

EXPERIMENTAL PROCEDURE

Fractography with the Scanning Electron Microscope

In general, there are four basic techniques used for examination and characterization of fracture morphology: (1) visual observation, (2) optical microscopy, (3) transmission electron microscopy (TEM), and (4) scanning electron microscopy (SEM), each of which can be documented by photography. The need for sufficient magnification to reveal the necessary microstructure for fractographic interpretation generally requires the use of either TEM or SEM. Since the introduction of commercially available SEM instruments in 1966, this technique has been found to offer the simplest and quickest approach to fractography. Discussions of all four methods, as well as the scope and usefulness of fractography in the characterization of metals, has been well documented in the literature. One of the most inclusive treatments of the subject may be found in the *Metals Handbook*.⁽²⁾

Specimen Preparation

Three potential problems are encountered in the preparation of metal fracture specimens for examination by SEM: (1) cutting to a size compatible to fit the SEM specimen chamber; (2) protection from, or removal of, a destructive oxidation coating which hides the surface detail, and (3) cleaning extraneous material from the surface. Since the majority of the fractures discussed in this report were from specially prepared and experimentally fractured specimens, very few required cutting. When cutting was necessary, extreme care was taken to protect the fracture surface from scratches or other types of disfiguration.

Unlike the fractures of most steel alloys which destructively oxidize rapidly and require special protection (by such methods as immersion in an inert liquid or plastic coating), the uranium alloys investigated to date appear to form a light protective oxide coat which does not seem to obliterate the basic fractographic details. Thus, no surface-protection measures were used on the uranium alloy fracture surfaces, and no attempt was made to remove the oxide coat before the SEM analysis was performed.

The rough nature of a fracture surface makes it extremely susceptible to picking up and holding dirt, lint, fibers (from protective tissues), plastic particles (sample vials), oil, grease, and, particularly, "finger grease" and/or tiny bits of skin from handling. All of these contaminants must be cleaned from the surface before SEM examination to avoid artifacts. In addition to the obvious reasons for avoiding such artifacts, interaction of the electron beam with loosely attached particles can cause localized charging, resulting in distortion—not only in the field of view, but frequently in adjacent areas. Thus, all such contaminants must be removed by an effective cleaning technique. If possible, the cleaning process should not remove any corrosion products which were part of the fracture-initiation mechanism. Consequently, a gentle liquid ultrasonic treatment was utilized to clean the alloy surfaces. The first liquid used was a dilute aqueous detergent (a drop of a commercial dishwashing detergent in a beaker of water) and the second, acetone. Before placing the specimen in the SEM, an inspection of the surface was made by using a Stereozoom optical microscope in the 10X-to-30X magnification range. If surface contaminants were still

present, longer ultrasonic times were tried and/or different organic solvents were used. In a few cases it was necessary to mechanically remove the contaminant (usually a fiber or piece of plastic trapped in a crevice) by brushing gently with a soft nylon brush with the specimen submerged in acetone. Regardless of the cleaning technique used, extreme care was exercised to avoid any damage to the fracture surface. For example, two specimens were never simultaneously treated ultrasonically in the same container because of the possibility that one specimen would scratch the other.

Scanning Electron Microscope Examination

The specimens were examined in a JEOL Model JSM-2 scanning electron microscope (SEM) equipped with a rapid-scan TV accessory and an ORTEC energy-dispersive X-ray identification unit. The entire fracture surface was surveyed at several magnifications using the TV-scan unit to check for such characteristics as uniformity, fracture modes, and corrosion products. Selected representative areas were chosen and micrographs were made using the SEM higher-resolution cathode-ray tubes, employing standard SEM techniques. The energy-dispersive X-ray unit was utilized to help identify inclusions and/or corrosion products.

RESULTS AND DISCUSSION

Uranium-7.5 Niobium-2.5 Zirconium Alloy (Mulberry)

Figure A-1 (Appendix) is an optical micrograph of an intergranular stress-corrosion crack in Mulberry that was vacuum water quenched from 800° C and aged at 150° C for one hour. The crack started from a pit. The intergranular character of the fracture is seen in a scanning electron micrograph, Figure A-2. Note the smooth grain facets and some secondary cracks at the grain boundaries. Figures A-3 through A-5 show Mulberry subjected to 0.35, 0.70, and 0.90% strain in an aqueous-chloride-containing solution. Failure times decreased with increasing strain. The grain facets of Figure A-3 are smoothest, perhaps since less strain was required before failure. More tear ridges are seen in Figure A-5 than in the others, as the specimen of Figure A-5 did undergo a higher strain. Magnani⁽³⁾ and Zehr⁽⁴⁾ have shown that, below a certain chloride ion level, an intergranular crack will not propagate in Mulberry, but transgranular cracking will occur and the path of the crack can be changed from intergranular to transgranular by lowering the chloride ion content.

The fracture surfaces shown in Figures A-6 and A-7 resulted from a fracture-toughness specimen exposed to 40% relative humidity air. The precracked area shows fatigue striations, a step-wise slip failure, and large dimples. The fracture surface shows fairly standard dimples. Figure A-8 is a tensile-overload area which looks much like Figure A-7. Increasing the hydrogen content of the alloy changed the fracture mode from ductile dimple to a mixed ductile dimple and dimpled intergranular.

Partially recrystallized Mulberry is much more resistant to aqueous-chloride-induced stress-corrosion cracking (SCC) than fully recrystallized Mulberry.⁽⁵⁾ The fracture surface of a partially recrystallized SCC specimen shows both ductile dimple and intergranular characteristics (Figure A-9). The presence of ductile areas indicates that the sample failed by tensile overload of the reduced surface area which resulted from the SCC. The sample would not fail by SCC alone.

Certain additions have been made to Mulberry to improve its mechanical properties and to affect its grain size. Figures A-10 and A-11 are stress-corrosion fracture surfaces of Mulberry with an addition of 0.25 wt % chromium (in Figure A-10) and 0.75 wt % germanium (in Figure A-11). (The specimens were strained 1%.) Note the smooth grain facets and the precipitates in both cases. X-ray identification techniques showed that the precipitates were chromium rich in Figure A-10 and germanium rich in Figure A-11.

Fracture surfaces of the three "modified" Mulberry alloys were compared. These specimens were also strained 1%. Figure A-12 is an SEM of the fracture surface of a specimen of U-6.5 Nb-1.5 Zr alloy. The surface is intergranular, with secondary cracks and corrosion product noted on the surface.

Figure A-13 shows the fracture surface of a U-7.5 Nb-2.5 Hf alloy specimen. The failure is intergranular, but the grain facets are not quite as smooth as those of "normal" Mulberry. Secondary cracks and precipitates are visible, along with some evidence of ductility. Figure A-14 is an SEM of the fracture surface of a U-8.5 Nb-1.5 Zr alloy specimen. Again, smooth faceted grains are the rule.

Mulberry, loaded with 100 ppm of hydrogen, fails in tension in a ductile manner (Figure A-15, Circle 2). Comparison of the intergranular failure under stress-corrosion conditions and the ductile behavior when loaded with hydrogen indicate that hydrogen embrittlement and SCC involve two totally different mechanisms.

Uranium-Niobium Alloys

Figure A-16 is a view of a tensile overload fracture surface of uranium-4 niobium (U-4 Nb) as vacuum-water quenched from 800° C. Tear ridges and secondary cracks are much in evidence, with no obvious dimples. The failure mode is ductile transgranular. The specimen of Figure A-17 failed under a strain of 1% in an aqueous chloride solution. The failure is primarily intergranular. Corrosion products are present.

Uranium-6 niobium (U-6 Nb) is a gamma-quenched alloy which can be age hardened.⁽⁶⁾ Figure A-18 is a typical optical micrograph of an intergranular stress-corrosion crack in vacuum-water quenched U-6 Nb unaged or aged below 300° C. The fracture surface of the crack is seen in Figure A-19. Corrosion products are also noted. The grain facets are not as smooth as those in Mulberry. After aging at 300° C, the strength of U-6 Nb is greatly increased and the ductility and stress-corrosion resistance is greatly decreased. Figure A-20 shows the tensile-overload fracture of the 300° C-aged U-6 Nb alloy. The fracture is primarily ductile dimple. Figure A-21 shows a SCC fracture of the 300° C-aged U-6 Nb alloy. The failure is primarily intergranular, with some quasi-cleavage regions.

After aging at 600° C, the alloy consists of two phases, is quite strong, and has reasonable ductility. Because one of the phases is high in uranium, the alloy is quite susceptible to general corrosion attack. An optical micrograph of a pearlitic two-phase structure is seen in Figure A-22. Figure A-23 shows the stress-corrosion fracture surface of the 600° C-aged U-6 Nb alloy. The black phase was brittle; and, because of the eutectoid structure, the fracture mode is difficult to define.

The SCC fracture surface of a vacuum-water quenched U-6 Nb alloy with 1000-ppm zirconium is seen in Figure A-24. Little effect of the zirconium addition was noted. The failure is intergranular, with considerable secondary cracking.

The tensile fracture surfaces of uranium-8.5 niobium (U-8.5 Nb) at three different hydrogen levels: 0 ppm (Circle 1), 12 ppm (Circle 2), and 27 ppm (Circle 3) are shown in Figure A-25. Above 15 ppm hydrogen, the fracture is quite brittle and transgranular.

Figure A-26 shows the tensile-overload fracture of the uranium-10 niobium (U-10 Nb) alloy. The fracture is characteristically ductile dimple. Figure A-27 shows a SCC fracture of the U-10 Nb alloy. Note that the failure is primarily intergranular. Corrosion product and secondary cracking are also noted. The tensile-overload fracture surface for U-10 Nb containing 0 ppm (Circle 1), 9 ppm (Circle 2), and 30 ppm (Circle 3) hydrogen is given in Figure A-28. The fracture is brittle, transgranular, and features small cleavage steps.

Uranium-Molybdenum Alloys

A stress-corrosion fracture surface of the as-quenched uranium-6 molybdenum (U-6 Mo) alloy is shown in Figure A-29. The failure mode is predominantly intergranular, and secondary cracks are seen. Figure A-30 shows the interface between both a stress-corrosion fracture surface and an overload surface. The overload surface of a specimen aged at 400° C has ductile-dimple characteristics, while the stress-corrosion surface is intergranular with some ductile areas. Figure A-31 is a micrograph of the stress-corrosion fracture surface of a specimen aged at 550° C. The fracture surface is intergranular and a second phase is seen at the grain boundaries.

Figure A-32 reveals the tensile-overload surface of as-quenched uranium-8 molybdenum (U-8 Mo) alloy. The fracture is predominantly ductile dimple. Figure A-33 is a view of the stress-corrosion fracture surface of the same alloy and it is primarily intergranular. Figure A-34 is the micrograph of the stress-corrosion fracture surface of U-8 Mo that was overaged at 550° C. The fracture path is primarily intergranular, with some evidence of fracture of the second-phase particles.

The failure mode of uranium-10 molybdenum (U-10 Mo) alloy with no hydrogen in the overload tensile tests was dimpled rupture. Additional amounts of hydrogen changed the appearance of the fracture surface to that of a brittle transgranular failure (Figure A-35). The surface shown in Circle 2 was from an alloy that contained 6 ppm hydrogen, while the material of Circle 3 contained 8 ppm hydrogen.

Uranium-Titanium Alloys

An optical micrograph of the uranium-0.75 titanium (U-0.75 Ti) alloy, aged at 400° C, is seen in Figure A-36. The microstructure is characterized by lenticular martensite and vestiges of the original grains. Figure A-37 shows the SCC surface of the alloy. Fracture occurred by shearing of the martensite lenticules, and the fracture appears as quasi cleavage following the martensitic phase. Johnson, et al,⁽⁷⁾ have shown that this fracture mode does not change with the changing test condition. Figure A-38 shows the SCC surface of a U-0.75 Ti-0.25 V alloy. The surface is somewhat different, due to different martensite phase

morphology. The surface resulting from tensile overload has a ductile appearance, as seen in Figure A-39.

CONCLUSIONS

Several conclusions can be stated because of this study:

1. The SCC fracture surface (from exposure to chloride solutions) of U-7.5 Nb-2.5 Zr alloy (Mulberry) shows very clean and smooth grain facets. The fracture mode is intergranular.
2. The tensile-overload fracture surfaces of Mulberry, the uranium-niobium alloys, and the uranium-molybdenum alloys are characteristically ductile dimple.
3. Hydrogen-embrittlement failures are brittle and the fracture mode is transgranular.
4. SCC fracture surfaces (chloride induced) of uranium-niobium alloys and uranium-molybdenum alloys are intergranular, but not as clean as those of Mulberry.
5. Fracture surfaces of the uranium-0.75 titanium alloy are quasi cleavage.

REFERENCES

- (1) Saxton, H. J.; *Fracture of Uranium Alloys*, SLL-74-5215; Sandia Laboratory, Livermore California (1974).
- (2) *Metals Handbook, Vol 9*, 8th Edition; *Fractography and an Atlas of Fractographs*; American Society for Metals, Metals Park, Ohio 44073.
- (3) Magnani, N. J.; "Stress Corrosion Cracking of Mulberry", *Corrosion*, **26**, p 406 (1970).
- (4) Zehr, S. W.; "A Study of the Intergranular Cracking of U-7.5 Wt % Nb-2.5 Wt % Zr (Mulberry) Alloy in Aqueous Chloride Solution", *Corrosion*, **28**, p 196 (1972).
- (5) Koger, J. W.; *Variables Which Influence the Stress-Corrosion Cracking of Uranium-7.5 Niobium-2.5 Zirconium Alloy*, Y-1965; Union Carbide Corporation-Nuclear Division, Oak Ridge Y-12 Plant, Oak Ridge, Tennessee; January 28, 1974.
- (6) Koger, J. W., Ammons, A. M., and Ferguson, J. E.; *Effect of Aging on the General Corrosion and Stress-Corrosion Cracking of Uranium-6 Wt % Niobium Alloy*, Y-1999; Union Carbide Corporation-Nuclear Division, Oak Ridge Y-12 Plant, Oak Ridge, Tennessee; November 26, 1975.
- (7) Johnson, H. R., Dini, J. W., and Zehr, S. W.; *On the Embrittlement of Uranium and Uranium-0.8 Titanium Alloy by Hydrogen and Water*, SLL-73-5300; Sandia Laboratories, Livermore, California (1973).

THIS PAGE
WAS INTENTIONALLY
LEFT BLANK

APPENDIX
MICROGRAPHS OF ALLOY SPECIMENS

(a) At 1000X.

SM-43665

(b) At 300X.

SM-43666

(c) At 100X.

SM-43667

Figure A-1. OPTICAL MICROGRAPH OF A STRESS-CORROSION CRACK IN URANIUM-7.5 WEIGHT PERCENT NIOBIUM-2.5 WEIGHT PERCENT ZIRCONIUM (MULBERRY).

MS-73-0989-4
Figure A-2. SCANNING ELECTRON MICROGRAPH OF A STRESS-CORROSION FRACTURE SURFACE OF MULBERRY. (100X)

(a) At 3000X.

SM-44487

(b) At 1000X.

SM-44488

(a) At 1000X.

SM-44517

(b) At 300X.

SM-44518

(c) At 300X.

SM-44489

Figure A-3. SCANNING ELECTRON MICROGRAPH OF A STRESS-CORROSION FRACTURE SURFACE OF MULBERRY, STRAINED 0.35 PERCENT.

(c) At 100X.

SM-44519

Figure A-4. SCANNING ELECTRON MICROGRAPH OF A STRESS-CORROSION FRACTURE SURFACE OF MULBERRY, STRAINED 0.7 PERCENT.

(a) At 1000X.

SM-44549

(b) At 300X.

SM-44550

(c) At 100X.

SM-44551

Figure A-5. SCANNING ELECTRON MICROGRAPH OF A STRESS-CORROSION FRACTURE SURFACE OF MULBERRY, STRAINED 0.9 PERCENT.

SM-44575-6

Figure A-6. SCANNING ELECTRON MICROGRAPH OF THE FRACTURE SURFACE OF A FAILED MULBERRY PRECRACKED FRACTURE-TOUGHNESS SPECIMEN. (300X)

(a) At 1000X.

SM-44568

(b) At 300X.

SM-44569

(c) At 100X

SM-44570

Figure A-7. SCANNING ELECTRON MICROGRAPH OF THE FRACTURE SURFACE OF A FAILED MULBERRY FRACTURE-TOUGHNESS SPECIMEN. (At Three Different Magnifications)

(a) At 3000X.

SM-43660

(b) At 1000X.

SM-43661

(c) At 300X.

SM-43662

Figure A-8. SCANNING ELECTRON MICROGRAPH OF A TENSILE-OVER-LOAD FRACTURE SURFACE OF MULBERRY.

(a) At 3000X.

SM-44552

b. At 1000X.

SM-44553

(c) At 300X.

SM-44554

Figure A-9. SCANNING ELECTRON MICROGRAPH OF A STRESS-CORROSION FRACTURE SURFACE OF PARTIALLY RECRYSTALLIZED MU_BERRY.

(a) At 1000X.

SM-43669

(b) At 300X.

SM-43670

(c) At 100X.

SM-43671

Figure A-10. SCANNING ELECTRON MICROGRAPH OF A STRESS-CORROSION FRACTURE SURFACE OF MULBERRY WITH 0.25 WEIGHT PERCENT CHROMIUM.

(a) At 3000X.

SM-43888

(b) At 1000X.

SM-43889

(c) At 300X.

SM-43890

Figure A-11. SCANNING ELECTRON MICROGRAPH OF A STRESS-CORROSION FRACTURE SURFACE OF MULBERRY WITH 0.75 WEIGHT PERCENT GERMANIUM.

(a) At 3000X.

SM-43703

(b) At 1000X.

SM-43704

(c) At 300X.

SM-43705

Figure A-12. SCANNING ELECTRON MICROGRAPH OF A STRESS-CORROSION FRACTURE SURFACE OF URANIUM-6.5 WEIGHT PERCENT NIOBIUM-1.5 WEIGHT PERCENT ZIRCONIUM.

(a) At 3000X.

SM-43689

(b) At 1000X.

SM-43690

(c) At 300X.

SM-43691

Figure A-13. SCANNING ELECTRON MICROGRAPH OF A STRESS-CORROSION FRACTURE SURFACE OF URANIUM-7.5 WEIGHT PERCENT NIOBIUM-2.5 WEIGHT PERCENT HAFNIUM.

Figure A-14. SCANNING ELECTRON MICROGRAPH OF A STRESS-CORROSION FRACTURE SURFACE OF URANIUM-8.5 WEIGHT PERCENT NIOBIUM-1.5 WEIGHT PERCENT ZIRCONIUM.

Figure A-15. SCANNING ELECTRON MICROGRAPH OF A TENSILE-OVERLOAD FRACTURE SURFACE OF MULBERRY WITH VARYING AMOUNTS OF HYDROGEN. (Circle 1, 0 ppm Hydrogen; Circle 2, 100 ppm Hydrogen)

161427

(a) At 1000X.

SM-43720 (b) At 300X.

SM-43721

(a) At 1000X.

SM-43712

(b) At 300X.

SM-43713

(c) At 100X.

SM-43722

Figure A-16. SCANNING ELECTRON MICROGRAPH OF A TENSILE-OVERLOAD FRACTURE SURFACE OF AS-QUENCHED URANIUM-4.5 WEIGHT PERCENT NIOBIUM.

(c) At 100X.

SM-43714

Figure A-17. SCANNING ELECTRON MICROGRAPH OF A STRESS-CORROSION FRACTURE SURFACE OF AS-QUENCHED URANIUM-4.5 WEIGHT PERCENT NIOBIUM.

MS-73-1110-2

Figure A-18. OPTICAL MICROGRAPH OF A STRESS-CORROSION CRACK IN AS-QUENCHED URANIUM-6 WEIGHT PERCENT NIOBIUM. (Identical Micrographs are Seen for the Alloy Aged up to 300° C; 100X)

(a) At 3000X.

SM-41102

(b) At 1000X.

SM-41103

(c) At 300X.

SM-41104

Figure A-19. SCANNING ELECTRON MICROGRAPH OF A STRESS-CORROSION FRACTURE SURFACE OF AS-QUENCHED URANIUM-6 WEIGHT PERCENT NIOBIUM.

(a) At 3000X.

SM-41089

(b) At 1000X.

SM-41090

(c) At 300X.

SM-41091

Figure A-20. SCANNING ELECTRON MICROGRAPH OF A TENSILE-OVERLOAD FRACTURE SURFACE OF URANIUM 6 WEIGHT PERCENT NIOBIUM, AGED AT 300°C.

(a) At 3000X.

SM-41110 (b) At 1000X.

SM-41111

(c) At 300X.

SM-41112

Figure A-21. SCANNING ELECTRON MICROGRAPH OF A STRESS-CORROSION FRACTURE SURFACE OF URANIUM-6 WEIGHT PERCENT NIOBIUM, AGED AT 300° C.

MS-73-1174-9

Figure A-22. OPTICAL MICROGRAPH OF URANIUM-6 WEIGHT PERCENT NIOBIUM, AGED AT 600° C. (1750X)

(a) At 3000X.

SM-41085

(b) At 300X.

SM-41087

Figure A-23. SCANNING ELECTRON MICROGRAPH OF A STRESS-CORROSION FRACTURE SURFACE OF URANIUM-6 WEIGHT PERCENT NIOBIUM, AGED AT 600° C.

(a) At 1000X.

SM-56156

(b) At 300X.

SM-56157

(c) At 100X.

SM-56158

Figure A-24. SCANNING ELECTRON MICROGRAPH OF A STRESS-CORROSION FRACTURE SURFACE OF AS-QUENCHED URANIUM-6 WEIGHT PERCENT NIOBIUM WITH 1000 ppm ZIRCONIUM.

161424
Figure A-25. SCANNING ELECTRON MICROGRAPHS OF TENSILE-OVERLOAD FRACTURE SURFACES OF URANIUM-8.5 WEIGHT PERCENT NIOBIUM WITH VARYING AMOUNTS OF HYDROGEN. (Circle 1, 0 ppm Hydrogen; Circle 2, 12 ppm Hydrogen; Circle 3, 27 ppm Hydrogen)

(a) At 3000X.

SM-43723

(b) At 1000X.

SM-43724

(c) At 300X.

SM-43725

Figure A-26. SCANNING ELECTRON MICROGRAPH OF TENSILE-OVERLOAD FRACTURE SURFACE OF URANIUM-10 WEIGHT PERCENT NIOBIUM.

(a) At 3000X.

SM-43727

(b) At 1000X.

SM-43728

(c) At 100X.

SM-43730

Figure A-27. SCANNING ELECTRON MICROGRAPH OF A STRESS-CORROSION FRACTURE SURFACE OF URANIUM-10 WEIGHT PERCENT NIOBIUM.

161431
Figure A-28. SCANNING ELECTRON MICROGRAPHS OF TENSILE-OVERLOAD FRACTURE SURFACES OF URANIUM-10 WEIGHT PERCENT NIOBIUM WITH VARYING AMOUNTS OF HYDROGEN. (Circle 1, 0 ppm Hydrogen; Circle 2, 9 ppm Hydrogen; Circle 3, 30 ppm Hydrogen)

(a) At 1000X.

SM-49121

(b) At 300X.

SM-49122

(c) At 100X.

SM-49123

Figure A-29. SCANNING ELECTRON MICROGRAPH OF A STRESS-CORROSION FRACTURE SURFACE OF AS-QUENCHED URANIUM-6 WEIGHT PERCENT MOLYBDENUM.

(a) At 1000X.

SM-49175

(b) At 300X.

SM-49176

(c) At 100X.

SM-49177

Figure A-30. SCANNING ELECTRON MICROGRAPH OF A STRESS-CORROSION FRACTURE SURFACE OF URANIUM-6 WEIGHT PERCENT MOLYBDENUM, AGED AT 400° C.

(a) At 1000X.

SM-49241

(b) At 3000X.

SM-49242

(c) At 100X.

SM-49243

Figure A-31. SCANNING ELECTRON MICROGRAPH OF A STRESS-CORROSION FRACTURE SURFACE OF URANIUM-6 WEIGHT PERCENT MOLYBDENUM, AGED AT 550° C.

Figure A-32. SCANNING ELECTRON MICROGRAPH OF TENSILE-OVERLOAD FRACTURE SURFACE OF URANIUM-8 WEIGHT PERCENT MOLYBDENUM.

Figure A-33. SCANNING ELECTRON MICROGRAPH OF A STRESS-CORROSION FRACTURE SURFACE OF AS-QUENCHED URANIUM-8 WEIGHT PERCENT MOLYBDENUM.

(a) At 1000X.

SM-50347

(b) At 300X.

SM-50348

(c) At 100X.

SM-50349

Figure A-34. SCANNING ELECTRON MICROGRAPH OF A STRESS-CORROSION FRACTURE SURFACE OF URANIUM-8 WEIGHT PERCENT MOLYBDENUM, AGED AT 550° C.

Figure A-35. SCANNING ELECTRON MICROGRAPHS OF TENSILE-OVERLOAD FRACTURE SURFACES OF URANIUM-10 WEIGHT PERCENT MOLYBDENUM WITH VARYING AMOUNTS OF HYDROGEN. (Circle 1, 0 ppm Hydrogen; Circle 2, 6 ppm Hydrogen; Circle 3, 8 ppm Hydrogen)

161429

MS-73-1174-5
Figure A-36. OPTICAL MICROGRAPH OF URANIUM-0.75 WEIGHT PERCENT TITANIUM, AGED AT 400° C. (100X)

(a) At 1000X.

SM-41201

(b) At 300X.

SM-41202

(a) At 3000X.

SM-44648

(b) At 1000X.

SM-44649

(c) At 100X.

SM-41203

(c) At 300X.

SM-44650

Figure A-37. SCANNING ELECTRON MICROGRAPH OF A STRESS-CORROSION FRACTURE SURFACE OF URANIUM-0.75 WEIGHT PERCENT TITANIUM, AGED AT 400° C.

Figure A-38. SCANNING ELECTRON MICROGRAPH OF A STRESS-CORROSION FRACTURE SURFACE OF URANIUM-0.75 WEIGHT PERCENT TITANIUM-0.25 WEIGHT PERCENT VANADIUM, AGED AT 400° C.

(a) At 3000X.

SM-44617

(b) At 1000X.

SM-44618

(c) At 300X.

SM-44619

Figure A-39. SCANNING ELECTRON MICROGRAPH OF A TENSILE-OVER-LOAD FRACTURE SURFACE OF URANIUM-0.75 WEIGHT PERCENT TITANIUM-0.25 WEIGHT PERCENT VANADIUM, AGED AT 400° C.

Distribution**Aerospace Corporation**

Kendall, G.

Air Force Armaments Laboratory

Wilson, L.

Air Force Materials Laboratory

Inouye, S.

Battelle Memorial Institute - Columbus

Meyer, G.

Battelle-Pacific Northwest Laboratories

Kemper, R.

Energy Research and Development**Administration - Oak Ridge**

Hickman, H. D.

Leed, R. E.

Zachry, D. S., Jr

Lawrence Livermore Laboratory

Nelson, W. E.

Robbins, J. L.

Los Alamos Scientific Laboratory

Hockett, J. R.

Hoyt, H. C.

Sandstrom, D.

National Lead of Ohio

Levy, L. M.

Poulsen, C. E.

Oak Ridge Gaseous Diffusion Plant

Stief, S. S.

Wilcox, W. J., Jr

Oak Ridge National Laboratory

Brinkman, C. R.

Cathcart, J. V.

Martin, W. R.

McHargue, C. J.

Vandermeer, R. A.

Weir, J. R., Jr

Oak Ridge Y-12 Plant

Armstrong, R. C.
 Bennett, R. K., Jr (5)
 Bernander, N. K.
 Dodson, W. H.
 Fraser, R. J.
 Jessen, N. C.
 Johnson, D. H.
 Keith, A.
 Koger, J. W. (5)
 Ludwig, R. L.
 Mason, D. L.
 McElroy, B. D.
 Mills, J. M., Jr
 Phillips, L. R.
 Poore, M. W.
 Rowan, J. H.
 Schreyer, J. M.
 Smith, H. F., Jr
 Snyder, W. B.
 Stoner, H. H.
 Yaggi, W. J./Googlin, J. M.
 Y-12 Central Files (5)
 Y-12 Central Files (master copy)
 Y-12 Central Files (route copy)
 Y-12 Central Files (Y-12RC)

Picatinny Arsenal

Hulbert, R.

Rock Island Arsenal

Johnson, L.

Rockwell International - Rocky Flats

Jackson, R. J.
 Wiederecht, D. A.

Sandia - Albuquerque

Davis, M. J.
 Ledman, J. L.
 Magnani, N. J.
 Rohde, R. W.

Sandia - Livermore

Adolphson, D. R.
 Saxton, H. J.

Union Carbide Corporation - New York

Winters, Charles

Union Carbide Corporation - Parma Research Center

Chambers, W. E.

University of Tennessee - College of Engineering

Stansbury, E. E.

US Army Ballistic Research Laboratories

Bloore, E. W.
 Gillich, W.

US Army Materials and Mechanics Research Center

Larsen, F.

US Naval Weapons Laboratory

Crowe, R.
 Fishman, S.