THE INFLUENCE OF STRAIN RATE AND TEMPERATURE
ON THE YIELD AND FRACTURE TOUGHNESS BEHAVIOR
OF SELECTED STEELS FOR AN LMFBR SPENT FUEL
SHIPPING CASK - A LITERATURE ASSESSMENT

H. J. Rack

Prepared by Sandia Laboratories, Albuquerque, New Mexico 87115
and Livermore, California 94550 for the United States Energy Research
and Development Administration under Contract AT (29-1)-789

February 1976

Sandia Laboratories

***When printing a copy of any digitized SAND
Report, you are required to update the
markings to current standards.***

Issued by Sandia Laboratories, operated for the United States Energy
Research and Development Administration by Sandia Corporation.

NOTICE

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Energy Research and Development Administration, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

Printed in the United States of America

Available from

National Technical Information Service

U. S. Department of Commerce

5285 Port Royal Road

Springfield, VA 22151

Price: Printed Copy \$5.00; Microfiche \$2.25

THE INFLUENCE OF STRAIN RATE AND TEMPERATURE ON THE YIELD
AND FRACTURE TOUGHNESS BEHAVIOR OF SELECTED STEELS FOR
AN LMFBR SPENT FUEL SHIPPING CASK - A LITERATURE REVIEW

H. J. Rack
Mechanical Metallurgy Division 5832
Sandia Laboratories
Albuquerque, New Mexico 87115

February 1976

ABSTRACT

The available literature has been reviewed to determine the possible influences of strain rate and temperature on the yield and fracture toughness behavior of selected steels suggested for use in an LMFBR Spent Fuel Shipping Cask. Based on this information, recommendations have been made for further work which is intended to alleviate potential problems prior to their having a major impact on the shipping cask program.

TABLE OF CONTENTS

	<u>Page</u>
INTRODUCTION	7
MATERIALS	7
Strain Rate/Temperature/Yield Behavior	13
Austenite Steels	13
Ferritic Steels	15
Strain Rate/Temperature/Fracture Toughness	17
Crack Initiation	17
Crack Arrest	24
RECOMMENDATIONS	32
Process Parameters	32
Strain Rate/Temperature/Yield Behavior	32
Strain Rate/Temperature/Fracture Toughness	33
REFERENCES	35

LIST OF FIGURES

<u>No.</u>		<u>Page</u>
1	Effect of strain rate on the 538° C tensile properties of type 308 weld metal and type 304 stainless steel base metal (14).	14
2	Yield stress versus elastic strain rate for 4340 fine grain martensite (21).	16
3	Rate-temperature correlation of the yield strength of ASTM A533, grade B, class 1 steel from HSST plate 02 (26).	18
4	Rate-temperature correlation of the yield strength of three ASTM A533-B submerged-arc welds (26).	19
5	Rate-temperature correlation of the yield strength of ASTM A508, class 2 forging (26).	20
6	Rate-temperature correlation of the yield strength of ASTM A516 steel (39).	21
7	8TCT dynamic toughness of ASTM A533 grade B, class 1 steel for rates between $K = 10^4$ and 10^5 MNm ^{-3/2} /sec (28).	22
8	Fracture toughness of ASTM A508 class 4 forging (29).	23
9	Results of fracture-toughness tests at center 20.3 cm of 29.85 cm thick weldment (Submerged Arc Process) of ASTM A533, grade B, class 1 steel plate 29.85 cm thick; static tests; nonirradiated (31).	25
10	Temperature dependence of the weld and heat-affected zone fracture toughness of a 12 in (30.5 cm) thick weldment (Submerged Arc Process) of A533, grade B, class 1 steel plate 12 in (30.5 cm) thick; static tests - nonirradiated (31).	26
11	Irradiated and unirradiated fracture toughness as a function of temperature for ASTM A533, grade B, class 1 steel from HSST plate 02. Open data points are plane strain, K_{IC} , and closed are lower bound toughness, K_{IC} (32).	28
12	Increase in the transition temperature of steels resulting from irradiation at temperatures below 450° F (232° C) (33).	29
13	Fracture toughness versus temperature for relatively radiation insensitive ASTM A508, class 2 steel ring forging (31).	30
14	Parametric representation of fracture toughness of selected steels (39).	31

THE INFLUENCE OF STRAIN RATE AND TEMPERATURE ON THE YIELD AND FRACTURE TOUGHNESS BEHAVIOR OF SELECTED STEELS FOR AN LMFBR SPENT FUEL SHIPPING CASK - A LITERATURE REVIEW

INTRODUCTION

The primary purpose of this survey was to assess the present state of knowledge as to the influence of strain rate and temperature on the flow and fracture characteristics of selected steels intended for use in the LMFBR spent fuel shipping cask. The strain rates and temperatures considered were chosen as those typical of cask applications, that is strain rates less than 10^2 /sec and temperatures between -40° and 800° C.[†] Neutron irradiation effects were only considered insofar as they affect mechanical response; a more detailed discussion of their importance will be the subject of future work.

Finally, this literature survey is not intended to be a restatement of all available information, rather it is an evaluation of previous investigations and identifies those areas where, in the author's opinion, present knowledge requires further reinforcement

MATERIALS

Table I lists the chemical compositions of the principal structural materials being considered for the LMFBR shipping cask. These materials may be generally classified as austenitic, martensitic precipitation hardening stainless or ferritic steels. The alloys designated A516, A333, A334, and A350 are quite similar in composition and are supplied, depending upon section size, in either the normalized or quenched and tempered condition. The composition of A508 suggests that it may be susceptible to temper embrittlement^{1,2} if exposed for long times at temperatures between 350° - 550° C. Fortunately, the times involved are in excess of those for the LMFBR spent fuel shipping cask. Tables II through IV provide appropriate product form descriptions and specifications.

[†]The latter temperature should be experienced only under a hypothetical fire associated accident, the normal operating temperature being 290° C.

TABLE I

Chemical Composition of Candidata Materials for LMFBR Spent Fuel Shipment Cask

Alloy Designation	C (max)	Mn (max)	S (max)	Si (max)	Cr	Weight Ni	Percent P (max)	Ti (max)	Cb + Ta (max)	Mo	Se (min)	V (max)
<u>Austenite Steels</u>												
304	0.08	2.0	0.03	1.0	18 - 20	8 - 12	0.045				0.15	
304L	0.03	2.0	0.03	1.0	18 - 20	8 - 12	0.045				0.15	
321	0.08	2.0	0.03	1.0	18 - 20	11 - 15	0.045	0.7				
347	0.08	2.0	0.03	1.0	17 - 19	9 - 13	0.045		1.1			
316	0.08	2.0	0.03	1.0	16 - 18	10 - 14	0.045			2 - 3		
<u>Ferritic</u>												
A508 Cl. 4, 4A	0.23	0.2 - 0.4	0.02	0.3	1.5 - 2	2.75 - 3.9	0.02			0.4 - 0.6		0.03
Cl. 5, 5A	0.23	0.2 - 0.4	0.02	0.3	1.5 - 2	2.75 - 3.9	0.02			0.4 - 0.6		0.08
A533(a)												
Grade A	0.25	1.15 - 1.5	0.04	0.15 - 0.3		0.4 - 0.7	0.035			0.45 - 0.6		
B	0.25	1.15 - 1.5	0.04	0.15 - 0.3		0.7 - 1.0	0.035			0.45 - 0.6		
C	0.25	1.15 - 1.5	0.04	0.5 - 0.3		0.2 - 0.3	0.035			0.45 - 0.6		
D	0.25	1.15 - 1.5	0.04	0.1 - 0.3			0.035			0.45 - 0.6		
4140 (A320-L7)	0.38 - 0.48	0.75 - 1.0	0.04	0.2 - 0.35	0.8 - 1.0		0.04			0.15 - 0.2		
4340 (A320-L43)	0.38 - 0.43	0.6 - 0.85	0.04	0.2 - 0.35	0.7 - 0.9	1.652.0	0.04			0.2 - 0.3		
A516 Gr. 55	0.18 - .26	0.6 - 1.2	0.04	0.15 - 0.3			0.035					
60	0.21 - 0.27	0.8 - 1.2	0.04	0.15 - 0.3			0.035					
A333 Gr. 1	0.3	0.4 - 1.06	0.06				0.05					
A334 6	0.3	0.29 - 1.06	0.058	0.1 min.			0.048					
A350 Gr. LF1	0.3	1.06	0.05				0.04					
LF2	0.3	1.35	0.05	0.15 - 0.3			0.04					
<u>Martensitic PH Stainless Steel</u>												
17-4PH(b)	0.07	1.0	0.03	1.0	15.5 - 17.5	3.0 - 5.0	0.04			0.15 - 0.45		
(a) Cu < 0.1, P < 0.01 wt. percent is recommended for maximum radiation stability.												
(b) Cu - 3.0 - 5.0 weight percent.												

TABLE II

Plate Materials

<u>Material (Steels)</u>	<u>ASTM Specification and Grade</u>
Austenitic	A240 Types 304, 304L, 321 and 347
Ferritic	A516 Grades 55 and 60 A588 Grade A, B, C

TABLE III

Forgings, Fittings and Bolting Materials

<u>Material (Steels)</u>	<u>ASTM Specification and Grade</u>
Forgings	
Ferritic	A508 Classes 4, 4A, 5 and 5A A350 Grades LF1 and LF2
Austenitic	A182 Types 304, 304L, 321 and 347 A473 Types 304, 304L, 321 and 347
Fittings	
Ferritic	A420 Grade WPL1
Austenitic	A403 Grades WP304, 304L, 321 and 347
Fittings	
Ferritic	A420 Grade WPL1
Austenitic	A403 Grades WP304, 304L, 321 and 347
Bolting	
Ferritic	A320 Grade L7, L43
Austenitic	A193 Types B8, B8C and B8T

TABLE IV

Pipe and Tube Materials

<u>Materials (Steels)</u>	<u>ASTM Specifications and Grade</u>
Pipe	
Ferritic	A333 Grades 1 and 6
Austenitic	A312 Type 304, 304L, 321 and 347
Tube	
Ferritic	A334 Grades 1 and 6
Austenitic	A213 Types 304, 304L, 321 and 347

The two additional materials presented in Table V are the ones currently being considered for LMFBR fuel cladding and primary shipping cask seals, although it should be recognized that both may be subject to change prior to completion of the cask program.

TABLE V

Miscellaneous

<u>Material</u>	<u>Use</u>
17-4PH	Primary Cask Seals
316	Fuel Rod Cladding

Nuclear reactor experience has shown that 304 stainless steel, if improperly processed, may be "sensitized".³ Sensitization results in an increase in the environmental cracking susceptibility of this steel. This susceptibility may be decreased and/or eliminated by either re-solution treatment after fabrication or selecting a stabilized stainless steel, e.g., 347. Other methods of minimizing the problem of stress corrosion cracking include controlling the environment, i.e., eliminating Cl^- and O^{2-} , or maintaining the operative stress levels, including residual welding stresses, below the yield stress.

General corrosion resistance can be obtained by either fabricating the cask from a suitable austenitic stainless steel or by weld-overlay cladding the ferritic base metal. The latter appears to be the optimum approach since it takes advantage

of both carbon steels and stainless steel in the cask design while maintaining a minimum cost. It should be noted, however, that weld-cladding overlay procedures can result in underclad cracks. These cracks tend to be intergranular, about 3 mm in depth and width, and are found in the coarse-grained heat-affected zone of low-alloy steels. Vinckier and Pense⁴ have suggested that the incidence of this cracking can be reduced by using a two-layer cladding technique, controlling welding process variables (e.g., low-heat-input weld processes), or normalizing the heat-affected region prior to post-weld treatment. Alternatively, materials can be selected which do not show the combination of a susceptible microstructure and low creep ductility.

Strain Rate/Temperature/Yield Behavior

Extensive reviews of the strain rate sensitivity of ferrous alloys have been prepared by Hoagland,⁵ Kendall,⁶ Eleiche,⁷ and Soohoo, et al.⁸ In general, the influence of strain rate and temperature on the yield behavior of austenitic and ferritic steels are quite different.

Austenite Steels

The yield behavior of austenitic steels tends to be more rate and temperature insensitive in comparison with that of low strength bcc ferritic steels. Steichen⁹⁻¹⁴ has shown that, while the room temperature yield strength of 304 increases by 48 MN/m² per decade change in strain rate, this alloy, as well as 20% CW 316 and 308 weld metal, is rather insensitive to strain rate changes when test temperatures lie between 315° - 530° C (Fig. 1). Increasing the test temperature to 650° C results in a significant increase in both the strength and tensile ductility with increasing strain rate. There does, however, appear to be some indication of a negative strain rate sensitivity in 304 stainless steel between 200 - 315° C, the temperature range where serrated (jerky) flow is initially observed in austenitic stainless steels.¹⁵⁻¹⁸ Furthermore, the results for 304/308 stainless steel weldments are quite sensitive to specimen location, i.e., residual δ ferrite level. This suggests that close control of weld practice is essential.

The effect of neutron irradiation on the tensile properties of austenitic stainless steel has been extensively investigated. Higgy and Hammond¹⁹ have recently shown that the low temperature (< 100° C) fast neutron ($E > 1$ MeV) radiation induced yield strength increases observed in types 304, 316, and 347 stainless steel

Figure 1. Effect of strain rate on the 538°C tensile properties of type 308 weld metal and type 304 stainless steel base metal (14).

may be described prior to saturation by:

$$\Delta\sigma = C \left[\theta t / 10^{17} \right]^{0.5} \quad (1)$$

where $\Delta\sigma$ is the irradiation associated yield strength increase, θt the total fast neutron dose, and C is a function of the pre-irradiation metallurgical condition. Source analysis of a typical LMFBF shipping cask suggests that, over an anticipated ten-year lifetime, θt will be less than 10^{15} n/cm². If we assume that $C \sim 100 - 140$ MN/m²,¹⁹ then the expected radiation associated yield strength increase will be approximately 14 MN/m², i.e., less than 7 percent of the nominal room temperature yield strength of 304 stainless steel. These same authors note that the yield strength is the most sensitive indicator of low temperature radiation damage, the ultimate tensile strength and tensile ductility both exhibit lower percentage change at equivalent radiation levels. The above observations indicate that the neutron irradiation effects on the primary austenitic steels being considered for the LMFBF shipping cask should be minimal.

Ferritic Steels

As noted above, the strain rate sensitivity of bcc ferrous alloys is quite large when compared to fcc austenitic stainless steel. However, as the absolute yield strength, σ_y , increases, this rate and temperature sensitivity tends to decrease and, when a strength level of 130 ksi (896 MN/n²) is reached, little sensitivity remains.⁵ This suggests that the strain rate sensitivity of 4140, 4340, and 17-4PH should be minimal. Kendall^{20,21} has shown that this assumption appears to be valid for 4140 and 4340 (Fig. 2). However, there is no information available on 17-4PH. Indeed, results on 18 Ni(300) Maraging steel, another precipitation hardening alloy system, indicate a 27.5 MN/m² per decade change in strain rate increase at room temperature and a similar decrease at 315° C.

Some years ago, Bennett and Sinclair²² proposed that the low-temperature yield strength behavior of strain rate sensitive bcc metals might be described by a simple rate equation of the form

$$\sigma = RT \ln(A/\dot{\epsilon}) \quad (2)$$

where σ is the flow stress corrected for loading mode variation, T the absolute temperature, $\dot{\epsilon}$ the strain rate, and A a frequency factor which is generally assigned

Figure 2. Yield stress versus elastic strain rate for 4340 fine grain martensite (21).

a value of 10^8 /sec for iron. Steichen and Williams²³⁻²⁶ have shown that this correlation gives a fairly accurate representation of the yield behavior of A533 B-1, A508, and A516 (Figs. 3-6). Data were not found for the other candidate materials [i.e., A350, A333(334)] which might indicate that their strain rate/temperature sensitivity could be described by Eq. (1). In addition, the influence of rate/temperature on the tensile ductility of the candidate materials is unclear; indeed, our operating conditions, in particular, temperatures, are such that dynamic strain aging and its accompanying decrease in tensile ductility are a strong possibility.²⁷

Strain Rate/Temperature/Fracture Toughness

When the integrity of a structure depends upon the avoidance of catastrophic failure, two alternative design philosophies are available. One is based upon prevention of fracture initiation (i.e., the first extension of an existing flaw) and the other upon the prevention of total crack propagation through the structural members. In the present instance, the latter philosophy involves selecting materials and designs that arrest cracks prior to their penetrating the cask wall. For ferritic steels the toughness in the fully shear (ductile) mode is far greater than that in the cleavage (brittle) mode. Thus, to ensure maximum resistance to propagating cracks, steels should be selected that either do not exhibit a tough/brittle transition (i.e., stainless steel) or do show a fracture mode transition at temperatures well below the anticipated minimum operating temperature. However, it should be noted that under certain conditions, where the stored available energy of the structure is high, even the toughness associated with full shear fracture may not be sufficient to arrest propagating cracks.

Crack Initiation

Fracture toughness evaluation which considers initial crack extension is well established and is based upon linear-elastic and elastic-plastic fracture mechanics wherein crack initiation is described in terms of a critical stress intensity factor. Figs. 7 and 8 illustrate typical results for A533 B-1 and A508 steels; the plane strain fracture toughness, K_{IC} , increases with increasing temperature and decreasing strain rate. This sensitivity to strain rate and temperature again tends to decrease with increasing yield strength.^{29,30} This suggests that the effects of strain rate and temperature on the fracture toughness of 4140, 4340, and 17-4PH may be minimal, at least at low temperatures. In addition, strain rate-temperature effects should also be low in austenitic steels, although this suggestion is rather difficult to assess since no fracture toughness data presently exist for these alloys.

Figure 3. Rate-temperature correlation of the yield strength of ASTM A533, grade B, class 1 steel from HSST plate 02 (26).

Figure 4. Rate-temperature correlation of the yield strength of three ASTM A533-B submerged-arc welds (26).

Figure 5. Rate-temperature correlation of the yield strength of ASTM A508, class 2 forging (26).

Figure 6. Rate-temperature correlation of the yield strength of ASTM A516 steel (39).

Figure 7. 8TCT dynamic toughness of ASTM A533 grade B, class 1 steel for rates between $K = 10^4$ and 10^5 $\text{MNm}^{-3/2}/\text{sec}$ (28).

Figure 8. Fracture toughness of ASTM A508 class 4 forging (29).

It should be recognized that K_{IC} is not uniform through a heavy section, i.e., it decreases with increasing distance below the surface. The latter variation is accentuated when weldments are considered. Although the fracture toughness of A533 weldments is generally higher than that of base metal, Fig. 9, there is a large amount of scatter between data taken from different weldments, Fig. 10. This is particularly true at low test temperature.

The fracture toughness of A533 may also be seriously degraded by irradiation Fig. 1. The extent of this damage depends upon both irradiation temperature and fluence, Fig. 12 and Table VI. Recent investigations^{33,36,37} indicate that the radiation sensitivity of A533 B-1 can be virtually eliminated by controlling the residual, impurity content. Limiting Cu to less than 0.1 wt% and P to less than 0.01 wt% appears to be both feasible in production and has been found to minimize the radiation effects noted above. Interestingly, irradiation damage in A508 does not seem to be as severe as in A533 (compare Figs. 11 and 13).

Attempts to consider the strain rate and temperature sensitivity of K_{IC} in A333(334) and A350 were unsuccessful, no data base exists for these materials. Initial impressions were that these materials, which are essentially Fe-C-Mn alloys, will be quite similar to A516 and would therefore be more sensitive to strain rate and temperature change than either A508 or A533.

Finally, Corten and Shoemaker³⁸ have suggested that the previously proposed parametric representation of the flow characteristics of bcc metals can give an adequate description of the influence of temperature and strain rate of K_{IC} . James³⁹ has applied this technique to a rather limited temperature and strain rate regime in A516 Grade 60 and 70, Fig. 14, where the agreement appears quite good. Since the strain rate temperature conditions considered by James are far removed from those anticipated in the LMFBR spent fuel shipping cask, the general validity of this parametric representation for our present purposes cannot be assessed, although it does appear promising.

Crack Arrest

The consideration of alternative fracture toughness analysis, wherein the principal criteria involves crack propagation and arrest, is hampered by the absence of general mathematical formulations for running cracks which take into account the inertial and dynamic effects for various structural geometries.⁴⁰ However, some investigators⁴¹⁻⁴⁹ have suggested that a stress intensity factor does exist below

Figure 9. Results of fracture-toughness tests at center 20.3 cm of 29.85 cm thick weldment (Submerged Arc Process) of ASTM A533, grade B, class 1 steel plate 29.85 cm thick; static tests; nonirradiated (31).

Figure 10. Temperature dependence of the weld and heat-affected zone fracture toughness of a 12 in (30.5 cm) thick weldment (Submerged Arc Process) of A533, grade B, class 1 steel plate 12 in (30.5 cm) thick; static tests - nonirradiated (31).

TABLE VI

Effect of Irradiation on Room-Temperature Tensile Properties of A302-B Steel⁽³⁵⁾

<u>Number of Specimens</u>	<u>Irradiation Temperature (°C)</u>	<u>Exposure 10^{19} n/cm² (> 1 MeV)</u>	<u>0.2% Yield Strength (MN/m²)</u>	<u>Tensile Strength (MN/m²)</u>	<u>Hardness Rockwell B</u>	<u>Elongation (%)</u>	<u>Reduction In Area (%)</u>	<u>True Strain at Load</u>
10	-	0	492	652	-	28.0	64.0	0.12
1	116	2.0	791	805	103	11.3	52.6	--
2	116	2.3	829	830	-	--	50.0	<0.02
2	121	2.2	782	796	103	--	46.0	0.02
2	121	7.0	818	818	102	3.0	--	<0.02
2	93	9.6	925	927	--	--	45.0	<0.02
2	316	to 5.7	686	793	103	--	47.0	0.12

Figure 11. Irradiated and unirradiated fracture toughness as a function of temperature for ASTM A533, grade B, class 1 steel from HSST plate 02. Open data points are plane strain, K_{IC} , and closed are lower bound toughness, K_{IC1} (32).

Figure 12. Increase in the transition temperature of steels resulting from irradiation at temperatures below 450° F (232° C) (33).

Figure 13. Fracture toughness versus temperature for relatively radiation insensitive ASTM A508, class 2 steel ring forging (31).

Figure 14. Parametric representation of fracture toughness of selected steels (39).

which a crack will not propagate (Hahn, et al.)^{30,46-48} concluded that this arrest factor, K_a , is not a material property but depends upon the entire history of crack propagation. If true, the entire philosophy of using K_a as a design criteria is, in the reviewer's opinion, in doubt. Until this question is answered, particularly by a combined materials/stress analysis effort, the most logical approach to designing against catastrophic crack propagation, i.e., assuring that the crack will arrest prior to penetrating the cask wall, should rest upon Pellini's FAD procedures.⁵⁰⁻⁵¹

RECOMMENDATIONS

Listed below are the reviewer's recommendations for cask baseline materials. In addition, those areas are presented which will require further evaluation and which may have an impact on cask safety and design.

Baseline Materials

<u>Use</u>	<u>Baseline</u>
Plate	A533 B1 Clad with 304L Cu < 0.1 wt. pct. P < 0.01 wt. pct.
Forging	A508 Class 4 Clad with 304L
Fittings	A403 Grade WP304
Bolting	A193 Type B8
Pipe	A312 Type 304L
Tube	A213 Type 304L

Process Parameters

1. Examine what influence variations in chemistry within allowable A533 and A508 specifications have on underclad cracking.
2. Examine the possible relationship between temper embrittlement and unclad cracking in A508.
3. Establish appropriate welding/fabrication practices for sub-scale and full-scale cask production.

Strain Rate/Temperature/Yield Behavior

1. Establish the strain rate sensitivity of candidate austenitic steels within temperature and irradiation conditions of interest to LMFBR fuel shipment cask.

2. Establish effect of varying δ ferrite content on strain rate and irradiation sensitivity of austenitic stainless steel weldments.
3. Establish influence of strain rate and temperature sensitivity on yield strength behavior of 17-4PH.
4. Confirm adequacy of Bennett-Sinclair relationship for describing the strain rate temperature sensitivity of low strength ferritic (bcc) steels.
5. Examine the extent of ductility loss as a function of strain rate and temperature in candidate casks ferritic steels, particular attention being paid to the temperature regime where dynamic strain aging is expected.

Strain Rate/Temperature/Fracture Toughness

1. Confirm the validity of the Corten-Shoemaker parametric representation for K_{IC} within the temperature range of interest.
2. Examine the influence of strain rate and temperature on the fracture toughness of 17-4PH and austenitic stainless steels.
3. Establish the underlying causes for the large scatter observed in heavy section weldments and develop methods for minimizing these effects.
4. Maintain an awareness of the present crack arrest programs, reviewing their impact upon the IMFBR spent fuel shipment cask at regular intervals.

REFERENCES

1. Temper Embrittlement in Steel, ASTM STP 407, American Society for Testing Materials, New York, N. Y., October 1967.
2. Temper Embrittlement of Alloy Steels, ASTM STP 499, American Society for Testing Materials, New York, N. Y., June 1971.
3. H. H. Uhlig, Corrosion and Corrosion Control, 2nd Ed., J. Wiley and Sons, New York, N. Y., 1971.
4. A. G. Vinckier and A. W. Pense, A Review of Unclad Cracking in Pressure-Vessel Components, WRC Bulletin #197, Welding Research Council, New York, N. Y., August 1974.
5. R. G. Hoagland, Effect of Strain Rate on Mechanical Properties of Austenitic Stainless Steels, BNWL Report #1105, Battelle-Northwest Pacific Northwest Laboratory, Richland, Washington, September 1969.
6. D. P. Kendall, Survey and Critical Review of Dynamic Mechanical Properties of Metals, WVT-TR-74034, Watervliet Arsenal, Benet Laboratories, New York, N. Y., July 1974.
7. A. M. Eleiche, A Literature Survey of the Combined Effects of Strain Rate and Elevated Temperature on the Mechanical Properties of Metals, AFML-TR-72-125, Air Force Materials Laboratory, Wright-Patterson AFB, Ohio, September 1972.
8. P. Soohoo, C. W. Jiang, and M. M. Chen, Dynamic Properties of Materials, Part III. Steels, AMMRC-CTR-74-24, Army Materials and Mechanics Research Center, Watertown, Massachusetts, April 1974.
9. J. M. Stiechen, High Strain Rate Mechanical Properties of Types 304 and 316 Stainless Steel, HEDL-TME-71-164, Hanford Engineering Development Laboratory, Richland, Washington, November 1971.
10. J. M. Steichen, High Strain Rate Mechanical Properties of Type 304 Stainless Steel and Nickel 200 (RM-14), HEDL-TME-71-147, Hanford Engineering Development Laboratory, Richland, Washington, September 1971.
11. J. M. Steichen, Effect of Thermal Aging on the High Strain Rate Tensile Properties of Type 304 Stainless Steel, HEDL-TME-74-38, Hanford Engineering Development Laboratory, Richland, Washington, July 1974.
12. J. M. Steichen, Effect of Strain Rate and Temperature on the Tensile Properties of Type 308 SMA Weld Metal, HEDL-SA-648, Hanford Engineering Development Laboratory, Richland, Washington, August 1973.
13. J. M. Steichen, "High Strain Rate Properties of AISI Type 304 Stainless Steel," J. Eng. Mat. Tech. 1, 182 (1973).

14. J. M. Steichen and A. L. Ward, "High Strain Rate Tensile Properties of Type 308 SMA Weld Metal," Welding Journal Research Supplement 54, 1308 (1975).
15. C. F. Jenkins and G. V. Smith, "Serrated Plastic Flow in Austenitic Stainless Steel," Trans. AIME 245, 2149 (1969).
16. K. S. B. Rose and S. G. Glover, "A Study of Strain-Aging in Austenite," Acta Met. 14, 1505 (1966).
17. E. Dalder, Flow and Fracture of Type 304 Austenitic Stainless Steel Bar and Weldments, PhD Thesis, Ohio State University, 1973.
18. D. Hauser, Effect of Temperature and Strain Rate on Plastic Instability of Type 316 Stainless Steel, PhD Thesis, Ohio State University, 1973.
19. H. R. Higgy and F. R. Hammond, "Effect of Fast-Neutron Irradiation on Mechanical Properties of Stainless Steels: AISI Types 304, 316 and 347," J. Nucl. Mat. 55, 177 (1975).
20. D. P. Kendall and T. E. Davidson, "The Effect of Strain Rate on Yielding in High Strength Steels," J. Basic Engineering 88, 37 (1966).
21. D. P. Kendall, "The Effect of Strain Rate and Temperature on Yielding in Steels," J. Basic Eng. 93, 207 (1972).
22. P. E. Bennett and G. M. Sinclair, "Parameter Representation of Low-Temperature Yield Behavior of Body-Centered Cubic Transition Metals," J. Basic Eng. 88, 518 (1966).
23. J. M. Steichen and J. A. Williams, Heavy Section Steel Technology Program Technical Report No. 32, High Strain Rate Tensile Properties of Irradiated ASTM A533, Grade B, Class 1 Pressure Vessel Steel, HEDL-TME-73-74, Hanford Engineering Development Laboratory, Richland, Washington, July 1973.
24. J. A. Williams and J. M. Steichen, Effect of Strain Rate on Tensile Behavior of Irradiated ASTM A533, Grade B, Class 1 Steel, HSST Semiannual Progress Report, ORNL-4971, Oak Ridge National Laboratory, Oak Ridge, Tennessee, August 31, 1973, pp. 37-64.
25. J. A. Williams, Effect of Strain Rate on Tensile Behavior of ASTM A533B, HSST Semiannual Prog. Rep., ORNL-4816, Oak Ridge National Laboratory, Oak Ridge, Tennessee, February 29, 1972, pp. 66-68.
26. J. A. Williams, Characterization of Tensile Properties of Pressure Vessel Steels and Rate-Temperature Correlations of Yield Strength, ORNL-TM-4805 (Vol. II), Oak Ridge National Laboratory, Oak Ridge, Tennessee, March 1975.
27. J. D. Baird, "The Effects of Strain-Aging Due to Interstitial Solutes on the Mechanical Properties of Metals," Met. Reviews 16, 1 (1971).
28. W. O. Shabbits, Dynamic Fracture Toughness Properties of Heavy Section A533 Grade B Class 1 Steel Plate, WCAP-7623, Westinghouse Electric Corp., Commercial Atomic Power, Pittsburgh, Pennsylvania, December 1970.

29. A. K. Shoemaker and S. T. Rolfe, "The Static and Dynamic Low-Temperature Crack-Toughness Performance of Seven Structural Steels," Eng. Fract. Mech. 2, 319 (1971).
30. G. T. Hahn, R. G. Hoagland, and A. R. Rosenfield, Influence of Metallurgical Factors on the Fast Fracture Energy Absorption Rates, AROD-9538, Army Research Office, Durham, N. C., July 1974.
31. D. J. Seman, G. P. Kallenberg, and R. J. Towner, Fracture Toughness of Low-Strength Steels, WAPD-TM-895, Westinghouse Electric Corp., Bettis Atomic Power Laboratory, Pittsburgh, Pennsylvania, May 1971.
32. J. A. Williams, The Irradiation and Temperature Dependence of Tensile and Fracture Properties of ASTM A533 Grade B Class 1 Steel Plate and Weldment, HEDL-TM-73-75, Hanford Engineering Development Laboratory, Richland, Washington, August 1973.
33. L. E. Steele, The Influence of Composition on the Fracture Toughness of Commercial Nuclear Vessel Welds, NRL-7095, Naval Research Laboratory, Washington, D. C., March 1970.
34. R. H. Stearne, Jr., and L. E. Steele, "Steels for Commercial Nuclear Power Reactor Pressure Vessels," Nuclear Engineering and Design 10, 259 (1969).
35. E. P. Klier, J. R. Hawthorne, and L. E. Steele, The Tensile Properties of Selected Steels for Use in Nuclear Reactor Pressure Vessels, NRL-6649, Naval Research Laboratory, Washington, D. C., December 1967.
36. J. R. Hawthorne, "Contributions of Selected Residual Elements to the Radiation Embrittlement Sensitivity of Steel Forgings," J. Testing and Evaluation 1, 439 (1973).
37. Effects of Radiation on Substructure and Mechanical Properties of Metals and Alloys, ASTM STP 529, American Society for Testing Materials, New York, N. Y., June 1972.
38. H. T. Corten and A. K. Shoemaker, "Fracture Toughness of Structural Steels as a Function of the Rate Parameter $T \ln A/\dot{\epsilon}$," J. Basic Eng. 89, 86 (1967).
39. L. A. James, "Fracture Toughness of A516 Grade 60 Steel," Welding Research Supp. 51, 506S (1972).
40. J. I. Bluhm, Fracture Arrest, in Fracture, An Advanced Treatise, Ed. H. Liebowitz, Vol. V, Academic Press, New York, 1969, p. 1.
41. E. J. Ripling and P. B. Crosley, "Strain Rate and Crack Arrest Studies," Paper #9, Fifth Annual Heavy Section Steel Technology Institute Meeting, March 1971.
42. P. B. Crosley and E. J. Ripling, Crack Arrest in an Increasing K-Field, HSSTP-TR-27, Oak Ridge National Laboratory, Oak Ridge, Tennessee, January 1973.

43. P. B. Crosley and E. J. Ripling, Crack Arrest Fracture Toughness of A533 Grade B Class 1 Pressure Vessel Steel, HSSTP-TR-8, Oak Ridge National Laboratory, Oak Ridge, Tennessee, March 1970.
44. P. B. Crosley and E. J. Ripling, "Dynamic Fracture Toughness of A533 Steel," J. Basic Eng. 91, 525 (1969).
45. R. C. Shah, Exploratory Investigation of Rapid Crack Propagation and Crack Arrest, AFFDL-TR-73-95, Air Force Flight Dynamics Laboratory, Wright-Patterson AFB, Ohio, August 1973.
46. G. T. Hahn, R. G. Hoagland, M. F. Kanninen, and A. R. Rosenfield, "A Preliminary Study of Fast Fracture and Arrest in the DCB Test Specimen," Proc. Int. Conf. on Dynamic Crack Prop., Noordhoff Int. Pub. 1, Leyden, Netherlands, 1973, p. 649.
47. G. T. Hahn, R. G. Hoagland, P. N. Mincer, and A. R. Rosenfield, Crack Propagation and Arrest in Ship and Other Steels, SSC-219, Ship Structures Committee, U. S. Navy, Battelle Memorial Institute, Columbus, Ohio, August 1971.
48. G. T. Hahn, R. G. Hoagland, M. F. Kanninen, A. R. Rosenfield, and R. Sejnoha, Fast Fracture Resistance and Crack Arrest in Structural Steels, SSC-242, Ship Structures Committee, U. S. Navy, Battelle Memorial Institute, Columbus, Ohio, June 1973.
49. I. Gray and A. H. Priest, "The Arrest of Propagating Cracks," Proc. Inst. Mech. Eng., May 1971.
50. W. S. Pellini, Design Options for Selection of Fracture Control Procedures in the Modernization of Codes, Rules and Standards, WRC Bulletin #186, Welding Research Council, New York, N. Y., August 1973, p. 1.
51. W. S. Pellini, Analytical Design Procedures for Metals of Elastic-Plastic and Plastic Fracture Properties, WRC Bulletin #186, Welding Research Council, New York, N. Y., August 1973, p. 17.

DISTRIBUTION:

TID-4500 - UC-79c (211 copies)

Division of Reactor Development and Demonstration

U.S. Energy Research
and Development Administration

Washington, DC 20545

Attn: F. A. Nemzek, Director, Reactor Development and Demonstration (1)
Stanley Ahrends, Deputy Director for Projects (1)
G. W. Cunningham, Deputy Director for Technology (1)
G. W. Cunningham, Actg. Assistant Director for Technology (1)
Keith Magnus, Chief, Fuel Reprocessing Branch (2)

Environmental Control Technology

U.S. Energy Research
and Development Administration

Washington, DC 20545

Attn: W. A. Brobst (1)
W. S. Holman (1)
J. A. Sisler (1)

U.S. Nuclear Regulatory Commission

Washington, DC 20555

Attn: W. F. Anderson (1)
C. R. Chappell (1)
W. Lahe (1)
C. B. MacDonald (1)
D. A. Nussbaumer (1)
R. C. Shieh (1)

L. D. Williams

Battelle Pacific Northwest Laboratories

P.O. Box 999

Richland, WA 99352

Battelle Columbus Laboratories

505 King Avenue

Columbus, OH 43201

Attn: S. J. Basham (1)
E. C. Lusk (1)
R. A. Robinson (1)

C. B. Quinn

U.S. Energy Research

and Development Administration

Albuquerque Operations Office

Albuquerque, NM 87115

C. E. Klotz, Manager

Breeder Reactor Evaluation Office

Argonne National Laboratory

9700 South Cass Avenue

Argonne, IL 60439

Oak Ridge National Laboratory
P.O. Box X
Oak Ridge, TN 37830
Attn: J. H. Evans (1)
L. B. Shappert (1)
R. Swindeman (1)

R. J. Donham
Group WX-8
Los Alamos Scientific Laboratory
Los Alamos, NM 87544

F. J. Tokarz
Engineering Mechanics Section
Mail Stop L-90
Livermore Lawrence Laboratory
Livermore, CA 74550

Westinghouse Electric Corporation
P.O. Box W
Oak Ridge, TN 37830
Attn: G. G. Ritter (1)
W. G. Rowan (1)
K. E. Rutenber (1)

S. G. Harbison
Aerojet Manufacturing Co.
601 S. Placentia Avenue
Fullerton, CA 92631

J. W. Langhaar
Atomic Energy Division
E. I. du Pont de Nemours & Co.
700 Wilmington Trust Building
Wilmington, DE 19898

W. H. Brinkman
Stearns-Roger, Inc.
P.O. Box 5888
Denver, CO 80217

C. Williams
N L Industries
Foot of West Street
Wilmington, DE 19801

G. R. Waymire
Exxon Nuclear Co., Inc.
777 106th Avenue, N.E.
Bellevue, WA 98004

W. R. Milne
The Boeing Company
P.O. Box 3707, MS 45-59
Seattle, WA 98124

W. T. Morgan
Program Manager, CRBRP
Atomics International
P.O. Box 309
Canoga Park, CA 91304

Electric Power Research Institute
P.O. Box 10412
Palo Alto, CA 94304
Attn: C. Chan (1)
M. Levenson (1)
R. K. Winkleblack (1)

Allied-General Nuclear Services
P.O. Box 847
Barnwell, NC 29812
Attn: R. E. Best (1)
R. W. Peterson (1)

K. H. Dufrane
Nuclear Fuel Services, Inc.
P.O. Box 124
West Valley, NY 14171

K. Goldmann
Transnuclear, Inc.
One North Broadway
White Plains, NY 10601

FFTF Project Office
Assistant Director
Engineering Technology Fuels
U.S. Energy Research and
Development Administration
P.O. Box 550
Richland, WA 99352

C. L. Boyd
Manager, Fuel Handling
Hanford Engineering Development Laboratory
P.O. Box 1970
Richland, WA 99352

J. L. Ridihalgh, President
Ridihalgh & Associates
2112 Iuka Avenue
Columbus, OH 43201

R. E. Best
Nuclear Assurance Corporation
24 Executive Park West
Atlanta, GA 30329

1200	W. A. Gardner
1280	T. B. Lane
1281	S. W. Key
1281	O. L. Burchett
1282	T. G. Priddy
1283	H. C. Hardee
1283	W. P. Schimmel

1284 R. T. Othmer
 1284 W. A. Von Rieseemann
 1284 L. I. Weingarten
 5000 A. Narath
 5100 J. K. Galt
 5200 E. H. Beckner
 5430 M. Cowan
 5231 J. H. Renken
 5231 S. A. Dupree
 5233 M. J. Forrestal
 5400 A. W. Snyder
 5410 D. J. McCloskey
 5420 J. V. Walker
 5430 R. M. Jefferson
 5431 R. E. Nickell
 5431 R. B. Pope
 5431 J. M. Freedman (5)
 5432 J. K. Cole
 5440 H. D. Sivinski
 5700 J. H. Scott
 5800 R. S. Claassen
 Attn: R. G. Kepler, 5810
 R. L. Schwoebel, 5820
 5830 M. J. Davis
 Attn: N. J. Magnani, 5831
 J. L. Ledman, 5833
 D. M. Mattox, 5834
 5832 R. W. Rohde
 5832 J. P. Hickerson
 5832 H. J. Rack (10)
 5832 J. A. Van Den Avyle
 5840 D. M. Schuster
 5847 C. H. Karnes
 9351 D. W. Ballard
 9352 O. J. Burchett
 8266 E. A. Aas (2)
 3141 C. A. Pepmuelier (5)
 3151 W. L. Garner (3)
 for ERDA/TIC
 3171-1 R. P. Campbell
 ERDA/TIC (25)